U.PORTO

FEUP FACULDADE DE ENGENHARIA
UNIVERSIDADE DO PORTO

PhD Thesis

Towards Data-driven Multi-scale Optimization of Thermoplastic Blends: Microstructural Generation, Constitutive Development and Clustering-based Reduced-Order Modeling

Author:
Bernardo Proença Ferreira

Advisor:
Dr. Francisco Manuel Andrade Pires

Co-Advisor:
Dr. Miguel Aníbal Bessa

Document submitted in partial fulfilment of the requirements
for the degree of Doctor of Philosophy in
Mechanical Engineering

Porto, December 2022

CM2S | Computational Multi-Scale Modeling of Solids and Structures

Institutional support

inegi driving science & innovation

Funding

FCT Fundação para a Ciência e a Tecnologia

REPÚBLICA PORTUGUESA | CIÊNCIA, TECNOLOGIA E ENSINO SUPERIOR

NORTE2020 PROGRAMA OPERACIONAL REGIONAL DO NORTE

PORTUGAL 2020

UNIÃO EUROPEIA Fundo Social Europeu

Supported by the Portuguese Science and Technology Foundation (FCT) under scholarships SFRH/BD/130593/2017 and COVID/BD/152397/2022

Dedicado aos meus pais,
Dídia e João,

à minha avó,
Odete,

e à minha melhor amiga,
Sofia

Page intentionally left blank

Abstract

Title: Towards Data-driven Multi-scale Optimization of Thermoplastic Blends: Microstructural Generation, Constitutive Development and Clustering-Based Reduced-Order Modeling

Keywords: Multi-scale modeling; Computational homogenization; Reduced-order modeling; Cluster analysis; Microstructure generation; Amorphous thermoplastics; Polymer blends; Constitutive modeling; Data-driven design

The present thesis addresses several challenges arising in the development of a state-of-the-art Integrated Computational Materials Engineering (ICME) framework to design and optimize amorphous thermoplastic blends exhibiting a particulate morphology. Without any loss in generality, particular focus is given to PC/ABS, one of the most successful commercial polymer blends composed of Acrylonitrile-Butadiene-Styrene (ABS) particles embedded in a polycarbonate (PC) matrix. Given the high dimensional engineering design space associated with this class of advanced materials, the recent data-driven material design paradigm arises as a promising tool to find optimum process-structure-property-performance bridges. However, unlocking the true potential of such a framework in terms of actual engineering applicability demands the development of powerful computational methodologies – this is the main driving force of the research endeavor put forth in the present thesis.

A new computational generation method for particle-reinforced materials, coined AMINO (Adaptive Multi-temperature Isokinetic Method), is proposed in a framework of time-driven molecular dynamics. Besides the suitable handling of the intersections between particles through a coupled cell-Verlet list method, AMINO's high efficiency stems from an adaptive (explicit) time integration scheme and a multi-temperature isokinetic thermostat that accelerate the convergence towards a legal configuration. Extensive numerical applications and comparisons with real micrographs demonstrate that AMINO can generate high-fidelity periodic representative volume elements (RVEs) under a broad spectrum of microstructure descriptors.

The recent clustering-based reduced-order modeling framework based on a Lippmann-Schwinger integral equilibrium formulation is thoroughly derived under both infinitesimal and finite strains, and adopted to perform a fast computational homogenization of high-fidelity RVEs. Clustering adaptivity is introduced for the first time in such a framework, enhancing the accuracy of clustering-based reduced-order models (CROMs) by unlocking a dynamic clustering in the prediction stage. A novel adaptive CROM coined Adaptive Self-Consistent Clustering Analysis (ASCA) is shown to accurately capture highly localized plasticity in a particle-reinforced composite while keeping high efficiency. A new finite strain extension of the Self-Consistent Clustering Analysis (SCA) CROM compatible with the multiplicative nature of the deformation gradient is also proposed, being an accurate and robust self-consistent scheme still under investigation.

A visco-elastic-visco-plastic constitutive model is formulated to describe the finite strain nonlinear behavior of amorphous thermoplastics. The constitutive formulation is presented within the framework of thermodynamics of irreversible processes, a highly efficient, fully implicit computational implementation is thoroughly derived, and a two-stage optimization-based calibration procedure is proposed. An excellent agreement between the constitutive model predictions and experimental results is obtained at different temperatures and strain rates for PC, being the distinct stages of the highly nonlinear finite deformation accurately captured. The new model is extended to account for the phenomenon of rubber particle internal cavitation, which plays a major role in the behavior of rubber-toughened amorphous thermoplastics such as ABS.

Page intentionally left blank

Sumário

Título: Avanços em Otimização Multi-escala de Misturas Termoplásticas baseadas em Dados: Geração de Microstruturas, Desenvolvimento Constitutivo e Modelação de Ordem Reduzida baseada em Clustering

Palavras-chave: Modelação Multi-escala, Homogeneização computacional, Modelação de ordem reduzida, Análise de clusters, Geração de microstruturas, Termoplásticos amorfos, Misturas poliméricas, Modelação constitutiva, Design baseado em dados

A presente tese endereça vários desafios que surgem no desenvolvimento de um paradigma de Integrated Computational Materials Engineering (ICME) para desenhar e otimizar misturas de termoplásticos amorfos com morfologia particulada. Sem perda de generalidade, é dado particular foco à PC/ABS, uma das misturas poliméricas comerciais de maior sucesso, composta por partículas de Acrilonitril-Butadieno-Estireno (ABS) embebidas numa matriz de policarbonato (PC). Dado a alta dimensionalidade do espaço de variáveis de engenharia associado a esta classe de materiais, o recente paradigma de desenho de materiais baseado em dados surge como uma ferramenta promissora para identificar relações ótimas de processo-estrutura-propriedade-desempenho. Desbloquear o potencial deste paradigma em termos de aplicabilidade exige, contudo, o desenvolvimento de metodologias computacionais poderosas – esta é a principal motivação do trabalho de investigação subjacente a esta tese.

É proposto um novo método de geração computacional para materiais reforçados com partículas chamado AMINO (Adaptive Multi-temperature Isokinetic Method) num enquadramento de dinâmica molecular de evolução temporal. Para além do tratamento de intersecções entre partículas através de um método de listagem acoplado cell-Verlet, a alta eficiência do AMINO provém de uma integração (explícita) adaptativa no tempo e de um termostato isocinético multi-temperatura que aceleram a convergência para uma configuração legal. Diversas aplicações numéricas e comparações com micrografias reais demonstram que o AMINO tem a capacidade de gerar elementos de volume representativos (EVRs) periódicos de alta fidelidade considerando um vasto espetro de descritores microestruturais.

O recente paradigma de modelação de ordem reduzida baseada em clustering e assente numa formulação de equilíbrio de Lippmann-Schwinger é derivado em detalhe no contexto de deformações infinitesimais e finitas, sendo adotado para realizar uma rápida homogeneização computacional de EVRs de alta fidelidade. A adaptividade do clustering é introduzida pela primeira vez neste paradigma, melhorando a precisão de modelos de ordem reduzida baseados em clustering (CROMs) ao permitir um clustering dinâmico durante a etapa preditiva. É demonstrado que um novo CROM chamado Adaptive Self-Consistent Clustering Analysis (ASCA) captura com precisão plasticidade altamente localizada num compósito reforçado com partículas, mantendo uma alta eficiência. É proposta uma nova extensão de deformações finitas do CROM Self-Consistent Clustering Analysis (SCA) compatível com a natureza multiplicativa do gradiente de deformação, estando sob investigação o desenvolvimento de um esquema self-consistent preciso e robusto.

É formulado um novo modelo constitutivo visco-elasto-visco-plástico para descrever o comportamento não-linear de termoplásticos amorfos em deformações finitas. A formulação constitutiva é apresentada num paradigma de termodinâmica de processos irreversíveis, é derivada em detalhe uma implementação computacional implícita e altamente eficiente, e é proposto um procedimento de calibração em duas etapas baseado em otimização. É obtida uma excelente correlação entre as previsões do modelo constitutivo e os resultados experimentais para o PC a diferentes temperaturas e taxas de deformação, sendo as diferentes fases da deformação finita altamente não-linear capturadas com precisão. O novo modelo é expandido de forma a incorporar o fenómeno de cavitação interna de partículas de borracha, um mecanismo central no comportamento de termoplásticos amorfos reforçados com borracha como o ABS.

Page intentionally left blank

Agradecimentos

Em primeiro lugar agradeço ao Professor Francisco Pires pela sua orientação ao longo de toda a minha carreira académica. Em particular, pela oportunidade de iniciar o meu percurso de investigação científica, pela constante disponibilidade de acompanhamento e pelo reconhecimento do trabalho desenvolvido. Um verdadeiro mentor, a nível pessoal e profissional, que me permitiu adquirir um vasto leque de competências fundamentais para o meu futuro profissional. Ao Professor Miguel Bessa agradeço o seu apoio constante, a sua capacidade de inspirar e motivar investigação científica de excelência e também o reconhecimento do meu esforço e dedicação. Acima de tudo agradeço o voto de confiança nas minhas capacidades e a oportunidade única de prosseguir a minha carreira numa instituição de elevado prestígio a nível mundial. Deixo também o meu agradecimento aos Professores José Luís Borges, Luís Guimarães, Pedro Camanho e Renato Natal pelo apoio transmitido ao longo da minha formação na Faculdade de Engenharia da Universidade do Porto.

Em segundo lugar agradeço a todos os colegas de equipa do CM2S, António, Francisca, Igor, José, Miguel, Rodrigo, Rui e Tiago, a sua amizade e companheirismo, a prontidão para ajudar nos momentos mais difíceis e as inúmeras horas de discussões científicas que me desafiam permanentemente a pensar mais e melhor. O seu apoio tornou todo este percurso mais fácil e enriquecedor, para além de permitir atingir objetivos que individualmente seriam inalcançáveis.

Em terceiro lugar um agradecimento aos meus grandes amigos Cláudio, Joel, José, Patrícia e Raquel, pela sua valiosa amizade e confiança. Agradeço também à Mariana, ao Roberto, à Teresa e à Vanessa o seu entusiasmo e apoio às minhas conquistas. À Margarida, um agradecimento especial por todo o apoio, carinho, paciência e partilha ao longo de toda esta aventura.

Em quarto lugar agradeço a toda a minha família que esteve ao meu lado durante este percurso e, sem a qual, não teria capacidade de atingir metas tão ambiciosas. À minha avó Odete, o meu profundo agradecimento por me incentivar a alcançar sempre mais e por me inspirar a ser uma pessoa melhor. Aos meus pais, Dídia e João, e à minha irmã, Beatriz, agradeço o apoio e incentivo incondicionais e o esforço para me proporcionar a vida que tenho hoje sem que nunca me faltasse nada.

Por último, à minha melhor amiga Sofia, um agradecimento especial pela sua amizade tão genuína e por todas as conversas que inspiram uma visão mais completa e crítica do mundo que nos rodeia.

A todos, o meu sincero obrigado.

Bernardo Ferreira

Page intentionally left blank

Contents

Abstract **i**

Sumário **iii**

Agradecimentos **v**

List of Figures **xiii**

List of Tables **xxvii**

Notation **xxxi**

1 Introduction **1**
1.1 Context . . . 1
1.2 Motivation . . . 4
1.2.1 PC/ABS polymer blend . . . 4
1.2.2 Data-driven material design framework . . . 10
1.2.3 Challenges . . . 16
1.3 Contributions . . . 18
1.4 Document structure . . . 21

2 Continuum Mechanics and Multi-scale Modeling **23**
2.1 Preliminaries . . . 23
2.2 Kinematics of deformation . . . 23
2.2.1 Motion . . . 23
2.2.2 Material and spatial descriptions . . . 24
2.2.3 Deformation gradient . . . 24
2.3 Strain tensors . . . 26
2.4 Forces and stress measures . . . 27
2.5 Fundamental conservation principles . . . 28
2.6 Weak equilibrium equations . . . 30
2.7 Mechanical constitutive initial value problem . . . 31
2.7.1 Constitutive axioms . . . 31
2.7.2 Thermodynamics with internal variables . . . 32
2.7.3 Mechanical constitutive initial value problem . . . 34
2.8 Time discretization . . . 36
2.9 Finite Element Method . . . 38
2.9.1 Finite element concept . . . 38
2.9.2 Interpolation functions . . . 39
2.9.3 Interpolation matrix and discrete gradient operators . . . 39
2.9.4 Spatial discretization . . . 40
2.9.5 Newton-Raphson Method . . . 42
2.9.6 Proportional loading . . . 46
2.9.7 Numerical integration . . . 46
2.10 Multi-scale modeling of heterogeneous materials . . . 47
2.11 First-order hierarchical homogenization scheme . . . 53

2.12 Scale Transition Theory . . . 54
2.12.1 Principle of Scales Separation . . . 54
2.12.2 Multi-scale kinematics . . . 55
2.12.3 Principle of Multi-scale Virtual Power . . . 57
2.12.4 Micro-scale boundary conditions . . . 58
2.12.5 Homogenized stress tensor . . . 61
2.13 Time discretization of the micro-scale problem . . . 62
2.14 Numerical solution of the micro-scale problem . . . 63
2.14.1 Spatial discretization . . . 63
2.14.2 Newton-Raphson Method . . . 63
2.14.3 Dependency matrix . . . 66
2.14.4 Homogenized stress tensor . . . 68
2.14.5 Homogenized consistent tangent modulus . . . 68

3 Efficient Microstructure Generation of Particle-Reinforced Materials 71
3.1 Multi-scale modeling of particle-reinforced materials . . . 71
3.2 Microstructure computational generation methods . . . 73
3.2.1 Reconstruction from experimental data . . . 73
3.2.2 Physics-based generation methods . . . 74
3.2.3 Geometrical generation methods . . . 74
3.2.4 Choice of base approach . . . 78
3.3 Particle types and intersections . . . 78
3.3.1 Geometrical parametrization . . . 78
3.3.2 Intersection conditions: detection, length and direction . . . 79
3.4 Adaptive Multi-temperature Isokinetic Method . . . 84
3.4.1 General time-driven molecular dynamics scheme . . . 84
3.4.2 Initial configuration . . . 85
3.4.3 Legal configuration . . . 85
3.4.4 Interaction forces . . . 86
3.4.5 The adaptive time integration scheme . . . 91
3.4.6 Multi-temperature isokinetic thermostat . . . 94
3.4.7 Approximation to the intersection length under a multi-temperature thermostat . . . 101
3.5 Numerical application . . . 101
3.5.1 Formulation assessment . . . 102
3.5.2 Miscellaneous microstructures . . . 111
3.5.3 Statistical analysis . . . 117
3.6 PC/ABS modeling . . . 126
3.6.1 High-fidelity PC/ABS RVEs . . . 126
3.6.2 PC/ABS design space . . . 127
3.7 Conclusions . . . 128

4 Clustering-based Reduced-Order Modeling of Heterogeneous Materials 135
4.1 Clustering-based reduced-order models . . . 135
4.2 The Lippmann-Schwinger integral equation . . . 136
4.2.1 Infinitesimal strains . . . 137
4.2.2 Finite strains . . . 141
4.3 Clustered Lippmann-Schwinger integral equation . . . 144
4.3.1 The concept of material cluster . . . 144
4.3.2 Infinitesimal strains . . . 145
4.3.3 Finite strains . . . 152

4.4 Adaptive clustering-based reduced-order modeling . . . 155
4.4.1 The concept of adaptivity . . . 155
4.4.2 Challenges of clustering adaptivity . . . 156
4.4.3 Nomenclature and fundamental concepts . . . 158
4.4.4 Adaptivity conditions . . . 159
4.4.5 Adaptive Self-consistent Clustering Analysis (ASCA) . . . 160
4.4.6 Adaptive clustering solution rewinding . . . 166
4.4.7 Additional adaptivity procedures . . . 166
4.4.8 Summary of hyperparameters . . . 170
4.5 Numerical application . . . 170
4.5.1 Material characterization and macro-scale loadings . . . 170
4.5.2 Solution methods and error assessment . . . 172
4.5.3 Benchmark analysis . . . 174
4.5.4 Particle-matrix RVE analysis under uniaxial tension . . . 177
4.5.5 Particle-matrix RVE analysis under different loadings . . . 184
4.5.6 Computational cost of updating the cluster interaction matrix . . . 189
4.6 Efficient finite strain FFT-based homogenization . . . 192
4.6.1 FFT-based homogenization offline-stage . . . 192
4.6.2 FFT-based homogenization basic scheme (finite strains) . . . 193
4.6.3 Acceleration through Hadamard operations . . . 195
4.7 Finite strain SCA under multiplicative kinematics . . . 199
4.7.1 Revisiting SCA's offline-stage under finite strains . . . 199
4.7.2 Multiplicative decomposition-based loading incrementation . . . 203
4.7.3 Numerical solution of micro-scale equilibrium problem . . . 204
4.7.4 Macro-scale material response . . . 205
4.8 Numerical application . . . 208
4.8.1 Material characterization and macro-scale loadings . . . 208
4.8.2 Solution methods and error assessment . . . 208
4.8.3 Clustering-based domain decomposition . . . 210
4.8.4 Macro-scale strain loading constraints . . . 211
4.9 Finite strain self-consistent scheme . . . 220
4.10 Conclusions . . . 223

5 CRATE: Clustering-based Nonlinear Analysis of Materials 225
5.1 Open source clustering-based reduced-order modeling . . . 225
5.2 CRATE overview . . . 225
5.3 Computational design and implementation . . . 228
5.3.1 Object-oriented programming . . . 228
5.3.2 Base code structure . . . 229
5.3.3 Clustering adaptivity extension . . . 241
5.4 Future developments . . . 241

6 Constitutive Modeling of Amorphous Thermoplastics 245
6.1 Introduction . . . 245
6.2 Visco-elastic visco-plastic constitutive model . . . 249
6.2.1 Rheological model . . . 249
6.2.2 Kinematics . . . 249
6.2.3 Specific free energy . . . 251
6.2.4 Stress constitutive laws and non-negative dissipation inequality . . . 254
6.2.5 The visco-plastic constitutive formulation . . . 255
6.2.6 Summary . . . 258

6.3 Computational implementation . . . 259
6.3.1 Computational framework . . . 259
6.3.2 Numerical integration scheme . . . 260
6.3.3 Fully implicit elastic predictor/return mapping algorithm . . . 262
6.3.4 State update . . . 263
6.3.5 Consistent tangent modulus . . . 265
6.4 The two-stage optimization-based calibration procedure . . . 267
6.4.1 Motivation . . . 267
6.4.2 Assumptions . . . 267
6.4.3 Optimization-based calibration procedure . . . 268
6.5 Numerical results and discussion . . . 271
6.5.1 Computational setting . . . 271
6.5.2 Case study 1: Isothermal deformation at room temperature and different strain rates . . . 271
6.5.3 Case study 2: Isothermal deformation at different temperatures and strain rates . . . 277
6.6 Accounting for rubber particle internal cavitation . . . 278
6.6.1 Motivation . . . 278
6.6.2 Rubber toughening mechanisms . . . 281
6.6.3 Constitutive extension for porous thermoplastics . . . 284
6.6.4 Summary . . . 289
6.6.5 Remarks on numerical integration scheme . . . 290
6.6.6 Preliminary numerical assessment . . . 291
6.7 Conclusions . . . 291

7 Conclusions and Future Research **295**
7.1 Conclusions and final remarks . . . 295
7.2 Future research and challenges . . . 298

Bibliography **301**

A Notes on Micromechanics **351**
A.1 Introduction . . . 351
A.2 Effective moduli of heterogeneous elastic solids . . . 352
A.2.1 Micro-scale boundary conditions . . . 352
A.2.2 Effective compliance tensor . . . 353
A.2.3 Effective elasticity tensor . . . 355
A.3 Theory of eigenstrains . . . 356
A.3.1 The concept of eigenstrain . . . 356
A.3.2 Eigenstrain problem . . . 356
A.3.3 Equivalent inclusion method . . . 357
A.3.4 Eshelby's solution . . . 359
A.4 Self-Consistent Method . . . 360
A.4.1 Self-Consistent assumption . . . 360
A.4.2 Effective compliance tensor . . . 361
A.4.3 Effective elasticity tensor . . . 361
A.4.4 Equivalence between the effective elastic moduli . . . 362

B FFT-based Homogenization Basic Scheme (Infinitesimal Strains) **363**
B.1 Problem formulation . . . 363
B.2 Spatial discretization . . . 364
B.3 Fixed point iterative solution . . . 365

C Self-Consistent Clustering Analysis (Infinitesimal Strains) 367
C.1 Formulation overview . . . 367
C.2 Step 1: Linear elastic DNS solutions . . . 367
C.3 Step 2: Cluster analysis . . . 369
C.4 Step 3: Cluster interaction tensors . . . 370
C.5 Step 4: Clustered Lippmann-Schwinger equilibrium . . . 372
C.5.1 Micro-scale equilibrium problem . . . 372
C.5.2 Self-consistent scheme . . . 376
C.6 Step 5: Macro-scale material response . . . 380
C.7 Numerical application . . . 381
C.7.1 Material characterization and macro-scale loadings . . . 381
C.7.2 Solution methods and error assessment . . . 383
C.7.3 Clustering-based domain decomposition . . . 385
C.7.4 Macro-scale strain-stress loading constraints . . . 385
C.7.5 Macro-scale strain loading constraints . . . 387

D Compatible FEM regular mesh and element averaging 395
D.1 Generation of compatible FEM regular mesh . . . 395
D.2 Element volumetric field averaging . . . 396

E Overview of Adaptive Finite Element Methods (AFEMs) 397
E.1 Adaptivity, localization and strain softening . . . 397
E.2 Adaptive finite element methodologies . . . 399
E.2.1 Error estimators and indicators . . . 399
E.2.2 Adaptive discretization procedures . . . 403
E.2.3 Remeshing criteria . . . 405

F Hyperelastic-based Constitutive Models through Kinematic Extension 407
F.1 Preliminaries . . . 407
F.2 Hyperelastic-based multiplicative elastoplastic models . . . 408
F.3 General elastic predictor/return-mapping algorithm . . . 409
F.4 Finite strains purely kinematical extension . . . 410
F.5 Coupling with finite strains SCA . . . 411

G Constitutive Model Mathematical Derivations 413
G.1 Time derivative of visco-elastic potential . . . 413
G.2 Constitutive model linearization . . . 414
G.2.1 State update residual derivative . . . 414
G.2.2 Consistent tangent modulus derivatives . . . 414

H Constitutive material properties parametric evaluation 417

Page intentionally left blank

List of Figures

1 Introduction

1.1 Examples of applications where high-performance materials are disruptive: (a) U.S. Air Force Lockheed Martin F-35A Lightning II aircraft (taken from www.f35.com); (b) BMW M5 Competition car model (taken from www.bmw.pt); (c) SpaceX Falcon 9 rocket (taken from www.spacex.com); (d) Intel Core I9-7980x Extreme Edition processor (taken from www.techexplorist.com). 2

1.2 Schematic representation of the ICME framework integrating process-structure-property-performance relationships (horizontal ICME) and multi-scale process-structure and structure-property modeling (vertical ICME). 3

1.3 Examples of PC/ABS applications: (a) Resinex PULSE^{TM} middle console (taken from www.resinex.co.uk); (b) GoPro frame mount (taken from www.gopro.com); (c) 3D printed housing (taken from www.deed3d.com). 4

1.4 Schematic representation of a PC/ABS (70/30) microstructure, evidencing the three phases of the ternary blend. SEM micrograph (PC matrix etched with a NaOH aqueous solution) taken from Greco (1996). 5

1.5 Schematic of the molecular structure of the PC/ABS constituents (molecular conformation is not considered): (a) Bisphenol-A Polycarbonate (PC); (b) Acrylonitrile-Butadiene-Styrene (ABS). 6

1.6 Schematic representation of two different types of PC/ABS morphologies. A particulate structure is shown for PC/ABS (70/30) and a co-continuous lamellar structure for PC/ABS (50/50). TEM micrograph was taken and adapted from Bärwinkel and coworkers (Bärwinkel et al., 2016) (the SAN phase appears as light areas in TEM as also observed by Inberg (Inberg, 2001)). 7

1.7 Schematic of the deformation and damage mechanisms occurring in a PC/ABS blend with particulate morphology. 8

1.8 Schematic of the data-driven computational framework for the design and modeling of materials proposed in Bessa et al. (2017). 12

1.9 Determination of the macroscopic (homogenized) response associated with a given design point through an RVE or multiple SVEs. 15

2 Continuum Mechanics and Multi-scale Modeling

2.1 Motion. 25

2.2 Quasi-static mechanical constitutive initial boundary value problem. 37

2.3 Schematic of the Newton-Raphon Method iterative cycle for a given increment $n+1$ of the equilibrium equation in a problem with one degree of freedom. . . . 45

2.4 Schematic of first-order strain-driven multi-scale model based on computational homogenization. 53

2.5 Schematic of first-order strain-driven hierarchical multi-scale model based on computational homogenization. 54

2.6 Schematic of the Principle of Scales Separation. 55

2.7 Taylor hypothesis. 59

2.8 Micro-scale linear boundary condition. 60

2.9 Micro-scale periodic boundary condition. 61

2.10 Micro-scale uniform traction boundary condition. 61

3 Efficient Microstructure Generation of Particle-Reinforced Materials

3.1 Examples of particle-reinforced composite materials: (a) SEM micrograph of aluminum oxide powder of aluminum based metal matrix composite (taken and adapted from Rahimian et al. (2009)); (b) SEM micrograph of aluminum oxide short-fibers of aluminum based metal matrix composite (taken and adapted from Clyne (2018)); (c) SEM micrograph of short carbon fibers in PES/SCF composite (taken and adapted from Li et al. (2015)); (d) SEM micrograph of PC/ABS(70/30) polymer blend (taken and adapted from Dong et al. (1993)). . . . 72
3.2 Particle types and associated geometrical descriptors admissible in AMINO: (a) 2D (disk, ellipse); (b) 3D (sphere, ellipsoid, cylinder). 79
3.3 Support function of a two-dimensional convex shape $\mathscr{A}$, $h_{\mathscr{A}}: \mathbb{R}^2 \rightarrow \mathbb{R}^2$. 80
3.4 Construction of the Minkowski difference of two convex shapes $\mathscr{A}$ and $\mathscr{B}$ in the two-dimensional space. 80
3.5 Location of the Minkowski difference, $\mathscr{A} - \mathscr{B}$, of two intersecting and non-intersecting convex shapes, $\mathscr{A}$ and $\mathscr{B}$, relative to the origin, $\boldsymbol{o}$. 81
3.6 Diagram of the Gilbert-Johnson-Keerthi algorithm: (a) intersecting shapes, $\mathscr{A}$ and $\mathscr{B}$; (b) non-intersecting shapes, $\mathscr{A}$ and $\mathscr{B}$. 82
3.7 Proposed approximation to the intersection length, $||\tilde{\boldsymbol{\delta}}||$, and direction, $\tilde{\boldsymbol{\delta}}$, between two convex shapes, $\mathscr{A}$ and $\mathscr{B}$. 83
3.8 Coordinate system adopted in the computational generation of: (a) 2D RVE; (b) 3D RVE. 85
3.9 Proposed strategies to improve the quality of the microstructure legal configuration: (a) enforcement of a minimum distance between particles, $\delta_{\min}$; (b) minimization of particles adjacenct to the RVE boundaries. 86
3.10 Interaction forces derived from different types of idealized springs as a function of the distance between two particles' geometrical centers: linear spring ($p = 1$), a linear spring approximating the effect of the 'energy rescaling' scheme proposed in Salnikov et al. (2015) ($p^* = 1$), and a nonlinear spring ($p > 1$). The parameter p is related to the nonlinear interaction force governing law established in Equation (3.3). 87
3.11 Schematic of the cell list method applied in a microstructure containing disks of radius r. 88
3.12 Schematic of the Verlet list method with total update applied in a microstructure containing disks of radius r. 89
3.13 Distance vector, $\boldsymbol{d}_m$, considered for computing the interaction forces between two particles in a periodic microstructure. 90
3.14 Enforcement of microstructure periodicity through a suitable update of the particles' position. 90
3.15 Evolution of the total overlap in a system of n particles, starting with an illegal configuration ($\Psi = \Psi_{\text{init}}$), when employing an isokinetic thermostat for different reference temperatures. 97
3.16 (a) Randomness in general particle-reinforced material resulting from a multi-temperature isokinetic microstructure generation scheme. Spurious features resulting from using a low temperature in constant-temperature microstructure generation scheme: (b) partially ordered configuration; (c) clustered configuration. 97

3.17 Evolution of the total overlap in a system of n-particles, starting with an illegal configuration ($\Psi = \Psi_{\text{init}}$), when employing the proposed multi-temperature isokinetic scheme. 98

3.18 Kinetic energy before velocity rescaling (EK) and after velocity rescaling (EK_{ref}) for a system of ellipsoids oriented along the same direction, with a mean ratio between principal axes equal to 2.5 (high elongation) and volume fraction of 40%: (a) intersection length computed using the proposed approximation; (b) exact intersection length computed through minimization algorithm. 102

3.19 Average CPU time (over 10 realizations of each microstructure) in the generation of a legal configuration ($\Psi_{\text{lim}} = 0$) of: (a) disks with linear interaction forces ($p = 1$); (b) disks with nonlinear interaction forces ($p = 2$). Comparison between the proposed adaptive time integration step and constant integration steps for a different number of particles, n, and volume fractions. Missing data points correspond to unstable simulations or simulations that could not achieve a legal configuration in a maximum of 5000 iterations (particle jamming). 104

3.20 Average CPU time (over 10 realizations of each microstructure) in the generation of a legal configuration ($\Psi_{\text{lim}} = 0$) of: (a) spheres with linear interaction forces ($p = 1$); (b) spheres with nonlinear interaction forces ($p = 2$). Comparison between the proposed adaptive time integration step and constant integration steps for a different number of particles, n, and volume fractions. Missing data points correspond to unstable simulations or simulations that could not achieve a legal configuration in a maximum of 5000 iterations (particle jamming). 105

3.21 Microstructure illegal configuration obtained with the adaptive time integration step after 5000 iterations due to particle jamming: (a) disks (10 particles at 80%); (b) spheres (10 particles at 60%). 105

3.22 Evolution of the total overlap in the generation of a microstructure containing disks at a volume fraction of 50% with: (a) 10 particles; (b) 50 particles; (c) 100 particles; (d) 500 particles. Comparison between the proposed adaptive time integration step and constant integration steps. All the compared microstructures have the same initial configuration. 106

3.23 Average CPU time (over 10 realizations of each microstructure) in the generation of a legal configuration ($\Psi_{\text{lim}} = 0$) of: (a) disks; (b) spheres. Comparison between linear ($p = 1$) and nonlinear ($p = 2$) interaction forces under the proposed adaptive time integration step. Missing data points correspond to simulations that could not achieve a legal configuration in a maximum of 5000 iterations (particle jamming). 107

3.24 Evolution of the total overlap in a system of 50 disks at a volume fraction of 50%, with the reference temperature of the isokinetic scheme and the first temperature stage of the multi-temperature isokinetic scheme equal to (a) $Tk_b = 2.5 \times 10^9$; (b) $Tk_b = 2.5 \times 10^{10}$. IK denotes the isokinetic simulation, MT the multi-temperature simulations and n the number of sign changes in the criterion proposed to lower the temperature as equilibrium is reached. 108

3.25 Evolution of the total overlap in a system of 50 spheres at a volume fraction of 50%, with the reference temperature of the isokinetic scheme and the first temperature stage of the multi-temperature isokinetic scheme equal to (a) $Tk_b = 2.5 \times 10^9$; (b) $Tk_b = 2.5 \times 10^{10}$. IK denotes the isokinetic simulation, MT the multi-temperature simulations and n the number of sign changes in the criterion proposed to lower the temperature as equilibrium is reached. 109

3.26 Average CPU time (over 10 realizations of each microstructure) in the generation of a legal configuration with zero overlap ($\Psi_{\text{lim}} = 0$) of: (a) disks; (b) spheres. Comparison between the proposed multi-temperature isokinetic scheme (MT) and the standard isokinetic scheme (IK) for a different number of particles, n, and volume fractions. Missing data points correspond to simulations that could not achieve a legal configuration in a maximum of 5000 iterations (particle jamming). 110
3.27 Evolution of the total overlap in a system of: (a) 500 disks at 70%; (b) 500 spheres at 50%. Comparison between the proposed multi-temperature scheme (MT) and the isokinetic scheme (IK). All the compared microstructures have the same initial configuration. 111
3.28 Evolution of the total overlap in a system of: (a) 500 disks at 40%; (b) 500 spheres at 20%. Comparison between the proposed multi-temperature scheme (MT) and the isokinetic scheme (IK). All the compared microstructures have the same initial configuration. 112
3.29 Final configurations for microstructures containing 500 disks at a volume fraction of: (a),(e) 30%; (b),(f) 40%; (c),(g) 50%; (d),(h) 60%. Microstructures in the upper row ((a)-(d)) are generated using an isokinetic scheme with a target temperature of $Tk_b = 10^3$, while microstructures in the lower row ((e)-(h)) are generated with the proposed multi-temperature scheme. 112
3.30 Average CPU time (over 20 realizations of each microstructure) in the generation of a legal configuration with zero overlap ($\Psi_{\text{lim}} = 0$) of: (a) disks; (b) spheres. Microstructures are generated through AMINO, accounting for both adaptive time integration step and multi-temperature isokinetic scheme. Missing data points correspond to simulations that could not achieve a legal configuration in a maximum of 5000 iterations (particle jamming). 113
3.31 Samples of microstructures generated through AMINO and containing 100 disks (upper row) and 100 spheres (lower row) at a volume fraction of: (a),(e) 30%; (b),(f) 40%; (c),(g) 50%; (d),(h) 60%. 113
3.32 Examples of 2D microstructures generated through AMINO: (a) 2A; (b) 2B; (c) 2C. Different colors correspond to different material phases. 116
3.33 Examples of 3D microstructures generated through AMINO: (a) 3A; (b) 3B; (c) 3C. Different colors correspond to different material phases. 116
3.34 Comparison between real and computationally generated two-dimensional microstructures through AMINO: (a) Micrograph of a carbon-fiber-reinforced metallic composite taken from Kim et al. (2001); (b)(c) post-process of micrograph using the open-source software ImageJ (Schneider et al., 2012); (d)-(h) computationally generated microstructure. 120
3.35 Statistical comparison between real and computationally generated microstructures (see Figure 3.34): (a) Difference between Ripley's K function and a Poisson point process; (b) Nearest neighbor function; (c) 2-point probability function. R is defined as the mean major semi-axis of the ellipses in the real micrograph. 121
3.36 Comparison between real and computationally generated two-dimensional microstructures through AMINO: (a) Micrograph of a carbon-fiber reinforced metallic composite taken from Kim et al. (2001); (b)(c) post-process of micrograph using the open-source software ImageJ (Schneider et al., 2012); (d)(g) computationally generated microstructures. 123
3.37 3D computationally generated microstructure with four equally-spaced cross-sections matching Figure 3.36: (a) section at $z = 1$; (b) section at $z = 0.8$; (c) section at $z = 0.6$; (d) section at $z = 0.4$. It is assumed that z is the injection molding direction. 124

3.38 Comparison between the 2-point correlation function of the real micrograph and several cross-sections of a three-dimensional computational generated microstructure (see Figure 3.36). R denotes the average length of the largest axis of the elliptical cross-sections in the real micrograph. 125
3.39 PC/ABS high-fidelity RVEs computationally generated through AMINO for different ABS(%) contents exhibiting a particulate morphology: (a) 10%; (b) 20%; (c) 30%; (d) 40%. It is assumed that the injection direction is along the x-axis. . . 130
3.40 Longitudinal cross-sections of PC/ABS high-fidelity RVEs computationally generated through AMINO for different ABS(%) contents exhibiting a particulate morphology: (a) 10%; (b) 20%; (c) 30%; (d) 40%. It is assumed that the injection direction is along the x-axis. 131
3.41 PC/ABS 3D RVEs computationally generated through AMINO for different microstructure descriptors: (a) (10, 20, 1.5); (b) (20, 30, 1.9); (c) (30, 20, 1.5); (d) (40, 40, 2.3). (V, S, R) with V denoting the ABS (%) content, S the RVE's size (μm) and R the ratio between ellipses/ellipsoids major and minor axes. 134

4 Clustering-based Reduced-Order Modeling of Heterogeneous Materials

4.1 Schematic of a material cluster, $\Omega_\mu^{(I)}$, within the micro-scale domain, $\Omega_{\mu,0}$, and the associated uniform assumption for a generic field $\boldsymbol{a}_\mu(\boldsymbol{Y})$. 145
4.2 Geometrical comparison between a finite element (left) and a material cluster (right). 156
4.3 Schematic illustration of a biphasic material (MP1 and MP2), from left to right: Representative volume element (RVE); Spatially discretized RVE in a regular grid of 8×8 voxels; Cluster-reduced representative volume element (CRVE) with 6 material clusters. 159
4.4 Adaptive Self-consistent Clustering Analysis (ASCA) as an ACROM implementation. A complete clustering adaptivity step comprises three fundamental blocks: (A) target clusters selection criterion, (B) adaptive cluster analysis and (C) computation of cluster interaction tensors. 160
4.5 Target clusters selection criterion based on the evaluation of the clustering adaptivity feature's, c_μ, spatial discontinuities along clusters' boundaries, jump(c_μ). Middle plot shows the clustering adaptivity feature's profile for a given row of voxels ($j = 4$) and the associated discontinuities at clusters' boundaries. Targeted clusters are stored together with any data relevant to the following adaptive cluster analysis. 161
4.6 Adaptive cluster analysis of each targeted cluster (parent cluster) into a given number of subclusters (child clusters), $n_{\mathrm{c,child}}$, through cluster subdivision. The adaptive cluster analysis can be performed with any available clustering algorithm. 164
4.7 Computation of the number of child clusters, $n_{\mathrm{c,child}}$, in which a given target cluster is decomposed through the proposed adaptivity split factor, γ_{split}. 164
4.8 Update of the cluster interaction matrix, $\mathbf{T}$, consistent with the clustering adaptivity step. By taking advantage of the cluster interaction tensors cluster-symmetry, only those tensors in the columns associated with the new clusters need to be fully computed. 165
4.9 Schematic of solution rewinding procedure after clustering adaptivity: (a) Solution rewinding main steps, namely (1) storage of rewind state, (2) evaluation of rewind criteria and (3) perform rewind operations; (b) Recovery of clusters state-related variables through a suitable search of clustering adaptivity hierarchy. 167

4.10 Randomized scanning frequency aiming to accelerate the CRVE scanning procedure underlying the target clusters selection criterion based on spatial discontinuities. 168
4.11 Proposed dynamic adaptivity split factor magnitude function. Three behaviors are available: (1) $n = 1.0$ means that the number of child clusters increases linearly with the magnitude associated with the parent cluster, (2) $n \rightarrow +\infty$ promotes an increasing number of child clusters in the high magnitude range (low sensitivity) and (3) $n \rightarrow 0$ raises an increasing number of child clusters from the low magnitude range (high sensitivity). 169
4.12 2D RVE of biphasic material characterized by randomly distributed circular particles ($f = 30\%$) embedded in a matrix ($f = 70\%$), and three SVEs representing different particle spatial arrangements found in the biphasic material RVE. 171
4.13 Simplified fracture criterion assumed for the particle-matrix composite under uniaxial tension loading: fracture occurs when 0.5% of the matrix material phase surpasses an accumulated plastic strain of $\bar{\varepsilon}^p = 0.125$. On the left, the accumulated plastic strain field at fracture predicted with the DNS solution. On the right, a schematic illustration of the fracture propagation and failure of the material's load-bearing capacity. 172
4.14 Uniaxial tension, pure shear and combined uniaxial tension - shear macro-scale strain loading constraints. 172
4.15 Comparison of the clustering-based domain decomposition and local accumulated plastic strain field at the end of the deformation path of Benchmark 1 under uniaxial tension. Colors displayed in the clustering row are associated with different material clusters within each CRVE. 174
4.16 Comparison of the macro-scale homogenized response of Benchmark 1 predicted by different solution methods under uniaxial tension: (a) Homogenized stress; (b) Relative error with respect to the FEM DNS solution. Symbology: clustering adaptivity step (⧫), fracture criterion prediction (★). 176
4.17 Root mean square error (RMSE) of Benchmark 1 micro-scale fields solutions relative to the FEM DNS solution under uniaxial tension: (a) Local accumulated plastic strain field; (b) Local accumulated plastic strain energy density field. Symbology: clustering adaptivity step (⧫). 178
4.18 Evolution of clustering adaptivity related metrics in Benchmark 1 under uniaxial tension: (a) Number of clusters; (b) Relative time of each block of the clustering adaptivity step with respect to the total time spent in clustering adaptivity procedures. 179
4.19 Comparison of the clustering-based domain decomposition and local accumulated plastic strain field at the end of the deformation path of the particle-matrix composite 2D RVE under uniaxial tension. Colors displayed in the clustering row are associated with different material clusters within each CRVE. Symbology: solution rewinding (⟲). 180
4.20 Comparison of the macro-scale homogenized response of the particle-matrix composite 2D RVE predicted by different solution methods under uniaxial tension: (a) Homogenized stress; (b) Relative error with respect to the FEM DNS solution. Symbology: clustering adaptivity step (⧫), fracture criterion prediction (★), solution rewinding (⟲). 181
4.21 Root mean square error (RMSE) of the particle-matrix composite 2D RVE micro-scale fields solutions relative to the FEM DNS solution under uniaxial tension: (a) Local accumulated plastic strain field; (b) Local accumulated plastic strain energy density field. Symbology: clustering adaptivity step (⧫), solution rewinding (⟲). . 182

4.22 Clustering adaptivity of particle-matrix composite 2D RVE (without rewinding) under uniaxial tension: (a) Evolution of the number of clusters; (b) Evolution of the cluster adaptivity framework's blocks computation time relative to the total adaptivity computation time up to a given increment. 183

4.23 Comparison of the clustering-based domain decomposition and local accumulated plastic strain field at the end of the deformation path of the particle-matrix composite 2D RVE under pure shear loading. Colors displayed in the clustering row are associated with different material clusters within each CRVE. Symbology: solution rewinding (↺). 184

4.24 Comparison of the clustering-based domain decomposition and local accumulated plastic strain field at the end of the deformation path of the particle-matrix composite 2D RVE under combined uniaxial tension - shear loading. Colors displayed in the clustering row are associated with different material clusters within each CRVE. Symbology: solution rewinding (↺). 185

4.25 Comparison of the macro-scale homogenized response of the particle-matrix composite 2D RVE under pure shear loading predicted by different solution methods: (a) Homogenized stress; (b) Relative error with respect to the FEM DNS solution. Symbology: clustering adaptivity step (⧫), fracture criterion prediction (★), solution rewinding (↺). 186

4.26 Comparison of the macro-scale homogenized response of the particle-matrix composite 2D RVE under combined uniaxial tension - pure shear loading predicted by different solution methods: (a) Homogenized stress; (b) Relative error with respect to the FEM DNS solution. Symbology: clustering adaptivity step (⧫), fracture criterion prediction (★), solution rewinding (↺). 186

4.27 Root mean square error (RMSE) of the particle-matrix composite 2D RVE micro-scale fields solutions relative to the FEM DNS solution under pure shear loading: (a) Local accumulated plastic strain field; (b) Local accumulated plastic strain energy density field. Symbology: clustering adaptivity step (⧫), solution rewinding (↺). 187

4.28 Root mean square error (RMSE) of the particle-matrix composite 2D RVE micro-scale fields solutions relative to the FEM DNS solution under combined uniaxial tension - shear loading: (a) Local accumulated plastic strain field; (b) Local accumulated plastic strain energy density field. Symbology: clustering adaptivity step (⧫), solution rewinding (↺). 187

4.29 Comparison between the computational cost of the cluster interaction tensors with and without taking advantage of the cluster-symmetry property. Conditions: 2D problem, $n_v = 400 \times 400$, infinitesimal strain formulation with 3 independent strain components. 189

4.30 Computational cost associated with the update of the cluster interaction matrix on a given clustering adaptivity step ($\alpha = 0.75$): (a) Comparison between standard and proposed approaches; (b) Speedup resulting from the proposed approach. Conditions: 2D problem, $n_v = 400 \times 400$, infinitesimal strain formulation with 3 independent strain components. 190

4.31 Computational cost associated with the update of the cluster interaction matrix on a given clustering adaptivity step. Conditions: 2D problem, $n_v = 400 \times 400$, infinitesimal strain formulation with 3 independent strain components. 191

4.32 Comparison between the computational time (s) associated with the naive (discrete loops) and proposed (Hadamard operations) approaches in the finite strain two-dimensional computation of: (a) Green operator; (b) Hyperelastic Saint Venant-Kirchhoff discrete stress field. The computational speedup is defined as the ratio between the computational time of the naive and proposed approaches. 196

4.33 Comparison between the computational time (s) associated with the naive (discrete loops) and proposed (Hadamard operations) approaches in the infinitesimal strains two-dimensional computation of: (a) Green operator; (b) Linear elastic Cauchy discrete stress field. The computational speedup is defined as the ratio between the computational time of the naive and proposed approaches. 198

4.34 Comparison of the norm of the fourth-order local elastic strain concentration tensor between infinitesimal and finite strain for different magnitudes of the imposed orthogonal macro-scale strain loadings. While under infinitesimal strains (isotropic linear elasticity) this tensor remains constant, it depends on the magnitude of the applied loadings under finite strains (isotropic Saint Venant-Kirchhoff hyperelasticity). 203

4.35 2D RVE of biphasic material characterized by randomly distributed circular hyperelastic particles ($f = 30\%$) embedded in a elasto-plastic matrix ($f = 70\%$). . 209

4.36 Uniaxial tension, pure shear, uniaxial compression, combined uniaxial tension - shear and combined uniaxial compression - shear macro-scale strain loading constraints. 210

4.37 Clustering-based domain decomposition (K-means clustering) of the particle-matrix composite RVE for a different number of clusters. The ratio between the number of clusters of the matrix phase ($f = 70\%$) and the particles phase ($f = 30\%$) is set as 2. 211

4.38 Homogenized response of the particle-matrix composite under uniaxial tension strain loading constraints obtained with SCA for a different number of clusters: (a) Homogenized stress; (b) Relative error with respect to the FEM DNS solution. The reference elastic material properties are kept constant throughout the deformation path ($(E^0, \nu^0) = (20\,\text{MPa}, 0.28)$). 212

4.39 Homogenized response of the particle-matrix composite under uniaxial tension strain loading constraint obtained with SCA for different (constant) reference elastic material's Young moduli, $(E^0, \nu^0) = (\Delta, 0.28)$: (a) Homogenized stress; (b) Relative error with respect to the FEM DNS solution. 214

4.40 Homogenized response of the particle-matrix composite under pure shear strain loading constraint obtained with SCA for different (constant) reference elastic material's Young moduli, $(E^0, \nu^0) = (\Delta, 0.28)$: (a) Homogenized stress; (b) Relative error with respect to the FEM DNS solution. 214

4.41 Homogenized response of the particle-matrix composite under uniaxial compression strain loading constraint obtained with SCA for different (constant) reference elastic material's Young moduli, $(E^0, \nu^0) = (\Delta, 0.28)$: (a) Homogenized stress; (b) Relative error with respect to the FEM DNS solution. 215

4.42 Homogenized response of the particle-matrix composite under combined uniaxial tension - shear strain loading constraint obtained with SCA for different (constant) reference elastic material's Young moduli, $(E^0, \nu^0) = (\Delta, 0.28)$: (a) Homogenized stress; (b) Relative error with respect to the FEM DNS solution. . . 215

4.43 Homogenized response of the particle-matrix composite under combined uniaxial compression - shear strain loading constraint obtained with SCA for different (constant) reference elastic material's Young moduli, $(E^0, \nu^0) = (\Delta, 0.28)$: (a) Homogenized stress; (b) Relative error with respect to the FEM DNS solution. 216
4.44 Homogenized response of the particle-matrix composite under uniaxial tension strain loading constraint obtained with SCA for different (constant) reference elastic material's Poisson ratios, $(E^0, \nu^0) = (145\,\text{MPa}, \Delta)$: (a) Homogenized stress; (b) Relative error with respect to the FEM DNS solution. 217
4.45 Homogenized response of the particle-matrix composite under pure shear strain loading constraint obtained with SCA for different (constant) reference elastic material's Poisson ratios, $(E^0, \nu^0) = (145\,\text{MPa}, \Delta)$: (a) Homogenized stress; (b) Relative error with respect to the FEM DNS solution. 218
4.46 Homogenized response of the particle-matrix composite under uniaxial compression strain loading constraint obtained with SCA for different (constant) reference elastic material's Poisson ratios, $(E^0, \nu^0) = (145\,\text{MPa}, \Delta)$: (a) Homogenized stress; (b) Relative error with respect to the FEM DNS solution. . . 218
4.47 Homogenized response of the particle-matrix composite under combined uniaxial tension - shear strain loading constraint obtained with SCA for different (constant) reference elastic material's Poisson ratios, $(E^0, \nu^0) = (145\,\text{MPa}, \Delta)$: (a) Homogenized stress; (b) Relative error with respect to the FEM DNS solution. . . 219
4.48 Homogenized response of the particle-matrix composite under combined uniaxial compression - shear strain loading constraint obtained with SCA for different (constant) reference elastic material's Poisson ratios, $(E^0, \nu^0) = (145\,\text{MPa}, \Delta)$: (a) Homogenized stress; (b) Relative error with respect to the FEM DNS solution. 219
4.49 Schematic of the regression-based self-consistent scheme proposed by Liu and coworkers (Liu et al., 2016) under infinitesimal strains. 221

5 CRATE: Clustering-based Nonlinear Analysis of Materials

5.1 Logo of CRATE (Clustering-based Nonlinear Analysis of Materials. 226
5.2 Schematic of a 2D Representative Volume Element directly obtained from a heterogeneous material micrograph and spatially discretized in a regular grid of voxels. 226
5.3 CRATE's material constitutive modeling interface. 227
5.4 CRATE's dynamic loading subincrementation scheme. 227
5.5 UML class diagram notation and class relationships. 230
5.6 CRATE UML class diagram associated with the material constitutive modeling. . . 231
5.7 CRATE UML class diagram associated with the cluster-reduced representative volume element (CRVE) and cluster-reduced material phase (CRMP). 232
5.8 CRATE UML class diagram associated with the clustering data computation and the cluster analysis. 234
5.9 CRATE UML class diagram associated with the computation of a DNS material elastic response database. 235
5.10 CRATE UML class diagram associated with the clustering-based reduced-order model. 236
5.11 CRATE UML class diagram associated with the loading path and incrementation. 237
5.12 CRATE UML class diagram associated with the incremental output files. 238
5.13 CRATE UML class diagram associated with the VTK output files. 239
5.14 CRATE UML class diagram associated with the tensorial and matricial operations. 240

5.15 CRATE UML class diagram associated with the clustering adaptivity management, criterion and rewinding procedure. 243

5.16 CRATE UML class diagram associated with the adaptive cluster-reduced material phase and clustering adaptivity code enrichment. 244

6 Constitutive Modeling of Amorphous Thermoplastics

6.1 Characteristic constitutive behavior of amorphous thermoplastics when subjected to uniaxial compression loading. 246

6.2 Rheological model of the proposed visco-elastic-visco-plastic constitutive model. 249

6.3 Deformation gradient multiplicative decomposition hypothesis. 250

6.4 Schematic of the two-stage optimization-based calibration procedure. Stage 1 involves the calibration of the material properties associated with the visco-elastic behavior and the yield point. Stage 2 comprises the calibration of the material properties associated with the post-yield visco-plastic behavior (strain softening and strain hardening). 269

6.5 Schematic of uniaxial compression test of cylindrical specimen performed at constant temperature T(°C) and strain rate. Finite element model of one-eight of cylindrical specimen discretized in a finite element mesh of 20-nodes hexahedral elements. 272

6.6 Comparison between the proposed constitutive model and the uniaxial compression experimental results conducted by Mulliken (Mulliken, 2006) at $T = 25$°C: (a) True stress-true strain compressive response for PC at different strain rates; (b) Close-up of the initial region of deformation path. Constitutive material properties are provided in Table 6.2. 274

6.7 Decomposition of the total stress into driving (elastic and visco-elastic) and hardening components at $T = 25$°C: (a) True stress-true strain compressive numerical response of PC for $\dot{\varepsilon} = 0.01\,\mathrm{s}^{-1}$; (b) Close-up of the initial region of deformation path. Constitutive material properties are provided in Table 6.2. . . . 274

6.8 True stress-true strain compressive numerical response of PC for $\dot{\varepsilon} = 0.1\,\mathrm{s}^{-1}$ at $T = 25$°C. Decomposition of the total stress into driving (elastic and visco-elastic) and hardening components for a different number of visco-elastic relaxation modes: (a) $n_{\mathrm{V}} = 1$; (b) $n_{\mathrm{V}} = 2$; (c) $n_{\mathrm{V}} = 3$; (d) $n_{\mathrm{V}} = 4$. 276

6.9 Comparison between the proposed constitutive model and the uniaxial compression experimental and numerical results obtained by Yu and coworkers (Yu et al., 2014) for $\dot{\varepsilon} = 0.001\,\mathrm{s}^{-1}$: (a) True stress-true strain compressive response of PC for different temperatures; (b) Close-up of the initial region of deformation path. Constitutive material properties are provided in Table 6.5. 278

6.10 Comparison between the proposed constitutive model and the uniaxial compression experimental and numerical results obtained by Yu and coworkers Yu et al. (2014) for $\dot{\varepsilon} = 0.01\,\mathrm{s}^{-1}$: (a) True stress-true strain compressive response of PC for different temperatures; (b) Close-up of the initial region of deformation path. Constitutive material properties are provided in Table 6.5. 279

6.11 Comparison between the proposed constitutive model and the uniaxial compression experimental and numerical results obtained by Yu and coworkers (Yu et al., 2014) for $\dot{\varepsilon} = 0.1\,\mathrm{s}^{-1}$: (a) True stress-true strain compressive response of PC for different temperatures; (b) Close-up of the initial region of deformation path. Constitutive material properties are provided in Table 6.5. 280

6.12 Decomposition of the total stress into driving (elastic and visco-elastic) and hardening components at $T = 60°C$: (a) True stress-true strain compressive numerical response of PC for $\dot{\varepsilon} = 0.001\,s^{-1}$; (b) Close-up of the initial region of deformation path. Constitutive material properties are provided in Table 6.5. . . . 280
6.13 Schematic representation of typical morphologies of rubber particles. 281
6.14 Schematic representation of the crazing phenomenon. 282
6.15 Schematic representation of the composite spherical element considered in the cavitation model of Bucknall and coworkers (Bucknall et al., 1994), before and after cavitation. 284
6.16 Schematic representation of the rubber toughened glassy polymer in the undamage state, where the rubber phase constitutive behaviour is neglected, and after rubber particle internal cavitation, where the polymer microstructure includes matrix and void phases. 285
6.17 Schematic representation of the RVE considered in the Gurson model. 286
6.18 Numerical assessment of extended visco-elastic-visco-plastic constitutive model accounting for rubber particle internal cavitation for $\dot{\varepsilon} = 0.001\,s^{-1}$ at $T = 25°C$ and different values of initial void volume fraction, f_0^v: (a) True stress-true strain tensile response; (b) Void volume fraction evolution; (c) Volumetric logarithmic plastic strain. Constitutive material properties are provided in Table 6.2. 293

A Notes on Micromechanics

A.1 Heterogeneous RVE composed by uniform linearly elastic inhomogeneities embedded in a uniform linearly elastic matrix. 352

B FFT-based Homogenization Basic Scheme (Infinitesimal Strains)

B.1 Spatial discretization of a 2D RVE in a regular grid of 7×7 voxels. 364

C Self-Consistent Clustering Analysis (Infinitesimal Strains)

C.1 Schematic of the Self-Consistent Clustering Analysis (SCA) clustering-based reduced-order model proposed by Liu and coworkers (Liu et al., 2016). 368
C.2 Schematic of the solution of the K-means clustering minimization problem through the standard Lloyds' algorithm (Lloyd, 1982). 370
C.3 Schematic of the cluster interaction tensors in a cluster-reduced RVE (CRVE) with 3 material clusters. 372
C.4 Biphasic heterogeneous materials microstructures: (a) Fiber-reinforced composite (randomly distributed unidirectional circular cross-section fibers, $f = 30\%$) – 2D RVE; (b) Particle-reinforced composite (randomly distributed spherical particles, $f = 20\%$) – 3D RVE. 382
C.5 Von Mises elastoplastic matrix isotropic strain hardening: (a) piecewise linear law; (b) power law. Notation: Yield stress (σ_y) and accumulated plastic strain ($\bar{\varepsilon}^p$).383
C.6 Clustering-based domain decomposition (K-means clustering) of the fiber-reinforced composite RVE for different number of clusters. The ratio between the number of clusters of the matrix phase ($f = 70\%$) and the fiber phase ($f = 30\%$) is set as 2. 385
C.7 Clustering-based domain decomposition (K-means clustering) of the particle-reinforced composite RVE for different number of clusters. The ratio between the number of clusters of the matrix phase ($f = 80\%$) and the particle phase ($f = 20\%$) is set as 4. 386

C.8 Homogenized response of the fiber-reinforced composite under uniaxial tension strain-stress loading constraints obtained with SCA for a different number of clusters: (a) Homogenized stress; (b) Relative error with respect to the FEM DNS solution. (*) The DNS solution is taken from Liu et al. (2016). 387
C.9 Homogenized response of the fiber-reinforced composite under pure shear strain-stress loading constraints obtained with SCA for a different number of clusters: (a) Homogenized stress; (b) Relative error with respect to the FEM DNS solution. (*) The DNS solution is taken from Liu et al. (2016). 388
C.10 Homogenized response of the particle-reinforced composite under uniaxial tension strain-stress loading constraints obtained with SCA for a different number of clusters: (a) Homogenized stress; (b) Relative error with respect to the FEM DNS solution. (*) The DNS solution is taken from Liu et al. (2016). 389
C.11 Homogenized response of the fiber-reinforced composite under pure shear strain-stress loading constraints obtained with SCA for a different number of clusters: (a) Homogenized stress; (b) Relative error with respect to the FEM DNS solution. (*) The DNS solution is taken from Liu et al. (2016). 389
C.12 Homogenized response of the fiber-reinforced composite under uniaxial tension strain loading conditions obtained with SCA for a different number of clusters: (a) Homogenized stress; (b) Relative error with respect to the FEM DNS solution. 392
C.13 SCA online-stage computational cost in the solution of the fiber-reinforced composite equilibrium problem under uniaxial tension strain loading conditions: (a) Comparison between the computational time of the SCA online-stage and the FEM DNS solution time; (b) Ratio between the computational time of the SCA online-stage and the FEM DNS solution time. The FEM DNS solution is obtained with a solver parallelization of 20 CPU cores. . 392
C.14 Local accumulated plastic strain field of the fiber-reinforced composite under uniaxial strain loading conditions. Comparison between the SCA solution for a different number of clusters and the FEM DNS solution. 393
C.15 Homogenized response of the particle-reinforced composite under uniaxial tension strain loading conditions obtained with SCA for a different number of clusters: (a) Homogenized stress; (b) Relative error with respect to the FEM DNS solution. 393
C.16 SCA online-stage computational cost in the solution of the particle-reinforced composite equilibrium problem under uniaxial tension strain loading conditions: (a) Comparison between the computational time of the SCA online-stage and the FEM DNS solution time; (b) Ratio between the computational time of the SCA online-stage and the FEM DNS solution time. The FEM DNS solution is obtained with a solver parallelization of 20 CPU cores. 394
C.17 Local accumulated plastic strain field of the particle-reinforced composite under uniaxial strain loading conditions. Comparison between the SCA solution for a different number of clusters and the FEM DNS solution. 394

D Compatible FEM regular mesh and element averaging

D.1 Conversion of a regular grid of pixels into a finite element mesh with quadrilateral 8-noded quadratic elements. 395
D.2 Element volumetric averaging as a means to transfer and/or compare data between a finite element mesh and a regular grid of pixels (2D) or voxels (3D). . . 396

E Overview of Adaptive Finite Element Methods (AFEMs)

E.1 Schematic illustration of problems involving strain softening and localization: (a) Rigid footing placed on an elasto-plastic embankment; (b) Uniaxial compression of plane strain elasto-plastic specimen with two circular openings. Arrows within the material denote (a) plastic flow and (b) plastic slip. 398
E.2 Strain softening in uniaxial compression of polycarbonate cylindrical specimen. . 399
E.3 Rigid footing placed on elasto-plastic foundation. Mesh h-refinement and elements aspect ratio based on gradient and curvature of displacement norm. . . 403
E.4 Schematic of the different h-refinement adaptive procedures in the analysis of a elasto-plastic perforated specimen (symmetry conditions) under uniaxial traction.404

H Constitutive material properties parametric evaluation

H.1 Influence of long-term Young's modulus, E_∞, in the true stress-true strain uniaxial compressive numerical response of PC for $\dot{\varepsilon} = 0.001\,\mathrm{s}^{-1}$ at $T = 25°\mathrm{C}$. Reference constitutive material properties are provided in Table 6.2. 418
H.2 Influence of visco-elastic properties in the true stress-true strain compressive numerical response of PC for $\dot{\varepsilon} = 0.001\,\mathrm{s}^{-1}$ at $T = 25°\mathrm{C}$: (a) Visco-elastic shear modulus, G_1; (b) Visco-elastic relaxation time, g_1. Reference constitutive material properties are provided in Table 6.2. 418
H.3 Influence of yielding properties in the true stress-true strain compressive numerical response of PC for $\dot{\varepsilon} = 0.001\,\mathrm{s}^{-1}$ at $T = 25°\mathrm{C}$: (a) Activation energy, ΔH; (b) Fundamental vibration temperature factor, A_0; (c) Shear activation volume, v^*; (c) Pressure coefficient, μ^*. Reference constitutive material properties are provided in Table 6.2. 419
H.4 Influence of post-yielding (strain softening and strain hardening) properties in the true stress-true strain compressive numerical response of PC for $\dot{\varepsilon} = 0.001\,\mathrm{s}^{-1}$ at $T = 25°\mathrm{C}$: (a) Softening slope, h; (b) Softening saturation, D_∞; (c) Hardening modulus, H. Reference constitutive material properties are provided in Table 6.2. 420

Page intentionally left blank

List of Tables

1 Introduction

1.1 Examples of process-structure-property-performance dimensions involved in the engineering design space of PC/ABS polymer blends in view of the ICME computational framework. 9

3 Efficient Microstructure Generation of Particle-Reinforced Materials

3.1 Average CPU time (over 20 realizations of each microstructure) in the generation of a legal configuration with zero overlap ($\Psi_{\text{lim}} = 0$) of disks. Microstructures are generated with the AMINO, accounting for both adaptive time integration step and multi-temperature isokinetic scheme. Missing data points correspond to simulations that could not achieve a legal configuration in a maximum of 5000 iterations (particle jamming). 114

3.2 Average CPU time (over 20 realizations of each microstructure) in the generation of a legal configuration with zero overlap ($\Psi_{\text{lim}} = 0$) of spheres. Microstructures are generated with AMINO, accounting for both adaptive time integration step and multi-temperature isokinetic scheme. Missing data points correspond to simulations that could not achieve a legal configuration in a maximum of 5000 iterations (particle jamming). 114

3.3 Average CPU time, the average number of particles and associated standard deviations (over 10 realizations of each microstructure) in the generation of microstructures with several particle phases 2A, 2B and 2C (see Figure 3.32). 115

3.4 Average CPU time, the average number of particles and associated standard deviations (over 10 realizations of each microstructure) in the generation of microstructures with several particle phases 3A, 3B and 3C (see Figure 3.33). 117

3.5 Average CPU time, number of particles and corresponding standard deviations (over 10 realizations of each microstructure), as well as, total volume fraction of the particle phase, in the generation of a legal configuration ($\Psi_{\text{lim}} = 0$). 120

3.6 Average CPU time, number of particles and corresponding standard deviations (over 10 realizations of each microstructure), as well as the total volume fraction of the particle phase, in the generation of a legal configuration ($\Psi_{\text{lim}} = 0$). 122

3.7 Average CPU time and average number of particles (over 5 realizations of each microstructure) in the generation of PC/ABS 2D RVEs through AMINO ($\Psi_{\text{lim}} = 0$). PC/ABS is modeled as a biphasic material characterized by ABS elliptical particles (phase 2) embedded in a PC matrix (phase 1). 132

3.8 Average CPU time and average number of particles (over 5 realizations of each microstructure) in the generation of PC/ABS 3D RVEs through AMINO ($\Psi_{\text{lim}} = 0$). PC/ABS is modeled as a biphasic material characterized by ABS ellipsoidal particles (phase 2) embedded in a PC matrix (phase 1). 133

4 Clustering-based Reduced-Order Modeling of Heterogeneous Materials

4.1 Essential hyperparameters of the ACROM framework. Insertion: target clusters selection criterion (Block A) and adaptive cluster analysis (Block B). 170

4.2 Constitutive model and properties of the particle-matrix composite's material phases. Notation: Young's Modulus (E), Poisson's ratio (ν), yield stress (σ_y) and accumulated plastic strain ($\bar{\varepsilon}^p$). 171

4.3 Ductile failure and associated toughness of Benchmark 1, predicted by the different solution methods under uniaxial tension. Failure assumed when 0.5% of the matrix phase surpasses an accumulated plastic strain of 0.125. Number of clusters: (c) $n_c = 65$ (coarse), (m) $n_c = 185$ (medium), (f) $n_c = 305$ (fine) and (*) $n_c = 65 \rightarrow 190$. . 177

4.4 Partial and total computational times (s) of the different solution methods associated to Benchmark 1 under uniaxial tension. Number of clusters: (c) $n_c = 65$ (coarse), (m) $n_c = 185$ (medium), (f) $n_c = 305$ (fine) and (*) $n_c = 65 \rightarrow 190$. Offline-stage: linear elastic DNS simulations (step 1), base cluster analysis (step 2) and computation of cluster-interaction tensors (step 3). 177

4.5 Ductile failure and associated toughness of the particle-matrix composite 2D RVE predicted by the different solution methods under uniaxial tension. Failure assumed when 0.5% of the matrix phase surpasses an accumulated plastic strain of 0.125. Number of clusters: (c) $n_c = 100$ (coarse), (m) $n_c = 200$ (medium), (f) $n_c = 300$ (fine), (*) $n_c = 100 \rightarrow 202$ and (↺) $n_c = 100 \rightarrow 202$ (with rewinding). 182

4.6 Partial and total computational times (s) of the different solution methods associated to the particle-matrix 2D RVE under uniaxial tension. Number of clusters: (c) $n_c = 100$ (coarse), (m) $n_c = 200$ (medium), (f) $n_c = 300$ (fine), (*) $n_c = 100 \rightarrow 202$ and (↺) $n_c = 100 \rightarrow 202$ (with rewinding). Offline-stage: linear elastic DNS solutions (step 1), base cluster analysis (step 2) and computation of cluster-interaction tensors (step 3). 183

4.7 Partial and total computational times (s) of the different solution methods associated to the particle-matrix 2D RVE under pure shear loading. Number of clusters: (c) $n_c = 100$ (coarse), (m) $n_c = 200$ (medium), (f) $n_c = 300$ (fine) and (↺) $n_c = 100 \rightarrow 201$ (with rewinding). Offline-stage: linear elastic DNS solutions (step 1), base cluster analysis (step 2) and computation of cluster-interaction tensors (step 3). 188

4.8 Partial and total computational times (s) of the different solution methods associated to the particle-matrix 2D RVE under combined uniaxial tension - pure shear loading. Number of clusters: (c) $n_c = 100$ (coarse), (m) $n_c = 200$ (medium), (f) $n_c = 300$ (fine) and (↺) $n_c = 100 \rightarrow 201$ (with rewinding). Offline-stage: linear elastic DNS solutions (step 1), base cluster analysis (step 2) and computation of cluster-interaction tensors (step 3). 188

4.9 Constitutive model and properties of the particle-matrix composite's material phases. Notation: Young's Modulus (E), Poisson's ratio (ν), yield stress (σ_y) and accumulated plastic strain ($\bar{\varepsilon}^p$). 208

4.10 Partial and total computational times (s) of the different solution methods associated with the particle-matrix 2D RVE under uniaxial tension strain loading constraints. The reference elastic material properties are kept constant throughout the deformation path in the SCA solutions. Offline-stage: hyperelastic DNS solutions (step 1), base cluster analysis (step 2) and computation of cluster-interaction tensors (step 3). 212

4.11 Convergence table of the particle-matrix composite SCA analyses ($n_c = 180$) under different macro-scale strain loading constraints. Normalized equilibrium residual of the clustered Lippmann-Schwinger system of equilibrium equations during the macro-scale loading increment 100. The reference elastic material's properties are kept constant throughout the deformation path. 220

6 Constitutive Modeling of Amorphous Thermoplastics

6.1 Material properties of the finite strain visco-elastic-visco-plastic constitutive model.259
6.2 Material properties of the proposed visco-elastic-visco-plastic model calibrated from the uniaxial compression experimental results conducted by Mulliken (Mulliken, 2006) for polycarbonate (PC). 273
6.3 Convergence table of the true stress-true strain compressive numerical response of PC for $\dot{\varepsilon} = 0.1\,\mathrm{s}^{-1}$ at $T = 25°\mathrm{C}$. Normalized equilibrium residual evolution at increment 100 and state update normalized residual evolution at a given Gauss point during each global iteration. Convergence tolerance set to 1.0×10^{-8}. 275
6.4 Convergence table of the true stress-true strain compressive numerical response of PC for $\dot{\varepsilon} = 0.1\,\mathrm{s}^{-1}$ at $T = 25°\mathrm{C}$ (see Figure 6.8(d) with $n_{\mathrm{V}} = 4$). Normalized equilibrium residual evolution at increment 100 and state update normalized residual evolution at a given Gauss point during each global iteration. Convergence tolerance set to 1.0×10^{-8}. 275
6.5 Material properties of the proposed visco-elastic-visco-plastic model calibrated from the uniaxial compression experimental results conducted by Yu and coworkers (Yu et al., 2014) for polycarbonate (PC). 277

C Self-Consistent Clustering Analysis (Infinitesimal Strains)

C.1 Constitutive model and properties of fiber-reinforced and particle-reinforced composites' material phases. Notation: Young's Modulus (E), Poisson's ratio (ν), yield stress (σ_y). 382
C.2 Specifications of the numerical testing machine. 384
C.3 Convergence table of the fiber-reinforced composite SCA analysis ($n_{\mathrm{c}} = 315$) under uniaxial tension strain-stress loading constraints. Normalized equilibrium residual evolution at the different self-consistent scheme iterations during the macro-scale loading increment 100. 390
C.4 Convergence table of the fiber-reinforced composite SCA analysis ($n_{\mathrm{c}} = 315$) under pure shear strain-stress loading constraints. Normalized equilibrium residual evolution at the different self-consistent scheme iterations during the macro-scale loading increment 100. 390
C.5 Convergence table of the particle-reinforced composite SCA analysis ($n_{\mathrm{c}} = 315$) under strain-stress uniaxial loading constraints. Normalized equilibrium residual evolution at the different self-consistent scheme iterations during the macro-scale loading increment 100. 391
C.6 Convergence table of the particle-reinforced composite SCA analysis ($n_{\mathrm{c}} = 315$) under strain-stress pure shear loading constraints. Normalized equilibrium residual evolution at the different self-consistent scheme iterations during the macro-scale loading increment 100. 391

H Constitutive material properties parametric evaluation

H.1 Parametric evaluation of the finite strain visco-elastic-visco-plastic constitutive model's material properties. True stress-true strain uniaxial compressive numerical response of PC for $\dot{\varepsilon} = 0.001\,\mathrm{s}^{-1}$ at $T = 25°\mathrm{C}$. Reference constitutive material properties are provided in Table 6.2. 417

Page intentionally left blank

Notation

General abbreviations

ACRMP	**A**daptive **C**luster-**R**educed **M**aterial **P**hase
ACROM	**A**daptive **C**lustering-based **R**educed-**O**rder **M**odel
AFEM	**A**daptive **F**inite **E**lement **M**ethod
AMINO	**A**daptive **M**ulti-temperature **I**soki**N**etic Meth**O**d
ASCA	**A**daptive **S**elf-consistent **C**lustering **A**nalysis
BVP	**B**oundary **V**alue **P**roblem
CIT	**C**luster **I**nteraction **T**ensor
CM2S	**C**omputational **M**ulti-scale **M**odeling of **S**olids and **S**tructures
CPU	**C**entral **P**rocessing **U**nit
CRATE	**C**lustering-based nonlinea**R** **A**nalysis of Ma**TE**rials
CRMP	**C**luster-**R**educed **M**aterial **P**hase
CROM	**C**lustering-based **R**educed-**O**rder **M**odel
CRVE	**C**luster Reduced **R**epresentative **V**olume **E**lement
DFT	**D**iscrete **F**ourier **T**ransform
DNS	**D**irect **N**umerical **S**imulation
DOE	**D**esign **O**f **E**xperiments
DOF	**D**egrees **O**f **F**reedom
FEM	**F**inite **E**lement **M**ethod
FFT	**F**ast **F**ourier **T**ransform
FLOP	**Flo**ating **P**oint Operation
ICME	**I**ntegrated **C**omputational **M**aterials **E**ngineering
INMSE	**I**ntegrated **N**ormalized **M**ean **S**quared **Error**
IVP	**I**nitial **V**alue **P**roblem
LINKS	**L**arge Strain **I**mplicit **N**on-linear Analysis of Solids **L**inking **S**cales
MP	**M**aterial **P**hase
OOP	**O**bject-**O**riented **P**rogramming
PMVP	**P**rinciple of **M**ulti-scale **V**irtual **P**ower
ROM	**R**educed- **O**rder **M**odel
RVE	**R**epresentative **V**olume **E**lement
RMSE	**R**oot **M**ean **S**quare **E**rror
SCRMP	**S**tatic **C**luster-**R**educed **M**aterial **P**hase
SCA	**S**elf-consistent **C**lustering **A**nalysis
SCT	**S**train **C**oncentration **T**ensor
SEM	**S**canning **E**lectron **M**icroscopy
SVE	**S**tatistical **V**olume **E**lement
TEM	**T**ransmission **E**lectron **M**icroscopy
UML	**U**nified **M**odeling **L**anguage

General notation

a	Scalar
$\boldsymbol{a}$	First-order tensor
$\boldsymbol{A}$	Second-order tensor
$\mathbf{a}, \mathbf{A}$	Fourth-order tensor
$\mathbf{a}$	Computational vector
$\mathbf{A}$	Computational matrix
$\mathscr{A}$	Body, space or set

Operators and symbols

$\mathrm{d}(\bullet)$	Infinitesimal
$\Delta(\bullet)$	Additive Incremental quantity
$\delta(\bullet)$	Iterative quantity
$\partial(\bullet)/\partial a$	Partial derivative with respect to a
$\mathrm{d}(\bullet)/\mathrm{d}a$	Total derivative with respect to a
$\boldsymbol{\varphi}_*[\bullet]$	Push-forward operator
$\boldsymbol{\varphi}_*^{-1}[\bullet]$	Push-back operator
$\mathscr{F}\{\bullet\}$	Fourier transform
$\mathscr{F}^{-1}\{\bullet\}$	Inverse Fourier transform
$\mathscr{DFT}\{\bullet\}$	Discrete Fourier transform
$\mathscr{DFT}^{-1}\{\bullet\}$	Inverse discrete Fourier transform
$\mathrm{div}[\bullet]$	Spatial divergence operator
$\mathrm{div}_0[\bullet]$	Material divergence operator
$\nabla(\bullet)$	Spatial gradient operator
$\nabla_0(\bullet)$	Material gradient operator
$\det[\bullet]$	Determinant
$\mathrm{diag}[\bullet]$	Diagonal matrix
$\exp[\bullet]$	Natural exponential function
$\inf[\bullet]$	Infimum
$\ln[\bullet]$	Natural logarithm
$\mathrm{skew}[\bullet]$	Skew-symmetric matrix component
$\sup[\bullet]$	Supremum
$\mathrm{sym}[\bullet]$	Symmetric matrix component
$\mathrm{tr}[\bullet]$	Matrix trace
$\lVert(\bullet)\rVert$	Frobenius norm
$(\bullet)\otimes(\bullet)$	Tensorial product
$(\bullet)\cdot(\bullet)$	Tensorial single contraction
$(\bullet):(\bullet)$	Tensorial double contraction
$(\bullet)*(\bullet)$	Appropriate product
$(\bullet)\circ(\bullet)$	Hadamard product

$(\bullet) \oslash (\bullet)$	Hadamard division
$\mathsf{A}(\bullet)$	Finite Element Method assembly operator
$\boldsymbol{I}$	Second-order identity tensor
I	Fourth-order identity tensor
I_d	Fourth-order deviatoric projection tensor
I_s	Fourth-order symmetric identity tensor
δ_{ij}	Discrete Dirac's delta
i	Imaginary unit

Subscripts and superscripts

$(\bullet)^{(e)}$	Finite Element Method elemental entity
$(\bullet)^{(I)}$	Cluster-related quantity (also (J) and (K))
$(\bullet)^0$	Reference material-related quantity
$(\bullet)^g$	Global Finite Element Method entity
$(\bullet)^{(k)}$	General iteration of the Newton-Raphson Method
$(\bullet)^T$	Matrix transpose
$(\bullet)^{-1}$	Matrix inverse
$(\bullet)^e$	Elastic component
$(\bullet)^{ve}$	Visco-elastic component
$(\bullet)^p$	Plastic component
$(\bullet)^{vp}$	Visco-plastic component
$(\bullet)^{\text{trial}}$	Elastic trial state
$(\bullet)^{\circ p}$	Hadamard power
$(\bullet)_\Delta$	Multiplicative incremental quantity
$(\bullet)_n$	General macro-scale increment
$(\bullet)_m$	General micro-scale increment
$(\bullet)_0$	Reference configuration, initial time
$(\bullet)_d$	Deviatoric component
$(\bullet)_h$	Hydrostatic component
$(\bullet)_\mu$	Micro-scale related quantity
$(\bullet)_s$	Sampled quantity

Accents

$(\dot{\bullet})$	First-order time derivative
$(\ddot{\bullet})$	Second-order time derivative
$(\hat{\bullet})$	Incremental constitutive function
$(\tilde{\bullet})$	Fluctuation quantity
$(\breve{\bullet})$	Defined in the frequency domain

Sets, domains and boundaries

$\mathscr{E}$	Euclidean space
$\mathscr{R}$	Real number domain
$\mathscr{K}$	Set of kinematically admissible macroscopic displacements
$\mathscr{K}_\mu$	Set of kinematically admissible minimally constrained microscopic displacements
$\tilde{\mathscr{K}}_\mu$	Set of kinematically admissible minimally constrained microscopic displacement fluctuations
$\mathscr{V}$	Set of virtual displacements
$\mathscr{V}_\mu$	Set of virtual displacement fluctuations
$\mathscr{H}$	Set of strain concentration tensors
$\mathscr{S}$	Set of cluster domain points
Υ	Local (or natural) normalized domain
Ω	Body domain in the current configuration
$\partial\Omega$	Body domain boundary in the current configuration
Ω_0	Body domain in the reference configuration
$\partial\Omega_0$	Body domain boundary in the reference configuration
Ω_μ	RVE domain in the current configuration
$\partial\Omega_\mu$	RVE domain boundary in the current configuration
$\Omega_{\mu,0}$	RVE domain in the reference configuration
$\partial\Omega_{\mu,0}$	RVE domain boundary in the reference configuration

Chapter 1
Introduction

1.1 Context

One of the most important challenges in the community of mechanics of materials is the development of accurate and efficient descriptions of the macroscopic behavior of materials with complex microstructures. In the so-called Age of New Materials, the development of new materials has helped expand the limits of human endeavor and achievements in a wide spectrum of scientific areas. Technological areas such as the aerospace, aeronautics, automobile and electronic industries are constantly pursuing high-performance applications, thus pushing the frontiers of material properties to more extreme levels (see Figure 1.1).

Due to the ability of polymeric-based materials and composites to fulfill requirements for a wide variety of applications, it became extremely important to understand how their thermomechanical performance is affected by the molecular chemical and physical structure. In fact, the versatility and intrinsic enhancement potential of this class of materials through suitable mixtures and processing conditions relies on the fact that their properties are closely tied with the underlying microstructural characteristics and mechanisms. As a consequence, their structural performance is generally associated with a highly nonlinear behavior with inherent uncertainty, demanding the development of accurate constitutive models.

Of utmost importance to the development of these materials is the understanding that they are hierarchical in nature, i.e., the macroscopic properties and response of a given material result from the interaction between heterogeneous structures spanning over multiple time and length scales. At each scale, different constituents are combined, interact with each other and promote several mechanisms and phenomena which are deeply connected to the behavior of the upper scales. Therefore, in order to accurately understand and predict the macroscopic behavior of a given material, it is necessary not only to characterize its constituents and understand the underlying mechanisms at each scale, but also to comprehend the interactions between these scales – this raises the paradigm of multi-scale modeling.

Such a paradigm is intrinsically embedded within the coined Integrated Computational Materials Engineering (ICME) (Horstemeyer (2012), Horstemeyer (2018)), which can be defined as a computational framework that integrates design, manufacturing and materials. It aims to accelerate the development of new materials, products and structures meeting specific performance criteria and/or reduce the associated costs (see Figure 1.2). In its most general form, coined hybrid ICME (Horstemeyer, 2018), it involves the integration of process-structure-property-performance relationships (horizontal ICME) with multi-scale process-structure and structure-property modeling over different length scales (vertical ICME). This interdisciplinary and integrated approach requires the collaboration of several research fields (mechanics, physics, chemistry, materials science, applied mathematics, data science and scientific computing) and is built upon three major sets of tools (Matouš et al., 2017):

- **Experimental tools:**
    1. Materials characterization at different length scales;
    2. Full-field testing and in situ measurements;
    3. Manufacturing processes (casting, forming, machining, additive manufacturing, ...);
    4. Material databases (experimental);

- **Computational tools:**
  1. Single-scale models;
  2. Multi-scale models;
  3. Reduced-order models;
  4. Verification, validation and uncertainty quantification;
  5. High-performance computing and software engineering;
- **Digital data strategies:**
  1. Material databases (numerical);
  2. Data science (material informatics);
  3. Machine learning and computational statistics;
  4. Decision-based system design and optimization.

These integrated experimental, computational and data informatics tools should span all material classes and applications, improve and accelerate predictive capabilities under uncertainty, and take advantage of the powerful computational resources available. Moreover, continuous integration of the most advanced methodologies and techniques effectively leads to a state-of-the-art modeling framework, which can provide the basis of Virtual Materials Testing standards, both easy to use, accessible and focused on engineering applicability.



(a) (b) (c) (d)

Figure 1.1: Examples of applications where high-performance materials are disruptive: (a) U.S. Air Force Lockheed Martin F-35A Lightning II aircraft (taken from www.f35.com); (b) BMW M5 Competition car model (taken from www.bmw.pt); (c) SpaceX Falcon 9 rocket (taken from www.spacex.com); (d) Intel Core I9-7980x Extreme Edition processor (taken from www.techexplorist.com).



Figure 1.2: Schematic representation of the ICME framework integrating process-structure-property-performance relationships (horizontal ICME) and multi-scale process-structure and structure-property modeling (vertical ICME).

1.2 Motivation

Within this context, the ultimate goal driving this research campaign is the establishment of an ICME framework to accurately and efficiently design and optimize PC/ABS polymer blends. As shown in Figure 1.2, this raises numerous challenges concerning the development of process-structure-property-performance relationships as well as multi-scale process-structure and structure-property modeling over different length scales. Although it is unreasonable to attempt to tackle all these challenges under the scope of this thesis, it is believed that a solid step forward can be taken. Despite the particular focus on PC/ABS polymer blends, the majority of the numerical tools developed throughout this thesis are extensible to many other classes of materials, as described at the end of this section.

Before pointing out the pursued challenges, it is important to provide a brief introduction of two fundamental topics, namely (1) the characterization of the PC/ABS polymer blends and their technological relevance, and (2) the description of the unified data-driven framework for the design of materials under uncertainty proposed by Bessa and coworkers (Bessa et al., 2017).

1.2.1 PC/ABS polymer blend

The PC/ABS is one of the most successful commercial polymer blends, finding its main applications in the automotive sector (e.g., middle console, lower instrumental panel, overhead console, structural components) and consumer electronics (e.g., electrical connectors and adapters, housings, portable hand-held devices, keypads) (see Figure 1.3). In addition, it is one of the most suitable materials for conceptual modeling and functional prototyping through three-dimensional printing.

(a) (b) (c)

Figure 1.3: Examples of PC/ABS applications: (a) Resinex PULSE^{TM} middle console (taken from www.resinex.co.uk); (b) GoPro frame mount (taken from www.gopro.com); (c) 3D printed housing (taken from www.deed3d.com).

The PC/ABS is a ternary blend composed of polycarbonate (PC) and acrylonitrile- butadiene-styrene (ABS), being the latter a binary blend of styrene-acrylonitrile (SAN) and polybutadiene (PB) (see Figure 1.4). A brief description of this polymer blend is provided in what follows, essentially based on the fundamental contributions of Greco (Greco, 1996) and Inberg (Inberg, 2001). The interested reader can find an exhaustive treatment of this topic in these two reference works and other studies mentioned therein.

With a worldwide demand of around 4.5 million tons in 2018, the PC has been one of the most widely used engineering plastic since its development in 1953 and first production in 1960. It is a linear amorphous glassy thermoplastic consisting of polyesters of carbonic acid with aliphatic or aromatic dihydroxy compounds, being the bisphenol-A polycarbonate the



Figure 1.4: Schematic representation of a PC/ABS (70/30) microstructure, evidencing the three phases of the ternary blend. SEM micrograph (PC matrix etched with a NaOH aqueous solution) taken from Greco (1996).

most used polycarbonate for commercial blends with ABS (see Figure 1.5). Common manufacturing processes include injection molding, structural foam molding, blow molding, extrusion and vacuum forming. PC products find their main applications in the automotive (e.g., dashboards, headlight lenses, windscreens, exterior cladding), electronics (e.g., connectors, housings, battery casing), packaging (e.g., medical industry, dispensers and bottles, food containers), optical media (e.g., eye protection goggles, bullet proof glasses, swimming googles) and construction sectors. Their wide application results, of course, from the excellent mechanical, thermal and optical properties of PC, among which it is possible to highlight (1) good overall mechanical resistance, (2) high unnotched impact resistance, (3) high toughness under many working conditions, (4) high heat distortion temperature and dimensional stability, (5) transparency and UV filtration, (6) glare reduction, (7) durability and recyclability. However, some drawbacks limit the range of application of this thermoplastic. First and foremost, PC loses its toughness and exhibits brittle fracture under certain conditions, namely at low temperatures, in thick-walled applications, and when small flaws and scratches are present. Such sharp hairline cracks can form when the material is exposed to the environment, a phenomenon called environmental stress cracking. Consequently, PC has a high notch sensitivity and a low notched impact resistance. In the second place, PC reveals some processability issues due to its high melt viscosity, namely in the injection molding of thin wall products. Finally, it can be added that PC has a low chemical resistance.

In order to mitigate the aforementioned drawbacks, PC can be effectively blended with ABS, with typical grades containing up to 50% of ABS (Seelig and Giessen, 2007). While SAN is an amorphous glassy thermoplastic, whose low-cost copolymers are prepared from styrene and acrylonitrile, PB is an amorphous elastomer whose behavior follows rubber-like elasticity (see Figure 1.5). Different processing methods (e.g., mechanical blending, polymerization by emulsion, bulk polymerization) may be used to produce ABS, allowing the control of several parameters such as the blend composition, molecular weight, degree of grafting and rubber particle size. Irrespective of the processing method, the ABS morphology is essentially characterized by a rubbery phase dispersed in a SAN matrix (see Figure 1.4), resulting from grafting SAN onto the PB-phase rubber. For instance, polymerization by emulsion allows the formation of very small rubber particles (0.1-0.5µm) and may achieve high rubber concentrations in SAN. In contrast, bulk polymerization leads to large rubber particles (0.5-1µm) that may even contain SAN inclusions, but rubber concentrations are limited.



Bisphenol-A Polycarbonate (Repeat Unit)

(a)



Styrene (Repeat Unit)

Polybutadiene (Repeat Unit)

(b)

Figure 1.5: Schematic of the molecular structure of the PC/ABS constituents (molecular conformation is not considered): (a) Bisphenol-A Polycarbonate (PC); (b) Acrylonitrile-Butadiene-Styrene (ABS).

From the previous description, this well-known blending process takes the general designation of rubber toughening and the PC/ABS blend owes its success to several reasons:

- **Complementary properties**. ABS exhibits several properties that are complementary to the excellent mechanical and thermal properties of PC. First, it presents a low notch sensitivity and a high impact resistance even at low temperatures. In the second place, it is able to lower the otherwise high melt viscosity of neat PC and therefore improve the processability conditions. Finally, it has an excellent chemical resistance when exposed to acids, alkalis, salts and many solvents. However, given that ABS is opaque, this particular blend is not suitable for optical applications where neat PC transparency is required;

- **Compatibility**. The PC and ABS are completely immiscible both in melt and in the solid state, being possible to blend them by simple melt-mixings in common equipment. In contrast with more complex techniques used in the toughening of incompatible systems, PC/ABS blends usually do not need the addition of interfacial compatibilizing agents due to a good interaction/adhesion between PC and SAN;

- **Production cost**. Being cheaper than PC, the addition of ABS also lowers the material cost of the product, and in this way, ABS is also used as a filler.

The PC/ABS morphology is strongly dependent on blending conditions and injection molding conditions. According to the ABS(%) content, two types of morphologies can be distinguished (see Figure 1.6). At low content (less than 30%), the ABS domains can be characterized as ellipsoidal-shaped particles with a few micrometers, typically around 5µm, spatially arranged in clusters and embedded in a PC matrix (particulate structure). The ABS particles may contain multiple PB rubber particles of different sizes and become oriented and elongated in the injection direction as the result of shear stresses during the injection molding process. Despite this elongation, it has been observed that the PB rubber particles remained round, consistent with the low viscosity of SAN during the injection. As the ABS(%) content approximates 50%, the ABS clusters become progressively more connected and lead instead to a co-continuous structure. This structure is often lamellar due to the injection moulding process, with PC and ABS lamellas of a few micrometers. In the remainder of this thesis, the focus is given to the PC/ABS particulate morphology, being in this ABS(%) range where the most interesting synergistic effects between PC and ABS are found in terms of technological application.



Figure 1.6: Schematic representation of two different types of PC/ABS morphologies. A particulate structure is shown for PC/ABS (70/30) and a co-continuous lamellar structure for PC/ABS (50/50). TEM micrograph was taken and adapted from Bärwinkel and coworkers (Bärwinkel et al., 2016) (the SAN phase appears as light areas in TEM as also observed by Inberg (Inberg, 2001)).

Given their role in the thermomechanical behavior of PC/ABS, another topic of importance in the context of this thesis are the associated deformation and damage mechanisms. In fact, it is now comprehended that several of these mechanisms play a major role in the toughening of PC through suitable blends with ABS. However, as clearly depicted by Inberg (Inberg, 2001), their occurrence and predominance in PC/ABS blends is still far from being completely understood and several authors report distinct observations under different experimental settings (e.g., blending conditions, blend morphology and composition, deformation path history). Therefore, rather than discussing the prevalence of each mechanism, the aim here is to introduce the different deformation and damage phenomena occurring in PC/ABS polymer blends (see Figure 1.7).

It is generally accepted that the microstructure damage takes place first in the ABS domains or at their interface with the PC matrix. Three types of mechanisms can be distinguished within the ABS domains: multiple crazing, dilatational bands and rubber particle's internal cavitation. Rubber particle internal cavitation is associated with the void nucleation within PB rubber particles followed by their collapse. Cavitated particles may then act as initiation sites for both

multiple crazing and shear yielding on the SAN phase. Regarding multiple crazing, a craze usually originates once the biggest rubber particles cavitate. The craze then grows and propagates, with the resulting strains causing the cavitation of smaller adjacent rubber particles from which more crazes are initiated. Crazes located close to each other may merge and eventually lead to fracture at sufficiently high strains. At the same time, shear deformations can localize into zones of high strain by strain softening of the material. These shear bands can be initiated and connect cavitated rubber particles, taking the designation of dilatational bands. In competition with the rubber particle internal cavitation occurring in the ABS domains is the void formation due to the failure of the interface between PC and ABS. This phenomenon is intrinsically related to the PC/SAN interfacial strength and its comparison with the dilatational stress required to cavitate the PB rubber particles may dictate which phenomenon prevails. When the multiple crazes propagating in the SAN phase reach the PC/SAN interface, shear yielding of the PC matrix may initiate in the points of highest strain concentrations. These shear yielding bands can eventually span the distance between ABS domains. Nonetheless, under certain conditions, craze propagation into the PC matrix is also observed with PC fracturing in a brittle manner.

Although this description of the PC/ABS polymer blend is by no means exhaustive, it is already apparent the reason why the accurate design and optimization of this heterogeneous material calls for a suitable ICME computational framework. As summarized in Table 1.1, the development of the underlying process-structure-property-performance relationships and the accurate numerical modeling of the thermomechanical behavior of PC/ABS involves the exploration of a high-dimensional engineering design space. Under such circumstances, the data-driven methodologies recently introduced in the community of computational mechanics are particularly useful.



Figure 1.7: Schematic of the deformation and damage mechanisms occurring in a PC/ABS blend with particulate morphology.

Table 1.1: Examples of process-structure-property-performance dimensions involved in the engineering design space of PC/ABS polymer blends in view of the ICME computational framework.

Process
ABS processing method (e.g., emulsion, suspension or bulk polymerization);
PC/ABS blending process (e.g., miscibility, melt temperature and viscosity);
PC/ABS manufacturing process (e.g., injection molding, extrusion, fused deposition);
...
Structure
AN and PB content (%) in ABS;
PB cross-linking level, particles size distribution and morphology (e.g., core-shell);
Type of ABS (SAN/PB grafting);
ABS(%) content in PC/ABS;
PC/ABS morphology (particulate or co-continuous);
PC/SAN interface strength/adhesion;
...
Property
Effective elastic properties (e.g., tensile modulus, bulk modulus);
Visco-elasto-plastic properties (e.g., yield stress, strain softening, strain hardening);
Dependency of loading conditions (e.g., temperature, strain rate and pressure);
Fracture strength and toughness (e.g., thickness, notch sensitivity);
Interplay and predominance of several deformation and damage mechanisms;
Impact strength and shatter resistance;
Glass transition temperature and melting point;
Thermal conductivity and distortion resistance;
...
Performance
Ability to satisfy application requirements and constraints;
Reliability under service conditions and compliance with safety standards;
Durability (e.g., resistance to water, UV radiation and chemicals, flammability);
Processing costs (e.g., energy, CO_2 footprint and water consumption);
Recycling and end of life (e.g., recycling fraction, CO_2 footprint, biodegradability);
...

1.2.2 Data-driven material design framework

Even though many developments are still to come, the extensive amount of research devoted to computational homogenization over the past decades provided highly accurate tools to predict and understand the behavior of heterogeneous materials. At the same time, technological advances brought forth imaging methodologies that rendered a deep insight into the material's lower scales as well as the capability of manipulating and operating them up to the atomic level. All the previous achievements inspire a promising future in what concerns the conception of innovative materials with disruptive properties.

To this day, structural and material design can be characterized as a highly iterative process where one strives to find an optimal design for a chosen set of quantities of interest and a given set of restrictions. For the particular case of material systems design, the high dimensionality of the engineering design space is striking when considering the overwhelming amount of possible combinations that lead to different materials (Bessa et al., 2017), which often result in suboptimal and/or unexplored solutions. This large dimension of the engineering design space represents a significant obstacle to accelerating and improving the design process in both academic and industrial contexts – the so-called curse of dimensionality. In summary, the main challenge in this context can be generally stated as follows: find a map which establishes the complete relationship between a finite set of input descriptors related to, e.g., processing conditions, microstructural attributes and work loading conditions, and a finite set of output quantities associated to, e.g., material properties, material physical behavior and performance metrics.

It transpires that the previous map is a fundamental piece in both bottom-up and top-down approaches integrated into the ICME paradigm, effectively establishing bridges between materials processing, structure, properties and performance. However, it is often a high-dimensional function and its construction poses a demanding challenge to standard methodologies. On the one hand, there are simply too many possibilities to conduct experimental investigations and/or standard computational analyses for every conceptual design. On the other hand, even if this database is available, the ability to extract the required relationships is rather limited with conventional tools (calibration procedures, trial and error approaches, etc.) when many dimensions are at stake. The recent advances in data science provided valuable resources to overcome these challenges.

Data-driven methods, which have been enabled in the past decade by the availability of data storage and computational resources, are taking center stage across many scientific disciplines (Liu et al., 2019a). At the intersection of high-performance computing, statistical theories and databases creation (Reichhardt (1999), Lynch (2008), Los and Wood (2011)), the tremendous development of powerful machine learning techniques (e.g., Mitchell (1997), Bishop (2010), Shalev-Shwartz and Ben-David (2014), Goodfellow et al. (2016), Hastie et al. (2017), Burkov (2019)) has yielded transformative and state-of-the-art performance solutions when trained with large amounts of data. This led to the outbreak of the so-called Big Data collection in several scientific fields and outstanding achievements, e.g., in the mapping of the human genome (Sachidanandam et al., 2001), unveiling the secrets of the brain (e.g., (Akil et al., 2011)), finding pathways to cure cancer (e.g., Buonamici et al. (2009), Shlush et al. (2014)), processing of natural language (e.g., Brown et al. (2020), Lan et al. (2020)), playing go, shogi and chess (Silver et al. (2017b), Silver et al. (2017a)), enhancing computer vision (e.g., Wu et al. (2020)), predicting the 3D structure of a protein based on its genetic sequence (Senior et al., 2020), and provided a better understanding of the world by often replacing smaller more targeted studies that may produce less generalizable results or lack key insights (Li et al., 2019).

In the meantime, data-driven methodologies were also introduced and have been growing since then in the context of computational methods in materials mechanics (e.g., developing a constitutive manifold directly from experimental data (Kirchdoerfer and Ortiz (2016),

Kirchdoerfer and Ortiz (2017b), Kirchdoerfer and Ortiz (2017a), Ayensa-Jiménez et al. (2018)), determining the shape of the free-energy potential in hyperelasticity (Zhang et al. (2016), Crespo et al. (2016), Latorre et al. (2016), Latorre and Montáns (2018)), guaranteeing the thermodynamic consistency in the presence of noisy experimental data (González et al., 2019), performing a data-driven correction of well-known plasticity models (Ibáñez et al., 2019b), developing data-driven multi-scale material models (Liu et al. (2019b), Liu and Wu (2019)), modeling process-structure-property relationships for additive manufacturing (Yan et al. (2018c), Yan et al. (2018b), Yan et al. (2018a))). A complete overview of this recent topic is provided by Chinesta and coworkers (Chinesta et al., 2018), where a clear distinction is made between the virtual, the digital and the proposed hybrid twins' paradigms. Besides introducing a new data-based engineering framework, this contribution provides a valuable discussion on an important aspect which summarizes and clearly distinguishes different approaches to date: to what extent and how should the data-based methodologies be integrated into the computational mechanic's frameworks? Should these techniques provide us the sought high dimensional functions in a mainly data-driven based fashion, or should they instead be only employed as a corrector to the modeler's ignorance (sometimes referred to as 'hidden physics')? In addition, it is important to realize that data science techniques rely heavily on the size and reliability of the databases, presenting difficulties when the data is scarce and of variable fidelity relative to the complexity of the system (Liu et al., 2019a). Unlike traditional applications in data science (e.g., image recognition), extremely large and well-defined datasets are generally unavailable, or merely inaccessible, in computational mechanics (Li et al., 2019). The way this challenge should be addressed is by promoting enriching discussions and raising different approaches, the big data and smart data paradigms (Chinesta et al., 2018). The debate over such fundamental questions in itself shows how much the data-driven methodologies already play an essential role in the context of computational methods in material mechanics.

One approach results from the pioneering work of Yvonnet and coworkers (Yvonnet et al. (2009), Clément et al. (2012), Yvonnet et al. (2013), Le et al. (2015)), which demonstrated for the first time that a data-driven framework could be used to determine the constitutive law of nonlinear elastic heterogeneous materials. They proposed to explore the material design space at macro-scale and micro-scale by performing the data-driven computational homogenization of nonlinear elastic composite RVEs. Their contribution inspired Bessa and coworkers (Bessa et al., 2017) to propose a unified data-driven framework for the design and modeling of materials and structures under uncertainty. Their work shows encouraging results by finding a constitutive law for a two-dimensional hyperelastic composite and by maximizing the toughness of a three-dimensional elasto-plastic composite.

The proposed data-driven framework is perfectly aligned with the development of the ICME computational framework for PC/ABS polymer blends. It provides a practical approach to the construction of the high-dimensional map previously introduced and the blueprints to establish the associated process-to-performance bridges. Therefore, despite not limiting the scope of this research by any means, it is adopted as an essential computational tool to achieve the established goals. In this view, a concise description of its structure is presented below, being the interested reader referred to a complete treatment in Bessa et al. (2017).

In the context of material design explored here, the proposed data-driven framework integrates three general steps as schematically shown in Figure 1.8: (1) the design of experiments, where the engineering design space is sampled; (2) the creation of a material response database through multi-scale computational homogenization analyses over design samples; and (3) machine learning to extract a high-dimensional map from the response database and obtain the new material design or model.



Figure 1.8: Schematic of the data-driven computational framework for the design and modeling of materials proposed in Bessa et al. (2017).

Having established the material design and/or modeling goals, the first step consists in performing the design of experiments. This characterizes and samples the high dimensional design space by a finite set of input descriptors and involves two main substeps:

- **Design descriptors.** First, it is necessary to define a finite set of descriptors that can be generally classified into three types: microstructure morphology (geometrical) descriptors (e.g., number of particles, particles aspect ratio and orientation, volume fraction) which can be properly identified via microstructure characterization methodologies (e.g., Xu et al. (2014), Xu et al. (2015), Bostanabad et al. (2016)); material property descriptors (e.g., constitutive models parameters) which are extracted from the constitutive assumptions for each constituent; and external (boundary) conditions descriptors (e.g., macro-scale homogenized strain/stress, micro-scale boundary conditions). Bounds and constraints must then be established for each descriptor. Otherwise, the associated values shall be specified. At this point, the set of input design variables, $\boldsymbol{x}$, for the problem is the group of all descriptors,

$$\boldsymbol{x} = \left\{ x_1 \quad x_2 \quad \dots \quad x_m \right\}, \tag{1.1}$$

  where m is the total number of input design variables. Each design point, $\boldsymbol{x}_i$, $i \in [1, N]$, where N is the total number of design samples, is then associated (1) with a given representative volume element (RVE) (or multiple statistical volume elements, SVEs), characterized by a fixed set of microstructural descriptors, (2) with a fixed set of material properties, characterizing the constitutive models of the RVE material phases, and (3) with a fixed set of boundary conditions;

- **Design space sampling.** After identifying the set of input design variables and their respective values, bounds and constraints, the design space must be explored and sampled in some way in order to perform the design of experiments. Assuming no prior knowledge about the problem to be solved[1], space-filling design methods (e.g., Sobol (1967), Sobol (1976), McKay et al. (1979), Simpson and Lin (2001), Fang et al. (2005), Jin et al. (2005), Jourdan and Franco (2010)) treat the different domain regions equally and ensure that the sample points are spread out in an optimal sense. Based on the comparative analysis of Santiago et al. (2012) and some additional comparison tests between different methods, Bessa and coworkers (Bessa et al., 2017) adopted the Sobol sequence in order to have a good compromise between a regular grid and a random distribution, among other useful characteristics.

The second step consists of the creation of a macroscopic response database that will serve as the training dataset required for the subsequent machine learning step. After defining the quantities of interest $\boldsymbol{q}$ (e.g., effective properties, yield stress, ductility),

$$\boldsymbol{q} = \left\{ q_1 \quad q_2 \quad \dots \quad q_n \right\}, \tag{1.2}$$

where n is the total number of quantities of interest (or output variables), the macroscopic response database is essentially a collection of N sets

$$\text{Database} \equiv \left\{ (\boldsymbol{x}_1, \boldsymbol{q}_1) \quad (\boldsymbol{x}_2, \boldsymbol{q}_2) \quad \dots \quad (\boldsymbol{x}_N, \boldsymbol{q}_N) \right\}, \tag{1.3}$$

where each set i, $i = 1, \dots, N$, represents the macroscopic material response, $\boldsymbol{q}_i$, for the design point, $\boldsymbol{x}_i$, in the design of experiments. As previously discussed, machine learning (as well as other data mining methods) often requires large databases in order to be effective. Unless in

[1] In fact, any prior knowledge about the problem to be solved should already be embedded in the choice of the finite set of descriptors and their respective bounds and constraints.

the unlikely event that a large experimental database is available, the creation of the response database through experimental analyses for each design point would typically take an unfeasible amount of time. Therefore, multi-scale analyses based on computational homogenization become an attractive option if two fundamental requirements are satisfied: the numerical predictions must be accurate (high-fidelity), otherwise the database does not represent the real behavior of the material and the design or model built by machine learning is a priori not reliable; the computational analyses must be efficient (low computational cost) so that the required large database can be obtained in a reasonable amount of time.

Even assuming that these computational requisites are satisfied, the creation of the response database still accounts for the majority of time in the data-driven framework. For this reason, preliminary (optional) studies may be conducted in order to improve the quality of the design of experiments before conducting the complete set of computational analyses. Among several possibilities:

- **Microstructure uncertainty.** A heterogeneous microstructure may not be, in general, uniquely characterized by a fixed set of microstructural descriptors due to the stochastic nature of its morphology. In this view, the uncertainty quantification is intrinsically related to the length scale of the computational representative domain. For instance, a larger length scale contains more information about the microstructure and tends to eliminate the stochastic effects, implying that the domain becomes more representative and a single RVE can be associated with the design point. On the contrary, a smaller length scale leads to domains exhibiting different material responses, implying that none of them is representative in a complete sense. In this case, multiple SVEs should be associated with each design point to account for such uncertainty. The choice of the length scale is then reflected on one of two options: perform computational analyses over one microstructure realization (RVE) per design point, each having a higher associated computational cost, or performing less demanding analyses for multiples realizations (SVEs) per design point and averaging them in some way (see Figure 1.9);

- **Sampling quality.** Analysing one or more typical microstructures for a range of other descriptors (material properties and/or external boundary conditions) may provide valuable information on the adequacy of the space-filling design. By defining appropriate prediction error metrics, one can obtain an estimate of the number of design points needed to predict the material response within a specified accuracy. Moreover, these preliminary analyses may pinpoint regions of the design space that are not sufficiently sampled and would consequently lead to a poor training dataset;

- **Descriptors influence.** A preliminary global sensitivity analysis, for instance, with variance-based methods (e.g., Saltelli et al. (2008), Saltelli et al. (2010)), may render important insights into the influence of the input design variables on the material response, i.e., quantify the influence of each descriptor on a given quantity of interest. On the one hand, some descriptors that were initially established may end up not having a significant impact on the quantities of interest. These may then be removed from the design of experiments to reduce the size of the training dataset. On the other hand, the influence of specific descriptors may suggest the inclusion of other related descriptors in the design of experiments that were not initially considered.

It is thus clear that these preliminary analyses may be crucial to enhancing the design of experiments, polishing the material representative domain, performing local refinements where necessary, including or excluding descriptors and reducing the number of design points according to the desired prediction accuracy. Such procedures are aligned with the smart-data paradigm discussed in Chinesta et al. (2018) – collecting the correct data, which (potentially)



Figure 1.9: Determination of the macroscopic (homogenized) response associated with a given design point through an RVE or multiple SVEs.

provides the maximum information and knowledge instead of collecting a massive amount of data where only a small percentage is indeed valuable.

The third and final step consists in constructing a model that establishes the relation between the input design variables (design of experiments) and the quantities of interest. For low dimensional and relatively small databases, this model can be obtained with traditional methods (e.g., calibration procedures, trial and error). However, the model is usually a high-dimensional function and the dimensionality of the design space leads to large response databases – this calls for the countless number of machine learning methods (or models learners) developed in the data science field (e.g., Forgy (1965), Cristianini and Shawe-Taylor (2000), Theodoridis and Koutroumbas (2008), Criminisi et al. (2011), Carlsson (2014), Brunton et al. (2016), Wasserman (2018), Parsa et al. (2018), Moitra (2018)). An appropriate machine learning method must then be selected according to the dimensionality of the design space and the size of the response database. Deep-learning is based on the use of neural networks (e.g., Rosenblatt (1958), Hopfield (1982), Widrow and Hoff (1988), Hagan et al. (1996), Goodfellow et al. (2016), Raissi et al. (2017a), Raissi et al. (2017b)) and is probably the most powerful and most extensively used model learning tool, being employed in Bessa et al. (2017) together with kringing (e.g., Krige (1951), Matheron (1963), Simpson et al. (2001), Ankenman et al. (2009), Staum (2009), Banerjee et al. (2014)).

Having obtained the high-dimensional map, it is essential to quantify the uncertainty associated with the machine learning predictions. Appropriate error metrics should be defined to perform suitable comparisons with available experimental data and/or direct numerical solutions (DNS). Compliance with fundamental conservation principles should be ascertained as well. In addition, a complete global sensitivity analysis can be performed at this point in order to discover and understand the influence of the design descriptors on the quantities of interest. Finally, suitable representations of the high-dimensional map over the design space can provide a clear vision of the model features and help to identify the global and/or local

optima for the new material design. The latter task can be performed with the help of optimization techniques, which can be nonetheless challenging for high-dimensional design spaces. On the other hand, the design sampling space can be refined based on the acquired knowledge of the problem, aiming to reduce the uncertainty of the predicted solution, improve the predicted solution accuracy, or obtain a better resolution of a given design space subdomain.

1.2.3 Challenges

Based on the brief introduction provided in the previous sections, it is now possible to adequately describe the addressed challenges towards the establishment of a PC/ABS ICME framework. Each of them is intrinsically associated with a given section of the ICME framework illustrated in Figure 1.2 and/or to a given step of the data-driven framework shown in Figure 1.8.

Challenge 1:

The first challenge is related to the process-structure bridge and the associated multi-scale modeling. A key requirement to perform accurate multi-scale computational analyses of PC/ABS polymer blends is the generation of high-fidelity computational representative domains, i.e., the generation of PC/ABS RVEs that closely resemble the real material microstructure. In the present research, interest is placed on the micro-scale level ($10^{-6} - 10^{-5}$m) and on PC/ABS blends exhibiting a particulate morphology (ABS content below 30%).

As described in Section 1.2.1, PC/ABS blends are often obtained through simple melt-mixings under immiscibility conditions between PC and ABS. This essentially leads to a random particle reinforced matrix microstructure such as the one illustrated in Figure 1.4, where ABS ellipsoidal domains containing dispersed PB particles are embedded in a PC matrix. Besides the different blending contents (see Table 1.1), processing conditions allow a certain degree of control over both ABS domains' and PB particles' size distribution. In addition, one of the main manufacturing processes of PC/ABS is injection molding, leading to a preferred orientation and elongation of the ABS domains in the injection direction. Note that all of these manufacturing parameters are none other than the microstructure descriptors required to perform the design of experiments of the data-driven framework, and must be accounted for to successfully generate high-fidelity PC/ABS RVEs.

In addition, given that one or more computational microstructures must be generated for each design point of an often large design of experiments, the computational generation method must be efficient and robust. It must be capable of producing hundreds or thousands of RVEs in a reasonable amount of time and in an entirely nonsupervised way, i.e., be as reliable as possible when dealing with a wide variety of microstructure descriptors.

To the best of the author's knowledge, none of the available methods found in the literature satisfied all of these requirements (e.g., Lubachevsky and Stillinger (1990), Donev et al. (2005), Ghossein and Lévesque (2013), Salnikov et al. (2015), Catalanotti (2016)). The main challenge is thus to develop a computational methodology to efficiently generate high-fidelity particle reinforced materials RVEs that complies with the different blending and process supplied parameters. Although focus is given to PC/ABS polymer blends, the scope of the proposed method extends to general random heterogeneous particle reinforced materials.

Challenge 2:

The second challenge addresses the structure-property bridge and the associated multi-scale modeling. With a realistic microstructure associated with each design point, it is necessary to compute the physical material response at the macro-scale level accurately.

By establishing a continuous interchange of information between scales through homogenization, computational homogenization multi-scale modeling emerged as a powerful method in computational mechanics. Despite the extensive research and achievements on this topic, new challenges arise when dealing with data-driven methodologies. Although the so-called direct numerical simulations (DNS) are able to provide accurate numerical predictions, these often lack the required computational efficiency to generate large material response databases in a feasible amount of time. In fact, this is the core challenge (or bottleneck) of the just described data-driven material design framework: the ability to perform high-fidelity computational analyses, i.e., capturing the fine stereological and phenomenological details of the microstructure, at low computational cost, i.e., with demanding computational time and resources are compatible with engineering applicability.

A myriad of so-called reduced-order models (ROMs) has been developed over the last decades, aiming to provide the required balance between accuracy and efficiency (e.g., Dvorak (1992), Michel and Suquet (2003), Yvonnet and He (2007), Ladevèze et al. (2010), Hernández et al. (2014), van Tuijl et al. (2019)). Among different successful approaches and strategies, the recent family of clustering-based ROM (Li et al., 2019) has shown promising results in the handling of the nonlinear inelastic behavior of heterogeneous materials (e.g., Liu et al. (2016), Wulfinghoff et al. (2017), Li et al. (2019)). Nonetheless, these models are still rather limited when attempting to efficiently capture localization phenomena and damage mechanisms occurring at the microstructure level. This is particularly relevant in the case of PC/ABS polymer blends, as several deformation and damage micro-scale mechanisms play an important role in their effective properties. Moreover, a proper finite strain formulation is required to accurately predict the thermomechanical behavior of PC/ABS polymer blends in many engineering applications of interest.

The main challenge is thus to develop a clustering-based ROM that can accurately capture the macro-scale thermomechanical behavior of PC/ABS polymer blends through computational homogenization, accounting for finite strains and general localization and damage phenomena, while preserving the essential efficiency demanded by a data-driven material design framework.

Challenge 3:

The third challenge is also focused on the structure-property bridge and the associated multi-scale modeling. Besides generating the heterogeneous material high-fidelity RVE, suitable constitutive models are required to accurately model and numerically predict the physical behavior of the different material phases. In the particular case of PC/ABS polymer blends, constitutive models are needed to model the PC, SAN and PB thermomechanical behavior under finite strains.

Being an amorphous elastomer that exhibits rubber-like elasticity behavior, the PB phase can be modeled through one of several well-established hyperelastic constitutive models. However, given the relatively low PB(%) content in ABS, the much lower stiffness than the surrounding SAN matrix and the PB particles cavitation at relatively low stress levels, this phase is often explicitly neglected, and instead, particles are modeled as voids (Seelig and Giessen, 2007). In turn, PC and SAN are both amorphous thermoplastics with a highly nonlinear thermomechanical visco-elastic-visco-plastic behavior that depends on temperature, strain rate and pressure. Moreover, the interplay of several deformation and damage micro-scale mechanisms must be accounted for, namely shear yielding, crazing and rubber particle's internal cavitation.

Since the pioneering contributions by Eyring (Eyring, 1936), Haward and coworkers (Haward et al., 1968), and Leonov (Leonov, 1976), many constitutive models that aim to enhance previously established constitutive laws, accurately capture the effects of different loading conditions, and account for distinct microstructural mechanisms have been proposed

(e.g., Anand and Gurtin (2003), Srivastava et al. (2010), Krairi and Doghri (2014), Nguyen et al. (2016), Yu et al. (2017), Khaleghi et al. (2022)). However, despite the vast number of constitutive models developed in the past decades to predict the mechanical behavior of amorphous thermoplastics, most of them are either visco-elastic or elasto-visco-plastic (Gudimetla and Doghri, 2017). Although intricate dependencies and complex phenomena have been accounted for in many valuable contributions, accurate constitutive predictions call for a suitable coupling of visco-elasticity and visco-plasticity characteristic of amorphous thermoplastics. On a different note, many constitutive models account for a lengthy set of material properties whose physical meaning is difficult to grasp and/or require cumbersome calibration procedures involving several types of experiments. Moreover, the computational implementation is not always detailed in an entirely comprehensive way and/or turns out to be rather complex for the interested analyst. The aforementioned aspects raise limitations in terms of actual engineering applicability of (sometimes) highly sophisticated and capable constitutive models.

The main challenge is thus to develop a constitutive model that describes the finite strain nonlinear constitutive behavior of amorphous thermoplastics below the glass transition temperature, including both visco-elasticity and visco-plasticity. In addition, the model should account for temperature, strain rate, and pressure dependencies, and incorporate the phenomena of shear yielding, crazing and rubber particles internal cavitation. Last but not least, the calibration of the constitutive model material properties should be properly described and made accessible through standard experiments.

Challenge 4:

The fourth and last challenge consists of the actual design and optimization of PC/ABS polymer blends through the described ICME framework. Even though several contributions in the literature addressed the computational modeling of PC/ABS (e.g., Seelig and Giessen (2007), Van der Giessen and Seelig (2015), Hund and Seelig (2017), Hund et al. (2018)), this approach has not been yet attempted to the best of the author's knowledge. This requires the effective computational implementation of the data-driven framework shown in Figure 1.8 and the integration of all the previous challenging developments in a unified and state-of-the-art computational tool for the design and optimization of materials.

1.3 Contributions

Attending to the challenges laid out in the previous section, the main contributions of the present thesis are summarized below. All the relevant scientific publications (Q1 peer-reviewed international journals or international books) directly associated with this thesis and where the author is either the first author or co-first author are also listed.

Challenge 1 - Contributions:

- A new computational generation method for particle-reinforced materials coined AMINO (Adaptive Multi-temperature Isokinetic Method) is proposed in a framework of time-driven molecular dynamics. This method's high efficiency accounts for two distinctive numerical features, namely an adaptive (explicit) time integration scheme and a multi-temperature isokinetic thermostat;

- Extensive numerical applications demonstrate that AMINO is compliant with a broad spectrum of microstructure descriptors and complex topologies, being suitable to be employed as a high-fidelity RVE generator in a data-driven framework for the design and modeling of new materials;

- Statistical comparisons with experimental micrographs show that AMINO is able to produce high-fidelity RVEs that closely resemble real microstructures.

- **Journal paper**: Ferreira, B.P., Vila-Chã, J.V.C. and Andrade Pires, F.M., (2021). An adaptive multi-temperature isokinetic method for the RVE generation of particle reinforced heterogeneous materials, Part I: Theoretical formulation and computational framework. *Mechanics of Materials*, 163.

- **Journal paper**: Ferreira, B.P., Vila-Chã, J.V.C. and Andrade Pires, F.M., (2021). An adaptive multi-temperature isokinetic method for the RVE generation of particle reinforced heterogeneous materials, Part II: Numerical assessment and statistical analysis. *Mechanics of Materials*, 165.

Challenge 2 - Contributions:

- The recent clustering-based reduced-order modeling framework based on a Lippmann-Schwinger integral equilibrium formulation is thoroughly and systematically derived under both infinitesimal and finite strains;

- A new clustering adaptivity approach is proposed to dynamically adapt the clustering domain decomposition throughout the prediction stage, introducing for the first time the so-called Adaptive Clustering-based Reduced-Order Models (ACROMs);

- A novel method called Adaptive Self-consistent Clustering Analysis (ASCA) is formulated and shown to capture highly localized plasticity accurately in the computational homogenization of an elasto-plastic particle-reinforced composite while keeping a high efficiency;

- A new finite strain extension of the Self-consistent Clustering Analysis (SCA) CROM compatible with the multiplicative nature of the deformation gradient is proposed, being accurate predictions achieved under elasto-plasticity for a suitable choice of the reference material elastic properties. The accuracy and robustness of the underlying self-consistent scheme are still under investigation;

- A first-of-its-kind open source software named CRATE (Clustering-based Nonlinear Analysis of Materials) is fully designed and developed to perform accurate and efficient multi-scale nonlinear analyses of heterogeneous materials based on a coupling between first-order computational homogenization and clustering-based reduced-order models.

- **Book chapter**: Ferreira, B.P., Andrade Pires, F.M. and Bessa, M.A., (2022). Fast Homogenization Through Clustering-Based Reduced-Order Modeling. In Fundamentals of Multiscale Modeling of Structural Materials. *Elsevier*.

- **Journal paper**: Ferreira, B.P., Andrade Pires, F.M. and Bessa, M.A., (2022). Adaptivity for clustering-based reduced-order modeling of localized history-dependent phenomena. *Computer Methods in Applied Mechanics and Engineering*, 393.

- **Journal paper** (in preparation): Ferreira, B.P., Andrade Pires, F.M. and Bessa, M.A. Topic: Finite strain extension of SCA compatible with the multiplicative nature of the deformation gradient.

- **Journal paper** (in preparation): Ferreira, B.P., Andrade Pires, F.M. and Bessa, M.A. Topic: Open source software CRATE (Clustering-based Nonlinear Analysis of Materials).

Challenge 3 - Contributions:

- A visco-elastic-visco-plastic constitutive model is formulated to describe the finite strain nonlinear behavior of amorphous thermoplastics below the glass transition temperature and isothermal conditions;
- A two-stage optimization-based procedure is proposed to calibrate the constitutive model's material properties based on uniaxial compression tests at different temperatures and strain rates;
- Both constitutive state update and consistent tangent modulus are described in detail to make a proper computational implementation accessible;
- An excellent agreement between the constitutive model predictions and experimental results is obtained at different temperatures and strain rates for polycarbonate, being the distinct stages of the highly nonlinear finite deformation accurately captured;
- A constitutive extension is proposed to account for the phenomenon of rubber particle internal cavitation arising in the finite deformation of rubber-toughened amorphous thermoplastics, namely by incorporating damage in the form of nucleation and growth of voids.
- **Journal paper** (submitted): Ferreira, B.P., Carvalho Alves, A.F. and Andrade Pires, F.M., (2022). An efficient finite strain constitutive model for amorphous thermoplastics: fully implicit computational implementation and optimization-based parameter calibration.

Besides the general supervision and expertise provided by both advisors, Dr. Francisco Manuel Andrade Pires and Dr. Miguel Aníbal Bessa, it is here emphasized that these contributions would not have been possible without a rich collaboration environment within the CM2S research group[2]. In particular, I'm deeply thankful to Eng. José Luís Passos Vila-Chã for a fruitful collaboration and support concerning the computational generation of particle reinforced materials microstructures. Regarding the constitutive modeling of amorphous thermoplastics, I'm sincerely grateful to Eng. Ana Francisca Carvalho Alves for her valuable cooperation in this challenging topic. At last, it is recognized that the achievements associated with this thesis also rest upon hours of shared ideas, immersive discussions and computational adventures with all the colleagues of the CM2S research group.

Additional contributions:

Other relevant scientific publications related to the topics covered in this thesis and where the author has a significant contribution are also listed below.

- **Journal paper**: Rodrigues Lopes, I.A., Ferreira, B.P. and Andrade Pires, F.M. (2021). On the efficient enforcement of uniform traction and mortar periodic boundary conditions in computational homogenisation. *Computer Methods in Applied Mechanics and Engineering*, 384.
- **Journal paper** (submitted): Carvalho Alves, A.F., Ferreira, B.P. and Andrade Pires, F.M. (2021). Optimization-based Parameter Identification and Development of a High Strain Rate Elasto-Viscoplastic Model for Amorphous Polymers.
- **Journal paper** (in preparation): Carvalho Alves, A.F., Ferreira, B.P. and Andrade Pires, F.M. Topic: Constitutive model for amorphous thermoplastics ranging from low to high strain rates.

[2] CM2S (Computational Multi-Scale Modeling of Solids and Structures) is a recently founded research group led by Dr. Francisco Manuel Andrade Pires at the Faculty of Engineering of the University of Porto.

1.4 Document structure

The remainder of this thesis is essentially organized in different chapters according to the aforementioned challenges. It is also important to remark that the notation provided at the beginning of the document is consistently applied throughout all chapters, being the meaning of each variable appropriately defined in the text.

Chapter 2 provides a fundamental but by no means exhaustive background to the following chapters of this thesis. In the first place, the basic concepts required to describe the behavior of a solid undergoing finite deformations are described, together with the conservation principles required to establish its mechanical equilibrium. Then, the solution to the mechanical initial boundary value equilibrium problem through the Finite Element Method is then presented. Finally, the main ingredients of the Scale Transition Theory are provided and the formulation of a first-order hierarchical multi-scale model based on computational homogenization is detailed.

Chapter 3 is dedicated to the computational generation of particle reinforced materials RVEs. First, the formulation of a novel time-driven molecular dynamics generation method is presented, coined AMINO (Adaptive Multi-temperature Isokinetic Method). Second, extensive numerical applications are shown to evidence the efficiency, robustness and flexibility of the proposed method, as well as comparisons with experimental micrographs. At last, high-fidelity PC/ABS RVEs are generated and is carried out a preliminary assessment of the method performance in a data-driven framework.

Chapter 4 describes the multi-scale modeling of heterogeneous materials through clustering-based reduced-order modeling and computational homogenization. In the first place, the clustered Lippmann-Schwinger integral equilibrium equation is systematically derived under both infinitesimal and finite strain settings. In the second place, a novel clustering adaptivity approach is proposed to enhance the ability of CROMs to handle cases where highly localized plasticity or damage phenomena take place. This introduces for the first time the so-called Adaptive Clustering-based Reduced-Order Models (ACROMs), and a particular CROM coined Adaptive Self-consistent Clustering Analysis (ASCA). Finally, a new finite strain extension of the pioneering CROM called Self-consistent Clustering Analysis (SCA) that is compatible with the multiplicative nature of the deformation gradient is proposed. Several numerical applications considering elasto-plastic particle reinforced heterogeneous materials demonstrate the accuracy, efficiency and limitations of the proposed methods. This chapter is complemented by several appendices that provide a suitable background to the covered topics (Appendices A-E).

Chapter 5 introduces CRATE (Clustering-based Nonlinear Analysis of Materials), a Python program fully developed within the scope of this thesis and designed to perform accurate and efficient multi-scale analyses based on a coupling between computational homogenization and clustering-based reduced-order models. After a brief overview of CRATE's main features, the underlying object-oriented design and computational implementation are thoroughly described to support its release as an open-source software.

Chapter 6 presents the complete description of a new visco-elastic-visco-plastic constitutive model to predict the finite strain mechanical behavior of amorphous thermoplastics under isothermal deformation conditions. Both constitutive state update and consistent tangent modulus are detailed for a fully implicit computational implementation, and a two-stage optimization-based procedure is proposed to calibrate the material properties. Several comparisons between numerical and experimental results demonstrate the accuracy of the constitutive model under uniaxial compression at different temperatures and strain rates. At last, a constitutive extension is proposed to account for the phenomenon of rubber particle internal cavitation arising in rubber-toughened amorphous thermoplastics. This chapter is complemented by two appendices that provide details on relevant mathematical derivations (Appendix G) and illustrate the parametric behavior of the constitutive model (Appendix H).

Chapter 7 puts forth the main conclusions of the present thesis and provides a conclusive assessment of the addressed challenges. Given the research experience acquired throughout this thesis, future research guidelines are finally established and discussed.

Page intentionally left blank

Chapter 2
Continuum Mechanics and Multi-scale Modeling

2.1 Preliminaries

This introductory chapter is included here with the sole purpose of providing a fundamental background to the remainder chapters of this thesis. First, the fundamental concepts required to describe the behavior of a solid undergoing finite deformations and the conservation principles required to establish its mechanic equilibrium are presented. A brief introduction is then given to the solution of a the mechanical initial boundary value equilibrium problem through the Finite Element Method. The interested reader can found extensive literature devoted to both of these topics (e.g., Holzapfel (2000), Tadmor et al. (2012), Belytschko et al. (2013), Zienkiewicz et al. (2014), Bonet et al. (2016)), being the following sections based on the approach in de Souza Neto et al. (2008). Second, the fundamental concepts underlying the Scale Transition Theory are introduced and the formulation of a first-order hierarchical multi-scale model based on computational homogenization is detailed. Particular emphasis is given to the numerical treatment of the micro-scale equilibrium problem through the Finite Element Method. The adopted formulation is based on the variational multi-scale constitutive theory established by de Souza Neto and coworkers (de Souza Neto and Feijóo (2006), de Souza Neto and Feijóo (2008), Perić et al. (2009), de Souza Neto and Feijóo (2011), Perić et al. (2011), de Souza Neto et al. (2014), Blanco et al. (2014), Blanco et al. (2016)).

2.2 Kinematics of deformation

2.2.1 Motion

Consider a deformable body $\mathscr{B}$ which occupies an open region Ω_0 of the tridimensional Euclidean space $\mathscr{E}$ with a regular boundary $\partial\Omega_0$ in its reference configuration. The motion of the body $\mathscr{B}$ (see Figure 2.1) is defined by a smooth univocal function

$$\boldsymbol{\varphi} : \Omega_0 \times \mathscr{R} \rightarrow \mathscr{E}\,, \tag{2.1}$$

which, for a given instant of time t, maps each material particle of coordinates $\boldsymbol{X}$ in the reference configuration to its position $\boldsymbol{x}$ in the deformed configuration as[1]

$$\boldsymbol{x} = \boldsymbol{\varphi}(\boldsymbol{X}, t)\,. \tag{2.2}$$

The displacements field can therefore be defined as

$$\boldsymbol{u}(\boldsymbol{X}, t) = \boldsymbol{\varphi}(\boldsymbol{X}, t) - \boldsymbol{X}\,, \tag{2.3}$$

[1] In the present report, the ortonormal basis associated with the reference configuration, $\boldsymbol{E}_i, i = 1,2,3$, and with the deformed configuration, $\boldsymbol{e}_i, i = 1,2,3$, are taken to be coincident, i.e., $\boldsymbol{x} = x_i E_i = x_i e_i$.

and, since the motion function is univocal, the reference configuration can be recovered as

$$\boldsymbol{X} = \boldsymbol{\varphi}^{-1}(\boldsymbol{x}, t) = \boldsymbol{x} - \boldsymbol{u}(\boldsymbol{\varphi}^{-1}(\boldsymbol{x}, t), t)\,, \tag{2.4}$$

where $\boldsymbol{\varphi}^{-1}$ is the reference mapping function.

2.2.2 Material and spatial descriptions

When dealing with finite deformation, the behavior of the body whose motion is under analysis can be described with respect to the reference configuration or to the deformed configuration. The former is called material (or Lagrangian) description and any field (scalar, vectorial or tensorial) defined over the body is expressed as a function of the reference configuration $\boldsymbol{X}$. For instance, despite being naturally associated with the deformed configuration, the material velocity field can be defined as

$$\boldsymbol{v}(\boldsymbol{X}, t) = \dot{\boldsymbol{u}}(\boldsymbol{X}, t) = \frac{\partial \boldsymbol{\varphi}(\boldsymbol{X}, t)}{\partial t}\,. \tag{2.5}$$

The latter is called spatial (or Eulerian) description and the same field is expressed as a function of the deformed configuration $\boldsymbol{x}$. The spatial velocity field can thus be defined as

$$\boldsymbol{v}(\boldsymbol{x}, t) = \dot{\boldsymbol{u}}(\boldsymbol{\varphi}^{-1}(\boldsymbol{x}, t), t)\,. \tag{2.6}$$

The relation between quantities defined in material and spatial descriptions is generally expressed in terms of the concepts of push forward, $\boldsymbol{\varphi}_*[\bullet]$, and pull back, $\boldsymbol{\varphi}_*^{-1}[\bullet]$, operators, where $\boldsymbol{a}[\bullet]$ implies an operation that will be evaluated according with the operand.

The same distinction applies to different operators, such as the divergence and the gradient. Let a be a generic field defined in both material and spatial descriptions as

$$a(\boldsymbol{X}, t) = a(\boldsymbol{\varphi}(\boldsymbol{X}, t), t)\,, \qquad a(\boldsymbol{x}, t) = a(\boldsymbol{\varphi}^{-1}(\boldsymbol{x}, t), t)\,. \tag{2.7}$$

The material and spatial gradients, ∇_0 and ∇ respectively, are defined as

$$\nabla_0 a = \frac{\partial}{\partial \boldsymbol{X}} a(\boldsymbol{X}, t)\,, \quad \nabla a = \frac{\partial}{\partial \boldsymbol{x}} a(\boldsymbol{x}, t)\,, \tag{2.8}$$

where the derivatives are taken with respect to the reference and deformed configuration accordingly. If a is, for instance, a generic first-order tensor $\boldsymbol{a}$, the material and spatial divergences, div_0 and div respectively, are defined as

$$\mathrm{div}_0[\boldsymbol{a}] = \mathrm{tr}[\nabla_0 \boldsymbol{a}]\,, \qquad \mathrm{div}[\boldsymbol{a}] = \mathrm{tr}[\nabla \boldsymbol{a}]\,. \tag{2.9}$$

2.2.3 Deformation gradient

The deformation gradient, second-order tensor denoted as $\boldsymbol{F}$, is a key quantity to describe finite deformations since, from a physical point of view, it relates the relative position between two neighbouring material particles before and after deformation. In a material description, the deformation gradient associated with the motion $\boldsymbol{\varphi}$ is defined as

$$\boldsymbol{F}(\boldsymbol{X}, t) = \nabla_0 \boldsymbol{\varphi}(\boldsymbol{X}, t) = \frac{\partial \boldsymbol{x}}{\partial \boldsymbol{X}}\,, \tag{2.10}$$

or, taking into account that

$$\boldsymbol{x} = \boldsymbol{X} + \boldsymbol{u}(\boldsymbol{X}, t)\,, \tag{2.11}$$



Figure 2.1: Motion.

it can be expressed as

$$\boldsymbol{F}(\boldsymbol{X}, t) = \boldsymbol{I} + \nabla_0 \boldsymbol{u}. \tag{2.12}$$

Alternatively, in a spatial description, it is defined as

$$\boldsymbol{F}(\boldsymbol{x}, t) = \left[\nabla \boldsymbol{\varphi}^{-1}(\boldsymbol{x}, t)\right]^{-1} = \left[\boldsymbol{I} - \nabla \boldsymbol{u}(\boldsymbol{x}, t)\right]^{-1}. \tag{2.13}$$

Isochoric/Volumetric decomposition

Any deformation can be locally decomposed in volumetric and isochoric (or distortional) components. Let $\mathrm{d}v_0$ be an infinitesimal volume of the body in its reference configuration and $\mathrm{d}v$ the infinitesimal volume after deformation. It is easy to prove that the determinant of the deformation gradient represents, locally, the volume change ratio as

$$J = \det[\boldsymbol{F}] = \frac{\mathrm{d}v}{\mathrm{d}v_0}, \tag{2.14}$$

hence, an isochoric deformation is characterized by $J = 1$. Therefore, the deformation gradient can be decomposed as

$$\boldsymbol{F} = \boldsymbol{F}_{\mathrm{iso}} \boldsymbol{F}_{\mathrm{vol}} = \boldsymbol{F}_{\mathrm{vol}} \boldsymbol{F}_{\mathrm{iso}}, \tag{2.15}$$

where the isochoric and volumetric components are defined by

$$\boldsymbol{F}_{\mathrm{iso}} = (\det[\boldsymbol{F}])^{-\frac{1}{3}} \boldsymbol{F}, \quad \boldsymbol{F}_{\mathrm{vol}} = (\det[\boldsymbol{F}])^{\frac{1}{3}} \boldsymbol{I}. \tag{2.16}$$

Polar decomposition

The deformation gradient can also be decomposed in rotation and stretch components, the so-called polar decomposition defined as

$$\boldsymbol{F} = \boldsymbol{R}\boldsymbol{U} = \boldsymbol{V}\boldsymbol{R}, \tag{2.17}$$

where $\boldsymbol{R}$ is the proper orthogonal rotation tensor and $\boldsymbol{U}$ and $\boldsymbol{V}$ are the symmetric positive right and left stretch tensors respectively. From a physical point of view, the right polar decomposition ($\boldsymbol{F} = \boldsymbol{RU}$) corresponds to a stretch mapping followed by a rotation, whereas in the left polar decomposition ($\boldsymbol{F} = \boldsymbol{VR}$) the rotation is applied before the stretch mapping. The right and left stretch tensors are related by

$$\boldsymbol{V} = \boldsymbol{RUR}^T, \tag{2.18}$$

and can be defined as

$$\boldsymbol{U} = \sqrt{\boldsymbol{C}}, \quad \boldsymbol{V} = \sqrt{\boldsymbol{B}}, \tag{2.19}$$

where $\boldsymbol{C}$ and $\boldsymbol{B}$ are the right and left Cauchy-Green strain tensors which are, in turn, defined as

$$\boldsymbol{C} = \boldsymbol{U}^2 = \boldsymbol{F}^T\boldsymbol{F}, \qquad \boldsymbol{B} = \boldsymbol{V}^2 = \boldsymbol{FF}^T. \tag{2.20}$$

Since $\boldsymbol{U}$ and $\boldsymbol{V}$ are symmetric tensors, if follows from the spectral theorem that they admit the spectral decomposition

$$\boldsymbol{U} = \sum_{i=1}^{3} \lambda_i \boldsymbol{E}_i^* \otimes \boldsymbol{E}_i^*, \qquad \boldsymbol{V} = \sum_{i=1}^{3} \lambda_i \boldsymbol{e}_i^* \otimes \boldsymbol{e}_i^*, \tag{2.21}$$

where λ_i, $i = 1,2,3$, are the eigenvalues of both $\boldsymbol{U}$ and $\boldsymbol{V}$, termed principal stretches, and $\boldsymbol{E}_i^*$ and $\boldsymbol{e}_i^*$ are the respetive eigenvectors that define the Lagrangian and Eulerian principal directions. In fact, the triads $\left\{\boldsymbol{E}_1^*, \boldsymbol{E}_2^*, \boldsymbol{E}_3^*\right\}$ and $\left\{\boldsymbol{e}_1^*, \boldsymbol{e}_2^*, \boldsymbol{e}_3^*\right\}$ form two orthogonal bases which are related by

$$\boldsymbol{e}_i^* = \boldsymbol{RE}_i^*, \tag{2.22}$$

and the local stretching from a material particle, associated to any deformation, can always be expressed as a superposition of stretches along the three mutually orthogonal directions. From the definitions of both right and left Cauchy-Green strain tensors, it naturally follows

$$\boldsymbol{C} = \sum_{i=1}^{3} \lambda_i^2 \boldsymbol{E}_i^* \otimes \boldsymbol{E}_i^*, \qquad \boldsymbol{B} = \sum_{i=1}^{3} \lambda_i^2 \boldsymbol{e}_i^* \otimes \boldsymbol{e}_i^*. \tag{2.23}$$

2.3 Strain tensors

In Continuum Mechanics there are two main families of strain tensors often employed to describe the body deformation and which are derived from the deformation gradient. The strain tensors from the Lagrange family, based on the right stretch tensor and defined by

$$\boldsymbol{E}^{(m)} = \begin{cases} \dfrac{1}{m}(\boldsymbol{U}^m - \boldsymbol{I}), & m \neq 0, \\ \ln[\boldsymbol{U}], & m = 0, \end{cases} \tag{2.24}$$

where m is a real number and $\ln[\bullet]$ denotes the tensor logarithm of $[\bullet]$, and, in a similar way, the strain tensors from the Eulerian family, based on the left stretch tensor and defined by

$$\boldsymbol{\varepsilon}^{(m)} = \begin{cases} \dfrac{1}{m}(\boldsymbol{V}^m - \boldsymbol{I}), & m \neq 0, \\ \ln[\boldsymbol{V}], & m = 0. \end{cases} \tag{2.25}$$

In the particular case of $m = 0$, the so-called material and spatial logarithmic strain tensors are defined as

$$\boldsymbol{E}^{(0)} = \ln[\boldsymbol{U}] = \sum_{i=1}^{3} \ln\lambda_i \, \boldsymbol{E}_i^* \otimes \boldsymbol{E}_i^* \,, \tag{2.26}$$

$$\boldsymbol{e}^{(0)} = \ln[\boldsymbol{V}] = \sum_{i=1}^{3} \ln\lambda_i \, \boldsymbol{e}_i^* \otimes \boldsymbol{e}_i^* \,. \tag{2.27}$$

2.4 Forces and stress measures

The deformation of a body is intrinsically related to the forces which are acting upon it. From a purely mechanical point of view, there are two distinct classes of forces: volume (or body) forces, exerted on the interior of the body and measured in force per unit volume; and surface forces, applied to the boundary of the body and transmitted across its interior, measured in force per unit area. Associated with the latter is the concept of stress, which can be mathematically described by different stress tensors.

Cauchy stress tensor

The Cauchy's theorem establishes that the relation between the so-called Cauchy stress vector, $\boldsymbol{t}(\boldsymbol{x},\boldsymbol{n})$, and the unitary outward vector normal to the deformed surface in consideration, $\boldsymbol{n}$, is linear and defined by

$$\boldsymbol{t}(\boldsymbol{x},\boldsymbol{n}) = \boldsymbol{\sigma}(\boldsymbol{x})\boldsymbol{n} \,, \tag{2.28}$$

where $\boldsymbol{\sigma}$ is the second-order Cauchy stress tensor. Given that the Cauchy stress vector is measured in force per unit deformed area, the Cauchy stress tensor is naturally associated with the deformed configuration, i.e., expressed in a spatial description. Furthermore, as a consequence of the balance of angular momentum, the Cauchy stress tensor is symmetric.

First Piola-Kirchhoff stress tensor

The First Piola-Kirchhoff stress tensor, $\boldsymbol{P}$, is commonly regarded as the material counterpart of the Cauchy stress tensor and, in a similar way, it establishes the linear dependence between the stress vector $\boldsymbol{t}_0(\boldsymbol{X},\boldsymbol{m})$, and the unitary outward vector normal to the undeformed surface in consideration, $\boldsymbol{m}$, as

$$\boldsymbol{t}_0(\boldsymbol{X},\boldsymbol{m}) = \boldsymbol{P}(\boldsymbol{X})\boldsymbol{m} \,. \tag{2.29}$$

Note that the stress vector $\boldsymbol{t}_0(\boldsymbol{X},\boldsymbol{m})$ is measured in force per unit undeformed area and, in contrast with the Cauchy stress tensor, the First Piola-Kirchhoff stress tensor is generally nonsymmetric. In fact, the latter can be obtained from the former through the following relation

$$\boldsymbol{P} = J\boldsymbol{\sigma}\boldsymbol{F}^{-T} \,. \tag{2.30}$$

Kirchhoff stress tensor

The Kirchhoff stress tensor, $\boldsymbol{\tau}$, is another widely used symmetric stress tensor that can be simply defined by

$$\boldsymbol{\tau} = J\boldsymbol{\sigma}\,. \tag{2.31}$$

Deviatoric/Hydrostatic decomposition

It is often convenient, particularly for the purpose of constitutive modeling, to split the Cauchy stress tensor, $\boldsymbol{\sigma}$, as

$$\boldsymbol{\sigma} = \boldsymbol{\sigma}_d - p\boldsymbol{I}\,, \tag{2.32}$$

where p is the (invariant) hydrostatic pressure defined as

$$p = -\frac{1}{3}\,\mathrm{tr}\,[\boldsymbol{\sigma}]\,, \tag{2.33}$$

and $\boldsymbol{\sigma}_d$ is the deviatoric stress defined as

$$\boldsymbol{\sigma}_d = \boldsymbol{\sigma} - p\boldsymbol{I}\,. \tag{2.34}$$

Given that

$$(\boldsymbol{I}\otimes\boldsymbol{I}) : \boldsymbol{A} = \mathrm{tr}\,[\boldsymbol{A}]\,, \tag{2.35}$$

where $\boldsymbol{A}$ is a generic second-order tensor, the hydrostatic stress tensor can be obtained as

$$p\boldsymbol{I} = -\frac{1}{3}\,(\boldsymbol{I}\otimes\boldsymbol{I}) : \boldsymbol{\sigma}\,, \tag{2.36}$$

and the traceless deviatoric stress tensor can be analogously obtained as

$$\boldsymbol{\sigma}_d = \mathbf{I}_d : \boldsymbol{\sigma}\,, \tag{2.37}$$

where $\mathbf{I}_D$ is the fourth order deviatoric projection tensor

$$\mathbf{I}_d = \mathbf{I} - \frac{1}{3}\,(\boldsymbol{I}\otimes\boldsymbol{I})\,. \tag{2.38}$$

Following its definition, the Kirchhoff stress tensor admits a similar decomposition as

$$\boldsymbol{\tau} = \boldsymbol{\tau}_d - Jp\boldsymbol{I} = \mathbf{I}_d : \boldsymbol{\tau} + \frac{1}{3}\,\mathrm{tr}\,[\boldsymbol{\tau}]\,. \tag{2.39}$$

2.5 Fundamental conservation principles

In Continuum Mechanics, irrespective of the quantities used to describe the mechanical behavior of a body undergoing large deformations, there is a set of conservation principles and thermodynamic laws that must always be satisfied.

Principle of mass conservation

The principle of mass conservation can be mathematically stated as

$$\dot{\rho} + \rho\,\mathrm{div}\,[\dot{\boldsymbol{u}}(\boldsymbol{x})] = 0\,, \tag{2.40}$$

where ρ is the material density measured in mass per unit deformed volume.

Principle of linear momentum conservation

The principle of linear momentum conservation can be postulated in both material and spatial descriptions. Adopting a spatial description it is stated as

$$\begin{cases} \operatorname{div}[\boldsymbol{\sigma}(\boldsymbol{x})] + \boldsymbol{b} = \rho\, \ddot{\boldsymbol{u}}(\boldsymbol{x}), & \forall \boldsymbol{x} \in \Omega, \\ \boldsymbol{t}(\boldsymbol{x}, \boldsymbol{n}) = \boldsymbol{\sigma}(\boldsymbol{x})\boldsymbol{n}, & \forall \boldsymbol{x} \in \partial\Omega, \end{cases} \tag{2.41}$$

where $\boldsymbol{b}$ is the body forces field (force per unit deformed volume). Alternatively, adopting a material description, it is stated as

$$\begin{cases} \operatorname{div}_0[\boldsymbol{P}(\boldsymbol{X})] + \boldsymbol{b}_0 = \rho_0\, \ddot{\boldsymbol{u}}(\boldsymbol{X}), & \forall \boldsymbol{X} \in \Omega_0, \\ \boldsymbol{t}_0(\boldsymbol{X}, \boldsymbol{m}) = \boldsymbol{P}(\boldsymbol{X})\boldsymbol{m}, & \forall \boldsymbol{X} \in \partial\Omega_0, \end{cases} \tag{2.42}$$

where $\boldsymbol{b}_0$ is the body forces field, measured in force per unit undeformed volume, and ρ_0 is the material density, measured in mass per unit undeformed volume. Both these quantities can be obtained from their spatial counterparts as

$$\boldsymbol{b}_0 = J\boldsymbol{b}, \quad \rho_0 = J\rho. \tag{2.43}$$

Stated in either material or spatial descriptions, these equations are the so-called strong, pointwise or local equilibrium equations, since they enforce the equilibrium at every material particle of the body.

First principle of thermodynamics

The first principle of thermodynamics postulates the conservation of energy and is mathematically established as

$$\rho\dot{e} = \boldsymbol{\sigma} : \boldsymbol{D} + \rho r - \operatorname{div}[\boldsymbol{q}], \tag{2.44}$$

where e is the specific internal energy field, r is the density of heat production field and $\boldsymbol{q}$ is the heat flux vector field. The second-order tensor $\boldsymbol{D}$ denotes a strain rate measure such that the double contration $\boldsymbol{\sigma} : \boldsymbol{D}$ represents the stress power per unit volume in the deformed configuration of a body.

Second principle of thermodynamics

The second principle of thermodynamics postulates the irreversibility of entropy production and is mathematically expressed by the inequality

$$\rho\dot{s} + \operatorname{div}\left[\frac{\boldsymbol{q}}{\theta}\right] - \frac{\rho r}{\theta} \geq 0, \tag{2.45}$$

where θ and s are the temperature and specific entropy fields respectively.

Clausius-Duhem inequality

Combination of both first and second thermodinamic principles yields

$$\rho\dot{s} + \operatorname{div}\left[\frac{\boldsymbol{q}}{\theta}\right] - \frac{1}{\theta}\left(\rho\dot{e} - \boldsymbol{\sigma} : \boldsymbol{D} + \operatorname{div}[\boldsymbol{q}]\right) \geq 0. \tag{2.46}$$

Defining the specific energy as

$$\psi = e - \theta s, \tag{2.47}$$

and the temperature field gradient as $\boldsymbol{g} = \nabla\theta$, it is possible to establish the so-called Clausius-Duhem inequality in the spatial description as

$$\boldsymbol{\sigma} : \boldsymbol{D} - \rho\left(\dot{\psi} + s\dot{\theta}\right) - \frac{1}{\theta}\boldsymbol{q}\cdot\boldsymbol{g} \geq 0, \tag{2.48}$$

where it was used the identity

$$\operatorname{div}\left[\frac{\boldsymbol{q}}{\theta}\right] = \frac{1}{\theta}\operatorname{div}[\boldsymbol{q}] - \frac{1}{\theta^2}\boldsymbol{q}\cdot\nabla\theta. \tag{2.49}$$

From the physical point of view, the left hand side of (2.48) represents the energy dissipation per unit deformed volume. Attending to Equation (2.31), the Clausius-Duhem inequality can be instead written as

$$\boldsymbol{\tau} : \boldsymbol{D} - \rho_0\left(\dot{\psi} + s\dot{\theta}\right) - \frac{J}{\theta}\boldsymbol{q}\cdot\boldsymbol{g} \geq 0, \tag{2.50}$$

where the left hand side now represents the energy dissipation per unit reference volume.

2.6 Weak equilibrium equations

Obtaining the exact solution of the strong equilibrium equations associated with real engineering problems is extremely challenging or impossible in the practical sense. For this reason, most of the numerical methods are formulated to obtain an approximate solution to the designated weak equilibrium equations. These result from a relaxation of the strong equilibrium equations in that it is not seek that the equilibrium equations are satisfied pointwise, but instead satisfied in an average sense as the result of an integration over the body volume. The weak equilibrium equations can be derived by several energetic and weighted residual methods — here it is applied the Virtual Work Principle.

Spatial description

Considering a quasi-static motion, in which the inertial terms can be neglected, the Virtual Work Principle states, in a spatial description, that the body is in equilibrium if and only if the Cauchy stress field satisfies

$$\int_\Omega \left[\boldsymbol{\sigma} : \nabla\boldsymbol{\eta} - \boldsymbol{b}\cdot\boldsymbol{\eta}\right] \mathrm{d}v - \int_{\partial\Omega} \boldsymbol{t}\cdot\boldsymbol{\eta}\,\mathrm{d}a = 0, \quad \forall\boldsymbol{\eta} \in \mathscr{V}, \tag{2.51}$$

where $\mathscr{V}$ is the space of virtual displacements of the body, defined by the space of sufficiently regular arbitrary displacements

$$\boldsymbol{\eta} : \Omega \to \mathscr{U}, \tag{2.52}$$

where $\mathscr{U}$ is the n-dimension vector space associated with $\mathscr{E}$.

Material description

Alternatively, in a material description, the Virtual Work Principle states that the body is in equilibrium if and only if the First Piola-Kirchhoff stress field satisfies

$$\int_{\Omega_0} \left[\boldsymbol{P} : \nabla_0 \boldsymbol{\eta} - \boldsymbol{b}_0 \cdot \boldsymbol{\eta} \right] \mathrm{d}v - \int_{\partial\Omega_0} \boldsymbol{t}_0 \cdot \boldsymbol{\eta} \, \mathrm{d}a = 0 , \quad \forall \boldsymbol{\eta} \in \mathscr{V} , \tag{2.53}$$

where $\mathscr{V}$ is the space of virtual displacements of the body, defined in this case by the space of sufficiently regular arbitrary displacements

$$\boldsymbol{\eta} : \Omega_0 \to \mathscr{U} . \tag{2.54}$$

2.7 Mechanical constitutive initial value problem

In the Continuum Mechanics context, a constitutive model is a given set of equations, usually called constitutive equations, which establishes the relation between strains and stresses for a certain material. Before going further, it is important to define a thermokinetic process of a body $\mathscr{B}$ as

$$\text{thermokinetic process}: \quad \left\{ \boldsymbol{\varphi}(\boldsymbol{X}, t), \theta(\boldsymbol{X}, t) \right\} , \tag{2.55}$$

and a calorodynamic process of $\mathscr{B}$ as

$$\text{calorodynamic process}: \quad \left\{ \boldsymbol{\sigma}(\boldsymbol{X}, t), e(\boldsymbol{X}, t), s(\boldsymbol{X}, t), r(\boldsymbol{X}, t), \boldsymbol{b}(\boldsymbol{X}, t), \boldsymbol{q}(\boldsymbol{X}, t), \right\} , \tag{2.56}$$

which satisfies the fundamental conservation principles previously introduced.

2.7.1 Constitutive axioms

Irrespective of the material under consideration, any constitutive model must satisfy three fundamentals axioms of the general constitutive theory, namely the principle of thermodinamically determinism, the principle of material objectivity and material symmetry restrictions. These can be summarized as follows:

- **Principle of thermodynamic compatible determinism**. Postulates that the history of the thermokinetic process to which a neighbourhood of a point $\boldsymbol{X}$ of $\mathscr{B}$ has been subjected determines a calorodynamic process for $\mathscr{B}$ at $\boldsymbol{X}$. In this sense, a simple material is a material for which the local history of $\boldsymbol{F}$, θ and $\boldsymbol{g}$ suffices to determine the history of the thermokinetic process. Therefore, the principle of thermodynamic compatible determinism implies the existence of constitutive functionals such that, for a material point $\boldsymbol{X}$, the calorodynamic process ($\boldsymbol{b}$ is delivered by linear momentum conservation and r by the first principle of thermodynamics) is defined as

$$\boldsymbol{\sigma}(t) = \mathfrak{F}(\boldsymbol{F}^t, \theta^t, \boldsymbol{g}^t) , \tag{2.57}$$

$$\psi(t) = \mathfrak{G}(\boldsymbol{F}^t, \theta^t, \boldsymbol{g}^t) , \tag{2.58}$$

$$s(t) = \mathfrak{H}(\boldsymbol{F}^t, \theta^t, \boldsymbol{g}^t) , \tag{2.59}$$

$$\boldsymbol{q}(t) = \mathfrak{J}(\boldsymbol{F}^t, \theta^t, \boldsymbol{g}^t) , \tag{2.60}$$

  where the thermokinetic process satisfies the Clausius-Duhem inequality and $(\bullet)^t$ denotes the history of $(\bullet)$ at $\boldsymbol{X}$ up to instant t.

- **Principle of material objectivity**. Postulates that the material response must be independent of the observer, placing restrictions on the constitutive functions formally expressed as

$$\boldsymbol{\sigma}^*(t) = \mathfrak{F}(\boldsymbol{F}^{t*}, \theta^t, \boldsymbol{g}^{t*}), \tag{2.61}$$

$$\psi(t) = \mathfrak{G}(\boldsymbol{F}^{t*}, \theta^t, \boldsymbol{g}^{t*}), \tag{2.62}$$

$$s(t) = \mathfrak{H}(\boldsymbol{F}^{t*}, \theta^t, \boldsymbol{g}^{t*}), \tag{2.63}$$

$$\boldsymbol{q}^*(t) = \mathfrak{J}(\boldsymbol{F}^{t*}, \theta^t, \boldsymbol{g}^{t*}), \tag{2.64}$$

  where $(\bullet)^*$ is associated with a motion $\boldsymbol{\varphi}^*$ which defines a rigid relative movement between two observers as

$$\boldsymbol{\varphi}^*(\boldsymbol{X}, t) = \boldsymbol{y}(t) + \boldsymbol{Q}(t)\left[\boldsymbol{\varphi}(\boldsymbol{X}, t) - \boldsymbol{x_0}\right], \tag{2.65}$$

  where $\boldsymbol{y}(t)$ is a point in space, $\boldsymbol{Q}(t)$ is a rotation tensor and $\boldsymbol{\varphi}(\boldsymbol{X}, t) - \boldsymbol{x_0}$ is the position vector of $\boldsymbol{\varphi}(\boldsymbol{X}, t)$ relative to an arbitrary origin $\boldsymbol{x_0}$.

- **Material symmetry restrictions**. Establishes that the constitutive functionals must satisfy the material symmetry group, which is defined as the set of rotations of the reference configuration under which the response functionals remain unchanged. This implies that the following relations

$$\mathfrak{F}(\boldsymbol{F}^t, \theta^t, \boldsymbol{g}^t) = \mathfrak{F}(\left[\boldsymbol{FQ}\right]^t, \theta^t, \boldsymbol{g}^t), \tag{2.66}$$

$$\mathfrak{G}(\boldsymbol{F}^t, \theta^t, \boldsymbol{g}^t) = \mathfrak{G}(\left[\boldsymbol{FQ}\right]^t, \theta^t, \boldsymbol{g}^t), \tag{2.67}$$

$$\mathfrak{H}(\boldsymbol{F}^t, \theta^t, \boldsymbol{g}^t) = \mathfrak{H}(\left[\boldsymbol{FQ}\right]^t, \theta^t, \boldsymbol{g}^t), \tag{2.68}$$

$$\mathfrak{J}(\boldsymbol{F}^t, \theta^t, \boldsymbol{g}^t) = \mathfrak{J}(\left[\boldsymbol{FQ}\right]^t, \theta^t, \boldsymbol{g}^t), \tag{2.69}$$

  hold for any time-independent rotation tensor $\boldsymbol{Q}$ which belongs to the material symmetry group.

2.7.2 Thermodynamics with internal variables

In the present document, a particular case of the general history functional-based constitutive theory is adopted, based on the well-known thermodynamics with internal variables. In such constitutive models, the thermodynamic state at a given material particle ($\boldsymbol{\sigma}$, ψ, s and $\boldsymbol{q}$), defined at a given instant of the calorodynamic process, is assumed to be completely defined by the instantaneous values of a finite number of state variables

$$\{\boldsymbol{F}, \theta, \boldsymbol{g}, \boldsymbol{\alpha}\}, \tag{2.70}$$

where $\boldsymbol{\alpha}$ is a given set of internal variables (scalar and tensorial nature) associated with dissipative mechanisms. It is thus clear that the accuracy of the constitutive model highly depends on the appropriate choice of the set of internal variables, since these contain all the relevant information about the material thermodynamical history. Following this formalism, the principle of thermodynamic compatible determinism can be specialized as

$$\boldsymbol{\sigma}(t) = \boldsymbol{\sigma}(\boldsymbol{F}, \theta, \boldsymbol{g}, \boldsymbol{\alpha}), \tag{2.71}$$

$$\psi(t) = \psi(\boldsymbol{F}, \theta, \boldsymbol{\alpha}), \tag{2.72}$$

$$s(t) = s(\boldsymbol{F}, \theta, \boldsymbol{g}, \boldsymbol{\alpha}), \tag{2.73}$$

$$\boldsymbol{q}(t) = \boldsymbol{q}(\boldsymbol{F}, \theta, \boldsymbol{g}, \boldsymbol{\alpha}), \tag{2.74}$$

and by adopting the velocity gradient to set the work conjugacy as

$$\boldsymbol{\sigma} : \boldsymbol{D} = \boldsymbol{\sigma} : \boldsymbol{L} = \boldsymbol{\sigma} : \dot{\boldsymbol{F}}\boldsymbol{F}^{-1} = \boldsymbol{\sigma}\boldsymbol{F}^{-T} : \boldsymbol{F}, \tag{2.75}$$

the Clausius-Duhem inequality can be written in terms of power per unit deformed volume as

$$\left(\boldsymbol{\sigma}\boldsymbol{F}^{-T} - \rho\frac{\partial\psi}{\partial\boldsymbol{F}}\right) : \dot{\boldsymbol{F}} - \rho\left(s + \frac{\partial\psi}{\partial\theta}\right)\dot{\theta} - \rho\,\frac{\partial\psi}{\partial\alpha_k}\dot{\alpha}_k - \frac{1}{\theta}\,\boldsymbol{q}\cdot\boldsymbol{g} \geq 0, \tag{2.76}$$

where the straightforward application of the derivation chain rule was used to establish the rate of ψ as

$$\dot{\psi} = \frac{\partial\psi}{\partial\boldsymbol{F}} : \dot{\boldsymbol{F}} + \frac{\partial\psi}{\partial\theta}\dot{\theta} + \frac{\partial\psi}{\partial\alpha_k}\dot{\alpha}_k. \tag{2.77}$$

Because the Clausius-Duhem inequality must hold for any thermokinetic process, i.e., must remain valid for any set $\{\dot{\boldsymbol{F}}(t), \dot{\theta}(t)\}$, it implies the following Cauchy stress and entropy constitutive equations

$$\boldsymbol{\sigma} = \rho\frac{\partial\psi}{\partial\boldsymbol{F}}\boldsymbol{F}^{T}, \qquad s = -\frac{\partial\psi}{\partial\theta}. \tag{2.78}$$

Once again, attending to Equation (2.31), the Kirchhoff stress constitutive equation can then be simply obtained as

$$\boldsymbol{\tau} = J\rho\frac{\partial\psi}{\partial\boldsymbol{F}}\boldsymbol{F}^{T}. \tag{2.79}$$

Moreover, by multiplying both sides of Equation (2.76) by J, which is the same as assuming the work conjugate $\boldsymbol{P} : \dot{\boldsymbol{F}}$, and attending to definitions (2.30) and (2.43), the Clasius-Duhem inequality can be written in terms of power per unit reference volume as

$$\left(\boldsymbol{P} - \rho_0\frac{\partial\psi}{\partial\boldsymbol{F}}\right) : \dot{\boldsymbol{F}} - \rho_0\left(s + \frac{\partial\psi}{\partial\theta}\right)\dot{\theta} - \rho_0\,\frac{\partial\psi}{\partial\alpha_k}\dot{\alpha}_k - \frac{J}{\theta}\,\boldsymbol{q}\cdot\boldsymbol{g} \geq 0, \tag{2.80}$$

which implies the first Piola-Kirchhoff stress constitutive equation

$$\boldsymbol{P} = \rho_0\frac{\partial\psi}{\partial\boldsymbol{F}}. \tag{2.81}$$

The Clausius-Duhem inequality can then be reduced to

$$-\boldsymbol{A} * \dot{\boldsymbol{\alpha}} - \frac{J}{\theta}\boldsymbol{q}\cdot\boldsymbol{g} \geq 0, \tag{2.82}$$

where the set of thermodynamical forces $\boldsymbol{A}$ is defined as

$$\boldsymbol{A} = \{A_k\}, \qquad A_k = \rho_0\frac{\partial\psi}{\partial\alpha_k}, \quad \alpha_k \in \boldsymbol{\alpha}, \tag{2.83}$$

and '$*$' denotes the appropriate product operation. This means that to completely define the constitutive model, constitutive equations for internal variables and for the thermal term $(1/\theta)\boldsymbol{q}$ must be postulated. Recalling the principle of thermodynamic compatible determinism and the formalism of thermodynamics with internal variables, the constitutive functions can then be postulated as

$$\dot{\boldsymbol{\alpha}} = f(\boldsymbol{F}, \theta, \boldsymbol{g}, \boldsymbol{\alpha}), \tag{2.84}$$

$$\frac{1}{\theta}\boldsymbol{q} = g(\boldsymbol{F}, \theta, \boldsymbol{g}, \boldsymbol{\alpha}). \tag{2.85}$$

An efficient and mathematically convenient way of ensuring that the previous constitutive functions satisfy the Clausius-Duhem inequality consists in postulating a non-negative scalar-valued function, often termed dissipation potential, as

$$\Xi = \Xi(\boldsymbol{A}, \boldsymbol{g}; \boldsymbol{F}, \theta, \boldsymbol{\alpha}), \tag{2.86}$$

which is convex with respect to each A_k and $\boldsymbol{g}$, and zero valued at the origin, $\{\boldsymbol{A}, \boldsymbol{g}\} = \{\boldsymbol{0}, \boldsymbol{0}\}$. Note that in the previous definition the state variables appear only as parameters. By assuming the hypothesis of normal dissipativity, the constitutive functions can then be defined as

$$\dot{\alpha}_k = -\frac{\partial \Xi}{\partial A_k}, \qquad \frac{1}{\theta}\boldsymbol{q} = -\frac{\partial \Xi}{\partial \boldsymbol{g}}. \tag{2.87}$$

2.7.3 Mechanical constitutive initial value problem

In the purely mechanical case, in which all the quantities related with the thermal domain can be removed, a constitutive model based in internal variables can be established by the following set of equations.

$$\boldsymbol{P} = \rho_0 \frac{\partial \psi}{\partial \boldsymbol{F}}, \tag{2.88}$$

$$\psi = \psi(\boldsymbol{F}, \boldsymbol{\alpha}), \tag{2.89}$$

$$\dot{\boldsymbol{\alpha}} = f(\boldsymbol{F}, \boldsymbol{\alpha}), \tag{2.90}$$

where ψ is the specific free energy. Hence, the spatial mechanical constitutive initial value problem can be stated as follows.

Problem 2.1 | Spatial mechanical constitutive initial value problem.

Given the initial values of the internal variables, $\boldsymbol{\alpha}(t_0)$, and the history of the deformation gradient

$$\boldsymbol{F}(t), \quad t \in [t_0, t_f], \tag{2.91}$$

find the functions for $\boldsymbol{\sigma}(t)$ and $\boldsymbol{\alpha}(t)$ such that the constitutive equations

$$\boldsymbol{\sigma} = \rho \frac{\partial \psi}{\partial \boldsymbol{F}} \boldsymbol{F}^T, \tag{2.92}$$

$$\psi = \psi(\boldsymbol{F}, \boldsymbol{\alpha}), \tag{2.93}$$

$$\dot{\boldsymbol{\alpha}} = f(\boldsymbol{F}, \boldsymbol{\alpha}), \tag{2.94}$$

are satisfied for every $t \in [t_0, t_f]$.

Alternatively, in the material description it is stated as presented below.

Problem 2.2 | Material mechanical constitutive initial value problem.

Given the initial values of the internal variables, $\boldsymbol{\alpha}(t_0)$, and the history of the deformation gradient

$$\boldsymbol{F}(t), \quad t \in [t_0, t_f], \tag{2.95}$$

find the functions for $\boldsymbol{P}(t)$ and $\boldsymbol{\alpha}(t)$ such that the constitutive equations

$$\boldsymbol{P} = \rho_0 \frac{\partial \psi}{\partial \boldsymbol{F}}, \tag{2.96}$$

$$\psi = \psi(\boldsymbol{F}, \boldsymbol{\alpha}), \tag{2.97}$$

$$\dot{\boldsymbol{\alpha}} = f(\boldsymbol{F}, \boldsymbol{\alpha}), \tag{2.98}$$

are satisfied for every $t \in [t_0, t_f]$.

With all the main ingredients presented before, it is now possible to finally set the weak form of the quasi-static mechanical constitutive initial value problem. Assume that a body $\mathscr{B}$ is made from a generic material which is characterized by a given constitutive model whose internal variables are known at the initial time t_0 (see Figure 2.2). In addition, assume that the body interior is subjected to a prescribed history of body forces, $\boldsymbol{b}(\boldsymbol{X}, t), t \in [t_0, t_f]$, and to the folowing boundary conditions:

- **Natural (or Neumann) boundary condition**. The boundary portion $\Omega_{\text{traction},0}$ of $\mathscr{B}$ is subjected to a prescribed history of traction forces, $\boldsymbol{t}_{\text{presc}}(\boldsymbol{X}, t)$, $\boldsymbol{X} \in \partial\Omega_{\text{traction},0}$, $t \in [t_0, t_f]$;
- **Essential (or Dirichlet) boundary condition**. The boundary portion $\Omega_{\text{motion},0}$ of $\mathscr{B}$ is subjected to a prescribed displacement field history, $\boldsymbol{u}_{\text{presc}}(\boldsymbol{X}, t)$, such that[2]

$$\boldsymbol{\varphi}_{\text{presc}}(\boldsymbol{X}, t) = \boldsymbol{X} + \boldsymbol{u}_{\text{presc}}(\boldsymbol{X}, t), \quad \boldsymbol{X} \in \partial\Omega_{\text{motion},0}, \quad t \in [t_0, t_f]. \tag{2.99}$$

  It is also convenient to define the set of kinematically admissible displacements of $\mathscr{B}$ as the set of all sufficiently regular displacement functions that satisfy the essential boundary condition (kinematical constraint) (de Souza Neto et al., 2008),

$$\mathscr{K} = \{\boldsymbol{u} : \Omega_0 \times \mathscr{R} \to \mathscr{U} \mid \boldsymbol{u}(\boldsymbol{X}, t) = \boldsymbol{u}_{\text{presc}}(\boldsymbol{X}, t), \quad \boldsymbol{X} \in \partial\Omega_{\text{motion},0}, \quad t \in [t_0, t_f]\}. \tag{2.100}$$

[2] For simplicy, it is assumed that $\partial\Omega_{\text{traction},0} \cap \partial\Omega_{\text{motion},0} = \emptyset$.

The weak form of the quasi-static mechanical constitutive initial boundary value problem can thus be stated in a spatial description as follows.

Problem 2.3 | Spatial quasi-static mechanical initial BVP.

Find a kinematically admissible displacement function, $\boldsymbol{u} \in \mathscr{K}$, such that for every $t \in [t_0, t_f]$, the body $\mathscr{B}$ is in equilibrium as stated by the Virtual Work Principle

$$\int_{\Omega} \left[\boldsymbol{\sigma} : \nabla \boldsymbol{\eta} - \boldsymbol{b} \cdot \boldsymbol{\eta} \right] \mathrm{d}v - \int_{\partial\Omega} \boldsymbol{t} \cdot \boldsymbol{\eta} \, \mathrm{d}a = 0, \quad \forall \boldsymbol{\eta} \in \mathscr{V}, \tag{2.101}$$

where the space of virtual displacements at time t is defined by

$$\mathscr{V} = \left\{ \boldsymbol{\eta} : \Omega \to \mathscr{U} \mid \boldsymbol{\eta} = \boldsymbol{0} \quad \text{in} \quad \partial\Omega_{\text{motion},0} \right\}, \tag{2.102}$$

and, at each point of $\mathscr{B}$, the Cauchy stress tensor is the solution of the spatial mechanical constitutive initial value problem (see page 34).

For the sake of completeness, the weak form of the quasi-static mechanical constitutive initial boundary value problem can be stated in a material description as presented below.

Problem 2.4 | Material quasi-static mechanical initial BVP.

Find a kinematically admissible displacement function, $\boldsymbol{u} \in \mathscr{K}$, such that for every $t \in [t_0, t_f]$, the body $\mathscr{B}$ is in equilibrium as stated by the Virtual Work Principle

$$\int_{\Omega_0} \left[\boldsymbol{P} : \nabla_0 \boldsymbol{\eta} - \boldsymbol{b}_0 \cdot \boldsymbol{\eta} \right] \mathrm{d}v - \int_{\partial\Omega_0} \boldsymbol{t}_0 \cdot \boldsymbol{\eta} \, \mathrm{d}a = 0, \quad \forall \boldsymbol{\eta} \in \mathscr{V}, \tag{2.103}$$

where the space of virtual displacements at time t is defined by

$$\mathscr{V} = \left\{ \boldsymbol{\eta} : \Omega_0 \to \mathscr{U} \mid \boldsymbol{\eta} = \boldsymbol{0} \quad \text{in} \quad \partial\Omega_{\text{motion},0} \right\}, \tag{2.104}$$

and, at each point of $\mathscr{B}$, the First Piola-Kirchhoff stress tensor is the solution of the material mechanical constitutive initial value problem (see page 35).

2.8 Time discretization

To accurately describe the mechanical behavior of many structural materials found in engineering, the corresponding constitutive constitutive models are said to be path-dependent. From a physical point of view, this means that the material stress state does not depend only on the instantaneous deformation state but also on the deformation history to which the material has been subjected. As was previously seen, this information about the intrinsic material state is stored in the set of internal variables associated with the constitutive model. To numerically deal with such constitutive models, it is essential to use an appropriate numerical algorithm to integrate the constitutive equations over time. The starting point of these algorithms is usually the discretization of the time domain $[t_0, t_f]$ in a given number of increments along with the assumption of a given hypothesis on the deformation path between adjacent time steps.

In the present document, it is adopted an algorithm based in approximated incremental constitutive functions. Attending to the mechanical constitutive initial boundary value problem (see page 34) and considering the time increment $[t_n, t_{n+1}]$, such approach is summarized in the following two requirements:



Figure 2.2: Quasi-static mechanical constitutive initial boundary value problem.

- **Cauchy and First Piola-Kirchhoff stress tensors**. Assuming that the set of internal variables $\boldsymbol{\alpha}_n$ is known at t_n, the Cauchy stress tensor $\boldsymbol{\sigma}_{n+1}$ must be uniquely determined by the prescribed deformation gradient $\boldsymbol{F}_{n+1}$ prescribed at t_{n+1} as

$$\boldsymbol{\sigma}_{n+1} = \hat{\boldsymbol{\sigma}}(\boldsymbol{F}_{n+1}, \boldsymbol{\alpha}_n), \tag{2.105}$$

  where $\hat{\boldsymbol{\sigma}}$ is the incremental constitutive function for the Cauchy stress tensor. In a similar way, the First Piola-Kirchhoff stress tensor $\boldsymbol{P}_{n+1}$ must be uniquely determined by the prescribed deformation gradient $\boldsymbol{F}_{n+1}$ prescribed at t_{n+1} as

$$\boldsymbol{P}_{n+1} = \hat{\boldsymbol{P}}(\boldsymbol{F}_{n+1}, \boldsymbol{\alpha}_n), \tag{2.106}$$

  where $\hat{\boldsymbol{P}}$ is the incremental constitutive function for the First Piola-Kirchhoff stress tensor.

- **Set of internal variables**. Assuming that the set of internal variables $\boldsymbol{\alpha}_n$ is known at t_n, the set of internal variables must be uniquely determined by the prescribed deformation gradient $\boldsymbol{F}_{n+1}$ prescribed at t_{n+1} as

$$\boldsymbol{\alpha}_{n+1} = \hat{\boldsymbol{\alpha}}(\boldsymbol{F}_{n+1}, \boldsymbol{\alpha}_n), \tag{2.107}$$

  where $\hat{\boldsymbol{\alpha}}$ is the incremental constitutive function for the set of internal variables.

Generally the incremental constitutive functions are nonlinear and are expected to converge to the exact solution as the strain increments are reduced.

Applying the aforementioned time discretization to the weak form of the quasi-static mechanical constitutive initial boundary value problem, we can then state it in the spatial description as

Problem 2.5 | Spatial incremental quasi-static mechanical initial BVP.

Given the set of internal variables $\boldsymbol{\alpha}_n$ at t_n, the prescribed body and traction force fields $\boldsymbol{b}_{n+1}$ and $\boldsymbol{t}_{n+1}$ at t_{n+1}, and the prescribed deformationg gradient $\boldsymbol{F}_{n+1}$ at t_{n+1}, find the kinematically admissible displacement field $\boldsymbol{u}_{n+1} \in \mathscr{K}_{n+1}$ such that the body $\mathscr{B}$ is in equilibrium as stated by the Virtual Work Principle

$$\int_{\Omega_{n+1}} \left[\hat{\boldsymbol{\sigma}}(\boldsymbol{F}_{n+1}, \boldsymbol{\alpha}_n) : \nabla\boldsymbol{\eta} - \boldsymbol{b}_{n+1} \cdot \boldsymbol{\eta}\right] \mathrm{d}v - \int_{\partial\Omega_{n+1}} \boldsymbol{t}_{n+1} \cdot \boldsymbol{\eta}\, \mathrm{d}a = 0, \quad \forall \boldsymbol{\eta} \in \mathscr{V}, \tag{2.108}$$

where the space of kinematically admissible displacement fields $\mathscr{K}_{n+1}$ is defined by

$$\mathscr{K}_{n+1} = \left\{ \boldsymbol{u} : \Omega \times \mathscr{R} \to \mathscr{U} \mid \boldsymbol{u}_{n+1}(\boldsymbol{X}) = \boldsymbol{u}_{\mathrm{presc},n+1}(\boldsymbol{X}), \quad \boldsymbol{X} \in \partial\Omega_{\mathrm{motion},0} \right\}. \tag{2.109}$$

and in the material description as

Problem 2.6 | Material incremental quasi-static mechanical initial BVP.

Given the set of internal variables $\boldsymbol{\alpha}_n$ at t_n, the prescribed body and traction forces fields $\boldsymbol{b}_{0,n+1}$ and $\boldsymbol{t}_{0,n+1}$ at t_{n+1}, and the prescribed deformationg gradient $\boldsymbol{F}_{n+1}$ at t_{n+1}, find the kinematically admissible displacement field $\boldsymbol{u}_{n+1} \in \mathscr{K}_{n+1}$ such that the body $\mathscr{B}$ is in equilibrium as stated by the Virtual Work Principle

$$\int_{\Omega_0} \left[\hat{\boldsymbol{P}}(\boldsymbol{F}_{n+1}, \boldsymbol{\alpha}_n) : \nabla_0\boldsymbol{\eta} - \boldsymbol{b}_{0,n+1} \cdot \boldsymbol{\eta}\right] \mathrm{d}v - \int_{\partial\Omega_0} \boldsymbol{t}_{0,n+1} \cdot \boldsymbol{\eta}\, \mathrm{d}a = 0, \quad \forall \boldsymbol{\eta} \in \mathscr{V}, \tag{2.110}$$

where the space of kinematically admissible displacement fields $\mathscr{K}_{n+1}$ is defined by

$$\mathscr{K}_{n+1} = \left\{ \boldsymbol{u} : \Omega \times \mathscr{R} \to \mathscr{U} \mid \boldsymbol{u}_{n+1}(\boldsymbol{X}) = \boldsymbol{u}_{\mathrm{presc},n+1}(\boldsymbol{X}), \quad \boldsymbol{X} \in \partial\Omega_{\mathrm{motion},0} \right\}. \tag{2.111}$$

2.9 Finite Element Method

Having established the incremental weak form of the quasi-static mechanical constitutive initial boundary value problem, an approximated solution can now be obtained by the use of the Finite Element Method. This method is essentially based in the space domain discretization and associated field interpolation.

2.9.1 Finite element concept

The starting point of the application of the Finite Element Method is the discretization h of the continuum domain Ω in a finite set of n_{elem} subdomains called finite elements, $\Omega^{(e)}$. The discretized domain, ${}^h\Omega$, is therefore an approximation to the continuum domain expressed by

$$\Omega \approx {}^h\Omega = \bigcup_{e=1}^{n_{\mathrm{elem}}} \Omega^{(e)}. \tag{2.112}$$

The space of virtual displacements $\mathscr{V}$ as well as the space of kinematically admissible displacement fields $\mathscr{K}$ must also take their discretized forms denoted by ${}^h\mathscr{V}$ and ${}^h\mathscr{K}$.

2.9.2 Interpolation functions

Let e be a generic finite element with n_{nodes} nodes where each node i of coordinates $\boldsymbol{x}_i$ is associated with an interpolation function $N_i^{(e)}$. Such interpolation functions are usually called shape functions and perform the required field interpolations inside the element domain $\Omega^{(e)}$.

Let $a(\boldsymbol{x})$ be a generic field defined over $\Omega^{(e)}$. The interpolation of $a(\boldsymbol{x})$ at any point $\boldsymbol{x}$ inside the element is defined by the element shape functions as

$$a(\boldsymbol{x}) \approx {}^h a(\boldsymbol{x}) = \sum_{i=1}^{n_{\text{nodes}}} a(\boldsymbol{x}_i)\, N_i^{(e)}(\boldsymbol{x})\,. \tag{2.113}$$

If $a(\boldsymbol{x})$ is instead a generic field defined over the global domain Ω, the interpolation of $a(\boldsymbol{x})$ at any point $\boldsymbol{x}$ is defined by the global shape functions as

$$a(\boldsymbol{x}) \approx {}^h a(\boldsymbol{x}) = \sum_{i=1}^{n_{\text{points}}} a(\boldsymbol{x}_i)\, N_i^{g}(\boldsymbol{x})\,, \tag{2.114}$$

where n_{points} is the total number of nodes of the finite element mesh. The discretized spaces ${}^h\mathscr{V}$ and ${}^h\mathscr{K}$ can now be defined as

$${}^h\mathscr{K} = \left\{ {}^h\boldsymbol{u}(\boldsymbol{x}) = \sum_{i=1}^{n_{\text{points}}} \boldsymbol{u}(\boldsymbol{x}_i)\, N_i^{g}(\boldsymbol{x}) \,|\, \boldsymbol{u}(\boldsymbol{x}_i) = \boldsymbol{u}_{\text{presc}}(\boldsymbol{x}_i) \quad \text{if } \boldsymbol{x}_i \in \partial\Omega_{\text{motion},0} \right\}, \tag{2.115}$$

$${}^h\mathscr{V} = \left\{ {}^h\boldsymbol{\eta}(\boldsymbol{x}) = \sum_{i=1}^{n_{\text{points}}} \boldsymbol{\eta}(\boldsymbol{x}_i)\, N_i^{g}(\boldsymbol{x}) \,|\, \boldsymbol{\eta}(\boldsymbol{x}_i) = \boldsymbol{0} \quad \text{if } \boldsymbol{x}_i \in \partial\Omega_{\text{motion},0} \right\}. \tag{2.116}$$

2.9.3 Interpolation matrix and discrete gradient operators

By convenience, the global shape functions can be assembled in the so-called global interpolation matrix as

$$\mathbf{N}^g(\boldsymbol{x}) = \left[\text{diag}[N_1^g(\boldsymbol{x})] \quad \text{diag}[N_2^g(\boldsymbol{x})] \quad \cdots \quad \text{diag}[N_{n_{\text{points}}}^g(\boldsymbol{x})] \right], \tag{2.117}$$

where $\text{diag}[N_i^g(\boldsymbol{x})]$ is a diagonal matrix $n_{\text{dim}} \times n_{\text{dim}}$

$$\text{diag}[N_i^g] = \begin{bmatrix} N_i^g & 0 & \cdots & 0 \\ 0 & N_i^g & \cdots & 0 \\ \vdots & \vdots & \ddots & \vdots \\ 0 & 0 & \cdots & N_i^g \end{bmatrix}. \tag{2.118}$$

where n_{dim} is the number of degrees of freedom per node.

Considering for example that $\boldsymbol{a}(\boldsymbol{x})$ is the displacement field $\boldsymbol{u}(\boldsymbol{x})$ defined over the global domain Ω, it is then possible to defined the global vector of nodal displacements as

$$\mathbf{u} = \left[u_1^1, \ldots, u_{n_{\text{dim}}}^1, \ldots, u_1^{n_{\text{points}}}, \ldots, u_{n_{\text{dim}}}^{n_{\text{points}}} \right]^T, \tag{2.119}$$

and at any point $\boldsymbol{x}$ it is possible to write

$${}^h\boldsymbol{u}(\boldsymbol{x}) = \mathbf{N}^g(\boldsymbol{x})\,\mathbf{u}, \quad {}^h\boldsymbol{u} \in {}^h\mathscr{K}\,. \tag{2.120}$$

It is also convenient to define the discrete symmetric global gradient operator, $\mathbf{B}^g$, and the discrete global gradient operator, $\mathbf{G}^g$. For instance, in a 2D problem where a cartesian coordinate system is employed, these discrete operators are defined as

$$\mathbf{B}^g = \begin{bmatrix} \frac{\partial N_1^g}{\partial x} & 0 & \frac{\partial N_2^g}{\partial x} & 0 & \cdots & \frac{\partial N_{n_{\text{points}}}^g}{\partial x} & 0 \\ 0 & \frac{\partial N_1^g}{\partial y} & 0 & \frac{\partial N_2^g}{\partial y} & \cdots & 0 & \frac{\partial N_{n_{\text{points}}}^g}{\partial y} \\ \frac{\partial N_1^g}{\partial y} & \frac{\partial N_1^g}{\partial x} & \frac{\partial N_2^g}{\partial y} & \frac{\partial N_2^g}{\partial x} & \cdots & \frac{\partial N_{n_{\text{points}}}^g}{\partial y} & \frac{\partial N_{n_{\text{points}}}^g}{\partial x} \end{bmatrix}, \tag{2.121}$$

and

$$\mathbf{G}^g = \begin{bmatrix} \frac{\partial N_1^g}{\partial x} & 0 & \frac{\partial N_2^g}{\partial x} & 0 & \cdots & \frac{\partial N_{n_{\text{points}}}^g}{\partial x} & 0 \\ 0 & \frac{\partial N_1^g}{\partial x} & 0 & \frac{\partial N_2^g}{\partial x} & \cdots & 0 & \frac{\partial N_{n_{\text{points}}}^g}{\partial x} \\ \frac{\partial N_1^g}{\partial y} & 0 & \frac{\partial N_2^g}{\partial y} & 0 & \cdots & \frac{\partial N_{n_{\text{points}}}^g}{\partial y} & 0 \\ 0 & \frac{\partial N_1^g}{\partial y} & 0 & \frac{\partial N_2^g}{\partial y} & \cdots & 0 & \frac{\partial N_{n_{\text{points}}}^g}{\partial y} \end{bmatrix}. \tag{2.122}$$

2.9.4 Spatial discretization

Applying the aforementioned finite element discretization to the incremental quasi-static mechanical constitutive initial boundary value problem (see page 38), we can then write in the spatial description

$$\int_{^h\Omega} \left[\hat{\boldsymbol{\sigma}}^T(\boldsymbol{F}_{n+1}, \boldsymbol{\alpha}_n) \mathbf{B}^g \boldsymbol{\eta} - \mathbf{b}_{n+1} \cdot \mathbf{N}^g \boldsymbol{\eta} \right] \mathrm{d}v - \int_{\partial^h\Omega_{\text{traction}}} \mathbf{t}_{n+1} \cdot \mathbf{N}^g \boldsymbol{\eta} \, \mathrm{d}a = 0, \quad \forall \boldsymbol{\eta} \in {}^h\mathcal{V}, \tag{2.123}$$

where $\mathbf{B}^g$ is employed due to the symmetry of the Cauchy stress tensor. The above equation can be rewritten as

$$\left\{ \int_{^h\Omega} \left[(\mathbf{B}^g)^T \hat{\boldsymbol{\sigma}}(\boldsymbol{\alpha}_n, \boldsymbol{F}_{n+1}) - (\mathbf{N}^g)^T \mathbf{b}_{n+1} \right] \mathrm{d}v - \int_{\partial^h\Omega_{\text{traction}}} (\mathbf{N}^g)^T \mathbf{t}_{n+1} \, \mathrm{d}a \right\}^T \boldsymbol{\eta} = 0, \quad \forall \boldsymbol{\eta} \in {}^h\mathcal{V}, \tag{2.124}$$

and, since it must be satisfied for any $\eta \in {}^h\mathcal{V}$, the incremental quasi-static discretized mechanical constitutive initial boundary value problem can thus be stated in the spatial description as

Problem 2.7 | Spatial incremental discretized quasi-static mechanical initial BVP.

Given the set of internal variables $\boldsymbol{\alpha}_n$ at t_n, the prescribed body and traction forces fields $\boldsymbol{b}_{n+1}$ and $\boldsymbol{t}_{n+1}$ at t_{n+1}, and the prescribed deformation gradient $\boldsymbol{F}_{n+1}$ at t_{n+1}, find the kinematically admissible nodal displacement field $\mathbf{u}_{n+1} \in {}^h\mathscr{K}_{n+1}$ such that the body $\mathscr{B}$ is in equilibrium as stated by the Virtual Work Principle

$$\mathbf{r}(\mathbf{u}_{n+1}) = \mathbf{f}^{\text{int}}(\mathbf{u}_{n+1}) - \mathbf{f}^{\text{ext}}_{n+1} = \mathbf{0}, \tag{2.125}$$

where $\mathbf{f}^{\text{int}}$ e $\mathbf{f}^{\text{ext}}_{n+1}$ are the global vectors of internal and external forces defined as

$$\mathbf{f}^{\text{int}} = \int_{{}^h\Omega} (\mathbf{B}^g)^T \hat{\boldsymbol{\sigma}}(\boldsymbol{F}_{n+1}, \boldsymbol{\alpha}_n)\, \mathrm{d}v, \tag{2.126}$$

$$\mathbf{f}^{\text{ext}}_{n+1} = \int_{{}^h\Omega} (\mathbf{N}^g)^T \mathbf{b}_{n+1}\, \mathrm{d}v + \int_{\partial^h\Omega_{\text{traction}}} (\mathbf{N}^g)^T \mathbf{t}_{n+1}\, \mathrm{d}a. \tag{2.127}$$

Following exactly the same procedure, the incremental quasi-static discretized mechanical constitutive initial boundary value problem can be stated in the material description as

Problem 2.8 | Material incremental discretized quasi-static mechanical initial BVP.

Given the set of internal variables $\boldsymbol{\alpha}_n$ at t_n, the prescribed body and traction forces fields $\boldsymbol{b}_{0,n+1}$ and $\boldsymbol{t}_{0,n+1}$ at t_{n+1}, and the prescribed deformation gradient $\boldsymbol{F}_{n+1}$ at t_{n+1}, find the kinematically admissible nodal displacement field $\mathbf{u}_{n+1} \in {}^h\mathscr{K}_{n+1}$ such that the body $\mathscr{B}$ is in equilibrium as stated by the Virtual Work Principle

$$\mathbf{r}(\mathbf{u}_{n+1}) = \mathbf{f}^{\text{int}}(\mathbf{u}_{n+1}) - \mathbf{f}^{\text{ext}}_{n+1} = \mathbf{0}, \tag{2.128}$$

where $\mathbf{f}^{\text{int}}$ e $\mathbf{f}^{\text{ext}}_{n+1}$ are the global vectors of internal and external forces defined as

$$\mathbf{f}^{\text{int}} = \int_{{}^h\Omega_0} (\mathbf{G}^g)^T \hat{\mathbf{P}}(\boldsymbol{F}_{n+1}, \boldsymbol{\alpha}_n)\, \mathrm{d}v, \tag{2.129}$$

$$\mathbf{f}^{\text{ext}}_{n+1} = \int_{{}^h\Omega_0} (\mathbf{N}^g)^T \mathbf{b}_{0,n+1}\, \mathrm{d}v + \int_{\partial^h\Omega_{\text{traction},0}} (\mathbf{N}^g)^T \mathbf{t}_{0,n+1}\, \mathrm{d}a. \tag{2.130}$$

The global vectors of internal and external forces are usually obtained by assemblage of their elemental counterparts as

$$\mathbf{f}^{\text{int}} = \mathop{\mathsf{A}}_{e=1}^{n_{\text{elem}}} (\mathbf{f}^{\text{int}})^{(e)}, \tag{2.131}$$

$$\mathbf{f}^{\text{ext}} = \mathop{\mathsf{A}}_{e=1}^{n_{\text{elem}}} (\mathbf{f}^{\text{ext}})^{(e)}, \tag{2.132}$$

where the elemental vectors in the spatial description are defined as

$$(\mathbf{f}^{\text{int}})^{(e)} = \int_{{}^h\Omega^{(e)}} \mathbf{B}^T \hat{\boldsymbol{\sigma}}(\boldsymbol{F}_{n+1}, \boldsymbol{\alpha}_n)\, \mathrm{d}v, \tag{2.133}$$

$$(\mathbf{f}^{\text{ext}}_{n+1})^{(e)} = \int_{{}^h\Omega^{(e)}} \mathbf{N}^T \mathbf{b}_{n+1}\, \mathrm{d}v + \int_{\partial^h\Omega^{(e)}_{\text{traction}}} \mathbf{N}^T \mathbf{t}_{n+1}\, \mathrm{d}a, \tag{2.134}$$

and in the material description as

$$(\mathbf{f}^{\text{int}})^{(e)} = \int_{{}^h\Omega_0^{(e)}} \mathbf{G}^T \hat{\mathbf{P}}(\boldsymbol{F}_{n+1}, \boldsymbol{\alpha}_n)\, \mathrm{d}v\,, \tag{2.135}$$

$$(\mathbf{f}^{\text{ext}}_{n+1})^{(e)} = \int_{{}^h\Omega_0^{(e)}} \mathbf{N}^T \mathbf{b}_{0,n+1}\, \mathrm{d}v + \int_{\partial {}^h\Omega^{(e)}_{\text{traction},0}} \mathbf{N}^T \mathbf{t}_{0,n+1}\, \mathrm{d}a\,. \tag{2.136}$$

The matrices **N**, **B** and **G** are the elemental interpolation matrix, the symmetric elemental gradient operator and the discrete elemental gradient operator respectively.

2.9.5 Newton-Raphson Method

The equilibrium equation (see Equations (2.125) and (2.128)) is generally nonlinear due to geometrial nonlinearities or the nonlinearities associated with the material constitutive behaviour.

The Newton-Raphson Method is an efficient and robust iterative scheme which is particulary attractive to solve the equilibrium equation, namely due to its quadratic convergence rate. Given a generic nonlinear equation

$$\boldsymbol{F}(\boldsymbol{x}) = \mathbf{0}, \tag{2.137}$$

where $\boldsymbol{F}$ maps $\mathscr{R}^n$ into $\mathscr{R}^n$, each Newton-Raphon Method iteration (k) consists in the solution of the linearized version of the previous equation as

$$\boldsymbol{J}(\boldsymbol{x}^{(k-1)})\delta\boldsymbol{x} = -\boldsymbol{F}(\boldsymbol{x}^{(k-1)})\,, \quad \delta\boldsymbol{x} = \boldsymbol{x}^{(k)} - \boldsymbol{x}^{(k-1)}\,, \tag{2.138}$$

where $\boldsymbol{J}$ is the so-called Jacobian matrix defined by

$$\boldsymbol{J} = \frac{\partial \boldsymbol{F}}{\partial \boldsymbol{x}}\,. \tag{2.139}$$

The linearized version of the spatial equilibrium equation (derived in detail in de Souza Neto et al. (2008)) is given by

$$\left\{\int_{{}^h\Omega} (\mathbf{G}^g)^T \mathbf{a} \mathbf{G}^g\, \mathrm{d}v\right\} \delta\boldsymbol{u}\cdot\boldsymbol{\eta} = -\left\{\int_{{}^h\Omega} \left[\, (\mathbf{B}^g)^T \hat{\boldsymbol{\sigma}}(\boldsymbol{F}_{n+1}, \boldsymbol{\alpha}_n) - (\mathbf{N}^g)^T \mathbf{b}_{n+1} \,\right] \mathrm{d}v \right.$$
$$\left. - \int_{\partial {}^h\Omega_{\text{traction}}} (\mathbf{N}^g)^T \mathbf{t}_{n+1}\, \mathrm{d}a \right\} \cdot \boldsymbol{\eta}\,, \quad \forall \boldsymbol{\eta} \in {}^h\mathscr{V}\,, \tag{2.140}$$

where **a** is the consistent spatial tangent modulus and, since it must be satisfied for any $\boldsymbol{\eta} \in {}^h\mathscr{V}$, it comes

$$\left\{\int_{{}^h\Omega} (\mathbf{G}^g)^T \mathbf{a} \mathbf{G}^g\, \mathrm{d}v\right\} \delta\boldsymbol{u} = -\left\{\int_{{}^h\Omega} \left[\, (\mathbf{B}^g)^T \hat{\boldsymbol{\sigma}}(\boldsymbol{F}_{n+1}, \boldsymbol{\alpha}_n) - (\mathbf{N}^g)^T \mathbf{b}_{n+1} \,\right] \mathrm{d}v \right.$$
$$\left. - \int_{\partial {}^h\Omega_{\text{traction}}} (\mathbf{N}^g)^T \mathbf{t}_{n+1}\, \mathrm{d}a \right\}, \quad \forall \boldsymbol{\eta} \in {}^h\mathscr{V}\,. \tag{2.141}$$

Thus, attending to the Equation (2.138), each Newton-Raphson Method iteration (k) consists in solving the following system of linear equations

$$\mathbf{K}_T\left(\mathbf{u}_{n+1}^{(k-1)}\right)\delta\mathbf{u} = -\mathbf{r}\left(\mathbf{u}_{n+1}^{(k-1)}\right), \tag{2.142}$$

where the Jacobian matrix $\mathbf{K}_T$ is so-called global tangent stiffness matrix defined as

$$\mathbf{K}_T = \frac{\partial \mathbf{r}}{\partial \mathbf{u}_{n+1}} = \int_{h\Omega} (\mathbf{G}^g)^T \mathbf{a} \mathbf{G}^g \, \mathrm{d}v. \tag{2.143}$$

In alternative, the linearized version of the material equilibrium equation is given by

$$\left\{ \int_{h\Omega_0} (\mathbf{G}^g)^T \mathbf{A} \mathbf{G}^g \, \mathrm{d}v \right\} \delta \boldsymbol{u} \cdot \boldsymbol{\eta} = -\left\{ \int_{h\Omega_0} \left[(\mathbf{G}^g)^T \hat{\mathbf{P}}(\boldsymbol{F}_{n+1}, \boldsymbol{\alpha}_n) - (\mathbf{N}^g)^T \mathbf{b}_{0,n+1} \right] \mathrm{d}v - \int_{\partial^h \Omega_{\text{traction},0}} (\mathbf{N}^g)^T \mathbf{t}_{0,n+1} \, \mathrm{d}a \right\} \cdot \boldsymbol{\eta}, \quad \forall \boldsymbol{\eta} \in {}^h\mathscr{V}, \tag{2.144}$$

where $\mathbf{A}$ is the consistent material tangent modulus and, since it must be satisfied for any $\boldsymbol{\eta} \in {}^h\mathscr{V}$, it comes

$$\left\{ \int_{h\Omega_0} (\mathbf{G}^g)^T \mathbf{A} \mathbf{G}^g \, \mathrm{d}v \right\} \delta \boldsymbol{u} = -\left\{ \int_{h\Omega_0} \left[(\mathbf{G}^g)^T \hat{\mathbf{P}}(\boldsymbol{F}_{n+1}, \boldsymbol{\alpha}_n) - (\mathbf{N}^g)^T \mathbf{b}_{0,n+1} \right] \mathrm{d}v - \int_{\partial^h \Omega_{\text{traction},0}} (\mathbf{N}^g)^T \mathbf{t}_{0,n+1} \, \mathrm{d}a \right\}, \quad \forall \boldsymbol{\eta} \in {}^h\mathscr{V}. \tag{2.145}$$

Hence, the global tangent stiffness matrix is now defined as

$$\mathbf{K}_T = \frac{\partial \mathbf{r}}{\partial \mathbf{u}_{n+1}} = \int_{h\Omega_0} (\mathbf{G}^g)^T \mathbf{A} \mathbf{G}^g \, \mathrm{d}v. \tag{2.146}$$

Following the same approach as for the global vectors of internal and external forces, the global tangent stiffness matrix is also usually obtained by assemblage of its elemental counterpart as

$$\mathbf{K}_T = \bigwedge_{e=1}^{n_{\text{elem}}} \mathbf{K}_T^{(e)}. \tag{2.147}$$

After solving the system of linear equations and obtain $\delta\mathbf{u}$, the global vector of nodal displacements is updated as

$$\mathbf{u}_{n+1}^{(k)} = \mathbf{u}_n + \Delta \mathbf{u}_{n+1}^{(k)}, \tag{2.148}$$

where $\Delta \mathbf{u}_{n+1}^{(k)}$ is the global incremental vector of nodal displacements defined by

$$\Delta \mathbf{u}_{n+1}^{(k)} = \Delta \mathbf{u}_{n+1}^{(k-1)} + \delta \mathbf{u}, \tag{2.149}$$

and it is implicit that

$$\mathbf{u}_{n+1}^{(k)} = \mathbf{u}_{n+1}^{(k-1)} + \delta \mathbf{u}. \tag{2.150}$$

The iterative cycle is then stopped when the solution $\mathbf{u}_{n+1}^{(m)}$ is deemed to have converged according with a given convergence criteria, i.e., $\mathbf{u}_{n+1} = \mathbf{u}_{n+1}^{(m)}$. For the sake of clarity, the iterative cycle of the Newton-Raphson Method is schematically represented in Figure 2.3 and presented in pseudo-code format in Box 2.1.

$$\mathbf{u}_{n+1} = \mathbf{u}_{n+1}^{(m)}. \tag{2.151}$$

Box 2.1: The Newton-Raphson Method steps in solving a given increment of the nonlinear equilibrium equation.

(i) Initialize iterative counter, $k := 1$

(ii) Set initial guess for displacements, $\mathbf{u}_{n+1}^{(0)} = \mathbf{u}_n$

(iii) Compute initial residual force vector

$$\mathbf{r}(\mathbf{u}_{n+1}^{(0)}) = \mathbf{f}^{\text{int}}(\mathbf{u}_n) - \lambda_{n+1}\mathbf{f}_{\text{total}}^{\text{ext}}$$

(iv) Compute consistent spatial tangent modulus

$$\mathsf{a}_{ijkl} = \frac{1}{J}\mathsf{A}_{imkn}F_{jm}F_{ln}$$

(v) Compute and assemble elemental tangent stiffness matrices

$$\mathbf{K}_T^{(e)} = \sum_{i=1}^{n_{\text{gauss}}} w_i\, \mathbf{G}_i^T \mathbf{a}_i \mathbf{G}_i\, j_i\,, \quad \mathbf{K}_T = \bigwedge_{e=1}^{n_{\text{elem}}} \mathbf{K}_T^{(e)}$$

(vi) Increment iteration counter, $k := k+1$

(vii) Solve the equilibrium system of equations

$$\delta\mathbf{u} = -\mathbf{K}_T^{-1}\left(\mathbf{u}_n^{(k-1)}\right)\mathbf{r}\left(\mathbf{u}_n^{(k-1)}\right)$$

(viii) Update displacements

$$\mathbf{u}_{n+1}^{(k)} = \mathbf{u}_{n+1}^{(k-1)} + \delta\mathbf{u}$$

(ix) Update deformation gradient

$$\boldsymbol{F}_{n+1} = \left[\boldsymbol{I} - \nabla\boldsymbol{u}_{n+1}^{(k)}\right]^{-1}$$

Box 2.1: (continuation)

(xiii) Update stresses and other state variables

$$\boldsymbol{\sigma}_{n+1} = \hat{\boldsymbol{\sigma}}(\boldsymbol{F}_{n+1}, \boldsymbol{\alpha}_n), \qquad \boldsymbol{\alpha}_{n+1} = \hat{\boldsymbol{\alpha}}(\boldsymbol{F}_{n+1}, \boldsymbol{\alpha}_n)$$

(xiv) Compute and assemble elemental internal forces vectors:

$$(\mathbf{f}^{\text{int}})^{(e)} = \sum_{i=1}^{n_{\text{gauss}}} w_i \, \mathbf{B}_i^T \, \hat{\boldsymbol{\sigma}}_i \, j_i, \qquad \mathbf{f}^{\text{int}} = \bigwedge_{e=1}^{n_{\text{elem}}} (\mathbf{f}^{\text{int}})^{(e)}$$

(xv) Update residual force vector

$$\mathbf{r}\left(\mathbf{u}_{n+1}^{(k)}\right) = \mathbf{f}^{\text{int}}(\mathbf{u}_{n+1}^{(k)}) - \lambda_{n+1}\mathbf{f}_{\text{total}}^{\text{ext}}$$

(xvi) Check for convergence

if (converged) then

- Update incremental solution, $(\bullet)_{n+1} = (\bullet)_{n+1}^{(k)}$, and exit

else

- Go to step (iv)



Figure 2.3: Schematic of the Newton-Raphon Method iterative cycle for a given increment $n+1$ of the equilibrium equation in a problem with one degree of freedom.

2.9.6 Proportional loading

So far no algorithm was presented to define the body forces, $\boldsymbol{b}_{n+1}$, and the traction forces, $\boldsymbol{t}_{n+1}$, at instant t_{n+1}. A possible and convenient approach that is here adopted is to assume that the loading is applied in a proportional way, $\lambda(t)$, such that

$$\boldsymbol{b}_{n+1} = \lambda_{n+1}\,\boldsymbol{b}^{\text{total}}, \tag{2.152}$$

$$\boldsymbol{t}_{n+1} = \lambda_{n+1}\,\boldsymbol{t}^{\text{total}}, \tag{2.153}$$

where $\lambda_{n+1} = \lambda(t_{n+1})$ is the prescribed load factor at t_{n+1} and $\boldsymbol{b}^{\text{total}}$ and $\boldsymbol{t}^{\text{total}}$ are the totally prescribed body and traction forces.

According with the aforementioned incremental loading scheme, the main steps required to solve the incremental equilibrium equation are summarized in pseudo-code format in Box 2.2.

Box 2.2: Solution of the incremental equilibrium equation by adopting a proportional loading scheme.

(i) Compute and assemble elemental external forces vector

$$\mathbf{f}^{\text{ext}}_{\text{total}} = \mathop{\mathsf{A}}_{e=1}^{n_{\text{elem}}} (\mathbf{f}^{\text{ext}}_{\text{total}})^{(e)}$$

(ii) Set up the proportional loading curve, $\lambda(t)$

(iii) Initialize increment counter, $n := 0$

(iv) Set load factor at the end of $[t_n, t_{n+1}]$, $\lambda_{n+1} = \lambda(t_{n+1})$

(v) Solve the nonlinear equilibrium equation (see Box 2.1)

$$\mathbf{r}(\mathbf{u}_{n+1}) = \mathbf{f}^{\text{int}}(\mathbf{u}_{n+1}) - \lambda_{n+1}\mathbf{f}^{\text{ext}}_{\text{total}} = \mathbf{0}$$

(vi) Check if the total load was applied

if $(n+1 < n_{\text{incr}})$ then

- Update incremental counter, $n := n+1$, and go to step (iv)

else

- Exit

2.9.7 Numerical integration

In the Finite Element Method, the integrations over the element domain are generally performed numerically by means of the Gaussian Quadrature Method. Let $a(\boldsymbol{x})$ be a generic field and consider the local (or natural) normalized domain Υ. If a mapping $\boldsymbol{x} : \Upsilon \to \Omega^{(e)}$ exists, the integral of $a(\boldsymbol{x})$ over the domain $\Omega^{(e)}$ can be numerically determined as

$$\int_{\Omega^{(e)}} a(\boldsymbol{x})\,\mathrm{d}\boldsymbol{x} = \int_{\Upsilon} a(\boldsymbol{x}(\boldsymbol{\xi}))\,j(\boldsymbol{\xi})\,\mathrm{d}\boldsymbol{\xi} \approx \sum_{i=1}^{n_{\text{gp}}} w_i\,a(\boldsymbol{x}(\boldsymbol{\xi}_i))\,j(\boldsymbol{\xi}_i)\,, \tag{2.154}$$

where $\boldsymbol{\xi}_i$, $i = 1,2,\ldots,n_{\text{gp}}$ and w_i are the positions and weights of the Gauss sampling points in the domain Υ and $j(\boldsymbol{\xi})$ is the determinant of the mapping Jacobian defined as

$$j(\boldsymbol{\zeta}) = \det\left[\frac{\partial \boldsymbol{x}}{\partial \boldsymbol{\xi}}\right]. \tag{2.155}$$

2.10 Multi-scale modeling of heterogeneous materials

In the past century, most of the progress in the modeling of nonlinear heterogeneous materials is associated with the development of phenomenological models at a particular scale. These single-scale models can thus be grouped in several distinct classes according to the time and length scales addressed (Matouš et al., 2017):

- **Density functional theory**. Relying on the quantum-mechanical analysis of the electronic structure of many-bodies systems (electron density functionals), these models aim to describe the complex physical material behavior at the subatomic scale (e.g., Runge and Gross (1984), Becke (1993), Geerlings et al. (2003), Cohen et al. (2008), Burke and Wagner (2013)). Typically these span the smallest length scales ($< 10^{-9}$m) and the smallest time scales ($10^{-15} - 10^{-9}$s), being particularly useful to build and assess the properties of atomic potentials used in molecular dynamics;

- **Molecular dynamics**. Based the Newton's equations of motion applied to single atoms and on atomic potentials to describe the atomic interactions (e.g., Hepburn and Ackland (2008), Yasi et al. (2009), Ventelon and Willaime (2010), Wu et al. (2014)), these models provide insights into the complex mechanisms and phenomena at the level of single phases and interfaces, such as dislocations and microfractures (e.g., Yamakov et al. (2002), Delogu and Cocco (2005). Kang and Cai (2010)). Models range from the atomic scale up to single microns ($10^{-9} - 10^{-6}$m) and still operates on very short time scales ($10^{-12} - 10^{-6}$s);

- **Statistical models**. Using extensive statistical and stochastic sampling methods, statistical models, such as the well-known Monte Carlo method (Metropolis et al. (1953)), construct approximate solutions for a variety of physical problems. Depending on the physical phenomena and mechanisms which are treated in a statistical manner, this class of models is applicable to a wide range of length and time scales, despite being mostly applied at molecular dynamics scales (interfaces, phase transformations, diffusional processes, etc.) (e.g., Raabe (1998), Binder and Heermann (2010));

- **Continuum models**. Continuum models are employed at length scales where the continuum approximation holds, i.e., at the level of individual phases within a microstructure ($10^{-5} - 10^{-3}$m) or at the macroscopic engineering range ($10^{-2} - 10^{2}$m), and larger time scales ($> 10^{-6}$s). A particularly important group of continuum models are those derived from the so-called thermodynamics with internal variables (de Souza Neto et al., 2008), based on the hypothesis that at any instant of a thermodynamical process the thermodynamic state can be completely determined by the knowledge of a finite number of state variables. These constitutive models are often formulated in closed-form analytical equations (to be solved analytically or numerically) and their success to describe the behavior of a particular material depends critically on the choice of an appropriate set of internal variables. Phenomenological approaches set the internal variables by direct association with the material response at the macro-scale level, while micromechanical approaches define them based on the mechanisms and phenomena observed at lower scales.

Traditional continuum models have been successfully applied, in both research and industrial contexts, in the simulation of many engineering problems over the last decades. However, the research and development of materials with optimized properties often lead to highly nonlinear heterogeneous multiphasic materials with complex microstructures where underlying mechanisms and phenomena play critical roles. As a result, the accurate description of their behavior through analytical equations poses difficult challenges to traditional continuum models. On the one hand, when such attempts are made, phenomenological models usually end up requiring several material parameters to be calibrated for a given set of conditions through time-consuming and expensive experiments. On the other hand, micromechanical models are often based on relatively simplified microstructures and idealized descriptions of phenomena and mechanisms. Also, performing direct numerical simulations by taking into account all the heterogeneities from the lower scales leads to problems with unfeasible dimension for realistic engineering problems.

In this context, the modeling of materials using a multi-scale approach emerged as an effective way to overcome the previous limitations and is nowadays a topic of extensive research and increasing interest by the scientific community. Ideally, efficient and accurate predictions of the macroscopic behavior of heterogeneous materials should be uniquely obtained from the constitutive behavior of each separate constituent (material phase) and from the information about the material microstructure (Liu et al., 2016). The main idea and challenge in multi-scale mechanics consists of extracting predictive macroscopic properties of heterogeneous multiphasic materials by resolving the topological, physical and statistical details of the underlying microstructure – this requires the proper definition and quantification of relationships bridging different scales.

Different classifications of multi-scale methods have been proposed in the literature based on different criteria (e.g., Engquist et al. (2007), Fish (2009), Weinan (2011)). If the classification is based on the underlying problem formulation, i.e., the linking between different scales, three typical classes can be distinguished:

- **Concurrent methods**. Methods in which different length and time scales are simultaneously addressed, possibly with different methodologies, in different subvolumes of a singular global domain (e.g., Broughton et al. (1999), Ladevèze et al. (2001), Ibrahimbegović and Markovič (2003), Ghosh et al. (2007), Temizer and Wriggers (2011a), Zhang et al. (2012), Khoei et al. (2015), Bitencourt et al. (2015));
- **Hierarchical methods**. Methods in which different length and time scales are linked in a hierarchical manner, i.e., different scales are coupled and solved in the same part of the global domain;
- **Hybrid methods**. Methods that share properties of both concurrent and hierarchical methods resulting in a hybrid coupling scheme between different length and time scales (e.g., Tadmor et al. (1996), Miehe and Bayreuther (2007), Plews and Duarte (2015)).

In hierarchical multi-scale methods the coupling between scales can be based solely on the parameter identification level or through field averaging theorems. Concerning the latter, the neighboring field of mathematical homogenization inspired engineers to apply proactively homogenization methods to engineering problems, being the homogenization method, originally coined by Babuška (1976), a well-established disciple for the analysis of heterogeneous materials in multi-scale mechanics nowadays (Matouš et al., 2017). Although most of the past and ongoing researches in homogenization methods are limited to the spatial homogenization, some contributions applied this method to both space and time (e.g., Yu and Fish (2002), Ladevèze (2004), Zhang et al. (2007), Crouch et al. (2013), Pham et al. (2013)).

During most of the 20th century, the homogenization method was applied to derive macroscopic constitutive laws and bounds that incorporated the underlying micro-scale

heterogeneities and nonlinearities, the so-called analytical and semi-analytical homogenization methods. Pioneering developments in homogenization date back to the 19th century, when Voigt (Voigt, 1889) and Reuss (Reuss, 1929) proposed uniform strain and stress field approximations that rendered lower and upper bounds to the elastic strain energy of multiphase composites. These approximations soon inspired Taylor (Taylor, 1938) and Sachs (Sachs, 1929) to propose bounds in the nonlinear case. Even though several authors (e.g., Leffers (1979), Van Houtte (1982)) suggested weakening modifications of these assumptions, they typically provide very rough estimates of the overall material properties and are not reliable for complex nonlinear structures (Matouš et al., 2017). Nonetheless, this methodology was the object of further developments in the following decades, starting with the well-known variational formulation of Hashin and Shtrikman (Hashin and Shtrikman, 1963) to obtain bounds on bulk and shear moduli in composites under isotropic conditions. Their bounds were extended to anisotropic media (Walpole, 1966b), to obtain bounds on the Poisson's ratio of the composites (Zimmerman, 1992) and later generalized (e.g., Nemat-Nasser et al. (1993), Nemat-Nasser et al. (1993), Bornert et al. (1996), Li and Dunn (2001)) to predict tighter and more reliable bounds than Voigt's and Reuss' by incorporating microstructural morphology information. Improvements were also achieved by using three-point bounds (e.g., Beran and Molyneux (1966), Milton et al. (1982), Torquato (1991)), including bounds derived for other fields such as thermo-mechanical (e.g., Rosen and Hashin (1970), Gibiansky and Torquato (1997)) and piezo-eletric (e.g., Hori and Nemat-Nasser (1998)).

A distinct and more sophisticated approach was established by Eshelby (Eshelby and Peierls, 1957), describing the elastic behavior of a solid (modeled as an infinite homogeneous matrix) in the presence of a single inclusion. Despite its importance, Eshelby neglected the interactions between heterogeneities by assuming that these were sufficiently distributed in space. To overcome this unrealistic assumption and approximate the interaction between the different material phases, models based on the mean-field approximation (Pierard et al., 2004) were proposed, such as the Mori and Tanaka scheme (e.g., Mori and Tanaka (1973), Benveniste (1987), Luo and Weng (1987)), the self-consistent scheme (e.g., Kröner (1958), Hill (1965b), Walpole (1969), Willis (1977)), the generalized self-consistent scheme (e.g., Kerner (1956), Christensen and Lo (1979), Huang et al. (1994)) and the differential method (e.g., McLaughlin (1977), Norris (1985)). Further contributions to the self-consistent scheme were derived for periodic porous composites (Nemat-Nasser et al., 1982), multilayered spherical heterogeneities (Herve and Zaoui, 1993) and aligned elliptical heterogeneities (Huang and Hu, 1995). In addition, based on the Mori and Tanaka and self-consistent schemes, Hori and Nemat-Nasser proposed the double-inclusion model (Hori and Nemat-Nasser, 1993).

The three decades between 1950 and 1980 were thus marked with significant progress in the homogenization of heterogeneous elastic solids. Extensions to nonlinear material behavior date from the early sixties and seventies (e.g., Kröner (1961), Hill (1965a)), with typical nonlinear phenomena (nonlinear elasticity, visco-elasticity, plasticity, visco-plasticity, creep, etc.) being addressed (Matouš et al., 2017). Pioneering works were devoted to finite deformation elasticity of nonlinear composites by Hill (Hill, 1972) and Ogden (Ogden, 1974), followed by well-known contributions made by Hutchinson (Hutchinson and Hill, 1976) for polycrystalline materials, Willis (Willis, 1986) for nonlinear dielectrics, Ponte Castaneda and Willis (Ponte Castañeda et al., 1988) for two-phase random composites made of nonlinearly viscous phases, Suquet (Suquet, 1993) for power-law composites, Olson (Olson, 1994) for perfectly plastic composites and others. Meanwhile, Ponte Castañeda and coworkers (Castañeda (1991), Castañeda (1992), Ponte Castañeda et al. (1992), deBotton and Castañeda (1993), Castañeda and Suquet (1997)) derived a nonlinear variational principle to estimate the effective property of nonlinear incompressible and compressible composites, followed by the establishment of exact second-order estimates (Castañeda, 1996). This approach was further improved and extended in the following contributions, such as Leroy and Ponte Castañeda (2001), Ponte Castañeda

(2002), Lahellec et al. (2004), Danas et al. (2008). Some recent contributions are devoted to the behavior of fiber-reinforced materials (e.g., Brun et al. (2007), deBotton and Shmuel (2009), Rudykh and deBotton (2012), deBotton and Oren (2013)) and to the modeling of reinforced composites materials considering interface conditions (e.g., Yanase and Ju (2012), Buryachenko (2013), Chatzigeorgiou et al. (2013)).

Having in mind that only a few contributions were here mentioned, some detailed reviews and comparisons of analytical and semi-analytical homogenization methods are left for the interested reader (e.g., Kanaun and Levin (2007), Benveniste and Milton (2010a), Benveniste and Milton (2010b), Dvorak (2012), Jöchen (2013), Ghossein and Lévesque (2014)).

Another critical approach, which rendered important contributions in the homogenization field, is termed asymptotic homogenization, based on asymptotic expansions of strain and stress fields around their corresponding macroscopic values and utilizing variational principles (Saeb et al., 2016). Early developments were made in the 1970s (Sanchez-Palencia (1974), Papanicolau et al. (1978)) and further well-known works followed until recent years (e.g., Guedes and Kikuchi (1990), Terada and Kikuchi (1995), Terada and Kikuchi (1996), Fish et al. (1997), Chung et al. (2001), Kalamkarov et al. (2009), Pinho-da-Cruz et al. (2009), Temizer (2012)).

All the previous works and many others contributed to the development of one of the most powerful methods in homogenization designated computational homogenization, a topic which has been the object of extensive research and achievements, and fundamental to the most recent paradigms of modeling heterogeneous materials (e.g., Geers et al. (2010), Nguyen et al. (2011), Saeb et al. (2016), Geers et al. (2017), Matouš et al. (2017)).

The main idea in computational homogenization multi-scale modeling is to relate the macroscopic constitutive behavior of materials with their underlying heterogeneous microstructure by continuous interchange of information between scales through homogenization. This method is based on the nested solution of boundary value problems (BVPs) at different scales, being most commonly considered two: (1) at the macro-scale, where the material's macroscopic constitutive response is sought, and (2) at the micro-scale, where numerical computations are conducted over representative volume elements in order to account for the microstructure heterogeneities and mechanisms. Although from a theoretical point of view the previous scheme can be readily extended to multiple scales, from a computational point of view, this would be extremely demanding and unfeasible for practical applications as discussed later.

A complete variational foundation for a multi-scale constitutive theory of solids based on computational homogenization has been established by de Souza Neto and coworkers (de Souza Neto and Feijóo (2006), de Souza Neto and Feijóo (2008), Perić et al. (2009), de Souza Neto and Feijóo (2011), Perić et al. (2011), de Souza Neto et al. (2014), Blanco et al. (2014), Blanco et al. (2016)). Their formulation is derived from the Method of Multi-Scale Virtual Power, being guaranteed that it is variationally consistent across the scales. It relies on two basic procedures to relate the kinematic descriptors from both scales: the kinematic insertion, which defines how the macro-scale kinematical quantities contribute to the micro-scale kinematics, and the kinematic homogenization, which establishes how the micro-scale kinematical quantities are averaged over the representative domain and related to their macro-scale counterparts. The constraint defining the kinematical admissibility, i.e., the minimal kinematical admissible constraint, is the result of the compatibilization between both kinematic insertion and homogenization definitions. The enforcement of such minimal constraint yields the so-called uniform traction boundary condition and additional restrictions lead to other micro-scale boundary conditions. In turn, the Principle of Multi-Scale Virtual Power (PMVP), which degenerates into the well-known Hill-Mandel Principle for the standard first-order homogenization formulation, establishes the energetic equivalence of the virtual power between the two scales. Its application renders the derivation of the micro-scale equilibrium equations over the micro-scale representative domain, subjected to a given set of admissible boundary conditions, as well as the stress homogenization procedure.

When modeling geometric and material nonlinearities in heterogeneous materials, analyzing realistic microstructures is critical for achieving high-fidelity predictive capabilities. Heterogeneous materials may contain a variety of heterogeneous phases (voids, inclusions, fibers, crystals, etc.) of varying composition, size and shape arranged in complex spatial distributions (Matouš et al., 2017). Therefore, it is crucial to develop a representative computational domain of the microstructure in order to perform accurate and efficient multi-scale simulations, i.e., a domain that accurately predicts the effective material behaviour (physically meaningful) and that preserves the geometrical and morphological complexity of the microstructure (statistically representative). Such a representative domain must satisfy the so-called Principle of Scales Separation, which requires that its characteristic dimension must be simultaneously much smaller than the macroscopic characteristic dimension and much bigger than the characteristic dimensions of the microstructure heterogeneities.

Hill (Hill, 1963) was the first to propose the so-called representative volume element (RVE), defined as a volume of material sufficiently large such that (1) it contains enough morphological and topological information about the microstructure heterogeneities to be representative in an average sense and (2) provides the same response under both homogeneous boundary conditions (Sab (1992), Ostoja-Starzewski (1998)). Three decades later, Drugen and Willis (Drugan and Willis, 1996) proposed an alternative definition of RVE as the sufficiently large volume of material that accurately captures the mean constitutive response of the microstructure. At the same time, Porvik (Povirk, 1995) followed a different approach and coined the representative unit cell (RUC), an optimally sized domain that preserves the statistical description of the original microstructure and for which the morphology approximation error is quantified with statistical descriptors. Since then, an extensive body of literature has been devoted to this fundamental topic, accounting for different representative domain definitions (e.g., Shan and Gokhale (2002), Kanit et al. (2003), Swaminathan et al. (2006), Swaminathan and Ghosh (2006), Jafari et al. (2011), Balzani et al. (2014), Scheunemann et al. (2015)), the appropriate size for distinct heterogeneous materials and material behavior regimes (e.g., Ostoja-Starzewski (2006), Temizer and Zohdi (2007), Gitman et al. (2007), Galli et al. (2012), Harper et al. (2012), Temizer et al. (2013), Moussaddy et al. (2013), Dirrenberger et al. (2014), Hoang et al. (2016)) and the effects of the shape of heterogeneities and their spatial distribution through analytical and numerical methods (e.g., Kouznetsova et al. (2001), Wongsto and Li (2005), Segurado and LLorca (2006), Kari et al. (2007), Li et al. (2011), Mortazavi et al. (2013), Mikdam et al. (2013), Altendorf et al. (2014), El Moumen et al. (2015)).

Given its influence in the solution of the micro-scale equilibrium problem, the choice of the appropriate boundary conditions to be imposed on the RVE and associated limitations has been a topic of long discussion (e.g., Pecullan et al. (1999), Jiang et al. (2001), Mesarovic and Padbidri (2005), Ostoja-Starzewski (2006), Shen and Brinson (2006), Drago and Pindera (2007), Larsson and Runesson (2007)). Nonetheless, linear displacement, periodic displacement and uniform traction boundary conditions are generally accepted as the most common ones, being the former and latter sometimes referred to as homogeneous boundary conditions. Several contributions (e.g., Suquet (1985), Hollister and Kikuchi (1992), Nemat-Nasser and Hori (1995), Terada et al. (2000), Miehe (2002)) have shown that these provide respectively lower and upper bounds to the effective behavior derived under periodic boundary conditions for a finite size of the RVE in pure mechanical problems. Although this does not imply that the periodic boundary conditions result in the most accurate solution, they are often applied considering their bounded nature and due to the fact that the resulting homogenized properties converge faster to their real values as the RVE size increases (Terada et al. (2000), Kanit et al. (2003)). Other sets of admissible boundary conditions have been proposed (e.g., Coenen et al. (2012c), Mercer et al. (2015)) as well as different formulation strategies to enforce them (e.g., Larsson et al. (2011), Glüge (2013), Reis and Andrade Pires (2014)). Also, aspects of the numerical solution and computational cost associated with different boundary conditions are investigated by (Fritzen and Böhlke, 2010).

The computational homogenization scheme previously formulated has initially been developed and applied for purely mechanical nonlinear quasi-static problems and, given its highly modular nature and ease of implementation, several different numerical schemes were developed and combined to this day (e.g., Ghosh and Moorthy (1995), Ghosh et al. (1995), Moorthy and Ghosh (1996), Moulinec and Suquet (1998), Michel et al. (1999b), Kamiński (1999), Okada et al. (2001), Procházka (2001), Lebensohn (2001), Moës et al. (2003), Miehe and Dettmar (2004), Brisard and Dormieux (2010), Monchiet and Bonnet (2012a), Spahn et al. (2014), Nguyen et al. (2014), Guo and Zhao (2014), Kabel et al. (2015)). A particular numerical approach based on the Finite Element Method (FEM) started with the pioneering works of Renard and Marmonier (1987), who first introduced the idea of using a finite element discretization at the micro-scale representative domain, and the contribution of Smit et al. (1998), who introduced a multi-level finite element model where a unique discretized RVE is attached to each macro-scale integration point. This approach received much attention and further developments followed in the next years (e.g., Miehe et al. (1999), Feyel and Chaboche (2000), Takano et al. (2000), Terada and Kikuchi (2001), Miehe (2002), Miehe and Koch (2002), Miehe et al. (2002a), Segurado and Llorca (2002), Feyel (2003), Terada et al. (2003), Klinge and Hackl (2012), Schröder (2014)). From these contributions emerged the so-called FE^2 Method, originally coined by (Feyel, 1998), where finite element discretizations and computations are performed in both macro and micro-scales in a coupled manner, through the solution of a micro-scale BVP associated with each macro-scale integration point (see Figure 2.4). Given its quantitative reliability and completeness, the first-order formulation is nowadays well-established and frequently used in both academia and industry. However, a severe disadvantage of this method resides in its high computational cost, both in terms of computational time and memory requirements, which limits its practical applicability and often calls for simplified representative domains and/or suboptimal mesh refinement. Since the micro-scale computations are completely independent of each other, from a purely computational point of view the efforts can be alleviated through high-performance parallel implementations (e.g., Feyel and Chaboche (2000), Okada et al. (2010), Nguyen et al. (2012), Mosby and Matouš (2015), Solinc and Korelc (2015), Mosby and Matouš (2016), Rodrigues Lopes et al. (2017)). In addition, from an accuracy-efficiency point of view, the so-called reduced order methods have received growing attention over the past decade and are showing promising outcomes as discussed in Chapter 4.

As a final remark, it is important to mention that the application of computational homogenization has been widely spread to solve problems involving other fields and coupled multi-physics problems (e.g., thermal (e.g., Özdemir et al. (2008a)), thermomechanical (e.g., Turteltaub and Suiker (2006), Özdemir et al. (2008b), Terada et al. (2010), Temizer and Wriggers (2011b), Mandadapu et al. (2012), Blanco and Giusti (2014)), magnetomechanical (Javili et al. (2013), Spieler et al. (2013), Chatzigeorgiou et al. (2014), Miehe et al. (2015b)), electromechanical (e.g., Schröder (2009), Schröder and Keip (2010), Zäh and Miehe (2013), Keip et al. (2014), Chatzigeorgiou et al. (2015), Miehe et al. (2016)), magnetoelectromechanical (e.g., (Schröder et al., 2016)), hydromechanical (e.g., Sandström et al. (2013))), to the modeling of failure, damage and crack propagation (e.g., Miehe et al. (2002b), Michel et al. (2007), Belytschko et al. (2008), Nezamabadi et al. (2009), Belytschko and Song (2010), Coenen et al. (2012b), Coenen et al. (2012a), Bosco et al. (2014a), Bosco et al. (2014b), Fritzen and Kochmann (2014), Cong et al. (2015), Lesičar et al. (2017a)), to the modeling of interfaces and cohesive cracks (e.g., Matouš et al. (2008), Verhoosel et al. (2010), Mosby and Matous (2015)), to the modeling of contact and friction problems (e.g., Temizer and Wriggers (2008), De Lorenzis and Wriggers (2013), Temizer (2014), Stupkiewicz et al. (2014), Wagner et al. (2017)) among many other applications. Moreover, the classical first-order computational homogenization scheme itself has been modified and extended, leading to second-order computational homogenization formulations for mechanical problems (e.g., Kouznetsova et al. (2002), Geers et al. (2003),



Figure 2.4: Schematic of first-order strain-driven multi-scale model based on computational homogenization.

Kouznetsova et al. (2004a), Kouznetsova et al. (2004b), Kaczmarczyk et al. (2008), Kaczmarczyk et al. (2010), Lesičar et al. (2015b), Lesičar et al. (2015a), Lesičar et al. (2017b), Rodrigues Lopes (2019)) and higher-order methods based on the computational continua approach (Fish and Kuznetsov (2010), Fish et al. (2015)).

2.11 First-order hierarchical homogenization scheme

In Section 2.9.4, the spatial (and material) incremental discretized quasi-static mechanical initial BVP is established and an iterative procedure is detailed in Section 2.9.5 to determine its numerical solution. In each iteration of the Newton-Raphson Method, the elemental vector of internal forces must be computed according with Equation (2.126) (or Equation (2.129)) and assembled into the global vector of internal forces afterwards. In Section 2.9.7 it is seen that the integrations over the element domain are generally performed numerically by means of the Gaussian Quadrature Method, thus the stress incremental constitutive function must be computed in the Gauss integration points. It is at this point that the transition macro-scale-micro-scale occurs and the micro-scale analysis comes into play — the computation of the stress incremental constitutive function is replaced by the solution of a microscopic equilibrium problem over the RVE associated with the Gauss integration point. This means that the total number of RVEs that must be considered is equal to the total number of integration points required to integrate the macro-scale finite element domain.

The disturbance to the RVE equilibrium is driven by the macro-scale deformation gradient, $\boldsymbol{F}(\boldsymbol{x}, t)$, and the equilibrium problem is then solved according with the assumed micro-scale boundary conditions. Finally, after the solution of the microscopic equilibrium problem is found, the return to the macro-scale occurs with the computation of the macro-scale stress tensor,

$\boldsymbol{P}(\boldsymbol{x},t)$, and the consistent tangent modulus, $\mathbf{A}(\boldsymbol{x},t)$, by computational homogenization. The macro-scale solution procedure can then proceed in a standard way. The first-order multi-scale scheme based on the strain-driven homogenized constitutive response of an RVE is illustrated in Figure 2.5.



Figure 2.5: Schematic of first-order strain-driven hierarchical multi-scale model based on computational homogenization.

In order to clearly distinguish quantities associated with both scales the following notation is considered hereafter: at the macro-scale, the domain and its boundary are denoted by Ω and $\partial\Omega$, and the coordinates of a material point are given by $\boldsymbol{X}$ and $\boldsymbol{x}$ in the reference and deformed configurations respectively; at the micro-scale, the domain and its boundary are denoted by Ω_μ and $\partial\Omega_\mu$, and the coordinates of a material point are given by $\boldsymbol{Y}$ and $\boldsymbol{y}$ in the reference and deformed configurations respectively. In addition, the micro-scale fields are generally denoted as $(\bullet)_\mu$.

2.12 Scale Transition Theory

As key assumptions underlying the hierarchical multi-scale models, the separation of scales and the associated relations can be formally stated under a general scale transition theory which relies on three main foundations: the Principle of Scales Separation, intrinsically associated with the RVE characteristic dimension; the kinematic multi-scale relations, involving the kinematic insertion and homogenization procedures; and the Principle of Multi-scale Virtual Power, establishing the energetic equivalence between both scales and the stress homogenization.

2.12.1 Principle of Scales Separation

The importance of the RVE size in a hierarchical multi-scale model has been already discussed in Section 2.10. Under the Hill (Hill, 1963) definition, the RVE must be large enough to be

representative of the domain in an average sense. However, in order to satisfy the assumption of scale separation, the RVE must satisfy the so-called Principle of Scales Separation – the characteristic dimension of the RVE, denoted by l_{RVE}, must be simultaneously much smaller than the macro-scale characteristic dimension, l_{macro}, and much bigger that the characteristic dimensions of the microstructure heterogeneities, l_{micro}, i.e., $l_{\text{micro}} \ll l_{\text{RVE}} \ll l_{\text{macro}}$ (see Figure 2.6).



Figure 2.6: Schematic of the Principle of Scales Separation.

2.12.2 Multi-scale kinematics

The formulation of the multi-scale hierarchical model within the Method of Multi-Scale Virtual Power relies on two basic ingredients that establish the relationship between kinematic quantities between both scales: the kinematic insertion and the kinematic homogenization.

Kinematic insertion

The kinematic insertion is the procedure associated with the downscale of the macro-scale kinematic quantities and their contribution to the micro-scale kinematics. In this case, the macro-scale deformation gradient is imposed to the RVE and results in a micro-scale displacement field that leaves the RVE in an initially nonequilibrium state. Without any loss of generality, the micro-scale displacement field can be conveniently decomposed as

$$\boldsymbol{u}_\mu(\boldsymbol{Y},t) = \left[\boldsymbol{F}(\boldsymbol{X},t) - \boldsymbol{I}\right]\boldsymbol{Y} + \tilde{\boldsymbol{u}}_\mu(\boldsymbol{Y},t) = \boldsymbol{u}_\mu^{\text{lin}} + \tilde{\boldsymbol{u}}_\mu(\boldsymbol{Y},t)\,, \tag{2.156}$$

where the first right-hand side term is the linear component and the second the fluctuation component. The former depends linearly on the prescribed macro-scale deformation gradient, whereas the latter is the displacement fluctuation field. It is then clear that the unknown of the microscopic equilibrium problem are the displacement fluctuations, since the linear component of the microscopic displacements field depends solely on the downscaled deformation gradient. In a similar way, by applying the microscopic displacements decomposition, the microscopic deformation gradient can also be decomposed as

$$\boldsymbol{F}_\mu(\boldsymbol{Y},t) = \boldsymbol{F}(\boldsymbol{X},t) + \nabla_0\tilde{\boldsymbol{u}}_\mu(\boldsymbol{Y},t)\,. \tag{2.157}$$

Kinematic homogenization

The kinematic homogenization is the procedure associated with the upscale of the microscopic kinematic quantities to their macro-scale counterparts. In this case, the transition is established by volume averaging the interest field over the RVE in its reference configuration, i.e., in a

material description. If we let $\boldsymbol{A}(\boldsymbol{Y})$ be a generic tensorial field at the micro-scale, its macro-scale counterpart can thus be obtained as

$$\boldsymbol{A}(\boldsymbol{X}) = \frac{1}{v_{\mu,0}} \int_{\Omega_{\mu,0}} \boldsymbol{A}_{\mu}(\boldsymbol{Y}) \, \mathrm{d}v \,, \tag{2.158}$$

where v_{μ_0} denotes the RVE volume in the reference configuration. The macro-scale deformation gradient, which drives the micro-scale deformation, can then be defined as

$$\boldsymbol{F}(\boldsymbol{X}, t) = \frac{1}{v_{\mu,0}} \int_{\Omega_{\mu,0}} \boldsymbol{F}_{\mu}(\boldsymbol{Y}, t) \, \mathrm{d}v \,, \tag{2.159}$$

or, attending to Equation (2.12), as

$$\boldsymbol{F}(\boldsymbol{X}, t) = \boldsymbol{I} + \frac{1}{v_{\mu,0}} \int_{\Omega_{\mu,0}} \nabla_0 \boldsymbol{u}_{\mu}(\boldsymbol{Y}, t) \, \mathrm{d}v \,. \tag{2.160}$$

By applying the so-called Gauss theorem, it is possible to transform the previous integral over the RVE volume into an integral over the RVE boundary as

$$\boldsymbol{F}(\boldsymbol{X}, t) = \boldsymbol{I} + \frac{1}{v_{\mu,0}} \int_{\partial\Omega_{\mu,0}} \boldsymbol{u}_{\mu}(\boldsymbol{Y}, t) \otimes \boldsymbol{n}(\boldsymbol{Y}) \, \mathrm{d}a \,, \tag{2.161}$$

where $\boldsymbol{n}(\boldsymbol{Y})$ is the unitary vector normal to the RVE boundary in its reference configuration.

Kinematic admissibility

By introducing the decomposition of the microscopic displacement field, Equation (2.156), into Equation (2.160) it is easily shown that

$$\boldsymbol{F}(\boldsymbol{X}, t) = \boldsymbol{F}(\boldsymbol{X}, t) + \frac{1}{v_{\mu,0}} \int_{\Omega_{\mu,0}} \nabla_0 \tilde{\boldsymbol{u}}_{\mu}(\boldsymbol{Y}, t) \, \mathrm{d}v \,. \tag{2.162}$$

Hence, as the result of the compatibilization between the kinematic insertion and homogenization definitions, the minimal kinematic admissible constraint is given by

$$\int_{\Omega_{\mu,0}} \nabla_0 \tilde{\boldsymbol{u}}_{\mu}(\boldsymbol{Y}, t) \, \mathrm{d}v = \boldsymbol{0} \,, \tag{2.163}$$

or, applying once again the Gauss theorem, by

$$\int_{\partial\Omega_{\mu,0}} \nabla_0 \tilde{\boldsymbol{u}}_{\mu}(\boldsymbol{Y}, t) \otimes \boldsymbol{n}(\boldsymbol{Y}) \, \mathrm{d}a = \boldsymbol{0} \,. \tag{2.164}$$

The set of kinematically admissible minimally constrained microscopic displacement fluctuations is therefore defined as

$$\tilde{\mathscr{K}_{\mu}} = \left\{ \tilde{\boldsymbol{u}}_{\mu}, \text{ sufficiently regular} \;\middle|\; \int_{\partial\Omega_{\mu,0}} \nabla_0 \tilde{\boldsymbol{u}}_{\mu}(\boldsymbol{Y}, t) \otimes \boldsymbol{n}(\boldsymbol{Y}) \, \mathrm{d}a = \boldsymbol{0} \right\} . \tag{2.165}$$

2.12.3 Principle of Multi-scale Virtual Power

In a first-order homogenization formulation, the Principle of Multi-scale Virtual Power degenerates into the well-known Hill-Mandel Principle and establishes the connection between macro and micro-scales by invoking a conservation of power between them. Formally, it states that the virtual power at the macro-scale must be equal to the homogenized microscopic virtual power such that

$$\boldsymbol{P}(\boldsymbol{X},t):\delta\boldsymbol{F}(\boldsymbol{X},t)=\frac{1}{v_{\mu,0}}\int_{\Omega_{\mu,0}}\boldsymbol{P}_{\mu}(\boldsymbol{Y},t):\delta\boldsymbol{F}_{\mu}(\boldsymbol{Y},t)\,\mathrm{d}v\,, \tag{2.166}$$

condition that must be satisfied for any virtual macro-scale deformation gradient, $\delta\boldsymbol{F}(\boldsymbol{X},t)$, and for any virtual microscopic deformation gradient, $\delta\boldsymbol{F}(\boldsymbol{Y},t)$. Moreover, by introducing Equation (2.157) into the previous relation, the PMVP can be rewritten as

$$\boldsymbol{P}(\boldsymbol{X},t):\delta\boldsymbol{F}(\boldsymbol{X},t)=\frac{1}{v_{\mu,0}}\int_{\Omega_{\mu,0}}\boldsymbol{P}_{\mu}(\boldsymbol{Y},t):\left[\delta\boldsymbol{F}(\boldsymbol{X},t)+\nabla_0\boldsymbol{\eta}_{\mu}\right]\mathrm{d}v\,, \tag{2.167}$$

for any virtual macro-scale deformation gradient, $\delta\boldsymbol{F}(\boldsymbol{X},t)$, and any admissible virtual microscopic displacement fluctuation, $\boldsymbol{\eta}_{\mu}$.

By assuming that $\delta\boldsymbol{F}(\boldsymbol{X},t)=\boldsymbol{0}$, the PMVP renders the weak micro-scale equilibrium equations in both spatial and material descriptions as

$$\int_{\Omega_{\mu}}\boldsymbol{\sigma}_{\mu}(\boldsymbol{y},t):\nabla\boldsymbol{\eta}_{\mu}\,\mathrm{d}v=0\qquad\forall\boldsymbol{\eta}_{\mu}\in\mathcal{V}_{\mu}\,, \tag{2.168}$$

and

$$\int_{\Omega_{\mu,0}}\boldsymbol{P}_{\mu}(\boldsymbol{Y},t):\nabla_0\boldsymbol{\eta}_{\mu}\,\mathrm{d}v=0\qquad\forall\boldsymbol{\eta}_{\mu}\in\mathcal{V}_{\mu}\,, \tag{2.169}$$

respectively, where the virtual displacement fluctuations belongs to the set of admissible displacement fluctuations, $\mathcal{V}_{\mu}\in\tilde{\mathcal{K}_{\mu}}$. The micro-scale equilibrium problem can thus be stated in the spatial description as

Problem 2.9 | Spatial quasi-static micro-scale mechanical initial BVP.

For a given macro-scale material particle $\boldsymbol{x}$ and the associated macro-scale deformation gradient $\boldsymbol{F}(\boldsymbol{x},t)$, find a kinematically admissible microscopic displacement fluctuation function, $\tilde{\boldsymbol{u}}\in\tilde{\mathcal{K}_{\mu}}$, such that, for every $t\in[t_0,t_f]$, the RVE is in equilibrium as stated by the Virtual Work Principle

$$\int_{\Omega_{\mu}}\boldsymbol{\sigma}_{\mu}(\boldsymbol{y},t):\nabla\boldsymbol{\eta}_{\mu}\,\mathrm{d}v=0\qquad\forall\boldsymbol{\eta}_{\mu}\in\mathcal{V}_{\mu}\,, \tag{2.170}$$

where the space of virtual displacements fluctuation, $\mathcal{V}_{\mu}$, at time t is defined by the set of kinematically admissible displacement fluctuations constrained by the adopted micro-scale boundary condition.

and in the material description as

Problem 2.10 | Material quasi-static micro-scale mechanical initial BVP.

For a given macro-scale material particle $\boldsymbol{X}$ and the associated macro-scale deformation gradient $\boldsymbol{F}(\boldsymbol{X},t)$, find a kinematically admissible microscopic displacement fluctuation function, $\tilde{\boldsymbol{u}} \in \tilde{\mathscr{K}}_\mu$, such that, for every $t \in [t_0, t_f]$, the RVE is in equilibrium as stated by the Virtual Work Principle

$$\int_{\Omega_{\mu,0}} \boldsymbol{P}_\mu(\boldsymbol{Y},t) : \nabla_0 \boldsymbol{\eta}_\mu \, \mathrm{d}v = 0 \qquad \forall \boldsymbol{\eta}_\mu \in \mathscr{V}_\mu \,, \tag{2.171}$$

where the space of virtual displacements fluctuation, $\mathscr{V}_\mu$, at time t is defined by the set of kinematically admissible displacement fluctuations constrained by the adopted micro-scale boundary condition.

In addition, attending to the general Virtual Work Principle equilibrium equations in both spatial and material descriptions,

$$\int_{\Omega_\mu} \left[\boldsymbol{\sigma}_\mu(\boldsymbol{y},t) : \nabla \boldsymbol{\eta}_\mu - \boldsymbol{b}_\mu \cdot \boldsymbol{\eta}_\mu \right] \mathrm{d}v - \int_{\partial\Omega_\mu} \boldsymbol{t}_\mu(\boldsymbol{y},t) \cdot \boldsymbol{\eta}_\mu \, \mathrm{d}a = \boldsymbol{0}, \qquad \forall \boldsymbol{\eta}_\mu \in \mathscr{V}_\mu \,, \tag{2.172}$$

and

$$\int_{\Omega_{\mu,0}} \left[\boldsymbol{P}_\mu(\boldsymbol{Y},t) : \nabla_0 \boldsymbol{\eta}_\mu - \boldsymbol{b}_{\mu,0} \cdot \boldsymbol{\eta}_\mu \right] \mathrm{d}v - \int_{\partial\Omega_{\mu,0}} \boldsymbol{t}_{\mu,0}(\boldsymbol{Y},t) \cdot \boldsymbol{\eta}_\mu \, \mathrm{d}a = \boldsymbol{0}, \qquad \forall \boldsymbol{\eta}_\mu \in \mathscr{V}_\mu \,, \tag{2.173}$$

it is possible to conclude that the microscopic body and traction forces do not produce work, i.e.,

$$\int_{\partial\Omega_\mu} \boldsymbol{t}_\mu(\boldsymbol{y},t) \cdot \boldsymbol{\eta}_\mu \, \mathrm{d}a = 0 \,, \qquad \int_{\Omega_\mu} \boldsymbol{b}_\mu(\boldsymbol{y},t) \cdot \boldsymbol{\eta}_\mu \, \mathrm{d}v = 0 \,, \tag{2.174}$$

$$\int_{\partial\Omega_{\mu,0}} \boldsymbol{t}_{\mu,0}(\boldsymbol{Y},t) \cdot \boldsymbol{\eta}_\mu \, \mathrm{d}a = 0 \,, \qquad \int_{\Omega_{\mu,0}} \boldsymbol{b}_{\mu,0}(\boldsymbol{Y},t) \cdot \boldsymbol{\eta}_\mu \, \mathrm{d}v = 0 \,. \tag{2.175}$$

This can be seen as a consequence of the PMVP and means that the microscopic body and traction forces can be seen as reaction forces arising from the enforcement of the kinematical constraints applied to the microscopic displacement field.

For the sake of completeness, the strong form of the micro-scale equilibrium equations can be simply established in both spatial and material descriptions respectively as

$$\begin{cases} \operatorname{div}\left[\boldsymbol{\sigma}_\mu(\boldsymbol{y},t)\right] + \boldsymbol{b}_\mu(\boldsymbol{y},t) = \boldsymbol{0}, & \forall \boldsymbol{y} \in \Omega_\mu \,, \\ \boldsymbol{\sigma}_\mu(\boldsymbol{y},t)\, \boldsymbol{n}(\boldsymbol{y},t) - \boldsymbol{t}_\mu(\boldsymbol{y},t) = \boldsymbol{0}, & \forall \boldsymbol{y} \in \partial\Omega_\mu \,, \end{cases} \tag{2.176}$$

and

$$\begin{cases} \operatorname{div}_0\left[\boldsymbol{P}_\mu(\boldsymbol{Y},t)\right] + \boldsymbol{b}_{\mu,0}(\boldsymbol{Y},t) = \boldsymbol{0}, & \forall \boldsymbol{Y} \in \Omega_{\mu,0} \,, \\ \boldsymbol{P}_\mu(\boldsymbol{Y},t)\, \boldsymbol{n}(\boldsymbol{Y},t) - \boldsymbol{t}_{\mu,0}(\boldsymbol{Y},t) = \boldsymbol{0}, & \forall \boldsymbol{Y} \in \partial\Omega_{\mu,0} \,. \end{cases} \tag{2.177}$$

2.12.4 Micro-scale boundary conditions

Given that the microscopic displacement field is directly dependent on the type of constraints imposed on the RVE boundary, the choice of a suitable micro-scale boundary condition is one of the most important aspects of a multi-scale model as discussed in Section 2.10.

The trivial solution of the micro-scale equilibrium problem consists in assuming that the micro-scale displacement fluctuations are null over the entire domain, i.e.,

$$\tilde{\boldsymbol{u}}_\mu(\boldsymbol{Y},t)=\boldsymbol{0}\,,\quad \forall\,\boldsymbol{Y}\in\Omega_{\mu,0}\,. \tag{2.178}$$

This is the most restrictive condition that can be applied to the RVE displacement field and is called Taylor hypothesis, being known to overestimate the stiffness of heterogeneous materials. The micro-scale displacement field is thus entirely defined by the imposed linear displacements (see Figure 2.7) as

$$\boldsymbol{u}_\mu(\boldsymbol{Y},t)=\left[\boldsymbol{F}(\boldsymbol{X},t)-\boldsymbol{I}\right]\boldsymbol{Y}=\boldsymbol{u}_\mu^{\text{lin}}\,,\quad \forall\,\boldsymbol{Y}\in\Omega_{\mu,0}\,, \tag{2.179}$$

and the set of kinematically admissible microscopic displacement fluctuations constrained by the Taylor hypothesis is defined as

$$\mathscr{K}_\mu^{\text{Taylor}}=\left\{\tilde{\boldsymbol{u}}_\mu,\ \text{sufficiently regular}\ \middle|\ \tilde{\boldsymbol{u}}_\mu(\boldsymbol{Y},t)=\boldsymbol{0}\,,\quad \forall\,\boldsymbol{Y}\in\Omega_{\mu,0}\right\}. \tag{2.180}$$



Figure 2.7: Taylor hypothesis.

There are three micro-scale boundary conditions that are usually considered in multi-scale models, the so-called homogeneous boundary conditions (linear displacement and uniform traction) and the most commonly applied periodic boundary condition. These are presented below, sorted by decreasing restriction of the microscopic displacement fluctuations.

Linear boundary condition

The linear boundary condition imposes null microscopic displacement fluctuations in the RVE boundary, i.e.,

$$\tilde{\boldsymbol{u}}_\mu(\boldsymbol{Y},t)=\boldsymbol{0}\,,\quad \forall\,\boldsymbol{Y}\in\partial\Omega_{\mu,0}\,. \tag{2.181}$$

Therefore, the microscopic displacement field in the RVE boundary is entirely defined by the imposed linear displacements (see Figure 2.8) as

$$\boldsymbol{u}_\mu(\boldsymbol{Y},t)=\left[\boldsymbol{F}(\boldsymbol{X},t)-\boldsymbol{I}\right]\boldsymbol{Y}=\boldsymbol{u}_\mu^{\text{lin}}\,,\quad \forall\,\boldsymbol{Y}\in\partial\Omega_{\mu,0}\,. \tag{2.182}$$

In accordance, the set of kinematically admissible microscopic displacement fluctuations constrained by the linear boundary condition can be defined as

$$\mathscr{K}_\mu^{\text{Linear}}=\left\{\tilde{\boldsymbol{u}}_\mu,\ \text{sufficiently regular}\ \middle|\ \tilde{\boldsymbol{u}}_\mu(\boldsymbol{Y},t)=\boldsymbol{0}\,,\quad \forall\,\boldsymbol{Y}\in\partial\Omega_{\mu,0}\right\}. \tag{2.183}$$



Figure 2.8: Micro-scale linear boundary condition.

Periodic boundary condition

The basic assumption behind the periodic boundary condition is that the microstructure can be reproduced by a pattern of identical RVEs, thus implying displacement compatibility between oposite sides of the RVE boundary. With this in mind, consider that the RVE boundary is divided in d equal pair groups such that

$$\partial\Omega_{\mu,0} = \bigcup_{i=1}^{d} \partial\Omega_{\mu,0,i}\,, \qquad \partial\Omega_{\mu,0,i} = (\Gamma_i^- \cup \Gamma_i^+)\,. \tag{2.184}$$

In each group $\partial\Omega_{\mu,0,i}$, each point of the positive side, $\boldsymbol{Y}^+ \in \Gamma_i^+$, has its pair in the opposing negative side, $\boldsymbol{Y}^- \in \Gamma_i^-$. Moreover, the unitary vectors $\boldsymbol{n}^+$ and $\boldsymbol{n}^-$, normal to Γ_i^+ and Γ_i^- respectively, must be antisymmetric. Taking in account these conditions, the periodic boundary condition can be stated as

$$\tilde{\boldsymbol{u}}_\mu(\boldsymbol{Y}^+,t) = \tilde{\boldsymbol{u}}_\mu(\boldsymbol{Y}^-,t)\,, \tag{2.185}$$

which means that the displacement fluctuations are equal in opposing sides of the RVE boundary (see Figure 2.9). In addition, based on the consequences of the PMVP, it is possible to show that the previous constraint is only satisfied if the traction forces field is anti-periodic, i.e.,

$$\boldsymbol{t}_{\mu,i}(\boldsymbol{Y}^+,t) = -\boldsymbol{t}_{\mu,i}(\boldsymbol{Y}^-,t)\,. \tag{2.186}$$

The set of kinematically admissible microscopic displacement fluctuation fields constrained by the periodic boundary condition can hence be defined as

$$\mathscr{K}_\mu^{\text{Periodic}} = \left\{ \tilde{\boldsymbol{u}}_\mu,\ \text{sufficiently regular} \;\middle|\; \tilde{\boldsymbol{u}}_{\mu,i}(\boldsymbol{Y}^+,t) = \tilde{\boldsymbol{u}}_{\mu,i}(\boldsymbol{Y}^-,t)\,, \quad \forall\{\boldsymbol{Y}^+,\boldsymbol{Y}^-\} \in \partial\Omega_{\mu,0,i} \right\}. \tag{2.187}$$

Uniform traction boundary condition

While the Taylor hypothesis is the most restrictive condition, the uniform traction boundary condition appears at the opposite side of the spectrum by imposing solely that the minimal constraint defined by Equation (2.164) must be satisfied (see Figure 2.10). This means that the set of kinematically admissible microscopic displacement fluctuations constrained by the uniform traction boundary condition is coincident with the set of kinematically admissible minimally constrained microscopic displacement fluctuations, i.e.,



Figure 2.9: Micro-scale periodic boundary condition.

$$\mathscr{K}_\mu^{\text{U.Traction}} = \tilde{\mathscr{K}}_\mu = \left\{ \tilde{\boldsymbol{u}}_\mu,\ \text{sufficiently regular} \;\middle|\; \int_{\partial\Omega_{\mu,0}} \tilde{\boldsymbol{u}}_\mu(\boldsymbol{Y},t) \otimes \boldsymbol{n}(\boldsymbol{Y})\, \mathrm{d}a = \boldsymbol{0} \right\}. \tag{2.188}$$

Moreover, as a consequence of the PMVP it is possible to conclude that the traction along the RVE boundary is uniform and equal to the homogenized traction, i.e.,

$$\boldsymbol{P}_\mu(\boldsymbol{Y},t)\,\boldsymbol{n}(\boldsymbol{Y},t) = \boldsymbol{P}(\boldsymbol{X},t)\,\boldsymbol{n}(\boldsymbol{Y},t)\,, \qquad \boldsymbol{Y} \in \partial\Omega_{\mu,0}\,. \tag{2.189}$$



Figure 2.10: Micro-scale uniform traction boundary condition.

2.12.5 Homogenized stress tensor

After the solution of the micro-scale equilibrium problem, the macro-scale stress tensor can be determined by homogenization through the PMVP. Recalling Equation (2.167) and assuming $\delta\tilde{\boldsymbol{u}}(\boldsymbol{Y},t) = \boldsymbol{0}$, the macro-scale First Piola-Kirchhoff stress tensor is obtained as a volume averaging of its microscopic counterpart,

$$\boldsymbol{P}(\boldsymbol{X},t)=\frac{1}{v_{\mu,0}}\int_{\Omega_{\mu,0}}\boldsymbol{P}_{\mu}(\boldsymbol{Y},t)\,\mathrm{d}v\,. \tag{2.190}$$

The integration of the right-hand side by parts and the introduction of the strong form of the micro-scale equilibrium problem (see Equation (2.176)) allows rewritting Equation (2.190) in terms of a boundary integral instead,

$$\boldsymbol{P}(\boldsymbol{X},t)=\frac{1}{v_{\mu,0}}\int_{\partial\Omega_{\mu,0}}\boldsymbol{t}_{\mu,0}\otimes\boldsymbol{Y}\,\mathrm{d}a\,. \tag{2.191}$$

Attending to the relation established in Equation (2.30), the macro-scale Cauchy stress tensor can then be simply obtained as

$$\boldsymbol{\sigma}=\frac{1}{J}\boldsymbol{P}\boldsymbol{F}^{T}. \tag{2.192}$$

2.13 Time discretization of the micro-scale problem

The time discretization of the micro-scale equilibrium follows the same approach presented in Section 2.8, where an algorithm based in approximated incremental constitutive functions is adopted. Therefore, considering the time increment $[t_n, t_{n+1}]$, the same requirements set in Equations (2.105)-(2.107) must be met, denoting the microscopic internal variables as $\boldsymbol{\beta}$ instead. Applying such time discretization scheme, it is then possible to state the incremental version of the micro-scale equilibrium problem in both spatial and material descriptions as follows.

Problem 2.11 | Spatial incremental quasi-static micro-scale mechanical initial BVP.

For a given macro-scale material particle $\boldsymbol{x}$, the associated macro-scale deformation gradient $\boldsymbol{F}(\boldsymbol{x},t)$ at t_{n+1} and the set of internal variables $\boldsymbol{\beta}_n$ at t_n, find the kinematically admissible microscopic displacement fluctuations, $\tilde{\boldsymbol{u}}_{\mu,n+1}\in\tilde{\mathscr{K}}_{\mu,n+1}$, such that the RVE is in equilibrium as stated by the Principle of Multi-scale Virtual Power

$$\int_{\Omega_{\mu}}\hat{\boldsymbol{\sigma}}_{\mu}(\boldsymbol{F}_{\mu,n+1},\boldsymbol{\beta}_n):\nabla\boldsymbol{\eta}_{\mu}\,\mathrm{d}v=0\,,\quad\forall\boldsymbol{\eta}_{\mu}\in\mathscr{V}_{\mu}\,, \tag{2.193}$$

where the space of admissible displacement fluctuations, $\tilde{\mathscr{K}}_{\mu,n+1}$, at time t_{n+1}, is defined by the set of kinematically admissible displacement fluctuations constrained by the adopted micro-scale boundary condition.

Problem 2.12 | Material incremental quasi-static micro-scale mechanical initial BVP.

For a given macro-scale material particle $\boldsymbol{X}$, the associated macro-scale deformation gradient $\boldsymbol{F}(\boldsymbol{X},t)$ at t_{n+1} and the set of internal variables $\boldsymbol{\beta}_n$ at t_n, find the kinematically admissible microscopic displacement fluctuations, $\tilde{\boldsymbol{u}}_{\mu,n+1}\in\tilde{\mathscr{K}}_{\mu,n+1}$, such that the RVE is in equilibrium as stated by the Principle of Multi-scale Virtual Power

$$\int_{\Omega_{\mu,0}}\hat{\boldsymbol{P}}_{\mu}(\boldsymbol{F}_{\mu,n+1},\boldsymbol{\beta}_n):\nabla_0\boldsymbol{\eta}_{\mu}\,\mathrm{d}v=0\,,\quad\forall\boldsymbol{\eta}_{\mu}\in\mathscr{V}_{\mu}\,, \tag{2.194}$$

where the space of admissible displacement fluctuations, $\tilde{\mathscr{K}}_{\mu,n+1}$, at time t_{n+1}, is defined by the set of kinematically admissible displacement fluctuations constrained by the adopted micro-scale boundary condition.

2.14 Numerical solution of the micro-scale problem

The numerical solution of the incremental weak form of the quasi-static micro-scale initial BVP can be obtained by the Finite Element Method as detailed in Section 2.9. However, additional numerical treatment is required to enforce the micro-scale boundary conditions as well as to obtain the homogenized consistent tangent modulus. Both these topics are covered in the following sections.

2.14.1 Spatial discretization

By performing a spatial finite element discretization of the problem domain, the discretized form of the incremental quasi-static micro-scale initial BVP can be stated in the spatial and material descriptions as follows.

Problem 2.13 | Spatial discretized quasi-static micro-scale mechanical initial BVP.

For a given macro-scale material particle $\boldsymbol{x}$, the associated macro-scale deformation gradient $\boldsymbol{F}(\boldsymbol{x},t)$ at t_{n+1} and the set of internal variables $\boldsymbol{\beta}_n$ at t_n, find the kinematically admissible microscopic nodal displacement fluctuations, $\tilde{\mathbf{u}}_{\mu,n+1} \in {}^{h}\tilde{\mathscr{K}}_{\mu,n+1}$, such that the RVE is in equilibrium as stated by the Principle of Multi-scale Virtual Power

$$\mathbf{f}_{\mu}^{\text{int}}(\tilde{\mathbf{u}}_{\mu,n+1}) = \mathbf{0}, \tag{2.195}$$

where $\mathbf{f}_{\mu}^{\text{int}}$ is the global vector of internal forces defined as

$$\mathbf{f}_{\mu}^{\text{int}} = \int_{{}^{h}\Omega_{\mu}} (\mathbf{B}^{g})^{T}\hat{\boldsymbol{\sigma}}(\boldsymbol{F}_{\mu,n+1},\boldsymbol{\beta}_n)\,\mathrm{d}v. \tag{2.196}$$

Problem 2.14 | Material discretized quasi-static micro-scale mechanical initial BVP.

For a given macro-scale material particle $\boldsymbol{X}$, the associated macro-scale deformation gradient $\boldsymbol{F}(\boldsymbol{X},t)$ at t_{n+1} and the set of internal variables $\boldsymbol{\beta}_n$ at t_n, find the kinematically admissible microscopic nodal displacements fluctuation field, $\tilde{\mathbf{u}}_{\mu,n+1} \in {}^{h}\tilde{\mathscr{K}}_{\mu,n+1}$, such that the RVE is in equilibrium as stated by the Principle of Multi-scale Virtual Power

$$\mathbf{f}_{\mu}^{\text{int}}(\tilde{\mathbf{u}}_{\mu,n+1}) = \mathbf{0}, \tag{2.197}$$

where $\mathbf{f}_{\mu}^{\text{int}}$ is the global vector of internal forces defined as

$$\mathbf{f}_{\mu}^{\text{int}} = \int_{{}^{h}\Omega_{\mu,0}} (\mathbf{G}^{g})^{T}\hat{\mathbf{P}}(\boldsymbol{F}_{\mu,n+1},\boldsymbol{\beta}_n)\,\mathrm{d}v. \tag{2.198}$$

2.14.2 Newton-Raphson Method

The Newton-Raphson Method can be employed once again to solve the generally nonlinear micro-scale equilibrium problem. However, at this point it is important to notice that both Equations (2.195) and (2.197) are completely general in what concerns the micro-scale boundary conditions. Different approaches have been proposed to enforce them, namely resorting to Lagrange Multipliers or to condensation procedures. Given its simplicity and elegant way of accounting for the micro-scale boundary conditions without introducing a

significant complexity in the micro-scale equilibrium problem linearization, a condensation procedure is detailed in what follows.

The first step consists in splitting the degrees of freedom into four distinct groups as:

- **Interior** (i). Related to nodes in the interior of the RVE;
- **Boundary** (b). Related to nodes in the boundary of the RVE, splitted as:
  - ◇ **Free** (f). Degrees of freedom whose displacement fluctuation is free;
  - ◇ **Dependent** (d). Degrees of freedom whose displacement fluctuation depends on free degrees of freedom;
  - ◇ **Prescribed** (p). Degrees of freedom whose displacement fluctuation is null by prescription in order to avoid rigid body motion.

In accordance, the global vectors of nodal displacements fluctuation, virtual displacements and internal forces can be rearranged as

$$\tilde{\mathbf{u}}_\mu = \left\{\tilde{\mathbf{u}}_\mu^i, \tilde{\mathbf{u}}_\mu^f, \tilde{\mathbf{u}}_\mu^d, \tilde{\mathbf{u}}_\mu^p\right\}^T, \quad \boldsymbol{\eta}_\mu = \left\{\boldsymbol{\eta}_\mu^i, \boldsymbol{\eta}_\mu^f, \boldsymbol{\eta}_\mu^d, \boldsymbol{\eta}_\mu^p\right\}^T, \quad \mathbf{f}_\mu^{\text{int}} = \left\{\mathbf{f}_\mu^i, \mathbf{f}_\mu^f, \mathbf{f}_\mu^d, \mathbf{f}_\mu^p\right\}^T. \tag{2.199}$$

The linearized version of the spatial micro-scale equilibrium equation is similar to the one performed for the macro-scale and is given by

$$\left\{\int_{^h\Omega_\mu} (\mathbf{G}^g)^T \mathbf{a} \mathbf{G}^g \, \mathrm{d}v\right\} \delta\tilde{\mathbf{u}}_\mu \cdot \boldsymbol{\eta}_\mu = -\left\{\int_{^h\Omega_\mu} (\mathbf{B}^g)^T \hat{\boldsymbol{\sigma}}_\mu(\boldsymbol{F}_{\mu,n+1}, \boldsymbol{\beta}_n) \, \mathrm{d}v\right\} \cdot \boldsymbol{\eta}_\mu, \quad \forall \boldsymbol{\eta}_\mu \in {}^h\mathscr{V}_\mu, \tag{2.200}$$

which can be rewritten as

$$\boldsymbol{\eta}_\mu^T \left\{\left\{\int_{^h\Omega_\mu} (\mathbf{G}^g)^T \mathbf{a} \mathbf{G}^g \, \mathrm{d}v\right\} \delta\tilde{\mathbf{u}}_\mu + \int_{^h\Omega_\mu} (\mathbf{B}^g)^T \hat{\boldsymbol{\sigma}}_\mu(\boldsymbol{F}_{\mu,n+1}, \boldsymbol{\beta}_n) \, \mathrm{d}v\right\} = 0, \quad \forall \boldsymbol{\eta}_\mu \in {}^h\mathscr{V}_\mu. \tag{2.201}$$

In alternative, the linearized version of the material micro-scale equilibrium equation comes

$$\boldsymbol{\eta}_\mu^T \left\{\left\{\int_{^h\Omega_{\mu,0}} (\mathbf{G}^g)^T \mathbf{A} \mathbf{G}^g \, \mathrm{d}v\right\} \delta\tilde{\mathbf{u}}_\mu + \int_{^h\Omega_{\mu,0}} (\mathbf{G}^g)^T \hat{\mathbf{P}}_\mu(\boldsymbol{F}_{\mu,n+1}, \boldsymbol{\beta}_n) \, \mathrm{d}v\right\} = 0, \quad \forall \boldsymbol{\eta}_\mu \in {}^h\mathscr{V}_\mu. \tag{2.202}$$

Recalling that the global tangent stiffness matrix is defined in the spatial and material descriptions as

$$\boldsymbol{K}_T = \int_{^h\Omega_\mu} (\mathbf{G}^g)^T \mathbf{a} \mathbf{G}^g \, \mathrm{d}v, \quad \text{(spatial)} \tag{2.203}$$

$$\boldsymbol{K}_T = \int_{^h\Omega_{\mu,0}} (\mathbf{G}^g)^T \mathbf{A} \mathbf{G}^g \, \mathrm{d}v, \quad \text{(material)} \tag{2.204}$$

and applying the degrees of freedom split, it is possible to write both linearized equilibrium equations[3] as

$$\begin{Bmatrix} \boldsymbol{\eta}_\mu^i \\ \boldsymbol{\eta}_\mu^f \\ \boldsymbol{\eta}_\mu^d \\ \boldsymbol{\eta}_\mu^p \end{Bmatrix}^T \left\{ \begin{bmatrix} \boldsymbol{k}^{ii} & \boldsymbol{k}^{if} & \boldsymbol{k}^{id} & \boldsymbol{k}^{ip} \\ \boldsymbol{k}^{fi} & \boldsymbol{k}^{ff} & \boldsymbol{k}^{fd} & \boldsymbol{k}^{fp} \\ \boldsymbol{k}^{di} & \boldsymbol{k}^{df} & \boldsymbol{k}^{dd} & \boldsymbol{k}^{dp} \\ \boldsymbol{k}^{pi} & \boldsymbol{k}^{pf} & \boldsymbol{k}^{pd} & \boldsymbol{k}^{pp} \end{bmatrix} \begin{Bmatrix} \delta\tilde{\mathbf{u}}_\mu^i \\ \delta\tilde{\mathbf{u}}_\mu^f \\ \delta\tilde{\mathbf{u}}_\mu^d \\ \delta\tilde{\mathbf{u}}_\mu^p \end{Bmatrix} + \begin{Bmatrix} \mathbf{f}_\mu^i \\ \mathbf{f}_\mu^f \\ \mathbf{f}_\mu^d \\ \mathbf{f}_\mu^p \end{Bmatrix} \right\} = 0, \quad \forall \boldsymbol{\eta}_\mu \in {}^h\mathscr{V}_\mu. \tag{2.205}$$

[3] The computation of the global stiffness matrices and vectors of internal forces is performed according to the spatial or material description.

The micro-scale boundary conditions can now be introduced by the condensation method: firstly, suitable prescribed boundary degrees of freedom must be chosen in order to avoid rigid body motions; then suitable dependent boundary degrees of freedom must be chosen in accordance with the imposed boundary condition; and finally, it is necessary to establish a relation between the dependent and the free degrees of freedom, which can be generally defined as

$$\tilde{\mathbf{u}}_\mu^d = \boldsymbol{\Theta}\,\tilde{\mathbf{u}}_\mu^f, \tag{2.206}$$

where $\boldsymbol{\Theta}$ is the dependency matrix. Therefore, making use of the previous relation and removing all the contributions from the prescribed degrees of freedom ($\tilde{\mathbf{u}}_\mu^p = \mathbf{0}$), it comes

$$\begin{Bmatrix} \boldsymbol{\eta}_\mu^i \\ \boldsymbol{\eta}_\mu^f \\ \boldsymbol{\Theta}\boldsymbol{\eta}_\mu^f \end{Bmatrix}^T \left\{ \begin{bmatrix} \boldsymbol{k}^{ii} & \boldsymbol{k}^{if} & \boldsymbol{k}^{id} \\ \boldsymbol{k}^{fi} & \boldsymbol{k}^{ff} & \boldsymbol{k}^{fd} \\ \boldsymbol{k}^{di} & \boldsymbol{k}^{df} & \boldsymbol{k}^{dd} \end{bmatrix} \begin{Bmatrix} \delta\tilde{\mathbf{u}}_\mu^i \\ \delta\tilde{\mathbf{u}}_\mu^f \\ \boldsymbol{\Theta}\delta\tilde{\mathbf{u}}_\mu^f \end{Bmatrix} + \begin{Bmatrix} \mathbf{f}_\mu^i \\ \mathbf{f}_\mu^f \\ \mathbf{f}_\mu^d \end{Bmatrix} \right\} = 0, \quad \forall \boldsymbol{\eta}_\mu \in {}^h\mathscr{V}_\mu. \tag{2.207}$$

Applying condensation to the vector $\delta\tilde{\mathbf{u}}_\mu$ yields

$$\begin{Bmatrix} \boldsymbol{\eta}_\mu^i \\ \boldsymbol{\eta}_\mu^f \\ \boldsymbol{\eta}_\mu^f \end{Bmatrix}^T \left\{ \begin{bmatrix} \boldsymbol{k}^{ii} & \boldsymbol{k}^{if} + \boldsymbol{k}^{id}\boldsymbol{\Theta} \\ \boldsymbol{k}^{fi} & \boldsymbol{k}^{ff} + \boldsymbol{k}^{fd}\boldsymbol{\Theta} \\ \boldsymbol{k}^{di} & \boldsymbol{k}^{df} + \boldsymbol{k}^{dd}\boldsymbol{\Theta} \end{bmatrix} \begin{Bmatrix} \delta\tilde{\mathbf{u}}_\mu^i \\ \delta\tilde{\mathbf{u}}_\mu^f \end{Bmatrix} + \begin{Bmatrix} \mathbf{f}_\mu^i \\ \mathbf{f}_\mu^f \\ \mathbf{f}_\mu^d \end{Bmatrix} \right\} = 0, \quad \forall \boldsymbol{\eta}_\mu \in {}^h\mathscr{V}_\mu, \tag{2.208}$$

and applying the same procedure to the vector $\boldsymbol{\eta}$ results in

$$\begin{Bmatrix} \boldsymbol{\eta}_\mu^i \\ \boldsymbol{\eta}_\mu^f \end{Bmatrix}^T \left\{ \begin{bmatrix} \boldsymbol{k}^{ii} & \boldsymbol{k}^{if} + \boldsymbol{k}^{id}\boldsymbol{\Theta} \\ \boldsymbol{k}^{fi} + \boldsymbol{\Theta}^T\boldsymbol{k}^{di} & \boldsymbol{k}^{ff} + \boldsymbol{k}^{fd}\boldsymbol{\Theta} + \boldsymbol{\Theta}^T\boldsymbol{k}^{df} + \boldsymbol{\Theta}^T\boldsymbol{k}^{dd}\boldsymbol{\Theta} \end{bmatrix} \begin{Bmatrix} \delta\tilde{\mathbf{u}}_\mu^i \\ \delta\tilde{\mathbf{u}}_\mu^f \end{Bmatrix} + \begin{Bmatrix} \mathbf{f}_\mu^i \\ \mathbf{f}_\mu^f + \boldsymbol{\Theta}^T\mathbf{f}_\mu^d \end{Bmatrix} \right\} = 0,$$

$$\forall \boldsymbol{\eta}_\mu \in {}^h\mathscr{V}_\mu. \tag{2.209}$$

Since the equality must hold for any $\boldsymbol{\eta}_\mu \in {}^h\mathscr{V}_\mu$, each Newton-Raphson Method iteration (k) consists in solving the following system of linear equations

$$\begin{bmatrix} \boldsymbol{k}^{ii} & \boldsymbol{k}^{if} + \boldsymbol{k}^{id}\boldsymbol{\Theta} \\ \boldsymbol{k}^{fi} + \boldsymbol{\Theta}^T\boldsymbol{k}^{di} & \boldsymbol{k}^{ff} + \boldsymbol{k}^{fd}\boldsymbol{\Theta} + \boldsymbol{\Theta}^T\boldsymbol{k}^{df} + \boldsymbol{\Theta}^T\boldsymbol{k}^{dd}\boldsymbol{\Theta} \end{bmatrix}^{(k-1)} \begin{Bmatrix} \delta\tilde{\mathbf{u}}_\mu^i \\ \delta\tilde{\mathbf{u}}_\mu^f \end{Bmatrix} = -\begin{Bmatrix} \mathbf{f}_\mu^i \\ \mathbf{f}_\mu^f + \boldsymbol{\Theta}^T\mathbf{f}_\mu^d \end{Bmatrix}^{(k-1)}. \tag{2.210}$$

After solving the system of linear equations, $\delta\tilde{\mathbf{u}}^d$ are computed through the Equation (2.206) and the iterative displacement fluctuations, $\delta\tilde{\mathbf{u}}$, is fully determined. The global vector of nodal displacement fluctuations can thus be updated as

$$\tilde{\mathbf{u}}_{\mu,n+1}^{(k)} = \tilde{\mathbf{u}}_{\mu,n} + \Delta\tilde{\mathbf{u}}_{\mu,n+1}^{(k)}, \tag{2.211}$$

where $\Delta\tilde{\mathbf{u}}_{\mu,n+1}^{(k)}$ is the global incremental vector of nodal displacement fluctuations defined by

$$\Delta\tilde{\mathbf{u}}_{\mu,n+1}^{(k)} = \Delta\tilde{\mathbf{u}}_{\mu,n+1}^{(k-1)} + \delta\tilde{\mathbf{u}}_\mu, \tag{2.212}$$

and is implicit that

$$\tilde{\mathbf{u}}^{(k)}_{\mu,\,n+1} = \tilde{\mathbf{u}}^{(k-1)}_{\mu,\,n+1} + \delta\tilde{\mathbf{u}}_{\mu}\,. \tag{2.213}$$

The global vector of nodal displacements, $\mathbf{u}^{(k)}_{\mu,\,n+1}$, can then be determined from the Equation (2.156), and the iterative cycle is stopped when the solution $\mathbf{u}^{(m)}_{\mu,\,n+1}$ is deemed to have converged according with a given convergence criteria, i.e., $\mathbf{u}_{\mu,\,n+1} = \mathbf{u}^{(m)}_{\mu,\,n+1}$.

2.14.3 Dependency matrix

Despite having introduced the dependency matrix as an effective way of imposing the micro-scale boundary conditions, the system of linear equations for the RVE equilibrium set in Equation (2.210) still remains general. In what follows, the dependency matrix is particularized for each boundary condition.

Linear boundary condition

The linear boundary condition imposes a null displacement fluctuation field in the RVE boundary, which means that $\tilde{\mathbf{u}}^{b}_{\mu} = \tilde{\mathbf{u}}^{f}_{\mu} = \tilde{\mathbf{u}}^{d}_{\mu} = \mathbf{0}$. Hence, the interior degrees of freedom, $\tilde{\mathbf{u}}^{i}_{\mu}$, are the only unknowns, the definition of the dependency matrix, $\boldsymbol{\Theta}$, is not required and the system of equations is simply reduced to

$$\boldsymbol{k}^{ii}\delta\tilde{\mathbf{u}}^{i}_{\mu} = -\mathbf{f}^{i}_{\mu}\,. \tag{2.214}$$

Note that the imposed constraint in the entire RVE boundary naturally avoids rigid body motions, thus none of the interior degrees of freedom must be prescribed.

Periodic boundary condition

Given that an one-to-one relation is established between nodes of opposite sides of the RVE boundary, the standard periodic boundary condition requires mesh conformity between those sides of the mesh. In this sense, each pair of boundary edges or surfaces is splitted: one of the sides is classified as 'negative' and is associated with the free degrees of freedom, and the other is classified as 'positive' and is associated with the dependent degrees of freedom. If the displacement fluctuation vectors, $\tilde{\mathbf{u}}^{f}_{\mu}$ and $\tilde{\mathbf{u}}^{d}_{\mu}$, are sorted according with such one-to-one dependency, then the dependency matrix is the identity, i.e., $\boldsymbol{\Theta} = \boldsymbol{I}$. The system of equations can thus be simplified as

$$\begin{bmatrix} \boldsymbol{k}^{ii} & \boldsymbol{k}^{i-} + \boldsymbol{k}^{i+} \\ \boldsymbol{k}^{-i} + \boldsymbol{k}^{+i} & \boldsymbol{k}^{--} + \boldsymbol{k}^{-+} + \boldsymbol{k}^{+-} + \boldsymbol{k}^{++} \end{bmatrix}^{(k-1)} \begin{Bmatrix} \delta\tilde{\mathbf{u}}^{i}_{\mu} \\ \delta\tilde{\mathbf{u}}^{-}_{\mu} \end{Bmatrix} = -\begin{Bmatrix} \mathbf{f}^{i}_{\mu} \\ \mathbf{f}^{-}_{\mu} + \mathbf{f}^{+}_{\mu} \end{Bmatrix}^{(k-1)}\,. \tag{2.215}$$

In order to avoid rigid body motions and to respect the periodicity constraint, the RVE boundary corners are prescribed with null displacement fluctuations.

Uniform traction boundary conditions

Unlike the previous cases, the uniform traction boundary condition does not enable the simplification of the system of equations and requires the proper definition of the dependency matrix. As a starting point, the constraint imposed in the displacement fluctuations (see Equation (2.188)) must be spatially discretized in a finite element sense, which yields

$$\int_{h\Omega_{\mu,0}} (\mathbf{N}^b)^g \tilde{\mathbf{u}}_\mu^b \otimes \boldsymbol{n}\, \mathrm{d}a = \mathbf{0}, \tag{2.216}$$

where the superscript b is referred to the boundary degrees of freedom. After a simple algebraic manipulation, it is possible to show that the previous discretized constraint can be rewritten as

$$\mathbf{C}\tilde{\mathbf{u}}_\mu^b = \mathbf{0}, \tag{2.217}$$

where $\mathbf{C}$ is the constraint matrix. This can be assembled from its elemental counterpart as

$$\mathbf{C} = \mathop{\mathsf{A}}_{e=1}^{n_{\text{elem}}} \mathbf{C}^{(e)}, \tag{2.218}$$

being the elemental constraint matrix defined for 2D problems as

$$\mathbf{C}^{(e)} = \begin{bmatrix} \dots & \int N_i n_1 \,\mathrm{d}a & 0 & \dots \\ \dots & 0 & \int N_i n_2 \,\mathrm{d}a & \dots \\ \dots & \int N_i n_2 \,\mathrm{d}a & 0 & \dots \\ \dots & 0 & \int N_i n_1 \,\mathrm{d}a & \dots \end{bmatrix}, \tag{2.219}$$

and for 3D problems as

$$\mathbf{C}^{(e)} = \begin{bmatrix} \dots & \int N_i n_1 \,\mathrm{d}a & 0 & 0 & \dots \\ \dots & 0 & \int N_i n_2 \,\mathrm{d}a & 0 & \dots \\ \dots & 0 & 0 & \int N_i n_3 \,\mathrm{d}a & \dots \\ \dots & \int N_i n_2 \,\mathrm{d}a & 0 & 0 & \dots \\ \dots & \int N_i n_3 \,\mathrm{d}a & 0 & 0 & \dots \\ \dots & 0 & \int N_i n_1 \,\mathrm{d}a & 0 & \dots \\ \dots & 0 & \int N_i n_3 \,\mathrm{d}a & 0 & \dots \\ \dots & 0 & 0 & \int N_i n_1 \,\mathrm{d}a & \dots \\ \dots & 0 & 0 & \int N_i n_2 \,\mathrm{d}a & \dots \end{bmatrix}. \tag{2.220}$$

where N_i is the shape function associated with node i, n_j are the components of the unitary vector normal do the boundary of the RVE, $\boldsymbol{n}$. Notice that these matrices must be compliant with the adopted vector storage and the integrals are performed over elemental surfaces which intercept the RVE boundary. Therefore, the uniform traction boundary condition constraint imposes 4 linear constraints in 2D problems and 9 linear constraints in 3D problems, which means that these are the number of dependent degrees of freedom for each case. In fact, it is convenient to split the constraint matrix as

$$\begin{bmatrix} \mathbf{C}^f & \mathbf{C}^d \end{bmatrix} \begin{Bmatrix} \tilde{\mathbf{u}}_\mu^f \\ \tilde{\mathbf{u}}_\mu^d \end{Bmatrix} = \mathbf{0}, \tag{2.221}$$

where $\mathbf{C}^d$ is a square matrix, and it is possible to write

$$\tilde{\mathbf{u}}_\mu^d = -\left[\mathbf{C}^d\right]^{-1} \left[\mathbf{C}^f\right] \tilde{\mathbf{u}}^f. \tag{2.222}$$

The dependency matrix can then be defined as

$$\boldsymbol{\Theta} = -\left[\mathbf{C}^d\right]^{-1}\left[\mathbf{C}^f\right], \tag{2.223}$$

and must only be determined once during the problem initialization, remaining unchanged thereafter. The choice of the dependent degrees of freedom must be carefully performed in order to ensure the nonsingularity of the dependent constraint matrix $\mathbf{C}^d$.

In addition, it is possible to show that the rigid body rotation is naturally constrained by the minimal kinematic admissible constraint, therefore it is only necessary to prescribe 2 and 3 suitable degrees of freedom in order to avoid rigid body translation.

2.14.4 Homogenized stress tensor

An efficient computation of the macro-scale First Piola-Kirchhoff stress tensor can be performed by discretizing Equation (2.191) as

$$\mathbf{P}(\boldsymbol{X}, t) = \frac{1}{v_{\mu,0}}\mathbf{D}^b\mathbf{f}_\mu^b, \tag{2.224}$$

where $\mathbf{f}_\mu^b$ is the vector of internal nodal forces associated with boundary nodes and $\mathbf{D}^b$ is the boundary reference nodal coordinates matrix defined as

$$\mathbf{D}^b = \begin{bmatrix}\mathbf{D}_1 & \mathbf{D}_2 & \dots & \mathbf{D}_{n_b}\end{bmatrix}, \tag{2.225}$$

where n_b is the number of boundary nodes and $\mathbf{D}_i$ is the reference i^{th} node coordinates matrix defined in 2D problems as

$$\mathbf{D}_i = \begin{bmatrix} Y_1\boldsymbol{I} \\ Y_2\boldsymbol{I} \end{bmatrix}_i, \tag{2.226}$$

and in 3D problems as

$$\mathbf{D}_i = \begin{bmatrix} Y_1\boldsymbol{I} \\ Y_2\boldsymbol{I} \\ Y_3\boldsymbol{I} \end{bmatrix}_i, \tag{2.227}$$

2.14.5 Homogenized consistent tangent modulus

After the solution of the micro-scale equilibrium problem and the computation of the macro-scale stress tensor, the Newton-Raphson scheme iterative at the macro-scale still needs a tangent matrix consistent with the state update procedure (see Equations (2.203)-(2.204)). The material consistent tangent modulus at each integration point is defined as

$$\mathbf{A} = \frac{\partial \boldsymbol{P}}{\partial \boldsymbol{F}}, \tag{2.228}$$

and, attending to Equation (2.224), can be written in the discretized domain as

$$\mathbf{A} = \frac{\partial \mathbf{P}}{\partial \mathbf{F}} = \frac{1}{v_{\mu,0}}\mathbf{D}^b\frac{\partial \mathbf{f}_\mu^b}{\partial \mathbf{F}}. \tag{2.229}$$

Applying the derivation chain rule and splitting the degrees of freedom according with the condensation procedure, it is possible to write

$$\begin{aligned}\mathbf{A} &= \frac{1}{v_{\mu,0}}\mathbf{D}^b \frac{\partial \mathbf{f}_\mu^b}{\partial \mathbf{u}_\mu}\frac{\partial \mathbf{u}_\mu}{\partial \mathbf{F}} \\ &= \frac{1}{v_{\mu,0}}\mathbf{D}^b \left[\frac{\partial \mathbf{f}_\mu^b}{\partial \mathbf{u}_\mu^i}\frac{\partial \mathbf{u}_\mu^i}{\partial \mathbf{F}} + \frac{\partial \mathbf{f}_\mu^b}{\partial \mathbf{u}_\mu^f}\frac{\partial \mathbf{u}_\mu^f}{\partial \mathbf{F}} + \frac{\partial \mathbf{f}_\mu^b}{\partial \mathbf{u}_\mu^d}\frac{\partial \mathbf{u}_\mu^d}{\partial \mathbf{F}} + \frac{\partial \mathbf{f}_\mu^b}{\partial \mathbf{u}_\mu^p}\frac{\partial \mathbf{u}_\mu^p}{\partial \mathbf{F}}\right] \\ &= \frac{1}{v_{\mu,0}}\mathbf{D}^b \left[\boldsymbol{k}^{bi}\frac{\partial \mathbf{u}_\mu^i}{\partial \mathbf{F}} + \boldsymbol{k}^{bf}\frac{\partial \mathbf{u}_\mu^f}{\partial \mathbf{F}} + \boldsymbol{k}^{bd}\frac{\partial \mathbf{u}_\mu^d}{\partial \mathbf{F}} + \boldsymbol{k}^{bp}\frac{\partial \mathbf{u}_\mu^p}{\partial \mathbf{F}}\right]. \end{aligned} \tag{2.230}$$

The spatial discretization of the microscopic displacement field given by Equation (2.156) yields

$$\mathbf{u}_\mu = \mathbf{D}^T(\mathbf{F}-\mathbf{I}) + \tilde{\mathbf{u}}_\mu, \tag{2.231}$$

thus the derivatives of interest may be defined in a general way as

$$\frac{\partial \mathbf{u}_\mu^{(\bullet)}}{\partial \mathbf{F}} = (\mathbf{D}^{(\bullet)})^T + \frac{\partial \tilde{\mathbf{u}}_\mu^{(\bullet)}}{\partial \mathbf{F}}, \tag{2.232}$$

with $(\bullet)$ denoting a given group of nodes. Replacement in Equation (2.230) and suitable reordering of the resulting terms gives

$$\mathbf{A} = \frac{1}{v_{\mu,0}}\mathbf{D}^b\left[\mathbf{k}^{bi}\frac{\partial \tilde{\mathbf{u}}_\mu^i}{\partial \mathbf{F}} + \mathbf{k}^{bf}\frac{\partial \tilde{\mathbf{u}}_\mu^f}{\partial \mathbf{F}} + \mathbf{k}^{bd}\frac{\partial \tilde{\mathbf{u}}_\mu^d}{\partial \mathbf{F}} + \mathbf{k}^{bi}(\mathbf{D}^i)^T + \mathbf{k}^{bf}(\mathbf{D}^f)^T + \mathbf{k}^{bd}(\mathbf{D}^d)^T + \mathbf{k}^{bp}(\mathbf{D}^p)^T\right], \tag{2.233}$$

which can be written in matricial notation as

$$\mathbf{A} = \frac{1}{v_{\mu,0}}\mathbf{D}^b\left[\begin{bmatrix}\mathbf{k}^{bi} & \mathbf{k}^{bf} & \mathbf{k}^{bd}\end{bmatrix}\begin{bmatrix}\dfrac{\partial \tilde{\mathbf{u}}_\mu^i}{\partial \mathbf{F}} \\ \dfrac{\partial \tilde{\mathbf{u}}_\mu^f}{\partial \mathbf{F}} \\ \dfrac{\partial \tilde{\mathbf{u}}_\mu^d}{\partial \mathbf{F}}\end{bmatrix} + \mathbf{K}^B\mathbf{D}^T\right], \tag{2.234}$$

where the boundary-related stiffness matrix, $\mathbf{K}^B$, is defined as

$$\mathbf{K}^B = \begin{bmatrix}\mathbf{k}^{fi} & \mathbf{k}^{ff} & \mathbf{k}^{fd} & \mathbf{k}^{fp} \\ \mathbf{k}^{di} & \mathbf{k}^{df} & \mathbf{k}^{dd} & \mathbf{k}^{dp} \\ \mathbf{k}^{pi} & \mathbf{k}^{pf} & \mathbf{k}^{pd} & \mathbf{k}^{pp}\end{bmatrix}, \tag{2.235}$$

and the total reference nodal coordinates matrix, $\mathbf{D}$, as

$$\mathbf{D} = \begin{bmatrix}\mathbf{D}^i & \mathbf{D}^f & \mathbf{D}^d & \mathbf{D}^p\end{bmatrix}. \tag{2.236}$$

Recalling the dependency relation established in Equation (2.206) and performing a condensation procedure it results

$$\mathbf{A} = \frac{1}{v_{\mu,0}} \mathbf{D}^b \left[\begin{bmatrix} \mathbf{k}^{bi} & \mathbf{k}^{bf} + \mathbf{k}^{bd}\boldsymbol{\Theta} \end{bmatrix} \begin{bmatrix} \dfrac{\partial \tilde{\mathbf{u}}_\mu^i}{\partial \mathbf{F}} \\ \dfrac{\partial \tilde{\mathbf{u}}_\mu^f}{\partial \mathbf{F}} \end{bmatrix} + \mathbf{K}^B \mathbf{D}^T \right] . \tag{2.237}$$

In order to completely determine the homogenized material consistent tangent modulus it is then required to compute the derivatives of the displacement fluctuations in order to the deformation gradient. This can be done in a straightforward manner by noticing that when the RVE is at equilibrium it is possible to write

$$\frac{\partial}{\partial \mathbf{F}} \begin{bmatrix} \mathbf{f}_\mu^i \\ \mathbf{f}_\mu^f + \boldsymbol{\Theta}^T \mathbf{f}_\mu^d \end{bmatrix} = \mathbf{0} , \tag{2.238}$$

which, after a linearization and condensation procedure similar to the one previously presented, yields the following system of linear equations

$$\begin{bmatrix} \mathbf{k}^{ii} & \mathbf{k}^{if} + \mathbf{k}^{id}\boldsymbol{\Theta} \\ \mathbf{k}^{fi} + \boldsymbol{\Theta}^T\mathbf{k}^{di} & \mathbf{k}^{ff} + \mathbf{k}^{fd}\boldsymbol{\Theta} + \boldsymbol{\Theta}^T\mathbf{k}^{df} + \boldsymbol{\Theta}^T\mathbf{k}^{dd}\boldsymbol{\Theta} \end{bmatrix}^{(k-1)} \begin{Bmatrix} \dfrac{\partial \tilde{\mathbf{u}}_\mu^i}{\partial \mathbf{F}} \\ \dfrac{\partial \tilde{\mathbf{u}}_\mu^f}{\partial \mathbf{F}} \end{Bmatrix} = - \left[\begin{bmatrix} \mathbf{K}^I \\ \mathbf{K}^F + \boldsymbol{\Theta}^T\mathbf{K}^D \end{bmatrix} \mathbf{D}^T \right]^{(k-1)} , \tag{2.239}$$

where

$$\mathbf{K}^\bullet = \begin{bmatrix} \mathbf{k}^{\bullet i} & \mathbf{k}^{\bullet f} & \mathbf{k}^{\bullet d} & \mathbf{k}^{\bullet p} \end{bmatrix} . \tag{2.240}$$

The solution of the previous system of linear equations provides the required derivatives to determine the homogenized material consistent tangent modulus and its spatial counterpart can be defined through the following relation (de Souza Neto et al., 2008)

$$\mathsf{a}_{ijkl} = \frac{1}{J} \mathsf{A}_{ipkq} F_{jp} F_{lq} . \tag{2.241}$$

Chapter 3
Efficient Microstructure Generation of Particle-Reinforced Materials

3.1 Multi-scale modeling of particle-reinforced materials

Particle-reinforced heterogeneous materials can be essentially characterized by a given set of non-overlapping particles[1], associated with single or multiple distinct phases, dispersed in a connected matrix phase. In general, the dispersion of particles through suitable manufacturing processes aims to improve the thermomechanical properties of the neat matrix material by taking into account the envisaged application requirements and optimal conditions (Lombardo et al. (1994), Bärwinkel et al. (2016), Bargmann (2018)). Thus, the main idea is to combine the benefical properties of a given set of compatible constituents and produce a material that possesses superior properties that those of each individual constituent.

Many advanced engineering materials can be classified as particle-reinforced materials and be found in a broad spectrum of applications (see Figure 3.1). The so-called metal matrix composites are the most widely used composites in the industrial scale (Haghshenas, 2016) and have gained significant attention in the aerospace, aircraft and automotive industries due to their elevated strength, stiffness, Young's modulus, fatigue strength, corrosion resistance, wear resistance, and low density compared to unreinforced alloys (e.g., Liu et al. (2013), Baradeswaran and Elaya Perumal (2014), Sharma et al. (2015), Shirvanimoghaddam et al. (2017), Selvam et al. (2021)). These are composed of a relatively ductile metallic matrix (e.g., aluminum, copper, magnesium, titanium) that is reinforced with stiff ceramic particles or short-fibers such as silicon carbide, boron carbide, aluminum oxide and titanium carbide (e.g., Toptan et al. (2010), Dinaharan et al. (2011), Knowles et al. (2014), Fadavi Boostani et al. (2015), Abraham et al. (2019)). Another example are the so-called short-fiber reinforced polymer composites (SFRP), extensively used in the automotive, aerospace, microelectronic and household applications. These composites are characterized by a given polymeric continuum matrix (e.g., polycarbonate, polyamide, polypropylene, polyethersulphone) reinforced with relatively short (length less than a few millimeters), variable length and imperfectly aligned fibers (e.g., glass, carbon, graphite). Besides the superior thermomechnical properties relative to the neat polymer matrix, these composites can be quickly processed in large-scale production at a relatively low cost through conventional techniques such as extrusion compounding and injection moulding (Fu et al., 2019). As a last example, polymer blending has attracted much attention as an easy and cost-effective method of developing polymeric materials that have versatility for commercial applications (Thomas et al., 2014). Polymer blends are essentially characterized by a mixture of two or more polymers (e.g., thermoplastic-thermoplastic, thermoplastic-thermosetting, thermoplastic-rubber) that under suitable blending conditions are able to deliver high performance taylored properties. Several polymer blends exhibit the morphology of a particle-reinforced material, such as the PC/ABS blends that receive particular attention on this thesis. In this thermoplastic-thermoplastic blend, the excellent mechanical and thermal properties of PC (e.g., toughness at low

[1] In the present document, the term 'particle' is employed to denote any convex arbitrarily-shaped subdomain embedded in a continuum matrix.

temperature, unnotched impact strength, high-temperature stability) are combined with the complementary properties of ABS (toughness at low temperature, low notch sensitivity, notched impact resistance, and ease of processability).



(a) (b)

(c) (d)

Figure 3.1: Examples of particle-reinforced composite materials: (a) SEM micrograph of aluminum oxide powder of aluminum based metal matrix composite (taken and adapted from Rahimian et al. (2009)); (b) SEM micrograph of aluminum oxide short-fibers of aluminum based metal matrix composite (taken and adapted from Clyne (2018)); (c) SEM micrograph of short carbon fibers in PES/SCF composite (taken and adapted from Li et al. (2015)); (d) SEM micrograph of PC/ABS(70/30) polymer blend (taken and adapted from Dong et al. (1993)).

Given the technological importance of this class of materials and an increasing market pressure, manufacturing processes are becoming highly sophisticated and capable of manipulating the material's microstructure to unprecedented levels. However, to truly push material's properties to their limits while still satisfying reliability and safety standards, in-depth numerical studies of their properties and performance are a critical part of the development process. As described in Chapter 2, a key requirement to accurately perform multi-scale material analyses is to develop representative computational domains that resemble as much as possible the real material's microstructure. Recalling here the definition of Hill (Hill, 1963), the so-called representative volume element (RVE) is a volume of material sufficiently large such that it contains enough morphological and topological details of the microstructure to be representative in an average sense. From a numerical point of view, it also bears reminding that periodic boundary conditions are often applied due to their bounded

nature (e.g., Suquet (1985), Hollister and Kikuchi (1992), Nemat-Nasser and Hori (1995), Terada et al. (2000), Miehe (2002)) and because the resulting homogenized properties converge faster to their 'exact' values as the RVE size increases (e.g., Terada et al. (2000), Kanit et al. (2003)). Besides these already challenging aspects, the data-driven methodologies introduced in Chapter 1 demand efficiency, flexibility and robustness. On the one hand, these frameworks require building large material databases and hence the generation of thousands of RVEs in a reasonable amount of time. On the other hand, compliance with a wide variety of microstructure descriptors is required together with a non-supervised efficacy.

In this context, the main goal of this chapter is the development of a robust and efficient method for the computational generation of high-fidelity particle-reinforced materials' RVEs. Section 3.2 provides a brief literature review on computational methods for microstructure generation and sets the suitable approach to tackle one of the challenges of this thesis (see Section 1.2.3). Section 3.3 describes the geometrical parametrization of the different admissible particle types as well as the intersection conditions between them. A new computational microstructure generation method coined Adaptive Multi-temperature Isokinetic Method (AMINO) is proposed in Section 3.4. Each stage of the proposed formulation is thoroughly described, including the generation of the initial configuration, the computation of the intersection forces between particles, the enforcement of the microstructure periodicity and, most importantly, the novel coupling between an adaptive time integration scheme and a multi-temperature isokinetic thermostat. Several numerical results are then presented in Section 3.5 to demonstrate the performance of AMINO, accounting for examples to validate the main formulation features, complex microstructures to illustrate the compliance with a wide spectrum of microstructure descriptors, and quantitative comparisons between experimental micrographs and the computationally generated microstructures. Finally, the ability of AMINO to generate high-fidelity RVEs of PC/ABS polymer blends with particulate morphology is illustrated in Section 3.6 and the main conclusions are summarized in Section 3.7.

3.2 Microstructure computational generation methods

According to the classification proposed in Bargmann (2018), the computational methods for microstructure generation can be divided into three types: (1) methods based on reconstruction from experimental data, (2) physics-based generation methods, and (3) geometrical generation methods. A brief review of these methods and some relevant contributions is provided in what follows, with particular focus being given to geometrical generation methods. In the author's opinion, the latter is the most suitable family of methods to generate particle-reinforced materials' RVEs, as discussed in the following sections.

3.2.1 Reconstruction from experimental data

In this family of methods, the microstructure is reconstructed from limited microstructural information often based on experimental imaging (e.g., lower-order correlation functions). However, it is remarked that such reconstruction procedures are non-unique, hence it is a distinct problem from data decompression algorithms that operate on complete information (Torquato, 2013).

According to Torquato (2013), the first reconstruction methods were based on thresholding Gaussian random fields. One of these procedures is presented in Roberts (1997), where microstructures are obtained from level cuts of random Gaussian fields, chosen so that the two-point probability function of the model coincides with real micrographs. In Yeong and Torquato (1998) this method is generalized, being proposed a stochastic optimization technique based on simulated annealing to reconstruct random media. Following this work, in

Jiao and Chawla (2014), a framework to model heterogeneous inclusions of secondary phases based on the directional correlation functions of the inclusions is described, including the directional two-point cluster functions. In Fullwood et al. (2008), phase-recovery signal processing algorithms are extended and applied to the problem of reconstructing microstructures from their 2-point statistics. In Tahmasebi and Sahimi (2013), a new reconstruction method based on a cross-correlation function and a one-dimensional raster path is introduced, providing an accurate description of a wide variety of materials and media. The reconstruction uses a single 2D slice of data to reconstruct an entire 3D medium.

Although these methods are primarily used with low-order statistical information, being the most easy to extract, this may be insufficient to allow the reconstruction of high-fidelity microstructures (Roberts, 1997). As shown in Torquato (2013), even when employing multiple statistical functions to describe the material, the reconstruction efforts may lead to microstructures whose phases do not resemble the non-overlapping particles found in particle-reinforced materials. In contrast with amorphous morphologies, high-order statistical information about the actual microstructure is needed to reconstruct phases with well-defined particles. Even in the absence of the previous limitations, these methods would not be suitable to be employed in a data-driven framework due to the general lack of available data. On the one hand, obtaining high-fidelity experimental data is a time-consuming and costly process. Acquiring micrographs for all the points in the design space would be extremely challenging and would required prohibitive costs. On the other hand, it would be cumbersome to accurately manufacture microstructures compliant with a potentially wide range of microstructure descriptors.

3.2.2 Physics-based generation methods

The main idea underlying the methods belonging to this family is to generate microstructures by simulating the physical manufacturing process. For instance, by combining mold filling flow simulations with hydrodynamic models of immersed fibers, the fibers' orientation in fiber-reinforced composites obtained through injection molding can be predicted. Although the information gathered by these means may be useful as input to other generation methods (e.g., Folgar and Tucker (1984), Wang et al. (2008), Phelps et al. (2013), Tseng et al. (2018)), simulation of the manufacturing process is, in most cases, inefficient for generating particle-reinforced microstructures. Bulk or mixing simulations are far too complex and the associated computational costs are usually not worth the gained findings about particle distribution (Bargmann, 2018). Therefore, even if these methods are able to produce high-fidelity particle-reinforced microstructures, the scaled computational cost to generate the required large databases forbids their adoption.

3.2.3 Geometrical generation methods

Particle-reinforced materials are most easily characterized by defining the embedded particles through well-defined geometrical shapes than statistical probability functions (Bargmann, 2018). The so-called geometrical generation methods are thus based on a suitable geometrical parametrization of the particle material phases. Nonetheless, the required data about these microstructures descriptors (e.g., particles' size and orientation, particles' spatial distribution) must be of course gathered from experimental observations and from the technological parameters of the manufacturing process. Three types of geometrical generation methods are distinguished by Buryachenko et al. (2003): (1) methods based on molecular dynamics, (2) methods based on Monte Carlo techniques, and (3) methods based on dense random packing.

Molecular dynamics

Molecular dynamics is a widely used computational approach in which the classical equations of motion are solved numerically and the resulting particles' trajectories are used to extract macroscopic observables (Tuckerman, 2010). Among the different types of molecular dynamics simulations, two are here distinguished: event-driven and time-driven. In an event-driven simulation, the focus is only given to those instants at which noteworthy events occur (e.g., collisions between particles). For instance, in a system of hard disks, the particles' paths are determined analytically, and the collision times and locations are computed and sorted in a priority list. The events are then solved according to their priority, advancing each particle until the first collision event in the priority list occurs. New velocities are consequently assigned to the colliding particles that result in new collision events. These are added to the priority list and the process repeats until some stopping criterion is met. In contrast, in a time-driven simulation, the time is discretized and the position of each particle is updated at each time increment, checking for overlaps. When an overlap is detected, the simulation is rolled back to the instant of collision, the velocities of the colliding particles are updated, and the simulation proceeds (Sedgewick and Wayne, 2011).

Each of these types of molecular dynamics simulations inspired the development of microstructure geometrical generation methods. In Lubachevsky and Stillinger (1990) and Lubachevsky et al. (1991), an algorithm based on event-driven molecular dynamics able to achieve high volume fractions of particles modeled as disks and spheres is proposed. Particles begin as moving points, grow in size at a uniform rate, undergo non-conserving collisions, and eventually jam up. The organization of the particles in the final configuration is highly dependent on the compression rate (i.e., rate of growth of particles), with higher compression rates leading to a more crystallized microstructure. This algorithm is generalized to ellipsoidal particles in Donev et al. (2004, 2005), using a partial-update near-neighbor list algorithm and bounding sphere complexes for very aspherical particles. In Ghossein and Lévesque (2013), a similar scheme to produce packings of ellipsoidal particles is proposed, computing binary collision times by finding the roots of a nonlinear function. It is important to remark that, in these methods, the successive generated configurations are always legal, i.e., there are no intersections between particles in any intermediate time step. Concerning generation methods based on time-driven molecular dynamics simulations, Salnikov et al. (2015) presented an algorithm that, after starting from an initial random illegal configuration, eliminates all the intersections by postulating repulsive forces between intersecting particles proportional to the depth of the overlapping domain. Later, Herráez et al. (2020) introduce a similar approach able to efficiently generate two-dimensional microstructures with non-convex particle shapes.

In either case, the implementation of this type of generation method requires some sort of contact algorithms to detect and possibly characterize the overlap between particles (Bargmann, 2018). Detecting an overlap between two similar-shaped particles at a given time instant can be done analytically for disks, ellipses, spheres, ellipsoids, and cylinders (Perram and Wertheim (1985), Hughes and Chraibi (2012), Salnikov et al. (2015), Wang et al. (2019b)). More complex shapes and/or interaction between different particle types often require the use of numerical methods. Moreover, to avoid computing unnecessary overlap checks, i.e., particles that can a priori be shown not to interact, methods such as the cell method and the near-neighbor list method may lead to significant efficiency improvements (Frenkel and Smit (2001), Donev et al. (2005)).

Monte Carlo techniques

The Random Sequential Adsorption (RSA) method is probably the most used method to generate microstructures of particle-reinforced materials. As the name implies, the underlying scheme fills the spatial domain with particles in a random and sequential manner. When a new particle

is to be added, a random location is picked. If the particle does not intersect any previously placed particle, it is placed there, otherwise it is discarded. A new particle is then taken and this process is repeated until the desired phase volume fraction is reached (Bargmann, 2018). Despite the simplicity of this method and its high efficiency for low volume fractions, it becomes slow at high volume fractions and may present significant saturation limits. In Buryachenko et al. (2003), some modifications of the RSA method are proposed when dealing with spherical particles. By including a virtual shaking of the particles through random displacements, a better mix of the system is achieved and more particles can be randomly placed, raising the saturation limit as a consequence. A more complex RSA-based algorithm is developed in Melro (2011), where the particles are perturbed in order to get a closer packing, and thus increasing the likelihood of placing a new particle without intersections. Another variant called the rejection-free RSA method is proposed for disks (Krauth, 2006). The main idea is to keep track of the area where disks may still be legally placed using a grid system, sampling the position for the new particle only from this area. This results in a massive speedup of the algorithm, as the biggest limitation of the RSA method at high volume fractions is precisely a high rejection rate. Miranda (2015) presented a similar algorithm, being claimed that it has linear complexity and that the time taken to place any disk is constant during the process.

Following a different approach, in Vaughan and McCarthy (2010), another Monte Carlo scheme is presented for disks based on a Markov-chain sampling. After the first particle is randomly placed in the RVE, the next particle is always established relative to the last-placed particle. The magnitude of the position vector is sampled from the nearest neighbor function and the associated direction from a uniform distribution, being the particle accepted only if there is no overlap with any other already placed. Another approach related o Markov-chain sampling starts from an initial periodic configuration. The main idea is to sample the configuration by randomly perturbing the particles' positions until a legal configuration sufficiently decoupled from the initial one is found (Bargmann, 2018). Following this idea, Catalanotti (2016) presented a method that can produce microstructures of spheres with a volume fraction as high as the theoretical maximum, starting from periodic arrangements of spheres derived from a face-centered cubic unit cell. This is possible for spheres of the same size, for which the maximum packing arrangement is known. However, this is not the case for most other shapes, which may lead to difficulties in finding a starting configuration at high volume fractions.

Other Monte Carlo schemes are used to explore the configuration space, the so-called cluster algorithms described in Krauth (2006). Starting from an initial legal configuration, these algorithms allow for movements of independent particles even if they temporarily result in one or more intersections. For instance, in the avalanche cluster algorithm an independent particle is randomly displaced and, if the displacement results in an overlap, the other particle is simply moved out of place to eliminate it. This leads to an avalanche, where the particles tip-off each other until a legal configuration is found.

Dense random packing

The goal of dense random packing generation methods is to create a random arrangement of particles such that the volume fraction is as high as possible. There are, however, relatively few analytical results related to the dense packing of even the simplest geometrical objects. For instance, packing densities for close lattice packing are $\pi/\sqrt{12} \approx 0.9069$ in $\mathbb{R}^2$, corresponding to a triangular arrangement of disks, and $\pi/\sqrt{18} \approx 0.7405$ in $\mathbb{R}^3$, corresponding to the face-centered cubic unit cell arrangement of spheres. In Buryachenko et al. (2003), the dense random packing methods are classified into two types: sequential generation models and collective rearrangement models.

Simply speaking, sequential generation models group together approaches where particles

are added sequentially to the system using an appropriate rule. In Bennett (1972), the cluster growth model is proposed, able to generate aggregates of several thousands of hard spheres of equal size. These are constructed by sequentially depositing additional spheres, one at a time, at surface sites of a small seed cluster, placing each new sphere in contact with the other spheres previously placed. In Feng et al. (2002), an advancing front-based algorithm to generate a random packing for disks with different radii is developed. The same authors extended this approach to ellipses, convex polygons, and spheres (Feng et al., 2003). In Ilin and Bernacki (2016), the advancing layer algorithm to construct packings of ellipses is proposed. Each ellipse is approximated by a set of circles and placed on the particle that is at the smallest 'height' in the domain, checking if there are no intersections with the remaining neighboring particles. An alternative approach is supplied in Zinchenko (1994), where the particles are allowed to swell by the numerical solution of the so-called differential equations of densification. As their radius increases, the algorithm tries to retain contacts throughout the densification as far as possible, terminating in a perfect contact network. Another model of the sequential type takes the designation of 'rigid sphere free fall into a virtual box', consisting of the sequential vertical drop of particles from random points onto the surface of an existing particle cluster growing upwards. The movement of the particles after being dropped is controlled and influences the density obtained (Nolan and Kavanagh (1992), Kondrachuk et al. (1997), Kurashige et al. (1999), Furukawa et al. (2000)).

Collective rearrangement models are typically employed in combination with RSA algorithms that, in a first step, generate an initial configuration that may contain overlapping particles. A denser packing with an overlap free configuration is achieved in a second step by repositioning and shrinking some or all particles (Bargmann, 2018). In Jodrey and Tory (1985), a numerical scheme to realize homogeneous and isotropic packing of spheres by assuming hypothetical spheres having a dual structure is presented, the inner diameter defining the true density and the outer one a nominal density. The algorithm eliminates overlaps among outer spheres using an heuristic while slowly shrinking the outer diameter. The two diameters approach each other and the eventual coincidence of true and nominal densities terminates the procedure. A variation of this method is presented in Mościński et al. (1989), where instead of using an heuristic, the displacement of the particles is proportional to their overlaps. In He and Ekere (2001), a method that uses heuristics to decrease the overlap area between randomly generated spheres in a cubic space is also presented. Relaxation and expansion steps are repeated several times until a random packing is obtained when the mean overlap rate drops below a preset tolerance. A similar approach is proposed in Segurado and Llorca (2002), where a unit cell is first generated through the RSA method with a volume fraction lower that the desired value. The cell is then compressed in several steps and the particles' positions and volumes are updated at each compression stage. The eventual intersections between each stage are dealt with using a Markov-chain approach, being each intersecting particle moved randomly until there are no overlaps.

Yet another type of methods are the ones based on the adaptive shrinking cell (ASC) algorithm (Torquato and Jiao, 2009). It intercalates boundary deformations, compression and shear, with particle movements, translation and rotation, to achieve a maximum random jammed packing. When a given step in the process leads to particle intersections, it is discarded and a new attempt to find a legal configuration is performed. An extension to enforce particular order criteria is introduced by Liu et al. (2017), and later explored to study the maximally dense random packing of a broad spectrum of particle shapes (e.g., Meng et al. (2017), Liu et al. (2018a), Yuan et al. (2019)).

3.2.4 Choice of base approach

Given the requirements established for the generation of particle-reinforced materials RVEs, both molecular dynamics and Monte Carlo techniques seem suitable approaches. Although dense random packing methods may be computationally efficient in some cases, they are developed with the goal of generating dense packings with the highest volume fraction possible. For instance, the microstructures produced by sequential methods tend to be too orderly to plausibly resemble real microstructures (Feng et al., 2002). Moreover, these methods exhibit limitations concerning microstructures containing particles of different types, namely in the 3D case.

The approach proposed in Salnikov et al. (2015), a time-driven molecular dynamics scheme, is adopted as a suitable basis of development point. As shown in some examples presented in Salnikov et al. (2015), the method is efficient, has an high flexibility regarding the admissible particle types and is able to produce microstructures with high volume fractions. In fact, any particle type can be considered as long as it is possible to define a clear intersection criterion that supplies the intersection length required for the computation of the interaction forces. Additionally, there are no constraints concerning the initial position of the particles, irrespective of their type. Although the simulation scheme may not be particularly physically accurate, this is not an issue in the present context. The goal is to find a legal configuration and not an equilibrated system whose macro-scale observables approximate real systems.

Despite all the aforementioned promising features, this method exhibits some limitations that prevents its adoption from fulfilling the established requirements. Therefore, in the remainder of this chapter a new computational generation method for particle-reinforced materials is proposed inspired on the approach presented in Salnikov et al. (2015). This method is coined AMINO (Adaptive Multi-temperature Isokinetic Method).

3.3 Particle types and intersections

Given that AMINO is a geometrical generation method, the first step consists in a suitable geometrical parametrization of the particle material phases. The intersection conditions between the different particle types must be then characterized.

3.3.1 Geometrical parametrization

AMINO can effectively deal with the different types of particles that provide a reasonable approximation to the particles found in many particle-reinforced materials. Irrespective of their type, the position of each particle is from here on defined as the position of its geometrical center.

In the 2D case, disks and ellipses are considered (see Figure 3.2(a)). A disk is defined by its radius, r, and an ellipse by its major and minor principal semi-axes, a and b, respectively. The orientation of the ellipse is specified by the angle that the major axis forms with the positive x semi-axis, denoted by θ. In the 3D case, spheres, ellipsoids and cylinders are considered (see Figure 3.2(b)). A sphere is characterized by its radius, r, an ellipsoid by its three principal semi-axes, a, b and c, and a cylinder by its length, l, and base radius, r_b. The spatial orientation of the ellipsoid is determined through a prescribed rotation axis, $\boldsymbol{e}_r$, and a rotation angle around that same axis, θ. It is remarked that the ellipsoid's reference orientation is defined as the one where the three principal axes are parallel to the three coordinate axes. The orientation of the cylinder is directly given by its axis, $\boldsymbol{e}_r$. In the general case of ellipses and ellipsoids, alternative parameters can also be supplied to geometrically define these particles (e.g., length ratios between principal axes).

Moreover, in what concerns the flexibility of the proposed method, any number of material phases is accepted, being a particle type and a given number of particles or volume fraction



Figure 3.2: Particle types and associated geometrical descriptors admissible in AMINO: (a) 2D (disk, ellipse); (b) 3D (sphere, ellipsoid, cylinder).

specified for each phase. All of the previous microstructure geometrical descriptors can be supplied either as a fixed prescribed value, assumed equal for all particle in that phase, or as following a given statistical distribution. Three types of statistical distributions are considered: (1) a uniform distribution, where lower and upper bounds must be prescribed; (2) a discrete distribution, where each value along with its probability must be prescribed; and (3) a Gaussian distribution, where the mean and standard deviation must be prescribed.

3.3.2 Intersection conditions: detection, length and direction

AMINO requires the ability to detect intersections between particles and, if they actual intersect each other, the ability to compute the associated intersection length and direction. The intersection length is here defined as the minimum distance that one of the geometrical shapes must be displaced without rotation to eliminate the intersection. As detailed later in Section 3.4, both intersection length and direction are needed to determine the interaction forces between intersecting particles.

In the particular case of an intersection between two disks or spheres, the detection of intersection requires the simples comparison between the sum of their radii and the distance between the geometrical centers. The intersection length is equal to the difference of the previous quantities and the associated direction coincides with the vector difference between geometrical centers. However, in the cases involving the remaining particle types, as well as intersection between different types of particles, such a simple approach is not readily available or it's cumbersome to derive analitically. In what concerns the detection of intersection though, some efficient procedures have been proposed in the literature for some instances and are thus adopted, namely: the intersection ellipse-ellipse (Hughes and Chraibi, 2012), the intersection ellipsoid-ellipsoid (Wang et al., 2001), and the intersections cylinder-cylinder and sphere-cylinder (Salnikov et al., 2015).

To perform the detection of intersections other than the previously mentioned, a numerical approach known as Gilbert-Johnson-Keerthi (GJK) distance algorithm (Gilbert et al., 1988) is adopted. Despite being able to determine the minimum distance between two disjoint convex sets of points, it is only employed in the present context to detect the intersection of two convex shapes. For the sake of completeness, a brief description of this algorithm is provided in what follows.



Figure 3.3: Support function of a two-dimensional convex shape $\mathscr{A}$, $h_{\mathscr{A}}: \mathbb{R}^2 \to \mathbb{R}^2$.

A given convex shape can be described by the so-called support function. This function returns the point on the shape which exhibits the highest dot product for a specified direction. For instance, let $\mathscr{A}$ be a given convex shape in the n-dimensional space. Its support function, $h_{\mathscr{A}}: \mathbb{R}^n \to \mathbb{R}^n$, returns, for some input direction $\boldsymbol{d}$, the point $\boldsymbol{p}$, such that $\boldsymbol{d} \cdot \boldsymbol{p}$ has the highest possible value for all $\boldsymbol{p} \in \mathscr{A}$ (see Figure 3.3).

The GJK algorithm is based on a property related to the Minkowski difference of two convex shapes, defined as the set formed by subtracting each position vector in one of the shapes to each position vector in the other. Letting $\mathscr{B}$ be another convex shape in the n-dimensional space, its Minkowski difference with $\mathscr{A}$ is given by

$$\mathscr{A} - \mathscr{B} = \{\boldsymbol{p} - \boldsymbol{q} \mid \boldsymbol{p} \in \mathscr{A}, \boldsymbol{q} \in \mathscr{B}\}, \tag{3.1}$$

where $\boldsymbol{p}$ and $\boldsymbol{q}$ are points belonging to $\mathscr{A}$ and $\mathscr{B}$, respectively (see Figure 3.4).



Figure 3.4: Construction of the Minkowski difference of two convex shapes $\mathscr{A}$ and $\mathscr{B}$ in the two-dimensional space.

The support function of the Minkowski difference in a given direction, $\boldsymbol{d}$, can be simply obtained from the support functions of the associated shapes as

$$h_{\mathscr{A}-\mathscr{B}}(\boldsymbol{d}) = h_{\mathscr{A}}(\boldsymbol{d}) - h_{\mathscr{B}}(-\boldsymbol{d}). \tag{3.2}$$

The property mentioned earlier states that the minimum distance between the two convex sets, $\mathscr{A}$ and $\mathscr{B}$, is equal to the closest distance between the Minkowski difference of the two

shapes, $\mathscr{A} - \mathscr{B}$, and the origin, $\boldsymbol{o}$ (see Figure 3.5). It is possible to conclude that if $\mathscr{A} - \mathscr{B}$ contains the origin, $\boldsymbol{o}$, then the two convex shapes intersect each other. Note that in this case, the smallest distance between the boundary of $\mathscr{A} - \mathscr{B}$ and the origin is the sought intersection length.



Figure 3.5: Location of the Minkowski difference, $\mathscr{A} - \mathscr{B}$, of two intersecting and non-intersecting convex shapes, $\mathscr{A}$ and $\mathscr{B}$, relative to the origin, $\boldsymbol{o}$.

Having established the previous property, it then remains to determine if $\mathscr{A} - \mathscr{B}$ contains the origin or not. In order to do so, a sequence of simplices is generated iteratively, aiming to enclose the origin. A simplex is defined as a point, a line, a triangle, or a tetrahedron. It is attempted to enclose the origin with a triangle and a tetrahedron n two and three dimensions, respectively. Given that the Minkowski difference of two convex sets is also convex, if the origin is inside a simplex constructed from points belonging to the Minkowski difference, then it must also belong to the set.

The sequence of simplices is generated considering, in each iteration, a new point that is obtained from the support function of the Minkowski difference and a given search direction. As the goal is to enclose the origin, this search direction will always be defined by the part of the current simplex that is closest to the origin. In particular, the search direction will always be perpendicular to the closest part of the simplex and in the direction of the origin. The remainder of the simplex in each iteration is discarded. The particular procedure used here terminates either when a simplex that encloses the origin is found or when the new point has the opposite direction relative to the search direction (see Figure 3.6). The pseudo-code for the GJK algorithm is summarized in Box 3.1.

Having handled the intersection detection for all the admissible intersection types, it remains to compute the intersection length and determine the corresponding direction, $||\boldsymbol{\delta}||$ and $\boldsymbol{\delta}$, respectively (see Figure 3.7). The computation of both these quantities cannot be, in general, performed directly from the support function of the Minkowski difference. However, since the intersection length is the minimum length from the origin to the boundary of the Minkowski difference, this computation can be conveniently posed as a minimization problem. Thus, the goal is to find the direction that minimizes the norm of the position vector among the points obtained from the support function of the Minkowski difference.

Several approaches could be, of course, adopted to tackle such minimization problem. For instance, the Nelder-Mead simplex algorithm can be effectively used to determine the intersection length and the associated direction along which the particles must be displaced to eliminate the intersection. Nonetheless, to avoid the use of an iterative minimization procedure, an approximation to the intersection length and associated direction is proposed here. Consider the normalized vector difference between the geometrical center of the two



Figure 3.6: Diagram of the Gilbert-Johnson-Keerthi algorithm: (a) intersecting shapes, $\mathscr{A}$ and $\mathscr{B}$; (b) non-intersecting shapes, $\mathscr{A}$ and $\mathscr{B}$.

intersecting particles $\mathscr{A}$ and $\mathscr{B}$, denoted by $\boldsymbol{d}_m = (\boldsymbol{m}_{\mathscr{B}} - \boldsymbol{m}_{\mathscr{A}})/\|\boldsymbol{m}_{\mathscr{B}} - \boldsymbol{m}_{\mathscr{A}}\|$, and the point $\boldsymbol{p}_m$, obtained from the support function of the Minkowski difference, $\boldsymbol{p}_m = h_{\mathscr{A}-\mathscr{B}}(\boldsymbol{d}_m)$. A simple and efficient approximation to the intersection length, $\tilde{\boldsymbol{\delta}}$, can be obtained through the projection $\boldsymbol{p}_m \cdot \boldsymbol{d}_m$, choosing as the corresponding direction, the direction of the vector difference between the two particles, $\boldsymbol{d}_m$ (see Figure 3.7). The proposed approximation can thus be seen as a suitable compromise between the true intersection length and direction, and the values found directly from the support function of the Minkowski difference, being efficiently computed for any admissible particle types. Note that this procedure supplies the exact solution, i.e., $\tilde{\boldsymbol{\delta}} = \boldsymbol{\delta}$, for the particular cases of disks and spheres. However, in the particular case of highly elongated particles at moderate-to-high volume fractions, it may hinder the removal of the overlap residue in the last stages of the simulation. This aspect is further discussed and dealt with in Section 3.4.7.

Box 3.1: Pseudo-code for the Gilbert-Johnson-Keerthi algorithm (Gilbert et al., 1988).

(i) Choose a random direction $\boldsymbol{d}_1$

(ii) Use the support function of the Minkowski difference to obtain the corresponding point to $\boldsymbol{d}_1$, $\boldsymbol{p}_1$

$$\boldsymbol{p}_1 = h_{\mathscr{A}-\mathscr{B}}(\boldsymbol{d}_1) = h_{\mathscr{A}}(\boldsymbol{d}_1) - h_{\mathscr{B}}(-\boldsymbol{d}_1)$$

(iii) Set the first simplex equal to $s_1 = \{\boldsymbol{p}_1\}$

(iv) Consider as the new search direction the opposite direction to the position vector of $\boldsymbol{p}_1$, i.e. the new search direction $\boldsymbol{d}_2 = -\boldsymbol{p}_1$

(v) Initialize the counter, $k := 2$

(vi) Use the support function of the Minkowski difference to obtain the corresponding point to $\boldsymbol{d}_k$, $\boldsymbol{p}_k$

$$\boldsymbol{p}_k = h_{\mathscr{A}-\mathscr{B}}(\boldsymbol{d}_k) = h_{\mathscr{A}}(\boldsymbol{d}_k) - h_{\mathscr{B}}(-\boldsymbol{d}_k)$$

(vii) If $\boldsymbol{d}_k \cdot \boldsymbol{p}_k < 0$, terminate the procedure, concluding that the shapes do not intersect

(viii) Add the point $\boldsymbol{p}_k$ to the simplex s_{k-1}

(ix) Obtain a new simplex, s_k, keeping the sub-simplex of the old simplex that was closest to the origin, $s_k \subseteq s_{k-1}$, the corresponding search direction, $\boldsymbol{d}_{k+1}$, and check if it contains the origin

(x) If the simplex contains the origin, terminate the procedure, concluding that the shapes intersect

(xi) Increase the counter, $k := k+1$

(xii) Go to step (vi)



Figure 3.7: Proposed approximation to the intersection length, $||\tilde{\boldsymbol{\delta}}||$, and direction, $\tilde{\boldsymbol{\delta}}$, between two convex shapes, $\mathscr{A}$ and $\mathscr{B}$.

3.4 Adaptive Multi-temperature Isokinetic Method

Having established the geometrical parametrization and the intersection conditions between the different admissible particle types, the proposed formulation of AMINO (Adaptive Multi-temperature Isokinetic Method) is now discussed.

3.4.1 General time-driven molecular dynamics scheme

As outlined in Frenkel and Smit (2001), the general procedure of a time-driven molecular dynamics simulation starts by generating an initial configuration and computing the associated forces between the particles in the system. After a suitable time discretization and time integration of the differential equations of motion, the position and velocity of each particle of the system are updated. This will result in a new configuration and the forces between particles must be consequently updated. These two steps are repeated, one after the other, until a given termination criterion is satisfied. This procedure is outlined in Box 3.2 and will produce a microcanonical ensemble, i.e., a system containing a constant number of particles at constant volume and energy.

Box 3.2: General time-driven molecular dynamics simulation of a microcanonical ensemble.

(i) Generate an initial configuration

(ii) Initialize the increment counter, $i := 0$

(iii) Compute interaction forces between particles

(iv) Update particles' positions and velocities through the solution of the discretized equations of motion

(v) Check termination criteria

If (condition) then

- Exit

else

- Update the increment counter, $i := i + 1$
- Go to step (iii)

Nonetheless, in the present context, the most convenient ensemble is the so-called canonical ensemble, where the volume and number of particles are also kept constant. However, rather than the energy of the system, it is the temperature that is maintained constant (Frenkel and Smit, 2001), implying the formulation of a thermostat, as discussed later.

In the following sections each stage of the proposed time-driven molecular dynamics method is detailed. First, the generation of the initial configuration is covered, including both the initial positions of the particles and their geometrical descriptors. Second, the concept of legal configuration is introduced, discussing the computational termination criteria and microstructure requirements. Third, the computation of the interaction forces between particles is discussed as well as the adopted approach to enforce the microstructure periodicity. Finally, the most significant features of the proposed method are presented, namely the adaptive time integration scheme and a multi-temperature isokinetic thermostat.

3.4.2 Initial configuration

In both the present work and the method proposed in Salnikov et al. (2015), the initial configuration is generated using the well-known Poisson point process to place the center points of the particles inside the RVE, i.e., the bounded spatial domain where the particles will move and interact with each other. Without loss of generality, the coordinate system adopted throughout this chapter is illustrated in Figure 3.8 for both 2D and 3D RVEs. Each component of the position vector of each particle is thus sampled from a uniform distribution between zero and the side length of the RVE in the corresponding dimension.



(a) (b)

Figure 3.8: Coordinate system adopted in the computational generation of: (a) 2D RVE; (b) 3D RVE.

3.4.3 Legal configuration

The legal configuration is determined according to a prescribed maximum average overlap residue, Ψ_{lim}. The average overlap residue, Ψ, is here defined as the sum of the norms of the repulsive interaction forces between each pair of particles divided by the number of particles. Successful termination of the generation method will produce a microstructure with an average overlap smaller or equal to the specified threshold. In all numerical examples provided in this chapter, the maximum overlap residue is set to zero, $\Psi_{\text{lim}} = 0$, i.e., a given RVE is only accepted if there is no intersection between the particles.

Under certain conditions it may not be simply possible to generate a microstructure compliant with the prescribed microstructural descriptors. For instance, if the prescribed volume fraction exceeds the maximum packing density, the final configuration will always exhibit overlaps between particles. Other example may include microstructural descriptors that shrink excessively the space of admissible configurations, e.g., high volume fractions with low number of particles. In order to deal with these cases, a maximum number of iterations can be enforced and/or a control procedure over the relative change of the total overlap residue over a given number of consecutive iterations.

Besides the average overlap residue, additional conditions may be required to accept a legal configuration. Two conditions are particularly relevant in the present work. The first condition is related to a minimum distance between particles, δ_{min}. This aspect may be useful in some applications, namely in the proper finite element meshing in micro-scale FE analyses. A minimum distance between particles mitigates excessively deformed elements or an excessive mesh refinement in between particles. The devised strategy to achieve this is fairly

comprehensible. First, the microstructure's geometrical descriptors characterizing the particle's size are virtually increased by $\delta_{\min}/2$, being the simulation performed with the set of virtually enlarged particles. When the simulation ends, the particles are shrunk back to their original prescribed size, producing a microstructure with the proper volume fraction and respecting the minimum distance specified (see Figure 3.9(a)). Nonetheless, $\delta_{\min} = 0$ is implicitly assumed in the numerical examples presented in this chapter unless otherwise stated.

The second aspect is also associated with the need for spatial discretization meshes. In particular, issues may emerge when particles are left too close to the boundaries of the RVE or when only a very small fraction of the particle remains on either side of the boundary. Both cases may lead to an unnecessary mesh refinement of the particles and their neighborhood. When assuming the microstructure periodicity, this problem can be mitigated by simply shifting the origin of the simulation box. The new location should lead to the largest minimum distance between the boundary elements of the simulation box (faces, edges, and vertices) and the boundaries of the particles (see Figure 3.9(b)).



Figure 3.9: Proposed strategies to improve the quality of the microstructure legal configuration: (a) enforcement of a minimum distance between particles, $\delta_{\min}$; (b) minimization of particles adjacenct to the RVE boundaries.

3.4.4 Interaction forces

In the present contribution, the magnitude of the interaction forces between each pair of particles is equal to their intersection length and their direction is parallel to the intersection direction. Given that the orientation of the particles is left as a prescribable microstructure geometrical descriptor, the forces are applied to the geometric center of the particles so that angular degrees of freedom are not considered.

In an attempt to explore the motivation behind the 'energy rescaling' procedure proposed in Salnikov et al. (2015), i.e., applying larger forces towards the end of the simulation, forces derived from nonlinear springs were investigated. To do so, a nonlinear interaction force governing law

is defined for disks/spheres of the same size as

$$F(d_m) = \begin{cases} 2r\left[1-\left(\dfrac{d_m}{2r}\right)^p\right], & \text{if } d_m \leq 2r\ , \\ 0, & \text{if } d_m > 2r\ , \end{cases} \tag{3.3}$$

where d_m is the distance between the center of the two particles, and r is the radius of both circular/spherical particles. Note that this reduces to a linear spring if $p = 1$, which is actually the case of setting the forces equal to the intersection length.

In Figure 3.10, a schematic plot of the three different idealized springs to determine the interaction forces is presented: a linear spring ($p = 1$), a linear spring approximating the effect of the 'energy rescaling' scheme proposed in Salnikov et al. (2015), and a nonlinear spring ($p > 1$). It is possible to see that the desired behavior (high/low forces in early/late simulation stages) can be best achieved with a nonlinear spring. However, an increasing stiffness of the system may lead to instabilities if an explicit time integration scheme is employed. In this case, if the time integration step is chosen to be very close to the critical time integration step, an approach of this kind doesn't seem to provide added benefits, as discussed later.



Figure 3.10: Interaction forces derived from different types of idealized springs as a function of the distance between two particles' geometrical centers: linear spring ($p = 1$), a linear spring approximating the effect of the 'energy rescaling' scheme proposed in Salnikov et al. (2015) ($p^* = 1$), and a nonlinear spring ($p > 1$). The parameter p is related to the nonlinear interaction force governing law established in Equation (3.3).

The naive approach to compute the required interaction forces is to check all non-repeated pairs of particles in the system, leading to the computation of $n(n-1)/2$ interaction verifications, where n is the total number of particles. Such an approach is inefficient given that the forces between the majority of particle pairs are null, i.e., the particles do not intersect each other. This motivated the development of more efficient approaches, among which the cell list and Verlet list schemes. A coupled version of these two schemes is integrated into the proposed method to avoid the computation of the interaction forces between particles shown a priori not to interact.

The cell list method is based on the partition of the RVE through a regular cell grid. The main idea is that each particle can only interact with particles in its own or adjacent cells (see Figure 3.11). This is achieved by setting the size of the cells equal or slightly larger than the diameter of the largest circumscribed circle/sphere of the particles (Frenkel and Smit (2001), Donev et al. (2005), Krauth (2006)), being assumed that each particle belongs to the cell containing the center of the associated circumscribed shape.

Therefore, this method is most efficient for disks and spheres, providing fewer benefits for ellipses and ellipsoids as the ratio between their principal axes increases (Donev et al., 2005).

Since the allocation of a particle to a cell is an operation that scales with the number of particles and the number of adjacent cells is independent of the system size, the cell list method scales linearly with the number of particles (Frenkel and Smit (2001), Krauth (2006)).



Figure 3.11: Schematic of the cell list method applied in a microstructure containing disks of radius r.

The Verlet list method makes use of several lists, called the Verlet lists, computed from a neighborhood analysis (see Figure 3.12). The neighborhood of each particle is obtained through an offset of its boundary, leading to a similar-shaped enlarged domain (Donev et al., 2005). Then, all the particles whose neighborhoods intersect each other are included in each other's Verlet lists. In the subsequent computation of the interaction forces, only those particles in the list have to be considered.

The neighborhood for each particle remains fixed in space, keeping the same position it had when the Verlet list of its corresponding particle was computed. As the particles move, one or more of the particles may intersect their neighborhoods. This triggers the computation of new Verlet lists and the recentering of the particle neighborhoods relative to the particles (Frenkel and Smit, 2001). In this sense, the definition of new Verlet lists may be total or partial. This means that if any particle intersects its neighborhood, one can recompute Verlet lists and recenter neighborhoods for all particles or only for those that crossed their neighborhoods. In Donev et al. (2005), it is reported that a total update is the most common approach in time-driven molecular dynamics simulations and produces Verlet lists that better reflect the relative position of the particles, despite a possible loss in efficiency. The evaluation and comparison of both strategies are out of the scope of the present work, being adopted the most common total update approach.

Regarding the use of the Verlet list, no CPU time is saved in the first iteration after its computation. However, suppose the maximum displacement of the particles is such that none of them exits its neighborhood. In that case, only the particles in the Verlet list of each particle must be considered in the computation of the interaction forces. This calculation is of the order of the number of particles in the system and, as soon as one of the particles moves outside its neighborhood, the Verlet lists must be updated. If such update is done according to the naive scheme described at the beginning of this section, then it is proportional to the square of the number of particles. Therefore, although this step is not performed at each iteration, it will dominate for a very large number of particles (Frenkel and Smit, 2001). In contrast, if this operation is performed using the previously introduced cell list method, it scales linearly with the number of particles instead.

The difference in efficiency between the Verlet list computed from a cell list and the standard cell list method depends on the specifics of the system and the size of the neighborhood (Frenkel and Smit, 2001). For instance, smaller neighborhoods lead to shorter Verlet lists but also imply more frequent updates. In the proposed method, since the particles's velocity decreases as the simulation progresses (see Section 3.4.6), shorter Verlet lists seem a more beneficial choice. Due to the low velocity of particles in the simulation's late stages, these lists don't need to be often updated. For this reason, in AMINO the described coupling between the Verlet list method and the cell list method is adopted, being the size of the neighborhood empirically set to 1.1 times the geometrical descriptors defining the particle dimensions. The pseudo-code of this coupled scheme is summarized in Box 3.3.



Figure 3.12: Schematic of the Verlet list method with total update applied in a microstructure containing disks of radius r.

At last, a simple procedure is devised in order to properly compute the interaction forces while enforcing the microstructure periodicity. Given a pair of interacting particles, the interaction that needs to be accounted for is the one occurring between the nearest periodic images of both particles. Therefore, the distance vector, $\boldsymbol{d}_m$, considered to compute the interaction forces between two particles, labeled 1 and 2, may be suitably defined as

$$(d_m)_i = x_i^{(1)} - x_i^{(2)} - \left(l_{\mathrm{RVE}}\right)_i \operatorname{nint}\left(\frac{x_i^{(1)} - x_i^{(2)}}{\left(l_{\mathrm{RVE}}\right)_i}\right), \quad i = 1, \ldots, n_{\mathrm{dim}}, \tag{3.4}$$

where $\boldsymbol{x}^{(1)}$ and $\boldsymbol{x}^{(2)}$ are the position vectors of the centers of the particles, $(l_{\mathrm{RVE}})_i$ is the length of the RVE in the i-th dimension and $\operatorname{nint}(x)$ denotes the nearest integer rounding function (see Figure 3.13).

Box 3.3: Computation of interaction forces between particles through the coupling between the Verlet list method and the cell list method. Verlet lists are computed from cell lists.

(i) Check Verlet list update condition

if (condition) then

- Compute new cell list
- Update Verlet lists from new cell list

(ii) For each particle i:

(1) For each particle j in the Verlet list of particle i, such that $j > i$:

- Compute the interaction force between particle i and particle j



Figure 3.13: Distance vector, $\boldsymbol{d}_m$, considered for computing the interaction forces between two particles in a periodic microstructure.



Figure 3.14: Enforcement of microstructure periodicity through a suitable update of the particles' position.

3.4.5 The adaptive time integration scheme

Several time-integration schemes have been employed in molecular dynamics to integrate the equations of motion of the system. Among many others, one can refer, for instance, the Verlet, the leap-frog, and the velocity Verlet integration schemes (Frenkel and Smit, 2001). Due to its simplicity, efficiency, and ability to provide velocities synchronous with the particles' positions, the Verlet integration scheme is adopted and described in what follows.

Verlet integration scheme

The Verlet integration scheme is an explicit time integration scheme for the equations of motion that estimates the new position with an error of order Δt^4, where Δt is the discretized time step. To derive the Verlet integration scheme, a Taylor expansion of the particle's position, $\boldsymbol{x}(t)$, is performed around a given instant t, yielding

$$\boldsymbol{x}(t+\Delta t) = \boldsymbol{x}(t) + \dot{\boldsymbol{x}}(t)\Delta t + \frac{\boldsymbol{f}(t)}{2m}\Delta t^2 + \dddot{\boldsymbol{x}}(t)\frac{\Delta t^3}{3!} + \mathcal{O}(\Delta t^4), \tag{3.5}$$

and

$$\boldsymbol{x}(t-\Delta t) = \boldsymbol{x}(t) - \dot{\boldsymbol{x}}(t)\Delta t + \frac{\boldsymbol{f}(t)}{2m}\Delta t^2 - \dddot{\boldsymbol{x}}(t)\frac{\Delta t^3}{3!} + \mathcal{O}(\Delta t^4), \tag{3.6}$$

where m is the particle's mass, assumed to be equal to the radius of the particle's circumscribed disk/spheres and $\boldsymbol{f}$ the force applied on the particle's center of mass. The addition of the two previous equations renders

$$\boldsymbol{x}(t+\Delta t) = 2\boldsymbol{x}(t) - \boldsymbol{x}(t-\Delta t) + \frac{\boldsymbol{f}(t)}{m}\Delta t^2 + \mathcal{O}(\Delta t^4), \tag{3.7}$$

being the update formula for the Verlet integration scheme given by

$$\boldsymbol{x}(t+\Delta t) = 2\boldsymbol{x}(t) - \boldsymbol{x}(t-\Delta t) + \frac{\boldsymbol{f}(t)}{m}\Delta t^2. \tag{3.8}$$

The velocity is usually computed from a centered finite difference as

$$\dot{\boldsymbol{x}}(t) = \frac{\boldsymbol{x}(t+\Delta t) - \boldsymbol{x}(t-\Delta t)}{2\Delta t}, \tag{3.9}$$

which has an error of order Δt^2. However, since an isokinetic-based thermostat is used in the proposed scheme (see Section 3.4.6), it is desirable to compute the velocity synchronously with the position. Therefore, despite having an error of order Δt, the velocity is instead calculated from a backward finite difference as

$$\dot{\boldsymbol{x}}(t) = \frac{\boldsymbol{x}(t) - \boldsymbol{x}(t-\Delta t)}{\Delta t}. \tag{3.10}$$

Moreover, the velocity of the particles must be rescaled between iterations in order to enforce the isokinetic thermostat. Since the update formula for the Verlet scheme only considers the particle's positions, a virtual position at $t-\Delta t$ must be consistently computed as

$$\boldsymbol{x}(t-\Delta t) = \boldsymbol{x}(t) - \dot{\boldsymbol{x}}(t)\Delta t + \frac{1}{2}\frac{\boldsymbol{f}(t)}{m}\Delta t^2, \tag{3.11}$$

where $\dot{\boldsymbol{x}}(t)$ is the velocity of the particle corresponding to the current temperature.

Finally, in order to enforce the microstructure periodicity (see Figure 3.14), the updated position of the particle is determined as

$$x_i(t+\Delta t) = x_i'(t+\Delta t) - \left(l_{\mathrm{RVE}}\right)_i \operatorname{nlint}\left(\frac{x_i'(t+\Delta t)}{\left(l_{\mathrm{RVE}}\right)_i}\right), \quad i = 1,\ldots,n_{\mathrm{dim}}, \tag{3.12}$$

where $\boldsymbol{x}'$ is the position obtained from Equation (3.8), $(l_{\mathrm{RVE}})_i$ is the length of the RVE in i-th dimension (see Figure 3.8) and $\operatorname{nlint}(x)$ denotes the nearest lower integer rounding function.

Critical time step

It is well-known that explicit algorithms are, in general, conditionally stable. Therefore, having adopted the explicit Verlet integration scheme, it must be ensured that the time integration step does not surpass the critical stability value. If this happens, the solution becomes unstable and the average overlap residue does not decay, preventing the legal configuration from being achieved. Although the time is only interpreted as a pseudo-time in the current framework (i.e., its absolute value does not yield any physical significance), it is, of course, desirable to increase the integration time step to reach the legal configuration as fast as possible.

It can be argued that an implicit time integration algorithm could be alternatively adopted, taking advantage of the associated unconditional stability. However, an implicit algorithm would require the computation of the interaction forces multiple times in each iteration of the numerical procedure employed to solve the system of dynamic equilibrium equations. On the other hand, the adoption of more accurate explicit methods, such as the fourth-order Runge-Kutta, seems unnecessary as the increase in accuracy would not lead to any tangible benefit in the proposed scheme.

In this scenario, a robust way of estimating the critical time integration step must be devised. To this end, it is convenient to make use of results in the field of discrete element methods (DEM), where the Verlet integration scheme goes by the name of explicit finite difference method (O'Sullivan and Bray (2004), Burns and Hanley (2017)). This is done with the understanding that the use of an isokinetic thermostat leads to an approach that is, in practice, slightly different from the standard Verlet scheme, as the velocity of the particles is rescaled between iterations to enforce the prescribed temperature. It also bears saying that DEM and molecular dynamics are very similar schemes, with the main difference being the more diverse shapes of particles and often the consideration of the rotational degrees of freedom in DEM.

The critical time step using the central finite differences is well-known and given by (Belytschko et al., 1985)

$$\Delta t_{\mathrm{crit}} = \frac{2}{\omega_{\mathrm{max}}}, \tag{3.13}$$

where the maximum angular frequency, ω_{max}, can be computed as

$$\omega_{\mathrm{max}} = \sqrt{\lambda_{\mathrm{max}}}. \tag{3.14}$$

Given the equations of dynamic equilibrium of an undamped system,

$$\mathbf{M}\ddot{\mathbf{x}} + \mathbf{K}\mathbf{x} = \mathbf{F}, \tag{3.15}$$

where $\mathbf{x}$ and $\ddot{\mathbf{x}}$ are the position and acceleration of the particles, $\boldsymbol{F}$ is the vector of external forces, $\mathbf{M}$ is the mass matrix and $\mathbf{K}$ is the stiffness matrix, λ_{max} is the maximum eigenvalue of the amplification matrix, $\mathbf{T}$, defined as

$$\mathbf{T} = \mathbf{M}^{-1}\mathbf{K}. \tag{3.16}$$

Consider a system of particles with similar mass m and where the springs characterizing the interaction forces have the same stiffness k. It can be shown that the critical time step in these conditions is always proportional to $\sqrt{m/k}$ (Burns and Hanley, 2017). In O'Sullivan and Bray (2004), an approach inspired in FEM is used to determine the critical time step for a diverse number of particle arrangements. Each particle contact is considered as a strut finite element, with a tangential and a normal stiffness. The mass matrix of each strut element is defined as diagonal, similar to the 'lumped' mass matrices used in FEM. Its non-zero elements are determined by dividing the mass of the particle equally by its different contacts, i.e., the different finite elements connecting to the particle. Considering similar normal and shear stiffness values, O'Sullivan and Bray (2004) derive the critical time steps for several particle arrangements (e.g., two disks, the maximum packing of disks in $\mathbb{R}^2$, cubic arrangement of spheres in $\mathbb{R}^3$) from the eigenvalues of the amplification matrix of the contact elements. These yield the following general result

$$\Delta t_{\text{crit}} = \sqrt{\frac{2}{n_c}} \sqrt{\frac{m}{k}}, \tag{3.17}$$

where n_c is the number of contacts or coordination number of the particles. Given that all spatial arrangements are considered symmetric and periodic, the coordination number is equal for all particles. Note that this result follows from the definition of the mass matrix of the strut element, where the mass of the particle is equally divided by all the contacts.

In the most general case of a system comprising different particle types and sizes, the derivation of such relations is infeasible. Therefore, in an attempt to take advantage of the valuable results in O'Sullivan and Bray (2004), it is here proposed that the critical time step is approximated by

$$\Delta t_{\text{crit}} \approx \alpha \sqrt{\frac{2}{\max(\bar{n}_c, 1)}} \sqrt{\frac{\bar{m}}{k}}, \tag{3.18}$$

where $\bar{n}_c$ is the mean coordination number of the particles in the system, and $\bar{m}$ is the mean of the particles' mass. These averages are employed to account for the diversity in the number of neighbors and sizes of the different particles in the RVE. In turn, $\alpha \leq 1$ can be interpreted as a safety factor multiplier that allows for a more conservative estimate of the critical time step. Nonetheless, it is emphasized that $\alpha = 1$ has been successfuly adopted in all the performed simulations throughout this thesis and no signs of instability arised.

To compute the mean of the particles' mass, $\bar{m}$, the mass of each particle is, without any loss of generality, set equal to the radius of the corresponding circumscribed circumpherence or sphere. Given that it is not sought to simulate a real physical system, such choice is not unique, being this approach adopted due to its computational simplicity and its ability to capture the difference in size between interacting particles.

In the present contribution, where the magnitude of the interaction forces is set equal to the intersection length, $k = 1$ for every pair of particles. Concerning the nonlinear spring for disks/spheres of the same size[2], it follows from the differentiation of Equation (3.3) that

[2] It is remarked that the nonlinear interaction force law (see Equation (3.3)) is solely employed to perform a comparison between linear and nonlinear springs in the case of disks/spheres of the same size.

$$k(d_m) = p\left(\frac{d_m}{2r}\right)^{p-1}. \tag{3.19}$$

If general nonlinear springs ($p > 1$) are considered, the stiffness k can be approximated by replacing r with $\bar{r}$, where $\bar{r}$ is the average circumscribed disks/spheres radius, and d_m with $2\bar{r} - \Delta t\,\bar{v}$, where $\bar{v}$ is the average velocity of all particles.

The proposed estimate for the critical time step deserves some comments. In the first place, from a physical point of view this approximation agrees with the fact that the coordination number dictates the number of non-zero elements in the global stiffness matrix and thus influences its overall stiffness. In the second place, when the system is near a legal configuration, most particles are in contact with one or no adjacent particles, being the critical time step derived for two disks/spheres in O'Sullivan and Bray (2004) recovered. Finally, the mean coordination number, $\bar{n}_c$, can be efficiently determined in the proposed approach through the Verlet lists of all particles. The numerical results presented in Section 3.5 demonstrate the robustness of the proposed approach for several cases, being shown that Equation (3.18) is indeed a reasonable estimate of the critical time step even without considering the safety factor multiplier ($\alpha = 1$).

3.4.6 Multi-temperature isokinetic thermostat

According to the equipartition theorem (Frenkel and Smit, 2001; Krauth, 2006), the temperature of a classical n-particle system is defined as

$$k_b T = \frac{1}{n_{\text{dof}}\, n_p} \sum_{i=1}^{n_p} m_i \| v_i \|^2, \tag{3.20}$$

where k_b is the Boltzmann constant, T is the absolute temperature, m_i and v_i are the mass and velocity of particle i, n_p the number of particles in the system and n_{dof} the number of degrees of freedom per particle. This theorem can also be rewritten as a function of the kinetic energy of the system, E_{kin}, in the following way

$$\frac{1}{2} k_b T = \frac{E_{\text{kin}}}{n_{\text{dof}}\, n_p}, \tag{3.21}$$

where the right-hand side term is the mean kinetic energy per degree of freedom of the system. The present work adopts an isokinetic thermostat based strategy described in what follows.

Isokinetic thermostat

The isokinetic scheme is one of the most straightforward thermostats that can be devised, keeping the average kinetic energy per particle strictly constant. Note that this scheme does not simulate the true constant-temperature ensemble, where the temperature suffers small fluctuations around a constant temperature value. However, in practice, the difference between the isokinetic and canonical schemes is often negligible (Frenkel and Smit, 2001). In the present framework, this aspect is even less relevant, as the main goal is to use the molecular dynamics simulation to find a legal configuration and not to simulate a real physical system.

Let us assume that the isokinetic thermostat is then adjusted to a reference temperature denoted as T_{ref}. To keep the system at this temperature, the velocities of all the particles in the system are rescaled by a factor λ. This factor can be determined from the equipartition theorem (see Equation (3.20)), finding the value that leads the mean kinetic energy per degree of freedom

to be equal to $1/2 k_b T_{\text{ref}}$. By inserting the velocity scale factor, λ, in Equation (3.20), it is possible to write

$$\frac{1}{2} n_p n_{\text{dof}} k_b T_{\text{ref}} = \frac{1}{2} \sum_{i=1}^{n_p} m_i \|\lambda \boldsymbol{v}_i\|^2, \tag{3.22}$$

or, according to the classical definition of kinetic energy,

$$\frac{1}{2} n_p n_{\text{dof}} k_b T_{\text{ref}} = \lambda^2 E_{\text{kin}}. \tag{3.23}$$

From the previous expression, λ can then be determined as

$$\lambda = \sqrt{\frac{n_p n_{\text{dof}} k_b T_{\text{ref}}}{2 E_{\text{kin}}}}. \tag{3.24}$$

The pseudo-code of a general time-driven molecular dynamics microstructure generation method based on an isokinetic thermostat at constant temperature T_{ref} is presented in Box 3.4.

Two critical aspects about the behavior of the isokinetic scheme are highlighted here. These are essentially related to the total overlap residue in the n-particle system and support the enhanced strategy proposed next.

First, a schematic illustration of the evolution of the total overlap residue for different temperatures T_{ref} is presented in Figure 3.15. Irrespective of the temperature, it is possible to see that the total overlap residue converges towards a given time-average overlap residue, $\bar{\Psi}_{T_{\text{ref}}}$, being such a phenomenon easy to understand from a physical point of view. As the particles move around in the RVE, they collide with each other. Given that the potential originating the repulsive interaction forces between the particles is soft[3], they penetrate each other at each collision and contribute momentarily to an increase of the total overlap. Simultaneously, overlapping particles are being driven apart due to the repulsive interaction forces between them, contributing to the decrease of the total overlap. As the system reaches equilibrium, these two counteracting mechanisms tend to equilibrate each other, i.e., the overlap originated from new collisions approximates the overlap removed from loose particles. This leads to the oscillating total overlap depicted in Figure 3.15, with a 'period' that is associated with the mean free path and the average velocity of the particles. In addition, it is also important to remark that the time-average overlap residue decreases with the decrease of the temperature enforced by the isokinetic scheme. This is physically comprehensive, given that the particles' velocity decreases and so does the overlap magnitude between colliding particles.

Second, from the update formula of the Verlet integration scheme it can be deduced that the same overlap takes longer to remove at lower particles' velocities, associated with lower temperatures (see Figure 3.15).

Multi-temperature isokinetic thermostat

By considering a constant number of particles at constant volume and energy, a microcanonical ensemble is a conservative system. Consequently, the particles are constantly colliding with each other and there is a very low probability of finding a legal configuration in a reasonable amount of time.

One possible approach is to introduce a drag force proportional to the velocity of the particles. This approach solves the problem of perpetual motion as the energy is now gradually dissipated. However, no particular strategy is proposed to select the associated viscous damping coefficient. Besides, this coefficient is set at the beginning of the simulation and is kept constant, i.e., it does not change as the system evolves towards a legal configuration.

[3] A soft potential allows for intersections, in opposition to a hard potential that prevents them.

Box 3.4: Time-driven molecular dynamics microstructure generation method based on an isokinetic thermostat at constant temperature T_{ref}.

(i) Generate an initial configuration

(ii) Initialize the increment counter, $k := 0$

(iii) Compute the interaction forces between particles

(iv) Check legal configuration termination criteria
if (condition) then

- Exit with current microstructure configuration

else

- Update the increment counter, $k := k + 1$

(v) Compute the kinetic energy of the system

$$E_{\text{kin}} = \frac{1}{2} \sum_{i=0}^{n_p} m_i \| \boldsymbol{v}_i \|^2$$

(vi) Compute the velocity rescaling factor, λ

$$\lambda = \sqrt{\frac{n_p n_{\text{dof}} k_b T_{\text{ref}}}{2 E_{\text{kin}}}}$$

(vii) Rescale all the velocities by λ, $\boldsymbol{v} := \lambda \boldsymbol{v}$

(viii) Update particles' positions and velocities through the solution of the discretized equations of dynamic equilibrium

(ix) Go to step (iii)

Another approach is the approximation to the canonical ensemble already introduced, using the isokinetic scheme. There are, however, several disadvantages and difficulties associated with this approach. The choice of an excessively high temperature will lead to a situation similar to the one described for the microcanonical ensemble, where the system is not likely to achieve a legal configuration. Additionally, high temperatures entail high particle velocities and lead to a high time-average overlap residue. In contrast, the choice of an excessively low temperature leads to an equilibrium stage at a lower time-average overlap residue. This implies a higher probability of finding a legal configuration as the mean time between collisions decreases. However, low temperatures tend to produce microstructures that may exhibit 'artificial' or spurious features despite having a legal configuration. At very low velocities, and even at low volume fractions, particles tend to remain very close to each other, resulting in partially ordered or clustered configurations as illustrated in Figure 3.16. Perhaps such features may resemble experimental observations in some cases but certainly do not capture the general spatial arrangement found in particle-reinforced materials. Moreover, lower particles' velocities result in a slow evolution of the system towards finding a legal configuration.



Figure 3.15: Evolution of the total overlap in a system of n particles, starting with an illegal configuration ($\Psi = \Psi_{\text{init}}$), when employing an isokinetic thermostat for different reference temperatures.

Therefore, to efficiently use this approach, a suitable temperature must be chosen between these two cases, such that (1) a legal configuration is found as fast as possible and (2) the microstructure does not exhibit undesired spurious features. However, to the author's best knowledge, no strategy has been proposed in the literature to find this optimal temperature.



(a) (b) (c)

Figure 3.16: (a) Randomness in general particle-reinforced material resulting from a multi-temperature isokinetic microstructure generation scheme. Spurious features resulting from using a low temperature in constant-temperature microstructure generation scheme: (b) partially ordered configuration; (c) clustered configuration.

Instead of trying to develop a suitable strategy to determine this optimal temperature, a multi-temperature isokinetic scheme is proposed here. The main idea is to precisely avoid the choice of a single temperature and let the microstructure be subjected to a quenching process until a legal configuration is achieved (see Figure 3.17). In this way, it is possible to take advantage of an adaptive multi-temperature scheme in the sense that a high temperature is enforced to eliminate the initial overlap quickly and is progressively lowered in several stages as the total overlap decreases. Besides avoiding the spurious features illustrated in Figure 3.16, this quenching process allows that a null overlap residual is achieved even when dealing with high particle volume fractions. Moreover, it is essential to remark that the proposed scheme is entirely general in what concerns the particle types included in the microstructure.

Before introducing the details underlying the proposed scheme, it is instructive to characterize its main features based on Figure 3.17. Assuming a general illegal initial configuration with an overlap Ψ_{init}, it is first necessary to choose the initial temperature, T_1. Then the temperature lowering scheme comes into action, being necessary to define when and how the temperature is lowered. Nonetheless, the simulation proceeds in several temperature

stages, each associated with a given number of iterations and equilibration time, t^{eq}, until the prescribed average overlap residual threshold is achieved. Each of these points is discussed in what follows.



Figure 3.17: Evolution of the total overlap in a system of n-particles, starting with an illegal configuration ($\Psi = \Psi_{\text{init}}$), when employing the proposed multi-temperature isokinetic scheme.

Initial temperature. Despite the adaptive nature of the proposed scheme, note that the temperature is only allowed to decrease throughout the simulation. Hence, although not critical by any means, the appropriate choice of the initial temperature shall not be disregarded. The main goal of the first temperature stage is to remove the relatively large initial overlap as fast as possible. Recall that the initial overlap results from the generation of the initial configuration through a Poisson point process, ensuring that the particles' centers are randomly distributed. Therefore, the initial temperature should be sufficiently high such that a significant part of the initial overlap is quickly removed and that the potential clusters existent in the initial configuration are dissolved. However, the choice of an excessively high initial temperature leads to equally excessive velocities, with particles going through each other in a single iteration and even causing the total overlap to increase. In the worst-case scenario, this temperature can even prevent that the first stage equilibrium is achieved, similar to what happens in a conservative system.

With this in mind, a simple procedure is devised to estimate a suitable initial temperature. Let's assume a given system of n equal particles with radius r and an initial velocity v. To avoid that two particles in a perfectly alligned collision penetrate more than halfway through each other in one iteration, it must be ensured that the particles' velocity satisfies $\|\boldsymbol{v}\|\Delta t < 0.5r$. Hence, to remove the initial overlap in a reasonable number of iterations, it is possible to set the initial particles' velocity as $v = 0.1r/\Delta t$, i.e., in one iteration, each particle is displaced one tenth of its radius. From this initial velocity estimate, it is then possible to compute the associated initial temperature through the equipartition theorem (see Equation (3.20)).

Temperature lowering scheme. Concerning the temperature lowering scheme, the temperature may be decreased between each stage by dividing the current temperature by a factor greater than 1. The higher this factor is, the higher is the cooling of the system and fewer temperature stages are performed until a legal configuration is found. An excessive cooling rate of the system tends to an isokinetic scheme with a low reference temperature, leading to the disadvantages already discussed. From numerical experience, the author recommends that such a factor is set to 10.

Equilibration time. Having defined how the temperature is updated, it remains to establish when and under what conditions should a stage transition happen. Each temperature stage is essentially divided into two different phases. A first phase, where it is attempted to remove the overlap that remains from the previous stage, and a second phase, where the time-average overlap residue corresponding to the current temperature is achieved. It is important to emphasize that the previous stage is always associated with a higher temperature, meaning that the remaining overlaps result from particles with higher velocities and tend to have a higher magnitude.

The key aspect of the proposed scheme is to explore higher temperatures as much as possible, given that these lead to a faster removal of particles intersections in an average sense. At the same time, it must be ensured that the particles' velocities are compatible with the decrease of the total overlap. Hence, to take full advantage of this approach, it must be ensured that the system reaches the equilibrium at each stage before lowering the temperature. On the one hand, a premature lowering of temperature essentially corresponds to discarding an opportunity to remove part of the existent overlap in a faster way. On the other hand, if the equilibrium has already been reached in the current stage, the additional time spent at that temperature does not lead to a decrease in the total overlap. The problem is thus to find the suitable equilibration time at each temperature stage, i.e., to identify when the equilibrium has been reached.

To do so, it is instructive to characterize the equilibrium plateau from a physical point of view, where the total overlap oscillates around a given value when averaged with respect to time. This means that, on average, the increase of overlap resulting from new collisions, $\Psi_{\Delta+}$, is similar to the decrease of overlap resulting from particles being driven apart, $\Psi_{\Delta-}$, i.e., when the equilibrium is reached $\Psi_{\Delta+}/\Psi_{\Delta-} \approx 1$. Both of these quantities can be easily computed by looking at each pair of intersecting particles and comparing the current overlap to the overlap in the previous iteration. If it has increased, it is added to the global overlap increase measure, $\Psi_{\Delta+}$; otherwise, is added to $\Psi_{\Delta-}$. The proposed criterion to trigger the decrease of temperature is then based on the number of times that the ratio $\Psi_{\Delta+}/\Psi_{\Delta-}$ crosses the value 1, i.e., the number of times the algebraic sign of $\Psi_{\Delta+}/\Psi_{\Delta-} - 1$ changes. From numerical experience, the author found that two times is a solid choice, although more conservative (greater) values would be perfectly acceptable.

The pseudo-code of the proposed adaptive multi-temperature isokinetic thermostat is summarized in Box 3.5.

Box 3.5: Time-driven molecular dynamics microstructure generation method based on a multi-temperature isokinetic thermostat.

(i) Generate an initial configuration

(ii) Initialize the increment counter, $k := 0$

(iii) Initialize the reference temperature, $T_{\text{ref}} = T_{\text{init}}$

(iv) Compute the interaction forces between particles

(v) Check if the system has reached equilibrium at temperature T_{ref}
if (sign$(\Psi_{\Delta+}/\Psi_{\Delta-} - 1)$ changed twice) then

- Lower the temperature, $T_{\text{ref}} := 0.1\,T_{\text{ref}}$

(vi) Compute the kinetic energy of the system

$$E_{\text{kin}} = \frac{1}{2}\sum_{i=0}^{n_p} m_i \|\boldsymbol{v}_i\|^2$$

(vii) Compute the velocity rescaling factor, λ, at current temperature

$$\lambda = \sqrt{\frac{n_p\, n_{\text{dof}}\, k_b\, T_{\text{ref}}}{2E_{\text{kin}}}}$$

and rescale all particles' velocities, $\boldsymbol{v} := \lambda \boldsymbol{v}$

(viii) Check legal configuration termination criteria
if (condition) then

- Exit with current microstructure configuration

else

- Update the increment counter, $k := k + 1$

(ix) Update particles' positions and velocities through the solution of the discretized equations of dynamic equilibrium

(x) Go to step (iv)

3.4.7 Approximation to the intersection length under a multi-temperature thermostat

In Section 3.3 is proposed a simple and efficient approximation to the intersection length between two particles. However, being robustness a critical aspect of AMINO, the limitations of this approximation are here discussed in the context of the multi-temperature isokinetic scheme just described.

In the first place, it is pointed out that the proposed approximation to the intersection length will always be greater than its exact value for any convex shapes (see Figure 3.7), except disks and spheres. As a consequence, the magnitude of the interaction forces between particles, assumed proportional to the intersection length, is in general overestimated. Although in a broad range of microstructure descriptors this overestimation does not raise any issues, the removal of the overlap residue in the late stages of the simulation may be hindered when dealing with highly elongated particles at medium-to-high volume fractions. Given that the late stages of the multi-temperature isokinetic scheme deal with the lowest overlap residue, the interaction forces overestimate may disrupt the convergence and lead to similar behavior as numerical instability. Medium-to-high volume fractions are naturally more susceptible to such issues as the movement of the particles is more constrained.

To deal with this issue, it could be attempted to devise a criterion based on the provided microstructure descriptors. For instance, if the ratio between the major and minor axes of any particle material phase exceeded a given threshold above a given volume fraction, then the exact intersection length values would be computed through optimization. However, in the author's point of view, such a strategy is not sufficiently robust and the most suitable values for these thresholds are unknown. In addition, even if the described issue emerges in the late simulation stages, the higher efficiency of the proposed approximation can be explored until that moment. Therefore, the idea is to assume the approximation as a first approach and, if the described issue occurs, then the exact intersection length is computed through optimization until the legal configuration is found.

A robust criterion based on the kinetic energy of the system is thus proposed to detect this issue and perform the required switch when needed. To illustrate the behavior of this criterion, a microstructure containing ellipsoids with the same orientation at a volume fraction of 40% is considered, being the mean average ratio between the principal axes equal to 2.5 (high elongation). In Figure 3.18, the kinetic energy of the system before and after the particles' velocity rescaling in two cases is compared: (1) intersection length computed for the proposed approximation and (2) exact intersection length computed through a minimization procedure. It can be observed from Figure 3.18 that, after some iterations, the overestimation of the interaction forces due to the proposed approximation injects excessive energy into the system. Therefore, the switch should be made when the kinetic energy of the system significantly diverges from the reference kinetic energy associated with the current temperature. It is thus proposed that if the relative difference of $0.5(T_{n+1}/T_n)$ between the two kinetic energies is detected, then the temperature lowering is postponed and the particles exact intersection length is considered until the end of the simulation.

This criterion is successfully adopted in all the numerical applications presented in the remainder of this chapter, although this issue has only been detected in a few examples.

3.5 Numerical application

This section presents several numerical results aiming to demonstrate the performance of AMINO. First, a given set of results is presented to validate the developed formulation and to prove the efficiency and robustness of the method. Second, a set of complex microstructures is



Figure 3.18: Kinetic energy before velocity rescaling (EK) and after velocity rescaling (EK$_{ref}$) for a system of ellipsoids oriented along the same direction, with a mean ratio between principal axes equal to 2.5 (high elongation) and volume fraction of 40%: (a) intersection length computed using the proposed approximation; (b) exact intersection length computed through minimization algorithm.

generated to show the flexibility and compliance of the method with a wide spectrum of microstructure descriptors. Finally, a last set of examples provides quantitative analyses and comparison between experimental micrographs and computational microstructures.

The implementation of AMINO is performed in Python (Python 3 release) and all the numerical results presented in this section are obtained in a machine with the following computational resources: Intel® Core™ i7-10700K CPU @ 3.80GHz × 16, 32Gb of RAM. Apart from imported third-party libraries, the implementation of AMINO is not parallelized nor optimized, and only one core of the processor is used.

3.5.1 Formulation assessment

The set of results presented next aims to validate two main aspects of the proposed formulation: the adaptive time integration step and the multi-temperature isokinetic scheme. In theory, both of these strategies are completely general in what concerns the type of particles being considered. Thus, without any loss of generality and for the sake of brevity, the most important features of these strategies are discussed for microstructures containing disks (2D) and spheres (3D), covering a wide range of number of particles and volume fractions. More complex microstructures are considered later in Section 3.5.2.

Assessment: Adaptive time integration step

Microstructures containing disks and spheres are considered here to evaluate the adaptive time integration step approach for both 2D and 3D cases. Concerning disks, volume fractions span from 40% up to 80% and the number of particles from 10 to 500. Regarding spheres, volume

fractions from 30% to 60% are also examined between 10 and 500 particles. Given the random nature of each microstructure realization, several samples are averaged whenever the computational generation time is evaluated. For each set of microstructure descriptors, two approaches are thus compared: the approach where a constant time integration step is adopted and the proposed adaptive approach. In addition, results for both linear ($p = 1$) and nonlinear interaction forces ($p = 2$) are shown (see Equation (3.3)).

In Figures 3.19 and 3.20 show the average CPU time (over 10 realizations of each microstructure) required to produce a legal configuration with zero overlap ($\Psi_{\text{lim}} = 0$) for disks and spheres, respectively. First and foremost, the robustness of the adaptive scheme is evidenced, being able to achieve a legal configuration under practically the whole spectrum of microstructure descriptors. In contrast, adopting a constant time integration step shows significant limitations as the number of particles and/or the volume fraction increases and the critical time step is expected to decrease. This aspect is better emphasized in Figure 3.22, where the particular case of a microstructure with disks at a volume fraction of 50% is analyzed for a different number of particles. While for just 10 particles, all the constant time integration steps achieve a legal configuration, as the number of particles increases, the simulations become unstable by descending order of the time integration step. In the second place, these results also highlight the efficiency of the proposed numerical approximation as the computational time closely follows the highest time integration step possible below the critical value. It should also be pointed out that the adaptive scheme did not become unstable in the particular cases of 10 particles at 80% (disks) and 60% (spheres). Instead it could not converge to a zero overlap under a maximum number of iterations of 5000. As shown in Figure 3.21, the combination of such high volume fractions and the low number of particles shrinks significantly the space of admissible configurations and leads to extensive 'particle jamming' in the search for a legal configuration.

Finally, it is also apparent that the proposed approach produces satisfactory and similar results for both linear ($p = 1$) and nonlinear ($p = 2$) interaction forces. The comparison between both types of interaction forces under the proposed adaptive time integration scheme is better illustrated in Figure 3.22. These results suggest that the simple choice of linear interaction forces ($p = 1$) between particles is perfectly acceptable as long as the time integration step is adaptively selected.



Figure 3.19: Average CPU time (over 10 realizations of each microstructure) in the generation of a legal configuration ($\Psi_{\text{lim}} = 0$) of: (a) disks with linear interaction forces ($p = 1$); (b) disks with nonlinear interaction forces ($p = 2$). Comparison between the proposed adaptive time integration step and constant integration steps for a different number of particles, n, and volume fractions. Missing data points correspond to unstable simulations or simulations that could not achieve a legal configuration in a maximum of 5000 iterations (particle jamming).



Figure 3.20: Average CPU time (over 10 realizations of each microstructure) in the generation of a legal configuration ($\Psi_{\text{lim}} = 0$) of: (a) spheres with linear interaction forces ($p = 1$); (b) spheres with nonlinear interaction forces ($p = 2$). Comparison between the proposed adaptive time integration step and constant integration steps for a different number of particles, n, and volume fractions. Missing data points correspond to unstable simulations or simulations that could not achieve a legal configuration in a maximum of 5000 iterations (particle jamming).



Figure 3.21: Microstructure illegal configuration obtained with the adaptive time integration step after 5000 iterations due to particle jamming: (a) disks (10 particles at 80%); (b) spheres (10 particles at 60%).



Figure 3.22: Evolution of the total overlap in the generation of a microstructure containing disks at a volume fraction of 50% with: (a) 10 particles; (b) 50 particles; (c) 100 particles; (d) 500 particles. Comparison between the proposed adaptive time integration step and constant integration steps. All the compared microstructures have the same initial configuration.



Figure 3.23: Average CPU time (over 10 realizations of each microstructure) in the generation of a legal configuration ($\Psi_{\text{lim}} = 0$) of: (a) disks; (b) spheres. Comparison between linear ($p = 1$) and nonlinear ($p = 2$) interaction forces under the proposed adaptive time integration step. Missing data points correspond to simulations that could not achieve a legal configuration in a maximum of 5000 iterations (particle jamming).

Assessment: Multi-temperature isokinetic scheme

The evaluation of the proposed multi-temperature isokinetic scheme begins with the proposed criterion to lower the temperature of the system. As described in Section 3.4.6, this is based on the number of times that $\text{sign}(\Delta_+/\Delta_- - 1)$ changes, where Δ_+ and Δ_- are the increase and decrease in the total overlap of the system in each iteration.

The effectiveness of this criterion can be assessed concerning two aspects: first, if it can actually detect the equilibrium of the system at a given temperature, and second, how many iterations does it take to detect if that equilibrium has been reached. To do so, an isokinetic reference simulation can be performed at a temperature where a legal configuration cannot be achieved, i.e., the system reaches the equilibrium and oscillates around a given time average overlap. Then, considering the same initial configuration, multi-temperature simulations are performed such that the first temperature stage corresponds to the temperature of the reference isokinetic simulation. Simulations will thus coincide up to when a temperature decrease is triggered due to the proposed criterion.

Microstructures containing 50 disks and 50 spheres at a volume fraction of 50% are considered here to evaluate the criterion for both 2D and 3D cases. The results are presented in Figures 3.24 and 3.25, respectively, where two different isokinetic reference temperatures are examined as well as the criterion's number of sign changes. In the first place, it is possible to see that the proposed criterion can detect the equilibrium plateau in all cases, being thus suitable to trigger the temperature lowering in the multi-temperature isokinetic scheme. In the second place, it can also be verified that two changes in the sign are a proper choice of this parameter, minimizing the number of iterations at which the system is held in the equilibrium stage without leading to a premature lower temperature.



Figure 3.24: Evolution of the total overlap in a system of 50 disks at a volume fraction of 50%, with the reference temperature of the isokinetic scheme and the first temperature stage of the multi-temperature isokinetic scheme equal to (a) $Tk_b = 2.5\times10^{9}$; (b) $Tk_b = 2.5\times10^{10}$. IK denotes the isokinetic simulation, MT the multi-temperature simulations and n the number of sign changes in the criterion proposed to lower the temperature as equilibrium is reached.



Figure 3.25: Evolution of the total overlap in a system of 50 spheres at a volume fraction of 50%, with the reference temperature of the isokinetic scheme and the first temperature stage of the multi-temperature isokinetic scheme equal to (a) $Tk_b = 2.5 \times 10^9$; (b) $Tk_b = 2.5 \times 10^{10}$. IK denotes the isokinetic simulation, MT the multi-temperature simulations and n the number of sign changes in the criterion proposed to lower the temperature as equilibrium is reached.

With the temperature lowering criterion validated, the advantages provided by the proposed multi-temperature isokinetic scheme are now discussed through several comparisons with the standard isokinetic scheme. As in the previous section, evaluation in both 2D and 3D cases is made by considering microstructures containing disks, with volume fractions ranging between 10% and 80%, and spheres, with volume fractions ranging between 10% and 60%. In both cases, the number of particles ranges between 10 and 500. In addition, three suitable temperatures are considered for the isokinetic thermostat, $Tk_b = 10^3$, $Tk_b = 10^4$ and $Tk_b = 10^5$. At last, every time that the criterion is triggered in the multi-temperature thermostat, the temperature is lowered by a factor of 10.

Figure 3.26 shows the average CPU time (over 10 realizations of each microstructure) required to produce a legal configuration with overlap equal to zero ($\Psi_{\text{lim}} = 0$). In the first place, the robustness of the proposed multi-temperature approach is demonstrated, providing microstructures legal configurations under practically the complete set of microstructure descriptors. Exceptions include the highest volume fractions when considering solely 10 disks or spheres, where a legal configuration could not be found under a maximum number of 5000 iterations due to the particle jamming discussed in the previous section. In contrast, despite attempting to choose the most suitable temperatures based on some numerical experience, the isokinetic approach shows significant limitations as the number of particles and/or the volume fraction increases. This limitation is better comprehended in Figure 3.27, where the evolution of the total overlap in the particular cases of 500 disks at 70% and 500 spheres at 50% is illustrated.

In the second place, the suitable comparison between the efficiency of both approaches requires two distinct analyses. First, it is possible to verify that above a certain volume fraction threshold, around 60% in 2D and 35% in 3D, the multi-temperature scheme is faster than the

isokinetic scheme when the latter converges. As shown in Figure 3.27, the isokinetic scheme spends a considerable amount of iterations on finding a legal configuration after the system equilibrium plateau is reached. This emphasizes the low probability of finding a legal configuration at an excessively high temperature. On the contrary, the multi-temperature scheme explores the high-temperature range as much as possible and progressively lowers the temperature until a legal configuration is finally found. Second, for volume fractions lower than the threshold as mentioned earlier, where the probability of finding a legal configuration increases, the isokinetic scheme for the chosen temperatures is faster than the multi-temperature approach. As illustrated in Figure 3.28, if the temperature in the isokinetic scheme is properly calibrated, the total overlap evolution immediately exhibits a steep descent. In contrast, the multi-temperature scheme spends some iterations at the different temperature stages until the corresponding equilibrium states are achieved. To speedup the proposed scheme, it would be possible to increase the factor by which the temperature is lowered between different stages. With a sufficiently high factor, the isokinetic scheme behavior would be naturally recovered. However, the price to pay for such a premature low temperature is illustrated in Figure 3.29. Microstructures tend to exhibit partially ordered or clustered 'artificial' configurations that may spoil the sought close resemblance with experimental observations. In this regard, the multi-temperature approach leads to the dissolution of such spurious arrangements and often produces microstructures with better quality.



Figure 3.26: Average CPU time (over 10 realizations of each microstructure) in the generation of a legal configuration with zero overlap ($\Psi_{\text{lim}} = 0$) of: (a) disks; (b) spheres. Comparison between the proposed multi-temperature isokinetic scheme (MT) and the standard isokinetic scheme (IK) for a different number of particles, n, and volume fractions. Missing data points correspond to simulations that could not achieve a legal configuration in a maximum of 5000 iterations (particle jamming).



Figure 3.27: Evolution of the total overlap in a system of: (a) 500 disks at 70%; (b) 500 spheres at 50%. Comparison between the proposed multi-temperature scheme (MT) and the isokinetic scheme (IK). All the compared microstructures have the same initial configuration.

Assessment: Overall efficiency

To conclude this section, the efficiency of AMINO is here presented concisely, accounting for the proposed strategies validated in the previous sections. Focus is placed on the generation of microstructures containing disks and spheres, with volume fractions ranging between 5% and 80% and between 5% and 60%, respectively (see Figure 3.31). In both cases, the number of particles varies from 10 to 500.

Figure 3.30 shows the average CPU time (over 20 realizations of each microstructure) required to produce a legal configuration with zero overlap ($\Psi_{\text{lim}} = 0$). Concerning the number of particles, it can be seen that the increase in CPU time is approximately linear. In contrast, the CPU time evolution with the rise of the volume fraction is roughly exponential. In general, AMINO can successfully generate microstructures in the order of seconds, as summarized in Tables 3.1 and 3.2.

3.5.2 Miscellaneous microstructures

In this section, the performance of AMINO is demonstrated in the generation of several complex and miscellaneous microstructures. These include multiple particle material phases and all the different types of particles introduced in Section 3.3. Also, compliance with multiple microstructure descriptors is emphasized. Without any loss of generality, all the RVEs presented next are square (2D) or cubic (3D) with unitary side length.



Figure 3.28: Evolution of the total overlap in a system of: (a) 500 disks at 40%; (b) 500 spheres at 20%. Comparison between the proposed multi-temperature scheme (MT) and the isokinetic scheme (IK). All the compared microstructures have the same initial configuration.



Figure 3.29: Final configurations for microstructures containing 500 disks at a volume fraction of: (a),(e) 30%; (b),(f) 40%; (c),(g) 50%; (d),(h) 60%. Microstructures in the upper row ((a)-(d)) are generated using an isokinetic scheme with a target temperature of $Tk_b = 10^3$, while microstructures in the lower row ((e)-(h)) are generated with the proposed multi-temperature scheme.



Figure 3.30: Average CPU time (over 20 realizations of each microstructure) in the generation of a legal configuration with zero overlap ($\Psi_{\text{lim}} = 0$) of: (a) disks; (b) spheres. Microstructures are generated through AMINO, accounting for both adaptive time integration step and multi-temperature isokinetic scheme. Missing data points correspond to simulations that could not achieve a legal configuration in a maximum of 5000 iterations (particle jamming).



Figure 3.31: Samples of microstructures generated through AMINO and containing 100 disks (upper row) and 100 spheres (lower row) at a volume fraction of: (a),(e) 30%; (b),(f) 40%; (c),(g) 50%; (d),(h) 60%.

Table 3.1: Average CPU time (over 20 realizations of each microstructure) in the generation of a legal configuration with zero overlap ($\Psi_{\text{lim}} = 0$) of disks. Microstructures are generated with the AMINO, accounting for both adaptive time integration step and multi-temperature isokinetic scheme. Missing data points correspond to simulations that could not achieve a legal configuration in a maximum of 5000 iterations (particle jamming).

Number of Particles	Time (s)	Volume fraction (%)			
		20	40	60	80
10	Mean	1.07×10^{-2}	3.34×10^{-2}	5.95×10^{-2}	-
	Std. Dev.	7.84×10^{-3}	7.04×10^{-3}	5.36×10^{-3}	-
50	Mean	1.20×10^{-1}	2.15×10^{-1}	3.41×10^{-1}	$1.80 \times 10^{+0}$
	Std. Dev.	2.84×10^{-2}	2.88×10^{-2}	4.81×10^{-2}	1.10×10^{0}
100	Mean	2.61×10^{-1}	4.46×10^{-1}	6.92×10^{-1}	$2.19 \times 10^{+0}$
	Std. Dev.	4.49×10^{-2}	4.94×10^{-2}	7.65×10^{-2}	4.52×10^{-1}
500	Mean	$1.58 \times 10^{+0}$	$2.45 \times 10^{+0}$	4.19×10^{0}	$1.08 \times 10^{+1}$
	Std. Dev.	2.38×10^{-1}	2.13×10^{-1}	4.32×10^{-1}	6.25×10^{-1}

Table 3.2: Average CPU time (over 20 realizations of each microstructure) in the generation of a legal configuration with zero overlap ($\Psi_{\text{lim}} = 0$) of spheres. Microstructures are generated with AMINO, accounting for both adaptive time integration step and multi-temperature isokinetic scheme. Missing data points correspond to simulations that could not achieve a legal configuration in a maximum of 5000 iterations (particle jamming).

Number of Particles	Time (s)	Volume fraction (%)			
		20	40	50	60
10	Mean	8.86×10^{-2}	1.52×10^{-1}	2.09×10^{-1}	-
	Std. Dev.	1.58×10^{-2}	2.49×10^{-2}	2.52×10^{-2}	-
50	Mean	6.25×10^{-1}	$1.17 \times 10^{+0}$	$2.38 \times 10^{+0}$	$6.28 \times 10^{+0}$
	Std. Dev.	1.01×10^{-1}	1.93×10^{-1}	3.02×10^{-1}	$2.37 \times 10^{+0}$
100	Mean	$1.34 \times 10^{+0}$	$2.77 \times 10^{+0}$	$4.56 \times 10^{+0}$	$9.63 \times 10^{+0}$
	Std. Dev.	1.94×10^{-1}	4.19×10^{-1}	6.47×10^{-1}	$1.81 \times 10^{+0}$
500	Mean	$9.71 \times 10^{+0}$	$1.86 \times 10^{+1}$	$2.32 \times 10^{+1}$	$4.94 \times 10^{+1}$
	Std. Dev.	7.28×10^{-1}	$2.10 \times 10^{+0}$	$2.52 \times 10^{+0}$	$3.37 \times 10^{+0}$

2D microstructures

The first two-dimensional example (2A) is a microstructure containing two particle material phases (see Figure 3.32(a)). Phase 1 has a volume fraction of 20% and contains disks of different radii. In particular, the radius follows a discrete distribution prescribed as: $P(r = 0.05) = 0.5$, $P(r = 0.025) = 0.25$ and $P(r = 0.0125) = 0.25$. Phase 2 has a volume fraction of 30% and contains ellipses of different dimensions. The ellipses' major axis follows a normal distribution, $N(0.15, 0.02^2)$, and the ratio between the major and minor axes also follows a normal distribution, $N(1.5, 0.15^2)$. The angle that the major axis of each ellipse forms with the positive x semi-axis follows a uniform distribution, $U(0, 2\pi)$ rad.

The second two-dimensional example (2B) is a microstructure containing three-particle material phases (see Figure 3.32(b)). Phase 1 has a volume fraction of 15% and contains disks with a radius equal to 0.05. Phase 2 has a volume fraction of 10% and contains disks of different radii. In particular, the radius follows a normal distribution, $N(0.03, 0.005^2)$. Phase 3 has a volume fraction of 35% and includes ellipses of different dimensions. The ellipses' major axis follows a normal distribution, $N(0.15, 0.02^2)$, and the ratio between the major and minor axes follows a uniform distribution between 1.5 and 2.5. The angle that the major axis of each ellipse forms with the positive x semi-axis follows a normal distribution, $N(0.0, 0.1^2)$rad.

The third two-dimensional example (2C) is a microstructure containing two-particle material phases (see Figure 3.32(c)). Phase 1 has a volume fraction of 10% and contains disks of different radii. In particular, the radius follows a discrete distribution prescribed as: $P(r = 0.025) = 0.5$ and $P(r = 0.0125) = 0.5$. Phase 2 has a volume fraction of 30% and contains ellipses of different dimensions. The ellipses' major axis follows a normal distribution, $N(0.15, 0.02^2)$, and the ratio between the major and minor axes follows a normal distribution, $N(4.0, 0.15^2)$. The angle that the major axis of each ellipse forms with the positive x semi-axis is fixed and equal to $\pi/2$.

For each example, 10 microstructures are generated and the results regarding computational generation time, number of particles, and total volume fraction can be found in Table 3.3.

Table 3.3: Average CPU time, the average number of particles and associated standard deviations (over 10 realizations of each microstructure) in the generation of microstructures with several particle phases 2A, 2B and 2C (see Figure 3.32).

Example	CPU Time (s)		Number of particles		Total volume fraction of particles (%)
	Mean	Std. Dev.	Mean	Std. Dev.	
2A	5.07	1.22	71	6	50
2B	13.67	1.87	94	3	60
2C	26.49	9.64	147	7	40

3D microstructures

The first three-dimensional example (3A) is a microstructure containing two-particle material phases (see Figure 3.33(a)). Phase 1 has a volume fraction of 10% and contains spheres of different radii. In particular, the radius follows a discrete distribution prescribed as: $P(r = 0.1) = 0.5$, $P(r = 0.05) = 0.25$ and $P(r = 0.025) = 0.25$. Phase 2 has a volume fraction of 20% and contains ellipsoids of different dimensions. The ellipsoids' major axis follows a normal distribution, $N(0.3, 0.04^2)$, and the ratio between the major and minor axes also follows a normal distribution, $N(1.5, 0.15^2)$. The angle that the major axis of each ellipsoid forms with the positive x semi-axis follows a uniform distribution, $U(0, 2\pi)$ rad.



(a) (b) (c)

Figure 3.32: Examples of 2D microstructures generated through AMINO: (a) 2A; (b) 2B; (c) 2C. Different colors correspond to different material phases.

The second three-dimensional example (3B) is a microstructure containing four-particle material phases (see Figure 3.33(b)). Phase 1 has a volume fraction of 5% and includes cylinders with a fixed size and a random orientation. The radius is equal to 0.0625 and the length is equal to 0.25. Phase 2 has a volume fraction of 5% and contains cylinders. However, the radius follows a normal distribution, $N(0.00625, 0.1^2)$, and both length and orientation are fixed. The length is equal to 0.125 and the orientation is such that both the azimuthal and the polar angle defining the symmetry axis is equal to $\pi/10$. Phase 3 has a volume fraction of 3% and contains spheres whose radius is uniformly distributed, $U(0.1, 0.15)$. Phase 4 has a volume fraction of 5% and contains ellipsoids. The major axis follows a normal distribution, $N(0.1875, 0.025^2)$. The ratio between the major axis and the other two principal axes is normally distributed as $N(1.5, 0.15^2)$. The orientation of the particles is entirely random.

The third three-dimensional example (3C) is a microstructure containing two-particle material phases (see Figure 3.33(c)). Phase 1 has a volume fraction of 10% and includes cylinders of the same size. The radius is equal to 0.0425, the length equal to 0.25, and the orientation is random. Phase 2 has a volume fraction of 2.5% containing spheres whose radius follows a uniform distribution, $U(0.15, 0.1)$.

For each example, 10 microstructures are generated and the results regarding computational generation time, the number of particles, and total volume fraction can be found in Table 3.4.



(a) (b) (c)

Figure 3.33: Examples of 3D microstructures generated through AMINO: (a) 3A; (b) 3B; (c) 3C. Different colors correspond to different material phases.

Table 3.4: Average CPU time, the average number of particles and associated standard deviations (over 10 realizations of each microstructure) in the generation of microstructures with several particle phases 3A, 3B and 3C (see Figure 3.33).

Example	CPU Time (s)		Number of particles		Total volume fraction of particles (%)
	Mean	Std. Dev.	Mean	Std. Dev.	
3A	18.15	4.00	77	5	30
3B	20.10	7.96	65	1	18
3C	40.14	8.31	153	5	12.5

3.5.3 Statistical analysis

In this section, the quality of the microstructures generated through AMINO is evaluated by comparing real and computational generated microstructures through suitable statistical descriptors. Three well-known statistical functions are considered and briefly introduced in the following sections, namely the n-point probability function, the nearest neighbor function, and the Ripley's K function.

n-point correlation functions

The brief definition of the n-point probability function presented here is based on Torquato (2013). The term random heterogeneous material implies that any sample of the medium is a realization of a specific random process or field and an ensemble is a collection of all such possible realizations. Let each point ω denote a realization of the random medium that occupies some subset $\mathscr{V}$ of the d-dimensional Euclidean space, i.e. $\mathscr{V} \subseteq \mathbb{R}^d$. Each realization ω of the two-phase random medium occupies the region of space $\mathscr{V} \subseteq \mathbb{R}^d$ of volume V that is partitioned into two disjoint random sets or phases: phase 1, a region $\mathscr{V}_1(\omega)$ of volume fraction ϕ_1, and phase 2, a region $\mathscr{V}_2(\omega)$ of volume fraction ϕ_2. For a given realization ω, the indicator function $I^{(i)}(\boldsymbol{x};\omega)$ for phase i, $i = 1,2$ characterizes the random process and it is defined for a given point $\boldsymbol{x} \in \mathscr{V}$ by

$$I^{(i)}(\boldsymbol{x};\omega) = \begin{cases} 1, & \text{if } \boldsymbol{x} \in \mathscr{V}_i(\omega), \\ 0, & \text{otherwise.} \end{cases} \tag{3.25}$$

For a given point $\boldsymbol{x}$, the indicator function $I^{(i)}(\boldsymbol{x})$ has only two possible values, i.e., for some realizations ω, it will be 0 and for others, 1. Thus, the random variable $I^{(i)}(\boldsymbol{x})$ does not possess a probability density but is instead described by the probability that it takes the value of 1,

$$P\left\{I^{(i)}(\boldsymbol{x}) = 1\right\}, \tag{3.26}$$

and

$$P\left\{I^{(i)}(\boldsymbol{x}) = 0\right\} = 1 - P\left\{I^{(i)}(\boldsymbol{x}) = 1\right\}. \tag{3.27}$$

The n-point probability function for phase i, denoted as $S_n^{(i)}$, is defined as

$$S_n^{(i)}(\boldsymbol{x}_1, \boldsymbol{x}_2, \ldots, \boldsymbol{x}_n) \equiv \left\langle I^{(i)}(\boldsymbol{x}_1) I^{(i)}(\boldsymbol{x}_2) \cdots I^{(i)}(\boldsymbol{x}_n) \right\rangle, \tag{3.28}$$

and is equal to the probability that n points at positions $\boldsymbol{x}_1, \boldsymbol{x}_2, \ldots, \boldsymbol{x}_n$ are found in phase i, where $\langle(\bullet)\rangle$ denotes an ensemble average, i.e., an average over all realizations ω of the ensemble. This function can also be referred to as an n-point correlation function.

When the n-point probability function $S_n^{(i)}$ depends on the absolute positions $\boldsymbol{x}_1, \boldsymbol{x}_2, \ldots, \boldsymbol{x}_n$, the medium is said to be statistically inhomogeneous. Assuming that the medium is statistically homogeneous and isotropic, the n-point correlation function depends only on the relative distances between points. Adopting the notation $x_{jk} = |\boldsymbol{x}_{jk}|$ and $\boldsymbol{x}_{jk} = \boldsymbol{x}_k - \boldsymbol{x}_j$, the 2-point correlation function can then be written as

$$S_2^{(i)}(\boldsymbol{x}_1, \boldsymbol{x}_2) = S_2^{(i)}(x_{12}). \tag{3.29}$$

When the system is statistically homogeneous, it is meaningful to define volume averages. This suggests an ergodic hypothesis, i.e., the result of averaging over all realizations of the ensemble is equivalent to averaging over the volume for one realization in the infinite-volume limit. Thus, complete probabilistic information can be obtained from a single realization of the infinite medium, and ensemble averaging can be replaced with volume averaging when the volume tends to infinity, i.e.,

$$S_n^{(i)}(\boldsymbol{x}_{12}, \ldots, \boldsymbol{x}_{1n}) = \lim_{V\to\infty} \frac{1}{V} \int_{\mathscr{V}} I^{(i)}(\boldsymbol{y}) I^{(i)}(\boldsymbol{y}+\boldsymbol{x}_{12}) \cdots I^{(i)}(\boldsymbol{y}+\boldsymbol{x}_{1n})\, \mathrm{d}y. \tag{3.30}$$

It is possible to establish asymptotic properties of $S_n^{(i)}$ and associated bounds that apply to any statistically inhomogeneous two-phase random medium. For $n = 2$, one has

$$\lim_{x_{12}\to 0} S_2^{(i)}(\boldsymbol{x}_{12}) = \phi_i, \quad \lim_{x_{12}\to\infty} S_2^{(i)}(\boldsymbol{x}_{12}) = \phi_i^2, \tag{3.31}$$

where ϕ_i denotes the volume fraction of phase i.

The geometrical-probabilistic significance of the n-point probability function can be easily comprehended for a given microstructure. For statistically isotropic media, $S_2^{(i)}$ may be interpreted as the probability that the two vertices of a line segment lie in $\mathscr{V}_i$ when the line segment is randomly placed in the material domain.

Nearest neighbor function

The aforementioned statistical functions are defined for random media of arbitrary microstructure. However, statistical descriptors may be formulated to characterize specific types of microstructures, e.g., an isotropic media composed of identical spherical particles of radius, R, at number density ρ[4], embedded in another phase.

One example is the so-called nearest neighbor function, denoted as H_P. Despite multiple definitions, the one adopted here states that $H_P(r)\,\mathrm{d}r$ is the probability that, at an arbitrary particle center in the system, the center of the nearest particle lies at a distance between r and $r + \mathrm{d}r$. Another similar function, used in Pathan et al. (2017) and here denoted as H_P^*, is defined such that $H_P^*(\theta)\,\mathrm{d}\theta$ is the probability that, at an arbitrary point particle center in the system, the center of the nearest particle lies at an angle between θ and $\theta + \mathrm{d}\theta$. Both $H_P(r)$ and $H_P^*(\theta)$ are probability density functions, nonnegative for all r and θ and normalize to unity. For statistically inhomogeneous media, both functions will also depend upon the location of the central particle.

Ripley's K function

Another widely used function in the description of point distributions is called Ripley's K function, $K(r)$ (Buryachenko et al. (2003), Melro (2011), Pathan et al. (2017)). Also known as the

[4]The number density ρ is defined as the number of particle centers per unit volume.

second-order intensity function, it is a tool used to analyze completely mapped spatial point process data. For the particular application envisaged here, the points are the coordinates of the particles' center-of-mass.

According to Dixon (2014), Ripley's K function is defined as the number of points expected to be located within a distance r of an arbitrary point divided by the number of points per unit area. It can be defined as

$$K(r) = \rho^{-1} E, \tag{3.32}$$

where ρ is the density of points, r is the distance, and E is the number of extra points within a distance r of the randomly chosen point. Given the locations of all events within a defined area of interest, Ω, whose area is denoted as A, the density of points can be estimated as $\widehat{\rho} = N/A$, where N is the observed number of points. Accordingly, an estimator for $K(r)$ is given by

$$\widehat{K}(r) = \frac{A}{N^2} \sum_i \sum_{j \neq i} \frac{I(d_{ij} \leq r)}{w(l_i, l_j)}, \tag{3.33}$$

where A is the area of the region of interest, N is the total number of particles, d_{ij} is the distance between points i and j, and $I(x)$ is an indicator function having the value 1 if the condition x is true and 0 otherwise.

The weight function, $w(l_i, l_j)$, provides an edge correction. To see the need for this correction term, consider some point i and a given distance r. Summing the function $I(d_{ij} \leq r)$ over all points except i, the result is the number of points at a distance smaller or equal to r from i. When the point i is located near the boundary of Ω, there will be fewer points than expected at a distance r or smaller from i, as a significant part of the circle with center at i is outside the area of interest Ω. Thus, if part of the circle falls outside of Ω, then $w(l_i, l_j)$ is the fraction of the circumference of that circle that falls within Ω. It has the value 1 when the circle is centered at l_i and passing through the point l_j, i.e. it has a radius equal to d_{ij} and is completely inside the area Ω. The effects of edge corrections are more important for large r because large circles are more likely to be outside the region of interest. For this reason, it is common practice to consider only values of r less than one-half the shortest dimension of Ω. The information it provides about the medium is different from the one given by the nearest neighbor functions. While the latter only provides information about the short-range interaction between the particles, Ripley's K function also provides some insight into the microstructure at distances beyond the vicinity of the particles.

For a homogeneous Poisson process, also known as complete spatial randomness, it can be shown that

$$K(r) = \pi r^2. \tag{3.34}$$

If the spatial distribution under analysis provides a plot of $\widehat{K}(r)$ below the Poisson curve, then it is likely that the microstructure exhibits some degree of regularity. On the contrary, if $\widehat{K}(r)$ is above the Poisson curve, the distribution is likely to present clustering. A stair-like pattern for $\widehat{K}(r)$ points to a regular pattern. The difference between a Poisson distribution and the actual spatial distribution in the region of interest Ω can be conveniently studied using an alternative function, $\widehat{L}(r)$, defined as

$$\widehat{L}(r) = \sqrt{\frac{\widehat{K}(r)}{\pi}} - r. \tag{3.35}$$

In this case, peaks of positive values in a plot of $\widehat{L}(r)$ would indicate clustering while negative troughs indicate regularity at distance r.

Comparison: 2D microstructure

In this section is performed a comparison between a real microstructure and the corresponding computationally generated microstructure through AMINO.

The real microstructure is a carbon-fiber-reinforced metallic composite taken from Kim et al. (2001) (see Figure 3.34(a)). The original micrograph is post-processed using the open-source software ImageJ (Schneider et al., 2012) (see Figure 3.34(b) and 3.34(c)), being the extracted particle volume fraction approximately 67%.

Using the ellipses fitted by ImageJ to determine the geometrical descriptors, the particle phase is modeled as containing ellipses whose major axis follows a normal distribution $N(0.0526, 0.0027^2)$. The ratio between the major and minor axes follows a normal distribution $N(1.2029, 0.0887)$ and the angle that the ellipses make with positive x semi-axis follows another normal distribution $N(1.6386, 0.9360)$ rad. The computational microstructure is normalized to have a unitary side length. Five realizations of this microstructure are generated through AMINO and shown in Figures 3.34(d)-3.34(h). The average CPU time, the number of particles, and the corresponding standard deviations are shown in Table 3.5 for 10 realizations.



Figure 3.34: Comparison between real and computationally generated two-dimensional microstructures through AMINO: (a) Micrograph of a carbon-fiber-reinforced metallic composite taken from Kim et al. (2001); (b)(c) post-process of micrograph using the open-source software ImageJ (Schneider et al., 2012); (d)-(h) computationally generated microstructure.

Table 3.5: Average CPU time, number of particles and corresponding standard deviations (over 10 realizations of each microstructure), as well as, total volume fraction of the particle phase, in the generation of a legal configuration ($\Psi_{\text{lim}} = 0$).

CPU Time (s)		Number of particles		Total volume fraction of particles (%)
Mean	Std. Dev.	Mean	Std. Dev.	
49.29	5.04	369	1	67



Figure 3.35: Statistical comparison between real and computationally generated microstructures (see Figure 3.34): (a) Difference between Ripley's K function and a Poisson point process; (b) Nearest neighbor function; (c) 2-point probability function. R is defined as the mean major semi-axis of the ellipses in the real micrograph.

In Figure 3.35, the previously introduced statistical descriptors are employed to compare the real and computationally generated microstructures. An excellent agreement between real and computational statistics supports the ability of AMINO to generate high-fidelity microstructures.

Comparison: 3D microstructure

In this section the previous comparison is extended to the three-dimensional case in some sense, being attempted to generate a high-fidelity 3D computational microstructure from a cross-sectional micrograph.

The real microstructure is a PC/ABS polymer blend, whose micrograph is taken from Dong et al. (1993) (see Figure 3.36(a)). In this case, the particle phase corresponds to ABS ellipsoidal domains with a total volume fraction equal to 30%. It is also important to emphasize that the micrograph cut plane is perpendicular to the injection molding direction, being the main elongation of the ABS particles therefore hidden (aligned with the direction perpendicular to the paper). As in the previous analyses, the original micrograph is post-processed using the open-source software ImageJ (Schneider et al., 2012) (see Figures 3.36(b) and 3.36(c)). However, the accurate extraction of 3D microstructure descriptors from 2D micrographs is quite challenging in itself. On the one hand, the morphology observed is strongly dependent on the orientation angle and location of the plane cut (e.g., Bärwinkel et al. (2016)). On the other hand, only the apparent values of the particles' geometrical parameters and associated distributions can be directly extracted from the micrograph. For instance, the ABS volume fraction extracted from the post-processing of the micrograph shown in Figure 3.36(a) is equal to 26%, a significant difference relative to the actual volume fraction of 30%.

Given that overcoming these challenges is out of the scope of the present work, a simple modeling approach is assumed here. In the first place, given that the ABS domains are known to have approximately an ellipsoidal shape, the associated cross-sections observed in the 2D micrograph are approximated to ellipses in the post-processing (see Figure 3.36(c)). Pertaining the known injection molding direction, the ellipsoidal smallest semi-axes, a_2 and a_3, are assumed to be in the plane of the micrograph, and the largest semi-axis, a_1, oriented along the out-of-the-plane direction. The dimensions a_2 and a_3 are sampled directly from the joint experimental probability distribution that is found by fitting the ellipses to the particles found in the micrograph. Concerning the hidden dimension, a_1, it is assumed that the ratio a_1/a_2 is equal to the apparent ratio a_2/a_3, being here considered that $a_1 \geq a_2 \geq a_3$.

The computational microstructure is normalized to have a unitary side length and ten microstructures are generated using the proposed approach. Four equally-spaced cross-sections of one of the generated microstructures are shown in Figures 3.36(e)-3.36(g). Figure 3.37 presents the full 3D microstructure and the aforementioned cross-sections. The average CPU time, the number of particles, and the corresponding standard deviations are presented in Table 3.6.

Table 3.6: Average CPU time, number of particles and corresponding standard deviations (over 10 realizations of each microstructure), as well as the total volume fraction of the particle phase, in the generation of a legal configuration ($\Psi_{\text{lim}} = 0$).

CPU Time (s)		Number of particles		Total volume fraction of particles (%)
Mean	Std. Dev.	Mean	Std. Dev.	
1089.85	144.37	990	65	30



Figure 3.36: Comparison between real and computationally generated two-dimensional microstructures through AMINO: (a) Micrograph of a carbon-fiber reinforced metallic composite taken from Kim et al. (2001); (b)(c) post-process of micrograph using the open-source software ImageJ (Schneider et al., 2012); (d)(g) computationally generated microstructures.



(a) (b)



(c) (d)

Figure 3.37: 3D computationally generated microstructure with four equally-spaced cross-sections matching Figure 3.36: (a) section at $z = 1$; (b) section at $z = 0.8$; (c) section at $z = 0.6$; (d) section at $z = 0.4$. It is assumed that z is the injection molding direction.



Figure 3.38: Comparison between the 2-point correlation function of the real micrograph and several cross-sections of a three-dimensional computational generated microstructure (see Figure 3.36). R denotes the average length of the largest axis of the elliptical cross-sections in the real micrograph.

Figure 3.38 presents a comparison between the 2-point correlation functions describing the real micrograph and the several cross-sections of the three-dimensional computational microstructure. Given the uncertainty associated with the apparent microstructure descriptors and the simplicity of the adopted approach, a reasonable agreement is obtained between experimental and computational results. According to Wu et al. (2018), the area fraction extracted from a representative micrograph can be an acceptable estimate of the actual volume fraction. Moreover, the 2-point correlation function is expected to yield the area fraction for $r = 0$. Attending to the fact that the real ABS volume fraction is known to be 30%, it can be concluded that the 2-point correlation function of the real micrograph is actually a lower bound, yielding approximately 26% for $r = 0$ together with one of the computational cross-sections (section #3). The 2-point correlation function of the remaining cross-sections yield values closer to 30% for $r = 0$, as expected.

3.6 PC/ABS modeling

Given that the main focus of the present thesis is the PC/ABS polymer blend (see Section 1.2.1), this last section is dedicated to the generation of PC/ABS RVEs exhibiting a particulate morphology. First, it is shown that AMINO is able to generate high-fidelity PC/ABS RVEs accounting for the three constituents of the ternary blend. Second, the efficiency, robustness and flexibility of AMINO is evidenced in the generation of several RVEs compliant with relevant microstructure descriptors.

3.6.1 High-fidelity PC/ABS RVEs

The PC/ABS polymer blend composition and morphology has been described in detail in Section 1.2.1. In the low range of ABS(%) content, the PC/ABS exhibits a particulate morphology as shown in Figure 1.4. In summary, the ABS domains (SAN grafted onto PB rubber particles) are usually characterized as ellipsoidal-shaped particles that are embedded in a PC matrix through a suitable blending process. Moreover, given that the most common manufacturing process of PC/ABS components is injection moulding, the ABS domains tend to become oriented and elongated in the injection direction. Despite this, the PB rubber particles remain approximately spherical due to the low viscosity of SAN.

In order to generate high-fidelity PC/ABS RVEs, AMINO must be slightly extended to deal with the PB rubber particles embedded in the ABS domains. The computational generation process can be thus divided into two different steps: (1) the generation of an RVE containing the ABS ellipsoidal domains; (2) the generation of dispersed PB rubber particles within each ABS ellipsoidal domain. The first step is relatively straightforward and follows precisely the formulation and numerical applications presented in the previous sections. Concerning the second step, AMINO could be equally employed through some suitable modifications, namely (i) assuming that each ABS ellipsoidal particle is an independent simulation box and (ii) dropping the periodicity enforcement. However, given that the PB(%) content in ABS is usually low (5-20%) (Greco (1996), Inberg (2001)) and PB particles are spherical, the RSA method (Monte Carlo technique introduced in Section 3.2.3) can be easily integrated to perform this step. The complete set of PB particles is initially generated according to the corresponding microstructure descriptors (e.g., volume fraction, particles' radii distribution). Then the different particles are randomly distributed by the ABS ellipsoidal domains and placed through the RSA method.

PC/ABS RVEs are generated for four different ABS(%) content values between 10% and 40%, as illustrated in Figures 3.39 and 3.40. The microstructure descriptors follow the representative values found in the literature for PC/ABS blends with particulate morphology (see Section 1.2.1). It is assumed a cubic RVE with a side length equal to 30μm and the ABS domains are modeled as ellipsoidal particles in accordance with experimental observations. The major axis follows a normal distribution, $N(5.0, 1.0^2)$μm, and the ratio between the major axis and the other two principal axes is normally distributed, $N(1.5, 0.1^2)$μm. The orientation of the ABS ellipsoidal particles is enforced to be around the x-axis and the rotation angle follows a normal distribution, $N(0.1, 0.2^2)$rad. Both these aspects reproduce the expected elongation and orientation of the ABS domains associated with the injection moulding direction. The PB(%) content is assumed to be 10% of the ABS, resulting in a global volume fraction of 1% (10%ABS), 2% (20%ABS), 3% (30%ABS) and 4% (40%ABS) in the PC/ABS blend. The rubber phase is modeled as spherical particles whose radii follow a normal distribution, $N(0.25, 0.1^2)$μm.

3.6.2 PC/ABS design space

Despite being able to generate high-fidelity PC/ABS RVEs as shown in Figure 3.39, an enormous computational effort would be required to solve the micro-scale equilibrium problem. Given the fine topological details associated with the PB rubber particles and the PB/SAN interface, a suitable spatial discretization would be quite refined and lead to a problem of large dimensions. While the micro-scale analysis of a few samples could still be performed with significant computational costs, the consideration of such RVEs in a data-driven material design framework (see Section 1.2.2) is unfeasible.

A common modeling approach of PC/ABS blends that decreases the problem dimension consists in considering solely two material phases: (1) the PC matrix phase, constitutively treated as a amorphous glassy thermoplastic, and (2) the ABS particles phase, constitutively treated as a porous amorphous glassy thermoplastic to account for the internal cavitation of the PB rubber particles. Such modeling approximation is acceptable from a physical point of view given that PB rubber particles' stiffness is much lower than the surrounding SAN matrix and these cavitate at a relatively low stress level. Therefore, in the remainder of this thesis are considered PC/ABS RVEs that follow this approach and that can be employed to perform the design of experiments of the adopted data-driven framework.

At this point it is instructive to do a preliminary evaluation on the ability to generate the required RVEs in two different aspects: first, the compliance with the different microstructure descriptors, namely the ABS(%) content and the geometry of the ABS ellipsoidal particles; and second, the expected computational cost to generate single RVEs under different microstructure descriptors. This preliminary analysis allows to estimate the bounds of the PC/ABS design space that can be explored in a reasonable amount of time in what concerns the RVE generation step.

Tables 3.7 and 3.8 summarize this preliminary assessment, presenting the average computational generation time and the average number of particles over 5 realizations of each design point. Although two-dimensional micro-scale analyses under plain strain conditions are not adequate to accurately model the ABS ellipsoisal particles, 2D RVEs containing ABS elliptical particles are also included in this analysis with the in-plane descriptors similar to the three-dimensional case. Four discrete values of the ABS (%) content are considered between 10% and 40%, and three different RVE sizes are explored, namely with side length 20μm, 30μm and 40μm. The ABS elliptical/ellipsoidal particles' major axis follows a normal distribution, $N(5.0, 1.0^2)\mu$m, and the ratio between the major axis and the other(s) principal axis/axes assumes different discrete values between 1.5 (moderate elongation) and 2.3 (high elongation). The orientation of the ABS elliptical/ellipsoidal particles is again enforced to be around the x-axis (assumed injection moulding direction) and the rotation angle follows a normal distribution, $N(0.1, 0.2^2)$.

It can be first observed that AMINO is able to successfully generate all the required microstructures in a non-supervised way, accounting for the different values of ABS (%) content, RVE's sizes, ABS particles' geometrical ratios and preferred orientation (see Figure 3.41). This highlights both the robustness and flexibility of the developed method, crucial requirements in a data-driven framework. In the second place, as expected, the computational generation time depends significantly on the microstructure descriptors. In general, the computational time increases with the increase of the number of particles, resultant from either increasing the ABS (%) content or the RVE size, and with the ABS ellipsoidal particles' elongation. Nonetheless, the generation of 2D microstructures with a number of particles between a few (3) and a few dozens (46) is quite fast and lies in the range 0.005-2.96s. In contrast, the 3D case involves substantially higher computational costs due to the third spatial dimension. Note that for similar microstructure descriptors, there is a substantial increase of the number of particles, now lying between a few dozens (25) and a few thousands (1846). For these limit cases, the computational generation cost associated with

each 3D RVE ranges between 1.35s and 1.73h, which is a significant difference of three orders of magnitude.

For simple estimation purposes, it can be considered a DoE where all the design points share the same microstructure descriptors. Note that this scenario would probably never occur in practice, given that a single RVE could be generated once and associated with all design points. In addition, it is assumed that each design is characterized by a single RVE. For a reasonably large DoE of 10000 design points, the corresponding 2D PC/ABS RVEs could be generated in a time frame of 0.01-8h. Thus, even in the case of the most computationally expensive RVE present in Table 3.7, the total generation time is perfectly acceptable. In contrast, the 3D PC/ABS RVEs required to perform a similar DoE of 10000 design points would take 3.75h-2yr in the limit cases of Table 3.8. It is evident that the total computational time is prohibitive when considering 3D RVEs with several hundreds of particles. However, note that even if the microstructure generation time was neglectable, a very refined spatial discretization would be required to capture the fine topological details. This would lead to expensive micro-scale equilibrium analyses that would most likely be the bottleneck of the data-driven framework. Nonetheless, by considering a 3D PC/ABS RVE with approximately 100 particles, the total computational time to generate a DoE of 10000 design points would be approximately 4 days.

3.7 Conclusions

In this contribution, a new computational generation method for particle-reinforced materials is proposed, being coined AMINO (Adaptive Multi-temperature Isokinetic Method). It can be classified as a geometrical generation method and is characterized as an adaptive multi-temperature isokinetic time-driven molecular dynamics scheme. Through extensive numerical application and some comparisons with experimental micrographs, AMINO is shown to be efficient, robust, flexible and able to generate high-fidelity particle-reinforced materials RVEs under a wide spectrum of supplied microstructure descriptors. These features make AMINO suitable to be employed in a data-driven framework for the design and modeling of materials.

Concerning the geometrical parametrization, AMINO can effectively deal with several types of particles, namely disks and ellipses in the two-dimensional case, and spheres, ellipsoids and cylinders in the three-dimensional case. Any number of particulate material phases is accepted and the microstructure descriptors may be supplied as either fixed prescribed values or as following known statistical distributions. Interaction forces, assumed proportional to the intersection length, are computed in a fast way through a coupling between the well-known cell list and Verlet list methods. An efficient approximation to the intersection length and associated direction is proposed based on the concept of Minkowski difference between two convex sets, being valid for any admissible particle types. As an explicit time integration scheme is adopted, it is proposed an estimate for the critical time step of the system and the time integration step is always adaptively maximized throughout the simulation. In addition, a multi-temperature isokinetic thermostat is formulated such that the microstructure is subjected to a quenching process until a legal configuration is found. This approach explores higher temperatures as much as possible, given that these lead to a faster removal of particle intersections and improves the overall quality of the microstructure. Both of these strategies can be readily employed without requiring cumbersome parameters calibration based on numerical experience. Regarding the final configuration, microstructure periodicity is effectively handled and two features are included to ease the spatial mesh discretization of the RVE.

In a first set of numerical results, the two main proposed features are evaluated for microstructures containing disks (2D) and spheres (3D), covering a wide range of number of particles and volume fractions. The robustness of the adaptive time integration step scheme is clearly evidenced, with no signs of numerical instability arising in the whole spectrum of microstructure descriptors. Comparison with a standard constant time integration steps show that the adaptive time integration step closely follows the highest value possible below the critical time step. As for the multi-temperature isokinetic thermostat, it is shown that the proposed temperature lowering criterion is able to detect the overlap residue plateaus and that the different temperature stages are efficiently explored until a null overlap residue is achieved. Both approaches allow AMINO to be highly efficient and robust, namely in the medium-to-high volume fraction range, and able to deliver high-fidelity RVEs. In a second set of results, several miscellaneous complex microstructures are generated in both 2D and 3D cases, accounting for mixtures of different particle types and microstructure descriptors following different statistics. Finally, suitable statistical functions are employed to compare experimental micrographs obtained in the literature with the RVEs computationally generated from the extracted microstructure descriptors. An excellent agreement suggests that AMINO is indeed able to produce RVEs that closely resemble actual particle-reinforced materials.

At last, given that the main material focused of the present thesis is the PC/ABS polymer blend, AMINO is further explored in the generation of the corresponding microstructures. First, AMINO is successfully coupled with the RSA to generate high-fidelity PC/ABS RVEs accounting for the three constituents of the blend (PC, SAN and PB). Second, a preliminary analysis is carried out to evaluate the performance of AMINO in a data-driven framework. In terms of robustness and flexibility, the method is shown to comply with several microstructure descriptors and is able to successfuly generate all the required microstructures in a non-supervised way. Concerning efficiency, it is observed that the computational time depends significantly on the prescribed descriptors, besides the spatial dimensionality of the RVE. While in the 2D case a reasonably large DoE of 10000 design points can be generated in a few hours at most, the 3D case computational time for the same DoE size exhibits prohibitive costs when considering RVEs with several hundreds of particles. Nonetheless, even when considering rather detailed 3D RVEs with approximately 100 particles (e.g., see Figure 3.41(c)), the DoE generation time is acceptably bounded to a couple of days.



(a) (b)

(c) (d)

Figure 3.39: PC/ABS high-fidelity RVEs computationally generated through AMINO for different ABS(%) contents exhibiting a particulate morphology: (a) 10%; (b) 20%; (c) 30%; (d) 40%. It is assumed that the injection direction is along the x-axis.



(a) (b)

(c) (d)

Figure 3.40: Longitudinal cross-sections of PC/ABS high-fidelity RVEs computationally generated through AMINO for different ABS(%) contents exhibiting a particulate morphology: (a) 10%; (b) 20%; (c) 30%; (d) 40%. It is assumed that the injection direction is along the x-axis.

Table 3.7: Average CPU time and average number of particles (over 5 realizations of each microstructure) in the generation of PC/ABS 2D RVEs through AMINO ($\Psi_{\text{lim}} = 0$). PC/ABS is modeled as a biphasic material characterized by ABS elliptical particles (phase 2) embedded in a PC matrix (phase 1).

ABS (%)	l_{RVE} (μm)	Ratio (a/b)	Avg. CPU Time (s)	Avg. Number of Particles
10	20	1.5	5.40×10^{-03}	3
		1.9	1.02×10^{-02}	3
		2.3	5.00×10^{-03}	3
	30	1.5	2.12×10^{-02}	7
		1.9	1.24×10^{-02}	6
		2.3	1.62×10^{-02}	7
	40	1.5	4.30×10^{-02}	12
		1.9	5.32×10^{-02}	12
		2.3	6.42×10^{-02}	13
20	20	1.5	4.00×10^{-02}	6
		1.9	4.20×10^{-02}	5
		2.3	6.66×10^{-02}	5
	30	1.5	2.37×10^{-01}	14
		1.9	3.13×10^{-01}	14
		2.3	2.27×10^{-01}	14
	40	1.5	5.53×10^{-01}	24
		1.9	4.41×10^{-01}	25
		2.3	5.54×10^{-01}	23
30	20	1.5	3.00×10^{-01}	10
		1.9	2.32×10^{-01}	9
		2.3	2.53×10^{-01}	9
	30	1.5	7.35×10^{-01}	20
		1.9	7.46×10^{-01}	20
		2.3	8.37×10^{-01}	20
	40	1.5	$1.55 \times 10^{+00}$	37
		1.9	$1.30 \times 10^{+00}$	34
		2.3	$1.26 \times 10^{+00}$	34
40	20	1.5	5.00×10^{-01}	13
		1.9	4.71×10^{-01}	12
		2.3	5.05×10^{-01}	12
	30	1.5	$1.60 \times 10^{+00}$	26
		1.9	$1.23 \times 10^{+00}$	28
		2.3	$1.50 \times 10^{+00}$	26
	40	1.5	$2.61 \times 10^{+00}$	46
		1.9	$2.92 \times 10^{+00}$	46
		2.3	$2.96 \times 10^{+00}$	46

Table 3.8: Average CPU time and average number of particles (over 5 realizations of each microstructure) in the generation of PC/ABS 3D RVEs through AMINO ($\Psi_{\text{lim}} = 0$). PC/ABS is modeled as a biphasic material characterized by ABS ellipsoidal particles (phase 2) embedded in a PC matrix (phase 1).

ABS (%)	l_{RVE} (μm)	Ratio ($a/b, c$)	Avg. CPU Time (s)	Avg. Number of Particles
10	20	1.5	$1.35 \times 10^{+00}$	25
		1.9	$3.54 \times 10^{+00}$	42
		2.3	$6.31 \times 10^{+00}$	59
	30	1.5	$7.54 \times 10^{+00}$	80
		1.9	$2.84 \times 10^{+01}$	128
		2.3	$6.98 \times 10^{+01}$	192
	40	1.5	$2.91 \times 10^{+01}$	198
		1.9	$6.34 \times 10^{+01}$	313
		2.3	$1.50 \times 10^{+02}$	457
20	20	1.5	$5.70 \times 10^{+00}$	48
		1.9	$1.55 \times 10^{+01}$	78
		2.3	$3.81 \times 10^{+01}$	116
	30	1.5	$5.27 \times 10^{+01}$	171
		1.9	$1.48 \times 10^{+02}$	266
		2.3	$4.30 \times 10^{+02}$	385
	40	1.5	$1.50 \times 10^{+02}$	392
		1.9	$4.85 \times 10^{+02}$	632
		2.3	$1.16 \times 10^{+03}$	919
30	20	1.5	$1.48 \times 10^{+01}$	69
		1.9	$4.21 \times 10^{+01}$	119
		2.3	$9.10 \times 10^{+01}$	172
	30	1.5	$1.39 \times 10^{+02}$	250
		1.9	$5.63 \times 10^{+02}$	400
		2.3	$1.09 \times 10^{+03}$	587
	40	1.5	$4.14 \times 10^{+02}$	590
		1.9	$1.36 \times 10^{+03}$	948
		2.3	$2.76 \times 10^{+03}$	1385
40	20	1.5	$3.61 \times 10^{+01}$	97
		1.9	$9.64 \times 10^{+01}$	156
		2.3	$2.42 \times 10^{+02}$	237
	30	1.5	$4.11 \times 10^{+02}$	339
		1.9	$1.02 \times 10^{+03}$	525
		2.3	$2.41 \times 10^{+03}$	766
	40	1.5	$9.01 \times 10^{+02}$	772
		1.9	$2.74 \times 10^{+03}$	1250
		2.3	$6.22 \times 10^{+03}$	1846



Figure 3.41: PC/ABS 3D RVEs computationally generated through AMINO for different microstructure descriptors: (a) (10, 20, 1.5); (b) (20, 30, 1.9); (c) (30, 20, 1.5); (d) (40, 40, 2.3). (V, S, R) with V denoting the ABS (%) content, S the RVE's size (μm) and R the ratio between ellipses/ellipsoids major and minor axes.

Chapter 4

Clustering-based Reduced-Order Modeling of Heterogeneous Materials

4.1 Clustering-based reduced-order models

A myriad of so-called ROMs has been developed over the last decades aiming to find an appropriate balance between accuracy and computational cost. Different approaches and strategies have proven successful and one can enumerate the following among the most well-known ROMs: analytical micromechanical methods (e.g, Moore et al. (2014)), Transformation Field Analysis (TFA) (Dvorak, 1992), Nonuniform Transformation Field Analysis (NTFA) (e.g., Michel and Suquet (2003), Roussette et al. (2009)), Principal Component Analysis (PCA) (e.g., Jolliffe (2002)), Proper Orthogonal Decomposition (POD) (e.g., Yvonnet and He (2007)), Proper Generalized Decomposition (PGD) (e.g., Ladevèze et al. (2010), Cueto et al. (2016), Ibáñez et al. (2019a)), Reduced Basis Method (RB) (e.g Boyaval (2008), Nguyen (2008)), High-Performance Reduced-Order Model (HPROM) (Hernández et al., 2014), Empirical Interpolation Method (EIM) (Barrault et al., 2004), Best Point Interpolation Method (Nguyen et al., 2008), Missing Point Estimation (MPE) (Astrid et al., 2008), Discrete Empirical Interpolation Method (DEIM) (Chaturantabut and Sorensen, 2010), Energy Conserving Sampling and Weighting (ECSW) (Farhat et al., 2014), Empirical Cubature Method (ECM) (Hernández et al., 2017) and Wavelet-Reduced-Order Model (WROM) (van Tuijl et al., 2019). These methods have advantages and disadvantages, mainly related to the nature of the applications where they are employed, and, in some cases, the potential to be coupled with each other to combine their best characteristics.

A particular ROM family coined clustering-based ROMs (CROMs) has been recently introduced and comprises models that rely on unsupervised machine learning cluster analysis algorithms in order to perform the model reduction. This class of ROMs emerged from the pioneering contribution of Liu and coworkers, who proposed the Self-consistent Clustering Analysis (SCA) method (Liu et al., 2016). Several contributions of Liu and coworkers have been published since then with the aim of improving the formulation, integrating the method in state-of-the-art modeling frameworks and exploring different applications. Bessa et al. (2017) incorporated the SCA in the proposed data-driven modeling framework in order to build the material response database in an accurate and efficient way. Liu et al. (2018b) formulated a regularized multi-scale damage method (coupling between a nonlocal macroscopic damage model with a stable micro-scale damage homogenization algorithm) relying on the efficient SCA analyses to conduct FE-SCA multi-scale simulations. Yan et al. (2018c), Yan et al. (2018b) and Yan et al. (2018a) proposed a data-driven multi-scale multi-physics modeling framework to link process-structure-property-performance on additive manufacturing, taking advantage of the SCA in the structure-property multi-scale modeling. Based on the previous work laid down in Liu's PhD thesis (Liu, 2017), Yu et al. (2019) generalized the SCA formulation for finite strains and the latter was readily applied to perform FE-SCA multi-scale simulations on polycrystalline materials and to predict the nucleation and growth of voids in ductile materials by debonding and fragmentation (Shakoor et al., 2019). More recently, He et al. (2020), Gao et al. (2020) and Han et al. (2020) further explored the SCA formulation in the multi-scale modeling of composite materials, and Yu et al. (2021) formalized a Multiresolution Clustering Analysis

(MCA) framework to perform n-scale concurrent SCA simulations.

Other relevant contributions stem from Wulfinghoff and coworkers (Wulfinghoff et al., 2017), proposing a CROM derived from the Hashin-Shtrikman variational principle (HSFE), which turned out to be equivalent to the SCA formulation. This method was later integrated into an efficient FE^2-like multi-scale homogenization approach by Cavaliere et al. (2019). Recently, Schneider provided valuable mathematical foundations to both SCA and HSFE CROMs, namely by demonstrating the well-posedness of the equilibrium equations and convergence upon cluster refinement (Schneider, 2019). Tang et al. (2018) propose an alternative formulation of the SCA called Virtual Clustering Analysis (VCA) by introducing an enlarged virtual domain surrounding the original domain, proposing a strategy to select the suitable reference stiffness of such virtual domain in a recent contribution (Zhu et al., 2021). Taking inspiration from the work of Liu and coworkers, Li et al. (2019) reformulated the SCA in a consistent FEM framework, proposing the FEM-Cluster based Analysis (FCA) method. This method was later enhanced through the Principle of Minimum Complementary Energy in a cluster-based variational way (Nie et al., 2019) and recently applied to predict the effective properties of porous materials (Nie et al., 2021).

Given the potential of the SCA method (Liu et al., 2016) demonstrated in the aforementioned research, it is deemed as a particularly appealing method to tackle one of the challenges established in this thesis (see Section 1.2.3). In this context, this chapter aims to provide some contributions to enhance this CROM further as well as to enrich the overall clustering-based reduced-order modeling framework. In the first place, the clustered Lippmann-Schwinger integral equilibrium equation is thoroughly and systematically derived under both infinitesimal and finite strain settings (Sections 4.2 and 4.3). Such derivation sheds light on important aspects of the SCA formulation, namely related to the nature of the homogeneous far-field strain, the incremental update of the reference homogeneous material properties and a proper finite strain extension following multiplicative kinematics. In the second place, a novel strategy is proposed to enhance the ability of CROMs to handle cases where highly localized plasticity or damage phenomena take place (Sections 4.4 and 4.5). This strategy introduces for the first time the so-called Adaptive Clustering-based Reduced-Order Models (ACROMs), readily yielding the adaptive extension of the SCA method coined Adaptive Self-consistent Clustering Analysis (ASCA). Last but not least, a new finite strain extension of the SCA method compatible with the multiplicative nature of the deformation gradient is proposed (Sections 4.7 and 4.8). This unveils new challenges concerning the numerical dependency of the reference homogeneous material properties and the convergence conditions of the self-consistent partitioned scheme. Moreover, a highly efficient computational implementation strategy of the FFT-based homogenization basic scheme (Liu et al., 2016) is proposed to perform the SCA's offline-stage DNS analyses (Section 4.6). It is also worth mentioning that this chapter is complemented by several appendices aiming to provide a suitable background to the topics covered in the previously mentioned contributions (Appendices A-E). The main conclusions are finally summarized in Section 4.10.

4.2 The Lippmann-Schwinger integral equation

The fundamentals of a first-order homogenization hierarchical multi-scale model are described in Chapter 2, followed by the numerical solution of the micro-scale equilibrium problem based on the Finite Element Method (FEM). Despite the theoretical background provided therein, the actual mathematical formulation of the Self-consistent Clustering Analysis (SCA) (Liu et al., 2016) calls for further concepts stemming from micromechanics and FFT-based homogenization. With this in mind, the goal of this section is twofold: (i) provide a suitable multi-scale modeling framework from which the SCA formulation is properly derived and (ii)

provide a deeper comprehension and insight into the physics involved in the SCA's formulation. Both of these goals are hopefully achieved throughout the derivation of the so-called Lippmann-Schwinger integral (quasi-static) equilibrium equation[1]. Note that this contrasts with the quasi-static equilibrium formulation derived by means of the Virtual Work Principle in Chapter 2.

For the sake of completeness, some fundamentals on micromechanics are introduced in Appendix A, mainly directed toward the reader who is unfamiliar with this subject. In addition, the interested reader is referred to Newland (1984), Rao et al. (2010), Kreyszig (2010) and Chaparro (2011) for a complete treatment on the topic of Fourier Analysis.

4.2.1 Infinitesimal strains

Three decades ago, Moulinec and Suquet (1994) proposed an ingenious micromechanics-based homogenization method based on Fourier series and on the solution of a Lippmann-Schwinger type equilibrium equation under infinitesimal strains. Their pioneering contribution, often referred to as the FFT-based homogenization basic scheme, opened new avenues to the so-called FFT-based homogenization methods that have received a lot of attention since then (e.g., Michel et al. (1999a), Zeman et al. (2010), Monchiet and Bonnet (2012b), Yvonnet (2012), de Geus et al. (2017), Zeman et al. (2017))[2]. Despite the potential of the most recent FFT-based homogenization methods and the well-known limitations of the FFT-based homogenization basic scheme (Moulinec and Suquet, 1994), its pioneering formulation introduces valuable concepts that are closely related to the SCA's formulation and that are explored in what follows. For the interested reader, the numerical implementation of the FFT-based homogenization basic scheme (Moulinec and Suquet, 1994) is provided in Appendix B.

Problem formulation

Consider a heterogeneous RVE of domain $\Omega_{\mu,0}$ and boundary $\partial\Omega_{\mu,0}$ in its reference configuration, composed of a given number of perfectly bonded linear elastic phases and characterized by a given tangent modulus $\mathbf{D}^e(\boldsymbol{Y})$. Following the multi-scale kinematic procedures introduced in Chapter 2, consider that a given macro-scale strain, $\boldsymbol{\varepsilon}(\boldsymbol{X})$, is prescribed such that

$$\boldsymbol{\varepsilon}(\boldsymbol{X}) = \frac{1}{v_{\mu,0}} \int_{\Omega_{\mu,0}} \boldsymbol{\varepsilon}_\mu(\boldsymbol{Y}) \, \mathrm{d}v \,, \tag{4.1}$$

where $v_{\mu,0}$ denotes the volume of the RVE in the reference configuration, and periodic boundary conditions are assumed. In addition, without any loss of generality, the micro-scale strain field can be decomposed as (see Section 2.12.2)

$$\boldsymbol{\varepsilon}_\mu(\boldsymbol{Y}) = \boldsymbol{\varepsilon}(\boldsymbol{X}) + \tilde{\boldsymbol{\varepsilon}}_\mu(\boldsymbol{Y}) \,, \tag{4.2}$$

where $\boldsymbol{\varepsilon}(\boldsymbol{X})$ and $\tilde{\boldsymbol{\varepsilon}}_\mu$ are the average and fluctuation components, respectively.

In the absence of body forces, the micro-scale quasi-static equilibrium problem consists of finding the micro-scale strain field that satisfies the strong equilibrium equations,

[1] Given the quasi-static nature of the Lippmann-Schwinger integral equilibrium equation derived here, the explicit dependence of t is dropped in this chapter. The instants of time resulting from a suitable time discretization shall be then regarded as a pseudo-time associated with the loading incrementation.

[2] The particular interest of this family of methods in the context of clustering-based reduced-order modeling is discussed later in Section 4.6.

$$\operatorname{div}_0[\boldsymbol{\sigma}_\mu(\boldsymbol{Y})] = \mathbf{0} \quad \text{with} \quad \boldsymbol{\sigma}_\mu(\boldsymbol{Y}) = \mathbf{D}^e(\boldsymbol{Y}) : \boldsymbol{\varepsilon}_\mu(\boldsymbol{Y}), \quad \forall \boldsymbol{Y} \in \Omega_{\mu,0}. \tag{4.3}$$

The auxiliary homogeneous problem

In order to solve the micro-scale equilibrium problem, a suitable eigenstress problem can be formulated by considering a reference (fictitious) homogeneous linear elastic solid occupying the same region $\Omega_{\mu,0}$ of boundary $\partial\Omega_{\mu,0}$ and characterized by a given tangent modulus $\mathbf{D}^{e,0}$. Note that in this auxiliary homogeneous problem, the fictitious RVE is solely subjected to a prescribed eigenstress field, $\boldsymbol{\sigma}^*_\mu(\boldsymbol{Y})$, such that the associated micro-scale quasi-static equilibrium problem reads

$$\operatorname{div}_0[\boldsymbol{\sigma}_\mu(\boldsymbol{Y})] = \mathbf{0} \quad \text{with} \quad \boldsymbol{\sigma}_\mu(\boldsymbol{Y}) = \mathbf{D}^{e,0}(\boldsymbol{Y}) : \tilde{\boldsymbol{\varepsilon}}_\mu(\boldsymbol{Y}) + \boldsymbol{\sigma}^*_\mu(\boldsymbol{Y}), \quad \forall \boldsymbol{Y} \in \Omega_{\mu,0}. \tag{4.4}$$

By performing the following Fourier transforms[3],

$$\mathscr{F}\left\{\left(\operatorname{div}_0[\boldsymbol{\sigma}_\mu(\boldsymbol{Y})]\right)_i\right\} = \mathrm{i}\,\check{\sigma}_{\mu,ij}(\boldsymbol{\zeta})\,\zeta_j, \tag{4.5}$$

$$\mathscr{F}\left\{\sigma_{\mu,ij}(\boldsymbol{Y})\right\} = \check{\sigma}_{\mu,ij}(\boldsymbol{\zeta}) = \mathrm{i}\,\mathsf{D}^{e,0}_{ijkl}\,\zeta_l\,\check{\tilde{u}}_k(\boldsymbol{\zeta}) + \check{\sigma}^*_{\mu,ij}(\boldsymbol{\zeta}), \tag{4.6}$$

where $\boldsymbol{\zeta}$ is the frequency wave vector and $(\check{\bullet})$ denotes the definition in the frequency domain, the auxiliary micro-scale quasi-static equilibrium problem can be established in the frequency domain as

$$\mathrm{i}\,\check{\sigma}_{\mu,ij}(\boldsymbol{\zeta})\,\zeta_j = 0 \quad \text{with} \quad \check{\sigma}_{\mu,ij}(\boldsymbol{\zeta}) = \mathrm{i}\,\mathsf{D}^{e,0}_{ijkl}\,\zeta_l\,\check{\tilde{u}}_{\mu,k}(\boldsymbol{\zeta}) + \check{\sigma}^*_{\mu,ij}(\boldsymbol{\zeta}). \tag{4.7}$$

After replacing the constitutive relation in the strong equilibrium equation and performing some straightforward algebraic manipulations, it comes

$$\check{K}^0_{ik}(\boldsymbol{\zeta})\,\check{\tilde{u}}_{\mu,k}(\boldsymbol{\zeta}) = \mathrm{i}\,\check{\sigma}^*_{\mu,ij}\,\zeta_j, \tag{4.8}$$

where $\check{\boldsymbol{K}}^0$ is defined as

$$\check{K}^0_{ik}(\boldsymbol{\zeta}) = \mathsf{D}^{e,0}_{ijkl}\,\zeta_j\,\zeta_l. \tag{4.9}$$

From the previous equation, the micro-scale displacement field can be obtained as

$$\check{\tilde{u}}_{\mu,k}(\boldsymbol{\zeta}) = \mathrm{i}\,\check{Q}^0_{ki}(\boldsymbol{\zeta})\,\check{\sigma}^*_{\mu,ij}(\boldsymbol{\zeta})\,\zeta_j, \tag{4.10}$$

where $\check{\boldsymbol{Q}}^0 = \left(\check{\boldsymbol{K}}^0\right)^{-1}$, and attending to the symmetry of the eigenstress field, $\check{\boldsymbol{\sigma}}^*_\mu(\boldsymbol{\zeta})$, it can be conveniently rewritten as

$$\check{\tilde{u}}_{\mu,k}(\boldsymbol{\zeta}) = \frac{\mathrm{i}}{2}\left[\check{Q}^0_{ki}(\boldsymbol{\zeta})\,\zeta_j + \check{Q}^0_{kj}(\boldsymbol{\zeta})\,\zeta_i\right]\check{\sigma}^*_{\mu,ij}(\boldsymbol{\zeta}). \tag{4.11}$$

The micro-scale strain field can then be obtained through the symmetric material gradient of the micro-scale displacement field as

$$\check{\tilde{\varepsilon}}_{\mu,kl}(\boldsymbol{\zeta}) = \frac{\mathrm{i}}{2}\left(\zeta_l\,\check{\tilde{u}}_{\mu,k}(\boldsymbol{\zeta}) + \zeta_k\,\check{\tilde{u}}_{\mu,l}(\boldsymbol{\zeta})\right). \tag{4.12}$$

[3] Recall that in the infinitesimal strain formulation, one has the explicit relation between the displacement and strain fields given by $\tilde{\boldsymbol{\varepsilon}}_\mu(\boldsymbol{Y}) = \nabla^s_0\,\tilde{\boldsymbol{u}}_\mu(\boldsymbol{Y})$, where ∇^s_0 denotes the symmetric material gradient operator.

After substitution of Equation (4.11), the micro-scale strain field can be finally expressed as

$$\check{\tilde{\varepsilon}}_{\mu,kl}(\boldsymbol{\zeta}) = -\check{\Phi}^0_{klij}(\boldsymbol{\zeta})\,\check{\sigma}^*_{\mu,ij}(\boldsymbol{\zeta})\,, \tag{4.13}$$

where $\check{\boldsymbol{\Phi}}^0(\boldsymbol{\zeta})$ is the Green operator defined as

$$\check{\Phi}^0_{klij}(\boldsymbol{\zeta}) = \frac{1}{4}\left[\check{Q}^0_{ki}(\boldsymbol{\zeta})\zeta_j\zeta_l + \check{Q}^0_{kj}(\boldsymbol{\zeta})\zeta_i\zeta_l + \check{Q}^0_{li}(\boldsymbol{\zeta})\zeta_j\zeta_k + \check{Q}^0_{lj}(\boldsymbol{\zeta})\zeta_i\zeta_k\right]. \tag{4.14}$$

The solution to the auxiliary homogeneous equilibrium problem can then be established in the frequency domain as[4]

$$\check{\tilde{\boldsymbol{\varepsilon}}}_\mu(\boldsymbol{\zeta}) = -\check{\boldsymbol{\Phi}}^0(\boldsymbol{\zeta}) : \check{\boldsymbol{\sigma}}^*_\mu(\boldsymbol{\zeta})\,, \quad \forall\boldsymbol{\zeta}\neq\mathbf{0}\,, \quad \check{\tilde{\boldsymbol{\varepsilon}}}_\mu(\mathbf{0}) = \mathbf{0}\,. \tag{4.15}$$

Attending to the following inverse Fourier transform,

$$\mathscr{F}^{-1}\left\{\check{\boldsymbol{\Phi}}^0(\boldsymbol{\zeta}) : \check{\boldsymbol{\sigma}}^*_\mu(\boldsymbol{\zeta})\right\} = \int_{\Omega_{\mu,0}} \boldsymbol{\Phi}^0(\boldsymbol{Y}-\boldsymbol{Y}')\,\boldsymbol{\sigma}^*_\mu(\boldsymbol{Y}')\,\mathrm{d}v'\,, \tag{4.16}$$

where the volume integration is performed over $\boldsymbol{Y}'$ as denoted by the prime $(\bullet)'$, the solution of the auxiliary homogeneous equilibrium problem is given in the spatial domain by

$$\tilde{\boldsymbol{\varepsilon}}_\mu(\boldsymbol{Y}) = -\int_{\Omega_{\mu,0}} \boldsymbol{\Phi}^0(\boldsymbol{Y}-\boldsymbol{Y}') : \boldsymbol{\sigma}^*_\mu(\boldsymbol{Y}')\,\mathrm{d}v'\,, \quad \forall\boldsymbol{Y}\in\Omega_{\mu,0}\,. \tag{4.17}$$

From a physical point of view, it transpires from this solution that the Green operator component $\Phi_{ijkl}(\boldsymbol{Y}-\boldsymbol{Y}')$ represents the strain $\varepsilon_{\mu,ij}$ at the point $\boldsymbol{Y}$ due to a unit stress $\sigma^*_{\mu,kl}$ applied at the point $\boldsymbol{Y}'$, thus effectively establishing a strain-stress relationship between two points of the domain.

Green operator under linear elastic isotropy

Despite having established the solution of the auxiliary homogeneous equilibrium problem in Equation (4.17), it still remains to define the Green operator explicitly. While for anisotropic materials the closed-form expression of the Green operator is usually complex (Mura, 1987), under isotropy conditions it assumes a particularly simple explicit form in the frequency domain, as demonstrated below. Considering the tangent modulus of an isotropic linear elastic material,

$$\mathsf{D}^{e,0}_{ijkl} = \lambda^0\delta_{ij}\delta_{kl} + \mu^0(\delta_{ik}\delta_{jl} + \delta_{il}\delta_{jk})\,, \tag{4.18}$$

where (λ^0, μ^0) are the reference material Lamé parameters and δ_{ij} is the discrete Dirac's delta, substitution on Equation (4.9) yields

$$\check{K}^0_{ik}(\boldsymbol{\zeta}) = (\lambda^0+\mu^0)\zeta_i\zeta_k + \mu^0\|\boldsymbol{\zeta}\|^2\delta_{ik}\,, \tag{4.19}$$

[4]Note that the zero frequency term of the micro-scale strain field, $\check{\tilde{\boldsymbol{\varepsilon}}}_\mu(\boldsymbol{\zeta}=\mathbf{0})$, is associated with its average value on the spatial domain, which in the case of the auxiliary homogeneous equilibrium problem is null.

and, after some algebraic manipulations, the inverse of the previous expression leads to

$$\check{Q}^0_{ik} = \left(\check{K}^0_{ik}\right)^{-1} = \frac{1}{\mu^0 \|\boldsymbol{\zeta}\|^2}\left(\delta_{ki} - \frac{\lambda^0+\mu^0}{\lambda^0+2\mu^0}\frac{\zeta_k\zeta_i}{\|\boldsymbol{\zeta}\|^2}\right). \tag{4.20}$$

Finally, the substitution of this result in Equation (4.14) renders

$$\check{\Phi}^0_{klij}(\boldsymbol{\zeta}) = \frac{1}{4\mu^0}\frac{\delta_{ki}\zeta_j\zeta_l + \delta_{kj}\zeta_i\zeta_l + \delta_{li}\zeta_j\zeta_k + \delta_{lj}\zeta_i\zeta_k}{\|\boldsymbol{\zeta}\|^2} - \frac{\lambda^0+\mu^0}{\mu^0(\lambda^0+2\mu^0)}\frac{\zeta_k\zeta_l\zeta_i\zeta_j}{\|\boldsymbol{\zeta}\|^4}. \tag{4.21}$$

The Lippmann-Schwinger integral equation

Having the solution to the auxiliary homogeneous equilibrium problem at hand, it is now possible to solve the actual micro-scale equilibrium problem. In order to do so, it is convenient to introduce a reference (fictitious) homogeneous linear elastic material with tangent modulus $\mathbf{D}^{e,0}$ into the constitutive formulation as

$$\boldsymbol{\sigma}_\mu(\boldsymbol{Y}) = \left(\mathbf{D}^e(\boldsymbol{Y}) + \mathbf{D}^{e,0} - \mathbf{D}^{e,0}\right) : \boldsymbol{\varepsilon}_\mu(\boldsymbol{Y}), \quad \forall \boldsymbol{Y} \in \Omega_{\mu,0}, \tag{4.22}$$

which can be rewritten as

$$\boldsymbol{\sigma}_\mu(\boldsymbol{Y}) = \mathbf{D}^{e,0} : \boldsymbol{\varepsilon}_\mu(\boldsymbol{Y}) + \left(\mathbf{D}^e(\boldsymbol{Y}) - \mathbf{D}^{e,0}\right) : \boldsymbol{\varepsilon}_\mu(\boldsymbol{Y}), \quad \forall \boldsymbol{Y} \in \Omega_{\mu,0}. \tag{4.23}$$

In the first place, it is possible to notice that the last right-hand side term can be regarded as an eigenstress field defined as

$$\boldsymbol{\sigma}^*_\mu(\boldsymbol{Y}) = \left(\mathbf{D}^e(\boldsymbol{Y}) - \mathbf{D}^{e,0}\right) : \boldsymbol{\varepsilon}_\mu(\boldsymbol{Y}). \tag{4.24}$$

From a physical point of view, $\boldsymbol{\sigma}^*_\mu(\boldsymbol{Y})$ represents, at each point $\boldsymbol{Y}$, the difference in the stress between the actual heterogeneous material and the reference homogeneous material for a given strain $\boldsymbol{\varepsilon}_\mu(\boldsymbol{Y})$. In addition, taking into account Equation (4.2), the constitutive formulation can be finally established as

$$\boldsymbol{\sigma}_\mu(\boldsymbol{Y}) = \mathbf{D}^{e,0} : \tilde{\boldsymbol{\varepsilon}}_\mu(\boldsymbol{Y}) + \boldsymbol{\sigma}^*_\mu(\boldsymbol{Y}) + \mathbf{D}^{e,0} : \boldsymbol{\varepsilon}(\boldsymbol{X}). \tag{4.25}$$

Given that the term $\mathbf{D}^{e,0} : \boldsymbol{\varepsilon}(\boldsymbol{X})$ is constant with respect to $\boldsymbol{Y}$, i.e., is a divergence-free term, the micro-scale quasi-static equilibrium problem can then be restated as

$$\mathrm{div}_0\left[\boldsymbol{\sigma}_\mu(\boldsymbol{Y})\right] = \mathbf{0} \quad \text{with} \quad \boldsymbol{\sigma}_\mu(\boldsymbol{Y}) = \mathbf{D}^{e,0}(\boldsymbol{Y}) : \tilde{\boldsymbol{\varepsilon}}_\mu(\boldsymbol{Y}) + \boldsymbol{\sigma}^*_\mu(\boldsymbol{Y}), \quad \forall \boldsymbol{Y} \in \Omega_{\mu,0}, \tag{4.26}$$

having a similar functional format to the auxiliary homogeneous problem previously solved. Attending to Equation (4.15), the micro-scale quasi-static equilibrium problem reads in the frequency and spatial domain, respectively,

$$\check{\boldsymbol{\varepsilon}}_\mu(\boldsymbol{\zeta}) = -\check{\boldsymbol{\Phi}}^0(\boldsymbol{\zeta}) : \check{\boldsymbol{\sigma}}^*_\mu(\boldsymbol{\zeta}), \quad \forall \boldsymbol{\zeta} \neq \mathbf{0}, \quad \check{\boldsymbol{\varepsilon}}_\mu(\mathbf{0}) = \boldsymbol{\varepsilon}(\boldsymbol{X}), \tag{4.27}$$

and

$$\boldsymbol{\varepsilon}_{\mu}(\boldsymbol{Y}) = -\int_{\Omega_{\mu,0}} \boldsymbol{\Phi}^{0}(\boldsymbol{Y}-\boldsymbol{Y}') : \boldsymbol{\sigma}^{*}_{\mu}(\boldsymbol{Y}')\,\mathrm{d}v' + \boldsymbol{\varepsilon}(\boldsymbol{X})\,, \quad \forall\,\boldsymbol{Y}\in\Omega_{\mu,0}\,. \tag{4.28}$$

This nonlinear integral equation can be identified as a Fredholm equation of the second type (Yvonnet, 2012) and has the same functional form as the so-called Lippmann-Schwinger equation of Quantum Mechanical Scattering Theory (Lippmann and Schwinger, 1950). Early applications of the Lippmann-Schwinger nonlinear integral equilibrium equation in the context of elastic mechanical problems are due to Kröner (1971), Dederichs and Zeller (1973) and Zeller and Dederichs (1973), being later shown that it plays a major role on the SCA's formulation.

4.2.2 Finite strains

The derivation of the Lippmann-Schwinger integral equilibrium equation under finite strains is here performed according to a material description. Despite following the same derivation steps, several differences relative to the infinitesimal strains case lead to a rather different Green operator.

Problem formulation

Consider a heterogeneous RVE of domain $\Omega_{\mu,0}$ and boundary $\partial\Omega_{\mu,0}$ in its reference configuration, composed of a given number of perfectly bonded hyperelastic phases. Following the multi-scale kinematic procedures introduced in Chapter 2, consider that a given macro-scale deformation gradient, $\boldsymbol{F}(\boldsymbol{X})$, is prescribed such that

$$\boldsymbol{F}(\boldsymbol{X}) = \frac{1}{v_{\mu,0}}\int_{\Omega_{\mu,0}} \boldsymbol{F}_{\mu}(\boldsymbol{Y})\,\mathrm{d}v\,, \tag{4.29}$$

where $v_{\mu,0}$ denotes the volume of the RVE in the reference configuration, and periodic boundary conditions are assumed. In addition, without any loss of generality, the micro-scale deformation gradient field can be decomposed as (see Section 2.12.2)

$$\boldsymbol{F}_{\mu}(\boldsymbol{Y}) = \boldsymbol{F}(\boldsymbol{X}) + \tilde{\boldsymbol{F}}_{\mu}(\boldsymbol{Y})\,, \tag{4.30}$$

where $\boldsymbol{F}(\boldsymbol{X})$ and $\tilde{\boldsymbol{F}}_{\mu}$ are the average and fluctuation components, respectively.

In the absence of body forces, the micro-scale quasi-static equilibrium problem consists of finding the micro-scale deformation gradient field that satisfies the strong equilibrium equations

$$\mathrm{div}_0\left[\boldsymbol{P}_{\mu}(\boldsymbol{Y})\right] = \boldsymbol{0} \quad \text{with} \quad \boldsymbol{P}_{\mu}(\boldsymbol{Y}) = \boldsymbol{P}_{\mu}(\boldsymbol{F}_{\mu}(\boldsymbol{Y}))\,, \quad \forall\,\boldsymbol{Y}\in\Omega_{\mu,0}\,. \tag{4.31}$$

The auxiliary homogeneous problem

In order to solve the micro-scale equilibrium problem, a suitable eigenstress problem can be formulated by considering a reference (fictitious) homogeneous hyperelastic solid occupying the same region $\Omega_{\mu,0}$ of boundary $\partial\Omega_{\mu,0}$ and characterized by a given tangent modulus $\mathbf{A}^{e,0}$. Note that in this auxiliary homogeneous problem, the fictitious RVE is solely subjected to a prescribed eigenstress field, $\boldsymbol{P}^{*}_{\mu}(\boldsymbol{Y})$, such that the associated micro-scale quasi-static equilibrium problem reads

$$\operatorname{div}_0 [\boldsymbol{P}_\mu(\boldsymbol{Y})] = \boldsymbol{0} \quad \text{with} \quad \boldsymbol{P}_\mu(\boldsymbol{Y}) = \mathbf{A}^{e,0}(\boldsymbol{Y}) : \tilde{\boldsymbol{F}}_\mu(\boldsymbol{Y}) + \boldsymbol{P}^*_\mu(\boldsymbol{Y}), \quad \forall \boldsymbol{Y} \in \Omega_{\mu,0}. \tag{4.32}$$

By performing the suitable Fourier transforms[5],

$$\mathscr{F}\left\{\left(\operatorname{div}_0 [\boldsymbol{P}_\mu(\boldsymbol{Y})]\right)_i\right\} = \mathrm{i}\, \check{P}_{\mu,ij}(\boldsymbol{\zeta})\zeta_j, \tag{4.33}$$

$$\mathscr{F}\left\{P_{\mu,ij}(\boldsymbol{Y})\right\} = \check{P}_{\mu,ij}(\boldsymbol{\zeta}) = \mathrm{i}\, \mathsf{A}^{e,0}_{ijkl}\zeta_l \check{\tilde{u}}_k(\boldsymbol{\zeta}) + \check{P}^*_{\mu,ij}(\boldsymbol{\zeta}), \tag{4.34}$$

the auxiliary micro-scale quasi-static equilibrium problem can be established in the frequency domain as

$$\mathrm{i}\, \check{P}_{\mu,ij}(\boldsymbol{\zeta})\zeta_j = 0 \quad \text{with} \quad \check{P}_{\mu,ij}(\boldsymbol{\zeta}) = \mathrm{i}\, \mathsf{A}^{e,0}_{ijkl}\zeta_l \check{\tilde{u}}_{\mu,k}(\boldsymbol{\zeta}) + \check{P}^*_{\mu,ij}(\boldsymbol{\zeta}). \tag{4.35}$$

After replacing the constitutive relation in the strong equilibrium equation and performing some straightforward algebraic manipulations, it comes

$$\check{K}^0_{ik}(\boldsymbol{\zeta})\, \check{\tilde{u}}_{\mu,k}(\boldsymbol{\zeta}) = \mathrm{i}\, \check{P}^*_{\mu,ij}\zeta_j, \tag{4.36}$$

where $\check{\boldsymbol{K}}^0$ is defined as

$$\check{K}^0_{ik}(\boldsymbol{\zeta}) = \mathsf{A}^{e,0}_{ijkl}\zeta_j\zeta_l. \tag{4.37}$$

From the previous equation, the micro-scale displacement field can be obtained as

$$\check{\tilde{u}}_{\mu,k}(\boldsymbol{\zeta}) = \mathrm{i}\, \check{Q}^0_{ki}(\boldsymbol{\zeta})\, \check{P}^*_{\mu,ij}(\boldsymbol{\zeta})\zeta_j, \tag{4.38}$$

where $\check{\boldsymbol{Q}}^0 = \left(\check{\boldsymbol{K}}^0\right)^{-1}$. The micro-scale deformation gradient field can then be obtained through the material gradient of the micro-scale displacement field as

$$\check{\tilde{F}}_{\mu,kl}(\boldsymbol{\zeta}) = \mathrm{i}\, \zeta_l \check{\tilde{u}}_{\mu,k}(\boldsymbol{\zeta}). \tag{4.39}$$

After substitution of Equation (4.38), the micro-scale strain field can be finally expressed as

$$\check{\tilde{F}}_{\mu,kl}(\boldsymbol{\zeta}) = -\check{\Phi}^0_{klij}(\boldsymbol{\zeta})\, \check{P}^*_{\mu,ij}(\boldsymbol{\zeta}), \tag{4.40}$$

where $\check{\boldsymbol{\Phi}}^0(\boldsymbol{\zeta})$ is the Green operator defined as

$$\check{\Phi}^0_{klij}(\boldsymbol{\zeta}) = \check{Q}^0_{ki}(\boldsymbol{\zeta})\zeta_j\zeta_l. \tag{4.41}$$

The solution to the auxiliary homogeneous equilibrium problem can then be established in the frequency domain as[6]

$$\check{\tilde{\boldsymbol{F}}}_\mu(\boldsymbol{\zeta}) = -\check{\boldsymbol{\Phi}}^0(\boldsymbol{\zeta}) : \check{\boldsymbol{P}}^*_\mu(\boldsymbol{\zeta}), \quad \forall \boldsymbol{\zeta} \neq \boldsymbol{0}, \quad \check{\tilde{\boldsymbol{F}}}_\mu(\boldsymbol{0}) = \boldsymbol{0}. \tag{4.42}$$

[5] Recall that in the finite strain formulation one has $\tilde{\boldsymbol{F}}_\mu(\boldsymbol{Y}) = \nabla_0\, \tilde{\boldsymbol{u}}_\mu(\boldsymbol{Y})$.

[6] Note that the zero frequency term of the micro-scale deformation gradient field, $\check{\tilde{\boldsymbol{F}}}_\mu(\boldsymbol{\zeta} = \boldsymbol{0})$, is associated with its average value on the spatial domain, which in the case of the auxiliary homogeneous equilibrium problem, is null.

Attending to the following inverse Fourier transform,

$$\mathscr{F}^{-1}\left\{\check{\boldsymbol{\Phi}}^0(\boldsymbol{\zeta}) : \check{\boldsymbol{P}}^*_\mu(\boldsymbol{\zeta})\right\} = \int_{\Omega_{\mu,0}} \boldsymbol{\Phi}^0(\boldsymbol{Y}-\boldsymbol{Y}')\,\boldsymbol{P}^*_\mu(\boldsymbol{Y}')\,\mathrm{d}\nu'\,, \tag{4.43}$$

where the volume integration is performed over $\boldsymbol{Y}'$ as denoted by the prime $(\bullet)'$, the solution of the auxiliary homogeneous equilibrium problem is given in the spatial domain by

$$\tilde{\boldsymbol{F}}_\mu(\boldsymbol{Y}) = -\int_{\Omega_{\mu,0}} \boldsymbol{\Phi}^0(\boldsymbol{Y}-\boldsymbol{Y}') : \boldsymbol{P}^*_\mu(\boldsymbol{Y}')\,\mathrm{d}\nu'\,, \quad \forall\,\boldsymbol{Y}\in\Omega_{\mu,0}\,. \tag{4.44}$$

From a physical point of view, it transpires from this solution that the Green operator component $\Phi_{ijkl}(\boldsymbol{Y}-\boldsymbol{Y}')$ represents the deformation gradient $F_{\mu,ij}$ at the point $\boldsymbol{Y}$ due to a unit stress $P^*_{\mu,kl}$ applied at the point $\boldsymbol{Y}'$, thus effectively establishing a strain-stress relationship between two points of the domain.

Green operator under hyperelastic isotropy

Despite having established the solution of the auxiliary homogeneous equilibrium problem in Equation (4.44), it still remains to define the Green operator explicitly. As in the infinitesimal strains case, the Green operator assumes a particularly simple explicit form in the frequency domain under isotropy conditions. Considering the tangent modulus of an isotropic hyperelastic material[7],

$$\mathsf{A}^{e,0}_{ijkl} = \lambda^0\delta_{ij}\delta_{kl} + 2\mu^0\delta_{ik}\delta_{jl}\,, \tag{4.45}$$

where $(\lambda^0,\ \mu^0)$ are the reference material Lamé parameters, substitution on Equation (4.37) yields

$$\check{K}^0_{ik}(\boldsymbol{\zeta}) = \lambda^0\zeta_i\zeta_k + 2\mu^0\|\boldsymbol{\zeta}\|^2\delta_{ik}\,, \tag{4.46}$$

and, after some algebraic manipulations, the inverse of the previous expression leads to

$$\check{Q}^0_{ik} = \left(\check{K}^0_{ik}\right)^{-1} = \frac{1}{2\mu^0\|\boldsymbol{\zeta}\|^2}\left(\delta_{ki} - \frac{\lambda^0}{\lambda^0+2\mu^0}\frac{\zeta_k\zeta_i}{\|\boldsymbol{\zeta}\|^2}\right). \tag{4.47}$$

Finally, the substitution of this result in Equation (4.41) renders

$$\check{\Phi}^0_{klij}(\boldsymbol{\zeta}) = \frac{1}{2\mu^0}\frac{\delta_{ki}\zeta_j\zeta_l}{\|\boldsymbol{\zeta}\|^2} - \frac{\lambda^0}{2\mu^0(\lambda^0+2\mu^0)}\frac{\zeta_k\zeta_l\zeta_i\zeta_j}{\|\boldsymbol{\zeta}\|^4}\,. \tag{4.48}$$

The Lippmann-Schwinger integral equation

Having the solution to the auxiliary homogeneous equilibrium problem at hand, it is now possible to solve the actual micro-scale equilibrium problem. In order to do so, it is convenient to introduce a reference (fictitious) homogeneous hyperelastic material with tangent modulus $\mathbf{A}^{e,0}$ into the constitutive formulation as

$$\boldsymbol{P}_\mu(\boldsymbol{Y}) = \boldsymbol{P}_\mu(\boldsymbol{F}_\mu(\boldsymbol{Y})) + \left(\mathbf{A}^{e,0} - \mathbf{A}^{e,0}\right) : \boldsymbol{F}_\mu(\boldsymbol{Y})\,, \quad \forall\,\boldsymbol{Y}\in\Omega_{\mu,0}\,, \tag{4.49}$$

[7] In contrast with the infinitesimal strain case, note that the nonsymmetrized isotropic elasticity tensor must be considered due to the nonsymmetric nature of both first Piola-Kirchhoff stress and deformation gradient tensors.

which can be rewritten as

$$\boldsymbol{P}_\mu(\boldsymbol{Y}) = \mathbf{A}^{e,0} : \boldsymbol{F}_\mu(\boldsymbol{Y}) + \Big[\boldsymbol{P}_\mu(\boldsymbol{F}_\mu(\boldsymbol{Y})) - \mathbf{A}^{e,0} : \boldsymbol{F}_\mu(\boldsymbol{Y})\Big], \quad \forall \boldsymbol{Y} \in \Omega_{\mu,0}. \tag{4.50}$$

In the first place, it is possible to notice that the last right-hand side term can be regarded as an eigenstress field defined as

$$\boldsymbol{P}^*_\mu(\boldsymbol{Y}) = \boldsymbol{P}_\mu(\boldsymbol{F}_\mu(\boldsymbol{Y})) - \mathbf{A}^{e,0} : \boldsymbol{F}_\mu(\boldsymbol{Y}). \tag{4.51}$$

From a physical point of view, $\boldsymbol{P}^*_\mu(\boldsymbol{Y})$ represents, at each point $\boldsymbol{Y}$, the difference of stress between the actual heterogeneous material and the reference homogeneous material for a given $\boldsymbol{F}_\mu(\boldsymbol{Y})$. In addition, taking into account Equation (4.30), the constitutive formulation can be finally established as

$$\boldsymbol{P}_\mu(\boldsymbol{Y}) = \mathbf{A}^{e,0} : \tilde{\boldsymbol{F}}_\mu(\boldsymbol{Y}) + \boldsymbol{P}^*_\mu(\boldsymbol{Y}) + \mathbf{A}^{e,0} : \boldsymbol{F}(\boldsymbol{X}). \tag{4.52}$$

Given that the term $\mathbf{A}^{e,0} : \boldsymbol{F}(\boldsymbol{X})$ is constant with respect to $\boldsymbol{Y}$, i.e., is a divergence-free term, the micro-scale quasi-static equilibrium problem can then be restated as

$$\mathrm{div}_0\,[\boldsymbol{P}_\mu(\boldsymbol{Y})] = \mathbf{0} \quad \text{with} \quad \boldsymbol{P}_\mu(\boldsymbol{Y}) = \mathbf{A}^{e,0}(\boldsymbol{Y}) : \tilde{\boldsymbol{F}}_\mu(\boldsymbol{Y}) + \boldsymbol{P}^*_\mu(\boldsymbol{Y}), \quad \forall \boldsymbol{Y} \in \Omega_{\mu,0}, \tag{4.53}$$

having a similar functional format to the auxiliary homogeneous problem previously solved. Attending to Equation (4.42), the micro-scale quasi-static equilibrium problem reads in the frequency and spatial domain, respectively,

$$\check{\boldsymbol{F}}_\mu(\boldsymbol{\zeta}) = -\check{\boldsymbol{\Phi}}^0(\boldsymbol{\zeta}) : \check{\boldsymbol{P}}^*_\mu(\boldsymbol{\zeta}), \quad \forall \boldsymbol{\zeta} \neq \mathbf{0}, \quad \check{\boldsymbol{F}}_\mu(\mathbf{0}) = \boldsymbol{F}(\boldsymbol{X}), \tag{4.54}$$

and

$$\boldsymbol{F}_\mu(\boldsymbol{Y}) = -\int_{\Omega_{\mu,0}} \boldsymbol{\Phi}^0(\boldsymbol{Y} - \boldsymbol{Y}') : \boldsymbol{P}^*_\mu(\boldsymbol{Y}')\,\mathrm{d}v' + \boldsymbol{F}(\boldsymbol{X}), \quad \forall \boldsymbol{Y} \in \Omega_{\mu,0}. \tag{4.55}$$

4.3 Clustered Lippmann-Schwinger integral equation

This section establishes one of the main ingredients of the SCA's formulation, the clustered Lippmann-Schwinger integral equation. Here lies the core of the SCA's model reduction approach around which the whole numerical formulation is developed. While the original idea behind the SCA's formulation is completely attributed to Liu and coworkers (Liu et al., 2016), this contribution sheds some light on important theoretical aspects and lays the foundations to propose a new finite strains formulation of the SCA under multiplicative kinematics.

4.3.1 The concept of material cluster

In the solution of the micro-scale equilibrium problem by the Finite Element Method, the continuum RVE domain Ω_μ is discretized in a finite set of n_{elem} subdomains called finite elements, $\Omega^{(e)}_\mu$, $e = 1,2,\ldots,n_{\text{elem}}$. Each finite element is characterized by a given number of nodes and associated shape functions that perform the required field interpolations inside the element domain (see Section 2.9).

In contrast, the SCA method (as well as other CROMs) relies on the discretization of the continuum RVE domain Ω_μ in a finite set of n_c subdomains called material clusters, $\Omega_\mu^{(I)}$, $I = 1,2,\ldots,n_c$. Each material cluster is simply defined as a group of domain points that exhibit similar mechanical behavior. Irrespective of the criterion employed to evaluate such similarity[8], it is important to notice that each material cluster may be arbitrarily shaped and may aggregate points that are not adjacent to each other. In accordance, the different fields are usually assumed uniform within each material cluster domain. Letting $\boldsymbol{a}_\mu(\boldsymbol{Y})$ denote a generic field, the cluster uniform piecewise assumption can be mathematically formulated as

$$\boldsymbol{a}_\mu(\boldsymbol{Y}) = \sum_{I=1}^{n_c} \boldsymbol{a}_\mu^{(I)} \chi^{(I)}(\boldsymbol{Y}), \qquad \chi^{(I)}(\boldsymbol{Y}) = \begin{cases} 1 & \text{if } \boldsymbol{Y} \in \Omega_{\mu,0}^{(I)} \\ 0 & \text{otherwise} \end{cases}, \tag{4.56}$$

where $\boldsymbol{a}_\mu^{(I)}$ is the homogeneous field in the Ith material cluster and $\chi^{(I)}(\boldsymbol{Y})$ is the characteristic function of the Ith material cluster (see Figure 4.1). From this definition, the following equivalence can also be conveniently established,

$$\int_{\Omega_{\mu,0}} \chi^{(I)}(\boldsymbol{Y}) \, [\bullet]_\mu \, \mathrm{d}v = \int_{\Omega_{\mu,0}^{(I)}} [\bullet]_\mu \, \mathrm{d}v. \tag{4.57}$$



Figure 4.1: Schematic of a material cluster, $\Omega_\mu^{(I)}$, within the micro-scale domain, $\Omega_{\mu,0}$, and the associated uniform assumption for a generic field $\boldsymbol{a}_\mu(\boldsymbol{Y})$.

Given that the number of material clusters is usually much lower than the number of finite elements, $n_c \ll n_{\text{elem}}$, the clustering-based domain decomposition materializes the model reduction and leads to a cluster-reduced RVE (CRVE).

4.3.2 Infinitesimal strains

Continuous Lippmann-Schwinger integral equation

Liu and coworkers (Liu et al., 2016) proposed the original SCA's formulation under infinitesimal strains by postulating the continuous Lippmann-Schwinger integral equation as

$$\boldsymbol{\varepsilon}_\mu(\boldsymbol{Y}) = -\int_{\Omega_{\mu,0}} \boldsymbol{\Phi}^0(\boldsymbol{Y} - \boldsymbol{Y}') : \boldsymbol{\sigma}_\mu^*(\boldsymbol{Y}') \, \mathrm{d}v' + \boldsymbol{\varepsilon}_\mu^0, \quad \forall \boldsymbol{Y} \in \Omega_{\mu,0}, \tag{4.58}$$

[8] In the particular case of the SCA's formulation, the mechanical behavior similarity between different domain points is based on the fourth-order local elastic strain concentration tensor (see Appendix C).

that, attending to the definition of the eigenstress field (see Equation (4.24)), can be conveniently expanded as

$$\boldsymbol{\varepsilon}_\mu(\boldsymbol{Y}) = -\int_{\Omega_{\mu,0}} \boldsymbol{\Phi}^0(\boldsymbol{Y}-\boldsymbol{Y}') : \left(\boldsymbol{\sigma}_\mu(\boldsymbol{Y}') - \mathbf{D}^{e,0} : \boldsymbol{\varepsilon}_\mu(\boldsymbol{Y}')\right) \mathrm{d}v' + \boldsymbol{\varepsilon}^0_\mu, \quad \forall \boldsymbol{Y} \in \Omega_{\mu,0}\,. \tag{4.59}$$

Several comments are in order to complement the original publication:

- **Homogeneous far-field strain**. In comparison with Equation (4.28), the homogeneous far-field strain, $\boldsymbol{\varepsilon}^0_\mu$, has been introduced as a replacement for the macro-scale strain tensor, $\boldsymbol{\varepsilon}(\boldsymbol{X})$, and assumed as an additional unknown of the equilibrium problem. Such tensor is here interpreted as a convenient numerical artifact to enforce general macro-scale strain and/or stress tensors formulated through homogenization-based constraints as

$$\frac{1}{v_\mu}\int_{\Omega_{\mu,0}} \boldsymbol{\varepsilon}_\mu(\boldsymbol{Y})\,\mathrm{d}v = \boldsymbol{\varepsilon}(\boldsymbol{X}), \quad \forall \boldsymbol{Y} \in \Omega_{\mu,0}\,, \tag{4.60}$$

  and

$$\frac{1}{v_\mu}\int_{\Omega_{\mu,0}} \boldsymbol{\sigma}_\mu(\boldsymbol{Y})\,\mathrm{d}v = \boldsymbol{\sigma}(\boldsymbol{X}), \quad \forall \boldsymbol{Y} \in \Omega_{\mu,0}\,. \tag{4.61}$$

  It is numerically observed that the homogeneous far-field strain tensor, $\boldsymbol{\varepsilon}^0_\mu$, recovers the macro-scale strain tensor, $\boldsymbol{\varepsilon}(\boldsymbol{X})$, in the most common case of a pure strain homogenization-based constraint. This observation contrasts with the original paper (Liu et al., 2016), where such recovery is presented as a consequence of adopting a self-consistent scheme to set the reference material Lamé parameters. In the more general case of mixed strain and stress constraints, the prescribed macro-scale strain tensor components are numerically recovered as well;

- **Green operator singularity**. It should be noticed that the explicit form of the Green operator derived in Equation (4.21) has a singularity at $\boldsymbol{\zeta} = \mathbf{0}$. Such singularity is circumvented in the FFT-based homogenization basic scheme (Moulinec and Suquet, 1994) (see Appendix B) because the macro-scale strain tensor is directly enforced at the zero frequency of the micro-scale strain field, i.e., $\check{\boldsymbol{\varepsilon}}_\mu(\mathbf{0}) = \boldsymbol{\varepsilon}(\boldsymbol{X})$ (see Equation (4.27)). Given that in the SCA's formulation the macro-scale constraints are explicitly enforced in the spatial domain by Equations (4.60) and (4.61), the zero frequency of the Green operator should be set to zero, i.e., $\check{\boldsymbol{\Phi}}^0(\boldsymbol{\zeta} = \mathbf{0}) = \mathbf{0}$. Such enforcement seems to numerically guarantee that the homogeneous far-field strain tensor, $\boldsymbol{\varepsilon}^0_\mu$, recovers the macro-scale strain tensor, $\boldsymbol{\varepsilon}(\boldsymbol{X})$, as expected from the Lippmann-Schwinger integral equation derived in Equation (4.28);

- **Extension to constitutive nonlinearity**. The derivation of the Lippmann-Schwinger integral equation described in Section 4.2.1 assumed linear elastic phases. The extension to the case where the material phases have a general nonlinear behavior calls for a suitable time discretization of the Lippmann-Schwinger integral equilibrium equation and can be achieved by means of an implicit scheme based on approximated incremental constitutive functions (see Section 2.8). The resulting incremental Lippmann-Schwinger integral equation is established in the following section.

Incremental Lippmann-Schwinger integral equation

Considering the general (pseudo-)time increment $\left[t_m, t_{m+1}\right]$, the incremental Lippmann-Schwinger integral equilibrium equation can be written as

$$\boldsymbol{\varepsilon}_{\mu,m+1}(\boldsymbol{Y}) = -\int_{\Omega_{\mu,0}} \boldsymbol{\Phi}^0(\boldsymbol{Y}-\boldsymbol{Y}') : \left(\hat{\boldsymbol{\sigma}}_{\mu,m+1}(\boldsymbol{Y}') - \mathbf{D}^{e,0} : \boldsymbol{\varepsilon}_{\mu,m+1}(\boldsymbol{Y}')\right) \mathrm{d}v' + \boldsymbol{\varepsilon}^0_{\mu,m+1}, \quad \forall \boldsymbol{Y} \in \Omega_{\mu,0}, \tag{4.62}$$

as well as the macro-scale constraints,

$$\frac{1}{v_\mu}\int_{\Omega_{\mu,0}} \boldsymbol{\varepsilon}_{\mu,m+1}(\boldsymbol{Y})\,\mathrm{d}v = \boldsymbol{\varepsilon}_{m+1}(\boldsymbol{X}), \quad \forall \boldsymbol{Y} \in \Omega_{\mu,0}, \tag{4.63}$$

and

$$\frac{1}{v_\mu}\int_{\Omega_{\mu,0}} \hat{\boldsymbol{\sigma}}_{\mu,m+1}(\boldsymbol{Y})\,\mathrm{d}v = \boldsymbol{\sigma}_{m+1}(\boldsymbol{X}), \quad \forall \boldsymbol{Y} \in \Omega_{\mu,0}, \tag{4.64}$$

where $\hat{\boldsymbol{\sigma}}_\mu$ denotes the incremental constitutive function for the Cauchy stress tensor such that $\boldsymbol{\sigma}_{\mu,m+1} = \hat{\boldsymbol{\sigma}}_\mu(\boldsymbol{\varepsilon}_{\mu,m+1}, \boldsymbol{\beta}_m)$[9].

Furthermore, given the additive nature of the infinitesimal strain tensor,

$$\Delta\boldsymbol{\varepsilon}_{\mu,m+1}(\boldsymbol{Y}) = \boldsymbol{\varepsilon}_{\mu,m+1}(\boldsymbol{Y}) - \boldsymbol{\varepsilon}_{\mu,m}(\boldsymbol{Y}), \tag{4.65}$$

and of the Cauchy stress tensor,

$$\Delta\boldsymbol{\sigma}_{\mu,m+1}(\boldsymbol{Y}) = \boldsymbol{\sigma}_{\mu,m+1}(\boldsymbol{Y}) - \boldsymbol{\sigma}_{\mu,m}(\boldsymbol{Y}), \tag{4.66}$$

it is possible to rewrite the equilibrium formulation having the incremental infinitesimal strain tensor as the primary unknown. Substitution of the right-hand side terms of Equation (4.65) by the corresponding (pseudo-)time Lippmann-Schwinger integral equilibrium equation (Equation (4.62)) and simple algebraic operations[10] yield

$$\begin{aligned}&\Delta\boldsymbol{\varepsilon}_{\mu,m+1}(\boldsymbol{Y}) = \\ &\quad -\int_{\Omega_{\mu,0}} \boldsymbol{\Phi}^0(\boldsymbol{Y}-\boldsymbol{Y}') : \left(\Delta\hat{\boldsymbol{\sigma}}_{\mu,m+1}(\boldsymbol{Y}') - \mathbf{D}^{e,0} : \Delta\boldsymbol{\varepsilon}_{\mu,m+1}(\boldsymbol{Y}')\right) \mathrm{d}v' + \Delta\boldsymbol{\varepsilon}^0_{\mu,m+1}, \quad \forall \boldsymbol{Y} \in \Omega_{\mu,0},\end{aligned} \tag{4.67}$$

with the macro-scale constraints formulated accordingly as

$$\frac{1}{v_\mu}\int_{\Omega_{\mu,0}} \Delta\boldsymbol{\varepsilon}_{\mu,m+1}(\boldsymbol{Y})\,\mathrm{d}v = \Delta\boldsymbol{\varepsilon}_{m+1}(\boldsymbol{X}), \quad \forall \boldsymbol{Y} \in \Omega_{\mu,0}, \tag{4.68}$$

and

[9] The explicit dependence of the Cauchy stress tensor incremental constitutive function, $\hat{\boldsymbol{\sigma}}_\mu$, on the infinitesimal strain tensor, $\boldsymbol{\varepsilon}_{\mu,m+1}$, and on the set of internal variables, $\boldsymbol{\beta}_m$, is often omitted hereafter for the sake of compactness.

[10] Due to the fact that the Lippmann-Schwinger integral equilibrium equation is formulated in the reference configuration, the volume integrals stemming from t_m and t_{m+1} can be conveniently added.

$$\frac{1}{v_\mu}\int_{\Omega_{\mu,0}} \Delta\hat{\boldsymbol{\sigma}}_{\mu,m+1}(\boldsymbol{Y})\,\mathrm{d}v = \Delta\boldsymbol{\sigma}_{m+1}(\boldsymbol{X}), \quad \forall \boldsymbol{Y}\in\Omega_{\mu,0}\,. \tag{4.69}$$

Clustered Lippmann-Schwinger integral equation

In order to formulate the reduced equilibrium problem, the incremental Lippmann-Schwinger integral equation (see Equation (4.62)) can now be averaged over each material cluster I of the CRVE as

$$\frac{1}{v_\mu^{(I)}}\int_{\Omega_{\mu,0}^{(I)}} \boldsymbol{\varepsilon}_{\mu,m+1}(\boldsymbol{Y})\,\mathrm{d}v = -\frac{1}{v_\mu^{(I)}}\int_{\Omega_{\mu,0}^{(I)}}\left[\int_{\Omega_{\mu,0}} \boldsymbol{\Phi}^0(\boldsymbol{Y}-\boldsymbol{Y}'):\right.$$
$$\left.\left(\hat{\boldsymbol{\sigma}}_{\mu,m+1}(\boldsymbol{Y}') - \mathbf{D}^{e,0}:\boldsymbol{\varepsilon}_{\mu,m+1}(\boldsymbol{Y}')\right)\mathrm{d}v'\right]\mathrm{d}v + \frac{1}{v_\mu^{(I)}}\int_{\Omega_{\mu,0}^{(I)}}\boldsymbol{\varepsilon}^0_{\mu,m+1}\,\mathrm{d}v, \quad I=1,2,\ldots,n_\mathrm{c}\,. \tag{4.70}$$

Attending to the relation established in Equation (4.57), the previous equation can be rewritten as

$$\frac{1}{f^{(I)}v_\mu}\int_{\Omega_{\mu,0}} \chi^{(I)}(\boldsymbol{Y})\boldsymbol{\varepsilon}_{\mu,m+1}(\boldsymbol{Y})\,\mathrm{d}v = -\frac{1}{f^{(I)}v_\mu}\int_{\Omega_{\mu,0}}\left[\int_{\Omega_{\mu,0}} \chi^{(I)}(\boldsymbol{Y})\,\boldsymbol{\Phi}^0(\boldsymbol{Y}-\boldsymbol{Y}'):\right.$$
$$\left.\left(\hat{\boldsymbol{\sigma}}_{\mu,m+1}(\boldsymbol{Y}') - \mathbf{D}^{e,0}:\boldsymbol{\varepsilon}_{\mu,m+1}(\boldsymbol{Y}')\right)\mathrm{d}v'\right]\mathrm{d}v + \boldsymbol{\varepsilon}^0_{\mu,m+1}, \quad I=1,2,\ldots,n_\mathrm{c}, \tag{4.71}$$

where $f^{(I)}$ denotes the volume fraction of the Ith cluster,

$$f^{(I)} = \frac{v_\mu^{(I)}}{v_\mu}\,. \tag{4.72}$$

In addition, the cluster piecewise uniform assumption established in Equation (4.56) yields

$$\boldsymbol{\varepsilon}_{\mu,m+1}(\boldsymbol{Y}') = \sum_{J=1}^{n_\mathrm{c}} \chi^{(J)}(\boldsymbol{Y}')\,\boldsymbol{\varepsilon}^{(J)}_{\mu,m+1}\,, \tag{4.73}$$

$$\boldsymbol{\sigma}_{\mu,m+1}(\boldsymbol{Y}') = \sum_{J=1}^{n_\mathrm{c}} \chi^{(J)}(\boldsymbol{Y}')\,\boldsymbol{\sigma}^{(J)}_{\mu,m+1}\,, \tag{4.74}$$

which after substitution in Equation (4.71) renders

$$\frac{1}{f^{(I)}v_\mu}\int_{\Omega_{\mu,0}} \chi^{(I)}(\boldsymbol{Y})\boldsymbol{\varepsilon}_{\mu,m+1}(\boldsymbol{Y})\,\mathrm{d}v = -\frac{1}{f^{(I)}v_\mu}\int_{\Omega_{\mu,0}}\left[\int_{\Omega_{\mu,0}} \chi^{(I)}(\boldsymbol{Y})\,\boldsymbol{\Phi}^0(\boldsymbol{Y}-\boldsymbol{Y}'):\right.$$
$$\left.\left[\sum_{J=1}^{n_\mathrm{c}}\chi^{(J)}(\boldsymbol{Y}')\left(\hat{\boldsymbol{\sigma}}^{(J)}_{\mu,m+1} - \mathbf{D}^{e,0}:\boldsymbol{\varepsilon}^{(J)}_{\mu,m+1}\right)\right]\mathrm{d}v'\right]\mathrm{d}v + \boldsymbol{\varepsilon}^0_{\mu,m+1}, \quad I=1,2,\ldots,n_\mathrm{c}\,. \tag{4.75}$$

Finally, by performing some rearrangements and noticing that the first term is actually the homogeneous incremental strain in the Ith cluster,

$$\frac{1}{f^{(I)}v_\mu}\int_{\Omega_{\mu,0}} \chi^{(I)}(\boldsymbol{Y})\,\boldsymbol{\varepsilon}_{\mu,m+1}(\boldsymbol{Y})\,\mathrm{d}v = \boldsymbol{\varepsilon}^{(I)}_{\mu,m+1}, \quad I=1,2,\ldots,n_\mathrm{c}\,, \tag{4.76}$$

the clustered incremental Lippmann-Schwinger integral equilibrium equation can be written as

$$\boldsymbol{\varepsilon}^{(I)}_{\mu,m+1} = -\sum_{J=1}^{n_c}\left(\frac{1}{f^{(I)}v_\mu}\int_{\Omega_{\mu,0}}\int_{\Omega_{\mu,0}}\chi^{(I)}(\boldsymbol{Y})\chi^{(J)}(\boldsymbol{Y}')\boldsymbol{\Phi}^0(\boldsymbol{Y}-\boldsymbol{Y}')\,\mathrm{d}v'\,\mathrm{d}v\right): \left(\hat{\boldsymbol{\sigma}}^{(J)}_{\mu,m+1} - \mathbf{D}^{e,0}:\boldsymbol{\varepsilon}^{(J)}_{\mu,m+1}\right) + \boldsymbol{\varepsilon}^0_{\mu,m+1}, \quad I=1,2,\ldots,n_c, \tag{4.77}$$

or in a more compact way as

$$\boldsymbol{\varepsilon}^{(I)}_{\mu,m+1} = -\sum_{J=1}^{n_c}\mathbf{T}^{(I)(J)}:\left(\hat{\boldsymbol{\sigma}}^{(J)}_{\mu,m+1} - \mathbf{D}^{e,0}:\boldsymbol{\varepsilon}^{(J)}_{\mu,m+1}\right) + \boldsymbol{\varepsilon}^0_{\mu,m+1}, \quad I=1,2,\ldots,n_c, \tag{4.78}$$

where the so-called cluster interaction tensors are defined as

$$\mathbf{T}^{(I)(J)} = \frac{1}{f^{(I)}v_\mu}\int_{\Omega_{\mu,0}}\int_{\Omega_{\mu,0}}\chi^{(I)}(\boldsymbol{Y})\,\chi^{(J)}(\boldsymbol{Y}')\,\boldsymbol{\Phi}^0(\boldsymbol{Y}-\boldsymbol{Y}')\,\mathrm{d}v'\mathrm{d}v, \quad I,J=1,2,\ldots,n_c. \tag{4.79}$$

Recalling the physical meaning of the reference homogeneous material Green operator introduced in Section 4.2.1, it transpires from the previous definition that the fourth-order interaction tensor $\mathbf{T}^{(I)(J)}$ physically represents the influence of the stress in the Jth cluster on the strain in the Ith cluster, i.e., describes the strain-stress interaction between clusters I and J.

Concerning the discretization of the macro-scale constraints (Equations (4.63) and (4.64)), substitution of Equations (4.73) and (4.74), and the use of the cluster piecewise uniform assumption (see Equation (4.57)) yields

$$\sum_{I=1}^{n_c} f^{(I)}\boldsymbol{\varepsilon}^{(I)}_{\mu,m+1} = \boldsymbol{\varepsilon}_{m+1}(\boldsymbol{X}), \tag{4.80}$$

and

$$\sum_{I=1}^{n_c} f^{(I)}\hat{\boldsymbol{\sigma}}^{(I)}_{\mu,m+1} = \boldsymbol{\sigma}_{m+1}(\boldsymbol{X}). \tag{4.81}$$

In summary, collecting Equations (4.78), (4.80) and (4.81), the reduced micro-scale equilibrium problem consists of the solution of a system of nonlinear equations composed of (i) n_c clustered Lippmann-Schwinger integral equilibrium equations and (ii) macro-scale strain and/or stress constraints. The clustered Lippmann-Schwinger system of equilibrium equations can then be established as

$$
\begin{cases}
\boldsymbol{\varepsilon}^{(1)}_{\mu,m+1} = -\sum_{J=1}^{n_c} \mathbf{T}^{(1)(J)} : \left(\hat{\boldsymbol{\sigma}}^{(J)}_{\mu,m+1}\left(\boldsymbol{\varepsilon}^{(J)}_{\mu,m+1}, \boldsymbol{\beta}_m\right) - \mathbf{D}^{e,0} : \boldsymbol{\varepsilon}^{(J)}_{\mu,m+1} \right) + \boldsymbol{\varepsilon}^{0}_{\mu,m+1}, \\
\boldsymbol{\varepsilon}^{(2)}_{\mu,m+1} = -\sum_{J=1}^{n_c} \mathbf{T}^{(2)(J)} : \left(\hat{\boldsymbol{\sigma}}^{(J)}_{\mu,m+1}\left(\boldsymbol{\varepsilon}^{(J)}_{\mu,m+1}, \boldsymbol{\beta}_m\right) - \mathbf{D}^{e,0} : \boldsymbol{\varepsilon}^{(J)}_{\mu,m+1} \right) + \boldsymbol{\varepsilon}^{0}_{\mu,m+1}, \\
\vdots \\
\boldsymbol{\varepsilon}^{(n_c)}_{\mu,m+1} = -\sum_{J=1}^{n_c} \mathbf{T}^{(n_c)(J)} : \left(\hat{\boldsymbol{\sigma}}^{(J)}_{\mu,m+1}\left(\boldsymbol{\varepsilon}^{(J)}_{\mu,m+1}, \boldsymbol{\beta}_m\right) - \mathbf{D}^{e,0} : \boldsymbol{\varepsilon}^{(J)}_{\mu,m+1} \right) + \boldsymbol{\varepsilon}^{0}_{\mu,n+1}, \\
\sum_{I=1}^{n_c} f^{(I)} \boldsymbol{\varepsilon}^{(I)}_{\mu,m+1} = \boldsymbol{\varepsilon}_{m+1}(\boldsymbol{X}) \quad ; \quad \sum_{I=1}^{n_c} f^{(I)} \hat{\boldsymbol{\sigma}}^{(I)}_{\mu,m+1}\left(\boldsymbol{\varepsilon}^{(I)}_{\mu,m+1}, \boldsymbol{\beta}_m\right) = \boldsymbol{\sigma}_{m+1}(\boldsymbol{X}),
\end{cases}
\tag{4.82}
$$

and must be solved for the unknowns

$$
\boldsymbol{\varepsilon}_{\mu,m+1} = \left\{ \boldsymbol{\varepsilon}^{(1)}_{\mu,m+1}, \boldsymbol{\varepsilon}^{(2)}_{\mu,m+1}, \ldots, \boldsymbol{\varepsilon}^{(n_c)}_{\mu,m+1}, \boldsymbol{\varepsilon}^{0}_{\mu,m+1} \right\}. \tag{4.83}
$$

By performing the same steps over the additive formulation established in Equations (4.67), (4.68) and (4.69), the clustered incremental Lippmann-Schwinger integral equilibrium equation and the macro-scale constraints come

$$
\Delta\boldsymbol{\varepsilon}^{(I)}_{\mu,m+1} = -\sum_{J=1}^{n_c} \mathbf{T}^{(I)(J)} : \left(\Delta\hat{\boldsymbol{\sigma}}^{(J)}_{\mu,m+1} - \mathbf{D}^{e,0} : \Delta\boldsymbol{\varepsilon}^{(J)}_{\mu,m+1} \right) + \Delta\boldsymbol{\varepsilon}^{0}_{\mu,m+1}, \quad I = 1,2,\ldots,n_c, \tag{4.84}
$$

$$
\sum_{I=1}^{n_c} f^{(I)} \Delta\boldsymbol{\varepsilon}^{(I)}_{\mu,m+1} = \Delta\boldsymbol{\varepsilon}_{m+1}(\boldsymbol{X}), \tag{4.85}
$$

and

$$
\sum_{I=1}^{n_c} f^{(I)} \Delta\hat{\boldsymbol{\sigma}}^{(I)}_{\mu,m+1} = \Delta\boldsymbol{\sigma}_{m+1}(\boldsymbol{X}). \tag{4.86}
$$

For the sake of completeness, the corresponding clustered Lippmann-Schwinger system of equilibrium equations can then be alternatively established as

$$
\begin{cases}
\Delta\boldsymbol{\varepsilon}^{(1)}_{\mu,m+1} = -\sum_{J=1}^{n_c} \mathbf{T}^{(1)(J)} : \left(\Delta\hat{\boldsymbol{\sigma}}^{(J)}_{\mu,m+1}\left(\Delta\boldsymbol{\varepsilon}^{(J)}_{\mu,m+1}, \boldsymbol{\beta}_m\right) - \mathbf{D}^{e,0} : \Delta\boldsymbol{\varepsilon}^{(J)}_{\mu,m+1} \right) + \Delta\boldsymbol{\varepsilon}^{0}_{\mu,m+1}, \\
\Delta\boldsymbol{\varepsilon}^{(2)}_{\mu,m+1} = -\sum_{J=1}^{n_c} \mathbf{T}^{(2)(J)} : \left(\Delta\hat{\boldsymbol{\sigma}}^{(J)}_{\mu,m+1}\left(\Delta\boldsymbol{\varepsilon}^{(J)}_{\mu,m+1}, \boldsymbol{\beta}_m\right) - \mathbf{D}^{e,0} : \Delta\boldsymbol{\varepsilon}^{(J)}_{\mu,m+1} \right) + \Delta\boldsymbol{\varepsilon}^{0}_{\mu,m+1}, \\
\vdots \\
\Delta\boldsymbol{\varepsilon}^{(n_c)}_{\mu,m+1} = -\sum_{J=1}^{n_c} \mathbf{T}^{(n_c)(J)} : \left(\Delta\hat{\boldsymbol{\sigma}}^{(J)}_{\mu,m+1}\left(\Delta\boldsymbol{\varepsilon}^{(J)}_{\mu,m+1}, \boldsymbol{\beta}_m\right) - \mathbf{D}^{e,0} : \Delta\boldsymbol{\varepsilon}^{(J)}_{\mu,m+1} \right) + \Delta\boldsymbol{\varepsilon}^{0}_{\mu,n+1}, \\
\sum_{I=1}^{n_c} f^{(I)} \Delta\boldsymbol{\varepsilon}^{(I)}_{\mu,m+1} = \Delta\boldsymbol{\varepsilon}_{m+1}(\boldsymbol{X}) \quad ; \quad \sum_{I=1}^{n_c} f^{(I)} \Delta\hat{\boldsymbol{\sigma}}^{(I)}_{\mu,m+1}\left(\Delta\boldsymbol{\varepsilon}^{(I)}_{\mu,m+1}, \boldsymbol{\beta}_m\right) = \Delta\boldsymbol{\sigma}_{m+1}(\boldsymbol{X}),
\end{cases}
\tag{4.87}
$$

and must be then solved for the unknowns

$$\Delta\boldsymbol{\varepsilon}_{\mu,m+1} = \left\{\Delta\boldsymbol{\varepsilon}^{(1)}_{\mu,m+1}, \Delta\boldsymbol{\varepsilon}^{(2)}_{\mu,m+1}, \ldots, \Delta\boldsymbol{\varepsilon}^{(n_c)}_{\mu,m+1}, \Delta\boldsymbol{\varepsilon}^{0}_{\mu,m+1}\right\}. \tag{4.88}$$

Incremental reference homogeneous material properties

In order to derive the Lippmann-Schwinger integral equation in Section 4.2.1, a reference (fictitious) homogeneous linear elastic material is conveniently introduced into the constitutive formulation. In addition, this reference material is assumed isotropic (see Equation (4.18)) so that a closed-form of the Green operator can be derived in the frequency domain. However, it should be noticed that so far, (i) the reference material Lamé parameters, (λ^0, μ^0), have been assumed constant throughout the deformation path and (ii) a suitable choice of such parameters has not been discussed yet.

As pointed out by Liu and coworkers (Liu et al., 2016) and recently addressed by Schneider (Schneider, 2019), the solution of the continuous Lippmann-Schwinger integral equilibrium equation does not depend on the choice of the reference material Lamé parameters. Nonetheless, it should be remarked that such a choice plays a major role in the convergence rate of several FFT-based homogenization methods and has been a topic of extensive research over the last years. In contrast, and most importantly, the solution of the clustered Lippmann-Schwinger integral equilibrium equation does actually depend on the reference material's properties (Liu et al. (2016), Schneider (2019)). Despite the recent progress in understanding polarization schemes popular in FFT-based homogenization methods, the mathematical quantification of such dependency still remains an open and crucial challenge to the best of the author's knowledge.

Although not addressing this mathematical quantification, Liu and coworkers (Liu et al., 2016) propose a well-known self-consistent micromechanical approach (see Appendix A) to find an 'optimal' choice of the reference material Lamé parameters (see details in Appendix C). As in the self-consistent method of classical micromechanics, the idea consists of setting, at each instant t_m, the homogeneous tangent modulus of the reference material, $\mathbf{D}^{e,0}_m$, that best approximates the effective tangent modulus of the CRVE, $\overline{\mathbf{D}}_m$. Rather than discussing the effectiveness of such a strategy at this point, the aim here is instead to evaluate the impact of an incremental update of the reference homogeneous material properties in the previous derivations.

In the first place, it is important to clearly identify the actual mathematical sources of influence of the reference material's properties on the incremental Lippmann-Schwinger integral equilibrium equation (see Equation (4.62)): (1) the Green operator (see Equation (4.21)); and (2) the polarization stress, $\boldsymbol{\sigma}^*_\mu$, by means of the reference material homogeneous tangent modulus, $\mathbf{D}^{e,0}$ (see Equation (4.18)). Note that these sources are later transferred to the clustered Lippmann-Schwinger integral equilibrium equation (see Equation (4.78)) by means of the cluster interaction tensors, $\mathbf{T}^{(I)(J)}$, and the cluster polarization stress, $(\boldsymbol{\sigma}^*_\mu)^{(J)}$, respectively.

With this in mind, the incremental Lippmann-Schwinger integral equilibrium equation can now be written as

$$\boldsymbol{\varepsilon}_{\mu,m+1}(\boldsymbol{Y}) = -\int_{\Omega_{\mu,0}} \boldsymbol{\Phi}^0_{m+1}(\boldsymbol{Y}-\boldsymbol{Y}') : \left(\hat{\boldsymbol{\sigma}}_{\mu,m+1}(\boldsymbol{Y}') - \mathbf{D}^{e,0}_{m+1} : \boldsymbol{\varepsilon}_{\mu,m+1}(\boldsymbol{Y}')\right) \mathrm{d}v' + \boldsymbol{\varepsilon}^0_{\mu,m+1}, \quad \forall \boldsymbol{Y} \in \Omega_{\mu,0}, \tag{4.89}$$

where the subscript $(\bullet)_{m+1}$ has been included in the identified sources to denote the incremental

nature of the reference material's properties, and its clustered counterpart as

$$\boldsymbol{\varepsilon}^{(I)}_{\mu,m+1} = -\sum_{J=1}^{n_\mathrm{c}} \mathbf{T}^{(I)(J)}_{m+1} : \left(\hat{\boldsymbol{\sigma}}^{(J)}_{\mu,m+1} - \mathbf{D}^{e,0}_{m+1} : \boldsymbol{\varepsilon}^{(J)}_{\mu,m+1}\right) + \boldsymbol{\varepsilon}^{0}_{\mu,m+1}, \quad I = 1,2,\ldots,n_\mathrm{c}. \tag{4.90}$$

Given the additive nature of the infinitesimal strain tensor and the Cauchy stress tensor (see Equations (4.65) and (4.66)), the additive incremental Lippmann-Schwinger integral equilibrium equation comes

$$\begin{aligned}\Delta\boldsymbol{\varepsilon}_{\mu,m+1}(\boldsymbol{Y}) = &-\int_{\Omega_{\mu,0}} \boldsymbol{\Phi}^0_{m+1}(\boldsymbol{Y}-\boldsymbol{Y}') : \left(\Delta\hat{\boldsymbol{\sigma}}_{\mu,m+1}(\boldsymbol{Y}') - \mathbf{D}^{e,0}_{m+1} : \Delta\boldsymbol{\varepsilon}_{\mu,m+1}(\boldsymbol{Y}')\right) \mathrm{d}v' + \Delta\boldsymbol{\varepsilon}^0_{\mu,m+1} \\ &-\int_{\Omega_{\mu,0}} \left(\boldsymbol{\Phi}^0_{m+1}(\boldsymbol{Y}-\boldsymbol{Y}') - \boldsymbol{\Phi}^0_{m}(\boldsymbol{Y}-\boldsymbol{Y}')\right) : \hat{\boldsymbol{\sigma}}_{\mu,m}(\boldsymbol{Y}') \\ &-\left(\boldsymbol{\Phi}^0_{m+1}(\boldsymbol{Y}-\boldsymbol{Y}') : \mathbf{D}^{e,0}_{m+1} - \boldsymbol{\Phi}^0_{m}(\boldsymbol{Y}-\boldsymbol{Y}') : \mathbf{D}^{e,0}_{m}\right) : \boldsymbol{\varepsilon}_{\mu,m}(\boldsymbol{Y}')\,\mathrm{d}v', \quad \forall \boldsymbol{Y} \in \Omega_{\mu,0}.\end{aligned} \tag{4.91}$$

The comparison between this result and the previously derived Equation (4.67) reveals an additional term intrinsically related to the incremental update of the reference material's properties. In the particular case of a constant reference material throughout the deformation path, i.e., $\boldsymbol{\Phi}^0 = \boldsymbol{\Phi}^0_{m+1} = \boldsymbol{\Phi}^0_m$ and $\mathbf{D}^{e,0} = \mathbf{D}^{e,0}_{m+1} = \mathbf{D}^{e,0}_m$, Equation (4.67) is recovered as expected. Moreover, by performing the same cluster averaging procedures that led to Equation (4.78), the clustered incremental Lippmann-Schwinger integral equilibrium equation comes

$$\begin{aligned}\Delta\boldsymbol{\varepsilon}^{(I)}_{\mu,m+1} = &-\sum_{J=1}^{n_\mathrm{c}} \mathbf{T}^{(I)(J)}_{m+1} : \left(\Delta\hat{\boldsymbol{\sigma}}^{(J)}_{\mu,m+1} - \mathbf{D}^{e,0}_{m+1} : \Delta\boldsymbol{\varepsilon}^{(J)}_{\mu,m+1}\right) + \Delta\boldsymbol{\varepsilon}^{0}_{\mu,m+1} \\ &+\sum_{J=1}^{n_\mathrm{c}} \mathbf{T}^{(I)(J)}_{m+1} : \left(\hat{\boldsymbol{\sigma}}^{(J)}_{\mu,m} - \mathbf{D}^{e,0}_{m+1} : \boldsymbol{\varepsilon}^{(J)}_{\mu,m}\right) \\ &-\sum_{J=1}^{n_\mathrm{c}} \mathbf{T}^{(I)(J)}_{m} : \left(\hat{\boldsymbol{\sigma}}^{(J)}_{\mu,m} - \mathbf{D}^{e,0}_{m} : \boldsymbol{\varepsilon}^{(J)}_{\mu,m}\right), \quad I = 1,2,\ldots,n_\mathrm{c}.\end{aligned} \tag{4.92}$$

Remark.
Despite adopting a self-consistent scheme to perform the incremental update of the reference material Lamé parameters, Liu and coworkers (Liu et al., 2016) neglected such additional terms and formulated the clustered Lippmann-Schwinger system of equilibrium equations given by Equations (4.84)-(4.88) *(see Appendix C). Nonetheless, provided a smooth evolution of the reference material's properties and a sufficiently refined incrementation, it is expected that the magnitude of the additional terms is small in comparison with the remaining terms.*

4.3.3 Finite strains

Continuous Lippmann-Schwinger integral equation

Following the formulation by Liu and coworkers (Liu et al., 2016), the continuous Lippmann-Schwinger integral equation under finite strains can be formulated as

$$\boldsymbol{F}_\mu(\boldsymbol{Y}) = -\int_{\Omega_{\mu,0}} \boldsymbol{\Phi}^0(\boldsymbol{Y}-\boldsymbol{Y}') : \left(\boldsymbol{P}_\mu(\boldsymbol{Y}') - \mathbf{A}^{e,0} : \boldsymbol{F}_\mu(\boldsymbol{Y}')\right) \mathrm{d}v' + \boldsymbol{F}^0_\mu, \quad \forall \boldsymbol{Y} \in \Omega_{\mu,0}, \tag{4.93}$$

where $\boldsymbol{F}_{\mu}^{0}$ denotes the homogeneous far-field deformation gradient. The same comments established in Section 4.3.2 hold under finite strains as well, provided that the strain and stress tensors are instead taken as the deformation gradient and the first Piola-Kirchhoff stress tensor, respectively.

Incremental Lippmann-Schwinger integral equation

Considering the general (pseudo-)time increment $\left[t_m\,,\,t_{m+1}\right]$, the incremental Lippmann-Schwinger integral equilibrium equation can be written as

$$\boldsymbol{F}_{\mu,\,m+1}(\boldsymbol{Y}) = -\int_{\Omega_{\mu,0}} \boldsymbol{\Phi}^{0}(\boldsymbol{Y}-\boldsymbol{Y}') : \left(\hat{\boldsymbol{P}}_{\mu,\,m+1}(\boldsymbol{Y}') - \mathbf{A}^{e,0} : \boldsymbol{F}_{\mu,\,m+1}(\boldsymbol{Y}')\right) \mathrm{d}v' + \boldsymbol{F}_{\mu,\,m+1}^{0}\,, \quad \forall\, \boldsymbol{Y} \in \Omega_{\mu,0}\,, \tag{4.94}$$

as well as the macro-scale constraints,

$$\frac{1}{v_{\mu}} \int_{\Omega_{\mu,0}} \boldsymbol{F}_{\mu,\,m+1}(\boldsymbol{Y})\, \mathrm{d}v = \boldsymbol{F}_{m+1}(\boldsymbol{X})\,, \quad \forall\, \boldsymbol{Y} \in \Omega_{\mu,0}\,, \tag{4.95}$$

and

$$\frac{1}{v_{\mu}} \int_{\Omega_{\mu,0}} \hat{\boldsymbol{P}}_{\mu,\,m+1}(\boldsymbol{Y})\, \mathrm{d}v = \boldsymbol{P}_{m+1}(\boldsymbol{X})\,, \quad \forall\, \boldsymbol{Y} \in \Omega_{\mu,0}\,, \tag{4.96}$$

where $\hat{\boldsymbol{P}}_{\mu}$ denotes the incremental constitutive function for the first Piola-Kirchhoff stress tensor such that $\boldsymbol{P}_{\mu,\,m+1} = \hat{\boldsymbol{P}}_{\mu}(\boldsymbol{F}_{\mu,\,m+1}, \boldsymbol{\beta}_{m})$[11].

Despite the additive nature of the first Piola-Kirchhoff stress tensor,

$$\Delta\boldsymbol{P}_{\mu,\,m+1}(\boldsymbol{Y}) = \boldsymbol{P}_{\mu,\,m+1}(\boldsymbol{Y}) - \boldsymbol{P}_{\mu,\,m}(\boldsymbol{Y})\,, \tag{4.97}$$

the multiplicative nature of the deformation gradient,

$$\left(\boldsymbol{F}_{\Delta}\right)_{\mu,m+1}(\boldsymbol{Y}) = \boldsymbol{F}_{\mu,m+1}(\boldsymbol{Y}) \left(\boldsymbol{F}_{\mu,m}(\boldsymbol{Y})\right)^{-1}\,, \tag{4.98}$$

contrasts with the infinitesimal strains case. Given the mathematically challenging analytical inversion of the incremental Lippmann-Schwinger integral equation (see Equation (4.95)), rewriting the equilibrium formulation having the incremental deformation gradient tensor as the primary unknown is not straightforward.

Clustered Lippmann-Schwinger integral equation

By performing the same cluster averaging procedures described in the infinitesimal strain case, the clustered incremental Lippmann-Schwinger integral equilibrium equation can be written under finite strains as

$$\boldsymbol{F}_{\mu,\,m+1}^{(I)} = -\sum_{J=1}^{n_{\mathrm{c}}} \mathbf{T}^{(I)(J)} : \left(\hat{\boldsymbol{P}}_{\mu,\,m+1}^{(J)} - \mathbf{A}^{e,0} : \boldsymbol{F}_{\mu,\,m+1}^{(J)}\right) + \boldsymbol{F}_{\mu,\,m+1}^{0}\,, \quad I = 1,2,\ldots,n_{\mathrm{c}}\,, \tag{4.99}$$

[11] The explicit dependence of the Cauchy stress tensor incremental constitutive function, $\hat{\boldsymbol{P}}_{\mu}$, on the deformation gradient tensor, $\boldsymbol{F}_{\mu,\,m+1}$, and on the set of internal variables, $\boldsymbol{\beta}_{m}$, is often omitted hereafter for the sake of compactness.

where the cluster interaction tensors are similarly defined as

$$\mathbf{T}^{(I)(J)} = \frac{1}{f^{(I)} v_\mu} \int_{\Omega_{\mu,0}} \int_{\Omega_{\mu,0}} \chi^{(I)}(\boldsymbol{Y}) \, \chi^{(J)}(\boldsymbol{Y}') \, \boldsymbol{\Phi}^0(\boldsymbol{Y} - \boldsymbol{Y}') \, \mathrm{d}v' \mathrm{d}v \,, \quad I, J = 1, 2, \ldots, n_\mathrm{c} \,. \tag{4.100}$$

Proceeding analogously to the infinitesimal strain case, the discretization of the macro-scale constraints (Equations (4.95) and (4.96)) yields

$$\sum_{I=1}^{n_\mathrm{c}} f^{(I)} \boldsymbol{F}^{(I)}_{\mu,m+1} = \boldsymbol{F}_{m+1}(\boldsymbol{X}) \,, \tag{4.101}$$

and

$$\sum_{I=1}^{n_\mathrm{c}} f^{(I)} \hat{\boldsymbol{P}}^{(I)}_{\mu,m+1} = \boldsymbol{P}_{m+1}(\boldsymbol{X}) \,. \tag{4.102}$$

In summary, collecting Equations (4.99), (4.101) and (4.102), the reduced micro-scale equilibrium problem consists of the solution of a system of nonlinear equations composed of (i) n_c clustered Lippmann-Schwinger integral equilibrium equations and (ii) macro-scale strain and/or stress constraints. The clustered Lippmann-Schwinger system of equilibrium equations can then be established as

$$\begin{cases} \boldsymbol{F}^{(1)}_{\mu,m+1} = -\sum_{J=1}^{n_\mathrm{c}} \mathbf{T}^{(1)(J)} : \left(\hat{\boldsymbol{P}}^{(J)}_{\mu,m+1} \left(\boldsymbol{F}^{(J)}_{\mu,m+1}, \boldsymbol{\beta}_m \right) - \mathbf{A}^{e,0} : \boldsymbol{F}^{(J)}_{\mu,m+1} \right) + \boldsymbol{F}^0_{\mu,m+1} \,, \\ \boldsymbol{F}^{(2)}_{\mu,m+1} = -\sum_{J=1}^{n_\mathrm{c}} \mathbf{T}^{(2)(J)} : \left(\hat{\boldsymbol{P}}^{(J)}_{\mu,m+1} \left(\boldsymbol{F}^{(J)}_{\mu,m+1}, \boldsymbol{\beta}_m \right) - \mathbf{A}^{e,0} : \boldsymbol{F}^{(J)}_{\mu,m+1} \right) + \boldsymbol{F}^0_{\mu,m+1} \,, \\ \qquad\qquad \vdots \\ \boldsymbol{F}^{(n_c)}_{\mu,m+1} = -\sum_{J=1}^{n_\mathrm{c}} \mathbf{T}^{(n_\mathrm{c})(J)} : \left(\hat{\boldsymbol{P}}^{(J)}_{\mu,m+1} \left(\boldsymbol{F}^{(J)}_{\mu,m+1}, \boldsymbol{\beta}_m \right) - \mathbf{A}^{e,0} : \boldsymbol{F}^{(J)}_{\mu,m+1} \right) + \boldsymbol{F}^0_{\mu,n+1} \,, \\ \sum_{I=1}^{n_\mathrm{c}} f^{(I)} \boldsymbol{F}^{(I)}_{\mu,m+1} = \boldsymbol{F}_{m+1}(\boldsymbol{X}) \quad ; \quad \sum_{I=1}^{n_\mathrm{c}} f^{(I)} \hat{\boldsymbol{P}}^{(I)}_{\mu,m+1} \left(\boldsymbol{F}^{(I)}_{\mu,m+1}, \boldsymbol{\beta}_m \right) = \boldsymbol{P}_{m+1}(\boldsymbol{X}) \,, \end{cases} \tag{4.103}$$

and must be solved for the unknowns

$$\boldsymbol{F}_{\mu,m+1} = \left\{ \boldsymbol{F}^{(1)}_{\mu,m+1}, \boldsymbol{F}^{(2)}_{\mu,m+1}, \ldots, \boldsymbol{F}^{(n_\mathrm{c})}_{\mu,m+1}, \boldsymbol{F}^0_{\mu,m+1} \right\} . \tag{4.104}$$

Due to the unresolved expansion of Equation (4.98), it is not possible to derive the corresponding clustered incremental Lippmann-Schwinger integral equilibrium equation and the clustered Lippmann-Schwinger system of equilibrium equations.

Remark.
In their contribution, Yu and coworkers (Yu et al., 2019) establish the clustered incremental Lippmann-Schwinger integral equilibrium equation by assuming an additive decomposition of the deformation gradient. Irrespective of the physical meaning of such an assumption, it leads to a clustered Lippmann-Schwinger system of equilibrium equations similar to the infinitesimal strain case (see Equations (4.84)-(4.88)*).*

Incremental reference homogeneous material properties

The main aspects previously discussed concerning the influence and the incremental update of the reference homogeneous material properties held under finite strains.

The incremental Lippmann-Schwinger integral equilibrium equation can then be written as

$$\boldsymbol{F}_{\mu,m+1}(\boldsymbol{Y}) = -\int_{\Omega_{\mu,0}} \boldsymbol{\Phi}^0_{m+1}(\boldsymbol{Y}-\boldsymbol{Y}') : \left(\hat{\boldsymbol{P}}_{\mu,m+1}(\boldsymbol{Y}') - \mathbf{A}^{e,0}_{m+1} : \boldsymbol{F}_{\mu,m+1}(\boldsymbol{Y}')\right) \mathrm{d}v' + \boldsymbol{F}^0_{\mu,m+1}\,, \quad \forall \boldsymbol{Y} \in \Omega_{\mu,0}\,, \tag{4.105}$$

where the subscript $(\bullet)_{m+1}$ is again included to denote the incremental nature of the reference material's properties, and its clustered counterpart as

$$\boldsymbol{F}^{(I)}_{\mu,m+1} = -\sum_{J=1}^{n_\mathrm{c}} \mathbf{T}^{(I)(J)}_{m+1} : \left(\hat{\boldsymbol{P}}^{(J)}_{\mu,m+1} - \mathbf{A}^{e,0}_{m+1} : \boldsymbol{F}^{(J)}_{\mu,m+1}\right) + \boldsymbol{F}^0_{\mu,m+1}\,, \quad I = 1,2,\ldots,n_\mathrm{c}\,. \tag{4.106}$$

4.4 Adaptive clustering-based reduced-order modeling

4.4.1 The concept of adaptivity

The concept of adaptivity (or adaptability) is applied in many different fields of study and plays an important role in the underlying developments. Perhaps one of the most well-known examples comes from the area of Natural Sciences where, according to Charles Darwin's Origin of Species (e.g., Darwin (1998)), the species that survive are the ones that can best change to fit the conditions of the surrounding environment. In the recent outbreak of the so-called Big Data Science, artificial neural networks are constantly adapting based on new sample observations to handle a given task with greater accuracy. In a more general but similar sense, adaptivity can be here defined as a feature of a given system that characterizes its ability to change and perform better under a given set of potentially evolving external conditions.

As described in Section 4.1, the main ideia behind CROMs is to perform a spatial domain decomposition where material points with similar mechanical behavior are grouped together in clusters (see Section 4.3.1). The procedure is performed in a offline-stage that precedes the actual micro-scale equilibrium problem, usually based on one or more efficient analyses of the material's elastic response under a given set of prescribed representative loadings. In what concerns the spatial clustering discretization, this system can therefore be classified as static, in the sense that it remains constant irrespective of the conditions found in the actual problem solved in the online-stage. These may include, for instance, general non-monotonic loading paths, history path-dependent nonlinear constitutive behavior, and the onset and propagation of highly localized or damage phenomena. Under these circumstances, the lack of adaptivity of these clustering-based ROMs can thus severely limit their predictive accuracy despite their high efficiency.

Therefore, akin to what happened in the past with Adaptive Finite Element Methods (AFEMs) pioneered by Babuška and Rheinboldt (Babuška and Rheinboldt, 1978, 1979), a novel strategy is here proposed towards Adaptive Clustering-based Reduced-Order Models (ACROMs). For convenience, Appendix E includes an overview of AFEM for the reader unfamiliar with the topic, including key references and illustrations. For the purposes of this section, the key is to recall that AFEMs have three main ingredients (Huerta et al., 1998), as summarized in the same Appendix: (1) an error estimator or indicator, employed to locate where there is a need for mesh refinement/de-refinement; (2) a procedure to adapt the spatial interpolation, increasing

or decreasing the interpolation in a particular region of the computational domain; and (3) a remeshing criterion, translating the output of the error analysis into a need for adaptivity and actual mesh parameters (e.g., minimum element size). The interested reader is also referred to the extensive literature on the topic (e.g., Ladevèze and Oden (1998); Ainsworth and Oden (2000); Stein (2005); Zienkiewicz et al. (2013)).

Without any loss of generality, the following sections demonstrate how adaptivity can be introduced in CROMs. In this respect, the first ACROM stems from the adaptive extension of the SCA method proposed by Liu and coworkers (Liu et al., 2016), being here coined Adaptive SCA (ASCA). Yet, it is emphasized that the proposed clustering adaptivity procedures may be readily applied to extending other CROMs as well.

4.4.2 Challenges of clustering adaptivity

Despite the extensive work in the context of AFEMs (see Appendix E), all the successfull contributions do not translate directly to CROMs and the several differences between FEM and CROMs raise new challenges that must be properly addressed. These are discussed here so as to set the stage for the formulation of the ASCA method.

The most significant difference between AFEMs and ACROMs resides in the spatial decomposition, already described in Section 4.3.1. Each finite element, e, is a geometrically well-defined connected subspace characterized by a given number of nodes and an equal number of so-called shape functions. The latter are polynomials of a given order that perform the required field interpolations within the element domain. In contrast, each material cluster, I, is a geometrically (often) disconnected subspace that groups a given number of points with similar mechanical behavior (see Figure 4.2). In accordance, the different fields are usually assumed uniform within the cluster domain (see Equation (4.56)). Another difference that should be remarked concerns the primary unknowns of the formulation. While in FEM the primary unknowns are generally the displacements at nodes (displacement-based formulation), in CROMs such as the SCA they are often taken as the (uniform) strains at the material clusters (strain-based formulation).



Figure 4.2: Geometrical comparison between a finite element (left) and a material cluster (right).

Given that fields are assumed to be uniform within each material cluster, recovery-based error estimators that take advantage of optimal sampling points (e.g., SPR-like procedures) are not readily available. The main idea of the alternative recovery-based estimators that attempt to determine a recovered system that is smooth and continuous may be applicable. Still, the

proposed contributions are closely tied to the FE formulation. By making use of the equilibrium residuals, the primary approach of residual-based error estimators seems to be most easily translated to the context of CROMs. However, explicit residual-based estimators usually depend on mesh-dependent parameters and often account only for the significant contribution of the so-called jump discontinuities. Given that clusters are usually disconnected subdomains, i.e., each cluster boundary is not a connected path (see Figure 4.2), such discontinuities require suitable treatment. In addition, cluster boundaries are not as well-defined as finite element boundaries, the latter easily characterized by a given set of boundary nodes. Implicit residual-based estimators depend significantly on the choice of suitable recovery methods and require the proper treatment of boundary fluxes. Other types of estimators related, for instance, with the analysis of constitutive functionals, may be of interest, as the material constitutive behavior of each cluster follows standard procedures.

Due to their heuristic nature, there is a lot of flexibility in the definition of error indicators in the context of CROMs as well. While several error indicators employed in AFEMs may also be readily available in the solution procedure, some are not translatable due to the previously mentioned formulation differences. This is the case of the element aspect ratio or distortion, a geometrical indicator used effectively to deal with localization phenomena and discontinuities in finite element computations (see Figure E.3).

Concerning the adaptive discretization procedures, p-adaptivity and hp-adaptivity are of no interest while assuming the uniformity of fields within the disconnected cluster subdomains. Focus can thus be given to h-adaptivity (see Figure E.4), where the size of clusters may be refined or de-refined according to the accuracy requirements. A significant difference already emerges at this point regarding the size measure. In AFEMs, the finite element size, h, is usually taken as the diameter of the smallest circle/sphere that contains the element domain, $\Omega^{(e)}$. Given that the domain of each material cluster is, in general, disconnected, such measure loses its significance. The closest size measure is, for instance, the number of voxels belonging to the cluster.

Besides the overall limitation in terms of engineering practicality, the simplest approach of r-refinement is not applicable as clusters are not well-defined by a given set of boundary nodes. At the other end of the degree of adaptivity, the complete mesh regeneration approach can be, in theory, adopted by performing a new cluster analysis and subsequent cluster domain decomposition. However, the crucial transfer of data between the old and new clusterings would be highly cumbersome, as the cluster domains are not only disconnected but can also exhibit a significantly different topology. The more conservative element subdivision seems the most suitable and natural approach to be employed in the context of CROMs. The most prominent difficulties in AFEMs are related to the placement of new nodes and mismatches between adjacent elements, inexistent issues when dealing with material clusters. In fact, the capabilities of different clustering algorithms may be explored to perform an enriched data-based subdivision effectively. Nonetheless, de-refinement procedures may be challenging in terms of data management, primarily due to the ambiguous concept of adjacency when dealing with disconnected cluster domains.

In terms of remeshing criteria, the most popular strategies can be formulated similarly. The same applies to the coupling of the adaptive procedures with the general incremental scheme to solve nonlinear problems, where some specifics of CROMs must be taken into account. A crucial aspect concerns the interaction tensors that frequently emerge in the CROMs' formulation and establish a strain-stress relationship between each pair of clusters. Given the significant costs associated with the computation of these tensors, their update must be efficiently performed every time the clustering is adapted.

Finally, a vital aspect of the reduced-order modeling paradigm is the balance between accuracy and efficiency. The primary objective of clustering adaptivity is, of course, an improvement of the solution's accuracy. Of particular importance in modeling path-dependent

nonlinear elasto-plastic materials is the onset and propagation of highly localized phenomena, often the precursor of material failure and fracture. Besides the shortcomings stemming from the lack of adaptivity, note that the main idea underlying the clustering-based (non-local) domain decomposition is, to a certain extent, opposite to the main features of localization. Hence, adaptivity is deemed crucial in this context and, perhaps, more challenging. Nonetheless, it must always be present that any accuracy gains are only valuable if the computational costs of the adaptive procedures do not compromise the high efficiency of CROMs. The higher the computational cost, the lower the true value of the accuracy gains compared to standard DNS methodologies. Finding such an accuracy-efficiency equilibrium point in the development of ACROMs is the challenge addressed here.

4.4.3 Nomenclature and fundamental concepts

Besides the general nomenclature consistently adopted throughout this document, additional concepts are introduced here to support the description of the ACROMs adaptive procedures.

The RVE is here assumed to be discretized in a regular grid of voxels[12], $n_v = \prod_{i=1}^{n_{\text{dim}}} n_i$, where n_i denotes the number of voxels in the ith dimension (see Figure 4.3). This type of discretization is suitable for CROMs whose solution procedure is partially computed in the discrete frequency domain, but can be easily converted to a finite element mesh of quadrilateral/hexahedral finite elements (see Appendix D). In the former case, each spatial sampling point is denoted as $\boldsymbol{Y}_{s_1,s_2} = \boldsymbol{Y}(s_1,s_2) \in \Omega_{\mu,0}$ (2D) or $\boldsymbol{Y}_{s_1,s_2,s_3} = \boldsymbol{Y}(s_1,s_2,s_3) \in \Omega_{\mu,0}$ (3D), where $s_i = 0,1,\ldots,n_i-1$ and $i = 1,2,\ldots,n_{\text{dim}}$. The associated coordinates can be determined in the two-dimensional case as

$$\boldsymbol{Y}_{s_1,s_2} = \left(\frac{(l_{\text{RVE}})_1}{n_1} s_1, \frac{(l_{\text{RVE}})_2}{n_2} s_2 \right), \quad s_i = 0,1,\ldots,n_i-1, \quad i = 1,2, \tag{4.107}$$

and in the three-dimensional case in an analogous way. By performing a discrete Fourier transform (DFT) and jumping to the discrete frequency domain, each sampling angular frequency is then characterized by a wave vector, $\boldsymbol{\zeta}_{s_1,s_2} = \boldsymbol{\zeta}(s_1,s_2)$ (2D) or $\boldsymbol{\zeta}_{s_1,s_2,s_3} = \boldsymbol{\zeta}(s_1,s_2,s_3)$ (3D), that is defined in the two-dimensional case as

$$\boldsymbol{\zeta}_{s_1,s_2} = \left(\frac{2\pi}{(l_{\text{RVE}})_1} s_1, \frac{2\pi}{(l_{\text{RVE}})_2} s_2 \right), \quad s_i = 0,1,\ldots,n_i-1, \quad i = 1,2, \tag{4.108}$$

and similarly in the three-dimensional case.

After the CROM clustering-based domain decomposition is performed, the RVE domain is decomposed in n_c material clusters and a cluster-reduced representative volume element (CRVE) is obtained. The clustering-based domain decomposition that characterizes the initial CRVE is hereafter called base clustering. To take advantage of a priori knowledge about the material behavior, the cluster analysis is usually performed independently for each material phase, henceforth designated cluster-reduced material phase (CRMP). Each material cluster groups a given number of voxels and may have an arbitrary-shaped discontinuous domain, as illustrated in Figure 4.3. The equilibrium problem solution procedure is then formulated over the CRVE according to the chosen CROM's formulation.

Adaptivity in ACROMs is performed independently for each CRMP. For clarity, these material phases are further classified as static cluster-reduced material phase (SCRMP) if the associated clustering-based decomposition is kept constant throughout the problem's solution (no adaptivity), or as an adaptive cluster-reduced material (ACRMP) if clustering adaptivity is allowed.

[12] Although the term pixel is more adequate to describe a material point in a 2D domain, the term voxel is adopted hereafter for both 2D and 3D domains.



Figure 4.3: Schematic illustration of a biphasic material (MP1 and MP2), from left to right: Representative volume element (RVE); Spatially discretized RVE in a regular grid of 8×8 voxels; Cluster-reduced representative volume element (CRVE) with 6 material clusters.

4.4.4 Adaptivity conditions

The first point to be discussed concerns the linkage between the clustering adaptivity procedures and the CROM's micro-scale equilibrium problem solution procedure. After the solution of each loading increment is obtained, a given set of adaptivity conditions is verified. If all adaptivity conditions are met for at least one material phase, then a clustering adaptivity step is performed (see Figure 4.4). Otherwise, the equilibrium problem solution procedure continues to the next macro-scale loading increment in a standard way.

Some possible adaptivity conditions include:

- **Clustering adaptivity frequency**. The clustering adaptivity frequency, Δm_{adapt}, defines if the ACROM framework is activated after each loading increment ($\Delta m_{\text{adapt}} = 1$), or only every q loading increments ($\Delta m_{\text{adapt}} = q$). This condition could be simply set by default as $\Delta m_{\text{adapt}} = 1$. However, given that the total number of clusters is often limited, a smart choice of this parameter is crucial for achieving an optimal accuracy-efficiency balance, as later discussed. In addition, this parameter can be defined independently for each ACRMP, being the ACROM framework only activated if at least one material phase needs to be evaluated. Note that a similar strategy can be adopted based on the evolution of any relevant variable other than the loading increments (e.g., a relative increase of a damage variable);

- **Maximum consecutive adaptivity steps**. A maximum number of consecutive clustering adaptivity steps can be set so that the equilibrium problem solution procedure continues even if further clustering adaptivity would still be triggered within the following clustering adaptivity step;

- **Threshold number of clusters**. A threshold may be enforced on the number of clusters of each ACRMP, $n_{\text{c}}^{\text{max}}$, to limit the computational cost of the equilibrium problem solution procedure. If the number of clusters surpasses this threshold, then the ACRMP's adaptivity is locked and the associated clustering is kept static during the remaining solution procedure;

- **Minimum localization/damage value**. A minimum significant value for a given localized or damage variable can be defined for each ACRMP. Clustering adaptivity procedures are

only activated for that material phase when the variable of interest reaches the minimum significant defined value (e.g., a minimum value of accumulated plastic strain, $\bar{\varepsilon}^{p}_{\text{min}}$, associated with the material plastic yielding).

4.4.5 Adaptive Self-consistent Clustering Analysis (ASCA)

Figure 4.4 summarizes the ACROM implementation for the SCA method: the Adaptive Self-consistent Clustering Analysis (ASCA). In close resemblance with the key ingredients of AFEMs described in E, a clustering adaptivity step comprises three fundamental blocks. The first block (Block A) involves the evaluation of a given error estimator or indicator, i.e., a criterion that selects the target clusters to be adapted. If there is at least one target cluster, an adaptive cluster analysis (Block B) is performed for each target cluster together with a suitable transfer of clusters' state-related variables. Otherwise, the equilibrium problem solution procedure continues if the clustering adaptivity is not triggered for any cluster. After performing the adaptive cluster analysis for all target clusters, the CRVE clustering-based domain decomposition has been effectively updated. However, the SCA method requires the computation of the new cluster interaction tensors, which must be updated accordingly (Block C). Each of these blocks is described in detail in the following sections.

Remark.
In addition to the adaptivity conditions described in Section 4.4.4, the formulation of both Block A (Section 4.4.5) and Block B (Section 4.4.5) is completely independent from the particular extended CROM. In contrast, Block C involves the computation of any clustering-dependent formulation entities which, in the particular case of the SCA method, are the cluster interaction tensors.

Once the clustering adaptivity step is concluded, the adaptivity conditions are re-evaluated. If these continue to be satisfied for at least one material phase, a new clustering adaptivity step is performed. Otherwise, the equilibrium problem solution procedure continues to the next macro-scale loading increment. Even if a new clustering adaptivity step is performed, clustering adaptivity might not be triggered for any cluster (see Figure 4.4). It is also remarked that the macro-scale loading increment where the clustering adaptivity procedure has been performed may be repeated with the updated CRVE before proceeding to the next macro-scale loading increment.



Figure 4.4: Adaptive Self-consistent Clustering Analysis (ASCA) as an ACROM implementation. A complete clustering adaptivity step comprises three fundamental blocks: (A) target clusters selection criterion, (B) adaptive cluster analysis and (C) computation of cluster interaction tensors.

Block A: Target clusters selection criterion

The first block in the clustering adaptivity step is to determine what material clusters need to be refined in order to fulfill the desired accuracy requirements. Assume that the clustering adaptivity is designed to capture a given scalar micro-scale field, $c_\mu(\boldsymbol{y})$, hereafter called clustering adaptivity feature. This choice may be set independently for each CRMP and can be, for instance, a constitutive state variable associated with localization phenomena (e.g., accumulated plastic strain, $c_\mu(\boldsymbol{y}) = \bar{\varepsilon}^p(\boldsymbol{y})$) or a damage variable ($c_\mu(\boldsymbol{y}) = D(\boldsymbol{y})$). Irrespective of the chosen clustering adaptivity feature, having such variable directly available from the CRMP's clusters' state variables is convenient for efficiently computing it from them (e.g., the norm of cluster strain concentration tensor, $c_\mu(\boldsymbol{y}) = \|\mathbf{H}\|(\boldsymbol{y})$, the density of plastic strain energy, $c_\mu(\boldsymbol{y}) = U^p_{\text{dens.}}(\boldsymbol{y})$).

After setting the suitable clustering adaptivity feature, a criterion to select the target clusters to be adapted is needed. Taking inspiration from several contributions of residual error estimators and error indicators employed in AFEMs (Kelly et al. (1983), Ortiz et al. (1987), Ortiz and Quigley (1991), Zienkiewicz et al. (1995a), see also E.2.1), a selection criterion is proposed here based on the evaluation of the spatial discontinuities (or jumps) of $c_\mu(\boldsymbol{y})$ along the material clusters' boundaries (see Figure 4.5). This requires a scanning procedure over the CRVE whose scan directions are collinear and equal in number to the problem dimensions, i.e., two scanning directions (2D problem) or three scanning directions (3D problem)[13].



Figure 4.5: Target clusters selection criterion based on the evaluation of the clustering adaptivity feature's, c_μ, spatial discontinuities along clusters' boundaries, jump(c_μ). Middle plot shows the clustering adaptivity feature's profile for a given row of voxels ($j = 4$) and the associated discontinuities at clusters' boundaries. Targeted clusters are stored together with any data relevant to the following adaptive cluster analysis.

For simplicity, assume a 2D problem and that direction 1 is currently being scanned, as illustrated in Figure 4.5. Assume further that the jth row of voxels is being evaluated, i.e., the row whose voxels are defined as $\boldsymbol{Y}_{i,j}$, $i = 0,1,\ldots,n_1$. Every pair of two consecutive voxels, $(\boldsymbol{Y}_{i,j}, \boldsymbol{Y}_{i+1,j})$, $i = 0,1,\ldots,n_{v,1}$, is evaluated as follows[14]:

1. **Skip conditions**. Several conditions are defined to avoid unnecessary computations and skip straight to the next pair of voxels if:

    - Both voxels belong to the same material cluster (cluster($\boldsymbol{Y}_{i,j}$) = cluster($\boldsymbol{Y}_{i+1,j}$)). This condition has two main outcomes: (1) ensures that only the jump in the boundaries

[13] A simple strategy to accelerate the CRVE scanning procedure is described in Section 4.4.7 by introducing a scanning frequency.

[14] The last pair of consecutive voxels to be evaluated is $(\boldsymbol{Y}_{n_1,j}, \boldsymbol{Y}_{0,j})$, i.e., the last voxel is paired with the first voxel $(\boldsymbol{Y}_{n_1+1,j} = \boldsymbol{Y}_{0,j})$.

of the clusters is evaluated; (2) computations are avoided when assuming the uniformity of fields within each cluster, i.e., when $\text{jump}(c_\mu) = 0$ is known a priori;

- Voxels belonging to different material phases ($\text{MP}(\boldsymbol{Y}_{i,j}) \neq \text{MP}(\boldsymbol{Y}_{i+1,j})$). This condition is optional, being nonetheless relevant to (1) comply with a different clustering adaptivity feature for each material phase and (2) perform the clustering adaptivity independently for each CRMP. It can be dropped if the clustering adaptivity should conform to the discontinuity of a given clustering adaptivity feature at the interface between different material phases (e.g., interface phenomena).

2. **Jump evaluation**. The clustering adaptivity feature jump can be evaluated and normalized as

$$\text{jump}_r(c_\mu) = \frac{\left| c_\mu(\boldsymbol{Y}_{i,j}) - c_\mu(\boldsymbol{Y}_{i+1,j}) \right|}{\left| \max(c_\mu(\forall \boldsymbol{Y} \in \text{MP})) - \min(c_\mu(\forall \boldsymbol{Y} \in \text{MP})) \right|}, \tag{4.109}$$

being conveniently bounded as $\text{jump}_r(c_\mu) \in [0,1]$. This normalized ratio quantifies the magnitude of the clustering adaptivity feature discontinuity relative to the maximum amplitude within the material phase. It can be interpreted as an error indicator in the sense that a significant discontinuity is often associated with localization or damage phenomena that demand a more refined clustering to be properly captured;

3. **Target selection condition**. The normalized jump is now compared with a user-defined parameter called adaptivity trigger ratio, $\gamma_{\text{ratio}} \in [0,1]$.

If $\text{jump}_r(c_\mu) >= \gamma_{\text{ratio}}$, the discontinuity is assumed to be significant and both clusters are marked as target clusters to be adapted. Otherwise, none of the clusters is marked. The adaptivity trigger ratio is thus a parameter that controls the sensitivity of the selection criterion. As $\gamma_{\text{ratio}} \to 0$, the adaptivity tends to generalize to the whole ACRMP clustering, whereas $\gamma_{\text{ratio}} \to 1$ tends to focus adaptivity only on clusters placed on regions exhibiting very high discontinuities.

After evaluating all directions and every pair of consecutive voxels, the clusters targeted during the CRVE scanning procedure are stored for the following adaptive cluster analysis.

Block B: Adaptive cluster analysis

If there is at least one target cluster stemming from Block A, then the clustering adaptivity step proceeds to the following block. A generalized adaptive cluster-reduced material phase (GACRMP) is proposed here. The adaptive cluster analysis of each material phase cluster is performed independently through any chosen unsupervised machine learning clustering algorithm (see Figure 4.6). The adopted strategy is similar to the h-refinement element subdivision approach employed in AFEMs (e.g. Belytschko (1988); Zhu et al. (1993); Zienkiewicz et al. (2013); Ródenas et al. (2017), see also E.2.2), where target clusters are divided into smaller ones and keep their original boundaries intact. This strategy is convenient concerning the transfer of clusters' state-related variables to the refined clustering. After the adaptive cluster analysis and subdivision of a given cluster, each child cluster inherits its parent cluster state-related variables.

Given that any field is usually assumed uniform within each material cluster (see Equation (4.56)), the cluster-level dataset in the online-stage has a null cluster tendency. Therefore, the offline-stage data computed at the voxels belonging to the target cluster can be conveniently recovered and used to perform the adaptive cluster analysis.

Remark.
The voxel-level dataset employed to perform the adaptive clustering procedure may be different from the one employed to perform the base clustering of the CRMP.

Besides the dataset required to perform the adaptive cluster analysis, it is necessary to define the suitable degree of decomposition, i.e., the number of child clusters created from each target cluster (parent cluster) (see Figure 4.7). The possible number of child clusters ranges from an absolute minimum of $n_{\text{c,child}}^{\text{min}} = 2$ up to a user-defined maximum of $n_{\text{c,child}}^{\text{max}} = \text{nint}((f_{c,\text{child}})^{-1})$, where $\text{nint}(x)$ denotes the nearest integer rounding function. The parameter $f_{\text{c,child}} \in [0,1]$ denotes the volume fraction of each child cluster relative to the parent cluster by assuming a uniform subdivision, e.g., $f_{\text{c,child}} = 0.2$ would result in a maximum of $n_{\text{c,child}}^{\text{max}} = 5$ child clusters. Given the established range of number of child clusters, the user-defined parameter called adaptivity split factor, $\gamma_{\text{split}} \in [0,1]$, sets the adequate number of child clusters as[15]

$$n_{\text{c,child}} = \max(2, \text{nint}(\gamma_{\text{split}}\, n_{\text{c,child}}^{\text{max}}))\,. \tag{4.110}$$

A value of $\gamma_{\text{split}} = 0$ leads to the minimum number of child clusters, $n_{\text{c,child}} = 2$, whereas a value of $\gamma_{\text{split}} = 1$ results in the maximum number of child clusters, $n_{\text{c,child}} = \text{nint}((f_{c,\text{child}})^{-1})$. Besides the bounded and comprehensible nature of both these parameters, $f_{\text{c,child}}$ and γ_{split}, the proposed strategy is convenient as it is independent of the target cluster's number of voxels and often discontinuous spatial arrangement.

Remark.
To accurately capture localized and damage phenomena, adaptivity needs to counteract the non-local nature of static CROMs (here, the SCA). When a given set of material points is grouped into a single cluster, it is implicitly enforced that all follow exactly the same deformation history path. As soon as that cluster is adaptively subdivided, each resulting child cluster is able to follow its own deformation history path, i.e., the non-local connection with the remaining child clusters is broken from that point onwards. In this way, the evolution of material points where localized phenomena occur is not dampened by other material points assumed to have a similar behavior up to that point.

The adaptive cluster analysis ends when every target cluster has been adapted and the CRVE clustering-based domain decomposition has been updated.

Block C: Computation of cluster interaction tensors

The last block of the clustering adaptivity step involves the required update of the cluster interaction tensors, $\mathbf{T}^{(I)(J)}$, $I,J = 1,2,\ldots,n_{\text{c}}$ (see Equation (4.79)). These are computed at the SCA's offline-stage after performing the CRVE base cluster analysis (see Section C.4). It is thus understandable that the cluster interaction tensors must be updated according to the new CRVE clustering, i.e., account for the strain-stress relations involving the new clusters created during the adaptive cluster analysis. As illustrated in Figure 4.8, the complete set of tensors may be conveniently stored in a cluster interaction matrix.

A simple approach would be to compute all the cluster interaction tensors as done relative to the CRVE based clustering. Despite being a valid solution, the computational cost of these fourth-order tensors is high. This cost scales with the number of clusters, where a new cluster implies a new cluster interaction tensor with itself ($I = J$) and with all the remaining clusters ($I \neq J$), and it also scales with the spatial discretization of the RVE in the spatial and/or frequency

[15] Note, however, that $n_{\text{c,child}}$ must be lower or equal than the number of voxels of the parent cluster, i.e., the dimension of the voxel-level dataset, so that the adaptive cluster analysis is possible.



Figure 4.6: Adaptive cluster analysis of each targeted cluster (parent cluster) into a given number of subclusters (child clusters), $n_{\text{c,child}}$, through cluster subdivision. The adaptive cluster analysis can be performed with any available clustering algorithm.



Figure 4.7: Computation of the number of child clusters, $n_{\text{c,child}}$, in which a given target cluster is decomposed through the proposed adaptivity split factor, γ_{split}.

domains. If the Green operator is assumed to be known in the frequency domain, $\check{\boldsymbol{\Phi}}^0$, the computation of $\mathbf{T}^{(I)(J)}$ for a given pair of clusters I and J (see Equation (4.79)) involves two main steps: (1) the convolution over the cluster J, which can be computed in the frequency domain as

$$\int_{\Omega_{\mu,0}} \chi^{(J)}(\boldsymbol{Y}')\,\boldsymbol{\Phi}^0(\boldsymbol{Y}-\boldsymbol{Y}')\,\mathrm{d}v' = \mathscr{F}^{-1}\left(\check{\chi}^{(J)}(\boldsymbol{\zeta})\,\check{\boldsymbol{\Phi}}^0(\boldsymbol{\zeta})\right), \tag{4.111}$$

where $\mathscr{F}^{-1}$ denotes the inverse Fourier transform; and (2) the spatial integration over the cluster I domain implied in

$$\int_{\Omega_{\mu,0}} \chi^{(I)}(\boldsymbol{Y})\left(\int_{\Omega_{\mu,0}} \chi^{(J)}(\boldsymbol{Y})\,\boldsymbol{\Phi}^0(\boldsymbol{Y}-\boldsymbol{Y}')\,\mathrm{d}v'\right)\mathrm{d}v. \tag{4.112}$$

The computation of $\mathbf{T}^{(I)(J)}$ is then concluded with the product by $(v^{(I)}_{\mu})^{-1} = (f^{(I)}\,v_{\mu})^{-1}$.

Note that the cluster interaction tensors exhibit a cluster-symmetry in the sense that, from Equation (4.79),

$$\mathbf{T}^{(J)(I)} = \frac{f^{(I)}}{f^{(J)}}\,\mathbf{T}^{(I)(J)}. \tag{4.113}$$

For a CRVE base clustering with n_c material clusters, cluster-symmetry can be exploited by only performing a full computation of $0.5\,n_c(n_c+1)$ cluster interaction tensors (lower triangular elements of the cluster interaction matrix). The remaining $0.5\,n_c(n_c-1)$ cluster interaction tensors, representing $0.5\,(1+n_c^{-1})\times 100\,(\%)$ of the total number of tensors, may be directly obtained from Equation (4.113). This fraction tends to 50% as the number of clusters increases.

The cluster-symmetry of the cluster interaction tensors can be further explored in the context of clustering adaptivity to minimize computational costs. In the following explanation, assume that I and J denote existing clusters before the clustering adaptivity step, and I^* and J^* denote new clusters stemming from the adaptive cluster analysis. It is proposed that the full computation is only performed for $\mathbf{T}^{(I)(J^*)}$, i.e., the cluster interaction tensors located in the columns of the cluster interaction matrix associated with new clusters (see Figure 4.8). Besides the cluster interaction tensors $\mathbf{T}^{(I^*)(J^*)}$, it can be verified that all the remaining new cluster interaction tensors $\mathbf{T}^{(I^*)(J)}$ can be computed directly from cluster-symmetry. This approach not only takes advantage of the cluster-symmetry to reduce the number of full tensor computations, but also avoids repeating the computation of the convolution (see Equation (4.111)) associated with previously existent clusters. The cluster interaction tensors $\mathbf{T}^{(I)(J)}$ can be naturally recovered from the previous clustering. In summary, if the CRVE updated clustering is characterized by n_c previously existent clusters and n_c^* new clusters, the update of the cluster interaction tensors requires $0.5\,n_c^*\,(n_c^*+2n_c+1)$ full tensor computations and $0.5\,n_c^*\,(n_c^*+2n_c-1)$ cluster-symmetry tensor computations. Note that the proposed strategy is valid irrespective of the actual method employed to compute each cluster interaction tensor as long as the cluster-symmetry holds (see Equation (4.113)).



Figure 4.8: Update of the cluster interaction matrix, $\mathbf{T}$, consistent with the clustering adaptivity step. By taking advantage of the cluster interaction tensors cluster-symmetry, only those tensors in the columns associated with the new clusters need to be fully computed.

4.4.6 Adaptive clustering solution rewinding

The numerical solution of a general equilibrium problem depends on the spatial discretization of the domain. This is particularly important when dealing with path-dependent nonlinear material behavior and/or damage mechanisms, where the proper discretization of specific regions of the domain can be crucial to get accurate predictions. For these reasons, preliminary mesh convergence studies are a standard practice in DNS analyses of a given problem which can then be complemented by adaptive methodologies.

Given the fundamental accuracy-efficiency balance subjacent to CROMs, it is often the case that the clustering-based domain decomposition is not sufficiently refined to assume convergence with respect to spatial discretization. This means that an ACROM has a persistent material state history prior to any clustering adaptivity step that will affect the solution accuracy of the remaining loading path. In other words, even if an 'optimal' clustering refinement is performed at a given instant of time, the resulting child clusters inherit a less accurate material state. For instance, it is expected that a coarser clustering leads to a rather diffuse modeling of localized phenomena, which means that child clusters inherit underestimations of the magnitude of the localized fields. More importantly, the predictions of the onset and propagation of the material failure are consequently delayed.

To address this challenge, a solution rewinding procedure is proposed herein. This procedure is composed of three main steps, as illustrated in Figure 4.9(a). The first step consists in storing the rewind state whenever a given condition is met (e.g., when the material begins yielding plastically). This essentially involves taking a snapshot of the solution state, saving the loading path state, the material homogenized strain and stress, the clusters state variables, and so on. Once the rewind state is stored, the second step consists in evaluating one or more rewind criteria at each loading increment, i.e., criteria that establish when the solution must be rewound after at least one clustering adaptivity step has been performed. If the rewind criteria are met, the third step performs the actual rewind operations, returning the solution to the rewind state but with the updated clustering. This requires that the new clustering somehow recovers the material state variables associated with the rewind state.

The clusters' state variables recovery process is illustrated in Figure 4.9(b). Given the adaptive cluster analysis described in Section 4.4.5, the clustering adaptivity hierarchy of the GACRMP can be built during the problem solution. Therefore, the recovery process requires finding the rewind state's parent cluster of each cluster from which the associated state variables are transferred. The pseudo-code of this parent cluster search procedure is presented in Figure 4.9(b) and consists of an upward hierarchical search for each cluster.

4.4.7 Additional adaptivity procedures

Some additional procedures are proposed here to complement ACROMs. These are optional but can effectively improve the clustering adaptivity and/or provide a more practical tool to the analyst.

- **Randomized scanning frequency**. The target clusters selection criterion described in Section 4.4.5 involves a scanning procedure where every pair of consecutive voxels is scanned along each direction. However, despite the completeness of this procedure, it can be argued that scanning every voxel is not absolutely necessary to perform a proper assessment and cluster selection. This is especially true when considering a spatial discretization where the voxels' dimensions are small in comparison with the clusters' sizes and/or the characteristic length of the relevant phenomena. The main idea is thus to set a scanning frequency (user-defined parameter) associated with each scanning direction as schematically illustrated in Figure 4.10. A frequency of X means that the scanning is performed every X voxels, with $X = 1$ recovering the standard (complete)



Figure 4.9: Schematic of solution rewinding procedure after clustering adaptivity: (a) Solution rewinding main steps, namely (1) storage of rewind state, (2) evaluation of rewind criteria and (3) perform rewind operations; (b) Recovery of clusters state-related variables through a suitable search of clustering adaptivity hierarchy.

approach, being enforced that the first and last voxels of each scanning direction are always evaluated. In addition, in order to avoid missing any particular domain regions, the initial voxel index can be randomly picked at each clustering adaptive step. Note that a frequency of X leads to X distinct initial voxel indexes defined as $0, 1, \ldots, X-1$.

- **Cluster adaptivity level**. The adaptivity level of a given cluster I, $\lambda^{(I)}$, describes its depth of refinement throughout the equilibrium problem solution procedure, being $\lambda^{(I)} = 0$ associated with the base clustering. If cluster I is targeted and subjected to adaptive cluster analysis, each child cluster inherits its adaptivity level incremented by 1. In this sense, the adaptivity level measures how many clustering adaptivity steps led to its creation, i.e., how far it is from the base clustering domain decomposition. This information can be useful in two different ways. In the first place, a user-defined parameter, $\lambda_{\max}$, may be enforced to limit the adaptivity level of all clusters belonging to a given ACRMP. This would be an additional target selection condition in the sense that any cluster I could only be targeted if $\lambda^I < \lambda_{\max}$ (see Section 4.4.5). In the second place, the adaptivity level may be used to enforce a certain degree of uniformity concerning the domain clustering adaptivity. A user-defined parameter, $\lambda^{\Delta}_{\max}$, can be defined to limit the difference between adaptivity levels of adjacent clusters. Assume the generic pair of consecutive voxels $(\boldsymbol{Y}_{i,j}, \boldsymbol{Y}_{i+1,j})$ described in Section 4.4.5 and that $I = \text{cluster}(\boldsymbol{Y}_{i,j})$ and $J = \text{cluster}(\boldsymbol{Y}_{i+1,j})$. If $\text{jump}_r(c_\mu) >= \gamma_{\text{ratio}}$ and $|\lambda^{(I)} - \lambda^{(J)}| <= \lambda^{\Delta}_{\max}$, then both clusters are marked as target clusters to be adapted. However, if $|\lambda^{(I)} - \lambda^{(J)}| > \lambda^{\Delta}_{\max}$, only the cluster with the lowest adaptivity level, $\min(\lambda^{(I)}, \lambda^{(J)})$, is marked as target cluster.



Figure 4.10: Randomized scanning frequency aiming to accelerate the CRVE scanning procedure underlying the target clusters selection criterion based on spatial discontinuities.

- **Cluster minimum number of voxels**. Irrespective of the microstructure under analysis, the smallest cluster possible is composed of a single voxel. If a proper domain discretization is performed, usually involving thousands of voxels, it is most likely that a single-voxel cluster does not contribute significantly to the accuracy of the problem solution. However, either in the computation of the base clustering or in each clustering adaptivity step, an additional cluster may contribute to a significant increase in the number of cluster interaction tensors and associated computation cost. This reasoning can be extended to a given minimum number of voxels per cluster, a user-defined parameter that naturally depends on the spatial discretization of the domain and on the minimum dimension considered significant to capture the material behavior accurately. This threshold is then enforced as an additional target selection condition, being a given cluster targetable only if the associated number of voxels is greater or equal to the prescribed minimum;

- **Dynamic adaptivity split factor**. In Section 4.4.5, the adaptivity split factor, γ_{split}, is proposed as a user-defined parameter that defines the number of child clusters of every target cluster in a given ACRMP. This concept can be further explored by recognizing that certain target clusters should be more refined on a given clustering adaptivity step than others, depending on the error estimator or indicator being employed. For instance, target clusters associated with higher discontinuities of the clustering adaptivity feature, $\text{jump}_r(c_\mu)$, most likely demand a greater refinement. In this sense, a magnitude associated to each target cluster, s_{split}, can be conveniently defined as $s_{\text{split}} = \max(\text{jump}_r(c_\mu)) - \gamma_{\text{ratio}}$, $s_{\text{split}} \in [0, 1 - \gamma_{\text{ratio}}]$, where $\max(\text{jump}_r(c_\mu))$ is the maximum jump associated with each target cluster and stored during the CRVE scanning procedure (see Section 4.4.5). This data may be used in three different adaptivity procedures:

  - **Enforcement of the number of clusters.** When no metric is employed to distinguish the different target clusters, the threshold number of clusters can only be evaluated after the clustering adaptivity step. This means that the total number of clusters may largely exceed the prescribed threshold, given that all target clusters are split. By sorting the target clusters in descending order of magnitude, s_{split}, the remaining target clusters can be discarded as soon as the total number of clusters surpasses the prescribed threshold. The deviation of the total number of clusters relative to the prescribed threshold is at most $n_{\text{c,child}}^{\max} - 1$ in this case;
  - **Dynamic split factor magnitude function.** An additional user-defined parameter

called adaptivity split factor amplitude, $\gamma^{\Delta}_{\text{split}}$, may be set around the prescribed adaptivity split factor, $\gamma^{p}_{\text{split}}$ (see Figure 4.7). The range of the adaptivity split factor is then characterized by a lower bound, $\gamma^{-}_{\text{split}} = \gamma^{p}_{\text{split}} - 0.5\,\gamma^{\Delta}_{\text{split}}$, and an upper bound, $\gamma^{+}_{\text{split}} = \gamma^{p}_{\text{split}} + 0.5\,\gamma^{\Delta}_{\text{split}}$. The suitable number of child clusters associated with each target cluster may then be set as

$$\gamma_{\text{split}} = \gamma^{-}_{\text{split}} + g_{\text{split}}(s_{\text{split}})\,\gamma^{\Delta}_{\text{split}}, \tag{4.114}$$

where $g_{\text{split}} = g_{\text{split}}(s_{\text{split}})$ can be any monotonically increasing scalar function that satisfies the boundary conditions $g_{\text{split}}(0) = 0$ and $g_{\text{split}}(1-\gamma_{\text{ratio}}) = 1$. This means that a target cluster that has been marked with the minimum possible magnitude ($s_{\text{split}} = 0$) is adapted with $\gamma_{\text{split}} = \gamma^{-}_{\text{split}}$, whereas target clusters with $s_{\text{split}} > 0$ are adapted with a γ_{split} proportional to the associated s_{split}. Here a general power function is proposed as

$$\gamma_{\text{split}} = (1-\gamma_{\text{ratio}})^{-n} s^{n}_{\text{split}}, \tag{4.115}$$

where $n \in [0, +\infty]$ (see Figure 4.11). A value of $n = 1.0$ can be set by default, which means that the number of child clusters increases linearly with the magnitude. A value of $n > 1.0$ can be set to decrease the split factor sensitivity, i.e., to promote an increasing number of clusters in the higher magnitude range. In contrast, $n < 1.0$ can be set to increase the split factor sensitivity and have an increased number of clusters from the low magnitude range;

– **Lower-valued cluster split factor.** By default, it has been assumed that both target clusters associated to a given spatial discontinuity, cluster($\boldsymbol{Y}_{i,j}$) and cluster($\boldsymbol{Y}_{i+1,j}$), are evaluated in a similar way concerning the discontinuity magnitude. However, it may be of interest to differenciate the number of child clusters between the lower and higher-valued cluster, namely decreasing the number of clusters created in the lower-valued side of the jump. To achieve this behavior, the magnitude associated to the lower-valued cluster, $s^{\text{low}}_{\text{split}}$, can be defined as $s^{\text{low}}_{\text{split}} = \theta\, s_{\text{split}}$, where $\theta \in [0,1]$ sets the desired differentiation.



Figure 4.11: Proposed dynamic adaptivity split factor magnitude function. Three behaviors are available: (1) $n = 1.0$ means that the number of child clusters increases linearly with the magnitude associated with the parent cluster, (2) $n \to +\infty$ promotes an increasing number of child clusters in the high magnitude range (low sensitivity) and (3) $n \to 0$ raises an increasing number of child clusters from the low magnitude range (high sensitivity).

4.4.8 Summary of hyperparameters

Numerical methods can include hyperparameters (or user-defined parameters) that are (i) difficult to interpret, (ii) cumbersome to calibrate properly, and (iii) significantly impact the results when slightly changed. The hyperparameters introduced here for ACROMs (see summary in Table 4.1) do not exhibit these issues, as shown in the following section. Some numerical experience shows that the role of each parameter can be easily understood and that results exhibit a lower parameter sensitivity as long as the proper strategy is adopted.

Table 4.1: Essential hyperparameters of the ACROM framework. Insertion: target clusters selection criterion (Block A) and adaptive cluster analysis (Block B).

Parameter	Notation	Insertion	Meaning
Adaptivity frequency	Δm_{adapt}	Adaptivity conditions	Controls when adaptivity procedures take place relative to loading increments
Adaptivity trigger ratio	γ_{ratio}	Block A	Sets the sensitivity of the selection criterion (e.g., significant field discontinuity)
Maximum adaptive level	$\lambda_{\max}$		Limits the cluster level of refinement relative to base clustering
Maximum number of child clusters	$n_{\text{c,child}}^{\max}$	Block B	Sets the maximum allowed number of child clusters created from each target cluster
Adaptivity split factor	γ_{split}		Controls the number of child clusters created from each target cluster[(a)]
Adaptivity split factor amplitude	$\gamma_{\text{split}}^{\Delta}$		Controls the variation of the number of child clusters created from each target cluster[(b)]

[(a)] Set as $\gamma_{\text{split}} = 1.0$ if using a static adaptivity split factor, i.e., $n_{\text{c,child}} = \max(2, \text{nint}(n_{\text{c,child}}^{\max}))$.

[(b)] Only required if using a dynamic adaptivity split factor.

4.5 Numerical application

4.5.1 Material characterization and macro-scale loadings

In order to follow the numerical examples of the original SCA paper (Liu et al., 2016), a biphasic material characterized by randomly distributed circular particles ($f = 30\%$) embedded in a matrix ($f = 70\%$) is here considered (see Figure 4.12). The matrix material phase constitutive behavior is assumed isotropic and elasto-plastic, governed by a standard von Mises associative flow rule with isotropic strain hardening, while the particle material phase is assumed isotropic and elastic. However, in contrast with the SCA paper (Liu et al., 2016), particles are assumed

soft to promote localized shear yielding and failure in the matrix. The material phase's properties are summarized in Table 4.2. In addition, a simplified ductile fracture criterion is formulated according to which fracture occurs when 0.5% of the matrix material phase surpasses an accumulated plastic strain of 0.125 (see Figure 4.13). Under uniaxial tension, the composite's toughness is computed as the integral of the composite stress-strain curve before fracture prediction. It is remarked that such a simple fracture criterion does not affect the constitutive behavior of the material and is only employed here to compare the failure prediction between different solution methods.

Table 4.2: Constitutive model and properties of the particle-matrix composite's material phases. Notation: Young's Modulus (E), Poisson's ratio (ν), yield stress (σ_y) and accumulated plastic strain ($\bar{\varepsilon}^p$).

Phase	Model	E(MPa)	ν	σ_y(MPa)
Matrix	von Mises (isotropic)	100	0.3	$\sigma_y = 0.5 + 0.2(\bar{\varepsilon}^p)^{0.4}$
Particles	Elastic (isotropic)	1	0.19	-

The following examples focus on two-dimensional cases under infinitesimal strains. Problems involving more complex loading paths and material constitutive behavior are left for future work, as discussed in Chapter 7. The RVE of the particle-matrix composite is shown in Figure 4.12, together with three statistical volume elements (SVEs) that resemble different particles' spatial arrangements found in the actual RVE. Three different macro-scale strain-driven loadings are considered in the following sections (see Figure 4.14), namely

- uniaxial tension: $[\varepsilon_{xx}, \varepsilon_{yy}, \varepsilon_{xy}] = [5.0, 0.0, 0.0] \times 10^{-2}$;
- pure shear: $[\varepsilon_{xx}, \varepsilon_{yy}, \varepsilon_{xy}] = [0.0, 0.0, 5.0] \times 10^{-2}$;
- combined uniaxial tension - shear: $[\varepsilon_{xx}, \varepsilon_{yy}, \varepsilon_{xy}] = [0.0, 5.0, 5.0] \times 10^{-2}$;

being all prescribed in a total of 200 increments of equal magnitude.



Figure 4.12: 2D RVE of biphasic material characterized by randomly distributed circular particles ($f = 30\%$) embedded in a matrix ($f = 70\%$), and three SVEs representing different particle spatial arrangements found in the biphasic material RVE.



Figure 4.13: Simplified fracture criterion assumed for the particle-matrix composite under uniaxial tension loading: fracture occurs when 0.5% of the matrix material phase surpasses an accumulated plastic strain of $\bar{\varepsilon}^p = 0.125$. On the left, the accumulated plastic strain field at fracture predicted with the DNS solution. On the right, a schematic illustration of the fracture propagation and failure of the material's load-bearing capacity.



Figure 4.14: Uniaxial tension, pure shear and combined uniaxial tension - shear macro-scale strain loading constraints.

4.5.2 Solution methods and error assessment

Three solution methods are considered in the numerical assessment presented in the following sections: a direct numerical simulation (DNS) solution, here adopted as the reference (or 'high-fidelity') solution, an SCA solution following the original paper Liu et al. (2016) (see Appendix C), and the Adaptive Self-consistent Clustering Analysis (ASCA) proposed herein.

The DNS solution is obtained with an FEM first-order hierarchical multi-scale model based on computational homogenization (see Chapter 2). This solution is carried out with LINKS (Large Strain Implicit Non-linear Analysis of Solids Linking Scales), an implicit multi-scale finite element Fortran code developed by the CM2S research group at the Faculty of Engineering of the University of Porto[16]. LINKS is also employed to perform the linear elastic DNS simulations required in the offline-stage of both SCA and ASCA (see Appendix D for finite element mesh

[16]Bernardo P. Ferreira is an active member of the CM2S research group, led by F.M. Andrade Pires, and one of the developers of LINKS. This motivated the choice of FEM as the DNS solution, as opposed to the choice of an external FFT-based homogenization solver. Despite the different fundamental basis of the solution, some preliminary studies showed a close agreement between both approaches under elasticity and elasto-plasticity for a sufficiently refined mesh.

compatibility and element averaging procedures) due to the well-known limitation of the FFT-based homogenization basic scheme (see Appendix B) to deal with the highly contrasting phases.

In turn, both SCA and ASCA solutions are obtained with CRATE (Clustering-based Nonlinear Analyses of Materials), an object-oriented Python program that performs multi-scale nonlinear analyses through clustering-based reduced-order models. This program has been fully designed and implemented as part of this thesis and is thoroughly described in Chapter 5. Periodic boundary conditions are assumed and a refined spatial discretization of $n_v = 400 \times 400$ voxels is considered for all numerical examples. Without loss of generality, only the matrix material phase is subject to clustering adaptivity in the ASCA solution. The base clustering of both material phases is performed with the well-known K-Means clustering (standard Lloyds' algorithm) with 10 centroid initializations computed with K-Means++. The adaptive cluster analysis of the matrix material phase relies on the Mini-Batch K-Means with the same 10 centroid initializations computed with K-Means++. Both of these algorithms implementations are readily available from Scikit-learn, a Python module integrating a wide range of state-of-the-art machine-learning algorithms for medium-scale supervised and unsupervised problems Pedregosa et al. (2012).

Remark.
It is well-known that performing a first-order homogenization and assuming micro-scale periodic boundary conditions in the presence of localized phenomena is not accurate from a physical point of view. Although such a topic has received a lot of attention in recent years, such considerations can be disregarded here, where the DNS is assumed to deliver the 'high-fidelity' (reference) solution to evaluate the CROMs numerical accuracy.

Concerning the error assessment, two different metrics are adopted. On the one hand, the relative error, ϵ, is employed to compare the macro-scale homogenized response and toughness, being always defined as

$$\epsilon\,(\%) = \left| \frac{a_{\mathrm{CROM}} - a_{\mathrm{DNS}}}{a_{\mathrm{DNS}}} \right| \times 100\,, \tag{4.116}$$

where a denotes the scalar quantity of interest. On the other hand, the root mean square error (RMSE) is employed to compare the micro-scale field solutions (see Appendix D), being defined as

$$\mathrm{RMSE}\,(a_\mu) = \sqrt{\frac{1}{n_v} \sum_{i=1}^{n_v} \left(a_{\mu,\mathrm{CROM}} - a_{\mu,\mathrm{DNS}} \right)_i^2}\,, \tag{4.117}$$

where a_μ denotes any micro-scale scalar quantity. Note that the RMSE has the units of the actual quantity being evaluated. Two micro-scale local scalar quantities are evaluated in the following analyses: (1) the accumulated plastic strain, $\bar{\varepsilon}^p$, a state variable of the von Mises constitutive model governing the behavior of the matrix material phase; and (2) the accumulated plastic strain energy density defined as $U^p_{\mathrm{dens}} = \int \Delta\boldsymbol{\sigma}\, \mathrm{d}\boldsymbol{\varepsilon}^p$. Both quantities are intrinsically associated with the highly localized plastic yielding of the composite as well as with the adopted fracture criterion.

At last, unless otherwise stated, all the numerical simulations presented in this section are run with 1 CPU core in a personal computer with the following specifications: CPU Intel Core i7-6800K (3.40GHz × 6 cores/12 threads, Broadwell), RAM 32GB (4 × 8GB) DDR4 @ 2400MHz. Nonetheless, some third-party (low-level) packages may perform multi-processor computations at certain operations.

4.5.3 Benchmark analysis

The benchmarks presented in Figure 4.12 promote simple plastic strain localization patterns under uniaxial tension that can be easily visualized. Despite this simplicity, accurately capturing such localized phenomena already poses important challenges to standard CROMs. For these reasons, they are selected as the first illustration of the ASCA application and performance without introducing additional complexities.

As shown in Figure 4.15, Benchmark 1 promotes a single plastic strain localized band between both particles under uniaxial tension. The first important task consists in identifying, as well as possible, what are the main evolution steps of the field of interest. The evolution of the accumulated plastic strain field in this benchmark has essentially two main steps: (1) the initial plastic yielding of the matrix at the particle-matrix interface (transverse plane relative to loading direction), and (2) the propagation of plastic yielding that leads to the band connecting both particles. In accordance, it is expected that the 'optimal' clustering should exhibit a more refined domain decomposition on these regions to accurately capture the material response.



Figure 4.15: Comparison of the clustering-based domain decomposition and local accumulated plastic strain field at the end of the deformation path of Benchmark 1 under uniaxial tension. Colors displayed in the clustering row are associated with different material clusters within each CRVE.

The second task consists in choosing a suitable number of initial clusters. Such choice is by no means unique and should ensure a minimal accuracy upon which the adaptivity can be properly developed. As a rule of thumb, the base clustering should at the very least capture the main regions where the field of interest shows some significant evolution. In this benchmark, the minimal number of clusters has been set to $n_c = 65$ (60 clusters in the matrix ACRMP and 5 clusters in the particles SCRMP). From Figure 4.15, it can be verified that the SCA solution with $n_c = 65$ can capture the main regions of plastic strain but in a rather diffuse manner.

Last but not least, it remains to define how should the ASCA be effectively employed and set the associated parameters accordingly. In the first place, the clustering adaptivity feature for the matrix ACRMP is set as the accumulated plastic strain, $c_\mu(\boldsymbol{y}) = \bar{\varepsilon}^p$. At this point, the clustering adaptivity strategy must be defined based on the available knowledge about the problem physics, namely the main evolution steps already described. Here, clustering adaptivity should follow the plastic strain field front propagation, a similar strategy to that commonly used in phase-field methodologies. It is assumed that a 10% normalized

accumulated plastic strain discontinuity is significant by setting $\gamma_{\text{ratio}} = 0.1$ and the number of child clusters is simply set constant and equal to $n_{\text{c,child}} = 2$ ($f_{\text{c,child}} = 0.5$, $\gamma_{\text{split}} = 1.0$). Clustering adaptivity procedures should be activated as soon as the matrix begins to yield plastically and the clustering adaptivity frequency is set to $\Delta m_{\text{adapt}} = 15$ so that adaptivity steps may efficiently accompany the plastic strain field front propagation.

Besides the DNS solution, three different SCA solutions are selected to provide insightful comparisons: a 'coarse' solution with $n_{\text{c}} = 65$, a 'medium' solution with $n_{\text{c}} = 185$ and a 'fine' solution[17] with $n_{\text{c}} = 305$. To focus the attention on the matrix material phase and perform a fair comparison between the different solution methods, the number of clusters of the particles SCRMP is always set to 5 (approximately proportional to the particles volume fraction in the SCA 'coarse' solution). To evaluate the performance of the ASCA solution, the initial number of clusters is also set to $n_{\text{c}} = 65$, similar to the SCA 'coarse' solution, and the threshold number of clusters is set to $n_{\text{c}} = 185$, similar to the SCA 'medium' solution. The maximum allowed adaptivity level is set as $\lambda_{\max} = 2$, i.e., each cluster can only be subject to a maximum of two adaptive cluster analyses. This limit is important to avoid exhausting the available number of clusters before all the critical domain regions are properly refined.

Remark.
To focus the attention on the matrix material phase and perform a fair comparison between the different solution methods, the number of clusters of the particles SCRMP is always set to 5, approximately proportional to the particles volume fraction in the SCA 'coarse' solution. This means that the actual accuracy of the remaining solutions with respect to the DNS solution would be increased by considering the particles number of clusters proportional to their volume fraction. A similar comparison is performed in the following analyses of the particle-matrix RVE.

The comparison between the macro-scale homogenized response predicted by the different solution methods is shown in Figure 4.16. The clustering has been dynamically adapted throughout the ASCA solution procedure, where the number of clusters has increased from $n_{\text{c}} = 65$ to $n_{\text{c}} = 190$ (see Figure 4.18(a)). A total of 5 clustering adaptivity steps have been performed (signaled by the diamond-shaped markers), two of them in the yielding region (particle-matrix interface) and the remaining on the post-yielding region (plastic band). It is possible to see that ASCA solution's accuracy outperforms the SCA 'medium' solution with a similar number of clusters as well as the SCA 'fine' solution with $n_{\text{c}} = 305$, exhibiting an overall relative error below 4%. The ASCA solution departs from the SCA 'coarse' solution with $n_{\text{c}} = 65$ occurs in the yielding region soon after the first clustering adaptivity step, hence highlighting the importance of such procedure to accurately capture the initial yielding of the matrix material phase. In addition, ASCA is able to predict the material fracture (signaled by the star-shaped marker) and toughness with significantly greater accuracy (see Table 4.3).

The numerical assessment proceeds with the comparison between the micro-scale solution fields, as shown by the RMSE of the local accumulated plastic strain and accumulated plastic strain energy density fields in Figure 4.17. Note that such error metric accounts for the errors stemming from the whole domain, hence the improvement from the SCA solution with $n_{\text{c}} = 65$ is delayed in comparison with macro-scale homogenized response. Nonetheless, the ASCA solution's accuracy surpasses the SCA 'medium' solution with a similar number of clusters and even reaches the SCA 'fine' solution with $n_{\text{c}} = 305$. These and the macro-scale homogenized results can be further comprehended by analyzing the clustering and local accumulated plastic strain field at the end of the deformation path (see Figure 4.15). While the SCA 'fine' solution with $n_{\text{c}} = 305$ scatters the clusters over the whole domain, the ASCA solution places the majority of clusters where they are most needed. As the magnitude of the plastic strain

[17] The number of clusters of the SCA 'fine' solution has been selected so that the relative error of the macro-scale homogenized response is below 5% with respect to the FEM DNS solution.



(a) (b)

Figure 4.16: Comparison of the macro-scale homogenized response of Benchmark 1 predicted by different solution methods under uniaxial tension: (a) Homogenized stress; (b) Relative error with respect to the FEM DNS solution. Symbology: clustering adaptivity step (♦), fracture criterion prediction (★).

localization increases, the improved accuracy of the ASCA on these regions dominates over the less significant errors in the remaining domain, in accordance with Figure 4.17.

Nevertheless, ASCA's improved accuracy involves some computational cost due to the adaptivity procedure that tries to compensate for the evaluation of more clusters when adaptivity is not present. Therefore, the partial and total computational times of the different solution methods are presented in Table 4.4 (see Figure C.1 for a description of each step). In the first place, the DNS solution computational time is approximately one order of magnitude greater than the most expensive SCA solution with $n_c = 305$. Second, the total time of the ASCA solution is faster than the SCA 'medium' solution with a similar number of clusters.

Analyzing the partial computational times is useful to understand the differences between SCA and ASCA. The computational time associated with the DNS linear elastic analyses (step 1 of the offline-stage) is independent of the number of clusters, hence similar among the different solutions. The computational cost of the base cluster analysis (step 2 of the offline-stage) scales with the number of clusters. Given that ASCA starts with an initial number of clusters $n_c = 65$, this step is faster than both SCA solutions with a higher number of clusters. The same applies to the computation of the cluster interaction tensors (step 3 of the offline-stage), the most expensive step of the offline-stage. It is thus clear that ASCA results in significant savings associated with the offline-stage overhead costs. Concerning the actual solution procedure of the online-stage, ASCA is much faster than the SCA with a similar number of clusters. This results from the fact that approximately one-fourth of the deformation path is solved with $n_c < 185$ (see Figure 4.18). Finally, there is a computational cost associated with all clustering adaptivity procedures exclusive to the ASCA solution. It is noticeable that this cost is relatively high when compared with the actual online solution procedure. Figure 4.18(b) shows that the update of the cluster interaction tensors (Block C) dominates the computational

Table 4.3: Ductile failure and associated toughness of Benchmark 1, predicted by the different solution methods under uniaxial tension. Failure assumed when 0.5% of the matrix phase surpasses an accumulated plastic strain of 0.125. Number of clusters: (c) $n_c = 65$ (coarse), (m) $n_c = 185$ (medium), (f) $n_c = 305$ (fine) and (*) $n_c = 65 \rightarrow 190$.

	Failure		**Toughness**	
Method	ε_{xx}	σ_{xx}(MPa)	J(mJ/mm^3)	ϵ(%)
DNS	2.00×10^{-2}	7.40×10^{-1}	1.06×10^{-2}	-
SCA$^{(c)}$	2.58×10^{-2}	8.58×10^{-1}	1.59×10^{-2}	50.00
SCA$^{(m)}$	4.48×10^{-2}	8.15×10^{-1}	1.44×10^{-2}	35.85
SCA$^{(f)}$	2.40×10^{-2}	8.02×10^{-1}	1.37×10^{-2}	29.25
ASCA$^{(*)}$	2.35×10^{-2}	7.94×10^{-1}	1.30×10^{-2}	22.64

Table 4.4: Partial and total computational times (s) of the different solution methods associated to Benchmark 1 under uniaxial tension. Number of clusters: (c) $n_c = 65$ (coarse), (m) $n_c = 185$ (medium), (f) $n_c = 305$ (fine) and (*) $n_c = 65 \rightarrow 190$. Offline-stage: linear elastic DNS simulations (step 1), base cluster analysis (step 2) and computation of cluster-interaction tensors (step 3).

	Computational time (s)					
Method	**Offline (step 1)**	**Offline (step 2)**	**Offline (step 3)**	**Online (solution)**	**Online (adapt.)**	**Total**
DNS	-	-	-	23800	-	23800
SCA$^{(c)}$	219	22	52	132	-	425
SCA$^{(m)}$	219	108	399	1350	-	2080
SCA$^{(f)}$	219	154	1100	2460	-	3930
ASCA$^{(*)}$	219	22	52	324	637	1010

cost of the clustering adaptivity after the first clustering adaptivity step is performed.

Remark.
Despite promoting different plastic strain localization patterns, the same clustering adaptivity strategy has been successfully employed to solve Benchmarks 2 and 3 (see Figure 4.12). Given that similar conclusions have been obtained, the corresponding results and discussion are omitted here.

4.5.4 Particle-matrix RVE analysis under uniaxial tension

The analysis of the particle-matrix RVE is more complex than the previously described benchmarks. Figure 4.13 shows numerous plastic strain localized bands developed between particles throughout the deformation path under uniaxial tension. It is possible to conclude that the composite fracture results from two prominent plastic bands whose propagation occurs transversally to the loading direction. It is thus understandable that the clustering adaptivity strategy employed in the previous section may not be the most suitable choice to tackle this problem. Moreover, some of the additional adaptivity procedures proposed in Section 4.4.7 can be explored here as well as the adaptive clustering solution rewinding



(a) (b)

Figure 4.17: Root mean square error (RMSE) of Benchmark 1 micro-scale fields solutions relative to the FEM DNS solution under uniaxial tension: (a) Local accumulated plastic strain field; (b) Local accumulated plastic strain energy density field. Symbology: clustering adaptivity step (⧫).

procedure described in Section 4.4.6.

The identification of the accumulated plastic strain field's main evolution steps is not straightforward as in the benchmark cases. At most, it can be a priori expected that the composite macro-scale yielding and posterior fracture is dictated by one or more continuous bands where plastic strain localizes with a higher magnitude. The 'optimal' clustering should thus prioritize the refinement of the primary plastic bands but cannot disregard the development of secondary localized phenomena with lower magnitude.

The initial number of clusters is set to $n_c = 100$ (70 clusters in the matrix ACRMP and 30 clusters in the particles SCRMP). Figure 4.19 shows that the corresponding SCA solution satisfies a minimal required accuracy despite failing to capture several secondary plastic bands.

The clustering adaptivity feature for the matrix ACRMP is again set as the accumulated plastic strain, $c_\mu(\boldsymbol{y}) = \bar{\varepsilon}^p$. Given that several plastic strain localized bands are not developed at the same time and/or rate, attempting to follow all plastic strain fronts efficiently is cumbersome. Instead, the strategy adopted here is to perform a single clustering adaptivity step right after the yielding region ($\bar{\varepsilon}^p = 0.05$), i.e., once the primary plastic bands have developed as well as some of the secondary ones. In order to do so, it is assumed that a 5% normalized accumulated plastic strain discontinuity is significant by setting $\gamma_{\text{ratio}} = 0.05$. In addition, the number of child clusters is set dynamically as $n_{\text{c,child}} \in [3,8]$ ($f_{\text{c,child}} = 0.125$, $\gamma_{\text{split}} = 0.7$, $\gamma^{\Delta}_{\text{split}} = 0.6$) and assuming the default linear magnitude function ($n = 1.0$). In this way, the regions associated with the primary plastic bands (higher discontinuities) are refined with a greater number of clusters without wasting too many clusters in the secondary plastic bands (lower discontinuities). For the same reason, $s^{\text{low}}_{\text{split}} = 0.0$ ($\theta = 0.0$) so that the matrix lower-valued clusters surrounding all plastic bands do not exhaust the available number of clusters.

Remark.
Although the refined clustering of the primary plastic bands is crucial to accurately predict the



Figure 4.18: Evolution of clustering adaptivity related metrics in Benchmark 1 under uniaxial tension: (a) Number of clusters; (b) Relative time of each block of the clustering adaptivity step with respect to the total time spent in clustering adaptivity procedures.

material's structural degradation and fracture, the suitable refinement of the surrounding matrix clustering plays an important role in the macro-scale homogenized response.

Besides the DNS solution, three different SCA solutions are again selected for comparison following the same reasoning: a 'coarse' solution with $n_c = 100$, a 'medium' solution with $n_c = 200$ and a 'fine' solution with $n_c = 300$. The number of clusters of the particles SCRMP[18] is always set to 30. To evaluate the performance of the ASCA solution, the initial number of clusters is set to $n_c = 100$, the threshold number of clusters is set to $n_c = 200$ and the maximum allowed adaptivity level is kept as $\gamma_{max} = 2$. Moreover, following the discussion in Section 4.4.6, two ASCA solutions are evaluated: one where the ASCA solution proceeds after the clustering adaptivity step is performed, and the other where the ASCA solution is rewound back to the beginning of the deformation path after the clustering adaptivity step. The following results demonstrate that solving the yielding region with a proper clustering refinement and overwriting the less accurate state variable history is fundamental to the solution's accuracy[19]. This approach can then be characterized by two steps: (1) a first fast step where a coarse clustering is solved up to the point where a proper clustering adaptivity has been performed and (2) a second step where the deformation path and material state history is partially or totally solved with adequate domain decomposition. Unless otherwise stated, the ASCA solution with rewinding is evaluated in the following discussion.

The comparison between the macro-scale homogenized response predicted by the different solution methods is shown in Figure 4.20. The clustering has been dynamically adapted from $n_c = 100$ to $n_c = 202$ in a single clustering adaptivity step (signaled by the diamond-shaped

[18] It is emphasized that if the number of clusters of the particles' SCRMP is increased proportionally to the corresponding volume fraction, then the approximation of the SCA and ASCA solutions towards the DNS is significantly improved.

[19] Despite improved results obtained in Benchmark 1, suitable use of the adaptive clustering solution rewinding may play a major role in the improvement of the ASCA solution's accuracy.



Figure 4.19: Comparison of the clustering-based domain decomposition and local accumulated plastic strain field at the end of the deformation path of the particle-matrix composite 2D RVE under uniaxial tension. Colors displayed in the clustering row are associated with different material clusters within each CRVE. Symbology: solution rewinding ($\circlearrowleft$).

marker) right after the yielding region (see Figure 4.22). It is possible to see that the ASCA solution's accuracy outperforms the SCA solution with a similar number of clusters, namely in the yielding region where the departure between both solutions occurs. The outcome of a clustering adaptivity step performed right after the yielding region is even more highlighted in comparison with the SCA 'fine' solution with $n_c = 300$. The ASCA solution has greater accuracy in the yielding and early post-yielding region, after which the SCA 'fine' solution catches up due to a more refined clustering dispersed over the whole matrix material phase. A similar comparison results from the prediction of the material fracture (signaled by the star-shaped marker) and toughness (see Table 4.5). ASCA prediction's accuracy is almost equal to the SCA's 'fine' solution, while significantly better than the SCA 'medium' solution with a similar number of clusters. Despite the reasonable fracture and toughness predictions of the ASCA solution without rewinding, the accuracy of the macro-scale homogenized response is severely affected and significantly worse than SCA 'medium' solution with a similar number of clusters.

The RMSE of the local accumulated plastic strain and accumulated plastic strain energy density fields is shown in Figure 4.21. The ASCA solution's accuracy surpasses the SCA 'medium' solution with a similar number of clusters and closely follows the SCA 'fine' solution in the yielding and early post-yielding regions. These results follow the same reasoning of the macro-scale homogenized response and are complemented by the clustering and local accumulated plastic strain field at the end of the deformation path (see Figure 4.19). It is important to highlight the contrast between the ASCA solution with and without performing the rewinding procedure. While the former departs from the SCA 'coarse' solution after the clustering adaptivity step, the latter departs from the beginning and improves the solution's accuracy throughout the whole deformation path.

The partial and total computational times of the different methods are presented in Table 4.6. In the first place, the ASCA solution is much faster than the DNS solution concerning the total computational time, faster than the SCA 'fine' solution with $n_c = 300$ and slightly slower than the SCA 'medium' solution with the same number of clusters. The latter comparison results from the balance between different costs: (i) ASCA base cluster analysis is faster due to the lower number of initial clusters; (ii) the computation of ASCA base clustering cluster interaction tensors is



(a) (b)

Figure 4.20: Comparison of the macro-scale homogenized response of the particle-matrix composite 2D RVE predicted by different solution methods under uniaxial tension: (a) Homogenized stress; (b) Relative error with respect to the FEM DNS solution. Symbology: clustering adaptivity step (⧫), fracture criterion prediction (★), solution rewinding (⟲).

much faster for the same reason; (iii) ASCA must re-solve the macro-scale loading increments prior to the solution rewinding; (iv) ASCA must spend additional computational time associated to the clustering adaptivity procedures. Hence, by rewinding the solution back to the beginning of the deformation path, the ASCA solution not only loses the benefit of partially solving the deformation path with a lower number of clusters but also needs to re-solve the overwritten loading increments. This is a clear trade-off between accuracy and efficiency, which is perfectly reasonable in this particular problem. In addition, concerning the memory consumption of the rewinding procedure, the rewind state storage required 12.7kB for data about the applied loading and 11.2kB for data about the material constitutive state (cluster state variables). This short memory consumption results from not needing to store any voxel-based data (i.e., regular grid-shaped arrays). At last, Figure 4.22(b) shows once again that the update of the cluster interaction tensors (Block C) dominates the computational cost of the clustering adaptivity.

Table 4.5: Ductile failure and associated toughness of the particle-matrix composite 2D RVE predicted by the different solution methods under uniaxial tension. Failure assumed when 0.5% of the matrix phase surpasses an accumulated plastic strain of 0.125. Number of clusters: (c) $n_c = 100$ (coarse), (m) $n_c = 200$ (medium), (f) $n_c = 300$ (fine), (*) $n_c = 100 \rightarrow 202$ and (⟲) $n_c = 100 \rightarrow 202$ (with rewinding).

	Failure		**Toughness**	
Method	ε_{xx}	σ_{xx}(MPa)	J(mJ/mm^3)	ϵ(%)
DNS	1.68×10^{-2}	3.16×10^{-1}	3.70×10^{-3}	-
SCA$^{(c)}$	2.23×10^{-2}	3.68×10^{-1}	6.10×10^{-3}	64.86
SCA$^{(m)}$	2.10×10^{-2}	3.62×10^{-1}	5.65×10^{-3}	52.70
SCA$^{(f)}$	1.75×10^{-2}	3.42×10^{-1}	4.39×10^{-3}	18.64
ASCA$^{(*)}$	2.03×10^{-2}	3.61×10^{-1}	5.39×10^{-3}	45.68
ASCA$^{(⟲)}$	1.85×10^{-2}	3.48×10^{-1}	4.70×10^{-3}	27.03



(a) (b)

Figure 4.21: Root mean square error (RMSE) of the particle-matrix composite 2D RVE micro-scale fields solutions relative to the FEM DNS solution under uniaxial tension: (a) Local accumulated plastic strain field; (b) Local accumulated plastic strain energy density field. Symbology: clustering adaptivity step (⧫), solution rewinding (⟲).

Table 4.6: Partial and total computational times (s) of the different solution methods associated to the particle-matrix 2D RVE under uniaxial tension. Number of clusters: (c) $n_c = 100$ (coarse), (m) $n_c = 200$ (medium), (f) $n_c = 300$ (fine), (*) $n_c = 100 \rightarrow 202$ and (↻) $n_c = 100 \rightarrow 202$ (with rewinding). Offline-stage: linear elastic DNS solutions (step 1), base cluster analysis (step 2) and computation of cluster-interaction tensors (step 3).

	Computational time (s)					
Method	**Offline (step 1)**	**Offline (step 2)**	**Offline (step 3)**	**Online (solution)**	**Online (adapt.)**	**Total**
DNS	-	-	-	30800	-	30800
$SCA^{(c)}$	219	34	115	184	-	552
$SCA^{(m)}$	219	145	438	397	-	1200
$SCA^{(f)}$	219	216	696	638	-	2040
$ASCA^{(*)}$	219	34	115	367	432	1170
$ASCA^{(↻)}$	219	34	115	475	432	1280



Figure 4.22: Clustering adaptivity of particle-matrix composite 2D RVE (without rewinding) under uniaxial tension: (a) Evolution of the number of clusters; (b) Evolution of the cluster adaptivity framework's blocks computation time relative to the total adaptivity computation time up to a given increment.

4.5.5 Particle-matrix RVE analysis under different loadings

When subjected to different loading constraints, namely pure shear and a combined uniaxial tension - shear loadings (see Figure 4.14), it is possible to see that the distinction between primary and secondary plastic localization bands is not as clear as in the uniaxial tension case (see Figures 4.23 and 4.24). In order to demonstrate the robustness of the proposed clustering adaptivity approach, it is instructive to evaluate its response by adopting the same strategy described in Section 4.5.4 (uniaxial tension loading) and keeping exactly the same set of hyperparameters. Following the numerical observations of the previous section, only the ASCA solution with the rewinding procedure after the clustering adaptivity step is illustrated.



Figure 4.23: Comparison of the clustering-based domain decomposition and local accumulated plastic strain field at the end of the deformation path of the particle-matrix composite 2D RVE under pure shear loading. Colors displayed in the clustering row are associated with different material clusters within each CRVE. Symbology: solution rewinding ($\circlearrowleft$).

The comparison between the macro-scale homogenized response[20] predicted by the different solution methods is shown in Figures 4.25 and 4.26. In both loading cases, the clustering has been dynamically adapted from $n_c = 100$ to $n_c = 201$ in a single clustering adaptivity step (signaled by the diamond-shaped marker) right after the yielding region. The accuracy improvements stemming from the single clustering adaptivity step are as expected. Prior to the clustering adaptivity step, the ASCA delivers the most accurate solution in the yielding region even when compared with the SCA 'fine' solution with $n_c = 300$. This suggests that the clustering adaptivity step performs suitable refinements in the regions of interest, namely in the regions where the most severe plastic localization took place at that stage of the deformation path. Then, as several new plastic yielding bands are developed, the ASCA solution without any further adaptivity steps tends to approximate the solution delivered by the SCA with a similar initial number of clusters. As a consequence of the adopted clustering adaptivity strategy, all the 'available' clusters have been deployed to capture the plastic localization in the yielding region. The remaining loading path lacks the required adaptivity. Regarding the fracture criterion, both SCA 'coarse' and 'medium' solutions, with $n_c = 100$ and

[20] In the combined uniaxial tension - shear loading case, the equivalent strain, ε^{eq}, and equivalent stress, σ^{eq}, are defined as

$$\varepsilon^{eq} = \sqrt{\frac{2}{3}\boldsymbol{\varepsilon}_d : \boldsymbol{\varepsilon}_d}, \qquad \sigma^{eq} = \sqrt{\frac{1}{2}\boldsymbol{\sigma}_d : \boldsymbol{\sigma}_d},$$

where $\boldsymbol{\varepsilon}_d$ and $\boldsymbol{\sigma}_d$ are the deviatoric components of the infinitesimal strain tensor and Cauchy stress tensor, respectively.



Figure 4.24: Comparison of the clustering-based domain decomposition and local accumulated plastic strain field at the end of the deformation path of the particle-matrix composite 2D RVE under combined uniaxial tension - shear loading. Colors displayed in the clustering row are associated with different material clusters within each CRVE. Symbology: solution rewinding ($\circlearrowleft$).

n_c = 200 respectively, fail to predict the material fracture under a pure shear loading. In contrast, the ASCA solution predicts fracture (signaled by the star-shaped marker) with greater accuracy than the SCA 'fine' solution with n_c = 300. Under the combined uniaxial tension - shear loading, the ASCA delivers the most accurate fracture prediction as well.

The RMSE of the local accumulated plastic strain and accumulated plastic strain energy density fields is shown in Figures 4.27 and 4.28, with similar results obtained for both loading constraints. Concerning the local accumulated plastic strain, the ASCA solution's accuracy surpasses the SCA 'medium' solution with a similar number of clusters except in the final stage of the deformation path. In terms of the local accumulated plastic strain energy density, the ASCA solution follows closely the SCA 'fine' solution with $n_c = 300$.

For the sake of completeness, the partial and total computational times of the different methods are presented in Tables 4.7 and 4.8, respectively, being similar to the uniaxial tension loading case (see Table 4.6).

Remark.
The results obtained for the composite RVE subjected to different loading constraints and considering the same hyperparameters reinforce the robustness of the ASCA and the improved accuracy without significant changes in the efficiency of the SCA method for a similar final number of clusters. Nevertheless, the main observations and tendencies shown in this section should hold irrespective of the problem dimension, the spatial discretization and strain formulation. Future investigations should shed additional light on the computational cost and accuracy of ASCA in more challenging scenarios.



Figure 4.25: Comparison of the macro-scale homogenized response of the particle-matrix composite 2D RVE under pure shear loading predicted by different solution methods: (a) Homogenized stress; (b) Relative error with respect to the FEM DNS solution. Symbology: clustering adaptivity step (⧫), fracture criterion prediction (★), solution rewinding (⟲).



Figure 4.26: Comparison of the macro-scale homogenized response of the particle-matrix composite 2D RVE under combined uniaxial tension - pure shear loading predicted by different solution methods: (a) Homogenized stress; (b) Relative error with respect to the FEM DNS solution. Symbology: clustering adaptivity step (⧫), fracture criterion prediction (★), solution rewinding (⟲).



(a) (b)

Figure 4.27: Root mean square error (RMSE) of the particle-matrix composite 2D RVE micro-scale fields solutions relative to the FEM DNS solution under pure shear loading: (a) Local accumulated plastic strain field; (b) Local accumulated plastic strain energy density field. Symbology: clustering adaptivity step (♦), solution rewinding (↺).



(a) (b)

Figure 4.28: Root mean square error (RMSE) of the particle-matrix composite 2D RVE micro-scale fields solutions relative to the FEM DNS solution under combined uniaxial tension - shear loading: (a) Local accumulated plastic strain field; (b) Local accumulated plastic strain energy density field. Symbology: clustering adaptivity step (♦), solution rewinding (↺).

Table 4.7: Partial and total computational times (s) of the different solution methods associated to the particle-matrix 2D RVE under pure shear loading. Number of clusters: (c) n_c = 100 (coarse), (m) n_c = 200 (medium), (f) n_c = 300 (fine) and (↻) n_c = 100 → 201 (with rewinding). Offline-stage: linear elastic DNS solutions (step 1), base cluster analysis (step 2) and computation of cluster-interaction tensors (step 3).

	Computational time (s)					
Method	**Offline (step 1)**	**Offline (step 2)**	**Offline (step 3)**	**Online (solution)**	**Online (adapt.)**	**Total**
DNS	-	-	-	33280	-	33280
SCA$^{(c)}$	219	34	115	187	-	555
SCA$^{(m)}$	219	145	438	435	-	1237
SCA$^{(f)}$	219	216	696	689	-	1820
ASCA$^{(↻)}$	219	34	115	490	398	1256

Table 4.8: Partial and total computational times (s) of the different solution methods associated to the particle-matrix 2D RVE under combined uniaxial tension - pure shear loading. Number of clusters: (c) $n_c = 100$ (coarse), (m) $n_c = 200$ (medium), (f) $n_c = 300$ (fine) and (↻) $n_c = 100 \rightarrow 201$ (with rewinding). Offline-stage: linear elastic DNS solutions (step 1), base cluster analysis (step 2) and computation of cluster-interaction tensors (step 3).

	Computational time (s)					
Method	**Offline (step 1)**	**Offline (step 2)**	**Offline (step 3)**	**Online (solution)**	**Online (adapt.)**	**Total**
DNS	-	-	-	32475	-	32475
SCA$^{(c)}$	219	34	115	216	-	584
SCA$^{(m)}$	219	145	438	423	-	1225
SCA$^{(f)}$	219	216	696	746	-	1877
ASCA$^{(↻)}$	219	34	115	493	396	1257

4.5.6 Computational cost of updating the cluster interaction matrix

The previous results show that the computation of the cluster interaction tensors (Block C) plays a major role in the total computational cost of the clustering adaptivity procedures. In this regard, two important aspects have been discussed in in Section 4.4.5: (i) taking advantage of the cluster-symmetry property of cluster interaction tensors (see Equation (4.113)) and (ii) update the cluster interaction matrix such that only new clusters require a full computation of the cluster interaction tensors. It is important to emphasize that the computational cost of the cluster interaction tensors scales with the number of problem dimensions, the total number of voxels and the number of independent strain components. This cost is analyzed here assuming a 2D problem, a spatial discretization in a regular grid of $n_v = 400 \times 400$ voxels and an infinitesimal strain formulation with 3 independent strain components, similar to the problems analysed in the previous sections. Moreover, the computational speedup is here defined as the ratio between the computational time of the reference approach and the computational time of the proposed technique.

To illustrate the advantage of the cluster-symmetry property, the computation of all cluster interaction tensors is performed for a different number of clusters comprised between 3 and 316. Figure 4.29 compares the computational time with and without considering the cluster-symmetry property as well as the associated speedup. As expected, the cluster-symmetry property accelerates the computation and the speedup increases significantly with the number of clusters. This scaling is a direct consequence of the increase in the number of cluster interaction tensors that are obtained directly through cluster-symmetry.



Figure 4.29: Comparison between the computational cost of the cluster interaction tensors with and without taking advantage of the cluster-symmetry property. Conditions: 2D problem, $n_v = 400 \times 400$, infinitesimal strain formulation with 3 independent strain components.

The analysis of the computational cost associated with the update of the cluster interaction matrix is more intricate. For a given clustering adaptivity step, this cost depends on the initial number of clusters, n_c^{init}, the number of unchanged clusters, n_c^{old}, and the number of new clusters, n_c^{new}. Assume that n_c^{old} and n_c^{new} are both defined as functions of n_c^{init} as

$$n_c^{\text{old}} = \text{nint}(\alpha\, n_c^{\text{init}}), \tag{4.118}$$

and

$$n_c^{\text{new}} = \text{nint}((1+\beta)\, n_c^{\text{init}}) - n_c^{\text{old}}, \tag{4.119}$$

where $\alpha \in [0,1]$ and $\beta \in [0,\infty[$. From these definitions, the parameter α sets the relative amount of initial clusters that are kept unchanged and parameter β sets the relative increase of the number of clusters resulting from the clustering adaptivity step. For the sake of clarity, assume that at the beginning of a clustering adaptivity step, one has $n_c^{\text{init}} = 10$ and $(\alpha,\beta) = (0.5, 1.0)$. This means that $n_c^{\text{old}} = 5$ clusters are not refined and the remaining 5 clusters are targeted, originating $n_c^{\text{new}} = 10$ new clusters and leading to a total of 20 clusters.

To illustrate the advantage of the procedure proposed in Section 4.4.5, Figure 4.30 shows the comparison of the computational cost associated with the update of the cluster interaction matrix on a given clustering adaptivity step. The standard procedure involves cycling through the cluster interaction matrix rows and columns in a sorted manner, computing the clustering interaction tensors and taking advantage of the cluster-symmetry property whenever possible. It is assumed that $\alpha = 0.75$, i.e., $n_c^{\text{old}} = \text{nint}(0.75\, n_c^{\text{init}})$ are kept unchanged, and the relative increase of the number of clusters is varied according to $\beta \in [0.25, 1.0]$.



(a) (b)

Figure 4.30: Computational cost associated with the update of the cluster interaction matrix on a given clustering adaptivity step ($\alpha = 0.75$): (a) Comparison between standard and proposed approaches; (b) Speedup resulting from the proposed approach. Conditions: 2D problem, $n_v = 400 \times 400$, infinitesimal strain formulation with 3 independent strain components.

In the first place, it is possible to observe that the proposed strategy is more efficient than the standard approach in the whole spectrum of the number of initial clusters, n_c^{init}. In the second place, it is seen that the speedup decreases as the number of initial clusters increases. This is expected given that the computational savings associated with the convolution of previously existing clusters interaction tensors becomes less relevant as the total number of computed tensors increases. Finally, the speedup also decreases as the relative number of new clusters increases and the full computation of the associated cluster interaction tensors becomes dominant.

At last, Figure 4.31 compiles the computational cost associated with the update of the cluster interaction matrix for $n_c^{init} \in [6,178]$, $\alpha \in [0,0.75]$ and $\beta \in [0.25,1.0]$[21]. As expected, the computational cost increases significantly with the increase of the number of initial clusters, i.e., the update of the cluster interaction matrix tends to become more expensive as the clustering adaptivity advances. For a given number of initial clusters, n_c^{init}, and a given number of unchanged clusters (fixed α), the computational cost increases with the number of new clusters as more cluster interaction tensors must be computed. For a given number of initial clusters, n_c^{init}, and a given number of new clusters (fixed β), the computational cost increases as the number of unchanged clusters decreases. Maximum computational cost occurs in the particular case where all clusters are adapted ($\alpha = 0$, $\beta > 0$), i.e., a whole new cluster interaction matrix must be computed.



Figure 4.31: Computational cost associated with the update of the cluster interaction matrix on a given clustering adaptivity step. Conditions: 2D problem, $n_v = 400 \times 400$, infinitesimal strain formulation with 3 independent strain components.

The previous analyses evidence that the computation of the cluster interaction tensors (Block C) plays a major role in the total computational cost of ASCA. Despite some improvements, it is clear that this challenge must be thoroughly addressed in future work to allow a more efficient clustering adaptivity and, therefore, improve the performance of ASCA.

[21] It is possible to verify that the constraint $\beta >= 1 - \alpha$ applies irrespective of the number of initial clusters.

4.6 Efficient finite strain FFT-based homogenization

4.6.1 FFT-based homogenization offline-stage

Since the pioneering contribution by Moulinec and Suquet (Moulinec and Suquet, 1994) (see Section 4.2.1 and Appendix B), FFT-based homogenization methods have been developed as a powerful approach to perform first-order multi-scale analyses based on computational homogenization (e.g., Kabel et al. (2014), de Geus et al. (2017), Lucarini and Segurado (2019)).

FFT-based homogenization methods are particularly appealing in the context of CROMs, namely to compute the material response dataset over which the cluster analysis is conducted. Several advantages of this family of methods are pointed out by Schneider and coworkers (Schneider et al., 2019). In the first place, these methods operate on a regular cartesian grid of pixels or voxels, where the coordinates of any discrete (sampling) point are well-defined by the sampling period along each dimension. This avoids the need of building a suitable finite element mesh, an operation which usually demands specialized softwares and may yield significant computational costs when dealing with complex microstructures[22]. In addition, it allows the direct use of the experimental output of microstructure imaging techniques (Cocco et al., 2013). In the second place, these methods take advantage of highly optimized Fast Fourier Transform (FFT) algorithms and avoid the assembly of system-sized coefficients matrices ($n_{\text{dof}} \times n_{\text{dof}}$, where n_{dof} stands for the total number of degrees of freedom), which leads to high efficiency and low memory footprint. Finally, FFT-based homogenization methods are, in general, fairly comprehensible and can be easily implemented.

In the particular cases of the SCA (Liu et al., 2016) and ASCA (see Sections 4.4-4.5) methods, FFT-based homogenization methods can be adopted to perform the required offline-stage DNS analyses, namely to compute the fourth-order local elastic strain concentration tensors (see Section C.2 under infinitesimal strains and Section 4.7.1 under finite strains). Despite some well-known drawbacks, namely the convergence rate when dealing with highly contrasting material phases (Michel et al., 2001) and sources of spurious field oscillations (Ma et al., 2021), the Moulinec-Suquet FFT-based homogenization basic scheme (Moulinec and Suquet, 1994) is remarkably useful in this context. Given the elastic (infinitesimal strains) or hyperelastic (finite strains) nature of the micro-scale equilibrium problems and the Lippmann-Schwinger-type equilibrium formulation: (i) shares the same fundamental equilibrium formulation as SCA and ASCA, e.g., renders a similar implementation of the Green operator in the frequency domain (see Equations (4.21) and (4.48)) that can be readily applied to compute the cluster interaction tensors; (ii) the implementation of the underlying fixed-point iterative scheme is straightforward (see Box B.1 and Box 4.1); (iii) allows a highly efficient computational implementation based on Hadamard operations.

Despite the finite strain extension of the FFT-based homogenization basic scheme has already been performed in the literature and proven successful (Eisenlohr et al. (2013), Kabel et al. (2014)), the theoretical formulation is here briefly described following the infinitesimal strains counterpart (see Appendix B). This provides a suitable basis to propose a highly efficient implementation strategy as well as to discuss specific requirements of the SCA/ASCA offline-stage.

[22] However, it should be noticed that the constraint of having a regular grid discretization may yield unnecessary costs when dealing with topologically simple microstructures. In contrast with a finite element mesh, where the spatial discretization can be locally optimized where needed, a regular grid discretization always propagates a given refinement over the whole dimension length.

4.6.2 FFT-based homogenization basic scheme (finite strains)

Let us assume a heterogeneous RVE of domain Ω_μ and boundary $\partial\Omega_\mu$, with dimensions $(l_{\text{RVE}})_i$, $i = 1,\dots,n_{\text{dim}}$, composed of a given number of perfectly bonded hyperelastic phases. Following standard first-order homogenization multi-scale kinematic procedures, further assume that a given macro-scale deformation gradient, $\boldsymbol{F}(\boldsymbol{X})$, is prescribed such that

$$\boldsymbol{F}(\boldsymbol{X}) = \frac{1}{v_{\mu,0}} \int_{\Omega_{\mu,0}} \boldsymbol{F}_\mu(\boldsymbol{Y})\, \mathrm{d}v\,, \tag{4.120}$$

where $v_{\mu,0}$ denotes the volume of the RVE in the reference configuration, and periodic boundary conditions are adopted.

In the absence of body forces, the micro-scale quasi-static equilibrium problem consists of finding the micro-scale deformation gradient field that satisfies the strong equilibrium equations established in a material description as

$$\mathrm{div}_0\,[\boldsymbol{P}_\mu(\boldsymbol{Y})] = \boldsymbol{0} \quad \text{with} \quad \boldsymbol{P}_\mu(\boldsymbol{Y}) = \boldsymbol{P}_\mu(\boldsymbol{F}_\mu(\boldsymbol{Y}))\,, \quad \forall\, \boldsymbol{Y} \in \Omega_{\mu,0}\,. \tag{4.121}$$

As demonstrated in Chapter 4 (see Section 4.2.2), the micro-scale quasi-static equilibrium problem can be formulated as a Lippmann-Schwinger nonlinear integral equilibrium equation. The latter is conveniently recovered here in both frequency and spatial domains as

$$\check{\boldsymbol{F}}_\mu(\boldsymbol{\zeta}) = -\check{\boldsymbol{\Phi}}^0(\boldsymbol{\zeta}) : \check{\boldsymbol{P}}^*_\mu(\boldsymbol{\zeta})\,, \quad \forall \boldsymbol{\zeta} \neq \boldsymbol{0}\,, \quad \check{\boldsymbol{F}}_\mu(\boldsymbol{0}) = \boldsymbol{F}(\boldsymbol{X})\,, \tag{4.122}$$

and

$$\boldsymbol{F}_\mu(\boldsymbol{Y}) = -\int_{\Omega_{\mu,0}} \boldsymbol{\Phi}^0(\boldsymbol{Y}-\boldsymbol{Y}') : \boldsymbol{P}^*_\mu(\boldsymbol{Y}')\, \mathrm{d}v' + \boldsymbol{F}(\boldsymbol{X})\,, \quad \forall\, \boldsymbol{Y} \in \Omega_{\mu,0}\,. \tag{4.123}$$

respectively, where $\boldsymbol{\Phi}^0$ denotes the Green operator associated with the reference micro-scale eigenstress problem and $\boldsymbol{P}^*_\mu$ denotes the stress polarization (or eigenstress) field,

$$\boldsymbol{P}^*_\mu(\boldsymbol{Y}) = \boldsymbol{P}_\mu(\boldsymbol{F}_\mu(\boldsymbol{Y})) - \mathbf{A}^{e,0} : \boldsymbol{F}_\mu(\boldsymbol{Y})\,. \tag{4.124}$$

Similar to the infinitesimal strain counterpart, it is assumed to be an isotropic elastic reference material (see Equation (4.18)) with Lamé parameters (λ^0, μ^0), which renders a closed-form expression of the Green operator in the frequency domain (see Equation (4.48)).

After performing a suitable discretization of the RVE in a regular grid of voxels (see Section B.2), the Lippmann-Schwinger integral equilibrium equation can then be solved through the Moulinec-Suquet fixed point iterative procedure (Moulinec and Suquet, 1994) as detailed in pseudo-code format in Box 4.1. The same numerical aspects described in Section B.3 apply here as well, provided that the deformation gradient and the first Piola-Kirchhoff are considered instead. However, in contrast with the infinitesimal strain case, the geometrical nonlinearity arising from hyperelasticity calls for a suitable time discretization of the Lippmann-Schwinger integral equilibrium equation and a proper multiplicative decomposition-based loading incrementation (see Section 4.7.2).

Box 4.1: Finite strain extension of the FFT-based homogenization basic scheme Moulinec and Suquet (1994) fixed point iterative procedure applied to the solution of the incremental Lippmann-Schwinger integral equilibrium equation associated with a general loading increment $[t_m, t_{m+1}]$ of a micro-scale quasi-static equilibrium problem. The subscript $(\bullet)_s$ denotes the discrete nature of the sampling points (spatial domain) and angular frequencies (frequency domain).

(i) Initialize iterative counter, $k := 0$

(ii) Set Lamé parameters of homogeneous reference material, $\left(\lambda^0, \mu^0\right)$

(iii) Set initial guess for the micro-scale discrete deformation gradient field (spatial domain)

if $(n = 0)$ then

$$\boldsymbol{F}^{(0)}_{\mu,\,m+1}(\boldsymbol{Y}_s) = \boldsymbol{F}_{m+1}(\boldsymbol{X}), \quad \forall \boldsymbol{Y}_s \in \Omega_{\mu,0}$$

else

$$\boldsymbol{F}^{(0)}_{\mu,\,m+1}(\boldsymbol{Y}_s) = \boldsymbol{F}_{\mu,\,m}(\boldsymbol{Y}_s), \quad \forall \boldsymbol{Y}_s \in \Omega_{\mu,0}$$

(iv) Compute micro-scale discrete stress field (spatial domain)

$$\boldsymbol{P}^{(k)}_{\mu,\,m+1}(\boldsymbol{Y}_s) = \boldsymbol{P}_{\mu,m+1}\left(\boldsymbol{F}^{(k)}_{\mu,\,m+1}(\boldsymbol{Y}_s)\right), \quad \forall \boldsymbol{Y}_s \in \Omega_{\mu,0}$$

(v) Compute micro-scale discrete stress field (frequency domain)

$$\check{\boldsymbol{P}}^{(k)}_{\mu,\,m+1}(\boldsymbol{\zeta}_s) = \mathscr{DF}\mathscr{T}\left\{\boldsymbol{P}^{(k)}_{\mu,\,m+1}(\boldsymbol{Y}_s)\right\}$$

(vi) Check for convergence

if (converged) then

- Exit

else

- Increment iteration counter, $k := k + 1$

(vii) Update micro-scale discrete deformation gradient field (frequency domain)

$$\check{\boldsymbol{F}}^{(k)}_{\mu,\,m+1}(\boldsymbol{\zeta}_s) = \check{\boldsymbol{F}}^{(k-1)}_{\mu,\,m+1}(\boldsymbol{\zeta}_s) - \check{\boldsymbol{\Phi}}^{0}(\boldsymbol{\zeta}_s) : \check{\boldsymbol{P}}^{(k-1)}_{\mu,\,m+1}(\boldsymbol{\zeta}_s), \quad \forall \boldsymbol{\zeta}_s \neq \boldsymbol{0}, \quad \check{\boldsymbol{F}}^{(k)}_{\mu,\,m+1}(\boldsymbol{0}) = \boldsymbol{F}_{m+1}(\boldsymbol{X})$$

(viii) Compute micro-scale discrete deformation gradient field (spatial domain)

$$\boldsymbol{F}^{(k)}_{\mu,\,m+1}(\boldsymbol{Y}_s) = \mathscr{DF}\mathscr{T}^{-1}\left\{\check{\boldsymbol{F}}^{(k)}_{\mu,\,m+1}(\boldsymbol{\zeta}_s)\right\}$$

(ix) Go to step (iv)

4.6.3 Acceleration through Hadamard operations

Besides the operations that take advantage of highly optimized FFT algorithms (steps (v) and (viii) of Box 4.1), there are three procedures whose efficient computation must also be taken into account: (1) the computation of the Green operator (step (vii) of Box 4.1, see Equation (4.48)), (2) the computation of the micro-scale discrete stress field in the spatial domain (step (iv) of Box 4.1), and (3) the update of the micro-scale discrete strain field in the frequency domain (step (vii) of Box 4.1).

The most simple and naive approach to implementing such procedures relies on standard loops over the discrete sampling points (spatial domain) or angular frequencies (frequency domain). However, the complexity arising from the dimensional nested loops, coupled with all the required operations on second- and fourth-order tensors, leads to considerable computational costs as the discretization refinement increases. At the expense of a slight increase in terms of memory footprint, a simple but highly effective strategy is proposed here to avoid the aforementioned discrete loops. The idea is based on the definition of suitable regular grid-shaped n_{dim}-dimensional arrays, where n_{dim} is the number of spatial dimensions, and takes advantage of efficient element-wise operations to perform those procedures simultaneously over the whole discretized domain. This approach is valid for both infinitesimal and finite strain settings and can be analogously adopted in other FFT-based homogenization methods. Moreover, a similar approach can be applied to perform key computations of the SCA method efficiently.

The so-called Hadamard (element-wise) operations are employed to describe the proposed approach, namely the Hadamard product ($(\mathbf{A}\circ\mathbf{B})_{ij} = A_{ij}B_{ij}$), the Hadamard p-power ($(\mathbf{A}^{\circ p})_{ij} = A_{ij}^{p}$), and the Hadamard division ($(\mathbf{A}\oslash\mathbf{B})_{ij} = A_{ij}/B_{ij}$). Moreover, for the sake of compactness, only the two-dimensional case is described, being the three-dimensional cases completely analogous. The notation $[\bullet]$ is adopted in this section to denote any regular grid-shaped array.

Green operator

The Green operator (see Equation (4.48)) is a fourth-order tensor that must be computed at every discrete frequency, $\boldsymbol{\zeta}_s$. Besides its role in the Moulinec-Suquet FFT-based homogenization basic scheme (step (vii) of Box 4.1), note that the Green operator is also required to compute the cluster interaction tensors arising in the formulation of the SCA (see Equation (4.100)).

In the two-dimensional case, all discrete angular frequencies can be conveniently stored in two regular grid-shaped arrays as

$$[\zeta_{s_1}] = \begin{bmatrix} \zeta_{s_1=0} & \cdots & \zeta_{s_1=0} \\ \vdots & \ddots & \vdots \\ \zeta_{s_1=n_1-1} & \cdots & \zeta_{s_1=n_1-1} \end{bmatrix}, \qquad [\zeta_{s_2}] = \begin{bmatrix} \zeta_{s_2=0} & \cdots & \zeta_{s_2=n_2-1} \\ \vdots & \ddots & \vdots \\ \zeta_{s_2=0} & \cdots & \zeta_{s_2=n_2-1} \end{bmatrix}, \tag{4.125}$$

from which the norm of each discrete angular frequency, $\|\boldsymbol{\zeta}_s\|$, can be obtained as

$$[\boldsymbol{\zeta}_s] = \left([\zeta_{s_1}]\circ[\zeta_{s_2}]\right)^{\circ\frac{1}{2}}. \tag{4.126}$$

With the previous arrays at hand, each component $\check{\Phi}^0_{klij}$ of the Green operator (see Equation (4.48)) can be computed simultaneously at every discrete angular frequency as

$$\left[\check{\Phi}^0_{klij}\right] = \frac{1}{2\mu^0}\delta_{ki}\left(\left[\zeta_{s_j}\right]\circ\left[\zeta_{s_l}\right]\right)\oslash[\boldsymbol{\zeta}_s]^{\circ 2} - \frac{\lambda^0}{2\mu^0(\lambda^0+2\mu^0)}\left(\left[\zeta_{s_k}\right]\circ\left[\zeta_{s_l}\right]\circ[\zeta_{s_i}]\circ\left[\zeta_{s_j}\right]\right)\oslash[\boldsymbol{\zeta}_s]^{\circ 4}. \tag{4.127}$$

The comparison between the computational time associated with the naive and proposed approaches is illustrated in Figure 4.32(a). In terms of memory footprint, each regular grid-shaped array associated with a very fine 1000×1000 regular grid ($n_v = 10^6$) allocates 7.63MB when stored in a Python NumPy array.



Figure 4.32: Comparison between the computational time (s) associated with the naive (discrete loops) and proposed (Hadamard operations) approaches in the finite strain two-dimensional computation of: (a) Green operator; (b) Hyperelastic Saint Venant-Kirchhoff discrete stress field. The computational speedup is defined as the ratio between the computational time of the naive and proposed approaches.

Micro-scale discrete stress field (spatial domain)

The computation of the micro-scale discrete stress field in the spatial domain (step (iv) of Box 4.1) involves performing the hyperelastic state update at every sampling point, $\boldsymbol{Y}_s$, for $\boldsymbol{F}^{(k)}_{\mu,n+1}(\boldsymbol{Y}_s)$. For demonstrative purposes, let us assume that the material phases hyperelastic constitutive behavior is isotropic and governed by the Saint Venant-Kirchhoff model (see Equation (4.160)). Given that the equilibrium problem is formulated in terms of the deformation gradient and the first Piola-Kirchhoff stress tensor, the hyperelastic state update requires three main operations at every sampling point: (i) the computation of the Green-Lagrange strain tensor from the deformation gradient, (ii) the computation of the Second Piola-Kirchhoff from the hyperelastic constitutive law, and (iii) the computation of the first Piola-Kirchhoff stress tensor from the second Piola-Kirchhoff stress tensor.

Firstly, if the components of the micro-scale deformation gradient, $\boldsymbol{F}_\mu$, are conveniently stored in (and always operated on as) regular grid-shaped arrays, i.e., $[F_{11}]$, $[F_{21}]$, $[F_{12}]$ and $[F_{22}]$, each component of the Green-Lagrange strain tensor can be computed as

$$[E_{11}] = \frac{1}{2}\left([F_{11}] \circ [F_{11}] + [F_{21}] \circ [F_{21}] - 1.0\right), \tag{4.128}$$

$$[E_{22}] = \frac{1}{2}\left([F_{12}] \circ [F_{12}] + [F_{22}] \circ [F_{22}] - 1.0\right), \tag{4.129}$$

$$[E_{12}] = \frac{1}{2}\left([F_{11}] \circ [F_{12}] + [F_{21}] \circ [F_{22}]\right). \tag{4.130}$$

Secondly, by conveniently defining the regular grid-shaped arrays containing the three distinct components of the isotropic elasticity tensor (see Equation (4.45)) at each sampling point[23], i.e., $[\lambda]$, $[2\mu]$, and $[\lambda+2\mu]$, the components of the second Piola-Kirchhoff stress tensor can be computed simultaneously at every sampling point as

$$[S_{11}] = [\lambda+2\mu] \circ [E_{11}] + [\lambda] \circ [E_{22}] \,, \tag{4.131}$$
$$[S_{22}] = [\lambda] \circ [E_{11}] + [\lambda+2\mu] \circ [E_{22}] \,, \tag{4.132}$$
$$[S_{12}] = [2\mu] \circ [E_{12}] \,. \tag{4.133}$$

Lastly, the first Piola-Kirchhoff stress tensor can be computed as

$$[P_{11}] = [F_{11}] \circ [S_{11}] + [F_{12}] \circ [S_{21}] \,, \tag{4.134}$$
$$[P_{21}] = [F_{21}] \circ [S_{11}] + [F_{22}] \circ [S_{21}] \,, \tag{4.135}$$
$$[P_{12}] = [F_{11}] \circ [S_{12}] + [F_{12}] \circ [S_{22}] \,, \tag{4.136}$$
$$[P_{22}] = [F_{21}] \circ [S_{12}] + [F_{22}] \circ [S_{22}] \,. \tag{4.137}$$

With the exception of the computation of the tensor logarithm, similar operations can be carried out for the Hencky hyperelastic model (see Equation (4.161)). While the computation of the Kirchhoff stress tensor is analogous to Equations (4.131)-(4.133), the computation of the first Piola-Kirchhoff stress tensor is slightly more involving and given by

$$[P_{11}] = \left[\left(\det[\boldsymbol{F}]\right)^{-1}\right] \left([\tau_{11}] \circ [F_{22}] - [\tau_{12}] \circ [F_{12}]\right) , \tag{4.138}$$
$$[P_{21}] = \left[\left(\det[\boldsymbol{F}]\right)^{-1}\right] \left([\tau_{21}] \circ [F_{22}] - [\tau_{22}] \circ [F_{12}]\right) , \tag{4.139}$$
$$[P_{12}] = \left[\left(\det[\boldsymbol{F}]\right)^{-1}\right] \left([\tau_{12}] \circ [F_{11}] - [\tau_{11}] \circ [F_{21}]\right) , \tag{4.140}$$
$$[P_{22}] = \left[\left(\det[\boldsymbol{F}]\right)^{-1}\right] \left([\tau_{22}] \circ [F_{11}] - [\tau_{21}] \circ [F_{21}]\right) . \tag{4.141}$$

The comparison between the computational time associated with the naive and proposed approaches is illustrated in Figure 4.32(b).

Micro-scale discrete deformation gradient field (frequency domain)

The update of the micro-scale discrete deformation gradient field in the frequency domain (step (vii) of Box 4.1) follows a similar approach and relies on the previously described regular grid-shaped arrays as (increment subscript omitted for compactness)

$$\begin{aligned}\left[\check{F}^{(k)}_{\mu,ij}\right] = \left[\check{F}^{(k-1)}_{\mu,ij}\right] - \Bigg(&\left[\check{\Phi}^{0}_{ij11}\right] \circ \left[\check{P}^{(k-1)}_{\mu,11}\right] + \left[\check{\Phi}^{0}_{ij21}\right] \circ \left[\check{P}^{(k-1)}_{\mu,21}\right] \\ &+ \left[\check{\Phi}^{0}_{ij12}\right] \circ \left[\check{P}^{(k-1)}_{\mu,12}\right] + \left[\check{\Phi}^{0}_{ij22}\right] \circ \left[\check{P}^{(k-1)}_{\mu,22}\right] \Bigg) ,\end{aligned} \tag{4.142}$$

where $i, j = 1, 2$, and

$$\left[\check{F}^{(k)}_{\mu,ij}\right] (\boldsymbol{\zeta}_s = \boldsymbol{0}) = \left[F_{ij}(\boldsymbol{X})\right] . \tag{4.143}$$

[23] Note that the elastic properties' regular grid-shaped arrays only need to be computed once in the problem initialization.

Infinitesimal strain case

The proposed approach can be analogously applied to the infinitesimal strain case as follows:

- **Green operator**. Each component $\check{\Phi}^0_{klij}$ of the Green operator (see Equation (4.21)) can be computed simultaneously at every discrete angular frequency as

$$\left[\check{\Phi}^0_{klij}\right] = \frac{1}{2\mu^0}\delta_{ki}\Bigg(\left[\zeta_{s_j}\right]\circ\left[\zeta_{s_l}\right] + \left[\zeta_{s_i}\right]\circ\left[\zeta_{s_l}\right] + \left[\zeta_{s_j}\right]\circ\left[\zeta_{s_k}\right] + \left[\zeta_{s_i}\right]\circ\left[\zeta_{s_k}\right]\Bigg)\oslash\left[\boldsymbol{\zeta}_s\right]^{\circ 2} - \frac{\lambda^0+\mu^0}{\mu^0(\lambda^0+2\mu^0)}\Big(\left[\zeta_{s_k}\right]\circ\left[\zeta_{s_l}\right]\circ\left[\zeta_{s_i}\right]\circ\left[\zeta_{s_j}\right]\Big)\oslash\left[\boldsymbol{\zeta}_s\right]^{\circ 4}. \tag{4.144}$$

- **Micro-scale discrete stress field (spatial domain)**. The components of the Cauchy stress tensor under isotropic elasticity (see step (iv) of Box B.1) can be computed simultaneously at every sampling point as

$$\left[\sigma_{11}\right] = \left[\lambda+2\mu\right]\circ\left[\varepsilon_{11}\right] + \left[\lambda\right]\circ\left[\varepsilon_{22}\right], \tag{4.145}$$
$$\left[\sigma_{22}\right] = \left[\lambda\right]\circ\left[\varepsilon_{11}\right] + \left[\lambda+2\mu\right]\circ\left[\varepsilon_{22}\right], \tag{4.146}$$
$$\left[\sigma_{12}\right] = \left[2\mu\right]\circ\left[\varepsilon_{12}\right]. \tag{4.147}$$

- **Micro-scale discrete strain field (frequency domain)**. The update of the micro-scale discrete strain field in the frequency domain (step (vii) of Box B.1) can be performed as

$$\left[\check{\varepsilon}^{(k)}_{\mu,ij}\right] = \left[\check{\varepsilon}^{(k-1)}_{\mu,ij}\right] - \Big(\left[\check{\Phi}^0_{ij11}\right]\circ\left[\check{\sigma}^{(k-1)}_{\mu,11}\right] + \left[\check{\Phi}^0_{ij12}\right]\circ\left[\check{\sigma}^{(k-1)}_{\mu,12}\right] + \left[\check{\Phi}^0_{ij22}\right]\circ\left[\check{\sigma}^{(k-1)}_{\mu,22}\right]\Big), \tag{4.148}$$

  where $i, j = 1, 2$, and

$$\left[\check{\varepsilon}^{(k)}_{\mu,ij}\right](\boldsymbol{\zeta}_s = \mathbf{0}) = \left[\varepsilon_{ij}(\boldsymbol{X})\right]. \tag{4.149}$$

The comparison between the computational time associated with the naive and proposed approaches is illustrated in Figure 4.33.



Figure 4.33: Comparison between the computational time (s) associated with the naive (discrete loops) and proposed (Hadamard operations) approaches in the infinitesimal strains two-dimensional computation of: (a) Green operator; (b) Linear elastic Cauchy discrete stress field. The computational speedup is defined as the ratio between the computational time of the naive and proposed approaches.

4.7 Finite strain SCA under multiplicative kinematics

This section aims to propose a finite strain extension of the SCA method compatible with the multiplicative nature of the deformation gradient[24]. Besides the alternative formulation of the online-stage in comparison with the contribution by Yu and coworkers (Yu et al., 2019), several aspects of the offline-stage that, to the best of the author's knowledge, were not yet addressed in the literature, are discussed as well. The following sections also attempt to provide all the numerical details required for a suitable computational implementation.

Remark.
An overview of the SCA method (Liu et al., 2016), originally proposed under infinitesimal strains, is provided in Section C.1 and schematically illustrated in Figure C.1. The finite strain extension covered in the remainder of this section keeps exactly the same two-stage structure and the underlying algorithmic steps described in Sections C.2-C.6. For this reason, rather than providing a similar step-by-step description as in Appendix C, the focus is given to the actual mathematical formulation intrinsically associated to finite strains.

4.7.1 Revisiting SCA's offline-stage under finite strains

Three relevant aspects of the finite strain SCA's offline-stage are addressed in what follows: (1) the finite strain clustering feature, (2) the choice of the hyperelastic constitutive models, and (3) the nonlinearity of the fourth-order local elastic strain concentration tensor.

Finite strain clustering feature

Under infinitesimal strains, Liu and coworkers (Liu et al., 2016) propose to evaluate the mechanical behavior similarity of different material points based on the fourth-order local elastic strain concentration tensor (see Section C.2). Yu and coworkers (Yu et al., 2019) readily extended this approach to finite strains by defining the fourth-order local elastic strain concentration tensor as the relation between the macro-scale deformation gradient, $\boldsymbol{F}^e(\boldsymbol{X})$, and the micro-scale deformation gradient tensor, $\boldsymbol{F}^e_\mu(\boldsymbol{Y})$,

$$\boldsymbol{F}^e_\mu(\boldsymbol{Y}) = \mathbf{H}^e(\boldsymbol{Y}) : \boldsymbol{F}^e(\boldsymbol{X}), \quad \forall \boldsymbol{Y} \in \Omega_{\mu,0}. \tag{4.150}$$

Given the general nonsymmetry of the deformation gradient tensor, the computation of $\mathbf{H}^e(\boldsymbol{Y})$ requires the DNS solution of 4 (2D) and 9 (3D) hyperelastic micro-scale equilibrium problems under orthogonal loading constraints. However, besides the increasing computational cost stemming from a higher number of required DNS analyses, the orthogonal loading constraints cannot be defined as in the infinitesimal strain case because $F^e_{ii}(\boldsymbol{X}) \neq 0$, $i = 1,\dots,n_{\text{dim}}$. To overcome this limitation, $\mathbf{H}^e(\boldsymbol{Y})$ could be alternatively computed by finite differences. For instance, by choosing a given base macro-scale deformation gradient, $(\boldsymbol{F}^e(\boldsymbol{X}))^{\text{b}}$,

$$\mathsf{H}^e_{ij11}(\boldsymbol{Y}) = \left[(\boldsymbol{F}^e_\mu)^{11}(\boldsymbol{Y}) - (\boldsymbol{F}^e_\mu)^{\text{b}}(\boldsymbol{Y}) \right] / \delta, \quad i,j = 1,\dots,n_{\text{dim}}, \tag{4.151}$$

where $(\boldsymbol{F}^e_\mu)^{\text{b}}(\boldsymbol{Y})$ and $(\boldsymbol{F}^e_\mu)^{11}(\boldsymbol{Y})$ are the local strain responses associated with $(\boldsymbol{F}^e(\boldsymbol{X}))^{\text{b}}$ and $(\boldsymbol{F}^e)^{11}(\boldsymbol{X}) = (\boldsymbol{F}^e_\mu)^{\text{b}}(\boldsymbol{X}) + [\delta,0,0,0,\dots]^T$, respectively, and δ is a strain finite perturbation. Note that this procedure requires an additional DNS solution associated with the base micro-scale equilibrium problem under $(\boldsymbol{F}^e(\boldsymbol{X}))^{\text{b}}$.

[24] As remarked in Section 4.3.3, Yu and coworkers (Yu et al., 2019) adopt a clustered incremental Lippmann-Schwinger integral equilibrium equation by assuming an additive decomposition of the deformation gradient.

Nevertheless, a different approach is proposed here where both the previous limitations are overcome. Given that the finite strain SCA's online-stage is formulated in the reference configuration (see Section 4.3.3), the fourth-order local elastic strain concentration tensor is instead defined as

$$\boldsymbol{E}^e_\mu(\boldsymbol{Y}) = \mathbf{H}^e(\boldsymbol{Y}) : \boldsymbol{E}^e(\boldsymbol{X}), \quad \forall\, \boldsymbol{Y} \in \Omega_{\mu,0}, \tag{4.152}$$

where $\boldsymbol{E}^e$ is the elastic material logarithmic strain tensor defined as

$$\boldsymbol{E}^e = \frac{1}{2} \ln\left[(\boldsymbol{F}^e)^T \boldsymbol{F}^e\right]. \tag{4.153}$$

In the first place, the infinitesimal strain case is recovered for sufficiently small strains for which $\boldsymbol{E}^e \rightarrow \boldsymbol{\varepsilon}^e$. Second, given that the material logarithmic strain tensor is symmetric, the required number of DNS analyses is reduced to 3 (2D) and 6 (3D), similar to the case of infinitesimal strains. Finally, the orthogonal loadings needed to compute $\mathbf{H}^e(\boldsymbol{Y})$ can now be properly defined in the standard way (see Section C.2). On the downside, it should be noted that the choice of a symmetric strain tensor does not allow orthogonal simple shear loadings, i.e., the constraint $E^e_{ij} = E^e_{ji}$ implies orthogonal pure shear loadings. However, given that the strain concentration tensor already aggregates material response data of several loading constraints, this is not considered a relevant drawback.

Remark.
The computation of the fourth-order local elastic strain concentration tensor defined by Equation (4.152) *allows the simultaneous and analogous computation of the RVE effective elastic tangent modulus,* $\overline{\mathbf{A}}^e$. *In fact, the material counterpart of the isotropic Hencky hyperelastic model (see Equation* (4.161)*) yields*[25]

$$\boldsymbol{R}^T \boldsymbol{P} \boldsymbol{F}^T \boldsymbol{R} = \mathbf{A}^e : \boldsymbol{E}, \tag{4.155}$$

where the left-hand side is the stress conjugate to the material logarithmic strain tensor and the rotation tensor can be determined as

$$\boldsymbol{R} = \boldsymbol{F}(\boldsymbol{F}^T \boldsymbol{F})^{-\frac{1}{2}}. \tag{4.156}$$

Therefore, given the set of orthogonal macro-scale material logarithmic strain loadings, each column of the matricial form of the RVE effective elastic tangent modulus is obtained by computing the homogenized stress conjugate according to Equation (4.155). *Such data may be applied, for instance, to set the (initial) properties of the reference homogeneous elastic material in the SCA's online-stage (see Section 4.3.3). A similar approach can be adopted in the infinitesimal strains setting where the stress conjugate is simply the Cauchy stress tensor,*

$$\boldsymbol{\sigma} = \mathbf{D}^e : \boldsymbol{\varepsilon}. \tag{4.157}$$

It should also be remarked that many DNS methods available to solve micro-scale equilibrium problems have the macro-scale deformation gradient as the loading constraint (e.g., see Sections 2.11 and 4.6). In this case, the adoption of the proposed strategy requires to finding the macro-scale deformation gradient, $\boldsymbol{F}^e(\boldsymbol{X})$, associated with each orthogonal material

[25] Proof stems from the known relation between the material and spatial logarithmic strain tensors, $\boldsymbol{\varepsilon} = \boldsymbol{R}\boldsymbol{E}\boldsymbol{R}^T$, and the isotropy of the fourth-order elasticity tensor,

$$D^e_{ijkl} = R_{mi} R_{nj} R_{pq} R_{ql} D^e_{mnpq}, \tag{4.154}$$

for any rotation tensor, $\boldsymbol{R}$.

logarithmic strain tensor, $\boldsymbol{E}^e(\boldsymbol{X})$. Given that such relation is not unique, i.e., there is a multiplicity of $\boldsymbol{F}^e(\boldsymbol{X})$ that renders the same $\boldsymbol{E}^e(\boldsymbol{X})$, a particular choice must be made. Since $\boldsymbol{E}^e(\boldsymbol{X})$ is symmetric, it follows from the spectral theorem that it admits the spectral decomposition

$$\boldsymbol{E}^e(\boldsymbol{X}) = \sum_{i=1}^{3} \lambda_i^{\boldsymbol{E}} \, \boldsymbol{l}_i^{\boldsymbol{E}} \otimes \boldsymbol{l}_i^{\boldsymbol{E}}, \tag{4.158}$$

where $\lambda_i^{\boldsymbol{E}}$ and $\boldsymbol{l}_i^{\boldsymbol{E}}$, $i = 1,2,3$, are the eigenvalues and eigenvectors of $\boldsymbol{E}^e$. By assuming coaxiality between $\boldsymbol{F}^e(\boldsymbol{X})$ and $\boldsymbol{E}^e(\boldsymbol{X})$, a unique symmetric $\boldsymbol{F}^e(\boldsymbol{X})$ can be defined as

$$\boldsymbol{F}^e(\boldsymbol{X}) = \sum_{i=1}^{3} \lambda_i^{\boldsymbol{F}} \, \boldsymbol{l}_i^{\boldsymbol{E}} \otimes \boldsymbol{l}_i^{\boldsymbol{E}}, \tag{4.159}$$

where it follows from Equation (4.153) that $\lambda_i^{\boldsymbol{F}} = \exp\left[\lambda_i^{\boldsymbol{E}}\right]$, $i = 1,2,3$. This particular choice is perfectly aligned with the already symmetric material logarithmic strain orthogonal loading.

Choice of hyperelastic models

One of the main bottlenecks of training-prediction two-stage algorithms is the computational cost associated with the training offline-stage. By adopting the fourth-order local elastic strain concentration tensor as the clustering feature, Liu and coworkers (Liu et al., 2016) circumvent this limitation by restricting the DNS analyses to fast linear elastic micro-scale equilibrium problems (see Section C.2). Taking advantage of the same approach, the finite strain SCA's offline-stage calls for a hyperelastic constitutive formulation. Despite the now geometrically nonlinear micro-scale equilibrium problem, material linearity still allows efficient DNS analyses to be carried out.

In contrast with the infinitesimal strain setting, where the linear elastic constitutive model is adopted for all material phases, a suitable hyperelastic constitutive model must be chosen and associated with each material phase. Such a choice should be determined from the actual finite strain constitutive model governing the material phase's behavior in the prediction stage. Two cases of interest are addressed below: the Saint Venant-Kirchhoff and the Hencky hyperelastic models.

The Saint Venant-Kirchhoff model is perhaps the simplest hyperelastic constitutive model, extending the geometrical linear elastic model as

$$\boldsymbol{S} = \mathbf{D}^e : \boldsymbol{E}^{(2)}, \tag{4.160}$$

where $\boldsymbol{S}$ is the second Piola-Kirchhoff stress tensor, $\boldsymbol{E}^{(2)}$ is the Green-Lagrange strain tensor and $\mathbf{D}^e$ is the fourth-order elasticity tensor. This hyperelastic model is commonly employed in the formulation of finite strain polycrystalline elasto-plastic constitutive models for metals and metallic alloys (e.g., Turteltaub and Suiker (2005), Kim (2014), de Carvalho et al. (2022)), where $\mathbf{D}^e$ follows a suitable anisotropic assumption according to the crystallographic structure and orientation. Moreover, the Saint Venant-Kirchhoff model can be efficiently implemented to perform fast DNS analyses through the simultaneous constitutive state update of all material domain points (see Section 4.6.3).

The Hencky hyperelastic model is the finite logarithmic strain-based extension of the geometrical linear elastic model and is defined as

$$\boldsymbol{\tau} = \mathbf{D}^e : \boldsymbol{\varepsilon}, \tag{4.161}$$

where $\boldsymbol{\tau}$ is the Kirchhoff stress tensor, $\boldsymbol{\varepsilon}$ is the spatial logarithmic strain tensor and $\mathbf{D}^e$ is the fourth-order elasticity tensor. By adopting the elasto-plastic multiplicative decomposition of

the deformation gradient ($\boldsymbol{F} = \boldsymbol{F}^e\boldsymbol{F}^p$) and the isotropic Hencky model to describe the elastic behavior,

$$\mathbf{D}^e = \lambda\, \boldsymbol{I} \otimes \boldsymbol{I} + 2\mu\, \mathbf{I}_S\,, \tag{4.162}$$

where $\boldsymbol{I}$ is the second-order identity tensor, $\mathbf{I}_S$ is the fourth-order symmetric identity tensor, and (λ, μ) are the Lamé parameters, a rather general class of isotropic hyperelastic-based finite strain elasto-plastic constitutive models can be formulated following the formalism of thermodynamics with internal variables (see Appendix F). In particular, the use of a suitable exponential map-based integrator for the plastic flow rule allows a return-mapping-based state update procedure with a similar functional format to the infinitesimal strains case, being the finite strain extension purely kinematical.

Geometrical nonlinearity of the strain concentration tensor

Due to the geometrical and material linearity of the elastic micro-scale equilibrium problem under infinitesimal strains, the fourth-order local elastic strain concentration tensor (see Equation (C.1)) is only a function of the spatial coordinates, i.e., $\mathbf{H}^e = \mathbf{H}^e(\boldsymbol{Y})$. Provided a suitable normalization, this means that the local elastic strain concentration tensors remain constant whether the magnitude of the orthogonal loadings is unitary (see Section C.2) or takes any other value. However, irrespective of the adopted strain metric, these tensors also depend on the actual magnitude of the imposed macro-scale strain loading under finite strains, i.e., enforcing unitary orthogonal loadings is no longer merely a mathematical convenience. This is a consequence of the geometrical nonlinearity stemming from the hyperelasticity constitutive formulation, rendering $\mathbf{H}^e = \mathbf{H}^e(\boldsymbol{Y}, \boldsymbol{E}^e(\boldsymbol{X}))$ when following the approach proposed by Equation (4.152).

The previous considerations are evidenced in Figure 4.34, where the norm of the fourth-order local elastic strain concentration tensor is compared between infinitesimal and finite strain formulations for different magnitudes of the imposed orthogonal macro-scale strain loadings. In particular, it is assumed that each orthogonal macro-scale strain loading has magnitude χ, and the computed local strain field (strain concentration tensor matrix column) is then normalized[26] by the factor χ^{-1}. Four domain points of a particle-reinforced hyperelastic composite RVE [27] are randomly selected and the strain magnitude factor χ ranges between 0.01% and 10%. The micro-scale equilibrium problems are solved with the finite strain extension of the FFT-based homogenization basic scheme proposed by Moulinec and Suquet (Moulinec and Suquet, 1994) (see Section 4.6), considering a spatial discretization of $n_v = 400 \times 400$ voxels and a total of 5 loading increments.

In the first place, it is possible to observe that the strain concentration tensor is constant under infinitesimal strains, as expected. In addition, both infinitesimal and finite strain formulations deliver similar results for a sufficiently small strain magnitude. In the second place, the nonlinearity of the strain concentration tensor is evident for a strain magnitude greater than 1%, with the associated norm significantly departing from the infinitesimal strain constant value. Finally and most importantly, the relation between the norm of the strain concentration tensors associated with different domain points changes with the strain magnitude. Consequently, the magnitude of the orthogonal strain loadings influences the offline-stage clustering of the CRVE under finite strains. In particular, note that the minimization problem of the well-known K-Means clustering algorithm evaluates precisely the

[26] Given the geometrical and material linearity in the infinitesimal strain setting, the particular choice of $\chi = 1$ recovers conveniently each column of the strain concentration tensor without any normalization.

[27] Both material phase constitutive behavior is governed by the isotropic Saint Venant-Kirchhoff hyperelastic model with the following elastic properties (SI units): $(E, \nu)_{\text{matrix}} = (100 \times 10^6, 0.30)$ and $(E, \nu)_{\text{particles}} = (500 \times 10^6, 0.19)$, where E and ν denote the Young modulus and Poisson ratio, respectively.

norm of the local elastic strain concentration tensors to group domain points into material clusters.



Figure 4.34: Comparison of the norm of the fourth-order local elastic strain concentration tensor between infinitesimal and finite strain for different magnitudes of the imposed orthogonal macro-scale strain loadings. While under infinitesimal strains (isotropic linear elasticity) this tensor remains constant, it depends on the magnitude of the applied loadings under finite strains (isotropic Saint Venant-Kirchhoff hyperelasticity).

4.7.2 Multiplicative decomposition-based loading incrementation

Given the multiplicative nature of the deformation gradient, a consistent multiplicative decomposition-based incrementation scheme is adopted to enforce the macro-scale strain constraint (see Equation (4.101)).

Let us assume that the prescribed deformation gradient is enforced in a total of n_{inc} increments and that a proportional loading factor, $\lambda \in [0,1]$, is defined such that $\lambda = 0$ is associated with the initially prescribed deformation gradient[28], $\bar{\boldsymbol{F}}_0(\boldsymbol{X})$, and $\lambda = 1$ with the total prescribed deformation gradient, $\bar{\boldsymbol{F}}(\boldsymbol{X})$. The total incremental prescribed deformation gradient, $\bar{\boldsymbol{F}}_\Delta$, is computed as

$$\bar{\boldsymbol{F}}_\Delta = \bar{\boldsymbol{F}}(\boldsymbol{X})(\bar{\boldsymbol{F}}_0(\boldsymbol{X}))^{-1}. \tag{4.163}$$

For simplicity, further assume that each increment is associated with a constant incremental proportional loading factor[29] defined as $\Delta\lambda = (n_{\text{inc}})^{-1}$. For a general time increment $[t_m, t_{m+1}]$, where $\boldsymbol{F}_m(\boldsymbol{X})$ is known, the prescribed deformation gradient at the instant t_{m+1} reads

$$\boldsymbol{F}_{m+1}(\boldsymbol{X}) = \left(\boldsymbol{F}_\Delta\right)_{m+1} \boldsymbol{F}_m(\boldsymbol{X}), \tag{4.164}$$

where the incremental deformation gradient tensor, $\left(\boldsymbol{F}_\Delta\right)_{m+1}$, is given by

[28] For instance, in the most simple case where the material is initially undeformed (reference configuration), the initially prescribed deformation gradient is $\bar{\boldsymbol{F}}_0(\boldsymbol{X}) = \boldsymbol{I}$.

[29] In the most general case, the prescribed proportional loading function $\lambda = \lambda(t)$ must be defined so that the incremental loading factor at each time increment $[t_m, t_{m+1}]$ is determined as $\Delta\lambda = \lambda(t_{m+1}) - \lambda(t_m)$.

$$\left(\boldsymbol{F}_{\Delta}\right)_{m+1} = \exp\left[\Delta\lambda \ln\left[\bar{\boldsymbol{F}}_{\Delta}\right]\right]. \tag{4.165}$$

4.7.3 Numerical solution of micro-scale equilibrium problem

The online-stage of the SCA method comprises the actual prediction of the material response under a given set of macro-scale strain and/or stress loading constraints. The micro-scale equilibrium problem is mathematically posed as a clustered Lippmann-Schwinger system of equilibrium equations defined by Equations (4.103) and (4.104). Due to the geometrical nonlinearity stemming from finite strains and the material nonlinearity arising from the material cluster's general constitutive behavior, the well-known Newton-Raphson Method (see Section 2.9.5) can be conveniently adopted to efficiently find the solution by taking advantage of the associated quadratic convergence rate.

Attending to Equation (4.103), the global residual function can be defined as

$$\boldsymbol{R}_{m+1} = \begin{bmatrix} \boldsymbol{R}^{(I)}_{m+1} \\ \boldsymbol{R}^{(n_c+1)}_{m+1} \end{bmatrix} = \begin{bmatrix} \boldsymbol{0} \\ \boldsymbol{0} \end{bmatrix}, \qquad \forall I = 1, 2, \ldots, n_c, \tag{4.166}$$

where the $n_c + 1$ residual functions are defined as

$$\boldsymbol{R}^{(I)}_{m+1} = \boldsymbol{F}^{(I)}_{\mu,m+1} + \sum_{J=1}^{n_c} \mathbf{T}^{(I)(J)} : \left(\hat{\boldsymbol{P}}^{(J)}_{\mu,m+1} - \mathbf{A}^{e,0} : \boldsymbol{F}^{(J)}_{\mu,m+1}\right) - \boldsymbol{F}^{0}_{\mu,m+1}, \quad \forall I = 1, \ldots, n_c, \tag{4.167}$$

$$\boldsymbol{R}^{(n_c+1)}_{m+1} = \sum_{I=1}^{n_c} f^{(I)} \boldsymbol{F}^{(I)}_{\mu,m+1} - \boldsymbol{F}_{m+1}(\boldsymbol{X}) \quad ; \quad \boldsymbol{R}^{(n_c+1)}_{m+1} = \sum_{I=1}^{n_c} f^{(I)} \hat{\boldsymbol{P}}^{(I)}_{\mu,m+1} - \boldsymbol{P}_{m+1}(\boldsymbol{X}). \tag{4.168}$$

Then, each Newton-Raphson iteration (k) consists in finding the solution of the linearized version of Equation (4.166) as

$$\mathbf{F}^{(k)}_{\mu,m+1} = \mathbf{F}^{(k-1)}_{\mu,m+1} + \delta\mathbf{F}^{(k)}_{\mu}, \qquad \delta\mathbf{F}^{(k)}_{\mu} = -\mathbf{J}^{-1}\left(\mathbf{F}^{(k-1)}_{\mu,m+1}\right)\mathbf{R}\left(\mathbf{F}^{(k-1)}_{\mu,m+1}\right), \tag{4.169}$$

where $\mathbf{F}_{\mu,m+1}$ is the matricial form of the vector of unknowns defined in Equation (4.104), $\mathbf{R}$ is the vectorial form of the global residual defined in Equation (4.166) and $\mathbf{J}$ is the matricial form of the Jacobian matrix

$$\boldsymbol{J}_{m+1} = \frac{\partial \boldsymbol{R}_{m+1}}{\partial \boldsymbol{F}_{\mu,m+1}} = \begin{bmatrix} \dfrac{\partial \boldsymbol{R}^{(I)}_{m+1}}{\partial \boldsymbol{F}^{(K)}_{\mu,m+1}} & \dfrac{\partial \boldsymbol{R}^{(I)}_{m+1}}{\partial \boldsymbol{F}^{0}_{\mu,m+1}} \\ \dfrac{\partial \boldsymbol{R}^{(n_c+1)}_{m+1}}{\partial \boldsymbol{F}^{(K)}_{\mu,m+1}} & \dfrac{\partial \boldsymbol{R}^{(n_c+1)}_{n+1}}{\partial \boldsymbol{F}^{0}_{\mu,m+1}} \end{bmatrix}, \qquad \forall I, K = 1, \ldots, n_c. \tag{4.170}$$

The solution procedure of a given loading increment $m+1$ of the clustered Lippmann-Schwinger system of equilibrium equations is summarized in pseudo-code format in Box 4.2.

Remark.
The incremental update of the reference elastic material Lamé parameters through a self-consistent micromechanical approach is discussed later in Section 4.9.

The linearization of the clustered Lippmann-Schwinger equilibrium residuals and macro-scale constraints residuals is similar to the infinitesimal strains case detailed in Appendix C. The residual derivatives required to completely define the Jacobian matrix (see Equation (4.170)) are given by

$$\frac{\partial \boldsymbol{R}^{(I)}_{m+1}}{\partial \boldsymbol{F}^{(K)}_{\mu,\,m+1}} = \delta_{(I)(K)}\mathbf{I} + \mathbf{T}^{(I)(K)} : \left(\mathbf{A}^{(K)}_{m+1} - \mathbf{A}^{e,0}\right). \tag{4.171}$$

$$\frac{\partial \boldsymbol{R}^{(I)}_{m+1}}{\partial \boldsymbol{F}^{0}_{\mu,\,m+1}} = -\mathbf{I}, \tag{4.172}$$

$$\frac{\partial \boldsymbol{R}^{(n_c+1)}_{m+1}}{\partial \boldsymbol{F}^{(K)}_{\mu,\,m+1}} = f^{(K)}\,\mathbf{I} \qquad \text{(strain constraint)}, \tag{4.173}$$

$$\frac{\partial \boldsymbol{R}^{(n_c+1)}_{m+1}}{\partial \boldsymbol{F}^{(K)}_{\mu,\,m+1}} = f^{(K)}\,\mathbf{A}^{(K)}_{m+1} \qquad \text{(stress constraint)}, \tag{4.174}$$

$$\frac{\partial \boldsymbol{R}^{(n_c+1)}_{m+1}}{\partial \boldsymbol{F}^{0}_{\mu,\,m+1}} = \mathbf{0}. \tag{4.175}$$

In the previous derivatives, $\mathbf{A}^{(K)}_{m+1}$ denotes the material consistent tangent modulus of the Kth cluster defined as

$$\mathbf{A}^{(K)}_{m+1} = \frac{\partial \hat{\boldsymbol{P}}^{(K)}_{\mu,\,m+1}\left(\boldsymbol{F}^{(K)}_{\mu,\,m+1}, \boldsymbol{\beta}_m\right)}{\partial \boldsymbol{F}^{(K)}_{\mu,\,m+1}}. \tag{4.176}$$

4.7.4 Macro-scale material response

After the numerical solution of the clustered Lippmann-Schwinger system of equilibrium equations is found, the macro-scale material response, i.e., the homogenized first Piola-Kirchhoff stress tensor, can be computed by computational homogenization as

$$\boldsymbol{P}(\boldsymbol{X}) = \sum_{I=1}^{n_c} f^{(I)}\,\hat{\boldsymbol{P}}^{(I)}_{\mu}. \tag{4.177}$$

In addition, if the SCA is employed to solve the micro-scale equilibrium problem of an implicit first-order strain-driven hierarchical multi-scale model (see Chapter 2), the solution of a macro-scale Newton-Raphson iteration requires the computation of the homogenized consistent tangent modulus of the CRVE (see Figure 2.4).

In view of the homogeneous far-field deformation gradient, $\boldsymbol{F}^0_\mu$, introduced in the Lippmann-Schwinger integral equilibrium equation (see Section 4.3.3), the homogenized consistent tangent modulus of the CRVE at the loading increment $m+1$ is defined as

$$\overline{\mathbf{A}}_{m+1} = \frac{\partial \boldsymbol{P}_{m+1}(\boldsymbol{X})}{\partial \boldsymbol{F}^{0}_{\mu,\,m+1}} = \frac{\partial}{\partial \boldsymbol{F}^{0}_{\mu,\,m+1}} \left(\sum_{I=1}^{n_{\mathrm{c}}} f^{(I)} \hat{\boldsymbol{P}}^{(I)}_{\mu,\,m+1} \right). \tag{4.178}$$

Applying the differentiation chain rule and noticing that the material consistent tangent modulus of the Ith cluster is defined as

$$\mathbf{A}^{(I)}_{m+1} = \frac{\partial \hat{\boldsymbol{P}}^{(I)}_{\mu,\,m+1}\left(\boldsymbol{F}^{(I)}_{\mu,\,m+1}, \boldsymbol{\beta}_{m}\right)}{\partial \boldsymbol{F}^{(I)}_{\mu,\,m+1}}, \tag{4.179}$$

the CRVE homogenized consistent tangent modulus can be written as

$$\overline{\mathbf{A}}_{m+1} = \sum_{I=1}^{n_{\mathrm{c}}} f^{(I)} \mathbf{A}^{(I)}_{m+1} : \mathbf{H}^{(I)}_{m+1}, \tag{4.180}$$

where $\mathbf{H}^{(I)}_{m+1}$ is the fourth-order strain concentration tensor of the Ith cluster,

$$\boldsymbol{F}^{(I)}_{\mu,\,m+1} = \mathbf{H}^{(I)}_{m+1} : \boldsymbol{F}^{0}_{\mu,\,m+1}, \quad \forall I = 1,2,\ldots,,n_{\mathrm{c}}, \tag{4.181}$$

such that

$$\boldsymbol{F}^{(I)}_{m+1} = \frac{\partial \boldsymbol{F}^{(I)}_{\mu,\,m+1}}{\partial \boldsymbol{F}^{0}_{\mu,\,m+1}}, \quad \forall I = 1,2,\ldots,n_{\mathrm{c}}. \tag{4.182}$$

In order to compute $\mathbf{H}^{(I)}_{m+1}$ at the equilibrium state of the Ith cluster, it is possible to state

$$\mathrm{d}\boldsymbol{R}^{(I)}_{m+1} = \frac{\partial \boldsymbol{R}^{(I)}_{m+1}}{\partial \boldsymbol{F}^{(K)}_{\mu,\,m+1}} : \mathrm{d}\boldsymbol{F}^{(K)}_{\mu,\,m+1} + \frac{\partial \boldsymbol{R}^{(I)}_{m+1}}{\partial \boldsymbol{F}^{0}_{\mu,\,m+1}} : \mathrm{d}\boldsymbol{F}^{0}_{\mu,\,m+1} = \mathbf{0}, \quad \forall I, K = 1,2,\ldots,n_{\mathrm{c}}, \tag{4.183}$$

where both $\partial \boldsymbol{R}^{(I)}_{m+1}/\partial \boldsymbol{F}^{(K)}_{\mu,\,m+1}$ and $\partial \boldsymbol{R}^{(I)}_{m+1}/\partial \boldsymbol{F}^{0}_{\mu,\,m+1}$ (see Equations (4.171) and (4.172)) are determined at the converged state. By assembling the previous equation for all material clusters $I = 1,2,\ldots,n_{\mathrm{c}}$ and taking the associated matricial forms, one can readily establish the following system of linear equations,

$$\mathbf{M}\mathbf{S}_{m+1} = -\mathbf{Q}, \tag{4.184}$$

where $\mathbf{M}$ and $\mathbf{Q}$ contain the residual derivatives as

$$\mathbf{M} = \begin{bmatrix} \dfrac{\partial \boldsymbol{R}^{(1)}_{m+1}}{\partial \boldsymbol{F}^{(1)}_{\mu,\,m+1}} & \cdots & \dfrac{\partial \boldsymbol{R}^{(1)}_{m+1}}{\partial \boldsymbol{F}^{(n_{\mathrm{c}})}_{\mu,\,m+1}} \\ \vdots & \ddots & \vdots \\ \dfrac{\partial \boldsymbol{R}^{(n_{\mathrm{c}})}_{m+1}}{\partial \boldsymbol{F}^{(1)}_{\mu,\,m+1}} & \cdots & \dfrac{\partial \boldsymbol{R}^{(n_{\mathrm{c}})}_{n+1}}{\partial \boldsymbol{F}^{(n_{\mathrm{c}})}_{\mu,\,m+1}} \end{bmatrix}, \quad \mathbf{Q} = \begin{bmatrix} \dfrac{\partial \boldsymbol{R}^{(1)}_{m+1}}{\partial \boldsymbol{F}^{0}_{\mu,\,m+1}} \\ \vdots \\ \dfrac{\partial \boldsymbol{R}^{(n_{\mathrm{c}})}_{m+1}}{\partial \boldsymbol{F}^{0}_{\mu,\,m+1}} \end{bmatrix}, \tag{4.185}$$

and $\mathbf{S}_{m+1}$ contains the clusters strain concentration tensors as

$$\mathbf{S}_{m+1} = \begin{bmatrix} \dfrac{\partial \boldsymbol{F}^{(1)}_{\mu,\,m+1}}{\partial \boldsymbol{F}^{0}_{\mu,\,m+1}} & \cdots & \dfrac{\partial \boldsymbol{F}^{(n_{\mathrm{c}})}_{\mu,\,m+1}}{\partial \boldsymbol{F}^{0}_{\mu,\,m+1}} \end{bmatrix}^{T} = \begin{bmatrix} \mathbf{H}^{(I)}_{m+1} & \cdots & \mathbf{H}^{(n_{\mathrm{c}})}_{m+1} \end{bmatrix}^{T}. \tag{4.186}$$

Attending to Equation (4.172), the solution of the previous system of linear equations shows that the strain concentration tensor of the Ith cluster is computed as

$$\mathbf{H}^{(I)}_{m+1} = \sum_{K=1}^{n_{\mathrm{c}}} \left(\mathbf{M}^{-1}\right)_{(I)(K)}, \quad \forall I = 1,2,\ldots,n_{\mathrm{c}}. \tag{4.187}$$

Box 4.2: The solution procedure of a given load increment $m+1$ of the Lippmann-Schwinger system of equilibrium equations through the Newton-Raphson Method.

(i) Initialize iterative counter, $k := 1$

(ii) Set initial guess for deformation gradient tensors,

$$\boldsymbol{F}^{(I)(0)}_{\mu,\,m+1} = \boldsymbol{I}\,, \qquad \forall I = 1,2,\ldots,n_{\mathrm{c}}\,, \qquad \boldsymbol{F}^{0,(0)}_{\mu,\,m+1} = \boldsymbol{I}$$

(iii) Perform the material state update for each cluster

$$\boldsymbol{P}^{(I)(k-1)}_{\mu,\,m+1} = \hat{\boldsymbol{P}}_{\mu,\,m+1}\left(\boldsymbol{F}^{(I)(k-1)}_{\mu,\,m+1},\,\boldsymbol{\alpha}^{(I)}_{m}\right), \qquad \forall I = 1,2,\ldots,n_{\mathrm{c}}$$

(iv) Compute global residual functions

$$\boldsymbol{R}^{(I)}_{m+1}\left(\boldsymbol{F}^{(k-1)}_{\mu,\,m+1}\right) = \boldsymbol{F}^{(I)(k-1)}_{\mu,\,m+1} + \sum_{J=1}^{n_{\mathrm{c}}} \mathsf{T}^{(I)(J)} : \left[\hat{\boldsymbol{P}}^{(J)(k-1)}_{\mu,\,m+1} - \mathbf{A}^{e,0} : \boldsymbol{F}^{(J)(k-1)}_{\mu,\,m+1}\right] - \boldsymbol{F}^{0,(k-1)}_{\mu,\,m+1}\,,$$

$$\forall I = 1,2,\ldots,n_{\mathrm{c}}$$

$$\boldsymbol{R}^{(n_{\mathrm{c}}+1)}_{m+1}\left(\boldsymbol{F}^{(k-1)}_{\mu,\,m+1}\right) = \sum_{I=1}^{n_{\mathrm{c}}} f^{(I)}\,\boldsymbol{F}^{(I)(k-1)}_{\mu,\,m+1} - \boldsymbol{F}_{m+1}(\boldsymbol{X})\,;$$

$$\boldsymbol{R}^{(n_{\mathrm{c}}+1)}_{m+1}\left(\boldsymbol{P}^{(k-1)}_{\mu,\,m+1}\right) = \sum_{I=1}^{n_{\mathrm{c}}} f^{(I)}\,\boldsymbol{P}^{(I)(k-1)}_{\mu,\,m+1} - \boldsymbol{P}_{m+1}(\boldsymbol{X})$$

(v) Check for convergence

if (converged) then

- Update incremental solution, $(\bullet)_{m+1} = (\bullet)^{(k)}_{m+1}$, and exit

(vi) Compute the Jacobian matrix

$$\boldsymbol{J}\left(\mathbf{F}^{(k-1)}_{\mu,\,m+1}\right) = \left[\begin{array}{cc} \dfrac{\partial \boldsymbol{R}^{(I)}_{m+1}}{\partial \boldsymbol{F}^{(K)}_{\mu,\,m+1}} & \dfrac{\partial \boldsymbol{R}^{(I)}_{m+1}}{\partial \boldsymbol{F}^{0}_{\mu,\,m+1}} \\[2ex] \dfrac{\partial \boldsymbol{R}^{(n_{\mathrm{c}}+1)}_{m+1}}{\partial \boldsymbol{F}^{(K)}_{\mu,\,m+1}} & \dfrac{\partial \boldsymbol{R}^{(n_{\mathrm{c}}+1)}_{m+1}}{\partial \boldsymbol{F}^{0}_{\mu,\,m+1}} \end{array}\right]_{\left(\mathbf{F}^{(k-1)}_{\mu,\,m+1}\right)}, \qquad \forall I,K = 1,2,\ldots,n_{\mathrm{c}}$$

(vii) Solve the system of linear equations

$$\delta\mathbf{F}^{(k)}_{\mu} = -\mathbf{J}^{-1}\left(\mathbf{F}^{(k-1)}_{\mu,\,m+1}\right)\mathbf{R}\left(\mathbf{F}^{(k-1)}_{\mu,\,m+1}\right)$$

(viii) Update deformation gradient tensors

$$\mathbf{F}^{(k)}_{\mu,\,m+1} = \mathbf{F}^{(k-1)}_{\mu,\,m+1} + \delta\mathbf{F}^{(k)}_{\mu}$$

(ix) Increment iteration counter, $k := k+1$

(x) Go to step (iii)

4.8 Numerical application

4.8.1 Material characterization and macro-scale loadings

A biphasic material characterized by randomly distributed circular particles (f = 30%) embedded in a matrix (f = 70%) is here considered (see Figure 4.35). The matrix material phase constitutive behavior is governed by a Hencky hyperelastic-based finite strain formulation of the von Mises elasto-plastic constitutive model with isotropic strain hardening (see Appendix F). The particle's material phase is assumed isotropic and governed by the isotropic Hencky hyperelastic constitutive model. The material properties adopted for each material phase are similar to the infinitesimal strains case[30] (see Appendix C) and are summarized in Table 4.9.

Table 4.9: Constitutive model and properties of the particle-matrix composite's material phases. Notation: Young's Modulus (E), Poisson's ratio (ν), yield stress (σ_y) and accumulated plastic strain ($\bar{\varepsilon}^p$).

Phase	Model	E(MPa)	ν	σ_y(MPa)
Matrix	von Mises* (isotropic)	100	0.3	$\sigma_y = 5.0 + 0.3(\bar{\varepsilon}^p)^{0.4}$
Particles	Hencky (isotropic)	500	0.19	-

(*) Hencky hyperelastic-based finite strain elasto-plastic formulation (see Appendix F).

The following examples focus on two-dimensional cases under finite strains and the RVE of the particle-matrix composite is shown in Figure 4.35. Five different macro-scale strain-driven loadings are considered in the following sections (see Figure 4.14), namely

- uniaxial tension: $[F_{xx},,F_{yx},F_{xy},F_{yy}] = [1.2, 0.0, 0.0, 1.2]$;
- pure shear: $[F_{xx},,F_{yx},F_{xy},F_{yy}] = [1.0, 0.1, 0.1, 1.0]$;
- uniaxial compression: $[F_{xx},,F_{yx},F_{xy},F_{yy}] = [0.8, 0.0, 0.0, 1.0]$;
- combined uniaxial tension - shear: $[F_{xx},,F_{yx},F_{xy},F_{yy}] = [1.0, 0.1, 0.1, 1.2]$;
- combined uniaxial compression - shear: $[F_{xx},,F_{yx},F_{xy},F_{yy}] = [1.0, 0.1, 0.1, 0.8]$;

being all prescribed in a total of 200 increments according to the multiplicative decomposition-based loading incrementation described in Section 4.7.2.

4.8.2 Solution methods and error assessment

Two solution methods are considered in the numerical assessment presented in the following sections: a direct numerical simulation (DNS) solution, adopted as the reference (or 'high-fidelity') solution, and the finite strain SCA solution following the formulation proposed in Section 4.7.

The DNS solution is obtained with a FEM first-order hierarchical multi-scale model based on computational homogenization (see Chapter 2). This solution is carried out with LINKS (Large Strain Implicit Non-linear Analysis of Solids Linking Scales), an implicit multi-scale finite

[30] The initial yield stress of the Swift isotropic strain hardening law is increased so that the material sustains the (finite) magnitude of the enforced macro-scale strain constraints.



Figure 4.35: 2D RVE of biphasic material characterized by randomly distributed circular hyperelastic particles ($f = 30\%$) embedded in a elasto-plastic matrix ($f = 70\%$).

element Fortran code developed by the CM2S research group at the Faculty of Engineering of the University of Porto[31].

The SCA solution is obtained with CRATE (Clustering-based Nonlinear Analyses of Materials), an object-oriented Python program that performs multi-scale nonlinear analyses through clustering-based reduced-order models. This program has been fully designed and implemented as part of this thesis and is thoroughly described in Chapter 5. Periodic boundary conditions are assumed and a refined spatial discretization of $n_v = 400 \times 400$ voxels is considered for all numerical examples. Concerning the SCA's offline-stage, the required hyperelastic DNS simulations are performed with the finite strain FFT-based homogenization basic scheme described in Section 4.6 and also implemented in CRATE following the strategy proposed in Section 4.6.3. In addition, the clustering of both material phases is performed with the well-known K-Means clustering (standard Lloyds' algorithm) with 10 centroid initializations computed with K-Means++. This algorithm implementation is readily available from Scikit-learn, a Python module integrating a wide range of state-of-the-art machine-learning algorithms for medium-scale supervised and unsupervised problems (Pedregosa et al., 2012). Regarding the SCA's online-stage, it is remarked that the reference elastic material's properties are kept constant throughout the deformation path. The formulation of an accurate finite strain self-consistent scheme compatible with the finite strain SCA under multiplicative kinematics is still under investigation, as reported in Section 4.9.

Concerning the error assessment, the relative error, ϵ, is employed to compare the macro-scale homogenized response, being always defined as

$$\epsilon\,(\%) = \left| \frac{a_{\mathrm{SCA}} - a_{\mathrm{DNS}}}{a_{\mathrm{DNS}}} \right| \times 100\,, \tag{4.188}$$

where a denotes the scalar quantity of interest.

At last, unless otherwise stated, all the numerical simulations presented in this section are run with 1 CPU core in a personal computer with the following specifications: CPU Intel Core i7-6800K (3.40GHz × 6 cores/12 threads, Broadwell), RAM 32GB (4 × 8GB) DDR4 @ 2400MHz. Nonetheless, some third-party (low-level) packages may perform multi-processor computations at certain operations.

[31] Bernardo P. Ferreira is an active member of the CM2S research group, led by F.M. Andrade Pires, and one of the developers of LINKS. This motivated the choice of FEM as the DNS solution, as opposed to the choice of an external FFT-based homogenization solver. Despite the different fundamental basis of the solution, some preliminary studies showed a close agreement between both approaches under elasticity and elasto-plasticity for a sufficiently refined mesh.



Figure 4.36: Uniaxial tension, pure shear, uniaxial compression, combined uniaxial tension - shear and combined uniaxial compression - shear macro-scale strain loading constraints.

4.8.3 Clustering-based domain decomposition

Following the SCA's offline-stage proposed in Section 4.7.1, the particle-matrix composite is compressed into CRVEs, as illustrated in Figure 4.37. The cluster analysis is performed independently for each material phase and the degree of data compression is set as $n_{c,1}/n_{c,2} = 2$, proportional to the respective volume fractions.

Despite the reference elastic material properties being kept constant, a preliminary analysis under uniaxial tension shows the expected convergence of the predicted material response with an increase in the number of clusters (see Figures 4.38). The partial and computational times of the DNS and SCA solutions are presented in Table 4.10, where the increase in computational cost with the number of clusters is evidenced. To fulfill the numerical purposes of the following sections, the CRVE with a total of $n_c = 180$ clusters is considered to perform the SCA analyses in the remainder of this section.

The effective elastic tangent modulus of the RVE, $\overline{\mathbf{A}}^e$, is also computed from the offline-stage as defined by Equations (4.155) and (4.156). By adopting a strain magnitude factor of $\chi = 1.0 \times 10^{-5}$, the fourth-order tensor $\overline{\mathbf{A}}^e$ does actually correspond to the initial effective elastic tangent modulus of the RVE. By adopting a self-consistent approach, this modulus can be conveniently employed to compute a first estimate of the isotropic reference homogeneous hyperelastic material's properties (see Equation (4.45)) as

$$E^0 = \frac{1}{\overline{\mathbf{A}}^e_{1111} + \overline{\mathbf{A}}^e_{1122}} \left[\left(\overline{\mathbf{A}}^e_{1111} \right)^2 + \overline{\mathbf{A}}^e_{1111} \overline{\mathbf{A}}^e_{1122} + 2 \left(\overline{\mathbf{A}}^e_{1122} \right)^2 \right], \tag{4.189}$$

and

$$\nu^0 = \frac{\overline{\mathbf{A}}^e_{1122}}{\overline{\mathbf{A}}^e_{1111} + \overline{\mathbf{A}}^e_{1122}}, \tag{4.190}$$



Figure 4.37: Clustering-based domain decomposition (K-means clustering) of the particle-matrix composite RVE for a different number of clusters. The ratio between the number of clusters of the matrix phase ($f = 70\%$) and the particles phase ($f = 30\%$) is set as 2.

with the corresponding Lamé parameters recovered as

$$\lambda^0 = \frac{E^0 \nu^0}{(1+\nu^0)(1-2\nu^0)}, \qquad \mu^0 = \frac{E^0}{2(1+\nu^0)}. \tag{4.191}$$

The self-consistent initial estimate given by Equations (4.189) and (4.190) yields $(E^0, \nu^0) = (145.26\,\text{MPa}, 0.28)$ for the particle-matrix composite. These estimates are conveniently taken as reference values to evaluate the influence of the reference elastic material's properties on the SCA's predictions.

4.8.4 Macro-scale strain loading constraints

The following numerical analyses aim to fulfill several purposes, among which the following are highlighted: (1) demonstrate the influence of the reference elastic material properties on the predicted material response, (2) show that the SCA is able to deliver fast and accurate finite strain elasto-plastic predictions with a significant model compression, and (3) validate the implementation of the Newton-Raphson Method underlying the SCA's online-stage.



(a) (b)

Figure 4.38: Homogenized response of the particle-matrix composite under uniaxial tension strain loading constraints obtained with SCA for a different number of clusters: (a) Homogenized stress; (b) Relative error with respect to the FEM DNS solution. The reference elastic material properties are kept constant throughout the deformation path ($(E^0, \nu^0) = (20\,\text{MPa}, 0.28)$).

Table 4.10: Partial and total computational times (s) of the different solution methods associated with the particle-matrix 2D RVE under uniaxial tension strain loading constraints. The reference elastic material properties are kept constant throughout the deformation path in the SCA solutions. Offline-stage: hyperelastic DNS solutions (step 1), base cluster analysis (step 2) and computation of cluster-interaction tensors (step 3).

	Computational time (s)				
Method	**Offline (step 1)**	**Offline (step 2)**	**Offline (step 3)**	**Online (solution)**	**Total**
DNS	-	-	-	24772	24772
SCA ($n_c = 3$)	85	4	1	6	96
SCA ($n_c = 6$)	85	6	2	24	117
SCA ($n_c = 18$)	85	17	10	59	171
SCA ($n_c = 54$)	85	20	64	137	306
SCA ($n_c = 180$)	85	151	617	479	1332

Influence of the reference material's Young modulus

In order to evaluate the influence of the reference material's Young modulus, E^0, on the SCA's predicted material response, the reference material's Poisson ratio is fixed according to the self-consistent initial estimate determined from Equation (4.190), i.e., $\nu^0 = 0.28$. In turn, the self-consistent initial estimate of the reference material's Young modulus (see Equation (4.189)) associated with the RVE initial effective elastic tangent modulus is taken as the upper limit of the E^0 parametric space.

The homogenized response of the particle-matrix composite is presented in Figures 4.39-4.43 for the different macro-scale strain loading constraints together with the FEM DNS solution obtained with LINKS and the associated relative error.

In the first place, it is possible to observe that the influence of E^0 on the SCA's numerical prediction is smooth and meaningful from a physical point of view, i.e., the greater the stiffness of the reference homogeneous material, the stiffer the predicted material response. In this sense, the estimate taken from the RVE initial effective elastic tangent modulus consistently provides an upper-bound with respect to the DNS solution. Moreover, the influence of E^0 is clearly more pronounced in the post-yielding elasto-plastic predicted behavior than in the initial hyperelastic regime.

In the second place, it is worth highlighting that, even with constant properties of the reference elastic material, the SCA is able to capture the homogenized nonlinear elasto-plastic behavior of the particle-matrix composite under finite strains with reasonable accuracy. This feat is achieved with a considerable model compression, with the SCA's solution being obtained with a total of 724 degrees of freedom and the FEM-based homogenization DNS solution ascending to approximately 1 million. Nonetheless, the need for an accurate incremental update of the reference elastic material's properties is fundamental for several reasons. Despite the reasonable upper-bound provided by the RVE initial effective stiffness estimate, the (constant) value of E^0, which delivers the most accurate prediction, is generally unknown and even distinct between the different loading cases. Most importantly, the error assessment of the different macro-scale strains constraints clearly shows that the most adequate value of E^0 differs between the hyperelastic and elasto-plastic regimes. In the particular case of the combined uniaxial compression - shear strain loading, the lack of an updating E^0 is also evidenced in the post-yielding regime, where the equivalent stress-strain response exhibits an inflection point. These observations are expected to be further augmented when dealing with more complex constitutive behavior and/or non-monotonic loading paths.

Finally, the convergence of the Newton-Raphson iterations in the solution of the clustered Lippmann-Schwinger system of equilibrium equations is presented in Table 4.11. The quadratic convergence rate achieved in all macro-scale strain loading cases strongly suggests that the associated linearization is properly derived and implemented.

Remark.
Convergence issues and/or erroneous solution paths are numerically observed as soon as the reference elastic material is not sufficiently stiff at any stage of the deformation path - whenever the associated Young modulus E^0 is such that the SCA's predicted stress is lower than the DNS's prediction for a given strain level. This numerical observation seems to be in agreement with Schneider (Schneider, 2019), which states that 'the reference materials need to be sufficiently stiff for the analysis to be carried out'. It is also interesting to notice that the adaptive strategy to select E^0 proposed by Zhu and coworkers (Zhu et al., 2021) in the context of the Virtual Clustering Analysis (VCA) method (infinitesimal strains) is based on a gradual decrease of E^0, i.e., a sequential approximation from the stiffer side.



Figure 4.39: Homogenized response of the particle-matrix composite under uniaxial tension strain loading constraint obtained with SCA for different (constant) reference elastic material's Young moduli, $(E^0, \nu^0) = (\Delta, 0.28)$: (a) Homogenized stress; (b) Relative error with respect to the FEM DNS solution.



Figure 4.40: Homogenized response of the particle-matrix composite under pure shear strain loading constraint obtained with SCA for different (constant) reference elastic material's Young moduli, $(E^0, \nu^0) = (\Delta, 0.28)$: (a) Homogenized stress; (b) Relative error with respect to the FEM DNS solution.



Figure 4.41: Homogenized response of the particle-matrix composite under uniaxial compression strain loading constraint obtained with SCA for different (constant) reference elastic material's Young moduli, $(E^0, \nu^0) = (\Delta, 0.28)$: (a) Homogenized stress; (b) Relative error with respect to the FEM DNS solution.



Figure 4.42: Homogenized response of the particle-matrix composite under combined uniaxial tension - shear strain loading constraint obtained with SCA for different (constant) reference elastic material's Young moduli, $(E^0, \nu^0) = (\Delta, 0.28)$: (a) Homogenized stress; (b) Relative error with respect to the FEM DNS solution.



(a) (b)

Figure 4.43: Homogenized response of the particle-matrix composite under combined uniaxial compression - shear strain loading constraint obtained with SCA for different (constant) reference elastic material's Young moduli, $(E^0, \nu^0) = (\Delta, 0.28)$: (a) Homogenized stress; (b) Relative error with respect to the FEM DNS solution.

Influence of the reference material's Poisson ratio

In order to evaluate the influence of the reference material's Poisson ratio, ν^0, on the SCA's predicted material response, the reference material's Young modulus is fixed according to the self-consistent initial estimate determined from Equation (4.189), i.e., $E^0 = 145\,\text{MPa}$. In turn, the parametric space of the reference material's Poisson ratio is set within the common range $\nu^0 \in [0, 0.5]$.

The homogenized response of the particle-matrix composite is presented in Figures 4.44-4.48 for the different macro-scale strain loading constraints together with the FEM DNS solution obtained with LINKS and the associated relative error.

It can be observed that the influence of ν^0 on the SCA's numerical prediction is very low in comparison with the influence of E^0 within the evaluated range. Similar analyses conducted for lower (fixed) values of E^0 yielded identical conclusions concerning the influence of ν^0.

Remark.
A minor influence of ν^0 is also reported by Zhu and coworkers (Zhu et al., 2021) in the context of the Virtual Clustering Analysis (VCA) method under infinitesimal strains. These authors select ν^0 as the volume average of ν over the RVE domain and keep it fixed throughout the deformation path.



Figure 4.44: Homogenized response of the particle-matrix composite under uniaxial tension strain loading constraint obtained with SCA for different (constant) reference elastic material's Poisson ratios, $(E^0, \nu^0) = (145\,\text{MPa}, \Delta)$: (a) Homogenized stress; (b) Relative error with respect to the FEM DNS solution.



(a) (b)

Figure 4.45: Homogenized response of the particle-matrix composite under pure shear strain loading constraint obtained with SCA for different (constant) reference elastic material's Poisson ratios, $(E^0, \nu^0) = (145\,\text{MPa}, \Delta)$: (a) Homogenized stress; (b) Relative error with respect to the FEM DNS solution.



(a) (b)

Figure 4.46: Homogenized response of the particle-matrix composite under uniaxial compression strain loading constraint obtained with SCA for different (constant) reference elastic material's Poisson ratios, $(E^0, \nu^0) = (145\,\text{MPa}, \Delta)$: (a) Homogenized stress; (b) Relative error with respect to the FEM DNS solution.



Figure 4.47: Homogenized response of the particle-matrix composite under combined uniaxial tension - shear strain loading constraint obtained with SCA for different (constant) reference elastic material's Poisson ratios, $(E^0, \nu^0) = (145\,\text{MPa}, \Delta)$: (a) Homogenized stress; (b) Relative error with respect to the FEM DNS solution.



Figure 4.48: Homogenized response of the particle-matrix composite under combined uniaxial compression - shear strain loading constraint obtained with SCA for different (constant) reference elastic material's Poisson ratios, $(E^0, \nu^0) = (145\,\text{MPa}, \Delta)$: (a) Homogenized stress; (b) Relative error with respect to the FEM DNS solution.

Table 4.11: Convergence table of the particle-matrix composite SCA analyses (n_c = 180) under different macro-scale strain loading constraints. Normalized equilibrium residual of the clustered Lippmann-Schwinger system of equilibrium equations during the macro-scale loading increment 100. The reference elastic material's properties are kept constant throughout the deformation path.

Macro-scale Loading		**Lippmann-Schwinger Newton-Raphson**	
Constraint	Increment	Iteration	Norm. Eq. Res.
Uniaxial tension	100	1	1.8651×10^{-03}
		2	4.0523×10^{-06}
		3	1.3274×10^{-11}
Pure shear	100	1	2.141210^{-03}
		2	1.4916×10^{-06}
		3	5.1049×10^{-12}
Uniaxial compression	100	1	3.2904×10^{-03}
		2	4.4285×10^{-06}
		3	5.9978×10^{-11}
Uniaxial tension + Shear	100	1	2.4605×10^{-03}
		2	1.6552×10^{-06}
		3	5.5969×10^{-12}
Uniaxial compression + Shear	100	1	4.3661×10^{-03}
		2	6.5086×10^{-06}
		3	9.7054×10^{-11}

4.9 Finite strain self-consistent scheme

As discussed in Section 4.3 and numerically evidenced in the previous section, the solution of the clustered Lippmann-Schwinger integral equilibrium equation depends on the reference elastic material's properties. Under infinitesimal strains, Liu and coworkers (Liu et al., 2016) propose an ingenious regression-based self-consistent scheme (see Section C.5.2) formulated as (see Problem C.3)

$$\left\{\lambda^0_{m+1}, \mu^0_{m+1}\right\} = \underset{\{\lambda', \mu'\}}{\operatorname{argmin}} \left\| \Delta\boldsymbol{\sigma}_{m+1} - \mathbf{D}^{e,0}_{m+1}(\lambda', \mu') : \Delta\boldsymbol{\varepsilon}_{m+1} \right\|^2. \tag{4.192}$$

This optimization problem is conveniently reduced to a system of two linear equations (see Equation (C.39)) and coupled with the additive formulation of the clustered Lippmann-Schwinger system of equilibrium equations (see Equation (4.87)) through a partitioned (or staggered) solution scheme (see Box C.3). From a physical point of view, such self-consistent scheme formulation replaces the generally anisotropic CRVE homogenized consistent tangent modulus by an isotropic elastic tangent modulus (see Figure 4.49), i.e.,

attempts to find the two Lamé parameters that establish the best fit between the incremental Cauchy and infinitesimal strain (symmetric) tensors.



Figure 4.49: Schematic of the regression-based self-consistent scheme proposed by Liu and coworkers (Liu et al., 2016) under infinitesimal strains.

Despite the success of the previous self-consistent scheme under infinitesimal strains, the extension of this approach to the finite strain setting under multiplicative kinematics is not straightforward. Several comments are in order:

- **Nonsymmetric stress-strain nature**. Besides the already challenging task of approximating the generally anisotropic CRVE homogenized consistent tangent modulus by an isotropic elastic tangent modulus, both first Piola-Kirchhoff stress and deformation gradient tensors are generally nonsymmetric. This is expected to further complicate the estimation of suitable reference elastic material's properties due to the major symmetry of the isotropic elasticity fourth-order tensor;

- **Nonphysical reference material**. Despite being conveniently introduced in Section 4.2.2 to solve the auxiliary homogeneous problem and derive the Green operator under hyperelastic isotropy, it should be remarked that the constitutive law of the reference material,

$$\boldsymbol{P} = \mathbf{A}^{e,0} : \boldsymbol{F}, \tag{4.193}$$

  is devoid of any physical significance as it violates essential constitutive hypotheses (Liu (2017), Kabel et al. (2016)). Therefore, in spite of the physically meaningful numerical influence observed in Section 4.8.4, the non-physical nature of the reference material may yield important consequences when attempting to formulate an accurate self-consistent scheme. Nonetheless, note that physically admissible reference elastic material's properties are considered in the parametric analyses performed in the previous section;

- **Incremental homogenized consistent tangent modulus**. In contrast with the infinitesimal strain setting, where the additive decomposition of the infinitesimal strains tensor yields

$$\frac{\partial \Delta\hat{\boldsymbol{\sigma}}_{m+1}}{\partial \Delta\boldsymbol{\varepsilon}_{m+1}} = \mathbf{D}_{m+1} = \frac{\partial \hat{\boldsymbol{\sigma}}_{m+1}}{\partial \boldsymbol{\varepsilon}_{m+1}}, \tag{4.194}$$

  the multiplicative decomposition of the deformation gradient under finite strains yields

$$\left(\frac{\partial \Delta \hat{\boldsymbol{P}}_{m+1}}{\partial \left(\boldsymbol{F}_{\Delta}\right)_{m+1}}\right)_{ijkl} = \left(\mathbf{A}_{m+1}\right)_{ijkq}\left(F_m\right)_{lq} = \left(\frac{\partial \hat{\boldsymbol{P}}_{m+1}}{\partial \boldsymbol{F}_{m+1}}\right)_{ijkl}\left(F_m\right)_{lq}. \tag{4.195}$$

In view of Equation (4.192) and given that the deformation gradient associated with the reference material is unknown, two options arise to formulate the finite strain regression-based self-consistent scheme analogous to Equation (4.192): (1) the CRVE homogenized consistent tangent modulus is replaced by the isotropic elastic tangent modulus,

$$\left\{\lambda^0_{m+1}, \mu^0_{m+1}\right\} = \underset{\{\lambda', \mu'\}}{\operatorname{argmin}} \left\| \Delta \boldsymbol{P}_{m+1} - \mathbf{A}^{e,0}_{m+1}(\lambda', \mu') * \boldsymbol{F}_m : \left(\boldsymbol{F}_{\Delta}\right)_{m+1} \right\|^2, \tag{4.196}$$

where $*$ denotes the suitable single contraction, or (2) the whole incremental derivative (see Equation (4.195)) is replaced by the isotropic elastic tangent modulus,

$$\left\{\lambda^0_{m+1}, \mu^0_{m+1}\right\} = \underset{\{\lambda', \mu'\}}{\operatorname{argmin}} \left\| \Delta \boldsymbol{P}_{m+1} - \mathbf{A}^{e,0}_{m+1}(\lambda', \mu') : \left(\boldsymbol{F}_{\Delta}\right)_{m+1} \right\|^2. \tag{4.197}$$

Both minimization problems can be solved by establishing a system of two linear equations analogous to the infinitesimal strains case (see Section C.5.2), with the second option yielding a similar functional format to Equation (C.39).

- **Convergence of partitioned scheme**. Both finite strain regression-based self-consistent schemes formulated by Equations (4.196) and (4.197) fail to converge, converge to physically inadmissible solutions (e.g., $E^0 < 0$) and/or converge to solutions that preclude the convergence of the micro-scale equilibrium problem (e.g., E^0 leading to reference material not sufficiently stiff). Several numerical assessments suggest that the convergence of the partitioned scheme calls for some sort of compatibility between the clustered Lippmann-Schwinger equilibrium formulation and the self-consistent scheme minimization problem. For instance, the partitioned scheme converges if the self-consistent scheme is instead formulated as

$$\left\{\lambda^0_{m+1}, \mu^0_{m+1}\right\} = \underset{\{\lambda', \mu'\}}{\operatorname{argmin}} \left\| \boldsymbol{P}_{m+1} - \mathbf{A}^{e,0}_{m+1}(\lambda', \mu') : \boldsymbol{F}_{m+1} \right\|^2, \tag{4.198}$$

which is consistent with the total nature of the clustered Lippmann-Schwinger system of equilibrium equations (see Equation (4.103)). However, the non-incremental nature of Equation (4.198) yields estimates of the reference elastic material's properties that lead to overstiff predictions. Similar numerical observations occur under infinitesimal strains when considering the clustered Lippmann-Schwinger system of equilibrium equations given by Equation (4.82) and the self-consistent scheme formulated as

$$\left\{\lambda^0_{m+1}, \mu^0_{m+1}\right\} = \underset{\{\lambda', \mu'\}}{\operatorname{argmin}} \left\| \boldsymbol{\sigma}_{m+1} - \mathbf{D}^{e,0}_{m+1}(\lambda', \mu') : \boldsymbol{\varepsilon}_{m+1} \right\|^2. \tag{4.199}$$

In this context, the development of an accurate self-consistent scheme compatible with the finite strain SCA under multiplicative kinematics is still under investigation. Besides unlocking a highly accurate and efficient CROM under finite strains, the research path to find the solution may well shed some light on the mathematical dependency of the clustered Lippmann-Schwinger integral equilibrium equation on the reference elastic material's properties.

4.10 Conclusions

This chapter aims to provide a solid contribution to the recent family of so-called clustering-based reduced-order models (CROMs), a promising approach to performing accurate and efficient multi-scale analyses based on computational homogenization. These methods are highly relevant to the paradigm of Integrated Computational Materials Engineering (ICME) as, among other applications, unlock feasible multi-scale coupled analyses of complex hierarchical material systems and allow the generation of high-fidelity material response databases for data-driven material design frameworks. Particular emphasis is given to the Self-consistent Clustering Analysis (SCA) method, the pioneering CROM proposed by Liu and coworkers (Liu et al., 2016), and a significant effort is put forth to provide all the numerical details required for a suitable computational implementation. In addition, several appendices are provided as a convenient background to the several contributions covered in this chapter.

In the first place, the Lippmann-Schwinger integral (quasi-static) equilibrium equation is thoroughly derived under both infinitesimal and finite strains. In addition to the fundamental concepts covered in Chapter 2, this introduces fundamental micromechanics concepts and sets the stage to formulate the clustered Lippmman-Schwinger integral equilibrium equation underlying the SCA's formulation. Concerning the original SCA formulation under infinitesimal strains (Liu et al., 2016): (i) it is demonstrated how the Lippmann-Schwinger integral equation can be equivalently established based on the additive nature of the infinitesimal strain and Cauchy stress tensors, (ii) the homogeneous far-field strain tensor is interpreted as a convenient numerical artifact to enforce general macro-scale strain and/or stress tensors, (iii) the suitable handling of the Green operator singularity at the zero frequency is discussed and related with the nature of the far-field strain tensor, and (iv) it is demonstrated that an incremental update of the reference homogeneous material's properties yields additional terms arising in the (additive) Lippmann-Schwinger integral equilibrium equation. Regarding the finite strain extension of the SCA method: (i) it is demonstrated that the formulation proposed by Yu and coworkers (Yu et al., 2019) assumes an additive decomposition of the deformation gradient and (ii) it is established the clustered Lippmann-Schwinger system of equilibrium equations compatible with the multiplicative nature of the deformation gradient.

In the second place, adaptivity is introduced to the recent family of CROMs with the goal of improving accuracy while keeping computational cost low when predicting localized phenomena such as plasticity and damage. In contrast with the static nature of most CROMs, where the clustering-based domain decomposition is solely defined by a preliminary offline-stage, the proposed ACROMs allow the clustering to evolve dynamically throughout the actual problem solution. Without loss of generality, the adaptive extension of the SCA method coined Adaptive Self-consistent Clustering Analysis (ASCA) is proposed and numerically evaluated. Three main blocks are considered in these methods: (i) target clusters selection criterion (Block A), to determine what clusters need to be refined; (ii) adaptive cluster analysis (Block B), to perform the actual clustering adaptivity; and (iii) computation of cluster interaction tensors (Block C), required to complete the clustering characterization. Several complementary procedures are further proposed to improve the overall performance of the adaptivity process, namely an adaptive clustering solution rewinding procedure and a dynamic adaptivity split factor strategy. An elasto-plastic particle–matrix composite exhibiting highly localized plasticity is numerically modeled and a simple ductile fracture criterion is defined. Two different clustering adaptivity strategies are successfully demonstrated and a thorough analysis shows that ASCA's accuracy is able to outperform SCA with a similar number of clusters concerning (i) the macro-scale homogenized response, (ii) the micro-scale accumulated plastic strain and accumulated plastic strain energy density fields and (iii) the composite's fracture and toughness prediction. From an efficiency point of view, ASCA can deliver solutions with greater accuracy than SCA with a lower or similar computational cost.

In the third place, the finite strain extension of the FFT-based homogenization basic scheme is briefly formulated following the infinitesimal strains counterpart originally proposed by Moulinec and Suquet (Moulinec and Suquet, 1994). Despite some well-known limitations of this pioneering FFT-based homogenization method, it shares the same fundamental Lippmann-Schwinger equilibrium formulation of the SCA and is particularly appealing to solve the associated offline-stage DNS elastic (infinitesimal strains) or hyperelastic (finite strains) analyses. With this in mind, a highly efficient implementation strategy based on Hadamard operations is proposed to accelerate (i) the computation of the Green operator associated to the auxiliary homogeneous problem, (ii) the computation of the micro-scale discrete stress field in the spatial domain, and (iii) the update of the micro-scale discrete strain field in the frequency domain. Despite its simplicity and a slight increase in terms of memory footprint, such a strategy is shown to yield massive speedups in comparison with a naive implementation under both infinitesimal and finite strains. The same approach can be adopted in the context of the SCA, namely to compute the Green operator underlying the definition of the cluster interaction tensors.

At last, a finite strain extension of the SCA compatible with the multiplicative nature of the deformation gradient is proposed. Concerning the SCA's offline-stage, four relevant aspects are addressed: (i) it is proposed a new definition of the fourth-order local elastic strain concentration tensor based on the elastic material logarithmic strain tensor, (ii) it is shown how the previous definition allows the simultaneous computation of the RVE effective elastic tangent modulus, (iii) the choice of suitable hyperelastic constitutive models is discussed, and (iv) the geometrical nonlinearity of the fourth-order strain concentration tensor with respect to the magnitude of the orthogonal strain loadings is numerically demonstrated. Regarding the SCA's online-stage, a multiplicative decomposition-based loading incrementation is described to enforce macro-scale strain constraints and the numerical solution of the micro-scale equilibrium problem is presented in great detail, namely (i) the formulation of the clustered Lippmann-Schwinger equilibrium residuals and the required Newton-Raphson linearization, (ii) the computation of the homogenized material response, and (iii) the computation of the CRVE homogenized consistent tangent modulus. Numerical analyses are performed over an elasto-plastic particle–matrix composite subject to several macro-scale (finite) strain-driven loadings and keeping the reference elastic material's properties constant throughout the deformation path. These analyses render important results with respect to the influence of the reference material's properties on the predicted material response, among which: (i) the influence of the reference material's Young modulus is smooth and associated with the 'stiffness' of the numerical prediction, (ii) a sufficiently stiff reference material is required to get a physically acceptable and converged solution of the equilibrium problem, and (iii) the reference material's Poisson ratio has a minor influence on the numerical predictions. In addition, it is shown that the proposed finite strain extension of the SCA (i) is able to deliver accurate predictions with a considerable model compression, provided that the reference material's properties are properly set, (ii) yields predictions whose accuracy increases with the number of clusters, i.e., converges with respect to the clustering-based domain decomposition, and (iii) is properly formulated, linearized and implemented as suggested by the quadratic convergence rate of the Newton-Raphson iterative scheme. Despite the success of the regression-based self-consistent scheme under infinitesimal strains (Liu et al., 2016), the finite strain extension of this approach is not straightforward, as discussed in the last section. The development of an accurate self-consistent scheme compatible with the proposed finite strain SCA under multiplicative kinematics is therefore still under investigation. Once this challenge is overcome, the finite strain ASCA under multiplicative kinematics becomes readily available.

Chapter 5
CRATE: Clustering-based Nonlinear Analysis of Materials

5.1 Open source clustering-based reduced-order modeling

One of the main contributions of this thesis to the scientific community is the development of CRATE (Clustering-based Nonlinear Analysis of Materials) (see Figure 5.1), a program designed to perform accurate and efficient multi-scale nonlinear analyses based on a coupling between first-order computational homogenization and clustering-based reduced-order models. This program will be released open source as one of the outputs of this thesis so that it can serve as a basis for development and/or an application tool for any researcher interested in this material multi-scale modeling approach.

In this context, the main features of CRATE are described in Section 5.2 and, although the code is extensively documented, the main ideas underlying its computational design and implementation structure are discussed in Section 5.3. Finally, although not implemented within the scope of this thesis, several future developments of CRATE are established in Section 5.4.

5.2 CRATE overview

CRATE is implemented in the open source programming language Python (Python 3 release), making it easily portable between all major computer platforms, easily integrated with other softwares implemented in different programming languages and benefiting from an extensive collection of prebuilt (standard library) and third-party libraries readily available. Because Python is not compiled down to binary machine code, a standard Python implementation execution speed may not be as fast as that of compiled languages such as C, C++ and Fortran. However, given the numerical nature of the program, its implementation relies heavily on the well-known NumPy scientific computing package and most numerical tasks are dispatched to compiled C code inside the Python interpreter. Therefore, by combining compiled and optimized numeric extension libraries (NumPy, SciPy, Scikit-learn, ...) with Python as the controlling language, the program is able to crunch numerical data at compiled code execution speeds. Nonetheless, it is important to remark that CRATE's initial version developed under the scope of the present thesis is not formally optimized nor parallelized except for the intrinsic optimization and/or parallelization of the aforementioned numerical extension libraries. Moreover, as clearly demonstrated in the following sections, CRATE is implemented in a high-modular architecture. Besides improving the overall readability and comprehension of the code, this means that the program can be easily extended to account for new features and developments, and be efficiently combined with other software.

In a single-scale analysis, the overall use of CRATE follows the main steps associated with the solution of a micro-scale equilibrium problem through first-order computational homogenization (see Chapter 2):

1. **Representative Volume Element (RVE)**. The first step consists of the definition of an RVE

Figure 5.1: Logo of CRATE (Clustering-based Nonlinear Analysis of Materials.

of the heterogeneous material under analysis. For instance, AMINO can be efficiently employed to generate RVEs of general particle-reinforced composite materials (see Chapter 3). Given that most CROMs operate on the frequency domain, the generation of a suitable node and/or element-based spatial discretization (e.g., finite element mesh, meshfree methods node placement), which usually demands specialized software, is not required. Instead, the spatial discretization can be simply provided as a regular grid of voxels where each voxel is labeled according to the material phase to which it belongs. In addition, this means that experimental micrographs (e.g., Scanning Electron Microscopy (SEM), Transmission Electron Microscopy (TEM)) can be directly used as an RVE as long as the different constituents can be identified through suitable image processing (see Figure 5.2)[1]. In contrast with the following steps, CRATE does not currently perform the computational generation of microstructures, i.e., the RVE must be provided as input data by the analyst.



Figure 5.2: Schematic of a 2D Representative Volume Element directly obtained from a heterogeneous material micrograph and spatially discretized in a regular grid of voxels.

2. **Material constitutive models.** The second step involves the selection of suitable constitutive models to characterize the behavior of the different material phases. CRATE admits general nonlinear constitutive models and distinguishes three different families (see Figure 5.3): (i) infinitesimal strains constitutive models, (ii) finite strains constitutive models, and (iii) finite strains constitutive models obtained from a purely kinematic extension of their infinitesimal counterpart (see Appendix F). The last family offers an elegant modeling approach in the sense that a infinitesimal strains constitutive

[1] Note that the number of voxels associated with the spatial discretization can be different from the micrograph resolution.

implementation suffices to consider both infinitesimal and finite strains problem formulations. In addition, CRATE already accounts for the possible access to constitutive models of external sources such as LINKS (Fortran) or ABAQUS (Fortran).



Figure 5.3: CRATE's material constitutive modeling interface.

3. **Macro-scale loading constraints.** The third step consists in defining the macro-scale loading constraints to be applied to the RVE. Under static or quasi-static loading constraints, CRATE offers flexible enforcement of general monotonic and non-monotonic loading paths characterized by first-order strain and/or stress constraints. Furthermore, a general incrementation scheme is provided by which the incrementation of each loading subpath can be prescribed nonuniformly and independently. A dynamic loading subincrementation scheme has also been implemented to prevent potential convergence failures stemming from excessively large increment steps. Whenever a convergence failure occurs, the current loading increment (or subincrement) magnitude is automatically cut in half in an attempt to ease the solution convergence by performing a smaller step in the enforced deformation path (see Figure 5.4). Once the solution convergence is achieved, an efficient progressive strategy is adopted to recover towards the originally prescribed increment magnitude. This means that the analyst doesn't need to define an excessively refined incrementation beforehand in an attempt to guarantee convergence throughout the whole deformation path.



Figure 5.4: CRATE's dynamic loading subincrementation scheme.

4. **Micro-scale equilibrium problem.** The fourth step concerns the solution of the micro-scale equilibrium problem through a given clustering-based reduced-order model.

CRATE's initial version accounts for the Self-consistent Clustering Analysis (SCA) method (see Appendix C) and its adaptive counterpart, the Adaptive Self-consistent Clustering Analysis (ASCA) method (see Chapter 4). Both methods are implemented following an implicit time integration scheme and are available under both infinitesimal and finite strains. Concerning the required offline-stage response database, which involves the DNS solution of linear elastic (infinitesimal strains) or hyperelastic (finite strains) micro-scale equilibrium problems, the so-called FFT-based homogenization basic scheme Moulinec and Suquet (1994) has been implemented in CRATE for both infinitesimal and finite strains (see Appendix B and Section 4.6). Nonetheless, a suitable interface with LINKS has also been implemented to compute the response database through a finite element-based first-order hierarchical multi-scale model based on computational homogenization. Regarding the cluster analysis, a suitable interface is implemented to integrate the most well-known clustering algorithms available in several open source third-party libraries (e.g., SciPy, PyClustering, Scikit-learn (Pedregosa et al., 2012)), namely the K-Means clustering algorithm (see Section C.3). In addition, a highly customized execution output allows the analyst to easily follow the problem solution, including steps completion, homogenized strain-stress response, residuals convergence and execution times.

5. **Post-processing results.** The fifth and last step consists of the post-processing of the results obtained. Several types of output files are available in CRATE, among which three are particularly important. In the first place, a log file is produced where the most important execution data is stored. In the second place, an output file stores the homogenized strain-stress material response for each loading increment together with additional strain- and stress-based pertinent metrics. Last but not least, a VTK XML format file is output for each loading increment containing all the local relevant fields (e.g., strain, stress, state variables, algorithmic variables). These are all linked in a collection VTK file together with the corresponding (pseudo-)time steps and can be spatially visualized through open source data analysis software such as ParaView.

Although nothing precludes the use of CRATE in single-scale analyses, it is in applications where the overall computational cost emerges as a bottleneck (both in terms of computational time and/or memory footprint) that the accuracy-efficiency trade-off is most valuable. Among such applications, it is possible to point out: (i) extensive parametric studies, where the computational cost stems from a large number of micro-scale analyses under different parameters values, (ii) hierarchically coupled multi-scale analyses, where the high computational cost arises from the nested solution of equilibrium problems at different scales[2], and (iii) build reliable material response databases to train machine learning models in the recent paradigm of data-driven material design frameworks.

5.3 Computational design and implementation

5.3.1 Object-oriented programming

CRATE is implemented in Python 3 following an object-oriented programming (OOP) paradigm and contains around 20000 lines of code in v1.0.0. In contrast with structured programming, where data and functionality are treated separately and extensive use of structured control flow constructs is made, object-oriented programming is built around data structures called objects.

[2] In the case of hierarchically coupled multi-scale analyses, the incremental strain and/or stress loading constraints are downscaled during the solution of each macro-scale loading increment and enforced in a single step by default. In addition, the effective tangent modulus must be up-scaled together with the homogenized stress tensor (see Chapter 2).

In a general sense, each object contains both data and behavior under the form of attributes and methods, respectively, and an OOP code essentially consists of a set of interacting objects. For a complete treatment of the Python OOP paradigm, the reader is referred to the vast literature available (e.g., Phillips (2018), Lott (2019)).

Fundamental to the Python OOP paradigm are the concepts of class and inheritance. Classes provide the definition of the data format and available methods for a given type of object, i.e., they are essentially constructors of objects that share similar properties and behavior. Besides defining their own specific data and behavior, inheritance allows lower-level classes to be built upon upper-level classes by inheriting their attributes and methods. This concept, which is often referred to as a 'is a' relationship between two classes, not only allows to follow code reusability principles but also to take advantage of abstraction and polymorphism.

Abstraction often emerges in the creation of classes that, although not having a spatial or temporal representation, aggregate common attributes and/or methods of several non-abstract (derived) classes. This concept is intrinsically associated with polymorphism, i.e., the creation of interfaces that serve as blueprints to implement new classes that respect a given contract. This contract establishes that certain attributes and/or methods must be defined by new classes according to their specific type, allowing different objects to be dynamically treated in a unified sense.

Finally, a desirable OOP implementation rests upon encapsulation or data hiding. This implies that the implementation details of a given class should be hidden from the remaining program and that different objects should only access and interact with each other through the available methods. Encapsulation is one of the pillars of a program's robustness and stability, inherently allowing code modularity and safe code maintenance and/or enrichment.

5.3.2 Base code structure

In this section, CRATE's OOP structure is described through the well-known Unified Modeling Language (UML), a language-independent abstract schematic toolkit that allows the visual representation of object-oriented programs (e.g., Rumbaugh (2005)). In particular, the so-called UML class diagrams are employed to represent the most important classes of CRATE as well as the interactions and relationships between them. It is remarked that the purpose here is not to explore any coding details, but rather to give the reader a global overview of CRATE's structure and the tools made available for the interested analyst and/or developer. Despite taking advantage of third-party libraries to perform several types of computations, it is remarked that only CRATE's original code is presented in the following sections. At last, given that different UML notations can be found in the literature, the UML notation consistently employed throughout this section is summarized in Figure 5.5.

Material constitutive modeling

The class `ConstitutiveModel` provides the interface to implement any constitutive model, requiring a suitable definition of the model strain type, material properties and state update. The latter method (`state_update`) is where the actual constitutive laws are implemented and ensures the incremental update of stress and state variables, as well as the computation of the consistent tangent modulus. The module `IsotropicHardLaw` provides a convenient set of functions to properly define different types of isotropic strain hardening laws useful to elasto-plastic constitutive modeling.

In turn, the class `MaterialState` contains the required data and the main high-level procedures related to the material constitutive modeling. In terms of data, it stores the different material phases constitutive models and associated properties, the material clusters deformation gradient, state variables and consistent tangent modulus, and the homogenized



Figure 5.5: UML class diagram notation and class relationships.

strain and stress tensors. In addition, it provides two essential operations. First, the method `update_clusters_state` performs the incremental state update of all material clusters, using a material state update interface (`material_su_interface`) and the pre- and post-processing kinematic operations (`compute_inc_log_strain` and `compute_spatial_tangent_modulus`, respectively) required to implement kinematically-extended finite strains constitutive models. Second, the method `update_state_homogenization` performs the strain and stress computational homogenization from the contribution of all material clusters.

The integration of a new constitutive model in CRATE essentially requires a new class (`NewConstitutiveModel`) that implements the `ConstitutiveModel` interface.



Figure 5.6: CRATE UML class diagram associated with the material constitutive modeling.

Cluster-reduced representative volume element

The class `CRVE` contains the required data and main high-level procedures related to the definition of the cluster-reduced representative volume element (CRVE). These include the base clustering constructor (`base_clustering_scheme`, `perform_crve_base_clustering`), the spatial and phase-wise base clustering distribution (`voxels_clusters` and `phase_clusters`) and the collection of cluster-reduced material phases (CRMPs) that compose the CRVE. The class `CRMP` provides the interface to implement any type of CRMP, such as the default static CRMP (`SCRMP`). Last but not least, the class `CRVE` incorporates the cluster interaction tensors (`cit_x_mf`) and the methods required to compute them (e.g., `compute_cit`). The integration of a new type of CRMP solely requires a new class (`NewCRMP`) that implements the `CRMP` interface.

The module `CITOperations` provides functions convenient to set the discretization in the frequency domain (`set_discrete_freqs`) and to compute the Green operator material-independent components (`gop_material_independent_terms`).



Figure 5.7: CRATE UML class diagram associated with the cluster-reduced representative volume element (CRVE) and cluster-reduced material phase (CRMP).

Clustering data and cluster analysis

The module `ClusteringData` contains all the required data and procedures to compute the clustering features serving as a basis to perform the RVE clustering-based domain decomposition. For this purpose, the main function (`set_clustering_data`) takes advantage of the class `ClusterAnalysisData`, which includes the complete information about the prescribed clustering features (e.g., `features_descriptors`, `mac_strains`) and the high-level method to compute the global features data matrix (`set_global_data_matrix`).

The class `FeatureAlgorithm` provides a suitable interface to define any feature computation algorithm, such as the fourth-order strain concentration tensor (`StrainConcentrationTensor`). The integration of a new clustering feature only requires a new class (`NewFeatureAlgorithm`) that implements this interface. In addition, the class `Standardizer` consists of an interface that performs the clustering feature data standardization, namely the common min-max scaling (`MinMaxScalar`) or standard scaling (`StandardScaler`).

With the clustering features data at hand, the actual cluster analysis of all cluster-reduced material phases is performed by the class `ClusterAnalysis` through the method `get_fitted_estimator`. The latter uses the clustering algorithms made available through the class `ClusteringAlgorithm`, an interface to implement any clustering algorithm such as the well-known K-Means (`KMeansSK`, see Section C.3).



Figure 5.8: CRATE UML class diagram associated with the clustering data computation and the cluster analysis.

DNS material response database

In a general sense, the clustering features require the DNS solution of one or more micro-scale equilibrium problems, i.e., the computation of an RVE material response database under different loading constraints. For instance, the particular case of the fourth-order local elastic strain concentration tensors demands the DNS solution of several elastic or hyperelastic micro-scale equilibrium problems under orthogonal strain loading constraints.

The computation of such a voxel-based local response database is assigned to the class `RVEElasticDatabase` through the method `compute_rve_response_database`. The later takes advantage of the DNS homogenization methods made available through the class `DNSHomogenizationMethod`, an interface to implement any type of solver based on first-order computational homogenization. In order to equip CRATE with an internal DNS homogenization method, the FFT-based homogenization basic scheme proposed by Moulinec and Suquet (Moulinec and Suquet, 1994) is implemented in the class `FFTBasicScheme`. The class `MacroscaleStrainIncrementer` is also implemented to enforce monotonic macro-scale strain loading constraints and the associated incrementation.



Figure 5.9: CRATE UML class diagram associated with the computation of a DNS material elastic response database.

Clustering-based reduced-order model

The class `CROM` provides the interface to implement any clustering-based reduced-order model (`CROM`). The module `ASCA` includes the class `ASCA` that contains the implementation of both Self-consistent Clustering Analysis (SCA) and the Adaptive Self-consistent Clustering Analysis (ASCA) methods. Besides the high-level method that solves the micro-scale equilibrium problem (`solve_equilibrium_problem`), additional procedures are implemented to compute the required residuals (`build_residual`), the Newton-Raphson iterative jacobian matrix (`build_jacobian`) and the CRVE effective tangent modulus (`crve_effective_tangent_modulus`). Moreover, the class `ElasticReferenceMaterial` is implemented to contain all data related to the reference (fictitious) homogeneous material as well as methods to solve the Self-consistent scheme and update the associated elastic properties. The integration of a new CROM requires a new class (`NewCROM`) that implements the `CROM` interface.

The class `LoadingPath` provides all data and high-level methods required to enforce completely general macro-scale strain and/or stress loading paths. This is accomplished by designing a loading path as a collection of sequential monotonic loading subpaths. Each loading subpath is constructed by the class `LoadingSubpath`, which also contains suitable procedures to set the loading incrementation and the dynamical loading subincrementation scheme. Note that these tools can be immediately accessed by any CROM implemented in CRATE.



Figure 5.10: CRATE UML class diagram associated with the clustering-based reduced-order model.



Figure 5.11: CRATE UML class diagram associated with the loading path and incrementation.

Post-processing and output files

The class `IncrementalOutputFile` provides the interface to implement any type of incremental output file, i.e., an output file that contains a given set of data associated with each macro-scale loading increment. Three different types of incremental output files are implemented: (i) the class `HomResOutput`, essentially related to the strain-stress homogenized material response; (ii) the class `RefMatOutput`, related to the reference material elastic properties and self-consistent scheme iterations; and (iii) the class `VoxelsOutput`, associated with the output of voxel-based local fields of interest. The integration of a new type of incremental output file solely requires a new class (`NewIncrementalOutputFile`) that implements the `IncrementalOutputFile` interface.

In contrast with the previous incremental output files, the VTK XML format output is implemented as an independent class (`VTKOutput`) due to the associated complexity. The main purpose of this class is to process relevant problem incremental data and output the corresponding VTK XML format files (`write_vtk_file_time_step`). This task is supported by the class `XMLGenerator`, which basically translates the output data into appropriate XML constructs. In addition, the class `VTKCollection` compiles a VTK collection file that contains a list of sequential pointers to the VTK incremental output files. The latter allows the spatial visualization of the problem's local field's evolution and renders animations.



Figure 5.12: CRATE UML class diagram associated with the incremental output files.



Figure 5.13: CRATE UML class diagram associated with the VTK output files.

Tensorial and matricial operations

Last but not least, two modules are implemented to consistently provide the required tensorial (`TensorOperations`) and matricial (`MatrixOperations`) entities and operations throughout the whole program.

The module `MatrixOperations` fulfills four types of operations. Firstly, the function `get_problem_type_parameters` sets the number of spatial dimensions and both symmetric- and non-symmetric strain/stress components matricial storage order according to the problem type. Secondly, the functions `get_tensor_mf` and `get_tensor_from_mf` perform the storage of second- and fourth-order tensors in matricial form and the opposite procedure. Symmetric second-order tensors and minor-symmetric fourth-order tensors are stored following the Kelvin notation[3], otherwise the matricial storage is performed columnwise. Thirdly, the function `get_condensed_matrix` performs a general matrix condensation procedure according to a given set of row and column indexes. Lastly, the functions `get_state_3Dmf_from_2D_mf` and `get_state_2Dmf_from_3Dmf` perform conversions between 2D and 3D strain and stress tensors matricial forms.

The module `TensorOperations` sets common second- and fourth-order identity operators (`get_id_operators`), common tensorial operations (e.g., dyadic product, single and double contraction), the discrete Dirac's delta function (`dd`) and the p-th root of a general non-symmetric square matrix (`matrix_root`). In turn, the function `spectral_decomposition` computes not only the eigenvalues and eigenvectors of a symmetric second-order tensor (available in many third-party libraries), but also the spectral decomposition eigenprojections. The latter allows the computation of isotropic symmetric tensor-valued functions of symmetric tensors and associated derivatives through `isotropic_tensor` and `derivative_isotropic_tensor`.



Figure 5.14: CRATE UML class diagram associated with the tensorial and matricial operations.

[3] As described by Nagel et al. (2016), the Kelvin notation has two advantages in comparison with the often employed Voigt notation: (1) by adopting an orthonormal tensor basis, it leads to an invariant representation and to the same matricial form mapping rules irrespective of the tensor's nature; (2) preserves the tensor character, leading to similar properties and operations between tensor and matricial form.

5.3.3 Clustering adaptivity extension

The first extension of CRATE's base code aims to enrich any CROM implementation with the clustering adaptivity formulation proposed in this thesis. The clustering adaptivity core implementation consists of three main classes described in what follows.

The class `AdaptivityManager` contains most of the data related to clustering adaptivity and provides the high-level methods to perform a clustering adaptive refinement. The first block of a clustering adaptivity step, which is related to the selection of clusters to be refined, is executed by `get_target_clusters`. This method builds the clustering adaptivity feature data matrix for each adaptive material phase and feeds this data to the target clusters selection criterion. The class `AdaptivityCriterion` provides an interface to implement any selection criterion. For instance, the selection criterion based on the evaluation of spatial discontinuities is implemented by the class `SpatialDiscontinuities`, containing all the associated hyperparameters and procedures required to perform the target clusters selection.

In turn, the second block of a clustering adaptivity step, which comprises the actual adaptive cluster analysis of the target clusters, is performed through `adaptive_refinement`. This method receives the set of target clusters and delegates to the (enriched) class `CRVE` the task of updating the clustering of each adaptive cluster-reduced material phase (ACRMP). The class `ACRMP` is derived as a specific type of `CRMP` and provides the interface to implement any ACRMP, such as the generalized adaptive cluster-reduced material phase (`GACRMP`). The latter contains all the required hyperparameters and procedures to perform the adaptive cluster analysis by following a dynamic cluster subdivision strategy. Concerning both SCA and ASCA methods, the update of the cluster interaction tensors consistent with the adaptive cluster analysis (third block of a clustering adaptivity step) is performed by the previously implemented method `compute_cit` of class `CRVE`. However, this method is now enriched with a special mode by which only the interaction tensors associated with new clusters are computed by taking advantage of cluster-symmetry whenever possible. At last, the inheritance of the cluster state variables consistent with the adaptive cluster analysis is delegated to the class `MaterialState`, enriched with the method `clustering_adaptivity_update`.

The adaptive clustering solution rewinding is essentially materialized by two different classes. The first is the class `RewindManager`, which comprises the data and procedures associated with the rewind state storage and rewinding criteria. The second is the class `IncrementRewinder`, which actually executes the required storage and rewinding whenever the corresponding criteria are triggered. The rewind state storage involves saving the objects `LoadingPath` and `MaterialState` at the rewind state, while the rewinding procedure essentially replaces the current instances with the stored ones. However, to account for the difference between the current clustering and the one stored at the rewind state, the proper recovery of the clusters state variables requires a suitable search throughout the clustering adaptivity hierarchy that is implemented in `get_material_state`. Finally, the method `rewind_output_files` rewinds all the output files back to the rewind state, demanding an enrichment of the interface `IncrementalOutputFile` and of the class `VTKOutput`.

5.4 Future developments

Despite being incompatible with the time frame of the present thesis, several developments of CRATE have already been established to be addressed in the next versions:

- **Hierarchically multi-scale coupled analysis**. Given the OOP structure previously described, the CRATE's extension to account for hierarchically coupled multi-scale analyses comes at little cost. Such extension essentially requires four main ingredients: (i) the instantiation of the already implemented classes for each scale under analysis, e.g.,

an object `CRVE` associated with each scale; (ii) the enrichment of the method `material_su_interface` of class `MaterialState`, such that the `state_update` of class `ConstitutiveModel` may be replaced by the solution of a micro-scale equilibrium problem through first-order computational homogenization; (iii) the computation of the CRVE effective consistent tangent modulus that is required to compute the macro-scale Newton-Raphson iteration jacobian matrix, which is already implemented in `crve_effective_tangent_modulus` of class `ASCA`; (iv) the computation of a consistent step whenever the dynamic loading subincrementation scheme is activated, i.e., solving the macro-scale increment in a single step by providing the known solution as an initial guess. This extension would immediately unlock the possibility to perform mesoscopic-microscopic or mesoscopic-microscopic-nanoscopic coupled analyses as long as the Principle of Scales Separation is satisfied and the computational homogenization is significant from a physical point of view. A suitable coupling with a standard finite element code may additionally yield feasible macro-scale-meso-scale (FE-ASCA) and macro-scale-meso-scale-micro-scale (FE-ASCA-ASCA) hierarchically multi-scale coupled analyses;

- **Dynamic state update subincrementation scheme**. A similar approach to the dynamic loading subincrementation scheme can be adopted regarding each cluster state update. In this case, if the state update fails to converge for a given incremental strain tensor (infinitesimal strains) or deformation gradient (finite strains), the subincrementation scheme depicted in Figure 5.4 can be analogously adopted to attempt a converged solution. This scheme prevents that the state update convergence failure of a single cluster leads to a macro-scale increment cut and the associated waste of computational resources;

- **Parallelization**. The advantage of highly parallel computational architectures should be taken through parallelization of the material clusters state update as well as parallelization of the cluster interaction tensors computation. While the former is completely general (any CROM online-stage), the latter is expected to yield significant efficiency gains in both SCA and ASCA methods where the computation of these tensors has a dominant computational cost (both offline-stage and adaptive online-stage);

- **Constitutive modeling**. The class `MaterialState` and the interface `ConstitutiveModel` allow a straightforward integration of new constitutive models in CRATE's constitutive modeling repository. This enrichment should prioritize the incorporation of constitutive models suitable for different classes of materials in order to generalize the application of CRATE in practical engineering problems;

- **FFT-based homogenization methods**. CRATE's FFT-based homogenization methods toolkit can be enriched through the implementation of more recent FFT-based methods with improved accuracy and efficiency (interface `DNSHomogenizationMethod`). Besides their role in the SCA's and ASCA's offline-stage, which currently only accounts for elastic or hyperelastic constitutive behavior, general FFT-based homogenization methods may be useful to internally evaluate the accuracy of CROM solutions without the need for external DNS solvers. This aspect is particularly interesting regarding both SCA and ASCA, where the fundamental basis of the solution is similar to FFT-based methods.



Figure 5.15: CRATE UML class diagram associated with the clustering adaptivity management, criterion and rewinding procedure.



Figure 5.16: CRATE UML class diagram associated with the adaptive cluster-reduced material phase and clustering adaptivity code enrichment.

Chapter 6
Constitutive Modeling of Amorphous Thermoplastics

6.1 Introduction

Nowadays, thermoplastic polymers are an important class of advanced engineering materials that are used in a variety of industrial applications such as aeronautics, automobile and consumer electronics. Their wide application as structural materials stems from the combination of excellent mechanical, thermal, optical and chemical properties, which can be tailored through suitable manufacturing processes at low production costs. However, their structural performance is generally associated with a highly nonlinear thermomechanical behavior which demands the development of accurate constitutive models that can be effectively used in terms of engineering practice.

Thermoplastics describe polymers which soften or melt when heated and harden when cooled in a reversible and repeatable way. This behavior is associated with the relative movement of adjacent molecular chains that result from thermally-induced rotations and vibrations usually allowed in both linear and branched polymers (Callister and Rethwisch, 2013). Amorphous thermoplastics are polymers that retain the amorphous structure characteristic of the liquid melt when cooled after going through the so-called glass transition, i.e., a second-order transition that occurs at the glass transition temperature and describes the gradual transition from a rubbery solid into the amorphous rigid solid[1] (Kumar and Gupta, 2018). Their solid structure is, therefore, essentially characterized by molecular chain disorder and randomness, associated with a high entanglement level resultant from a multitude of molecular chain bends, twists, coils and kinks (Sperling, 2006).

Besides the natural dependency on the underlying chemical (composition, repeating sequence) and physical (molecular size, shape, branching, configuration), the mechanical properties and behavior of thermoplastics is highly dependent on temperature, rate of deformation (or strain rate) and hydrostatic pressure (McCrum et al. (1997), Haward and Young (2012)). For temperatures below the glass transition temperature and for relatively small deformations, the mechanical behavior exhibits a combination of elastic and viscous characteristics usually called visco-elasticity. Elastic behavior is associated with a instantaneous (time-independent) deformation (and recovery), whereas viscous behavior denotes time-dependent deformations (and recovery) due to relaxation processes that occur at the molecular level (Bergstrom, 2015). For temperatures well below the glass transition temperature, molecular motions are largely restricted to vibration and short-range rotations, being the mechanical behavior essentially elastic (rigid solid material). As the temperature increases and approaches the glass transition temperature, molecular relaxation processes associated with viscous effects start to take place (rubbery solid material). When the deformation surpasses a given threshold, the amorphous thermoplastic may either fracture (brittle behavior) or undergo irreversible time-dependent viscous inelastic deformations (commonly designated visco-plasticity) prior to fracture. In contrast with the well-established

[1] For a temperature sufficiently below the glass transition temperature, the amorphous polymer can be said to be in a solid glassy state - hence the common designation of glassy polymer to describe amorphous thermoplastics.

plastic slip theory for metallic materials, the comprehension of the physical mechanisms underlying the yielding and post-yielding behavior of amorphous thermoplastics is still a topic of open discussion in virtue of their disordered and random microstructure. Fracture of amorphous thermoplastics is frequently preceded by crazing, a phenomenon associated with regions of very localized plastic deformation, which lead to the formation of small and interconnected microvoids that lead to crack propagation after rupturing of fibrillar bridges (Callister and Rethwisch, 2013).

The characteristic visco-elastic-visco-plastic behavior of a ductile amorphous thermoplastic subjected to a uniaxial compression monotonic loading is schematically illustrated in Figure 6.1. The true compressive stress-strain response can be clearly divided into four different stages (A-D). After an initial stage where the stress response is approximately linear elastic (A), a nonlinear visco-elastic behavior characterizes the stress response up to the yield point (B). Once the yield point is surpassed and the material undergoes visco-plastic deformation, the true stress decreases with increasing deformation (C) - this phenomenon is called strain softening and characterizes the intrinsic post-yielding behavior of most amorphous thermoplastics. At last, after the softening mechanism is saturated, the material exhibits a nonlinear strain hardening until failure (D). Numerous experimental contributions have provided valuable insights into the influence of temperature, strain rate and hydrostatic pressure on the mechanical response of amorphous thermoplastics (e.g., Bauwens-Crowet (1973), Arruda et al. (1995), Mulliken and Boyce (2006), Morelle et al. (2017)).



Figure 6.1: Characteristic constitutive behavior of amorphous thermoplastics when subjected to uniaxial compression loading.

Over the last decades, a considerable effort has been made by the scientific community to develop constitutive models that can describe the deformation behavior of polymeric materials accurately. Pioneering work dates back to the 30s, when Eyring proposed a molecular theory for the yield stress of amorphous polymers, already accounting for temperature and strain rate effects (Eyring, 1936). Some decades later, Haward and coworkers (Haward et al., 1968) developed one of the first one-dimensional constitutive models for predicting the behavior of amorphous thermoplastics. In this constitutive model, the post-yielding behavior included a rate-dependent plastic flow, modeled by an Eyring dashpot, and a rate-independent contribution associated with the molecular entanglements, modeled by a Langevin spring. Twenty years later, the Haward et al. (1968) model was extended to the three-dimensional case by Boyce and coworkers (Boyce et al., 1988), the so-called Boyce-Parks-Argon (BPA) model, being later enhanced with the well-known eight-chain model (Arruda and Boyce, 1993).

Another major constitutive approach was proposed by Leonov (Leonov, 1976), from which a compressible version was developed by Baaijens (Baaijens, 1991) that, in turn, was later derived within a thermodynamically consistent framework by Tveroort and coworkers (Tervoort et al., 1997). To capture the typical characteristics of the post-yield behavior of glassy polymers, namely the phenomenon of strain softening and hardening, Timmermans and Govaert (Timmermans (1997), Govaert et al. (2000)) extended Tvervoort's model, leading to the generalized compressible Leonov model, currently known as the Eindhoven Glassy Polymer (EGP) model. Another well-known contemporary model is due to Buckley and Jones (Buckley and Jones, 1995), named Oxford Glass Rubber (OGR) model, which is structurally similar to Tvervoort's model, but the resistance to entropy-elastic chain stretch is described by the Edwards-Vilgis free energy function (Edwards and Vilgis, 1986). Since then, these pioneering contributions have inspired the development of many constitutive models for amorphous thermoplastics that aim to enhance previously established constitutive laws, accurately capturing the effects of different loading conditions, and accounting for distinct microstructural mechanisms. Among these one may mention relevant contributions by Anand and coworkers (Anand and Gurtin (2003), Anand and Ames (2006), Anand et al. (2009), Lele and Anand (2009), Srivastava et al. (2010)), Doghri and coworkers (Miled et al. (2011), Krairi and Doghri (2014)), Govaert and coworkers (van Melick et al. (2003a), van Melick et al. (2003b), Klompen et al. (2005), van Breemen et al. (2011), van Breemen et al. (2012), Amiri-Rad et al. (2019)) and many others (Wu and Buckley (2004), Buckley et al. (2004), Yu et al. (2014), Abu Al-Rub et al. (2015), Mirkhalaf et al. (2016), Yu et al. (2016), Zhang and To (2016), Nguyen et al. (2016), Yu et al. (2017)). On a more recent note, Gudimetla and Doghri (Gudimetla and Doghri, 2017) propose a finite strain thermodynamically-based constitutive model for glassy polymers and perform comparisons with the experimental data obtained by Morelle and coworkers (Morelle et al., 2017). Krairi and coworkers Krairi et al. (2019) extend the small strain viscoelastic-viscoplastic model proposed by Miled and coworkers (Miled et al., 2011) by including the model into a thermo-mechanical coupled framework. By performing a suitable extension of the effective temperature model of Xiao and Nguyen (Xiao and Nguyen, 2015), Wang and coworkers (Wang et al., 2021) propose a large deformation model that aims to accurately capture the temperature-dependent and strain rate dependent post-yielding strain hardening behavior as well as the Bauschinger effect under reversed loading. Uchida and coworkers (Uchida et al., 2022) propose a viscoelastic-viscoplastic model based on the underlying physics of the polymer chain deformation, by extending their previous contribution (Uchida et al., 2019) to account for the temperature and strain rate dependent mechanical behavior below the glass transition temperature. A finite strain thermodynamically-based constitutive model with a highly physical basis is also proposed by Wang and coworkers (Wang et al., 2019a), with particular focus on the stress relaxation and strain recovery in the post-yielding stage. Holopainen and coworkers (Holopainen et al. (2017), Holopainen and Barriere (2018)) propose a thermodynamically consistent approach to model isothermal ductile fatigue damage in amorphous thermoplastics. Following other recent contributions that address continuum damage mechanics in amorphous thermoplastics (e.g., Shojaei and Volgers (2018), Shen et al. (2019)), Khaleghi and coworkers (Khaleghi et al., 2022) extend the EGP model with a thermodynamically consistent damage model based on the damage evolution law introduced by Lemaitre (Lemaitre, 2013).

However, despite the vast number of constitutive models developed in the past decades to predict the mechanical behavior of amorphous thermoplastics, most of them are either visco-elastic or elasto-visco-plastic (Gudimetla and Doghri, 2017). Although intricate dependencies and complex phenomena have been accounted for in many valuable contributions, accurate constitutive predictions call for a suitable coupling of visco-elasticity and visco-plasticity characteristic of amorphous thermoplastics as demonstrated by state-of-the-art contributions (e.g., Holopainen and Barriere (2018), Krairi et al. (2019), Matsubara et al. (2020)). On a different note, many constitutive models account for a lengthy

set of material properties whose physical meaning is difficult to grasp and/or require cumbersome calibration procedures involving several types of experiments. Moreover, the computational implementation is not always detailed in an entirely comprehensive way and/or turns out to be rather complex for the interested analyst. The aforementioned aspects raise limitations in terms of actual engineering applicability of (sometimes) highly sophisticated and capable constitutive models.

Within this context, the aim of this contribution is to formulate a constitutive model based on well-established rheological elements together with a computational implementation and calibration, which are extremely efficient. The overall framework has the following distinctive features:

- Describes the finite strains' nonlinear constitutive behavior of amorphous thermoplastics under isothermal deformation processes below the glass transition temperature, including both visco-elasticity and visco-plasticity (strain softening and strain hardening);

- Accounts for a reasonable number of material properties that (i) have a well-defined physical influence on each stage of the intrinsic visco-elastic-visco-plastic numerical response and (ii) can be completely calibrated from standard uniaxial compression experiments;

- Proposes a highly efficient, fully implicit computational implementation made accessible through a detailed description of both constitutive state update and consistent tangent modulus;

- Proposes a convenient two-stage optimization-based calibration procedure that identifies the material parameters in a completely unsupervised way.

Moreover, given the importance of rubber toughening to enhance the fracture resistance of amorphous thermoplastics, a constitutive extension of the proposed constitutive model to account for the phenomenon of rubber particle internal cavitation is also described. Such an extension incorporates damage in the form of nucleation and growth of voids in the post-yielding visco-plastic behavior of rubber-thoughened amorphous thermoplastics.

This chapter is organized as follows. Section 6.2 provides the complete description of the visco-elastic-visco-plastic constitutive model following the formalism of thermodynamics with internal variables. Section 6.3 presents all the required ingredients for a suitable numerical implementation, namely the constitutive state update and the consistent tangent modulus arising in the context of a fully implicit solution of a mechanical initial boundary value equilibrium problem formulated by means of the Finite Element Method. Section 6.4 illustrates the physical influence of the material properties and describes an efficient two-stage optimization-based calibration procedure based on simple uniaxial compression tests at different temperatures and strain rates. Section 6.5 demonstrates the accuracy of the proposed model in the prediction of the true stress - true strain compressive response of PC under several temperatures and strain rates, being the predictions compared with both experiments and numerical results available in the literature. Section 6.6 discusses an extension of the proposed constitutive model to account for the phenomenon of rubber particle internal cavitation occurring in the deformation of rubber-toughened amorphous thermoplastics. At last, Section 6.7 summarizes the main conclusions.

6.2 Visco-elastic visco-plastic constitutive model

6.2.1 Rheological model

In a one-dimensional setting, the visco-elastic-visco-plastic constitutive model formulated in this contribution is characterized by the rheological model schematically illustrated in Figure 6.2. The total stress, $\boldsymbol{\tau}_{\mathrm{T}}$, is additively decomposed into two main components as

$$\boldsymbol{\tau}_{\mathrm{T}} = \boldsymbol{\tau}_{\mathrm{D}} + \boldsymbol{\tau}_{\mathrm{H}}\,, \tag{6.1}$$

where $\boldsymbol{\tau}_{\mathrm{D}}$ denotes the driving stress (upper branch) and $\boldsymbol{\tau}_{\mathrm{H}}$ denotes the hardening stress (lower branch). The driving branch is composed of two elements connected in series. The first element consists of a linear spring, associated with the material (rate-independent) elastic response, connected in parallel with n_{V} Maxwell elements, each associated with a relaxation mode of the material (rate-dependent) visco-elastic response. The second element is an Eyring dashpot and characterizes the material (rate-dependent) visco-plastic response. The hardening branch is solely composed of a nonlinear hardening spring that accounts for the plasticity-induced material strain hardening.



Figure 6.2: Rheological model of the proposed visco-elastic-visco-plastic constitutive model.

6.2.2 Kinematics

In the finite strain setting, the deformation gradient, $\boldsymbol{F}$, is introduced to characterize the mapping between the reference (undeformed) and deformed configurations as $\boldsymbol{F} = \nabla_0 \boldsymbol{\varphi}(\boldsymbol{X}, t)$, where $\nabla_0(\bullet)$ denotes the material gradient operator and $\boldsymbol{\varphi}(\boldsymbol{X}, t)$ the motion function (see Figure 6.3). Here is assumed the well-known hypothesis of the multiplicative decomposition of the deformation gradient (Lee and Liu (1967), Lee (1969)) such that

$$\boldsymbol{F} = \boldsymbol{F}^e \boldsymbol{F}^p\,, \tag{6.2}$$

where $\boldsymbol{F}^e$ and $\boldsymbol{F}^p$ denote the visco-elastic and visco-plastic deformation gradients, respectively. Therefore, admitting the existence of a local unstressed intermediate configuration, $\boldsymbol{F}^p$ establishes the mapping between the reference and intermediate configurations, while $\boldsymbol{F}^e$ maps between the intermediate and deformed configurations. Attending to Figure 6.2, note

that in the present model: (i) $\boldsymbol{F} = \boldsymbol{F}_{\mathrm{D}} = \boldsymbol{F}_{\mathrm{H}}$, where $\boldsymbol{F}_{\mathrm{D}}$ and $\boldsymbol{F}_{\mathrm{H}}$ denote the deformation gradients acting on the driving and hardening branches, respectively; (ii) $\boldsymbol{F}^e_\infty = \boldsymbol{F}^{ve}_i = \boldsymbol{F}^e$, where $\boldsymbol{F}^e_\infty$ denotes the elastic deformation gradient acting on the (instantaneous) linear spring and $\boldsymbol{F}^{ve}_i$ denotes the visco-elastic deformation gradient acting on the i-th visco-elastic Maxwell element; (iii) $\boldsymbol{F}^p$ is acting on the Eyring visco-plastic dashpot.

In addition, the velocity gradient, $\boldsymbol{L}$, is defined as

$$\boldsymbol{L} = \dot{\boldsymbol{F}}\boldsymbol{F}^{-1}, \tag{6.3}$$

where $(\dot{\bullet})$ denotes the time derivative, which after insertion of Equation (6.2) yields

$$\boldsymbol{L} = \boldsymbol{L}^e + \boldsymbol{F}^e \boldsymbol{L}^p \left(\boldsymbol{F}^e\right)^{-1}, \tag{6.4}$$

where $\boldsymbol{L}^e = \dot{\boldsymbol{F}}^e(\boldsymbol{F}^e)^{-1}$ is the elastic velocity gradient (defined in the deformed configuration) and $\boldsymbol{L}^p = \dot{\boldsymbol{F}}^p(\boldsymbol{F}^p)^{-1}$ is the plastic velocity gradient (defined in the intermediate configuration). It transpires that the operator $\boldsymbol{F}^e(\bullet)\left(\boldsymbol{F}^e\right)^{-1}$ is nothing more than a push-forward of the plastic velocity gradient to the deformed configuration. The plastic velocity gradient can be decomposed into its symmetric and skew components as

$$\boldsymbol{L}^p = \boldsymbol{D}^p + \boldsymbol{W}^p, \tag{6.5}$$

where $\boldsymbol{D}^p = \mathrm{sym}[\boldsymbol{L}^p]$ is the rate of plastic deformation tensor and $\boldsymbol{W}^p = \mathrm{skew}[\boldsymbol{L}^p]$ is the plastic spin tensor. It is also convenient to define the spatially rotated rate of plastic deformation tensor as

$$\tilde{\boldsymbol{D}}^p = \boldsymbol{R}^e \boldsymbol{D}^p (\boldsymbol{R}^e)^T, \tag{6.6}$$

where $\boldsymbol{D}^p$ is rotated to the deformed configuration by means of the elastic rotation tensor $\boldsymbol{R}^e = \boldsymbol{F}^e[(\boldsymbol{F}^e)^T\boldsymbol{F}^e]^{-1/2}$.



Figure 6.3: Deformation gradient multiplicative decomposition hypothesis.

As the last kinematic ingredient, the spatial logarithmic strain tensor is adopted as a convenient strain measure, defined as

$$\boldsymbol{\varepsilon} = \ln[\boldsymbol{V}] = \frac{1}{2}\ln[\boldsymbol{B}]\,, \tag{6.7}$$

where $\boldsymbol{V}$ is the left stretch tensor and $\boldsymbol{B} = \boldsymbol{F}(\boldsymbol{F})^T$ is the left Cauchy-Green strain tensor. Substitution of Equation (6.2) renders the additive decomposition of the spatial logarithmic strain tensor into elastic and plastic components as

$$\boldsymbol{\varepsilon} = \boldsymbol{\varepsilon}^e + \boldsymbol{\varepsilon}^p\,, \tag{6.8}$$

where $\boldsymbol{\varepsilon}^e$ and $\boldsymbol{\varepsilon}^p$ denote the elastic and plastic spatial logarithmic strain tensors, respectively. Besides its physical meaning, the particular choice of such measure as the elastic primary kinematic unknown allows a considerable simplification of the constitutive problem solution, as discussed in Section 6.3.

Based on these fundamental assumptions, the constitutive model is described in the following sections. The formulation follows the formalism of thermodynamics with internal variables under isothermal conditions and results from the suitable combination of valuable constitutive contributions available in the literature.

6.2.3 Specific free energy

The specific free energy function (or Helmholtz free energy per unit mass), ψ, is assumed to be decomposed into two components as

$$\psi = \psi(\boldsymbol{\varepsilon}, \boldsymbol{\varepsilon}^p, \bar{\varepsilon}^p) = \psi^{ve}(\boldsymbol{\varepsilon}^e) + \psi^{vp}(\boldsymbol{\varepsilon}, \bar{\varepsilon}^p)\,, \tag{6.9}$$

where ψ^{ve} is a visco-elastic potential and ψ^{vp} a visco-plastic potential[2]. Both $\boldsymbol{\varepsilon}^p$ (see Equation (6.8)) and $\bar{\varepsilon}^p$, usually designated by accumulated plastic strain, are taken as internal variables of the constitutive model associated with dissipative mechanisms. Accordingly, the time derivative of the Helmholtz specific free energy function can be written as

$$\dot{\psi} = \dot{\psi}^{ve}(\boldsymbol{\varepsilon}^e) + \dot{\psi}^{vp}(\boldsymbol{\varepsilon}, \bar{\varepsilon}^p)\,. \tag{6.10}$$

The visco-elastic potential is explicitly established as

$$\psi^{ve} = \frac{1}{2\rho_0}\int_0^t \int_0^t \frac{\partial \boldsymbol{\varepsilon}^e(t^*)}{\partial t^*} : \mathbf{D}^{ve}(2t - t^* - t^\star) : \frac{\partial \boldsymbol{\varepsilon}^e(t^\star)}{\partial t^\star}\,\mathrm{d}t^*\,\mathrm{d}t^\star\,, \tag{6.11}$$

where ρ_0 denotes the material reference density, which results from the finite strains extension of the potential proposed by Christensen and coworkers (Christensen and Lo, 1979) with the spatial logarithmic strain tensor, and by considering the history of the strain visco-elastic component solely, similar to Krairi and Doghri (Krairi and Doghri, 2014). The visco-elasticity isotropic fourth-order relaxation tensor is defined in terms of deviatoric and volumetric components as

$$\mathbf{D}^{ve}(t) = 2G(t)\mathbf{I}_d + K(t)\boldsymbol{I}\otimes\boldsymbol{I}\,, \tag{6.12}$$

[2]The visco-plastic potential could be alternatively decomposed into two parts, one purely dependent on the (visco-plastic) dissipative mechanisms incorporated through the accumulated plastic strain and the other associated with the plasticity-induced hardening.

where $G(t)$ and $K(t)$ denote the shear and bulk moduli visco-elastic relaxation functions, respectively, $\boldsymbol{I}$ denotes the second-order identity tensor, and $\mathbf{I}_d$ denotes the fourth-order deviatoric identity tensor. Following standard procedures in visco-elastic formulations (e.g., Krairi and Doghri (2014), Bergstrom (2015), Nguyen et al. (2016)), both moduli relaxation function is defined as a Prony series expansion as

$$G(t) = G_\infty + \sum_{i=1}^{n_\mathrm{V}} G_i \exp\left[-\frac{t}{g_i}\right], \tag{6.13}$$

and

$$K(t) = K_\infty + \sum_{i=1}^{n_\mathrm{V}} K_i \exp\left[-\frac{t}{k_i}\right], \tag{6.14}$$

where G_∞ and K_∞ denote the long-term elastic moduli, i.e., the effective elastic properties after the viscous mechanisms have fully developed ($t/g_i \to \infty$, $t/k_i \to \infty$), G_i and K_i denote the bulk and shear moduli associated with the i-th visco-elastic relaxation mode, and g_i and k_i denote the i-th mode visco-elastic relaxation times. It is clear that the previous Prony series are equivalent to the effective relaxation moduli of the generalized Maxwell model (Bergstrom, 2015) illustrated in Figure 6.2. Furthermore, by defining the spatial logarithmic equivalent strain rate as

$$\dot{\varepsilon}^{\mathrm{eq}} = \frac{1}{\Delta t}\sqrt{\frac{2}{3}\Delta\boldsymbol{\varepsilon} : \Delta\boldsymbol{\varepsilon}}, \tag{6.15}$$

the dependency of the visco-elastic relaxation times on the strain rate can be introduced following Yu and coworkers (Yu et al., 2014) as

$$g_i(\dot{\varepsilon}^{\mathrm{eq}}) = g_{T,i}\,(\dot{\varepsilon}^{\mathrm{eq}})^{-\lambda_{g,i}}, \qquad i = 1, \ldots, n_\mathrm{V}, \tag{6.16}$$

$$k_i(\dot{\varepsilon}^{\mathrm{eq}}) = k_{T,i}\,(\dot{\varepsilon}^{\mathrm{eq}})^{-\lambda_{k,i}}, \qquad i = 1, \ldots, n_\mathrm{V}, \tag{6.17}$$

where $g_{T,i}$ and $k_{T,i}$ are constants, and $\lambda_{g,i}$ and $\lambda_{k,i}$ denote the shear and bulk relaxation times strain rate sensitivity, respectively.

As demonstrated in G.1, the time derivative of the visco-elastic potential renders

$$\dot{\psi}^{ve} = \frac{1}{\rho_0}\left(\int_0^t \mathbf{D}^{ve}(t-t^*) : \frac{\partial\boldsymbol{\varepsilon}^e(t^*)}{\partial t^*}\,\mathrm{d}t^*\right) : \dot{\boldsymbol{\varepsilon}}^e + \frac{1}{2\rho_0}\int_0^t\int_0^t \frac{\partial\boldsymbol{\varepsilon}^e(t^*)}{\partial t^*} : \frac{\partial\mathbf{D}^{ve}(2t-t^*-t^\star)}{\partial t} : \frac{\partial\boldsymbol{\varepsilon}^e(t^\star)}{\partial t^\star}\,\mathrm{d}t^*\mathrm{d}t^\star. \tag{6.18}$$

Denoting the Boltzmann's integral (second-order tensor) as $\boldsymbol{A}$ for compactness, the elastic left Cauchy-Green strain tensor definition, $\boldsymbol{B}^e = \boldsymbol{F}^e(\boldsymbol{F}^e)^T$, and the identity $\dot{\boldsymbol{B}}^e = \boldsymbol{B}^e : \dot{\boldsymbol{B}}^e(\boldsymbol{B}^e)^{-1}$, it it possible to write

$$\boldsymbol{A} : \dot{\boldsymbol{\varepsilon}}^e = \frac{1}{2}\boldsymbol{A} : \frac{\partial\ln[\boldsymbol{B}^e]}{\partial\boldsymbol{B}^e} : \dot{\boldsymbol{B}}^e = \frac{1}{2}\left[\boldsymbol{A} : \frac{\partial\ln[\boldsymbol{B}^e]}{\partial\boldsymbol{B}^e}\right]\boldsymbol{B}^e : \dot{\boldsymbol{B}}^e(\boldsymbol{B}^e)^{-1}. \tag{6.19}$$

Given the isotropy of $\boldsymbol{A}$ (see Equation (6.12)) and the definition of $\boldsymbol{\varepsilon}$ (see Equation (6.7)), the tensors $\boldsymbol{\varepsilon}^e$, $\boldsymbol{B}^e$ and $\boldsymbol{A}$ share the same eigenprojection tensors. This observation, coupled with

the fact that the tensor logarithm is an isotropic tensor function, leads to the following identity (de Souza Neto et al., 2008),

$$\left[\boldsymbol{A}:\frac{\partial \ln[\boldsymbol{B}^e]}{\partial \boldsymbol{B}^e}\right]\boldsymbol{B}^e=\boldsymbol{A}. \tag{6.20}$$

In addition, noticing the kinematic identities $\boldsymbol{B}^e=\boldsymbol{F}(\boldsymbol{F}^p)^{-1}(\boldsymbol{F}^p)^{-T}\boldsymbol{F}^T$, $\boldsymbol{F}^p\dot{\overline{(\boldsymbol{F}^p)^{-1}}}=-\boldsymbol{L}^p$ and $-\dot{\overline{(\boldsymbol{F}^p)^{-T}}}(\boldsymbol{F}^p)^T=-(\boldsymbol{L}^p)^T$, the visco-elastic isotropy, and the definition of the spatially rotated rate of plastic deformation tensor (see Equation (6.6)), after some algebraic manipulations Equation (6.19) yields

$$\boldsymbol{A}:\dot{\boldsymbol{\varepsilon}}^e=\boldsymbol{A}:(\boldsymbol{D}-\tilde{\boldsymbol{D}}^p), \tag{6.21}$$

where $\boldsymbol{D}$ stands for the symmetric part of the velocity gradient, $\boldsymbol{D}=\mathrm{sym}[\boldsymbol{L}]$. For the sake of completeness, the time derivative of the visco-elastic potential can then be finally written as

$$\begin{aligned}\dot{\psi}^{ve}=\frac{1}{\rho_0}\left(\int_0^t \mathbf{D}^{ve}(t-t^*):\frac{\partial \boldsymbol{\varepsilon}^e(t^*)}{\partial t^*}\,\mathrm{d}t^*\right):(\boldsymbol{D}-\tilde{\boldsymbol{D}}^p)\\ +\frac{1}{2\rho_0}\int_0^t\int_0^t \frac{\partial \boldsymbol{\varepsilon}^e(t^*)}{\partial t^*}:\frac{\partial \mathbf{D}^{ve}(2t-t^*-t^\star)}{\partial t}:\frac{\partial \boldsymbol{\varepsilon}^e(t^\star)}{\partial t^\star}\,\mathrm{d}t^*\,\mathrm{d}t^\star.\end{aligned} \tag{6.22}$$

Despite not being explicitly defined, the time derivative of the visco-plastic potential can be written as

$$\dot{\psi}^{vp}=\frac{\partial \psi^{vp}}{\partial \boldsymbol{\varepsilon}}:\dot{\boldsymbol{\varepsilon}}+\frac{\partial \psi^{vp}}{\partial \bar{\varepsilon}^p}:\dot{\bar{\varepsilon}}^p. \tag{6.23}$$

Attending to the definition of $\boldsymbol{\varepsilon}$ (see Equation (6.7)), it is convenient to express the time derivative of the spatial logarithmic strain tensor as

$$\dot{\varepsilon}^e=\frac{1}{2}\frac{\partial \ln[\boldsymbol{B}]}{\partial \boldsymbol{B}}:\dot{\boldsymbol{B}}=\frac{1}{2}\frac{\partial \ln[\boldsymbol{B}]}{\partial \boldsymbol{B}}:\boldsymbol{\Gamma}:\boldsymbol{L}, \tag{6.24}$$

where the fourth-order operator $\boldsymbol{\Gamma}$ is defined as

$$\boldsymbol{\Gamma}_{ijkl}=\delta_{ik}\boldsymbol{B}_{jl}+\delta_{jk}\boldsymbol{B}_{il}. \tag{6.25}$$

Due to the symmetry of the second-order tensors $\boldsymbol{\varepsilon}$ and $\boldsymbol{B}$, and both major and minor symmetries of the fourth-order tensor $\partial \ln[\boldsymbol{B}]/\partial \boldsymbol{B}$, it can be easily shown that the second-order tensor resulting from

$$\frac{\partial \psi^{vp}}{\partial \boldsymbol{\varepsilon}}:\frac{\partial \ln[\boldsymbol{B}]}{\partial \boldsymbol{B}}:\boldsymbol{\Gamma}, \tag{6.26}$$

is also a symmetric tensor. Therefore, the anti-symmetric component of the velocity gradient, $\boldsymbol{W}=\mathrm{skew}[\boldsymbol{L}]$, can be conveniently dropped in Equation (6.24), and the time derivative of the visco-plastic potential is finally written as

$$\dot{\psi}^{vp}=\frac{\partial \psi^{vp}}{\partial \boldsymbol{\varepsilon}}:\frac{\partial \ln[\boldsymbol{B}]}{\partial \boldsymbol{B}}:\boldsymbol{\Gamma}:\boldsymbol{D}+\frac{\partial \psi^{vp}}{\partial \bar{\varepsilon}^p}:\dot{\bar{\varepsilon}}^p. \tag{6.27}$$

6.2.4 Stress constitutive laws and non-negative dissipation inequality

In the purely mechanical case, compatible with the isothermal assumption underlying the proposed constitutive model, the Clausius-Duhem inequality can be expressed in terms of dissipation per unit reference volume as

$$\boldsymbol{\tau}_{\mathrm{T}} : \boldsymbol{D} - \rho_0 \dot{\psi} \geq 0 \,, \tag{6.28}$$

where $\boldsymbol{\tau}_{\mathrm{T}}$ is the Kirchhoff stress tensor and $\boldsymbol{\tau}_{\mathrm{T}} : \boldsymbol{D}$ represents a stress power per unit reference volume. Insertion of the additive decomposition of the Kirchhoff stress tensor (see Equation (6.1)) and the time derivative of the specific free energy (see Equations (6.10), (6.22) and (6.27)), renders

$$\begin{aligned} \left(\boldsymbol{\tau}_{\mathrm{D}} - \int_0^t \mathbf{D}^{ve}(t-t^*) : \frac{\partial \boldsymbol{\varepsilon}^e(t^*)}{\partial t^*} \, \mathrm{d}t^* \right) : \boldsymbol{D} + \left(\boldsymbol{\tau}_{\mathrm{H}} - \frac{\partial \psi^{vp}}{\partial \boldsymbol{\varepsilon}} : \frac{\partial \ln[\boldsymbol{B}]}{\partial \boldsymbol{B}} : \boldsymbol{\Gamma} \right) : \boldsymbol{D} \\ - \frac{1}{2} \int_0^t \int_0^t \frac{\partial \boldsymbol{\varepsilon}^e(t^*)}{\partial t^*} : \frac{\partial \mathbf{D}^{ve}(2t - t^* - t^\star)}{\partial t} : \frac{\partial \boldsymbol{\varepsilon}^e(t^\star)}{\partial t^\star} \, \mathrm{d}t^* \, \mathrm{d}t^\star \\ + \int_0^t \mathbf{D}^{ve}(t-t^*) : \frac{\partial \boldsymbol{\varepsilon}^e(t^*)}{\partial t^*} \, \mathrm{d}t^* : \tilde{\boldsymbol{D}}^p - \frac{\partial \psi^{vp}}{\partial \bar{\varepsilon}^p} : \dot{\bar{\varepsilon}}^p \geq 0 \,. \end{aligned} \tag{6.29}$$

Given that the Clausius-Duhem inequality must hold for any thermokinetic process, the previous inequation yields two fundamental consequences: (i) the Kirchhoff stress constitutive laws for both driving and hardening components and (ii) the non-negative intrinsic dissipation requirement.

The driving Kirchhoff stress tensor constitutive law comes

$$\boldsymbol{\tau}_{\mathrm{D}} = \int_0^t \mathbf{D}^{ve}(t-t^*) : \frac{\partial \boldsymbol{\varepsilon}^e(t^*)}{\partial t^*} \, \mathrm{d}t^* \,, \tag{6.30}$$

where the visco-elasticity fourth-order relaxation tensor is defined by Equation (6.12). However, assuming that the visco-elastic stress is mainly attributed to mechanisms involving the distortional component of the visco-elastic strain (e.g., Wriggers (2008), Khaleghi et al. (2022)), it is here assumed that $k_i \to 0$, $i = 1, \ldots, n_{\mathrm{V}}$, such that the driving Kirchhoff stress tensor depends on the volumetric strain only through the (instantaneous) linear spring ($K(t) = K_\infty$).

Remark.
In the particular case of a (non-viscous) elastic behavior ($t/g_i \to \infty$, $t/k_i \to \infty$), the driving Kirchhoff stress recovers the well-known Hencky hyperelastic constitutive model,

$$\boldsymbol{\tau}_{\mathrm{D}} = \mathbf{D}^e_\infty : \boldsymbol{\varepsilon}^e, \quad \mathbf{D}^e_\infty = 2G_\infty \mathbf{I}_d + K_\infty \boldsymbol{I} \otimes \boldsymbol{I} \,, \tag{6.31}$$

rendering a linear relationship between the Kirchhoff stress and the spatial logarithmic strain functionally similar to the infinitesimal strain case.

The hardening Kirchhoff stress tensor constitutive law is proposed as

$$\boldsymbol{\tau}_{\mathrm{H}} = \frac{\partial \psi^{vp}}{\partial \boldsymbol{\varepsilon}} : \frac{\partial \ln[\boldsymbol{B}]}{\partial \boldsymbol{B}} : \boldsymbol{\Gamma} = H \bar{\boldsymbol{\varepsilon}}^p \boldsymbol{\varepsilon}_d \,, \tag{6.32}$$

where $\boldsymbol{\varepsilon}_d$ denotes the deviatoric spatial logarithmic strain tensor and H is a material constant named hardening modulus. From a physical point of view, the proposed constitutive law

assumes local hardening mechanisms associated with the material distortional strains whose magnitude scales with the (nonlinear) accumulated plastic strain.

Having identified the Kirchhoff stress constitutive laws, the Clausius-Duhem inequality (see Equation (6.29)) can be written as

$$\Upsilon = \Upsilon^{ve} + \Upsilon^{vp} \geq 0\,, \tag{6.33}$$

where Υ denotes the total intrinsic dissipation per unit reference volume, Υ^{ve} denotes the visco-elastic intrinsic dissipation part,

$$\Upsilon^{ve} = -\frac{1}{2}\int_0^t \int_0^t \frac{\partial \boldsymbol{\varepsilon}^e(t^*)}{\partial t^*} : \frac{\partial \mathbf{D}^{ve}(2t - t^* - t^\star)}{\partial t} : \frac{\partial \boldsymbol{\varepsilon}^e(t^\star)}{\partial t^\star}\, \mathrm{d}t^* \mathrm{d}t^\star\,, \tag{6.34}$$

and Υ^{vp} denotes the visco-plastic intrinsic dissipation part,

$$\Upsilon^{vp} = \boldsymbol{\tau}_{\mathrm{D}} : \tilde{\boldsymbol{D}}^p - \frac{\partial \psi^{vp}}{\partial \bar{\varepsilon}^p} : \dot{\bar{\varepsilon}}^p\,. \tag{6.35}$$

The previous requirement embodies the so-called non-negative dissipation inequality that, based on the principle of thermodynamic determinism, must be satisfied for any thermokinetic process. While the intrinsic dissipation associated with the visco-elastic component is thoroughly discussed by Christensen and coworkers (Christensen and Lo, 1979), the visco-plastic intrinsic dissipation places restrictions on the constitutive laws that are postulated to govern the evolution of the model's internal variables, namely the visco-plastic flow rule and the accumulated plastic strain constitutive law discussed in the following section.

6.2.5 The visco-plastic constitutive formulation

Similar to the finite strain elasto-visco-plastic constitutive model proposed by Mirkhalaf and coworkers (Mirkhalaf et al., 2016), the (rate-dependent) visco-plastic constitutive law is established through the spatially rotated rate of plastic deformation as

$$\tilde{\boldsymbol{D}}^p = \dot{\gamma}\boldsymbol{N}\,, \tag{6.36}$$

where $\dot{\gamma}$ denotes the visco-plastic multiplier and $\boldsymbol{N}$ the visco-plastic flow vector, complemented by postulating a zero plastic spin tensor, $\boldsymbol{W}^p = \mathbf{0}$, compatible with visco-plastic isotropy. It is remarked that despite the functional format of Equation (6.36), and in contrast with standard rate-independent plasticity models, the model formulated here does not assume the existence of an elastic domain bounded by a yield surface, i.e., the local strain is always assumed as the result of both visco-elastic and visco-plastic contributions.

Mirkhalaf and coworkers (Mirkhalaf et al., 2016) postulate the existence of a visco-plastic flow potential defined as

$$\Psi^{vp}(\boldsymbol{\tau}_{\mathrm{D},d}) = \sqrt{\frac{1}{2}\boldsymbol{\tau}_{\mathrm{D},d} : \boldsymbol{\tau}_{\mathrm{D},d}}\,, \tag{6.37}$$

being the visco-plastic flow vector derived as

$$\boldsymbol{N} = \frac{\partial \Psi^{vp}(\boldsymbol{\tau}_{\mathrm{D},d})}{\partial \boldsymbol{\tau}_{\mathrm{D}}} = \frac{\partial \Psi^{vp}(\boldsymbol{\tau}_{\mathrm{D},d})}{\partial \boldsymbol{\tau}_{\mathrm{D},d}} : \frac{\partial \boldsymbol{\tau}_{\mathrm{D},d}}{\partial \boldsymbol{\tau}_{\mathrm{D}}} = \sqrt{\frac{1}{2}}\frac{\partial \left\|\boldsymbol{\tau}_{\mathrm{D},d}\right\|}{\partial \boldsymbol{\tau}_{\mathrm{D},d}} : \mathbf{I}_d = \sqrt{\frac{1}{2}}\frac{\boldsymbol{\tau}_{\mathrm{D},d}}{\left\|\boldsymbol{\tau}_{\mathrm{D},d}\right\|}\,, \tag{6.38}$$

where $\boldsymbol{\tau}_{\mathrm{D},d}$ is the deviatoric Kirchhoff stress tensor and $\|\cdot\|$ denotes the Frobenius norm. It transpires from the previous result that the adopted visco-plastic flow rule is purely deviatoric, similar to the standard J_2 plastic flow.

The formulation of the visco-plastic multiplier function is slightly more involving and, similar to Tvervoort (Tervoort, 1996), it is postulated by the Eyring visco-plastic flow model as

$$\dot{\gamma} = \frac{1}{A} \sinh \left[\frac{\tau_{\mathrm{D}}^{\mathrm{eq}}}{\tau^*} \right], \tag{6.39}$$

where A is an Eyring-related function, τ^* is a material constant, and $\tau_{\mathrm{D}}^{\mathrm{eq}}$ is a Kirchhoff equivalent stress defined as[3]

$$\tau_{\mathrm{D}}^{\mathrm{eq}} = \sqrt{\frac{1}{2} \boldsymbol{\tau}_{\mathrm{D},d} : \boldsymbol{\tau}_{\mathrm{D},d}} = \sqrt{\frac{1}{2}} \left\| \boldsymbol{\tau}_{\mathrm{D},d} \right\|. \tag{6.40}$$

The material constant τ^* is taken as the characteristic stress given by

$$\tau^* = \frac{R^* T}{v^*}, \tag{6.41}$$

where R^* is the universal gas constant ($R^* = 8.3144598(48)\,\mathrm{kg\,m^2 mol^{-1} K^{-1} s^{-2}}$), T is the absolute temperature and v^* is the shear activation volume. In turn, the Eyring-related function A is given by (Timmermans (1997), Govaert et al. (2000))

$$A = A_0 \exp \left(\underbrace{\frac{\Delta H}{R^* T}}_{A_1} + \underbrace{\frac{\mu P}{\tau^*}}_{A_2} \underbrace{- D}_{A_3} \right), \tag{6.42}$$

A_0 is a factor associated with the fundamental vibration temperature. The first term, A_1, adopted by Tvervoort (Tervoort, 1996), stems from the well-known Eyring equation, where ΔH denotes the activation energy (or enthalpy of activation). The second term, A_2, accounts for the pressure dependency, where μ is a pressure coefficient[4] and P denotes the total hydrostatic pressure defined as

$$P = p^* + p_{\mathrm{D}} = p^* - \frac{1}{3} \mathrm{tr}\left[\boldsymbol{\tau}_{\mathrm{D}} \right], \tag{6.43}$$

where p^* is the superimposed hydrostatic pressure (e.g., the atmospheric pressure) and p_{D} is the driving Kirchhoff hydrostatic pressure[5]. Last but not least, the third term A_3 introduces the softening phenomenon characteristic of the post-yield behavior of thermoplastics (see stage C of Figure 6.1), with D denoting a softening (internal) variable. The phenomenological law proposed by Hasan and coworkers (Hasan et al., 1993) is adopted here,

$$\dot{D} = h \left(1 - \frac{D}{D_\infty} \right) \sqrt{\tilde{\boldsymbol{D}}^p : \tilde{\boldsymbol{D}}^p}, \quad D(t=0) = 0, \tag{6.44}$$

[3] The Kirchhoff equivalent stress is defined according to a state of pure shear stress.

[4] The pressure coefficient μ is defined as the ratio between volumetric and shear activation volumes. Note that the pressure dependency introduced through the visco-plastic multiplier complements the purely deviatoric nature of the visco-plastic constitutive law (see Equation (6.38)).

[5] Note that the hardening Kirchhoff stress tensor is purely deviatoric (see Equation (6.32)) and does not contribute to the total hydrostatic pressure.

where h and D_∞ are material constants associated with the softening slope and the softening saturation value, respectively. In view of Equation (6.36), and defining the constitutive law for the accumulated plastic strain (taken as an internal variable) as[6]

$$\dot{\bar{\varepsilon}}^p = \sqrt{\frac{2}{3}\tilde{\boldsymbol{D}}^p : \tilde{\boldsymbol{D}}^p} = \sqrt{\frac{1}{3}}\,\dot{\gamma}\,, \tag{6.45}$$

Equation (6.44) can be written as

$$\sqrt{\frac{2}{3}}\frac{h\dot{\bar{\varepsilon}}^p}{D_\infty} = \frac{1}{D_\infty - D}\,\dot{D}\,. \tag{6.46}$$

The straightforward time integration of the previous equation yields

$$\sqrt{\frac{2}{3}}\frac{h\bar{\varepsilon}^p}{D_\infty}\Big|_0^t = -\ln[D - D_\infty]\Big|_0^t, \tag{6.47}$$

which attending to the initial conditions, $D(t=0) = 0$ and $\bar{\varepsilon}^p(t=0) = 0$, and after simple algebraic manipulations provides

$$D = D_\infty\left(1 - \exp\left[-\sqrt{\frac{3}{2}}\frac{h\bar{\varepsilon}^p}{D_\infty}\right]\right). \tag{6.48}$$

At last, the substitution of the previous result in Equation (6.42) sets the complete expression for the Eyring-related function as

$$A = A(\boldsymbol{\tau}_{\mathrm{D}}, \bar{\varepsilon}^p) = A_0 \exp\left[\frac{\Delta H}{R^* T} + \frac{\mu P}{\tau^*} - D_\infty\left(1 - \exp\left[-\sqrt{\frac{3}{2}}\frac{h\bar{\varepsilon}^p}{D_\infty}\right]\right)\right]. \tag{6.49}$$

Remark.
Attending to the definition of the plastic velocity gradient (see Equation (6.5)*), the definition of the spatially rotated rate of plastic deformation (see Equation* (6.6)*), the assumption of visco-plastic isotropy ($\boldsymbol{W}^p = \boldsymbol{0}$), and the orthogonality of the elastic rotation tensor, it follows that*

$$\boldsymbol{L}^p = \dot{\boldsymbol{F}}^p(\boldsymbol{F}^p)^{-1} = \boldsymbol{D}^p = (\boldsymbol{R}^e)^T\tilde{\boldsymbol{D}}^p\boldsymbol{R}^e\,. \tag{6.50}$$

Insertion of the visco-plastic flow rule defined in Equation (6.36) *yields*

$$\dot{\boldsymbol{F}}^p(\boldsymbol{F}^p)^{-1} = \dot{\gamma}(\boldsymbol{R}^e)^T\frac{\partial\Psi^{vp}}{\partial\boldsymbol{\tau}}\boldsymbol{R}^e\,, \tag{6.51}$$

which clearly emphasizes the constitutive evolution of the visco-plastic deformation gradient.

Remark.
By recognizing the identity $\|\boldsymbol{\tau}_{\mathrm{D},d}\| = \sqrt{2}\,\tau_{\mathrm{D}}^{\mathrm{eq}}$, the visco-plastic flow rule (see Equation (6.36)*) can be alternatively written as*

[6] The definition of the constitutive law for the accumulated plastic strain follows the one adopted in the standard von Mises elasto-plastic constitutive model. Attending to Equation (6.38), the alternative definition $\dot{\bar{\varepsilon}}^p = \sqrt{2\tilde{\boldsymbol{D}}^p : \tilde{\boldsymbol{D}}^p}$ would result in $\dot{\bar{\varepsilon}}^p = \dot{\gamma}$ instead.

$$\tilde{\boldsymbol{D}}^p = \frac{\boldsymbol{\tau}_{\mathrm{D},d}}{2\,\eta(\boldsymbol{\tau}_{\mathrm{D}}, \bar{\varepsilon}^p)}\,, \tag{6.52}$$

where η denotes the visco-plastic viscosity function defined as

$$\eta = \eta(\boldsymbol{\tau}_{\mathrm{D}}, \bar{\varepsilon}^p) = A(\boldsymbol{\tau}_{\mathrm{D}}, \bar{\varepsilon}^p)\, \tau_{\mathrm{D}}^{\mathrm{eq}} \left(\sinh\left(\frac{\tau^{\mathrm{eq}}}{\tau^*} \right) \right)^{-1}\,, \tag{6.53}$$

with the Eyring-related function established in Equation (6.49)*. This particular form of the visco-plastic flow rule corresponds to the multidimensional extension of the one-dimensional flow model characterized by the Eyring equation. Moreover, it is later shown in Section 6.3 that the visco-elastic-visco-plastic constitutive problem can be reduced to a single scalar nonlinear residual function based on the visco-plastic viscosity function.*

6.2.6 Summary

For the sake of clarity, the formulation of the finite strain visco-elastic-visco-plastic constitutive initial value problem can be summarized as follows: Given the initial values $\boldsymbol{F}^p(t_0)$ and $\bar{\varepsilon}^p(t_0)$ and given the history of the deformation gradient $\boldsymbol{F}(t)$, $t \in [t_0, t_f]$, find the functions $\boldsymbol{F}^p(t)$ and $\bar{\varepsilon}^p(t)$ that satisfy

$$\dot{\boldsymbol{F}}^p(t)(\boldsymbol{F}^p(t))^{-1} = \dot{\gamma}(t)(\boldsymbol{R}^e(t))^T\, \boldsymbol{N}(t)\, \boldsymbol{R}^e(t)\,, \tag{6.54}$$

$$\dot{\bar{\varepsilon}}^p(t) = \sqrt{\frac{1}{3}}\, \dot{\gamma}(t)\,, \tag{6.55}$$

with

$$\dot{\gamma}(t) = \frac{1}{A(t)} \sinh\left(\frac{\tau_{\mathrm{D}}^{\mathrm{eq}}(t)}{\tau^*} \right), \tag{6.56}$$

$$\tau_{\mathrm{D}}^{\mathrm{eq}}(t) = \sqrt{\frac{1}{2}\boldsymbol{\tau}_{\mathrm{D},d}(t) : \boldsymbol{\tau}_{\mathrm{D},d}(t)}\,, \tag{6.57}$$

$$A(t) = A_0 \exp\left[\frac{\Delta H}{R^* T} + \frac{\mu P(t)}{\tau^*} - D_\infty \left(1 - \exp\left[-\sqrt{\frac{3}{2}} \frac{h\bar{\varepsilon}^p(t)}{D_\infty} \right] \right) \right], \tag{6.58}$$

$$\boldsymbol{N}(t) = \sqrt{\frac{1}{2}}\, \frac{\boldsymbol{\tau}_{\mathrm{D},d}(t)}{\left\| \boldsymbol{\tau}_{\mathrm{D},d} \right\|(t)}\,, \tag{6.59}$$

for each instant $t \in [t_0, t_f]$, with

$$\boldsymbol{\tau}_{\mathrm{T}}(t) = \boldsymbol{\tau}_{\mathrm{D}}(t) + \boldsymbol{\tau}_{\mathrm{H}}(t)\,, \tag{6.60}$$

$$\boldsymbol{\tau}_{\mathrm{D}}(t) = \int_0^t \mathbf{D}^{ve}(t - t^*) : \frac{\partial \boldsymbol{\varepsilon}^e(t^*)}{\partial t^*}\, \mathrm{d}t^*\,, \tag{6.61}$$

$$\boldsymbol{\tau}_{\mathrm{H}}(t) = H\bar{\boldsymbol{\varepsilon}}^p(t)\, \boldsymbol{\varepsilon}_d(t)\,, \tag{6.62}$$

and the kinematic relations

$$\boldsymbol{\varepsilon}^e(t) = \frac{1}{2}\ln\left[\boldsymbol{F}^e(t)(\boldsymbol{F}^e(t))^T\right], \tag{6.63}$$

$$\boldsymbol{R}^e(t) = \boldsymbol{F}^e(t)[(\boldsymbol{F}^e(t))^T\boldsymbol{F}^e(t)]^{-1/2}, \tag{6.64}$$

$$\boldsymbol{F}^e(t) = \boldsymbol{F}(t)\left[\boldsymbol{F}^p(t)\right]^{-1}. \tag{6.65}$$

The constitutive model material properties are conveniently summarized in Box 6.1 and their physical influence on the numerically predicted intrinsic compressive material response is depicted in H. A suitable two-stage optimization-based calibration procedure is later detailed in Section 6.4, from which the material properties can be identified from a given set of uniaxial compression tests.

Table 6.1: Material properties of the finite strain visco-elastic-visco-plastic constitutive model.

Category	**Notation**	**Designation**
Elastic[(a)]	K_∞	Long-term elastic bulk modulus
	G_∞	Long-term elastic shear modulus
Visco-elastic[(b)]	G_i	Shear modulus of i-th visco-elastic relaxation mode
	g_i	Shear relaxation time of i-th visco-elastic relaxation mode
Yielding	ΔH	Activation energy (or enthalpy of activation)
	A_0	Fundamental vibration temperature factor
	v^*	Shear activation volume
	μ	Pressure coefficient (activation volume ratio)
Post-yielding	h	Softening slope
	D_∞	Softening saturation
	H	Hardening modulus

[(a)] Given the elastic isotropy assumption, any other pair of elastic properties can be provided (e.g., the long-term Young's modulus and Poisson's ratio, E_∞ and ν_∞, respectively).

[(b)] For a given number of visco-elastic relaxation modes, n_V, the associated properties are complemented by $i = 1,\ldots,n_V$. Due to the adopted dependency on the strain rate, the shear relaxation time, g_i, is actually defined by the two parameters $g_{T,i}$ and $\lambda_{g,i}$.

6.3 Computational implementation

6.3.1 Computational framework

The computational implementation described in this section is mainly focused on the fully implicit solution of a mechanical initial boundary value equilibrium problem formulated by means of the Finite Element Method and solved by means of the Newton-Raphson Method after being properly linearized (see Section 2.9). In this context, the numerical implementation of a given constitutive model involves essentially two main procedures: (1) the constitutive

state update, required to compute the elemental internal forces; and (2) the computation of the consistent tangent modulus, required to compute the elemental stiffness matrices. All the necessary ingredients to implement both procedures are detailed in what follows.

6.3.2 Numerical integration scheme

In order to perform a suitable computational implementation of the path-dependent constitutive model described in Section 6.2, it is essential to adopt an appropriate numerical integration scheme of the constitutive equations over time. In this context, let us start by discretizing the time domain, $t \in [t_0, t_f]$, in a given number of increments, n_{inc}, and consider the general time increment $[t_n, t_{n+1}]$, $n = 0, \dots, n_{\text{inc}} - 1$, with $\Delta t = t_{n+1} - t_n$, in the following derivations. In line with the thermodynamical formulation based on internal variables, an algorithm based on approximated incremental constitutive functions is adopted here. Denoting the set of constitutive internal variables by $\boldsymbol{\alpha} = \{\boldsymbol{\varepsilon}^p, \bar{\varepsilon}^p\}$ and assuming that $\boldsymbol{\alpha}_n = \boldsymbol{\alpha}(t_n)$ is known, both the Kirchhoff stress tensor and the set of internal variables must be uniquely determined at t_{n+1} by the prescribed deformation gradient $\boldsymbol{F}_{n+1} = \boldsymbol{F}(t_{n+1})$ as

$$\boldsymbol{\tau}_{\text{T},n+1} = \hat{\boldsymbol{\tau}}(\boldsymbol{F}_{n+1}, \boldsymbol{\alpha}_n), \qquad \boldsymbol{\alpha}_{n+1} = \hat{\boldsymbol{\tau}}(\boldsymbol{F}_{n+1}, \boldsymbol{\alpha}_n), \tag{6.66}$$

where $\hat{\boldsymbol{\tau}}$ and $\hat{\boldsymbol{\alpha}}$ denote the incremental constitutive functions. In the remainder of this section, the notation $a_{n+1} = a(t_{n+1})$ is adopted, where a is a general time-dependent function.

Kirchhoff stress constitutive law

Recalling the definition of the visco-elasticity fourth-order relaxation tensor (see Equation (6.12)) and adopting the approach presented by Kaliske (Kaliske, 2000), the driving Kirchhoff stress tensor constitutive law (see Equation (6.61)) time integral can be numerically approximated as[7]

$$\boldsymbol{\tau}_{\text{D},n+1} = \boldsymbol{\tau}_{\text{D},\infty,n+1} + \sum_{i=1}^{n_{\text{V}}} \boldsymbol{\tau}_{\text{D},i,n+1}, \tag{6.67}$$

where $\boldsymbol{\tau}_{\text{D},\infty,n+1}$ is the stress in the (instantaneous) linear spring,

$$\boldsymbol{\tau}_{\text{D},\infty,n+1} = \boldsymbol{\tau}_{\text{D},\infty,n} + \mathbf{D}^e_\infty : (\boldsymbol{\varepsilon}^e_{n+1} - \boldsymbol{\varepsilon}^e_n), \tag{6.68}$$

with

$$\mathbf{D}^e_\infty = 2G_\infty \mathbf{I}_d + K_\infty \boldsymbol{I} \otimes \boldsymbol{I}, \tag{6.69}$$

and $\boldsymbol{\tau}_{\text{D},i,n+1}$ is the stress in the i-th visco-elastic Maxwell element,

$$\boldsymbol{\tau}_{\text{D},i,n+1} = \hat{\omega}_{i,n+1} \boldsymbol{\tau}_{\text{D},i,n} + \breve{\omega}_{i,n+1} \mathbf{D}^e_i : (\boldsymbol{\varepsilon}^e_{n+1} - \boldsymbol{\varepsilon}^e_n), \tag{6.70}$$

with

$$\mathbf{D}^e_i = 2G_i \mathbf{I}_d, \tag{6.71}$$

and

$$\hat{\omega}_{i,n+1} = \exp\left[-\frac{\Delta t}{g_{i,n+1}}\right], \qquad \breve{\omega}_{i,n+1} = \left(\frac{\Delta t}{g_{i,n+1}}\right)^{-1} \left[1 - \exp\left[-\frac{\Delta t}{g_{i,n+1}}\right]\right], \tag{6.72}$$

[7] In the context of visco-elastic constitutive models, another commonly adopted numerical integration scheme relies on a standard mid-point rule (e.g., Simo (1987), Gudimetla and Doghri (2017)).

with $g_{i,n+1} = g_i(\dot{\varepsilon}^{\text{eq}}_{n+1})$.

Note that the incremental hardening Kirchhoff stress tensor (see Equation (6.62)) can be established as

$$\boldsymbol{\tau}_{\text{H},n+1} = H\bar{\boldsymbol{\varepsilon}}^{p}_{n+1}\boldsymbol{\varepsilon}_{d,n+1}\,, \tag{6.73}$$

and the total Kirchhoff stress tensor comes

$$\boldsymbol{\tau}_{\text{T},n+1} = \boldsymbol{\tau}_{\text{D},n+1} + \boldsymbol{\tau}_{\text{H},n+1}\,, \tag{6.74}$$

Visco-plastic constitutive law

The structure of the visco-plastic constitutive law defined by Equation (6.54) makes it optimal to be integrated by the so-called exponential map integrators (de Souza Neto et al., 2008). By adopting an implicit exponential map integrator, the incremental visco-plastic flow rule is obtained as

$$\boldsymbol{F}^{p}_{n+1} = \exp\left[\Delta\gamma_{n+1}\,(\boldsymbol{R}^{e}_{n+1})^{T}\boldsymbol{N}_{n+1}\,\boldsymbol{R}^{e}_{n+1}\right]\boldsymbol{F}^{p}_{n}\,, \tag{6.75}$$

where

$$\Delta\gamma_{n+1} = \frac{1}{A_{n+1}}\sinh\left(\frac{\tau^{\text{eq}}_{n+1}}{\tau^{*}}\right)\Delta t\,, \tag{6.76}$$

with $\boldsymbol{N}_{n+1}$, A_{n+1} and τ^{eq}_{n+1} evaluated from Equations (6.59), (6.58) and (6.57), respectively.

Recalling the elasto-plastic multiplicative decomposition of the deformation gradient (see Equation (6.2)) and attending to the definition of the incremental deformation gradient,

$$\boldsymbol{F}_{\Delta} = \boldsymbol{F}_{n+1}(\boldsymbol{F}_{n})^{-1}\,, \tag{6.77}$$

Equation (6.75) can be rewritten as

$$\boldsymbol{F}^{e}_{n+1} = \boldsymbol{F}_{\Delta}\boldsymbol{F}_{n}\left(\exp\left[\Delta\gamma_{n+1}\,(\boldsymbol{R}^{e}_{n+1})^{T}\boldsymbol{N}_{n+1}\boldsymbol{R}^{e}_{n+1}\right]\boldsymbol{F}^{p}_{n}\right)^{-1}. \tag{6.78}$$

In addition, by making use of the following properties of the tensor exponential,

$$\exp\left[-\boldsymbol{X}\right] = \left(\exp\left[\boldsymbol{X}\right]\right)^{-1}, \qquad \exp\left[\boldsymbol{Q}\boldsymbol{X}\boldsymbol{Q}^{T}\right] = \boldsymbol{Q}\exp\left[\boldsymbol{X}\right]\boldsymbol{Q}^{T}\,, \tag{6.79}$$

where $\boldsymbol{Q}$ denotes a general orthogonal tensor, Equation (6.75) can be further manipulated as

$$\boldsymbol{F}^{e}_{n+1} = \boldsymbol{F}_{\Delta}\boldsymbol{F}^{e}_{n}(\boldsymbol{R}^{e}_{n+1})^{T}\exp\left[-\Delta\gamma_{n+1}\,\boldsymbol{N}_{n+1}\right]\boldsymbol{R}^{e}_{n+1}\,. \tag{6.80}$$

Remark.
The result obtained in Equation (6.80) *is equivalent to the incremental visco-plastic flow rule established in Equation* (6.75) *but has the elastic deformation gradient as the primary unknown kinematic variable. The advantage of such a functional format becomes evident in the context of the elasto-plastic operator split algorithm discussed in the following section.*

Accumulated plastic strain constitutive law

The accumulated plastic strain constitutive law (see Equation (6.55)) can be numerically integrated by means of the conventional implicit Euler scheme as

$$\bar{\varepsilon}^p_{n+1} = \bar{\varepsilon}^p_n + \sqrt{\frac{1}{3}}\,\Delta\gamma_{n+1}\,. \tag{6.81}$$

6.3.3 Fully implicit elastic predictor/return mapping algorithm

Operator split or two-step algorithms are widely used to find the solution of the constitutive problem in the context of elasto-plasticity and elasto-visco-plasticity (Crisfield (1991), Simo and Hughes (1998)). The first step of the algorithm consists in assuming that the incremental strain is purely elastic, commonly designated by the elastic trial state, after which the second step involves the solution of the so-called return mapping system of algebraic equations, a designation which stems from the return operation to the plastic yield surface. Although the previously formulated constitutive model does not account for an explicit yield function, a fully implicit elastic predictor/return mapping algorithm is still adopted[8] consistently with the implicit time discretization described in the previous section.

By defining the visco-elastic trial deformation gradient as

$$\boldsymbol{F}^{e,\text{trial}}_{n+1} = \boldsymbol{F}_\Delta \boldsymbol{F}^e_n\,, \tag{6.82}$$

and post multiplying both sides of Equation (6.80) by $(\boldsymbol{R}^e_{n+1})^{-1}$ yields, after simple algebraic manipulations[9],

$$\boldsymbol{V}^e_{n+1} = \boldsymbol{V}^{e,\text{trial}}_{n+1} \exp\left[-\Delta\gamma\,\boldsymbol{N}_{n+1}\right], \tag{6.83}$$

where $\boldsymbol{V}^e_{n+1} = [\boldsymbol{F}^e_{n+1}(\boldsymbol{F}^e_{n+1})^T]^{1/2}$ and $\boldsymbol{V}^{e,\text{trial}}_{n+1} = [\boldsymbol{F}^{e,\text{trial}}_{n+1}(\boldsymbol{F}^{e,\text{trial}}_{n+1})^T]^{1/2}$. Applying logarithms to both sides of the previous result finally leads to

$$\boldsymbol{\varepsilon}^e_{n+1} = \boldsymbol{\varepsilon}^{e,\text{trial}}_{n+1} - \Delta\gamma\,\boldsymbol{N}_{n+1}\,, \tag{6.84}$$

where

$$\varepsilon^{e,\text{trial}}_{n+1} = \frac{1}{2}\ln\left[\boldsymbol{B}^{e,\text{trial}}_{n+1}\right], \quad \boldsymbol{B}^{e,\text{trial}}_{n+1} = \boldsymbol{F}^{e,\text{trial}}_{n+1}\left(\boldsymbol{F}^{e,\text{trial}}_{n+1}\right)^T = \boldsymbol{F}_\Delta \boldsymbol{B}^e_n \boldsymbol{F}^T_\Delta\,. \tag{6.85}$$

It can thus be concluded that the incremental visco-plastic flow rule recovers the same functional format of the implicit elastic predictor/return mapping algorithms of infinitesimal strains elasto-plasticity[10]. This allows that both the constitutive state update and the computation of the consistent tangent modulus are performed in the infinitesimal strains functional format, being the required finite strain extension purely kinematical.

[8] Due to the absence of an explicit yield function, the incremental constitutive problem of the formulated model always involves the solution of the return mapping algorithm.

[9] Note that due to the assumed elasto-plastic isotropy, $\boldsymbol{V}^e_{n+1}$ and $\boldsymbol{N}_{n+1}$ commute.

[10] It is important to emphasize that such a result came from the adoption of the spatial logarithmic strain tensor as the elastic kinematic variable, the assumption of elasto-plastic isotropy, and the numerical integration of the visco-plastic constitutive law by means of an implicit exponential map.

Remark.
The general class of isotropic hyperelastic-based finite strain elasto-plastic constitutive models whose computational implementation fits on such finite strains' kinematic extension has been widely used by different authors (see Perić et al. (1992), De Souza Neto et al. (1994), Rouainia and Perić (1998)). Besides its simplicity, it preserves the most important properties of the infinitesimal strains formulation, namely volume-preserving plastic deformations and finite plastic incompressibility. The interested reader is referred to de Souza Neto and coworkers (de Souza Neto et al., 2008), where this class of constitutive models is thoroughly discussed.

6.3.4 State update

Following the definition of the visco-plastic viscosity function (see Equation (6.53)), the incremental visco-plastic multiplier (see Equation (6.76)) can be written as

$$\Delta\gamma_{n+1} = \frac{\tau^{\text{eq}}_{\text{D},n+1}}{\eta_{n+1}}\Delta t\,. \tag{6.86}$$

Moreover, by reusing the identity $\left\|\boldsymbol{\tau}_{\text{D}}\right\| = \sqrt{2}\tau^{\text{eq}}_{\text{D}}$, the visco-plastic flow vector (see Equation (6.38)) can be expressed as

$$\boldsymbol{N}_{n+1} = \frac{1}{2}\frac{\boldsymbol{\tau}_{\text{D,d},n+1}}{\tau^{\text{eq}}_{\text{D},n+1}}\,. \tag{6.87}$$

Given the additive elasto-plastic decomposition of the spatial logarithmic strain tensor (see Equation (6.8)),

$$\boldsymbol{\varepsilon}_{n+1} = \boldsymbol{\varepsilon}^{e}_{n+1} + \boldsymbol{\varepsilon}^{p}_{n+1}\,, \tag{6.88}$$

the definition of the visco-elastic trial spatial logarithmic strain tensor,

$$\varepsilon^{e,\text{trial}}_{n+1} = \boldsymbol{\varepsilon}_{n+1} - \boldsymbol{\varepsilon}^{p}_{n} = \boldsymbol{\varepsilon}^{e}_{n+1} + (\boldsymbol{\varepsilon}^{p}_{n+1} - \boldsymbol{\varepsilon}^{p}_{n})\,, \tag{6.89}$$

and the purely deviatoric nature of the visco-plastic flow rule ($\boldsymbol{\varepsilon}^{p} = \boldsymbol{\varepsilon}^{p}_{d}$), it stems from Equation (6.84) that

$$\boldsymbol{\varepsilon}^{p}_{d,n+1} = \boldsymbol{\varepsilon}^{p}_{d,n} + \Delta\gamma_{n+1}\boldsymbol{N}_{n+1}\,. \tag{6.90}$$

Substitution of Equations (6.86) and (6.87) yields the incremental (deviatoric) visco-plastic flow rule as

$$\boldsymbol{\varepsilon}^{p}_{d,n+1} = \boldsymbol{\varepsilon}^{p}_{d,n} + \frac{\boldsymbol{\tau}_{\text{D,d},n+1}}{2\eta_{n+1}}\Delta t\,. \tag{6.91}$$

Finally, the substitution of Equation (6.86) in Equation (6.81) renders the incremental accumulated plastic strain as

$$\bar{\varepsilon}^{p}_{n+1} = \bar{\varepsilon}^{p}_{n} + \sqrt{\frac{1}{3}}\frac{\tau^{\text{eq}}_{\text{D},n+1}}{\eta_{n+1}}\Delta t\,. \tag{6.92}$$

Therefore, assuming that the state variables $\{\boldsymbol{\varepsilon}^{e}_{n}, \boldsymbol{\varepsilon}^{p}_{n}, \bar{\varepsilon}^{p}_{n}\}$ are known at t_n, the constitutive state update involves the solution of the following return mapping system of algebraic equations,

$$\begin{cases} \boldsymbol{\varepsilon}_{n+1} = \boldsymbol{\varepsilon}^e_{n+1} + \boldsymbol{\varepsilon}^p_{n+1} \\ \boldsymbol{\varepsilon}^p_{d,n+1} = \boldsymbol{\varepsilon}^p_{d,n} + \dfrac{\boldsymbol{\tau}_{\mathrm{D,d},n+1}}{2\eta_{n+1}}\Delta t \\ \bar{\varepsilon}^p_{n+1} = \bar{\varepsilon}^p_n + \sqrt{\dfrac{1}{3}}\dfrac{\tau^{\mathrm{eq}}_{\mathrm{D},n+1}}{\eta_{n+1}}\Delta t \end{cases} \quad , \qquad \left\{\boldsymbol{\varepsilon}^e_{n+1}, \boldsymbol{\varepsilon}^p_{d,n+1}, \bar{\varepsilon}^p_{n+1}\right\}, \tag{6.93}$$

with initial conditions $\boldsymbol{\varepsilon}^p_{n+1} = \boldsymbol{\varepsilon}^p_{d,n+1} = \boldsymbol{\varepsilon}^p_n$ and $\bar{\varepsilon}^p_{n+1} = \bar{\varepsilon}^p_n$, and needs to be solved for the kinematic state variable $\boldsymbol{\varepsilon}^e_{n+1}$ and the internal state variables $\boldsymbol{\varepsilon}^p_{d,n+1}$ and $\bar{\varepsilon}^p_{n+1}$. In what follows it is demonstrated how such a system of equations can be explicitly expressed in terms of the (known) visco-elastic trial predictor state and reduced to the solution of a single scalar nonlinear equation.

Firstly, attending to Equations (6.67) and (6.91), and the identity

$$\boldsymbol{\varepsilon}_{d,n+1} - \boldsymbol{\varepsilon}_{d,n} = \boldsymbol{\varepsilon}^{e,\mathrm{trial}}_{d,n+1} - \boldsymbol{\varepsilon}^e_{d,n}, \tag{6.94}$$

it is possible to write the deviatoric driving Kirchhoff stress tensor as

$$\boldsymbol{\tau}_{\mathrm{D},d,n+1} = \frac{\eta_{n+1}}{\eta_{n+1} + \bar{G}_{n+1}\Delta t}\boldsymbol{\tau}^{\mathrm{trial}}_{\mathrm{D},d,n+1}, \tag{6.95}$$

where $\boldsymbol{\tau}^{\mathrm{trial}}_{\mathrm{D},d,n+1}$ denotes the deviatoric part of the trial predictor driving Kirchhoff stress tensor,

$$\boldsymbol{\tau}^{\mathrm{trial}}_{\mathrm{D},n+1} = \left[\boldsymbol{\tau}_{\mathrm{D},\infty,n} + \sum_{i=1}^{n_{\mathrm{V}}}\hat{\omega}_{i,n+1}\boldsymbol{\tau}_{\mathrm{D},i,n}\right] + \left[\mathbf{D}^e_\infty + \sum_{i=1}^{n_{\mathrm{V}}}\check{\omega}_{i,n+1}\mathbf{D}^e_i\right] : (\boldsymbol{\varepsilon}^{e,\mathrm{trial}}_{n+1} - \boldsymbol{\varepsilon}^e_n), \tag{6.96}$$

and $\bar{G}_{n+1}$ denotes the visco-elastic effective shear modulus,

$$\bar{G}_{n+1} = G_\infty + \sum_{i=1}^{n_{\mathrm{V}}}\check{\omega}_{i,n+1}G_i. \tag{6.97}$$

Secondly, recalling Equation (6.57), the Kirchhoff equivalent stress can be expressed as

$$\tau^{\mathrm{eq}}_{\mathrm{D},n+1} = \sqrt{\frac{1}{2}}\frac{\eta_{n+1}}{\eta_{n+1} + \bar{G}_{n+1}\Delta t}\left\|\boldsymbol{\tau}^{\mathrm{trial}}_{\mathrm{D},d,n+1}\right\|. \tag{6.98}$$

Lastly, due to the purely deviatoric nature of the visco-plastic flow rule, the driving Kirchhoff hydrostatic pressure is given by

$$p_{\mathrm{D}} = -\frac{1}{3}\mathrm{tr}\left[\boldsymbol{\tau}_{\mathrm{D}}\right] = -\frac{1}{3}\mathrm{tr}\left[\boldsymbol{\tau}^{\mathrm{trial}}_{\mathrm{D},n+1}\right]. \tag{6.99}$$

With the previous relations at hand, the return mapping system of algebraic equations (see Equation (6.93)) can then be explicitly written in terms of the visco-elastic trial state as

$$\begin{cases} \boldsymbol{\varepsilon}^e_{n+1} = \boldsymbol{\varepsilon}^{e,\mathrm{trial}}_{n+1} - \boldsymbol{\varepsilon}^p_{n+1} + \boldsymbol{\varepsilon}^p_n \\ \boldsymbol{\varepsilon}^p_{d,n+1} = \boldsymbol{\varepsilon}^p_{d,n} + \dfrac{\boldsymbol{\tau}^{\mathrm{trial}}_{\mathrm{D},d,n+1}}{2(\eta_{n+1} + \bar{G}_{n+1}\Delta t)}\Delta t \\ \bar{\varepsilon}^p_{n+1} = \bar{\varepsilon}^p_n + \dfrac{1}{3}\sqrt{\dfrac{3}{2}}\dfrac{\Delta t}{\eta_{n+1} + \bar{G}_{n+1}\Delta t}\left\|\boldsymbol{\tau}^{\mathrm{trial}}_{\mathrm{D},d,n+1}\right\| \end{cases} \quad , \quad \left\{\boldsymbol{\varepsilon}^e_{n+1}, \boldsymbol{\varepsilon}^p_{d,n+1}, \bar{\varepsilon}^p_{n+1}\right\}, \tag{6.100}$$

with initial conditions $\boldsymbol{\varepsilon}^p_{n+1} = \boldsymbol{\varepsilon}^p_{d,n+1} = \boldsymbol{\varepsilon}^p_n$ and $\bar{\varepsilon}^p_{n+1} = \bar{\varepsilon}^p_n$.

Given that the first return mapping equation can be solved *a posteriori* for the elastic spatial logarithmic strain tensor, and taking advantage of the explicit relations in terms of the visco-elastic trial state for $\tau^{\text{eq}}_{\text{D},n+1}$ and $\bar{\varepsilon}^p_{n+1}$, the return mapping system of algebraic equations can be reduced to a single scalar nonlinear equation where the only unknown is the visco-plastic viscosity (see Equation (6.53)) as

$$\eta_{n+1} = C_1 \frac{C_2}{C_3}, \tag{6.101}$$

where

$$C_1 = A_0 \exp\left[\frac{\Delta H}{R^* T} + \frac{\mu}{\tau^*}\left(p^* - \frac{1}{3}\operatorname{tr}\left[\boldsymbol{\tau}^{\text{trial}}_{\text{D},n+1}\right]\right) - D_\infty + D_\infty \exp\left[-\sqrt{\frac{3}{2}}\frac{hC_4}{D_\infty}\right]\right], \tag{6.102}$$

$$C_2 = \sqrt{\frac{1}{2}}\frac{\eta_{n+1}}{\eta_{n+1} + \bar{G}_{n+1}\Delta t}\left\|\boldsymbol{\tau}^{\text{trial}}_{\text{D},d,n+1}\right\|, \tag{6.103}$$

$$C_3 = \sinh\left(\frac{1}{\tau^*}\sqrt{\frac{1}{2}}\frac{\eta_{n+1}}{\eta_{n+1} + \bar{G}_{n+1}\Delta t}\left\|\boldsymbol{\tau}^{\text{trial}}_{\text{D},d,n+1}\right\|\right), \tag{6.104}$$

$$C_4 = \bar{\varepsilon}^p_n + \frac{1}{3}\sqrt{\frac{3}{2}}\frac{\Delta t}{\eta_{n+1} + \bar{G}_{n+1}\Delta t}\left\|\boldsymbol{\tau}^{\text{trial}}_{\text{D},d,n+1}\right\|. \tag{6.105}$$

By defining a suitable scalar nonlinear residual function as

$$R \equiv \eta_{n+1} - C_1 \frac{C_2}{C_3} = 0, \tag{6.106}$$

the solution can be determined by means of the Newton-Raphson Method iterative scheme as

$$\eta^{(k)}_{n+1} = \eta^{(k-1)}_{n+1} - \frac{R^{(k-1)}}{\left(\dfrac{\partial R}{\partial \eta_{n+1}}\right)^{(k-1)}}, \tag{6.107}$$

where k denotes the k-th iteration, being the closed-form of the residual derivative provided in G.2.1. Once the solution η_{n+1} is found, the state variables $\{\boldsymbol{\varepsilon}^e_{n+1}, \boldsymbol{\varepsilon}^p_{d,n+1}, \bar{\varepsilon}^p_{n+1}\}$ can be determined from Equation (6.100), and the Kirchhoff stress tensor from Equations (6.74), (6.67) and (6.73).

6.3.5 Consistent tangent modulus

The general finite strains spatial tangent modulus, **a**, arises from the linearization of the elemental internal forces as (de Souza Neto et al., 2008),

$$(\mathsf{a}_{ijkl})_{n+1} = \left(\frac{1}{\det[\boldsymbol{F}]}\frac{\partial \tau_{ij}}{\partial F_{km}}F_{lm} - \sigma_{il}\delta_{jk}\right)_{n+1}, \tag{6.108}$$

where $\boldsymbol{\sigma}_{\text{T},n+1}$ denotes the Cauchy stress tensor,

$$\boldsymbol{\sigma}_{\text{T},n+1} = \frac{1}{\det\left[\boldsymbol{F}_{n+1}\right]}\boldsymbol{\tau}_{\text{T},n+1}. \tag{6.109}$$

By applying the differentiation chain rule to the Kirchhoff stress tensor incremental constitutive function defined in the previous section,

$$\frac{\partial \hat{\boldsymbol{\tau}}}{\partial \boldsymbol{F}_{n+1}} = \frac{\partial \hat{\boldsymbol{\tau}}}{\partial \boldsymbol{\varepsilon}^{e,\mathrm{trial}}_{n+1}} : \frac{\partial \boldsymbol{\varepsilon}^{e,\mathrm{trial}}_{n+1}}{\partial \boldsymbol{B}^{e,\mathrm{trial}}_{n+1}} : \frac{\partial \boldsymbol{B}^{e,\mathrm{trial}}_{n+1}}{\partial \boldsymbol{F}_{n+1}}, \tag{6.110}$$

and after straightforward manipulations, the spatial tangent modulus consistent with the constitutive state update can be expressed as

$$(\mathsf{a}_{ijkl})_{n+1} = \frac{1}{2\det[\boldsymbol{F}_{n+1}]}\left([\mathbf{D}:\mathbf{L}:\mathbf{B}]_{ijkl}\right)_{n+1} - (\sigma_{\mathrm{T},il})_{n+1}\delta_{jk}, \tag{6.111}$$

where

$$\mathbf{D}_{n+1} = \frac{\partial \hat{\boldsymbol{\tau}}}{\partial \boldsymbol{\varepsilon}^{e,\mathrm{trial}}_{n+1}}, \tag{6.112}$$

has the same functional format as the consistent tangent modulus at infinitesimal strains,

$$\mathbf{L}_{n+1} = \frac{\partial \ln[\boldsymbol{B}^{e,\mathrm{trial}}_{n+1}]}{\partial \boldsymbol{B}^{e,\mathrm{trial}}_{n+1}}, \tag{6.113}$$

is the derivative of the tensor logarithm function at $\boldsymbol{B}^{e,\mathrm{trial}}_{n+1}$, and

$$\mathsf{B}_{ijkl} = \delta_{ik}(B^{e,\mathrm{trial}}_{jl})_{n+1} + \delta_{jk}(B^{e,\mathrm{trial}}_{il})_{n+1}, \tag{6.114}$$

is solely defined by the cartesian components of $\boldsymbol{B}^{e,\mathrm{trial}}_{n+1}$. Similar to the constitutive state update procedure, it is thus evident that there is a complete separation between finite strains kinematics ($\mathbf{L}_{n+1}$ and $\mathbf{B}_{n+1}$) and material-related operations ($\mathbf{D}_{n+1}$) in the computation of the consistent tangent modulus.

In this context, it remains to define $\mathbf{D}_{n+1}$ to complete the computation of the spatial consistent tangent modulus. After laborious differentiation operations (see G.2.2), the closed-form of the visco-elastic-visco-plastic consistent tangent modulus is obtained as

$$\mathbf{D}^{vevp}_{n+1} = \frac{\partial \hat{\boldsymbol{\tau}}}{\partial \boldsymbol{\varepsilon}^{e,\mathrm{trial}}_{n+1}} = \frac{\partial \hat{\boldsymbol{\tau}}}{\partial \boldsymbol{\varepsilon}_{n+1}} : \frac{\partial \boldsymbol{\varepsilon}_{n+1}}{\partial \boldsymbol{\varepsilon}^{e,\mathrm{trial}}_{n+1}} = \frac{\partial \hat{\boldsymbol{\tau}}}{\partial \boldsymbol{\varepsilon}_{n+1}} = \frac{\partial \boldsymbol{\tau}_{\mathrm{D},n+1}}{\partial \boldsymbol{\varepsilon}_{n+1}} + \frac{\partial \boldsymbol{\tau}_{\mathrm{H},n+1}}{\partial \boldsymbol{\varepsilon}_{n+1}}, \tag{6.115}$$

where

$$\begin{aligned}\frac{\partial \boldsymbol{\tau}_{\mathrm{D},n+1}}{\partial \boldsymbol{\varepsilon}_{n+1}} &= K_\infty \boldsymbol{I}\otimes\boldsymbol{I} + \frac{\Delta t}{(\eta_{n+1}+\bar{G}_{n+1}\Delta t)^2}\boldsymbol{\tau}^{\mathrm{trial}}_{\mathrm{D},d,n+1}\otimes\left[\bar{G}_{n+1}\frac{\partial \eta_{n+1}}{\partial \boldsymbol{\varepsilon}_{n+1}} - \eta_{n+1}\frac{\partial \bar{G}_{n+1}}{\partial \boldsymbol{\varepsilon}_{n+1}}\right] \\ &+ \frac{\eta_{n+1}}{\eta_{n+1}+\bar{G}_{n+1}\Delta t}\left[\sum_{i=1}^{n_{\mathrm{V}}}\left(\boldsymbol{\tau}_{\mathrm{D},i,n}\otimes\frac{\partial \hat{\omega}_{i,n+1}}{\partial \boldsymbol{\varepsilon}_{n+1}}\right) + 2(\boldsymbol{\varepsilon}_{d,n+1}-\boldsymbol{\varepsilon}_{d,n})\otimes\frac{\partial \bar{G}_{n+1}}{\partial \boldsymbol{\varepsilon}_{n+1}} + 2\bar{G}_{n+1}\mathbf{I}_d\right],\end{aligned} \tag{6.116}$$

and

$$\frac{\partial \boldsymbol{\tau}_{\mathrm{H},n+1}}{\partial \boldsymbol{\varepsilon}_{n+1}} = H\left[\boldsymbol{\varepsilon}_{d,n+1} \otimes \frac{\partial \bar{\varepsilon}^{p}_{n+1}}{\partial \boldsymbol{\varepsilon}_{n+1}} + \bar{\varepsilon}^{p}_{n+1}\mathbf{I}_{d}\right]. \tag{6.117}$$

For the sake of compactness, the required derivatives arising in Equations (6.116) and (6.117) are provided in G.2.2.

6.4 The two-stage optimization-based calibration procedure

6.4.1 Motivation

Even when the computational implementation of highly sophisticated constitutive models is available, the actual calibration procedure of the models' material properties often raise limitations in engineering applicability. Difficulties usually stem from different sources, among which (i) extensive sets of material properties that yield a large dimensionality of the optimization space, (ii) material properties whose physical meaning is difficult to grasp and/or that exhibit an intricate numerical influence on predictions, and (iii) the requirement of non-standard and/or several types of experiments which are either time-consuming or not always accessible. In order to alleviate some of the previous limitations, a two-stage optimization-based calibration procedure (see Figure 6.4) is proposed in what follows to ease the application of the constitutive model formulated in this contribution.

6.4.2 Assumptions

Prior to the description of the actual calibration procedure, some assumptions regarding the material properties calibration shall be discussed.

In the first place, it is important to remark that the four yielding material properties (see Table 6.1) already account for the constitutive behavior dependency on both temperature and strain rate. This is particularly noticeable in the contribution of Govaert and coworkers (Govaert et al., 2000), where the proposed calibration procedure of these properties involves experimental results at different temperatures and strain rates. Inspired by the contributions of Yu and coworkers (Yu et al., 2014) and van Melick and coworkers (van Melick et al., 2003a), temperature-dependency is also incorporated in some visco-elastic and post-yielding properties to improve the constitutive model accuracy within the calibrated temperature range. Despite being isothermal, note that the formulated model can be effectively used to investigate and find suitable temperature-dependent laws of the aforementioned properties. To illustrate this approach, three linear dependencies on temperature, T(K), may be considered for: (i) the thermal relaxation time variable (Yu et al., 2014),

$$g_{T,i}(T) = m_{g_{T,i}}T + b_{g_{T,i}} \qquad i = 1,\ldots,n_{\mathrm{V}}; \tag{6.118}$$

(ii) the softening saturation parameter (van Melick et al., 2003a),

$$D_{\infty}(T) = m_{D_{\infty}}T + b_{D_{\infty}}; \tag{6.119}$$

and (iii) the hardening modulus (van Melick et al., 2003a),

$$H(T) = m_{H}T + b_{H}. \tag{6.120}$$

Note that accounting for the previous temperature-dependent linear functions introduces additional parameters to be calibrated. The accuracy of the temperature-enhanced constitutive model is demonstrated in Section 6.5.3.

Remark.
In contrast with the temperature, any explicit dependency of the material properties on the strain rate or hydrostatic pressure must be accounted for in the computational implementation of the constitutive model. Besides the actual update of the material property that must be performed in the constitutive state update, the computation of the consistent tangent modulus demands a proper linearization of the assumed evolution law due to the adopted implicit integration scheme.

In the second place, instead of letting the shear moduli and relaxation time of each visco-elastic relaxation mode be independent parameters, it is assumed that the corresponding ratios between consecutive modes are constant. In this case, taking the first visco-elastic relaxation mode as a reference, the remaining modes' (assuming that $n_{\mathrm{V}} > 1$) properties are defined as

$$G_i = \frac{1}{r_G^{i-1}} G_1 \,, \qquad g_i = \frac{1}{r_g^{i-1}} g_1 \,, \qquad i = 1, \ldots, n_{\mathrm{V}} \,. \tag{6.121}$$

where r_G and r_g denote ratios of shear moduli and relaxation times, respectively. This assumption reduces the number of visco-elastic material properties to a maximum which is independent of the number of visco-elastic relaxation modes through inheritance.

6.4.3 Optimization-based calibration procedure

As demonstrated in Appendix H, the material properties present in Table 6.1 have a well-defined physical influence on each stage of the intrinsic visco-elastic-visco-plastic material response (see Figure 6.1). This distinctive feature of the constitutive model allows the calibration procedure to be split into two stages (see Figure 6.4): stage 1 involves the material properties associated with the visco-elastic behavior and the yield point; and stage 2 comprises material properties associated with the post-yielding visco-plastic behavior (strain softening and strain hardening).

As discussed by Crist in Haward and Young (2012) (see Chapter 4), uniaxial compression tests on cylindrical specimens are suitable to characterize the intrinsic constitutive behavior of thermoplastics. With careful attention to frictional end effects (avoid specimen 'barreling'), alignment and sample geometry, it is possible to achieve a satisfactory (uniaxial) uniform deformation far beyond the yield point with a controlled rate of deformation[11]. Therefore, it is proposed that the calibration procedure is based on uniaxial compression tests of cylindrical specimens at constant strain rate and constant temperature (see Figure 6.5). In the general case, given the constitutive model dependency on both temperature and strain rate, a minimum of two different temperatures and two different strain rates must be considered (see Section 6.4.2). Moreover, the selected temperatures and strain rates should span the entire ranges of interest in terms of engineering applicability of the constitutive model (e.g., uniform discrete sampling).

Remark.
Considering a cylindrical specimen with diameter D and height L, a constant strain rate, $\dot{\varepsilon}$, can be achieved in a uniaxial compression test by prescribing a compressive displacement, d, defined as

$$d(t) = L\left[\exp[\dot{\varepsilon}\, t] - 1\right] , \tag{6.122}$$

[11] In contrast with the standard uniaxial tensile test, both necking and crazing are suppressed under uniaxial compression. This allows the inference of the intrinsic strain softening and strain hardening characteristic of the post-yielding behavior of amorphous thermoplastics.



Figure 6.4: Schematic of the two-stage optimization-based calibration procedure. Stage 1 involves the calibration of the material properties associated with the visco-elastic behavior and the yield point. Stage 2 comprises the calibration of the material properties associated with the post-yield visco-plastic behavior (strain softening and strain hardening).

or, alternatively, a velocity defined as

$$\dot{d}(t) = L\dot{\varepsilon}\exp\left[\dot{\varepsilon}\,t\right], \tag{6.123}$$

where the compression is assumed to begin at $t = 0$.

In what follows, let us assume that a total of n_{exp} uniaxial compression tests are performed and the corresponding true stress-true strain responses, $\sigma^{\text{exp}}(\varepsilon)$, have been recorded. Irrespective of the acquisition sampling frequency, let us further assume that the experimental data is available at n_s sampling points (each associated with a discrete value of the true strain), and that $\boldsymbol{p}$ denotes the vector of unknown material properties, here taken as optimization parameters. Without any loss of generality, and for a given set of parameters $\boldsymbol{p}$, a weighted error function can be defined at each sampling point of a given true stress-true strain response as

$$\epsilon_i(\boldsymbol{p}) = c_i(\sigma_i(\boldsymbol{p}) - \sigma_i^{\text{exp}}), \qquad i = 1,\ldots,n_s, \tag{6.124}$$

where $c(\varepsilon)$ denotes a (optional) weight function, $\sigma(\boldsymbol{p})$ denotes the numerical true stress-true strain response. Instead of employing such an error function directly in the parameter identification problem, an integrated normalized mean squared error (INMSE) loss function is defined as

$$\mathscr{L}_{\text{INMSE}}(\boldsymbol{p}) = \left[\frac{1}{n_s}\int_\varepsilon (c(\varepsilon)(\sigma(\varepsilon,\boldsymbol{p}) - \sigma^{\text{exp}}(\varepsilon)))^2\,\mathrm{d}\varepsilon\right]\left[\int_\varepsilon (c(\varepsilon)\,\sigma^{\text{exp}}(\varepsilon))^2\,\mathrm{d}\varepsilon\right]^{-1}, \tag{6.125}$$

where the integration is carried out numerically on the n_s discrete sampling points (e.g., by means of the trapezoidal rule). In comparison with its discrete counterpart[12], the integral nature

[12]The (discrete) normalized mean square error (NMSE) loss function is defined as

$$\mathscr{L}_{\text{NMSE}}(\boldsymbol{p}) = \left[\frac{1}{n_s}\sum_{i=1}^{n_s}(c_i(\sigma_i(\boldsymbol{p}) - \sigma_i^{\text{exp}}))^2\right]\left[\sum_{i=1}^{n_s}(c_i\sigma_i^{\text{exp}})^2\right]^{-1}.$$

.

of the adopted loss function is particularly advantageous when the sampling points are not evenly spaced. At last, to account for the n_{exp} true stress-true strain responses in the (multi-objective) parameter identification problem, an average INMSE loss function can be defined as

$$\bar{\mathscr{L}}_{\text{INMSE}}(\boldsymbol{p}) = \frac{1}{n_{\text{exp}}} \sum_{j=1}^{n_{\text{exp}}} \mathscr{L}^{j}_{\text{NMSE}}(\boldsymbol{p}), \tag{6.126}$$

where $\mathscr{L}^{j}_{\text{NMSE}}$ denotes the loss function associated with the j-th response. At this point, it is necessary to choose a suitable optimization algorithm to minimize the average INMSE loss function and solve the parametric identification problem, i.e., to find the set of material properties $\boldsymbol{p}$ that best fits the experimental results. Among the numerous optimization algorithms available in the literature, a hybrid algorithm (King, 2017) that couples the adaptive LIPO algorithm (Malherbe and Vayatis, 2017) with Powell's trust region method (convergence improvement) is adopted in this contribution[13].

Having defined the parameter identification problem, it remains to characterize the proposed two-stage optimization-based calibration procedure completely. Each stage comprises a multi-objective parameter identification optimization problem as follows:

- **Stage 1.** The vector of parameters is defined as[14]

$$\boldsymbol{p} = \left\{ E_{\infty}, G_1, g_{T,1}, \lambda_{g,1}, \Delta H, A_0, \nu^*, \mu, h \right\}, \tag{6.127}$$

  and the weight function is set as a normal distribution defined as

$$c(\varepsilon) \sim \mathscr{N}\left(\varepsilon_y, \left(\frac{\varepsilon_y}{4} \right)^2 \right), \tag{6.128}$$

  where ε_y denotes the yield strain. Compared with a uniform weight function, the adoption of the previous distribution improves the overall quality of the fitting by attributing greater weight to the highly nonlinear region around the yield point. Accounting for the explicit dependency of the thermal relaxation time, $g_{T,1}$, on temperature, replaces this parameter with the parameters associated with the adopted temperature-dependency law (e.g., $\{m_{g_{T,1}}, b_{g_{T,1}}\}$ by adopting Equation (6.118)). If several visco-elastic relaxation modes are considered ($n_{\text{V}} > 1$), the ratios of shear moduli and relaxation times, r_G and r_g, are taken as additional optimization parameters (see Equation 6.121). Note that the softening slope parameter, h, is also included in this stage solely to avoid over-constraining the initial post-yielding region with a (otherwise) fixed estimate. The remaining parameters calibrated in the following stage can be simply set as reasonable finite positive values;

- **Stage 2.** The vector of parameters is defined as

$$\boldsymbol{p} = \left\{ h, D_{\infty}, H \right\}, \tag{6.129}$$

[13] The implementation of the hybrid algorithm is open-source and available in the Python library named lipo.

[14] Instead of calibrating K_{∞} and G_{∞}, the Poisson's ratio, ν_{∞}, is taken from the literature or available experimental data, and Young's modulus is adopted as the only isotropic elasticity parameter to be calibrated. Both K_{∞} and G_{∞} can then be computed from the well-known relations,

$$K_{\infty} = \frac{E_{\infty}}{3(1-2\nu_{\infty})}, \qquad G_{\infty} = \frac{E_{\infty}}{2(1+\nu_{\infty})}.$$

A similar approach is adopted by different authors (e.g., Miled et al. (2011), Krairi and Doghri (2014), Nguyen et al. (2016)).

and the weight function is set as a uniform distribution, $c(\varepsilon) = 1$. Accounting for the explicit dependency of the softening saturation, D_∞, and the hardening modulus, H, on temperature, replaces these parameters by the parameters associated with the adopted temperature-dependency laws (e.g., $\{m_{D_\infty}, b_{D_\infty}, m_H, b_H\}$ by adopting Equations (6.119) and (6.120)). With the exception of the softening slope parameter, h, the remaining parameters are fixed to the calibrated values in the previous stage.

Remark.
Given the uniform strain/stress state promoted in the numerical simulation of a cylindrical specimen under uniaxial compression, and the fact that only the true stress-true strain response is required for the calibration procedure, the analysis of a single hexahedral finite element (subjected to uniaxial compression through Equation (6.122)*) suffices to solve the parameter identification problem. Attending to the numerous simulations usually involved in the optimization process (dependent on the adopted optimization algorithm), such model reduction yields a significant calibration speedup.*

6.5 Numerical results and discussion

6.5.1 Computational setting

The visco-elastic-visco-plastic constitutive model formulated in this contribution is implemented in LINKS (Large Strain Implicit Non-linear Analysis of Solids Linking Scales), an implicit multi-scale finite Fortran code developed by the CM2S research group at the Faculty of Engineering of the University of Porto[15]. The finite element analyses are carried out by considering one-eight of the cylindrical specimen (prescribing suitable symmetric boundary conditions) discretized in a finite element mesh of 20-nodes hexahedral elements (3000 elements, 13881 nodes) with reduced integration (8 Gauss integration points), as illustrated in Figure 6.5. The loading is enforced by means of a total (compressive) displacement prescribed on the upper surface and applied in a total of 200 increments.

All the experimental results considered in the following sections are performed at atmospheric pressure ($p^* = 0.1 \times 10^6$ Pa), and although the temperature is displayed in degrees Celsius to ease the interpretation of results, it is numerically prescribed in SI units (Kelvin) similarly to all constitutive material properties. Moreover, in contrast with several contributions in the literature (e.g., van Breemen et al. (2011), Krairi and Doghri (2014), Nguyen et al. (2016)), it is observed that a single visco-elastic relaxation mode ($n_V = 1$) suffices to achieve a close agreement with the experimental results with respect to the pre-yield nonlinear behavior. Nonetheless, the case where multiple visco-elastic relaxation modes ($n_V > 1$) are considered is included to illustrate the full extent of the constitutive model.

The numerical simulations presented in this section are run on a personal computer with the following specifications: CPU Intel Core i7-9700K (3.60GHz × 8 cores/16 threads, Coffee Lake), RAM 32GB (2 × 16GB) DDR4 @ 3200MHz.

6.5.2 Case study 1: Isothermal deformation at room temperature and different strain rates

The aim of this section is threefold: (i) demonstrate that the constitutive model can be properly calibrated for a single temperature with the two-stage optimization-based calibration procedure described in Section 6.4, (ii) show that the constitutive model is able to capture the different

[15] Bernardo P. Ferreira and A. Francisca C. Alves are both members of the CM2S research group, led by F.M. Andrade Pires, and developers of LINKS.



Figure 6.5: Schematic of uniaxial compression test of cylindrical specimen performed at constant temperature $T(^{\circ}\mathrm{C})$ and strain rate. Finite element model of one-eight of cylindrical specimen discretized in a finite element mesh of 20-nodes hexahedral elements.

stages of the intrinsic behavior of ductile amorphous thermoplastics under uniaxial compression (see Figure 6.1), and (iii) provide a numerical assessment of the computational implementation robustness.

Uniaxial compression experimental results for polycarbonate (PC) are taken from Mulliken (Mulliken, 2006) ($L = 6.35\,\mathrm{mm}$, $\phi D = 12.7\,\mathrm{mm}$) at $T = 25^{\circ}\mathrm{C}$ and different strain rates, $\dot{\varepsilon} \in [0.001, 0.01, 0.1, 1.0]\,\mathrm{s}^{-1}$. The two-stage calibration procedure is performed by taking into account the three experimental responses at $\dot{\varepsilon} \in [0.001, 0.01, 0.1]$ and yields the calibrated material properties presented in Table 6.2.

A close agreement between the constitutive model numerical predictions and the experimental results is achieved under uniaxial compression (see Figure 6.6). The comparison of the experimental and numerical results for $\dot{\varepsilon} \in [0.001, 0.01, 0.1]$ supports the efficacy of the proposed calibration procedure. An accurate numerical prediction is also obtained for the non-calibrated strain rate, $\dot{\varepsilon} = 1.0\,\mathrm{s}^{-1}$, and the different stages characteristic of the intrinsic behavior of PC are clearly captured. Although there is no experimental evidence to endorse the numerical results, the decomposition of the total stress in driving (elastic and visco-elastic contributions) and hardening components is illustrated in Figure 6.7 for the particular strain rate of $\dot{\varepsilon} = 0.1\,\mathrm{s}^{-1}$ to provide further insights into the numerical formulation of the constitutive model.

From a computational implementation point of view, Table 6.3 illustrates the expected Newton-Raphson's quadratic convergence rate in both constitutive state update and global equilibrium iterative scheme (relies on the proper computation of the material consistent tangent modulus). This strongly suggests that the constitutive model is successfully implemented and properly linearized.

To illustrate the case where multiple visco-elastic relaxation modes ($n_{\mathrm{V}} > 1$) are considered, the true stress-true strain compressive numerical response of PC for $\dot{\varepsilon} = 0.1\,\mathrm{s}^{-1}$ at $T = 25^{\circ}\mathrm{C}$ is evaluated for a different number of modes, $n_{\mathrm{V}} \in [1, 2, 3, 4]$ (see Figure 6.8). The two-stage optimization-based calibration procedure detailed in Section 6.4 is employed to fit the material properties for each number of visco-elastic relaxation modes. Similar to the previous results, the material calibration takes into account the uniaxial compression experimental results for PC

Table 6.2: Material properties of the proposed visco-elastic-visco-plastic model calibrated from the uniaxial compression experimental results conducted by Mulliken (Mulliken, 2006) for polycarbonate (PC).

Property	SI Units	Value
E_∞	Pa	3.091×10^8
ν_∞	-	0.390
G_1	Pa	1.880×10^9
$g_{T,1}$	-	1.108×10^{-2}
$\lambda_{g,1}$	-	0.973
ΔH	J/mol	2.769×10^5
A_0	s	8.800×10^{-29}
ν^*	m^3/mol	2.606×10^{-3}
μ	-	6.354×10^{-2}
h	-	2.831×10^2
D_∞	-	14.573
H	Pa	6.007×10^6

conducted by Mulliken (Mulliken, 2006) at $T = 25°C$.

Figure 6.8 shows a close agreement between the numerically predicted and experimental results observed independently of the adopted number of visco-elastic relaxation modes[16]. Attending to the decomposition of the total stress, the driving stress contribution of each visco-elastic relaxation mode, $\sigma_{D,i}$, $i = 1, \ldots, n_V$, decreases with the number of modes. Nevertheless, it is interesting to notice that the elastic and (total) visco-elastic components of the driving stress are approximately insensitive to the number of visco-elastic relaxation modes.

From a computational implementation point of view, Table 6.4 illustrates the expected Newton-Raphson's quadratic convergence rate in both constitutive state update and global equilibrium iterative scheme obtained in the case of four visco-elastic relaxation modes (see Figure 6.8(d)). This suggests that the constitutive model accounting for multiple visco-elastic relaxation modes is successfully implemented and properly linearized.

[16]From the optimization procedure output, no significative differences of the INMSE loss function are observed between the predictions with different number of visco-elastic relaxation modes.



Figure 6.6: Comparison between the proposed constitutive model and the uniaxial compression experimental results conducted by Mulliken (Mulliken, 2006) at $T = 25^{\circ}\text{C}$: (a) True stress-true strain compressive response for PC at different strain rates; (b) Close-up of the initial region of deformation path. Constitutive material properties are provided in Table 6.2.



Figure 6.7: Decomposition of the total stress into driving (elastic and visco-elastic) and hardening components at $T = 25^{\circ}\text{C}$: (a) True stress-true strain compressive numerical response of PC for $\dot{\varepsilon} = 0.01\,\text{s}^{-1}$; (b) Close-up of the initial region of deformation path. Constitutive material properties are provided in Table 6.2.

Table 6.3: Convergence table of the true stress-true strain compressive numerical response of PC for $\dot{\varepsilon} = 0.1\,\mathrm{s}^{-1}$ at $T = 25°\mathrm{C}$. Normalized equilibrium residual evolution at increment 100 and state update normalized residual evolution at a given Gauss point during each global iteration. Convergence tolerance set to 1.0×10^{-8}.

Global			**State Update**	
Increment	Iteration	Norm. Eq. Res.	Iteration	Norm. Res.
100	1	$0.2887 \times 10^{+00}$	1	$0.9974 \times 10^{+00}$
			2	$0.2029 \times 10^{+00}$
			3	0.1531×10^{-01}
			4	0.1079×10^{-04}
			5	0.5472×10^{-08}
	2	0.8205×10^{-03}	1	0.2925×10^{-02}
			2	0.4005×10^{-05}
			3	0.7527×10^{-10}
	3	0.6409×10^{-08}	1	0.1050×10^{-02}
			2	0.5173×10^{-05}
			3	0.1332×10^{-12}

Table 6.4: Convergence table of the true stress-true strain compressive numerical response of PC for $\dot{\varepsilon} = 0.1\,\mathrm{s}^{-1}$ at $T = 25°\mathrm{C}$ (see Figure 6.8(d) with $n_{\mathrm{V}} = 4$). Normalized equilibrium residual evolution at increment 100 and state update normalized residual evolution at a given Gauss point during each global iteration. Convergence tolerance set to 1.0×10^{-8}.

Global			**State Update**	
Increment	Iteration	Norm. Eq. Res.	Iteration	Norm. Res.
100	1	$0.2898 \times 10^{+00}$	1	$0.9336 \times 10^{+00}$
			2	$0.1843 \times 10^{+00}$
			3	0.1287×10^{-01}
			4	0.7650×10^{-04}
			5	0.2747×10^{-08}
	2	0.7493×10^{-03}	1	0.3254×10^{-02}
			2	0.4951×10^{-05}
			3	0.1151×10^{-10}
	3	0.4727×10^{-08}	1	0.1584×10^{-02}
			2	0.1175×10^{-05}
			3	0.6604×10^{-12}



Figure 6.8: True stress-true strain compressive numerical response of PC for $\dot{\varepsilon} = 0.1\,\mathrm{s}^{-1}$ at $T = 25^{\circ}\mathrm{C}$. Decomposition of the total stress into driving (elastic and visco-elastic) and hardening components for a different number of visco-elastic relaxation modes: (a) $n_V = 1$; (b) $n_V = 2$; (c) $n_V = 3$; (d) $n_V = 4$.

6.5.3 Case study 2: Isothermal deformation at different temperatures and strain rates

The aim of this section is to demonstrate that the formulated constitutive model can be effectively applied in the general case where a given range of temperatures (below the glass transition temperature) and strain rates (compatible with isothermal deformation processes) must be simultaneous accounted for in terms of engineering practice.

Uniaxial compression experimental results for polycarbonate (PC) are taken from Yu and coworkers (Yu et al., 2014) ($L = 6.0\,\text{mm}$, $\phi D = 12.0\,\text{mm}$) at different temperatures, $T \in [0, 20, 40, 60]°\text{C}$, and different strain rates, $\dot{\varepsilon} \in [0.001, 0.01, 0.1]\,\text{s}^{-1}$. In comparison with the previous case study, the linear dependencies on the temperature of the thermal relaxation time variable (see Equation (6.118)), the softening saturation parameter (see Equation (6.119)), and the hardening modulus (see (6.120)) are additionally considered. The two-stage calibration procedure is performed by taking into account the following five experimental responses, $(\dot{\varepsilon}\,(\text{s}^{-1}), T(°\text{C})) \in [(0.001, 0), (0.001, 40), (0.001, 60), (0.01, 20), (0.1, 20)]$ and yields the material properties presented in Table 6.5.

Table 6.5: Material properties of the proposed visco-elastic-visco-plastic model calibrated from the uniaxial compression experimental results conducted by Yu and coworkers (Yu et al., 2014) for polycarbonate (PC).

Property	SI Units	Value
E_∞	Pa	4.082×10^8
ν_∞	-	0.39
G_1	Pa	6.407×10^8
$\lambda_{g,1}$	-	0.969
$m_{g_{T,1}}$	-	8.145×10^{-2}
$b_{g_{T,1}}$	-	1.800×10^{-4}
ΔH	J/mol	2.317×10^5
A_0	s	7.940×10^{-22}
v^*	m^3/mol	2.523×10^{-3}
μ	-	4.445×10^{-2}
h	-	1.637×10^2
m_{D_∞}	1/K	4.172×10^{-2}
b_{D_∞}	-	-4.214
m_H	Pa/K	-6.920×10^4
b_H	Pa	6.358×10^7

Figures 6.9, 6.10, and 6.11 present the comparison between the constitutive model predictions and the experimental results under uniaxial compression. The numerical results obtained by Yu and coworkers (Yu et al., 2014) through their one-dimensional visco-elastic-visco-plastic constitutive model are included as well. The results demonstrate that, after a suitable calibration procedure, the constitutive model generalizes well to different strain rates and/or temperatures and can capture the experimentally observed intrinsic behavior of PC accurately. It can also be observed that it delivers more accurate results than Yu and coworkers (Yu et al., 2014) model, namely regarding the smoothness of the transition region at the yield point and the magnitude of stress in the post-yielding region. Similar to the previous

section, the decomposition of the total stress in driving (elastic and visco-elastic contributions) and hardening components is illustrated in Figure 6.12 for the particular temperature-strain rate of $(\dot{\varepsilon}\,(\mathrm{s}^{-1}),\, T(^{\circ}\mathrm{C})) = (0.001, 60)$.



Figure 6.9: Comparison between the proposed constitutive model and the uniaxial compression experimental and numerical results obtained by Yu and coworkers (Yu et al., 2014) for $\dot{\varepsilon} = 0.001\,\mathrm{s}^{-1}$: (a) True stress-true strain compressive response of PC for different temperatures; (b) Close-up of the initial region of deformation path. Constitutive material properties are provided in Table 6.5.

6.6 Accounting for rubber particle internal cavitation

6.6.1 Motivation

In the context of fracture mechanics, toughness characterizes the ability of a given material to resist fracture by dissipating energy. Based on its capacity to experience plastic deformation, two fracture modes are frequently distinguished: brittle and ductile fracture. While in ductile fracture there is substancial plastic deformation with high energy dissipation before failure, brittle fracture is accompanied by little or no plastic deformation prior to failure and low energy dissipation. It is important to remark that the mode of fracture depends not only on the material intrinsic properties, but also on temperature, strain rate and stress state.

A well-known and undesired characteristic of most amorphous thermoplastics is their brittleness while operating below the glass transition temperature. The discovery that the addition of 5 to 15% of rubbery particles into the polymer matrix could enhance their toughness, a process usually called rubber toughening, emerged as an efficient technique and of major importance to the plastics industry. In fact, rubber toughening has proved so effective that it has been extended to almost all of the commercial glassy thermoplastics, including polymethylmethacrylate (PMMA), polyvinylchloride (PVC) and even polycarbonate (PC), the thoughest among the glassy polymers (Haward and Young, 2012). Nonetheless, it is evident that



Figure 6.10: Comparison between the proposed constitutive model and the uniaxial compression experimental and numerical results obtained by Yu and coworkers Yu et al. (2014) for $\dot{\varepsilon} = 0.01\,s^{-1}$: (a) True stress-true strain compressive response of PC for different temperatures; (b) Close-up of the initial region of deformation path. Constitutive material properties are provided in Table 6.5.

toughness in rubber-modified polymers is achieved at some sacrifice of strength and stiffness, i.e. the material ability to resist to high stresses that is enhanced by supressing deformation mechanisms. Hence, the reduction of the glassy polymers longitudinal and shear moduli due to rubber toughening is only acceptable if it is accompanied by a substantial increase in toughness.

The rubber phase intended for rubber toughening must be highly dispersed as small particles in the plastic matrix. The particle size and size distribution of the dispersed particles will depend on the miscibility of the two phases and on the way in which they are mixed and processed (Collyer, 1994). An appropriate choice of the rubber to toughen a given polymeric matrix is essential to obtain the desired two-phase blends with a good interfacial adhesion between the two phases. In turn, the desired size distribution, whose optimization ultimately depends on identifying the predominant fracture mechanism of the polymer matrix, can be obtained through suitable processing conditions. At a fixed rubber concentration and interfacial adhesion, a plot of toughness versus rubber particle size clearly shows that there is an optimum particle size to achieve a maximum toughness (e.g. Cigna et al. (1989)), which depends on the entanglement density of the polymer matrix. In terms of the internal morphology of the rubber particles, they are plain homogeneous rubber spheres at their simplest but often exhibit more complex morphologies in most rubber toughened polymers (see Figure 6.13). Furthermore, standard rubber particles tend to be spherical in the relaxed state, becoming deformed and distorted only as a result of solid straining.



Figure 6.11: Comparison between the proposed constitutive model and the uniaxial compression experimental and numerical results obtained by Yu and coworkers (Yu et al., 2014) for $\dot{\varepsilon} = 0.1\,s^{-1}$: (a) True stress-true strain compressive response of PC for different temperatures; (b) Close-up of the initial region of deformation path. Constitutive material properties are provided in Table 6.5.



Figure 6.12: Decomposition of the total stress into driving (elastic and visco-elastic) and hardening components at $T = 60°C$: (a) True stress-true strain compressive numerical response of PC for $\dot{\varepsilon} = 0.001\,s^{-1}$; (b) Close-up of the initial region of deformation path. Constitutive material properties are provided in Table 6.5.

Given the intrinsic relationship between the rubber toughening underlying mechanisms and the failure of amorphous thermoplastics, properly accounting for such phenomena is fundamental to develop accurate constitutive models. Recall that in the particular case of the PC/ABS thermoplastic blend (see Section 1.2.1), the acrylonitrile-butadiene-styrene (ABS) is a binary blend of styrene-acrylonitrile (SAN, amorphous thermoplastic) and polybutadiene (PB, amorphous elastomer). Therefore, the accurate constitutive modeling of the ABS material phase motivates the enhancement of the visco-elastic-visco-plastic constitutive model proposed in Section 6.2.

Remark.
Alternatively, both SAN and PB material phases may be constitutively modeled as independent material phases (e.g., see PC/ABS RVE illustrated in Figure 1.4). In this case, the proposed constitutive model is suitable for the SAN material phase, while a suitable hyperelastic constitutive model could be adopted for the PB material phase. However, the micro-scale equilibrium problem would most likely have a very large dimension due to the spatial discretization required to properly model such RVE. Under certain assumptions (discussed in Section 6.6.3), it is therefore advantageous to perform the numerical treatment of the ABS material phase in a unified way.



Figure 6.13: Schematic representation of typical morphologies of rubber particles.

6.6.2 Rubber toughening mechanisms

Attainable levels of fracture resistance in rubber toughened glassy polymers are largely determined by the properties of the matrix, which is capable of dissipating large amounts of energy per unit volume through visco-plastic flow. Therefore, it is not surprising that toughening techniques are directed towards maximizing the volume of material participating in this type of deformation. The main problem is that stress concentrations around cracks, notches and other geometric features act to localize the deformation, often to the extent of

causing brittle fracture (Haward and Young, 2012). When subjected to these high local stresses, a tough polymer is able to respond by deforming and strain hardening, a process which in glassy polymers occurs through rotation ot the carbon chain axes towards the direction of maximum extension, often termed drawing. If such process is effective in stabilizing the overstressed region against fracture, yielding spreads to the surrounding material and may eventually encompass a large fraction of the component.

The manner in which rubber toughening works depends on the way in which the matrix polymer usually fails under impact conditions, either by crazing, shear yielding or a combination of both (Collyer, 1994). Crazing is a well-known phenomenon that frequently precedes fracture in some thermoplastic polymers (Callister and Rethwisch, 2013). Associated with crazes are regions of very localized plastic deformation, which lead to the formation of small and interconnected microvoids at the craze tip. Fibrillar bridges form between these microvoids wherein molecular chains become oriented as shown in Figure 6.14. As the craze tip advances, the craze thickens by drawing in more polymer from the craze surfaces and is the presence of the relatively strong craze fibrils that makes the craze load bearing. If the applied tensile load is sufficient, often termed craze initiation stress, these bridges elongate and break, the microvoids grow and coalesce by the rupture of surrounding craze fibrils, and a crack begins to propagate, eventually leading to a catastrophic rupture when a critical size is attained. The process of craze growth prior to cracking dissipates energy through visco-plastic flow, hence increasing the toughness of the polymer. In amorphous glassy polymers, characterized by a brittle polymeric matrix, the crack propagates with little craze formation and growth, resulting in the aforementioned low fracture toughness (e.g. Collyer (1994), Haward and Young (2012)). In this context, if the craze initiation stress of the polymer matrix is lower than the yield stress, the predominant fracture mechanism is by crazing. On the other hand, if the yield stress is lower than the craze initiation stress, then the predominant fracture mechanism is by shear yielding of the polymer matrix. When the craze initiation stress and the yield stress are comparable, or certain interactions take place between multiple crazes and shear bands, mixed fracture occurs simultaneously by crazing and shear yielding. It is important to remark that both crazing and shear yielding mechanisms are rate processes which follow Eyring kinetics, hence a decrease in temperature or increase of strain rate raises the polymer matrix craze initiation and yield stresses (Haward and Young, 2012).



Figure 6.14: Schematic representation of the crazing phenomenon.

The effect of the rubber particles depends on the mechanism by which toughening is

believed to occur, be it as a stress concentrator to initiate crazes or shear bands (Wu (1985), Hobbs et al. (1983)) or to relieve local hydrostatic stresses by internal cavitation (Donald and Kramer, 1982). Regarding the crazing fracture mechanism, rubber particles have been shown to act as craze initiators and also as controlers of their growth (Bucknall (1977), Donald and Kramer (1981)). Under a sufficiently high applied tensile stress, crazes are initiated at points of maximum principal strain (typically near the equator of rubber particles where there is a concentration of triaxial stresses) and propagate outwards normal to the maximum applied stress, although interactions between adjacent rubber particles' surrounding stress fields may introduce deviations (Collyer, 1994). Since the craze growth is terminated when an adjacent rubber particle is encountered, the latter effectively toughens the polymer by preventing the growth of very large crazes that would otherwise result in a premature crack and contribute to a potential catastrophic rupture. Therefore, the rubber toughening leads to the formation of a large number of small crazes, phenomenon termed multiple crazing, instead of the undesired small number of large crazes in the absence of rubber particles. Moreover, the multiple crazing promotes a comparatively large volume of the multiphasic material dissipating energy through viscoelastic-plastic flow, which is consistent with the high energy absorption observed in tensile and impact tests and the extensive stress whitening which accompanies the deformation and failure (Collyer, 1994). In turn, the shear yielding fracture mechanism also plays a major role in the mechanism of rubber toughening. Either in the form of localized shear bands or more generalized and diffuse regions of shear yielding, this phenomenon involves the dissipation of energy through viscoelastic-plastic flow, hence enhancing the polymer toughness. Furthermore, since crazing and shear yielding may occur simultaneously in many rubber toughened polymers, it was observed that shear bands also present a barrier to the propagation of crazed and hence crack growth (Bucknall, 1977), delaying the material fracture (Collyer, 1994). Early observations of Bucknall and coworkers (Bucknall et al., 1972) showed not only shear bands intersecting and effectively stopping crazes, but also that shear bands were generated and run between rubber particles, hence shedding some light of their role in the mechanism of rubber toughening.

It is now generally accepted that the shear yielding mechanism is intrinsically related with a phenomenon of rubber particle internal cavitation (see Figure 6.15). The ocurrence of rubber particle cavitation in the presence of shear yielding has been observed in rubber toughened amorphous glassy polymers by several authors (Yee and Pearson (1986), Pearson and Yee (1989), Haaf et al. (1977)), while being absent in the neat or untoughened polymer matrices, and has increasingly been recognized as a mechanism of central importance to rubber toughening. The extent of rubber particle cavitation became clear by observing fracture surfaces of tough RT-epoxy resins with scanning electron microscopy (SEM), where every particle on the fracture surface contains a prominent hemispherical void. This void is surrounded by a depressed crater of rubber, a feature produced when the contraction and yielding in the epoxy matrix makes the particle dilate, so that during fracture the two halves of the streched rubber shell retract where they are not restrained by the boundary wall. TEM have proved to be a more effective technique in observing particle cavitation in toughened thermoplastics (Haward and Young, 2012).

Internal cavitation was observed in rubber particles much smaller than $1\,\mu$m in diameter under dilatational stresses, hence it was concluded that the mechanism for void nucleation does not depend on the presence of occasional voids contained in the rubber. In fact, since resistance to dilatation in rubbers arises almost entirely from weak van der Waals bonds, microvoids are nucleated from a cohesive failure in the rubber, when the distribution of polymer chains within the expanded volume of the rubber particles become unstable under high triaxial tensile stresses. Inspired on the work of Gent and Wang (Gent and Wang, 1991), Bucknall and coworkers (Lazzeri and Bucknall (1993), Bucknall et al. (1994)) developed an energy-balance approach in order to model the cavitation in a spherical homogeneous rubber particle, assuming an undamaged initial state. The main idea is that the rubber particle only suffers internal cavitation if the

associated release of stored strain energy overcomes the energy needed to form the void, i.e. the energy required to increase the surface area of the void and to stretch the surrounding layers of rubber surrounding the growing void (see Figure 6.15).



Figure 6.15: Schematic representation of the composite spherical element considered in the cavitation model of Bucknall and coworkers (Bucknall et al., 1994), before and after cavitation.

With this brief description of the rubber particle internal cavitation phenomena, it is now comprehensible why it is usually followed and enhances the onset of shear yielding. When the rubber particle suffers cavitation, the associated dissipation of volume strain energy leads to a reduction in the local triaxial or hydrostatic stress and consequently lowers the polymer matrix yield stress. Moreover, because the surrounding matrix behaves approximately as if it were under plane stress conditions, the shear yielding is promoted in sacrifice of the craze-favouring triaxial state. For this reason, the onset of shear yielding and the formation of shear band is enhanced by the voids nucleated in the polymeric matrix due the rubber particle internal cavitation. Nonetheless, although the internal cavitation of rubber particles does involve energy dissipation, the enhanced shear yielding of the polymer matrix due to the rubber toughening is the major energy dissipation mechanism (Collyer, 1994).

Concerning the presence of a sharp notch or crack, where fracture problems become most severe, a triaxial stress exists ahead of the crack tip where the extent of shear yielding is severely restricted. However, such triaxial state promotes the internal cavitation of the rubber particles that result in the formation of a zone of voids and shear bands ahead of the crack tip on the opening up of the crack faces (Collyer, 1994). This voided zone blunts the crack tip and further tension leads to an even larger plastic zone where energy is dissipated through viscoelastic-plastic flow, thus effectively acting as a toughening mechanism.

6.6.3 Constitutive extension for porous thermoplastics

Inspired by the original contribution of Pan and coworkers (Pan et al., 1983), also followed by other contributions (e.g., Zaïri et al. (2008), Zaïri et al. (2011), Holopainen (2014)), the visco-elastic-visco-plastic constitutive model proposed in Section 6.2 can be extended to account for the phenomenon of rubber particle internal cavitation. In the previous contributions, the rubber material phase is explicitly neglected and the rubber particles are treated as voids after internal cavitation takes place. This modeling assumption is reasonable when (i) the content of rubber particles is relatively low, (ii) the stiffness of the rubber material phase is much lower than the surrounding amorphous thermoplastic matrix, and (iii) the rubber particles cavitate at relatively

low stress levels. These considerations are stated for the ABS by Seelig and Giessen (Seelig and Giessen, 2007), and can be similarly adopted for other rubber thoughened amorphous thermoplastics.

Following the previous modeling approach, two scales are implicitly assumed in the extended constitutive formulation: a macro-scale, where the rubber toughened amorphous thermoplastic is considered as a continuum, and a micro-scale, associated with the amorphous thermoplastic matrix behavior (see Figure 6.16). Prior to the occurrence of internal cavitation, the rubber material phase is neglected and the continuum (macro-scale) behavior is assumed to be coincident with the amorphous thermoplastic matrix (micro-scale) behavior. The latter can be conveniently modeled by the visco-elastic-visco-plastic constitutive model proposed in Section 6.2. As soon as the rubber particles suffer internal cavitation, microstructural damage in the form of void nucleation and growth is considered. Under such assumption, the continuum (macro-scale) behavior demands a visco-elastic-visco-plastic constitutive model for porous amorphous thermoplastics.

Remark.
In consistency with the notation adopted throughout this thesis, the state variables related with the amorphous thermoplastic matrix (here taken as the micro-scale) are subscripted as $(\bullet)_\mu$ *in the remainder of this section.*



Figure 6.16: Schematic representation of the rubber toughened glassy polymer in the undamage state, where the rubber phase constitutive behaviour is neglected, and after rubber particle internal cavitation, where the polymer microstructure includes matrix and void phases.

Over the past decades, there was a considerable effort to develop constitutive models to capture the damage in metallic materials associated with the nucleation, growth and coalescence of voids (McClintock (1968), Rice and Tracey (1969), (Gurson, 1977), Chu and Needleman (1980), Tvergaard (1981), Tvergaard (1982), Pan et al. (1983), Tvergaard and Needleman (1984), Mear and Hutchinson (1985), Tvergaard (1987), Gologanu et al. (1993), Gologanu et al. (1994), Gologanu et al. (2001b), Gologanu et al. (2001a), Benzerga and Besson (2001), Wen et al. (2005), Madou and Leblond (2012a), Madou and Leblond (2012b), Madou and Leblond (2013), Madou et al. (2013), Morin et al. (2014), Morin et al. (2015b), Morin et al. (2015a)), most of them based on the pioneering and well-known Gurson potential (Gurson, 1977). In its purely micromechanical model, developed from the application of limit analysis and Hill-Mandel homogenization theories (Mandel (1966), Hill (1967)) over a spherical

representative volume element (RVE) with a concentrical spherical void, Gurson assumes that the porous material is represented by a periodic distribution of spherical voids embeded in a isotropic, incompressible and rigid-perfectly plastic J_2 matrix (see Figure 6.17). In fact, the Gurson model is reduced to the von Mises elasto-plastic model when the material is undamaged (absence of voids) and thus can be seen as an extension of the latter to account for the microstructural damage in the form of void growth. Several investigations based on the Gurson-type description of porous solids have successfully captured the behaviour of thermoplastic polymers (Lazzeri and Bucknall (1995), Steenbrink et al. (1997), Pijnenburg and Van der Giessen (2001), Guo and Cheng (2002), Jeong (2002), Seelig and van der Giessen (2002), Imanaka et al. (2003), Pijnenburg et al. (2005), Zaïri et al. (2005), Challier et al. (2006), Guo et al. (2008), Zaïri et al. (2008), Laiarinandrasana et al. (2009), Imanaka et al. (2009)).



Figure 6.17: Schematic representation of the RVE considered in the Gurson model.

For illustrative purposes, the well-known Gurson-Tvergaard-Needleman (GTN) model (Chu and Needleman (1980), Tvergaard (1981), Tvergaard (1981), Tvergaard and Needleman (1984)) is considered in what follows. The yield function of the GTN model is here adopted as[17]

$$\Phi_{\mathrm{GTN}}(\boldsymbol{\tau}_{\mathrm{D}}) = (\tau_{\mathrm{D}}^{\mathrm{eq}})^2 + 2f^{v}q_1(\tau_{\mu}^{\mathrm{eq}})^2\cosh\left(q_2\frac{\mathrm{tr}[\boldsymbol{\tau}_{\mathrm{D}}]}{2\sqrt{3}\tau_{\mu}^{\mathrm{eq}}}\right) - (\tau_{\mu}^{\mathrm{eq}})^2\left(1+q_1^2(f^{v})^2\right) = 0\,, \tag{6.130}$$

where $\tau_{\mathrm{D}}^{\mathrm{eq}}$ is the macro-scale driving equivalent stress,

$$\tau_{\mathrm{D}}^{\mathrm{eq}} = \sqrt{\frac{1}{2}\boldsymbol{\tau}_{\mathrm{D},d} : \boldsymbol{\tau}_{\mathrm{D},d}}\,, \tag{6.131}$$

τ_{μ}^{eq} is the micro-scale equivalent stress, and f^{v} denotes the void volume fraction[18] The

[17] Similar to Steenbrink and coworkers (Steenbrink et al., 1997), note that yield function is formulated in terms of the equivalent shear stress rather than the von Mises equivalent stress. In addition, given the kinematical finite strain extension of the numerical integration algorithm, the Cauchy stress tensor is conveniently replaced by the Kirchhoff stress tensor.

[18] In a micro-scale equilibrium problem, the void volume fraction, f^{v}, can be explicitly defined as $f^{v} = v_{\mu}^{v}/v_{\mu}$, where v_{μ}^{v} and v_{μ} stand for the void volume and RVE volume, respectively.

heuristic parameters q_1 and q_2 are introduced by Tvergaard (Tvergaard, 1981) to obtain a better correlation with micromechanical simulations. Although these are often associated with the interaction between voids, their physical meaning is susceptible of distinct interpretations (e.g., Gologanu et al. (1997), Benzerga and Leblond (2010)). In general, the void volume fraction evolution law can be postulated as

$$\dot{f}^v = \dot{f}^v_{\mathrm{N}} + \dot{f}^v_{\mathrm{G}}\,, \tag{6.132}$$

where $\dot{f}^v_{\mathrm{N}}$ accounts for the nucleation of voids and $\dot{f}^v_{\mathrm{G}}$ for the growth of existing voids. Chu and Needleman (Chu and Needleman, 1980) proposed a void nucleation rate based on a normal distribution as

$$\dot{f}^v_{\mathrm{N}} = \frac{f_{\mathrm{N}}}{s_{\mathrm{N}}\sqrt{2\pi}} \exp\left[-\frac{1}{2}\left(\frac{\bar{\varepsilon}_\mu - \varepsilon_{\mathrm{N}}}{s_{\mathrm{N}}}\right)^2\right]\dot{\gamma}\,, \tag{6.133}$$

where f_{N} is a constant, ε_{N} and s_{N} are, respectively, the mean value and standard deviation of the normal distribution, and $\dot{\gamma}$ is a equivalent inelastic strain rate. In turn, the Gurson's model (Gurson, 1977) void growth rate is derived from the mass conservation law as

$$\dot{f}^v_{\mathrm{G}} = 3(1-f)\tilde{D}^p_h\,, \tag{6.134}$$

where $\tilde{D}^p_h$ denotes the volumetric component of the spatially rotated rate of plastic deformation. In order to incorporate the effects of void coalescence, Tvergaard and Needleman (Tvergaard and Needleman, 1984) propose an increased void growth rate after a given critical coalescence void volume fraction, $f^v = f^v_c$, is attained. It is also worth mentioning that Holopainen (Holopainen, 2014) sets $\dot{f}^v_{\mathrm{G}} = 0$ as soon as a crazing initiation-criterion is satisfied and the crazing is already accounted for in the visco-plastic flow rule of the constitutive model.

With the previous ingredients at hand, the extended visco-plastic flow vector can be associatively derived as (Pan et al., 1983)

$$\boldsymbol{N} = \frac{\partial \Phi_{\mathrm{GTN}}(\boldsymbol{\tau}_{\mathrm{D}})}{\partial \boldsymbol{\tau}_{\mathrm{D}}} = \boldsymbol{\tau}_{\mathrm{D},d} + \sqrt{\frac{1}{3}}\, q_1 q_2 f \tau^{\mathrm{eq}}_\mu \sinh\left(q_2 \frac{\mathrm{tr}[\boldsymbol{\tau}_{\mathrm{D}}]}{2\sqrt{3}\tau^{\mathrm{eq}}_\mu}\right)\boldsymbol{I}\,. \tag{6.135}$$

Instead of being explicitly defined as in Section 6.2 (see Equation (6.39)), the visco-plastic multiplier can be determined from the equivalence between the macro-scale plastic power, $\dot{W}^p$, defined as

$$\dot{W}^p = \boldsymbol{\tau}_{\mathrm{D}} : \tilde{\boldsymbol{D}}^p = \boldsymbol{\tau}_{\mathrm{D}} : \dot{\gamma}\boldsymbol{N}\,, \tag{6.136}$$

and the micro-scale plastic power (visco-plastic energy dissipation of amorphous thermoplastic matrix), $\dot{W}^p_\mu$, defined as

$$\dot{W}^p_\mu = (1-f^v)\,\boldsymbol{\tau}_{\mathrm{D},\mu} : \tilde{\boldsymbol{D}}^p_\mu = (1-f^v)\,\tau^{\mathrm{eq}}_\mu \dot{\gamma}_\mu = (1-f^v)\frac{(\tau^{\mathrm{eq}}_\mu)^2}{\eta_\mu}\,, \tag{6.137}$$

where use of Equations (6.39), (6.40), (6.52) and (6.53) has been made, and the matrix visco-plastic viscosity function (see Equation 6.53) is now written as

$$\eta_\mu = \eta_\mu(\boldsymbol{\tau}_{\mathrm{D},\mu}, \bar{\varepsilon}^p_\mu) = A_\mu(\boldsymbol{\tau}_{\mathrm{D},\mu}, \bar{\varepsilon}^p_\mu)\, \tau^{\mathrm{eq}}_\mu \left(\sinh\left(\frac{\tau^{\mathrm{eq}}_\mu}{\tau^*} \right) \right)^{-1}, \tag{6.138}$$

where

$$A_\mu = A_0 \exp\left[\frac{\Delta H}{R^* T} + \frac{\mu P_\mu}{\tau^*} - D_\infty \left(1 - \exp\left[-\sqrt{\frac{2}{3}} \frac{h \bar{\varepsilon}^p_\mu}{D_\infty} \right] \right) \right], \tag{6.139}$$

and

$$\dot{\bar{\varepsilon}}^p_\mu = \frac{1}{\sqrt{3}} \frac{1}{A} \sinh\left(\frac{\tau^{\mathrm{eq}}_\mu}{\tau^*} \right). \tag{6.140}$$

The equivalence between macro-scale and micro-scale plastic works can be understood as a necessary condition leading to a coherence in the definition of the energy dissipation at the two scales (Zaïri et al., 2011). After straightforward algebraic manipulations, the condition $\dot{W}^p = \dot{W}^p_\mu$ yields

$$\dot{\gamma} = (1 - f^\nu) \frac{(\tau^{\mathrm{eq}}_\mu)^2}{\eta_\mu} \left(\boldsymbol{\tau}_{\mathrm{D},d} : \boldsymbol{\tau}_{\mathrm{D},d} + \sqrt{\frac{1}{3}}\, q_1 q_2 f^\nu \tau^{\mathrm{eq}}_\mu \sinh\left(q_2 \frac{\mathrm{tr}[\boldsymbol{\tau}_{\mathrm{D}}]}{2\sqrt{3}\tau^{\mathrm{eq}}_\mu} \right) \mathrm{tr}[\boldsymbol{\tau}_{\mathrm{D}}] \right)^{-1}. \tag{6.141}$$

Remark.
Recall that the total hydrostatic pressure term, P_μ, is additively decomposed in a superimposed hydrostatic pressure, p^*, and a hydrostatic pressure, $p_{\mathrm{D},\mu} = (1/3)\,\mathrm{tr}[\boldsymbol{\tau}_{\mathrm{D},\mu}]$. However, although a relation between the macro- and the micro-scale is established through the GTN potential (see Equation (6.130)*) and the equivalence between macro-scale and micro-scale plastic dissipation, the amorphous thermoplastic matrix stress state is generally undetermined. Prior to internal cavitation (absence of voids, $f = 0$), the macro-scale and micro-scale stress state are assumed coincident, therefore $p_{\mathrm{D},\mu} = p_{\mathrm{D}} = (1/3)\,\mathrm{tr}\,[\boldsymbol{\tau}_{\mathrm{D}}]$. However, as soon as voids nucleate and grow ($f > 0$), the micro-scale stress state is no longer homogeneous due to the presence of voids in the matrix. In this case, it makes sense from a physical point of view to take an average or homogenized counterpart of $p_{\mathrm{D},\mu}$, which can be established as $p_{\mathrm{D},\mu} \approx p_{\mathrm{D}}$. For this reason, it is assumed that the hydrostatic pressure incorporated in the matrix viscosity function (see Equation* (6.138)*) is determined as $p_{\mathrm{D},\mu} = p$, i.e. $P_\mu = P$.*

The extended visco-plastic constitutive law is then established through the spatially rotated rate of plastic deformation as

$$\tilde{\boldsymbol{D}}^p = \dot{\gamma} \frac{\partial \Phi_{\mathrm{GTN}}(\boldsymbol{\tau}_{\mathrm{D}})}{\partial \boldsymbol{\tau}_{\mathrm{D}}} = \dot{\gamma} \left(\boldsymbol{\tau}_{\mathrm{D},d} + \frac{1}{\sqrt{3}}\, q_1 q_2 f^\nu \tau^{\mathrm{eq}}_\mu \sinh\left(q_2 \frac{\mathrm{tr}[\boldsymbol{\tau}_{\mathrm{D}}]}{2\sqrt{3}\tau^{\mathrm{eq}}_\mu} \right) \boldsymbol{I} \right), \tag{6.142}$$

where the visco-plastic multiplier is given by Equation (6.141), completed by postulating a zero plastic spin tensor, $\boldsymbol{W}^p = \boldsymbol{0}$. The spatially rotated rate of plastic deformation can now be conveniently decomposed as

$$\tilde{\boldsymbol{D}}^p = \tilde{\boldsymbol{D}}^p_d + \tilde{D}^p_h \boldsymbol{I}, \tag{6.143}$$

where the deviatoric and hydrostatic components are, respectively, defined as

$$\tilde{\boldsymbol{D}}_d^p = \dot{\gamma}\,\boldsymbol{\tau}_{\mathrm{D},d}\,, \tag{6.144}$$

and

$$\tilde{D}_h^p \boldsymbol{I} = \dot{\gamma}\sqrt{\frac{1}{3}}\,q_1 q_2 f^\nu \tau_\mu^{\mathrm{eq}} \sinh\left(q_2 \frac{\mathrm{tr}[\boldsymbol{\tau}_\mathrm{D}]}{2\sqrt{3}\tau_\mu^{\mathrm{eq}}}\right)\boldsymbol{I}\,, \tag{6.145}$$

In comparison with the constitutive model described in Section 6.2, it is possible to observe that the extended visco-plastic flow rule is no longer purely deviatoric, accounting for a volumetric component intrinsically associated with the rubber particles internal cavitation. In addition, note that the extended visco-plastic flow rule recovers Equation (6.52) in the absence of voids ($f^\nu = 0$), which is consistent with the assumptions underlying the proposed constitutive extension.

Remark.
Despite adopting the GTN model's yield function as the visco-plastic flow potential, note that the extended constitutive model does not assume the existence of an elastic domain bounded by a yield surface, i.e., the local strain is always assumed as the result of both visco-elastic and visco-plastic contributions.

6.6.4 Summary

For the sake of clarity, the extended finite strain visco-elastic-visco-plastic constitutive initial value problem can be summarized as follows: Given the initial values $\boldsymbol{F}^p(t_0)$, $f^\nu(t_0)$, $\eta_\mu(t_0)$, $\tau_\mu^{\mathrm{eq}}(t_0)$ and $\bar{\varepsilon}_\mu^p(t_0)$ and given the history of the deformation gradient $\boldsymbol{F}(t)$, $t \in [t_0, t_f]$, find the functions $\boldsymbol{F}^p(t)$, $f^\nu(t)$, $\eta_\mu(t)$, $\tau_\mu^{\mathrm{eq}}(t)$ and $\bar{\varepsilon}_\mu^p(t)$ that satisfy

$$\dot{\boldsymbol{F}}^p(t)(\boldsymbol{F}^p(t))^{-1} = \dot{\gamma}(t)(\boldsymbol{R}^e(t))^T \boldsymbol{N}(t)\,\boldsymbol{R}^e(t)\,, \tag{6.146}$$

$$\dot{\bar{\varepsilon}}_\mu^p(t) = \sqrt{\frac{1}{3}}\frac{1}{A(t)}\sinh\left(\frac{\tau_\mu^{\mathrm{eq}}(t)}{\tau^*}\right), \tag{6.147}$$

$$\dot{f}^\nu(t) = \dot{f}_\mathrm{N}^\nu(t) + 3(1-f^\nu(t))\,\dot{\gamma}(t)\sqrt{\frac{1}{3}}\,q_1 q_2 f^\nu(t)\,\tau_\mu^{\mathrm{eq}}(t)\sinh\left(q_2\frac{\mathrm{tr}[\boldsymbol{\tau}_\mathrm{D}]}{2\sqrt{3}\tau_\mu^{\mathrm{eq}}(t)}\right)\boldsymbol{I}\,, \tag{6.148}$$

and

$$\Phi_{\mathrm{GTN}} = (\tau_\mathrm{D}^{\mathrm{eq}}(t))^2 + 2f^\nu q_1 (\tau_\mu^{\mathrm{eq}}(t))^2 \cosh\left(q_2\frac{\mathrm{tr}[\boldsymbol{\tau}_\mathrm{D}(t)]}{2\sqrt{3}\tau_\mu^{\mathrm{eq}}(t)}\right) - (\tau_\mu^{\mathrm{eq}}(t))^2\left(1+q_1^2(f^\nu(t))^2\right) = 0\,, \tag{6.149}$$

with

$$\dot{\gamma} = (1-f^\nu(t))\frac{(\tau_\mu^{\mathrm{eq}}(t))^2}{\eta_\mu(t)}\Bigg(\boldsymbol{\tau}_{\mathrm{D},d}(t):\boldsymbol{\tau}_{\mathrm{D},d}(t) + \sqrt{\frac{1}{3}}q_1 q_2 f^\nu(t)\tau_\mu^{\mathrm{eq}}(t)\sinh\left(q_2\frac{\mathrm{tr}[\boldsymbol{\tau}_\mathrm{D}(t)]}{2\sqrt{3}\tau_\mu^{\mathrm{eq}}(t)}\right)\mathrm{tr}[\boldsymbol{\tau}_\mathrm{D}(t)]\Bigg)^{-1}, \tag{6.150}$$

$$\tau_\mathrm{D}^{\mathrm{eq}}(t) = \sqrt{\frac{1}{2}\,\boldsymbol{\tau}_{\mathrm{D},d}(t):\boldsymbol{\tau}_{\mathrm{D},d}(t)}\,, \tag{6.151}$$

$$\eta_{\mu}(t) = A(t)\tau_{\mu}^{\mathrm{eq}}(t)\left(\sinh\left(\frac{\tau_{\mu}^{\mathrm{eq}}(t)}{\tau^{*}}\right)\right)^{-1}, \tag{6.152}$$

$$A(t) = A_0 \exp\left[\frac{\Delta H}{R^{*}T} + \frac{\mu P(t)}{\tau^{*}} - D_{\infty}\left(1 - \exp\left[-\sqrt{\frac{3}{2}}\frac{h\bar{\varepsilon}_{\mu}^{p}(t)}{D_{\infty}}\right]\right)\right], \tag{6.153}$$

$$\boldsymbol{N}(t) = \boldsymbol{\tau}_{\mathrm{D},d}(t) + \sqrt{\frac{1}{3}}q_1 q_2 f^{v}(t)\tau_{\mu}^{\mathrm{eq}}(t)\sinh\left(q_2\frac{\mathrm{tr}[\boldsymbol{\tau}_{\mathrm{D}}(t)]}{2\sqrt{3}\tau_{\mu}^{\mathrm{eq}}(t)}\right)\boldsymbol{I}. \tag{6.154}$$

for each instant $t \in [t_0, t_f]$, with

$$\boldsymbol{\tau}_{\mathrm{T}}(t) = \boldsymbol{\tau}_{\mathrm{D}}(t) + \boldsymbol{\tau}_{\mathrm{H}}(t), \tag{6.155}$$

$$\boldsymbol{\tau}_{\mathrm{D}}(t) = \int_0^t \mathbf{D}^{ve}(t-t^{*}) : \frac{\partial \boldsymbol{\varepsilon}^{e}(t^{*})}{\partial t^{*}}\,\mathrm{d}t^{*}, \tag{6.156}$$

$$\boldsymbol{\tau}_{\mathrm{H}}(t) = H\bar{\boldsymbol{\varepsilon}}^{p}(t)\,\boldsymbol{\varepsilon}_{d}(t), \tag{6.157}$$

and the kinematic relations

$$\boldsymbol{\varepsilon}^{e}(t) = \frac{1}{2}\ln\left[\boldsymbol{F}^{e}(t)(\boldsymbol{F}^{e}(t))^{T}\right], \tag{6.158}$$

$$\boldsymbol{R}^{e}(t) = \boldsymbol{F}^{e}(t)[(\boldsymbol{F}^{e}(t))^{T}\boldsymbol{F}^{e}(t)]^{-1/2}, \tag{6.159}$$

$$\boldsymbol{F}^{e}(t) = \boldsymbol{F}(t)\left[\boldsymbol{F}^{p}(t)\right]^{-1}. \tag{6.160}$$

In addition to the material properties already summarized in Table 6.1, the extended visco-elastic-visco-plastic constitutive model just described accounts for (i) the heuristic parameters of the GTN model's yield function (see Equation (6.130)), (q_1, q_2), and (ii) the parameters associated with the void volume fraction evolution law (see Equations (6.132), (6.133) and (6.134)), (f_{N}^{v}, ε_{N}, s_{N}).

6.6.5 Remarks on numerical integration scheme

By defining the extended set of constitutive internal variables as $\boldsymbol{\alpha} = \{\boldsymbol{\varepsilon}^{p}, f^{v}, \eta_{\mu}, \tau_{\mu}^{\mathrm{eq}}, \bar{\varepsilon}_{\mu}^{p}\}$, the numerical integration scheme described in Section 6.3 can be similarly adopted. In particular, the integration of the visco-plastic flow rule (see Equation (6.146)) with an implicit exponential map integrator, and the integration of both micro-scale accumulated plastic strain (see Equation (6.147)) and void volume fraction (see Equation (6.148)) evolution laws with an implicit Euler scheme, renders a fully implicit computational implementation whose constitutive state update and computation of consistent tangent modulus are performed in the infinitesimal strains functional format, being the required finite strains extension purely kinematical.

Given that the formulation of the extended visco-elastic-visco-plastic constitutive model must still be validated against a proper set of experimental results, and that developments regarding the adopted yield function and the void volume fraction evolution law are still being investigated, the numerical derivation of both constitutive state update and consistent tangent modulus is out of scope of the present thesis.

6.6.6 Preliminary numerical assessment

To show the behavior of the extended visco-elastic-visco-plastic constitutive model accounting for rubber particle internal cavitation, a simple preliminary numerical assessment is presented in what follows. The same computational setting described in Section 6.5.1 is considered, but the cylindrical specimen is subjected to a total tensile displacement (rather than compressive) consistent with the phenomenon of rubber particle internal cavitation.

Given the illustrative purposes of this numerical assessment, the same material properties calibrated and summarized in Table 6.2 are adopted here. To avoid the calibration of the parameters associated with the void nucleation rate (f_N, ε_N, s_N), see Equation (6.133)), the associated constitutive law is set to zero, $\dot{f}_N^v = 0$, and different values of the initial void volume fraction, $f_0^v = f^v(t=0)$, are prescribed instead.

Figure 6.18 shows the numerically predicted true stress-true strain tensile response for different values of the initial void volume fraction, $f_0^v \in [0.0, 0.05, 0.1, 0.15]$. For the particular case of $f_0^v = 0.0$ (and $\dot{f}_N^v = 0$), the model does not account for internal cavitation ($f^v = 0$) and the visco-plastic flow is purely deviatoric. A distinct response is obtained for $f_0^v > 0$, where both void volume fraction and volumetric visco-plastic flow evolve in the post-yielding state. In consistency with the constitutive formulation, the volumetric visco-plastic strain rate increases with the void volume fraction, and the void volume fraction strain rate increases with the volumetric visco-plastic strain rate (see Figures 6.18(b) and 6.18(c)). In spite of the increased energy dissipation through (volumetric) visco-plastic flow, the void volume fraction stemming from the rubber particles internal cavitation lowers the yield stress and the strain hardening ability of the (porous) amorphous thermoplastic (see Figure 6.18(a). The suitable balance between both counteracting mechanics must be therefore properly accounted for when optimizing the performance of rubber toughened amorphous thermoplastic blends.

6.7 Conclusions

This contribution proposes a novel visco-elastic-visco-plastic constitutive model to predict the finite strain mechanical behavior of amorphous thermoplastics operating below the glass transition temperature at low strain rates compatible with isothermal deformation conditions.

The model is formulated within the framework of thermodynamics with internal variables and accounts for three main constitutive ingredients: (1) a visco-elastic generalized Maxwell model composed of a (rate-independent) elastic spring and n_V (rate-dependent) visco-elastic Maxwell elements, (2) a (rate-dependent) visco-plastic Eyring dashpot, and (3) a plasticity induced (nonlinear) hardening spring. These components and the underlying constitutive laws can capture the intrinsic behavior of ductile amorphous thermoplastics, generally characterized by an initial approximately linear elastic stage, a pre-yield nonlinear visco-elastic stage, and a post-yield visco-plastic stage exhibiting both strain softening and strain hardening phenomena. This is clearly demonstrated by the close agreement between the constitutive model's numerical predictions and the uniaxial compressive experimental results available in the literature for polycarbonate under several temperatures and strain rates.

From a computational point of view, both constitutive state update and consistent tangent modulus required for a suitable fully implicit implementation are properly established and described. It is shown that the constitutive problem can be conveniently reduced to a single (scalar) visco-plastic viscosity nonlinear residual function, rendering a simple but highly efficient implementation by means of the Newton-Raphson Method. In addition, a two-stage optimization-based procedure is proposed to calibrate the constitutive model's material properties based on uniaxial compression tests at different temperatures and strain rates. This is only possible due to the distinctive parametric behavior of the model, where the material properties have a well-defined physical influence on each stage of the intrinsic visco-elastic-visco-plastic material response.

The constitutive model is further extended to account for the phenomenon of rubber particle internal cavitation arising in the finite deformation of rubber-toughened amorphous thermoplastics. This enriches the constitutive model by introducing a volumetric component in visco-plastic flow rule and incorporating damage in the form of nucleation and growth of voids. Preliminary numerical results show the expected increase of energy dissipation through visco-plastic flow and the decrease of the amorphous thermoplastics yield stress due to the presence of voids.



Figure 6.18: Numerical assessment of extended visco-elastic-visco-plastic constitutive model accounting for rubber particle internal cavitation for $\dot{\varepsilon} = 0.001\,\text{s}^{-1}$ at $T = 25°\text{C}$ and different values of initial void volume fraction, f_0^v: (a) True stress-true strain tensile response; (b) Void volume fraction evolution; (c) Volumetric logarithmic plastic strain. Constitutive material properties are provided in Table 6.2.

Page intentionally left blank

Chapter 7
Conclusions and Future Research

7.1 Conclusions and final remarks

The main focus of this thesis is the development of a state-of-the-art Integrated Computational Materials Engineering (ICME) framework to design and optimize amorphous thermoplastic blends exhibiting a particulate morphology. Without any loss of generality, particular focus is given to PC/ABS, one of the most successful commercial polymer blends composed of Acrylonitrile-Butadiene-Styrene (ABS) particles embedded in a polycarbonate (PC) matrix. A detailed characterization of this polymer blend (see Section 1.2.1) demonstrates that an advanced optimization procedure involves the exploration of a high dimensional engineering design space, which accounts for numerous chemical attributes, processing conditions, a highly nonlinear thermomechanical behavior and distinct microstructural mechanisms. To counter the so-called curse of dimensionality, the unified data-driven framework for the design and modeling of materials (see Section 1.2.2) proposed by Bessa and coworkers (Bessa et al., 2017) is adopted as an essential numerical tool to achieve the established goals. Such a quest demands the proper development of several computational methods and motivates three major challenges addressed in this thesis (see Section 1.2.3):

1. The efficient computational generation of particle-reinforced materials' representative volume elements (RVEs) compliant with a broad spectrum of microstructural descriptors;

2. The computation of large material response databases through accurate and fast computational homogenization of heterogeneous materials' high-fidelity RVEs;

3. The accurate description of the finite strain nonlinear thermomechanical behavior of amorphous thermoplastics through the development of suitable constitutive models.

To provide a suitable theoretical background to the different contributions developed throughout this thesis, a preliminary overview over the fundamentals of continuum mechanics and first-order multi-scale modeling is included (see Chapter 2). In what follows, the main contributions to each of the aforementioned challenges are outlined. These lay a suitable basis to perform a critical assessment of the addressed topics that still need further investigation, as well as to discuss major challenges to be tackled in future research.

Concerning the first challenge, a new computational generation method for particle-reinforced materials, coined AMINO (Adaptive Multi-temperature Isokinetic Method), is proposed (see Chapter 3). It can be classified as a geometrical generation method and is formulated in an (explicit) time-driven molecular dynamics scheme. Given an initial configuration of particles, which is generally illegal, the differential equations of motion are incrementally solved to update the particles' positions and velocities by assuming interaction forces that are proportional to the intersection length between adjacent particles. Given the significant computational cost associated with the detection of particles' intersection, an efficient coupling between the well-known cell list and Verlet list methods is adopted. To detect and compute the intersection length between general convex particles, the Gilbert-Johnson-Keerthi (GJK) distance algorithm and the concept of the Minkowski difference between two convex shapes are explored. In addition, the high efficiency of the proposed

method stems from two distinctive numerical features, namely, an adaptive time integration scheme and a multi-temperature isokinetic thermostat. These approaches are developed to accelerate the convergence towards a legal configuration by maximizing the integration time step and the temperature of the isokinetic thermostat, both subject to convergence constraints, and to avoid cumbersome calibration procedures. A simple procedure is also devised to account and enforce the microstructure periodicity properly. In terms of geometrical parametrization, AMINO can effectively deal with any number of particulate material phases and several types of convex particles (e.g., disks, ellipses, spheres, ellipsoids, cylinders), and the microstructure descriptors may be supplied either as fixed prescribed values or as known statistical distributions. Extensive numerical applications demonstrate that AMINO can efficiently generate RVEs accounting for different particulate phases under a broad spectrum of number of particles, volume fractions and microstructure descriptors. No signs of numerical instabilities or spurious configurations (e.g., clustered, partially ordered) were detected throughout the numerical assessment, which further evidences the robustness of the developed numerical approaches. In addition, suitable statistical functions demonstrate the close resemblance between experimental micrographs and RVEs computationally generated from the extracted microstructure descriptors. It is also illustrated how AMINO can be coupled with the well-known RSA method to generate PC/ABS RVEs accounting for the rubber particles embedded in the ABS particles. The preliminary analysis demonstrates the excellent performance of AMINO in a data-driven framework for PC/ABS, being able to generate thousands of particle-reinforced materials RVEs in a completely non-supervised way. Nonetheless, the generation of a large database with three-dimensional RVEs involving complex microstructure descriptors (e.g., a high number of particles, highly elongated particles), may still demand considerable computational resources.

Regarding the second challenge, the recent family of so-called clustering-based reduced-order models (CROMs) is adopted as a promising approach to perform accurate and efficient multi-scale analyses based on computational homogenization (see Chapter 4). Particular emphasis is given to the Self-consistent Clustering Analysis (SCA) method, the pioneering CROM proposed by Liu and coworkers (Liu et al., 2016). Based on fundamental concepts of micromechanics, the Lippmann-Schwinger integral (quasi-static) equilibrium equation is thoroughly and systematically derived under both infinitesimal and finite strains. This sets the stage to establish and gain relevant insights into the clustered Lippmann-Schwinger integral equilibrium underlying the SCA's formulation, namely concerning the nature of homogeneous far-field strain tensor, the proper handling of the Green operator singularity at the zero frequency, and additional terms arising due to the incremental update of the reference material's properties. Clustering adaptivity is introduced for the first time in such a framework, enhancing the accuracy of CROMs when predicting localized phenomena such as shear plastic yielding and damage while keeping a low computational cost. In contrast with the static nature of most CROMs, where the clustering-based domain decomposition is solely defined by a preliminary offline-stage, the coined Adaptive CROMs (ACROMs) allows the clustering to evolve dynamically throughout the actual problem solution. Several complementary procedures are further proposed to improve the overall performance of the adaptivity process, namely an adaptive clustering solution rewinding procedure relevant to handling path-dependent constitutive behavior. The coined Adaptive Self-consistent Clustering Analysis (ASCA) method is shown to deliver more accurate results than its static counterpart in the numerical analysis of a particle-matrix composite where highly localized plasticity takes place. Most importantly, such results are achieved with a lower or similar computational cost, thus maintaining the crucial balance between accuracy and efficiency. Having noticed that the finite strain extension of the SCA method proposed by Yu and coworkers (Yu et al., 2019) assumes an additive decomposition of the deformation gradient, an alternative extension is proposed that is compatible with multiplicative kinematics. Besides the multiplicative

decomposition-based loading incrementation to enforce macro-scale strain constraints, the numerical solution of the micro-scale equilibrium problem is described in great detail, namely: (i) the formulation of the clustered Lippmann-Schwinger equilibrium residuals and the required Newton-Raphson linearization, (ii) the computation of the homogenized material response, and (iii) the computation of the CRVE homogenized consistent tangent modulus. In addition, several relevant aspects associated with the offline-stage are addressed, among which a new definition of the fourth-order local elastic strain concentration tensor based on the elastic material logarithmic strain tensor and the associated geometrical nonlinearity with respect to the magnitude of the orthogonal loadings. Numerical analyses are performed over an elasto-plastic particle–matrix composite subject to several macro-scale (finite) strain-driven loadings and keeping the reference elastic material's properties constant throughout the deformation path. These analyses render important results with respect to the influence of the reference material's properties on the predicted material response. For instance, the results suggest that the reference material's Young modulus is smooth and associated with the 'stiffness' of the numerical predictions, being a sufficiently stiff reference material required to get a physically acceptable and converged solution of the equilibrium problem. Despite the success of the regression-based self-consistent scheme under infinitesimal strains, the development of an accurate and robust self-consistent scheme compatible with the proposed finite strain SCA under multiplicative kinematics is still under investigation. It is also remarked that the FFT-based homogenization basic scheme originally proposed by Moulinec and Suquet (Moulinec and Suquet, 1994) is adopted to perform the offline-stage DNS elastic (infinitesimal strains) or hyperelastic (finite strains) analyses and a highly efficient implementation strategy based on Hadamard operations is proposed. The same approach can be adopted to compute the Green operator underlying the definition of the so-called cluster interaction tensors arising in the SCA's formulation. Although several numerical applications provide a first demonstration of the developed methods, it is fundamental that further validation involving more complex scenarios (e.g., non-monotonic loading paths, constitutive models incorporating damage mechanisms) is performed. Indeed, building a PC/ABS high-fidelity material response database demands accurate finite strain SCA analyses under a broad spectrum of loading cases as well as robust adaptivity procedures to properly handle the underlying damage mechanisms, such as shear yielding, crazing and rubber particle internal cavitation.

It is also worth mentioning that a first-of-its-kind software name CRATE (Clustering-based Nonlinear Analysis of Materials) is fully designed and developed to perform accurate and efficient multi-scale nonlinear analyses of heterogeneous materials based on a coupling between first-order computational homogenization and clustering-based reduced-order models (see Chapter 5). This program will soon be available open source as one of the outputs of this thesis so that it can serve as a basis for development and/or a computational tool for any researcher interested in such a multi-scale modeling approach. The underlying object-oriented design and computational implementation are thoroughly described to support the software release.

With respect to the third challenge, a visco-elastic-visco-plastic constitutive model is formulated to describe the finite strain thermomechanical behavior of amorphous thermoplastics operating below the glass transition temperature under isothermal deformation conditions (see Chapter 6). The constitutive formulation is presented within the framework of thermodynamics with internal variables and incorporates three main constitutive ingredients: (i) a (rate-dependent) visco-elastic generalized Maxwell model accounting for multiple relaxation modes, (ii) a (rate-dependent) visco-plastic Eyring dashpot, and (iii) a plasticity-induced (nonlinear) hardening spring. The model accounts for the intrinsic dependencies on temperature, strain-rate and pressure, as well as a distinctive parametric behavior where a reasonable number of material properties have a well-defined physical influence on the predicted response. From a computational point of view, a fully implicit

implementation is adopted and both constitutive state update and consistent tangent modulus are thoroughly derived accordingly. The adoption of the spatial logarithmic strain tensor as the elastic kinematic variable, the assumption of elasto-plastic isotropy, and the numerical integration of the visco-plastic constitutive law by means of an implicit exponential map, render an incremental visco-plastc flow rule that shares the same functional format of the implicit elastic predictor/return mapping algorithms of infinitesimal strains elasto-plasticity. As a consequence, the constitutive model fits into a general class of isotropic hyperelastic-based constitutive models whose finite strain extension is purely kinematical. Furthermore, it is shown that the constitutive problem can be conveniently reduced to a single (scalar) visco-plastic viscosity nonlinear residual function, rendering a simple but highly efficient implementation by means of the Newton-Raphson Method. A two-stage optimization procedure is also proposed to calibrate the constitutive model's material properties based on uniaxial compression tests at different temperatures and strain rates. Considering a uniaxial compression test to characterize the intrinsic behavior of ductile amorphous thermoplastics, it is demonstrated that the constitutive model is able to capture the different stages of deformation, namely an initial (approximately) linear elastic stage, a pre-yielding nonlinear visco-elastic stage, and a post-yielding stage exhibiting both strain softening and strain hardening phenomena. A close agreement with several experimental results available in the literature is obtained for PC under several temperatures and strain rates, with the model exhibiting a good generalization beyond the experimental responses used for calibration. Besides the shear yielding mechanism already accounted for, the constitutive model is further extended to incorporate the phenomenon of rubber particle internal cavitation that plays a major role in the finite deformation of rubber-toughened amorphous thermoplastics such as the ABS. This extension is performed by a suitable coupling with the well-known GTN model for porous materials and includes damage in the form of nucleation and growth of voids. Preliminary numerical results under uniaxial tension show the expected decrease of yield stress and the increase of energy dissipation through visco-plastic flow due to the presence of voids. Despite the promising results, the accuracy of the constitutive model must still be further validated under distinct multi-axial loading states and the mechanism of crazing needs to be incorporated as well. These and other relevant developments are conveniently discussed in the following section.

Due to the limited time scope of the present thesis, along with the topics that still need to be further investigated, the actual integration of the developed methods in a unified computational tool, initially taken as a fourth and last challenge, could not be accomplished. Nonetheless, it is believed that a solid step has been taken towards the ultimate goal of this thesis and that important foundations are established for further developments. Moreover, it is worth highlighting that the computational methodologies and resources arising as the outcome of this thesis may certainly be useful to aid the design and optimization of many other advanced materials of interest in both scientific and industrial contexts.

7.2 Future research and challenges

Despite the research effort placed on the different topics covered in this thesis, the ultimate quest to establish an effective ICME framework to design and optimize amorphous thermoplastic blends is still far from over. This motivates the following brief discussion on the current issues that are still being investigated and on additional challenges to be addressed in future research.

Extensive numerical applications and comparisons with experimental micrographs have already demonstrated that AMINO is a powerful computational tool to generate high-fidelity RVEs of particle-reinforced materials. Nonetheless, the flexibility of the proposed method can

still be further enhanced by incorporating the suitable handling of non-convex particles that may potentially arise in materials of interest. Suitable coupling with other generation methods, such as the one described with the RSA method, can also be devised to generate more complex microstructures. In terms of computational performance, the development of more efficient intersection detection algorithms is crucial to reducing the overall computational cost of AMINO. New approaches can also be pursued to break out of jammed configurations, a particularly important issue when attempting to generate microstructures with particulate volume fractions close to the (often unknown) maximum packing density.

In order to maximize the performance and applicability of the SCA method under finite strains, three aspects are sorted by relevance as follows. In the first place, a robust self-consistent scheme compatible with the multiplicative decomposition of the deformation gradient must be developed. Given the influence of the reference material's properties on the accuracy and convergence of the numerical predictions, such development is mandatory to adopt the SCA method as a trustworthy computational tool. In the second place, new strategies must be devised to alleviate the costs associated with the computation of the cluster interaction tensors, both in the offline-stage and in the online-stage (clustering adaptivity). The computation of such fourth-order tensors may actually be considered the main bottleneck in terms of computational cost, namely when a high number of clusters is required to achieve the desired level of accuracy. Last but not least, the performance of the proposed ASCA formulation must still be assessed under more challenging scenarios involving more complex microstructures, non-monotonic loading paths, and constitutive models that incorporate damage mechanisms and failure criteria. The advantage of highly parallel computational architectures can also be taken through parallelization of the material clusters state update as well as parallelization of the cluster interaction tensors computation. Other highly relevant challenges include the accurate treatment of interface phenomena and the proper incorporation of multi-physics in the adopted clustering-based reduced-order modeling framework.

Regarding the constitutive modeling of amorphous thermoplastics, the formulated constitutive model is believed to provide a solid basis for further developments. Among these, it is possible to highlight the incorporation of the mechanism of crazing, often preceding the fracture of amorphous thermoplastics, as well as the enhancement of the void nucleation and growth constitutive laws based on existing rubber particle internal cavitation physical models. Of no less importance is the integration of multiple visco-plastic relaxation modes and the extension of the model to a fully thermomechanical equilibrium framework, both pertinent when predicting the behavior from medium-to-high strain rates and/or in applications where the temperature evolution must be properly accounted for. Experimental tests must also be performed under different multi-axial stress states, namely with specimens that promote distinct triaxialities and that exhibit diverse notched geometries. These may well provide important insights and hints to improve the constitutive model's accuracy and, most importantly, its applicability in terms of engineering practice.

Page intentionally left blank

Bibliography

Abraham, S. J., Dinaharan, I., Selvam, J. D. R., and Akinlabi, E. T. (2019). Microstructural Characterization and Tensile Behavior of Rutile (TiO2)-Reinforced AA6063 Aluminum Matrix Composites Prepared by Friction Stir Processing. *Acta Metallurgica Sinica (English Letters)*, 32(1):52–62.

Abu Al-Rub, R. K., Tehrani, A. H., and Darabi, M. K. (2015). Application of a large deformation nonlinear-viscoelastic viscoplastic viscodamage constitutive model to polymers and their composites. *International Journal of Damage Mechanics*, 24(2):198–244.

Ainsworth, M., Kelly, D. W., Sloan, I. H., and Wang, S. L. (1997). Post-processing with computable error bounds for the finite element approximation of a nonlinear heat conduction problem. *IMA Journal of Numerical Analysis*, 17(4):547–561.

Ainsworth, M. and Oden, J. T. (1993). A unified approach to a posteriori error estimation using element residual methods. *Numerische Mathematik*, 65(1):23–50.

Ainsworth, M. and Oden, J. T. (2000). *A Posteriori Error Estimation in Finite Element Analysis*. John Wiley & Sons, Ltd.

Ainsworth, M. and Rankin, R. (2012). Guaranteed computable bounds on quantities of interest in finite element computations. *International Journal for Numerical Methods in Engineering*, 89(13):1605–1634.

Akil, H., Martone, M. E., and Essen, D. C. V. (2011). Challenges and Opportunities in Mining Neuroscience Data. *Science*, 331(6018):708–712.

Altendorf, H., Jeulin, D., and Willot, F. (2014). Influence of the fiber geometry on the macroscopic elastic and thermal properties. *International Journal of Solids and Structures*, 51(23):3807–3822.

Amiri-Rad, A., Pastukhov, L. V., Govaert, L. E., and van Dommelen, J. A. W. (2019). An anisotropic viscoelastic-viscoplastic model for short-fiber composites. *Mechanics of Materials*, 137:103141.

Anand, L. and Ames, N. M. (2006). On modeling the micro-indentation response of an amorphous polymer. *International Journal of Plasticity*, 22(6):1123–1170.

Anand, L., Ames, N. M., Srivastava, V., and Chester, S. A. (2009). A thermo-mechanically coupled theory for large deformations of amorphous polymers. Part I: Formulation. *International Journal of Plasticity*, 25(8):1474–1494.

Anand, L. and Gurtin, M. E. (2003). A theory of amorphous solids undergoing large deformations, with application to polymeric glasses. *International Journal of Solids and Structures*, 40(6):1465–1487.

Ankenman, B., Nelson, B. L., and Staum, J. (2009). Stochastic Kriging for Simulation Metamodeling. *Operations Research*, 58(2):371–382.

Arruda, E. M. and Boyce, M. C. (1993). A three-dimensional constitutive model for the large stretch behavior of rubber elastic materials. *Journal of the Mechanics and Physics of Solids*, 41(2):389–412.

Arruda, E. M., Boyce, M. C., and Jayachandran, R. (1995). Effects of strain rate, temperature and thermomechanical coupling on the finite strain deformation of glassy polymers. *Mechanics of Materials*, 19(2):193–212.

Astrid, P., Weiland, S., Willcox, K., and Backx, T. (2008). Missing Point Estimation in Models Described by Proper Orthogonal Decomposition. *Automatic Control, IEEE Transactions on*, 53:2237–2251.

Ayensa-Jiménez, J., Doweidar, M. H., Sanz-Herrera, J. A., and Doblaré, M. (2018). A new reliability-based data-driven approach for noisy experimental data with physical constraints. *Computer Methods in Applied Mechanics and Engineering*, 328:752–774.

Baaijens, F. (1991). Calculation of residual stresses in injection molded products. *Rheologica Acta*, 30(3):284–299.

Babuška, I. (1976). Homogenization and Its Application. Mathematical and Computational Problems. In Hubbard, B., editor, *Numerical Solution of Partial Differential Equations–III*, pages 89–116. Academic Press.

Babuška, I. (1988). The p and h-p Versions of the Finite Element Method: The State of the Art. In Dwoyer, D. L., Hussaini, M. Y., and Voigt, R. G., editors, *Finite Elements*, ICASE/NASA LaRC Series, pages 199–239, New York, NY. Springer.

Babuška, I. and Miller, A. (1984a). The post-processing approach in the finite element method—part 1: Calculation of displacements, stresses and other higher derivatives of the displacements. *International Journal for Numerical Methods in Engineering*, 20(6):1085–1109.

Babuška, I. and Miller, A. (1984b). The post-processing approach in the finite element method—Part 2: The calculation of stress intensity factors. *International Journal for Numerical Methods in Engineering*, 20(6):1111–1129.

Babuška, I. and Miller, A. (1984c). The post-processing approach in the finite element method—Part 3: A posteriori error estimates and adaptive mesh selection. *International Journal for Numerical Methods in Engineering*, 20(12):2311–2324.

Babuška, I. and Rheinboldt, W. C. (1978). A-posteriori error estimates for the finite element method. *International Journal for Numerical Methods in Engineering*, 12(10):1597–1615.

Babuška, I. and Rheinboldt, W. C. (1979). Adaptive approaches and reliability estimations in finite element analysis. *Computer Methods in Applied Mechanics and Engineering*, 17-18:519–540.

Babuška, I., Strouboulis, T., and Upadhyay, C. S. (1994a). A model study of the quality of a posteriori error estimators for linear elliptic problems. Error estimation in the interior of patchwise uniform grids of triangles. *Computer Methods in Applied Mechanics and Engineering*, 114(3):307–378.

Babuška, I., Strouboulis, T., and Upadhyay, C. S. (1997). A Model Study of the Quality of a Posteriori Error Estimators for Finite Element Solutions of Linear Elliptic Problems, with Particular Reference to the Behavior Near the Boundary. *International Journal for Numerical Methods in Engineering*, 40(14):2521–2577.

Babuška, I., Strouboulis, T., Upadhyay, C. S., Gangaraj, S. K., and Copps, K. (1994b). Validation of a posteriori error estimators by numerical approach. *International Journal for Numerical Methods in Engineering*, 37(7):1073–1123.

Babuška, I., Zienkiewicz, O. C., and Oliveira, E. R. D. (1986). *Accuracy Estimates and Adaptive Refinements in Finite Element Computations*. Wiley.

Balzani, D., Scheunemann, L., Brands, D., and Schröder, J. (2014). Construction of two- and three-dimensional statistically similar RVEs for coupled micro-macro simulations. *Computational Mechanics*, 54(5):1269–1284.

Banerjee, S., Carlin, B. P., and Gelfand, A. E. (2014). *Hierarchical Modeling and Analysis for Spatial Data*. CRC Press.

Bank, R. E. and Weiser, A. (1985). Some A Posteriori Error Estimators for Elliptic Partial Differential Equations. *Mathematics of Computation*, 44(170):283–301.

Baradeswaran, A. and Elaya Perumal, A. (2014). Study on mechanical and wear properties of Al 7075/Al2O3/graphite hybrid composites. *Composites Part B: Engineering*, 56:464–471.

Bargmann, S. (2018). Generation of 3D representative volume elements for heterogeneous materials: A review. *Progress in Materials Science*, page 63.

Barrault, M., Maday, Y., Nguyen, N. C., and Patera, A. T. (2004). An 'empirical interpolation' method: Application to efficient reduced-basis discretization of partial differential equations. *Comptes Rendus Mathematique*, 339(9):667–672.

Bärwinkel, S., Seidel, A., Hobeika, S., Hufen, R., Mörl, M., and Altstädt, V. (2016). Morphology Formation in PC/ABS Blends during Thermal Processing and the Effect of the Viscosity Ratio of Blend Partners. *Materials*, 9(8).

Batchelor, G. K. (1974). Transport Properties of Two-Phase Materials with Random Structure. *Annual Review of Fluid Mechanics*, 6(1):227–255.

Bauwens-Crowet, C. (1973). The compression yield behaviour of polymethyl methacrylate over a wide range of temperatures and strain-rates. *Journal of Materials Science*, 8(7):968–979.

Bazant, Z. P. and Lin, F. B. (1988). Non-local yield limit degradation. *International Journal for Numerical Methods in Engineering*, 26:1805–1823.

Bazant, Z. P. and Mazars, J. (1989). *Cracking and Damage*. CRC Press.

Bazant, Z. P. and Pijaudier-Cabot, G. (1988). Nonlocal Continuum Damage, Localization Instability and Convergence. *Journal of Applied Mechanics*, 55(2):287–293.

Becke, A. D. (1993). Density-functional thermochemistry. III. The role of exact exchange. *The Journal of Chemical Physics*, 98(7):5648–5652.

Becker, R. and Rannacher, R. (1996). A feed-back approach to error control in finite element methods: Basic analysis and examples. *East-West Journal of Numerical Mathematics*, 4.

Becker, R. and Rannacher, R. (1997). Weighted A Posteriori Error Control in FE Methods. *Institut für Angwandtle Mathematik Universität Heidelberg*.

Becker, R. and Rannacher, R. (2001). An optimal control approach to a posteriori error estimation in finite element methods. *Acta Numerica*, 10:1–102.

Belytschko, T. (1988). Fission-Fusion Adaptivity in Finite Elements for Nonlinear Dynamics of Shells. Technical report, Northwestern Univ Evanston IL Dept of Civil Engineering.

Belytschko, T., Hughes, T. J., and Burgers, P. (1985). Computational Methods for Transient Analysis. *Journal of Applied Mechanics*, 52:984–984.

Belytschko, T., Liu, W. K., Moran, B., and Elkhodary, K. (2013). *Nonlinear Finite Elements for Continua and Structures*. John Wiley & Sons.

Belytschko, T., Loehnert, S., and Song, J.-H. (2008). Multiscale aggregating discontinuities: A method for circumventing loss of material stability. *International Journal for Numerical Methods in Engineering*, 73(6):869–894.

Belytschko, T. and Song, J.-H. (2010). Coarse-graining of multiscale crack propagation. *International Journal for Numerical Methods in Engineering*, 81(5):537–563.

Belytschko, T. and Tabbara, M. (1993). H-Adaptive finite element methods for dynamic problems, with emphasis on localization. *International Journal for Numerical Methods in Engineering*, 36(24):4245–4265.

Benedetti, A., de Miranda, S., and Ubertini, F. (2006). A posteriori error estimation based on the superconvergent Recovery by Compatibility in Patches. *International Journal for Numerical Methods in Engineering*, 67(1):108–131.

Bennett, C. H. (1972). Serially Deposited Amorphous Aggregates of Hard Spheres. *Journal of Applied Physics*, 43(6):2727–2734.

Benveniste, Y. (1987). A new approach to the application of Mori-Tanaka's theory in composite materials. *Mechanics of Materials*, 6(2):147–157.

Benveniste, Y. and Milton, G. W. (2010a). The effective medium and the average field approximations vis-à-vis the Hashin–Shtrikman bounds. I. The self-consistent scheme in matrix-based composites. *Journal of the Mechanics and Physics of Solids*, 58(7):1026–1038.

Benveniste, Y. and Milton, G. W. (2010b). The effective medium and the average field approximations vis-à-vis the Hashin–Shtrikman bounds. II. The generalized self-consistent scheme in matrix-based composites. *Journal of the Mechanics and Physics of Solids*, 58(7):1039–1056.

Benzerga, A. A. and Besson, J. (2001). Plastic potentials for anisotropic porous solids. *European Journal of Mechanics - A/Solids*, 20(3):397–434.

Benzerga, A. A. and Leblond, J.-B. (2010). Ductile Fracture by Void Growth to Coalescence. In Aref, H. and van der Giessen, E., editors, *Advances in Applied Mechanics*, volume 44 of *Advances in Applied Mechanics*, pages 169–305. Elsevier.

Beran, M. (1971). Application of statistical theories to heterogeneous materials. *physica status solidi (a)*, 6:365–384.

Beran, M. and Molyneux, J. (1966). Use of Classical Variational Principles to Determine Bounds for the Effective Bulk Modulus in Heterogeneous Media. *Quarterly of Applied Mathematics*, 24(2):107–118.

Beran, M. J. (1968). *Statistical Continuum Theories*. Interscience Publishers.

Bergstrom, J. S. (2015). *Mechanics of Solid Polymers: Theory and Computational Modeling*. William Andrew.

Bessa, M., Bostanabad, R., Liu, Z., Hu, A., Apley, D. W., Brinson, C., Chen, W., and Liu, W. K. (2017). A framework for data-driven analysis of materials under uncertainty: Countering the curse of dimensionality. *Computer Methods in Applied Mechanics and Engineering*, 320:633–667.

Binder, K. and Heermann, D. (2010). *Monte Carlo Simulation in Statistical Physics : An Introduction*, volume 80. Springer Science & Business Media.

Bishop, C. M. (2010). *Pattern Recognition and Machine Learning*. Springer, New York, 1st ed. 2006. corr. 2nd printing 2011 edition edition.

Bitencourt, L. A. G., Manzoli, O. L., Prazeres, P. G. C., Rodrigues, E. A., and Bittencourt, T. N. (2015). A coupling technique for non-matching finite element meshes. *Computer Methods in Applied Mechanics and Engineering*, 290:19–44.

Blacker, T. and Belytschko, T. (1994). Superconvergent patch recovery with equilibrium and conjoint interpolant enhancements. *International Journal for Numerical Methods in Engineering*, 37(3):517–536.

Blanco, P., Sánchez, P., de Souza Neto, E., and Feijóo, R. (2014). Variational Foundations and Generalized Unified Theory of RVE-Based Multiscale Models. *Archives of Computational Methods in Engineering*.

Blanco, P., Sánchez, P., de Souza Neto, E., and Feijóo, R. (2016). The Method of Multiscale Virtual Power for the derivation of a second order mechanical model. *Mechanics of Materials*, 99.

Blanco, P. J. and Giusti, S. M. (2014). Thermomechanical Multiscale Constitutive Modeling: Accounting for Microstructural Thermal Effects. *Journal of Elasticity*, 115(1):27–46.

Bonet, J., Gil, A. J., and Wood, R. D. (2016). *Nonlinear Solid Mechanics for Finite Element Analysis: Statics*. Cambridge University Press, Cambridge.

Bornert, M., Stolz, C., and Zaoui, A. (1996). Morphologically representative pattern-based bounding in elasticity. *Journal of the Mechanics and Physics of Solids*, 44(3):307–331.

Boroomand, B. and Zienkiewicz, O. C. (1997a). An improved REP recovery and the effectivity robustness test. *International Journal for Numerical Methods in Engineering*, 40(17):3247–3277.

Boroomand, B. and Zienkiewicz, O. C. (1997b). Recovery by Equilibrium in Patches (rep). *International Journal for Numerical Methods in Engineering*, 40(1):137–164.

Boroomand, B. and Zienkiewicz, O. C. (1998). Recovery procedures in error estimation and adaptivity: Adaptivity in non-linear problems of elasto-plasticity behaviour. In *Aspects of Adaptive Strategies for Large Deformation Problems at Finite Inelastic Strains*, number 47 in Studies in Applied Mechanics. Elsevier, Amsterdam ; New York.

Bosco, E., Kouznetsova, V., Coenen, E., Geers, M., and Salvadori, A. (2014a). A multiscale framework for localizing microstructures towards the onset of macroscopic discontinuity. *Computational Mechanics*, 54.

Bosco, E., Kouznetsova, V., and Geers, M. (2014b). Multi-scale computational homogenization-localization for propagating discontinuities using X-FEM. *International Journal for Numerical Methods in Engineering*, 102(3-4):496–527.

Bostanabad, R., Bui, A. T., Xie, W., Apley, D. W., and Chen, W. (2016). Stochastic microstructure characterization and reconstruction via supervised learning. *Acta Materialia*, 103:89–102.

Bourdin, B., Francfort, G. A., and Marigo, J.-J. (2008). The Variational Approach to Fracture. *Journal of Elasticity*, 91(1):5–148.

Boyaval, S. (2008). Reduced-Basis Approach for Homogenization beyond the Periodic Setting. *Multiscale Modeling & Simulation*, 7(1):466–494.

Boyce, M. C., Parks, D. M., and Argon, A. S. (1988). Large inelastic deformation of glassy polymers. part I: Rate dependent constitutive model. *Mechanics of Materials*, 7(1):15–33.

Brisard, S. and Dormieux, L. (2010). FFT-based methods for the mechanics of composites: A general variational framework. *Computational Materials Science*, 49(3):663–671.

Broughton, J. Q., Abraham, F. F., Bernstein, N., and Kaxiras, E. (1999). Concurrent coupling of length scales: Methodology and application. *Physical Review B*, 60(4):2391–2403.

Brown, T. B., Mann, B., Ryder, N., Subbiah, M., Kaplan, J., Dhariwal, P., Neelakantan, A., Shyam, P., Sastry, G., Askell, A., Agarwal, S., Herbert-Voss, A., Krueger, G., Henighan, T., Child, R., Ramesh, A., Ziegler, D. M., Wu, J., Winter, C., Hesse, C., Chen, M., Sigler, E., Litwin, M., Gray, S., Chess, B., Clark, J., Berner, C., McCandlish, S., Radford, A., Sutskever, I., and Amodei, D. (2020). Language Models are Few-Shot Learners. *arXiv:2005.14165 [cs]*.

Brun, M., Lopez-Pamies, O., and Ponte Castañeda, P. (2007). Homogenization estimates for fiber-reinforced elastomers with periodic microstructures. *International Journal of Solids and Structures*, 44(18):5953–5979.

Brunton, S. L., Proctor, J. L., and Kutz, J. N. (2016). Discovering governing equations from data: Sparse identification of nonlinear dynamical systems. *Proceedings of the National Academy of Sciences*, 113(15):3932–3937.

Buckley, C. P., Dooling, P. J., Harding, J., and Ruiz, C. (2004). Deformation of thermosetting resins at impact rates of strain. Part 2: Constitutive model with rejuvenation. *Journal of the Mechanics and Physics of Solids*, 52(10):2355–2377.

Buckley, C. P. and Jones, D. C. (1995). Glass-rubber constitutive model for amorphous polymers near the glass transition. *Polymer*, 36(17):3301–3312.

Bucknall, C. (1977). *Toughened Plastics*. Materials Science Series. Springer Netherlands.

Bucknall, C. B., Clayton, D., and Keast, W. E. (1972). Rubber-toughening of plastics. *Journal of Materials Science*, 7(12):1443–1453.

Bucknall, C. B., Karpodinis, A., and Zhang, X. C. (1994). A model for particle cavitation in rubber-toughened plastics. *Journal of Materials Science*, 29(13):3377–3383.

Budiansky, B. (1965). On the elastic moduli of some heterogeneous materials. *Journal of the Mechanics and Physics of Solids*, 13(4):223–227.

Buonamici, S., Trimarchi, T., Ruocco, M. G., Reavie, L., Cathelin, S., Mar, B. G., Klinakis, A., Lukyanov, Y., Tseng, J.-C., Sen, F., Gehrie, E., Li, M., Newcomb, E., Zavadil, J., Meruelo, D., Lipp, M., Ibrahim, S., Efstratiadis, A., Zagzag, D., Bromberg, J. S., Dustin, M. L., and Aifantis, I. (2009). CCR7 signalling as an essential regulator of CNS infiltration in T-cell leukaemia. *Nature*, 459(7249):1000–1004.

Burke, K. and Wagner, L. O. (2013). DFT in a nutshell. *International Journal of Quantum Chemistry*, 113(2):96–101.

Burkov, A. (2019). *The Hundred-Page Machine Learning Book*. Andriy Burkov.

Burns, S. J. and Hanley, K. J. (2017). Establishing stable time-steps for DEM simulations of non-collinear planar collisions with linear contact laws: Establishing stable time-steps for DEM simulations of non-collinear planar collisions with linear contact laws. *International Journal for Numerical Methods in Engineering*, 110(2):186–200.

Buryachenko, V. A. (2013). General integral equations of thermoelasticity in micromechanics of composites with imperfectly bonded interfaces. *International Journal of Solids and Structures*, 50(20):3190–3206.

Buryachenko, V. A., Pagano, N. J., Kim, R. Y., and Spowart, J. E. (2003). Quantitative description and numerical simulation of random microstructures of composites and their effective elastic moduli. *International Journal of Solids and Structures*, page 26.

Callister, W. D. and Rethwisch, D. G. (2013). *Materials Science and Engineering: An Introduction*. John Wiley & Sons.

Carey, V. and Carey, G. F. (2011). Flexible patch post-processing recovery strategies for solution enhancement and adaptive mesh refinement. *International Journal for Numerical Methods in Engineering*, 87(1-5):424–436.

Carlsson, G. (2014). Topological pattern recognition for point cloud data. *Acta Numerica*, 23:289–368.

Carstensen, C. and Alberty, J. (2003). Averaging techniques for reliable a posteriori FE-error control in elastoplasticity with hardening. *Computer Methods in Applied Mechanics and Engineering*, 192(11):1435–1450.

Castañeda, P. P. (1991). The effective mechanical properties of nonlinear isotropic composites. *Journal of the Mechanics and Physics of Solids*, 39(1):45–71.

Castañeda, P. P. (1992). New variational principles in plasticity and their application to composite materials. *Journal of the Mechanics and Physics of Solids*, 40(8):1757–1788.

Castañeda, P. P. (1996). Exact second-order estimates for the effective mechanical properties of nonlinear composite materials. *Journal of the Mechanics and Physics of Solids*, 44(6):827–862.

Castañeda, P. P. and Suquet, P. (1997). Nonlinear Composites. In van der Giessen, E. and Wu, T. Y., editors, *Advances in Applied Mechanics*, volume 34, pages 171–302. Elsevier.

Catalanotti, G. (2016). On the generation of RVE-based models of composites reinforced with long fibres or spherical particles. *Composite Structures*, 138:84–95.

Cavaliere, F., Reese, S., and Wulfinghoff, S. (2019). Efficient two–scale simulations of engineering structures using the Hashin–Shtrikman type finite element method. *Computational Mechanics*.

Challier, M., Besson, J., Laiarinandrasana, L., and Piques, R. (2006). Damage and fracture of polyvinylidene fluoride (PVDF) at 20°C: Experiments and modelling. *Engineering Fracture Mechanics*, 73(1):79–90.

Chaparro, L. F. (2011). *Signals and Systems Using MATLAB*. Academic Press.

Chaturantabut, S. and Sorensen, D. (2010). Nonlinear Model Reduction via Discrete Empirical Interpolation. *SIAM Journal on Scientific Computing*, 32(5):2737–2764.

Chatzigeorgiou, G., Javili, A., and Steinmann, P. (2013). Multiscale modelling for composites with energetic interfaces at the micro- or nanoscale. *Mathematics and Mechanics of Solids*, 20.

Chatzigeorgiou, G., Javili, A., and Steinmann, P. (2014). Unified magnetomechanical homogenization framework with application to magnetorheological elastomers. *Mathematics and Mechanics of Solids*, 2.

Chatzigeorgiou, G., Javili, A., and Steinmann, P. (2015). Interface properties influence the effective dielectric constant of composites. *Philosophical Magazine*, 95(28-30):3402–3412.

Chessa, J., Smolinski, P., and Belytschko, T. (2002). The extended finite element method (XFEM) for solidification problems. *International Journal for Numerical Methods in Engineering*, 53(8):1959–1977.

Chinesta, F., Cueto, E., Abisset-Chavanne, E., Duval, J. L., and Khaldi, F. E. (2018). Virtual, Digital and Hybrid Twins: A New Paradigm in Data-Based Engineering and Engineered Data. *Archives of Computational Methods in Engineering*.

Christensen, R. M. and Lo, K. H. (1979). Solutions for effective shear properties in three phase sphere and cylinder models. *Journal of the Mechanics and Physics of Solids*, 27(4):315–330.

Chu, C. C. and Needleman, A. (1980). Void Nucleation Effects in Biaxially Stretched Sheets. *Journal of Engineering Materials and Technology*, 102(3):249–256.

Chung, P. W., Tamma, K. K., and Namburu, R. R. (2001). Asymptotic expansion homogenization for heterogeneous media: Computational issues and applications. *Composites Part A: Applied Science and Manufacturing*, 32(9):1291–1301.

Cigna, G., Lomellini, P., and Merlotti, M. (1989). Impact thermoplastics: Combined role of rubbery phase volume and particle size on toughening efficiency. *Journal of Applied Polymer Science*, 37(6):1527–1540.

Clément, A., Soize, C., and Yvonnet, J. (2012). Computational nonlinear stochastic homogenization using a nonconcurrent multiscale approach for hyperelastic heterogeneous microstructures analysis. *International Journal for Numerical Methods in Engineering*, 91(8):799–824.

Clyne, T. W. (2018). 4.1 An Introductory Overview of Metal Matrix Composites Systems, Types and Developments. In *Comprehensive Composite Materials II*, pages 1–21. Elsevier.

Cocco, A. P., Nelson, G. J., Harris, W. M., Nakajo, A., Myles, T. D., Kiss, A. M., Lombardo, J. J., and Chiu, W. K. S. (2013). Three-dimensional microstructural imaging methods for energy materials. *Physical Chemistry Chemical Physics*, 15(39):16377–16407.

Coenen, E., Kouznetsova, V., Bosco, E., and Geers, M. (2012a). A multi-scale approach to bridge microscale damage and macroscale failure: A nested computational homogenization-localization framework. *International Journal of Fracture*, 178.

Coenen, E. W. C., Kouznetsova, V. G., and Geers, M. G. D. (2012b). Multi-scale continuous–discontinuous framework for computational-homogenization–localization. *Journal of the Mechanics and Physics of Solids*, 60(8):1486–1507.

Coenen, E. W. C., Kouznetsova, V. G., and Geers, M. G. D. (2012c). Novel boundary conditions for strain localization analyses in microstructural volume elements. *International Journal for Numerical Methods in Engineering*, 90(1):1–21.

Cohen, A. J., Mori-Sánchez, P., and Yang, W. (2008). Insights into Current Limitations of Density Functional Theory. *Science*, 321(5890):792–794.

Collyer, A. A., editor (1994). *Rubber Toughened Engineering Plastics*. Springer Netherlands.

Cong, Y., Nezamabadi, S., Zahrouni, H., and Yvonnet, J. (2015). Multiscale computational homogenization of heterogeneous shells at small strains with extensions to finite displacements and buckling. *International Journal for Numerical Methods in Engineering*, 104(4):235–259.

Crespo, J., Latorre, M., and Montáns, F. (2016). WYPIWYG hyperelasticity for isotropic, compressible materials. *Computational Mechanics*, 59.

Criminisi, A., Konukoglu, E., and Shotton, J. (2011). Decision Forests for Classification, Regression, Density Estimation, Manifold Learning and Semi-Supervised Learning. *Microsoft*.

Crisfield, M. A. (1991). *Non-Linear Finite Element Analysis of Solids and Structures*. Wiley, Chichester ; New York.

Cristianini, N. and Shawe-Taylor, J. (2000). *An Introduction to Support Vector Machines and Other Kernel-Based Learning Methods*. Cambridge University Press.

Crouch, R., Oskay, C., and Clay, S. (2013). Multiple spatio-temporal scale modeling of composites subjected to cyclic loading. *Computational Mechanics*, 51(1):93–107.

Cueto, E., González, D., and Alfaro, I. (2016). *Proper Generalized Decompositions*. SpringerBriefs in Applied Sciences and Technology. Springer International Publishing, Cham.

Danas, K., Idiart, M. I., and Castañeda, P. P. (2008). A homogenization-based constitutive model for isotropic viscoplastic porous media. *International Journal of Solids and Structures*, 45(11):3392–3409.

Darwin, C. (1998). *The Origin of Species*. Oxford University Press.

de Borst, R., Pamin, J., Peerlings, R. H. J., and Sluys, L. J. (1995). On gradient-enhanced damage and plasticity models for failure in quasi-brittle and frictional materials. *Computational Mechanics*, 17(1):130–141.

De Borst, R., Sluys, L. J., Muhlhaus, H. B., and Pamin, J. (1993). Fundamental issues in finite element analyses of localization of deformation. *Engineering Computations 10(2), 99-121. (1993)*.

de Carvalho, M. V., de Bortoli, D., and Andrade Pires, F. M. (2022). Consistent modeling of the coupling between crystallographic slip and martensitic phase transformation for mechanically induced loadings. *International Journal for Numerical Methods in Engineering*, n/a(n/a).

de Geus, T., Vondřejc, J., Zeman, J., Peerlings, R., and Geers, M. (2017). Finite strain FFT-based non-linear solvers made simple. *Computer Methods in Applied Mechanics and Engineering*, 318:412–430.

De Lorenzis, L. and Wriggers, P. (2013). Computational homogenization of rubber friction on rough rigid surfaces. *Computational Materials Science*, 77:264–280.

de Souza Neto, E., Blanco, P., Sánchez, P., and Feijóo, R. (2014). An RVE-based mutiscale theory of solids with micro-scale inertia and body force effects. *Mechanics of Materials*, 80.

de Souza Neto, E. and Feijóo, R. (2006). EA de Souza Neto, RA Feijoo. Variational Foundations of Multi-Scale Constitutive Models of Solid: Small and Large Strain Kinematical Formulation. *LNCC R&D Report*.

de Souza Neto, E. and Feijóo, R. (2008). On the equivalence between spatial and material volume averaging of stress in large strain multi-scale solid constitutive models. *Mechanics of Materials*, 40:803–811.

de Souza Neto, E. and Feijóo, R. (2011). Variational foundations of large strain multiscale solid constitutive models: Kinematical formulation. *Advanced Computational Materials Modeling. from Classical to Multi-scale Techniques*, pages 341–378.

De Souza Neto, E., Perić, D., and Owen, D. (1994). A model for elastoplastic damage at finite strains: Algorithmicissues and applications. *Engineering Computations*, 11(3):257–281.

de Souza Neto, E. A., Peri, D., and Owen, D. R. J. (2008). *Computational Methods for Plasticity*. John Wiley & Sons, Ltd, Chichester, UK.

deBotton, G. and Castañeda, P. P. (1993). Elastoplastic constitutive relations for fiber-reinforced solids. *International Journal of Solids and Structures*, 30(14):1865–1890.

deBotton, G. and Oren, T. (2013). Analytical and numerical analyses of the micromechanics of soft fibrous connective tissues. *Biomechanics and Modeling in Mechanobiology*, 12(1):151–166.

deBotton, G. and Shmuel, G. (2009). Mechanics of composites with two families of finitely extensible fibers undergoing large deformations. *Journal of the Mechanics and Physics of Solids*, 57(8):1165–1181.

Dederichs, P. H. and Zeller, R. (1973). Variational treatment of the elastic constants of disordered materials. *Zeitschrift für Physik A Hadrons and nuclei*, 259(2):103–116.

Delogu, F. and Cocco, G. (2005). Molecular dynamics investigation on the role of sliding interfaces and friction in the formation of amorphous phases. *Physical Review B*, 71(14):144108.

Demkowicz, L., Oden, J. T., Rachowicz, W., and Hardy, O. (1989). Toward a universal h-p adaptive finite element strategy, part 1. Constrained approximation and data structure. *Computer Methods in Applied Mechanics and Engineering*, 77(1):79–112.

Díez, P., JoséEgozcue, J., and Huerta, A. (1998). A posteriori error estimation for standard finite element analysis. *Computer Methods in Applied Mechanics and Engineering*, 163(1):141–157.

Díez, P., Ródenas, J. J., and Zienkiewicz, O. C. (2007). Equilibrated patch recovery error estimates: Simple and accurate upper bounds of the error. *International Journal for Numerical Methods in Engineering*, 69(10):2075–2098.

Dinaharan, I., Murugan, N., and Parameswaran, S. (2011). Influence of in situ formed ZrB2 particles on microstructure and mechanical properties of AA6061 metal matrix composites. *Materials Science and Engineering: A*, 528(18):5733–5740.

Dirrenberger, J., Forest, S., and Jeulin, D. (2014). Towards gigantic RVE sizes for 3D stochastic fibrous networks. *International Journal of Solids and Structures*, 51(2):359–376.

Dixon, P. M. (2014). Ripley's K Function. In *Wiley StatsRef: Statistics Reference Online*. American Cancer Society.

Donald, A. M. and Kramer, E. J. (1981). The mechanism for craze-tip advance in glassy polymers. *Philosophical Magazine A*, 43(4):857–870.

Donald, A. M. and Kramer, E. J. (1982). The competition between shear deformation and crazing in glassy polymers. *Journal of Materials Science*, 17(7):1871–1879.

Donev, A., Torquato, S., and Stillinger, F. H. (2005). Neighbor list collision-driven molecular dynamics simulation for nonspherical hard particles. I. Algorithmic details. *Journal of Computational Physics*, 202(2):737–764.

Donev, A., Torquato, S., Stillinger, F. H., and Connelly, R. (2004). Comment on "Jamming at zero temperature and zero applied stress: The epitome of disorder". *Physical Review. E, Statistical, Nonlinear, and Soft Matter Physics*, 70(4 Pt 1):043301; discussion 043302.

Dong, L., Greco, R., and Orsello, G. (1993). Polycarbonate/acrylonitrile-butadiene-styrene blends: 1. Complementary etching techniques for morphology observations. *Polymer*, 34(7):1375–1382.

Drago, A. and Pindera, M.-J. (2007). Micro-macromechanical analysis of heterogeneous materials: Macroscopically homogeneous vs periodic microstructures. *Composites Science and Technology*, 67(6):1243–1263.

Drugan, W. J. and Willis, J. R. (1996). A micromechanics-based nonlocal constitutive equation and estimates of representative volume element size for elastic composites. *Journal of the Mechanics and Physics of Solids*, 44(4):497–524.

Dvorak, G. (2012). *Micromechanics of Composite Materials*. Springer Science & Business Media.

Dvorak, G. J. (1992). Transformation field analysis of inelastic composite materials. *Proceedings of the Royal Society of London. Series A: Mathematical and Physical Sciences*, 437(1900):311–327.

Edwards, S. F. and Vilgis, T. (1986). The effect of entanglements in rubber elasticity. *Polymer*, 27(4):483–492.

Eisenlohr, P., Diehl, M., Lebensohn, R. A., and Roters, F. (2013). A spectral method solution to crystal elasto-viscoplasticity at finite strains. *International Journal of Plasticity*, 46:37–53.

El Moumen, A., Kanit, T., Imad, A., and El Minor, H. (2015). Effect of reinforcement shape on physical properties and representative volume element of particles-reinforced composites: Statistical and numerical approaches. *Mechanics of Materials*, 83:1–16.

Engquist, B., Li, X., Ren, W., and Vanden-Eijnden, E. (2007). Heterogeneous Multiscale Methods: A Review. *Communications in Computational Physics*, 2:367–450.

Eriksson, K. and Johnson, C. (1988). An Adaptive Finite Element Method for Linear Elliptic Problems. *Mathematics of Computation*, 50(182):361–383.

Eshelby, J. D. and Peierls, R. E. (1957). The determination of the elastic field of an ellipsoidal inclusion, and related problems. *Proceedings of the Royal Society of London. Series A. Mathematical and Physical Sciences*, 241(1226):376–396.

Eyring, H. (1936). Viscosity, Plasticity, and Diffusion as Examples of Absolute Reaction Rates. *The Journal of Chemical Physics*, 4(4):283–291.

Fadavi Boostani, A., Tahamtan, S., Jiang, Z., Wei, D., Yazdani, S., Azari Khosroshahi, R., Taherzadeh Mousavian, R., Xu, J., Zhang, X., and Gong, D. (2015). Enhanced tensile properties of aluminium matrix composites reinforced with graphene encapsulated SiC nanoparticles. *Composites Part A: Applied Science and Manufacturing*, 68:155–163.

Fang, K.-T., Li, R., and Sudjianto, A. (2005). *Design and Modeling for Computer Experiments*. CRC Press.

Farhat, C., Avery, P., Chapman, T., and Cortial, J. (2014). Dimensional reduction of nonlinear finite element dynamic models with finite rotations and energy-based mesh sampling and weighting for computational efficiency. *International Journal for Numerical Methods in Engineering*, 98.

Feng, Y. T., Han, K., and Owen, D. R. J. (2002). An Advancing Front Packing of Polygons, Ellipses and Spheres. In *Discrete Element Methods*, pages 93–98, Santa Fe, New Mexico, United States. American Society of Civil Engineers.

Feng, Y. T., Han, K., and Owen, D. R. J. (2003). Filling domains with disks: An advancing front approach. *International Journal for Numerical Methods in Engineering*, 56(5):699–713.

Feyel, F. (1998). *Application Du Calcul Parallèle Aux Modèles à Grand Nombre de Variables Internes*. PhD Thesis, École Nationale Supérieure des Mines de Paris.

Feyel, F. (2003). A multilevel finite element method (FE2) to describe the response of highly non-linear structures using generalized continua. *Computer Methods in Applied Mechanics and Engineering*, 192(28):3233–3244.

Feyel, F. and Chaboche, J.-L. (2000). FE2 multiscale approach for modelling the elastoviscoplastic behaviour of long fibre SiC/Ti composite materials. *Computer Methods in Applied Mechanics and Engineering*, 183(3):309–330.

Fish, J. (2009). *Multiscale Methods: Bridging the Scales in Science and Engineering*. OUP Oxford.

Fish, J., Filonova, V., and Fafalis, D. (2015). Computational continua revisited. *International Journal for Numerical Methods in Engineering*, 102(3-4):332–378.

Fish, J. and Kuznetsov, S. (2010). Computational continua. *International Journal for Numerical Methods in Engineering*, 84(7):774–802.

Fish, J., Shek, K., Pandheeradi, M., and Shephard, M. S. (1997). Computational plasticity for composite structures based on mathematical homogenization: Theory and practice. *Computer Methods in Applied Mechanics and Engineering*, 148(1):53–73.

Folgar, F. and Tucker, C. L. (1984). Orientation Behavior of Fibers in Concentrated Suspensions. *Journal of Reinforced Plastics and Composites*, 3(2):98–119.

Forgy, E. W. (1965). Cluster analysis of multivariate data : Efficiency versus interpretability of classifications. *Biometrics*, 21:768–769.

Francfort, G. A. and Marigo, J.-J. (1998). Revisiting brittle fracture as an energy minimization problem. *Journal of Mechanics Physics of Solids*, 46:1319–1342.

Frenkel, D. and Smit, B. (2001). *Understanding Molecular Simulation: From Algorithms to Applications*. Elsevier.

Fritzen, F. and Böhlke, T. (2010). Influence of the type of boundary conditions on the numerical properties of unit cell problems. *Technische Mechanik*, 30:354–363.

Fritzen, F. and Kochmann, D. M. (2014). Material instability-induced extreme damping in composites: A computational study. *International Journal of Solids and Structures*, 51(23):4101–4112.

Fu, S.-Y., Lauke, B., and Mai, Y. W. (2019). *Science and Engineering of Short Fibre-Reinforced Polymer Composites*. Elsevier.

Fullwood, D. T., Niezgoda, S. R., and Kalidindi, S. R. (2008). Microstructure reconstructions from 2-point statistics using phase-recovery algorithms. *Acta Materialia*, page 7.

Furukawa, K., Imai, K., and Kurashige, M. (2000). Simulated effect of box size and wall on porosity of random packings of spherical particles. *Acta Mechanica*, 140(3):219–231.

Galli, M., Cugnoni, J., and Botsis, J. (2012). Numerical and statistical estimates of the representative volume element of elastoplastic random composites. *European Journal of Mechanics - A/Solids*, 33:31–38.

Gallimard, L., Ladevèze, P., and Pelle, J. (1996). Error estimation and adaptivity in elastoplasticity. *International Journal for Numerical Methods in Engineering*, 39(2):189–217.

Gao, J., Shakoor, M., Domel, G., Merzkirch, M., Zhou, G., Zeng, D., Su, X., and Liu, W. K. (2020). Predictive multiscale modeling for Unidirectional Carbon Fiber Reinforced Polymers. *Composites Science and Technology*, 186:107922.

Geerlings, P., Proft, F., and Langenaeker, W. (2003). Conceptual Density Functional Theory. *Chem. Rev.*, 103.

Geers, M., Kouznetsova, V., and Brekelmans, W. (2003). MultiScale First-Order and Second-Order Computational Homogenization of Microstructures towards Continua. *International Journal for Multiscale Computational Engineering*, 1:371–386.

Geers, M., Kouznetsova, V., and Brekelmans, W. (2010). Multi-scale computational homogenization: Trends and challenges. *Journal of Computational and Applied Mathematics*, 234(7):2175–2182.

Geers, M. G. D., Kouznetsova, V. G., Matouš, K., and Yvonnet, J. (2017). Homogenization Methods and Multiscale Modeling: Nonlinear Problems. In *Encyclopedia of Computational Mechanics Second Edition*, pages 1–34. American Cancer Society.

Geers, M. G. D., R. Borst, D., Brekelmans, W. a. M., and Peerlings, R. H. J. (1998). Strain-based transient-gradient damage model for failure analyses. *Computer Methods in Applied Mechanics and Engineering*, 160(1-2):133–153.

Gent, A. N. and Wang, C. (1991). Fracture mechanics and cavitation in rubber-like solids. *Journal of Materials Science*, 26(12):3392–3395.

Ghosh, S., Bai, J., and Raghavan, P. (2007). Concurrent multi-level model for damage evolution in microstructurally debonding composites. *Mechanics of Materials*, 39(3):241–266.

Ghosh, S., Lee, K., and Moorthy, S. (1995). Multiple scale analysis of heterogeneous elastic structures using homogenization theory and voronoi cell finite element method. *International Journal of Solids and Structures*, 32(1):27–62.

Ghosh, S. and Moorthy, S. (1995). Elastic-plastic analysis of arbitrary heterogeneous materials with the Voronoi Cell finite element method. *Computer Methods in Applied Mechanics and Engineering*, 121(1):373–409.

Ghossein, E. and Lévesque, M. (2013). Random generation of periodic hard ellipsoids based on molecular dynamics: A computationally-efficient algorithm. *Journal of Computational Physics*, 253:471–490.

Ghossein, E. and Lévesque, M. (2014). A comprehensive validation of analytical homogenization models: The case of ellipsoidal particles reinforced composites. *Mechanics of Materials*, 75:135–150.

Gibiansky, L. V. and Torquato, S. (1997). Thermal expansion of isotropic multiphase composites and polycrystals. *Journal of the Mechanics and Physics of Solids*, 45(7):1223–1252.

Gilbert, E., Johnson, D., and Keerthi, S. (1988). A fast procedure for computing the distance between complex objects in three-dimensional space. *IEEE Journal on Robotics and Automation*, 4(2):193–203.

Gitman, I. M., Askes, H., and Sluys, L. J. (2007). Representative volume: Existence and size determination. *Engineering Fracture Mechanics*, 74(16):2518–2534.

Glüge, R. (2013). Generalized boundary conditions on representative volume elements and their use in determining the effective material properties. *Computational Materials Science*, 79:408–416.

Gologanu, M., Leblond, J.-B., and Devaux, J. (1993). Approximate models for ductile metals containing non-spherical voids—Case of axisymmetric prolate ellipsoidal cavities. *Journal of the Mechanics and Physics of Solids*, 41(11):1723–1754.

Gologanu, M., Leblond, J.-B., and Devaux, J. (1994). Approximate Models for Ductile Metals Containing Nonspherical Voids—Case of Axisymmetric Oblate Ellipsoidal Cavities. *Journal of Engineering Materials and Technology*, 116(3):290–297.

Gologanu, M., Leblond, J.-B., and Devaux, J. (2001a). Theoretical models for void coalescence in porous ductile solids. II. Coalescence "in columns". *International Journal of Solids and Structures*, 38(32):5595–5604.

Gologanu, M., Leblond, J.-B., Perrin, G., and Devaux, J. (1997). Recent Extensions of Gurson's Model for Porous Ductile Metals. In Suquet, P., editor, *Continuum Micromechanics*, International Centre for Mechanical Sciences, pages 61–130. Springer, Vienna.

Gologanu, M., Leblond, J.-B., Perrin, G., and Devaux, J. (2001b). Theoretical models for void coalescence in porous ductile solids. I. Coalescence "in layers". *International Journal of Solids and Structures*, 38(32):5581–5594.

González, D., Chinesta, F., and Cueto, E. (2019). Thermodynamically consistent data-driven computational mechanics. *Continuum Mechanics and Thermodynamics*, 31(1):239–253.

Goodfellow, I., Bengio, Y., and Courville, A. (2016). *Deep Learning*. MIT Press.

Govaert, L., Timmermans, P., and Brekelmans, W. (2000). The Influence of Intrinsic Strain Softening on Strain Localization in Polycarbonate: Modeling and Experimental Validation. *Journal of Engineering Materials and Technology-transactions of The Asme - J ENG MATER TECHNOL*, 122.

Greco, R. (1996). Polycarbonate Toughening by ABS. In *Advanced Routes for Polymer Toughening*, number 10 in Polymer Science Library. Elsevier Science, The Netherlands.

Gudimetla, M. R. and Doghri, I. (2017). A finite strain thermodynamically-based constitutive framework coupling viscoelasticity and viscoplasticity with application to glassy polymers. *International Journal of Plasticity*, 98:197–216.

Guedes, J. and Kikuchi, N. (1990). Preprocessing and postprocessing for materials based on the homogenization method with adaptive finite element methods. *Computer Methods in Applied Mechanics and Engineering*, 83(2):143–198.

Guo, B. and Babuška, I. (1986a). The h-p version of the finite element method. *Computational Mechanics*, 1(1):21–41.

Guo, B. and Babuška, I. (1986b). The h-p version of the finite element method. *Computational Mechanics*, 1(3):203–220.

Guo, N. and Zhao, J. (2014). A coupled FEM/DEM approach for hierarchical multiscale modelling of granular media. *International Journal for Numerical Methods in Engineering*, 99(11):789–818.

Guo, T. F. and Cheng, L. (2002). Modeling vapor pressure effects on void rupture and crack growth resistance. *Acta Materialia*, 50(13):3487–3500.

Guo, T. F., Faleskog, J., and Shih, C. F. (2008). Continuum modeling of a porous solid with pressure-sensitive dilatant matrix. *Journal of the Mechanics and Physics of Solids*, 56(6):2188–2212.

Gurson, A. L. (1977). Continuum Theory of Ductile Rupture by Void Nucleation and Growth: Part I—Yield Criteria and Flow Rules for Porous Ductile Media. *Journal of Engineering Materials and Technology*, 99(1):2–15.

Haaf, F., Breuer, H., and Stabenow, J. (1977). Untersuchungen an kautschukmodifiziertem PVC. *Die Angewandte Makromolekulare Chemie*, 58(1):95–119.

Hagan, M. T., Demuth, H. B., and Beale, M. (1996). *Neural Network Design*. PWS Publishing Co., Boston, MA, USA.

Haghshenas, M. (2016). Metal–Matrix Composites. In *Reference Module in Materials Science and Materials Engineering*, page B9780128035818039503. Elsevier.

Han, X., Gao, J., Fleming, M., Xu, C., Xie, W., Meng, S., and Liu, W. K. (2020). Efficient multiscale modeling for woven composites based on self-consistent clustering analysis. *Computer Methods in Applied Mechanics and Engineering*, 364:112929.

Harper, L. T., Qian, C., Turner, T. A., Li, S., and Warrior, N. A. (2012). Representative volume elements for discontinuous carbon fibre composites – Part 2: Determining the critical size. *Composites Science and Technology*, 72(2):204–210.

Hasan, O. A., Boyce, M. C., Li, X. S., and Berko, S. (1993). An investigation of the yield and postyield behavior and corresponding structure of poly(methyl methacrylate). *Journal of Polymer Science Part B: Polymer Physics*, 31(2):185–197.

Hashin, Z. and Shtrikman, S. (1962a). On some variational principles in anisotropic and nonhomogeneous elasticity. *Journal of the Mechanics and Physics of Solids*, 10(4):335–342.

Hashin, Z. and Shtrikman, S. (1962b). A variational approach to the theory of the elastic behaviour of polycrystals. *Journal of the Mechanics and Physics of Solids*, 10(4):343–352.

Hashin, Z. and Shtrikman, S. (1963). A variational approach to the theory of the elastic behaviour of multiphase materials. *Journal of the Mechanics and Physics of Solids*, 11(2):127–140.

Hastie, T., Tibshirani, R., and Friedman, J. (2017). *The Elements of Statistical Learning: Data Mining, Inference, and Prediction, Second Edition*. Springer, New York, NY, 2nd ed. 2009, corr. 9th printing 2017 edition edition.

Haward, R. N., Thackray, G., and Sugden, T. M. (1968). The use of a mathematical model to describe isothermal stress-strain curves in glassy thermoplastics. *Proceedings of the Royal Society of London. Series A. Mathematical and Physical Sciences*, 302(1471):453–472.

Haward, R. N. and Young, R. J. (2012). *Physics of Glassy Polymers*. Springer Netherlands, Dordrecht.

He, C., Gao, J., Li, H., Ge, J., Chen, Y., Liu, J., and Fang, D. (2020). A data-driven self-consistent clustering analysis for the progressive damage behavior of 3D braided composites. *Composite Structures*, 249:112471.

He, D. and Ekere, N. N. (2001). Structure simulation of concentrated suspensions of hard spherical particles. *AIChE Journal*, 47(1):53–59.

Hepburn, D. J. and Ackland, G. J. (2008). Metallic-covalent interatomic potential for carbon in iron. *Physical Review B*, 78(16):165115.

Hernández, J., Oliver, J., Huespe, A., Caicedo, M., and Cante, J. (2014). High-performance model reduction techniques in computational multiscale homogenization. *Computer Methods in Applied Mechanics and Engineering*, 276:149–189.

Hernández, J. A., Caicedo, M. A., and Ferrer, A. (2017). Dimensional hyper-reduction of nonlinear finite element models via empirical cubature. *Computer Methods in Applied Mechanics and Engineering*, 313:687–722.

Herráez, M., Segurado, J., González, C., and Lopes, C. S. (2020). A microstructures generation tool for virtual ply property screening of hybrid composites with high volume fractions of non-circular fibers – VIPER. *Composites Part A: Applied Science and Manufacturing*, 129:105691.

Herve, E. and Zaoui, A. (1993). N-Layered inclusion-based micromechanical modelling. *International Journal of Engineering Science*, 31(1):1–10.

Hill, R. (1952). The Elastic Behaviour of a Crystalline Aggregate. *Proceedings of the Physical Society. Section A*, 65(5):349–354.

Hill, R. (1958). A general theory of uniqueness and stability in elastic-plastic solids. *Journal of the Mechanics and Physics of Solids*, 6(3):236–249.

Hill, R. (1963). Elastic properties of reinforced solids: Some theoretical principles. *Journal of the Mechanics and Physics of Solids*, 11(5):357–372.

Hill, R. (1964a). Theory of mechanical properties of fibre-strengthened materials: I. Elastic behaviour. *Journal of the Mechanics and Physics of Solids*, 12(4):199–212.

Hill, R. (1964b). Theory of mechanical properties of fibre-strengthened materials: II. Inelastic behaviour. *Journal of the Mechanics and Physics of Solids*, 12(4):213–218.

Hill, R. (1965a). Continuum micro-mechanics of elastoplastic polycrystals. *Journal of the Mechanics and Physics of Solids*, 13(2):89–101.

Hill, R. (1965b). A self-consistent mechanics of composite materials. *Journal of the Mechanics and Physics of Solids*, 13(4):213–222.

Hill, R. (1965c). Theory of mechanical properties of fibre-strengthened materials—III. self-consistent model. *Journal of the Mechanics and Physics of Solids*, 13(4):189–198.

Hill, R. (1967). The essential structure of constitutive laws for metal composites and polycrystals. *Journal of the Mechanics and Physics of Solids*, 15(2):79–95.

Hill, R. (1972). On constitutive macro-variables for heterogeneous solids at finite strain. *Proceedings of the Royal Society of London. A. Mathematical and Physical Sciences*, 326(1565):131–147.

Hillerborg, A., Modéer, M., and Petersson, P. E. (1976). Analysis of crack formation and crack growth in concrete by means of fracture mechanics and finite elements. *Cement and Concrete Research*, 6(6):773–781.

Hoang, T. H., Guerich M., and Yvonnet J. (2016). Determining the Size of RVE for Nonlinear Random Composites in an Incremental Computational Homogenization Framework. *Journal of Engineering Mechanics*, 142(5):04016018.

Hobbs, S. Y., Bopp, R. C., and Watkins, V. H. (1983). Toughened nylon resins. *Polymer Engineering & Science*, 23(7):380–389.

Hollister, S. J. and Kikuchi, N. (1992). A comparison of homogenization and standard mechanics analyses for periodic porous composites. *Computational Mechanics*, 10(2):73–95.

Holopainen, S. (2014). Influence of damage on inhomogeneous deformation behavior of amorphous glassy polymers. Modeling and algorithmic implementation in a finite element setting. *Engineering Fracture Mechanics*, 117:28–50.

Holopainen, S. and Barriere, T. (2018). Modeling of mechanical behavior of amorphous solids undergoing fatigue loadings, with application to polymers. *Computers & Structures*, 199:57–73.

Holopainen, S., Barriere, T., Cheng, G., and Kouhia, R. (2017). Continuum approach for modeling fatigue in amorphous glassy polymers. Applications to the investigation of damage-ratcheting interaction in polycarbonate. *International Journal of Plasticity*, 91:109–133.

Holzapfel, G. A. (2000). *Nonlinear Solid Mechanics: A Continuum Approach for Engineering*. Wiley.

Hopfield, J. J. (1982). Neural networks and physical systems with emergent collective computational abilities. *Proceedings of the National Academy of Sciences*, 79(8):2554–2558.

Hori, M. and Nemat-Nasser, S. (1993). Double-inclusion model and overall moduli of multi-phase composites. *Mechanics of Materials*, 14(3):189–206.

Hori, M. and Nemat-Nasser, S. (1998). Universal bounds for effective piezoelectric moduli. *Mechanics of Materials*, 30(1):1–19.

Hori, M. and Yonezawa, F. (1974). Statistical theory of effective electrical, thermal, and magnetic properties of random heterogeneous materials. III. Perturbation treatment of the effective permittivity in completely random heterogeneous materials. *Journal of Mathematical Physics*, 15:2177–2185.

Hori, M. and Yonezawa, F. (1975). Statistical theory of effective electrical, thermal, and magnetic properties of random heterogeneous materials. IV. Effective - medium theory and cumulant expansion method. *Journal of Mathematical Physics*, 16:352–364.

Horstemeyer, M. F. (2012). *Integrated Computational Materials Engineering (ICME) for Metals: Using Multiscale Modeling to Invigorate Engineering Design with Science*. John Wiley & Sons.

Horstemeyer, M. F. (2018). *Integrated Computational Materials Engineering (ICME) for Metals: Concepts and Case Studies*. John Wiley & Sons.

Huang, Y. and Hu, K. X. (1995). A Generalized Self-Consistent Mechanics Method for Solids Containing Elliptical Inclusions. *Journal of Applied Mechanics*, 62(3):566–572.

Huang, Y., Hu, K. X., Wei, X., and Chandra, A. (1994). A generalized self-consistent mechanics method for composite materials with multiphase inclusions. *Journal of the Mechanics and Physics of Solids*, 42(3):491–504.

Huang, Y. and Yi, N. (2010). The Superconvergent Cluster Recovery Method. *Journal of Scientific Computing*, 44(3):301–322.

Huerta, A., Díez, P., Rodrígues-Ferran, A., and Pijaudier-Cabot, G. (1998). Error estimation and adaptive finite element analysis of softening solids. In *Advances in Adaptive Computational Methods in Mechanics*, number 47 in Studies in Applied Mechanics, pages 333–347. Elsevier, Amsterdam ; New York.

Huerta, A., Rodríguez-Ferran, A., Díez, P., and Sarrate, J. (1999). Adaptive finite element strategies based on error assessment. *International Journal for Numerical Methods in Engineering*, 46(10):1803–1818.

Hughes, G. B. and Chraibi, M. (2012). Calculating ellipse overlap areas. *Computing and Visualization in Science*, 15(5):291–301.

Hund, J., Naumann, J., and Seelig, T. (2018). An experimental and constitutive modeling study on the large strain deformation and fracture behavior of PC/ABS blends. *Mechanics of Materials*, 124:132–142.

Hund, J. and Seelig, T. (2017). Multiscale modeling of thermoplastic PC/ABS blends. *PAMM*, 17(1):417–418.

Hutchinson, J. W. and Hill, R. (1976). Bounds and self-consistent estimates for creep of polycrystalline materials. *Proceedings of the Royal Society of London. A. Mathematical and Physical Sciences*, 348(1652):101–127.

Hutchinson, J. W. and Tvergaard, V. (1980). Surface instabilities on statically strained plastic solids. *International Journal of Mechanical Sciences*, 22(6):339–354.

Ibáñez, R., Abisset-Chavanne, E., Chinesta, F., Huerta, A., and Cueto, E. (2019a). A local multiple proper generalized decomposition based on the partition of unity. *International Journal for Numerical Methods in Engineering*, 120(2):139–152.

Ibáñez, R., Abisset-Chavanne, E., González, D., Duval, J.-L., Cueto, E., and Chinesta, F. (2019b). Hybrid constitutive modeling: Data-driven learning of corrections to plasticity models. *International Journal of Material Forming*, 12(4):717–725.

Ibrahimbegović, A. and Markovič, D. (2003). Strong coupling methods in multi-phase and multi-scale modeling of inelastic behavior of heterogeneous structures. *Computer Methods in Applied Mechanics and Engineering*, 192(28):3089–3107.

Ilin, D. N. and Bernacki, M. (2016). A new algorithm for dense ellipse packing and polygonal structures generation in context of FEM or DEM. *MATEC Web of Conferences*, 80:02004.

Imanaka, M., Motohashi, S., Nishi, K., Nakamura, Y., and Kimoto, M. (2009). Crack-growth behavior of epoxy adhesives modified with liquid rubber and cross-linked rubber particles under mode I loading. *International Journal of Adhesion and Adhesives*, 29(1):45–55.

Imanaka, M., Nakamura, Y., Nishimura, A., and Iida, T. (2003). Fracture toughness of rubber-modified epoxy adhesives: Effect of plastic deformability of the matrix phase. *Composites Science and Technology*, 63(1):41–51.

Inberg, J. P. F. (2001). *Fracture of Polycarbonate/ABS Blends*. PhD Thesis, University of Twente.

Jafari, A., Khatibi, A. A., and Mashhadi, M. M. (2011). Comprehensive investigation on hierarchical multiscale homogenization using Representative Volume Element for piezoelectric nanocomposites. *Composites Part B: Engineering*, 42(3):553–561.

Javili, A., Chatzigeorgiou, G., and Steinmann, P. (2013). Computational homogenization in magneto-mechanics. *International Journal of Solids and Structures*, 50(25):4197–4216.

Jeong, H. Y. (2002). A new yield function and a hydrostatic stress-controlled void nucleation model for porous solids with pressure-sensitive matrices. *International Journal of Solids and Structures*, 39(5):1385–1403.

Jiang, M., Alzebdeh, K., Jasiuk, I., and Ostoja-Starzewski, M. (2001). Scale and boundary conditions effects in elastic properties of random composites. *Acta Mechanica*, 148(1):63–78.

Jiao, Y. and Chawla, N. (2014). Modeling and characterizing anisotropic inclusion orientation in heterogeneous material via directional cluster functions and stochastic microstructure reconstruction. *Journal of Applied Physics*, 115(9):093511.

Jin, H. and Wiberg, N.-E. (1990). Two-dimensional mesh generation, adaptive remeshing and refinement. *International Journal for Numerical Methods in Engineering*, 29(7):1501–1526.

Jin, R., Chen, W., and Sudjianto, A. (2005). An efficient algorithm for constructing optimal design of computer experiments. *Journal of Statistical Planning and Inference*, 134(1):268–287.

Jöchen, K. (2013). *Homogenization of the Linear and Non-Linear Mechanical Behavior of Polycrystals*. KIT Scientific Publishing.

Jodrey, W. S. and Tory, E. M. (1985). Computer simulation of close random packing of equal spheres. *Physical Review A*, 32(4):2347–2351.

Johnson, C. and Hansbo, P. (1992). Adaptive finite element methods in computational mechanics. *Computer Methods in Applied Mechanics and Engineering*, 101(1):143–181.

Jolliffe, I. T. (2002). *Principal Component Analysis*. Springer Series in Statistics. Springer-Verlag, New York, second edition.

Jourdan, A. and Franco, J. (2010). Optimal Latin hypercube designs for the Kullback–Leibler criterion. *AStA Advances in Statistical Analysis*, 94(4):341–351.

Kabel, M., Böhlke, T., and Schneider, M. (2014). Efficient fixed point and Newton–Krylov solvers for FFT-based homogenization of elasticity at large deformations. *Computational Mechanics*, 54(6):1497–1514.

Kabel, M., Fliegener, S., and Schneider, M. (2016). Mixed boundary conditions for FFT-based homogenization at finite strains. *Computational Mechanics*, 57(2):193–210.

Kabel, M., Merkert, D., and Schneider, M. (2015). Use of composite voxels in FFT-based homogenization. *Computer Methods in Applied Mechanics and Engineering*, 294:168–188.

Kaczmarczyk, Ł., Pearce, C. J., and Bićanić, N. (2008). Scale transition and enforcement of RVE boundary conditions in second-order computational homogenization. *International Journal for Numerical Methods in Engineering*, 74(3):506–522.

Kaczmarczyk, Ł., Pearce, C. J., and Bićanić, N. (2010). Studies of microstructural size effect and higher-order deformation in second-order computational homogenization. *Computers & Structures*, 88(23):1383–1390.

Kalamkarov, A. L., Andrianov, I. V., and Danishevs'kyy, V. V. (2009). Asymptotic Homogenization of Composite Materials and Structures. *Applied Mechanics Reviews*, 62(3).

Kaliske, M. (2000). A formulation of elasticity and viscoelasticity for fibre reinforced material at small and finite strains. *Computer Methods in Applied Mechanics and Engineering*, 185(2):225–243.

Kamiński, M. (1999). Boundary element method homogenization of the periodic linear elastic fiber composites. *Engineering Analysis with Boundary Elements*, 23(10):815–823.

Kanaun, S. K. and Levin, V. (2007). *Self-Consistent Methods for Composites: Vol.1: Static Problems*. Springer Science & Business Media.

Kang, K. and Cai, W. (2010). Size and temperature effects on the fracture mechanisms of silicon nanowires: Molecular dynamics simulations. *International Journal of Plasticity*, 26(9):1387–1401.

Kanit, T., Forest, S., Galliet, I., Mounoury, V., and Jeulin, D. (2003). Determination of the size of the representative volume element for random composites: Statistical and numerical approach. *International Journal of Solids and Structures*, 40(13):3647–3679.

Kari, S., Berger, H., Rodriguez-Ramos, R., and Gabbert, U. (2007). Computational evaluation of effective material properties of composites reinforced by randomly distributed spherical particles. *Composite Structures*, 77(2):223–231.

Keip, M.-A., Steinmann, P., and Schröder, J. (2014). Two-scale computational homogenization of electro-elasticity at finite strains. *Computer Methods in Applied Mechanics and Engineering*, 278:62–79.

Kelly, D. W. (1984). The self-equilibration of residuals and complementary a posteriori error estimates in the finite element method. *International Journal for Numerical Methods in Engineering*, 20(8):1491–1506.

Kelly, D. W., Gago, J. P. D. S. R., Zienkiewicz, O. C., and Babuska, I. (1983). A posteriori error analysis and adaptive processes in the finite element method: Part I—error analysis. *International Journal for Numerical Methods in Engineering*, 19(11):1593–1619.

Kerner, E. H. (1956). The Elastic and Thermo-elastic Properties of Composite Media. *Proceedings of the Physical Society. Section B*, 69(8):808–813.

Khaleghi, H., Amiri-Rad, A., and Mashayekhi, M. (2022). A thermodynamically consistent continuum damage model for time-dependent failure of thermoplastic polymers. *International Journal of Plasticity*, 154:103278.

Khoei, A. R., Jahanbakhshi, F., and Aramoon, A. (2015). A concurrent multi-scale technique in modeling heterogeneous FCC nano-crystalline structures. *Mechanics of Materials*, 83:40–65.

Kim, C. P., Busch, R., Masuhr, A., Choi-Yim, H., and Johnson, W. L. (2001). Processing of carbon-fiber-reinforced Zr41.2Ti13.8Cu12.5Ni10.0Be22.5 bulk metallic glass composites. *Applied Physics Letters*, 79(10):1456–1458.

Kim, H.-G. (2014). The effect of different forms of strain energy functions in hyperelasticity-based crystal plasticity models on texture evolution and mechanical response of face-centered cubic crystals. *International Journal for Numerical Methods in Engineering*, 100(4):300–320.

King, D. (2017). A Global Optimization Algorithm Worth Using.

Kirchdoerfer, T. and Ortiz, M. (2016). Data-driven computational mechanics. *Computer Methods in Applied Mechanics and Engineering*, 304:81–101.

Kirchdoerfer, T. and Ortiz, M. (2017a). Data-Driven Computing in Dynamics. *International Journal for Numerical Methods in Engineering*.

Kirchdoerfer, T. and Ortiz, M. (2017b). Data Driven Computing with noisy material data sets. *Computer Methods in Applied Mechanics and Engineering*, 326:622–641.

Klinge, S. and Hackl, K. (2012). Application of the Multiscale Fem to the Modeling of Nonlinear Composites with a Random Microstructure. *International Journal for Multiscale Computational Engineering*, 10(3).

Klompen, E. T. J., Engels, T. A. P., Govaert, L. E., and Meijer, H. E. H. (2005). Modeling of the Postyield Response of Glassy Polymers: Influence of Thermomechanical History. *Macromolecules*, 38(16):6997–7008.

Knowles, A., Jiang, X., Galano, M., and Audebert, F. (2014). Microstructure and mechanical properties of 6061 Al alloy based composites with SiC nanoparticles. *Journal of Alloys and Compounds*, 615:S401–S405.

Kondrachuk, A. V., Shapovalov, G. G., and Kartuzov, V. V. (1997). Simulation modeling of the randomly nonuniform structure of powders. Two-dimensional formulation of the problem. *Powder Metallurgy and Metal Ceramics*, 36(1):101–106.

Kouznetsova, V., Brekelmans, W. A. M., and Baaijens, F. P. T. (2001). An approach to micro-macro modeling of heterogeneous materials. *Computational Mechanics*, 27(1):37–48.

Kouznetsova, V., Geers, M., and Brekelmans, W. (2002). Multi-scale constitutive modelling of heterogeneous materials with a gradient-enhanced computational homogenization scheme. *International Journal for Numerical Methods in Engineering*, 54:1235–1260.

Kouznetsova, V., Geers, M., and Brekelmans, W. (2004a). Size of a Representative Volume Element in a Second-Order Computational Homogenization Framework. *International Journal for Multiscale Computational Engineering*, 2:575–598.

Kouznetsova, V. G., Geers, M. G. D., and Brekelmans, W. A. M. (2004b). Multi-scale second-order computational homogenization of multi-phase materials: A nested finite element solution strategy. *Computer Methods in Applied Mechanics and Engineering*, 193(48):5525–5550.

Krairi, A. and Doghri, I. (2014). A thermodynamically-based constitutive model for thermoplastic polymers coupling viscoelasticity, viscoplasticity and ductile damage. *International Journal of Plasticity*, 60:163–181.

Krairi, A., Doghri, I., Schalnat, J., Robert, G., and Van Paepegem, W. (2019). Thermo-mechanical coupling of a viscoelastic-viscoplastic model for thermoplastic polymers: Thermodynamical derivation and experimental assessment. *International Journal of Plasticity*, 115:154–177.

Krauth, W. (2006). *Statistical Mechanics: Algorithms and Computations*. Oxford University Press, UK.

Kreyszig, E. (2010). *Advanced Engineering Mathematics*. John Wiley & Sons.

Krige, D. G. (1951). A statistical approach to some basic mine valuation problems on the Witwatersrand. *Journal of the Southern African Institute of Mining and Metallurgy*, 52(6):119–139.

Kröner, E. (1953). Das Fundamentalintegral der anisotropen elastischen Differentialgleichungen. *Zeitschrift für Physik*, 136(4):402–410.

Kröner, E. (1958). Berechnung der elastischen Konstanten des Vielkristalls aus den Konstanten des Einkristalls. *Zeitschrift für Physik*, 151(4):504–518.

Kröner, E. (1961). Zur plastischen verformung des vielkristalls. *Acta Metallurgica*, 9(2):155–161.

Kröner, E. (1971). *Statistical Continuum Mechanics: Course Held at the Department of General Mechanics, October 1971*. Springer.

Kröner, E. (1977). Bounds for effective elastic moduli of disordered materials. *Journal of the Mechanics and Physics of Solids*, 25(2):137–155.

Kroner, E. (1978). Self-consistent scheme and graded disorder in polycrystal elasticity. *Journal of Physics F: Metal Physics*, 8(11):2261–2267.

Kuhl, E., Ramm, E., and Borst, R. (2000). An anisotropic gradient damage model for quasi-brittle materials. *Computer Methods in Applied Mechanics and Engineering*, 183(1-2):87–103.

Kumar, A. and Gupta, R. K. (2018). *Fundamentals of Polymer Engineering*. CRC Press.

Kurashige, M., Hayashi, T., and Imai, K. (1999). Simulated effective elastic moduli and wave velocities in water-saturated sintered glass-beads. *Acta Mechanica*, 132(1):177–194.

Ladevèze, P. (1985). Sur une famille d'algorithmes en mécanique des structures. *undefined*.

Ladevèze, P. (1996). *Mécanique non linéaire des structures: Nouvelle approche et méthodes de calcul non incrémentales*. Hermes Science Publications.

Ladevèze, P. (2004). Multiscale modelling and computational strategies for composites. *International Journal for Numerical Methods in Engineering*, 60(1):233–253.

Ladevèze, P. and Chamoin, L. (2010). Calculation of strict error bounds for finite element approximations of non-linear pointwise quantities of interest. *International Journal for Numerical Methods in Engineering*, 84(13):1638–1664.

Ladevèze, P. and Germain, P. (1989). La méthode à grand incrément de temps pour l'analyse de structures à comportement non linéaire décrit par variables internes. *undefined*.

Ladevèze, P. and Leguillon, D. (1983). Error Estimate Procedure in the Finite Element Method and Applications. *SIAM Journal on Numerical Analysis*, 20(3):485–509.

Ladevèze, P., Loiseau, O., and Dureisseix, D. (2001). A micro–macro and parallel computational strategy for highly heterogeneous structures. *International Journal for Numerical Methods in Engineering*, 52(1-2):121–138.

Ladevèze, P. and Moës, N. (1998). A new a posteriori error estimation for nonlinear time-dependent finite element analysis. *Computer Methods in Applied Mechanics and Engineering*, 157(1):45–68.

Ladevèze, P. and Nicolas, M. (1998). A posteriori constitutive relation error estimators for nonlinear finite element analysis and adaptive control. In *Advances in Adaptive Computational Methods in Mechanics*, number 47 in Studies in Applied Mechanics. Elsevier, Amsterdam ; New York.

Ladevèze, P. and Oden, J. T., editors (1998). *Advances in Adaptive Computational Methods in Mechanics*. Number 47 in Studies in Applied Mechanics. Elsevier, Amsterdam ; New York.

Ladevèze, P., Passieux, J. C., and Néron, D. (2010). The LATIN multiscale computational method and the Proper Generalized Decomposition. *Computer Methods in Applied Mechanics and Engineering*, 199(21):1287–1296.

Ladevèze, P., Pelle, J.-P., and Rougeot, P. (1991). Error Estimation and Mesh Optimization for Classical Finite Elements. *Engineering Computations*, 8(1):69–80.

Lahellec, N., Mazerolle, F., and Michel, J. C. (2004). Second-order estimate of the macroscopic behavior of periodic hyperelastic composites: Theory and experimental validation. *Journal of the Mechanics and Physics of Solids*, 52(1):27–49.

Laiarinandrasana, L., Besson, J., Lafarge, M., and Hochstetter, G. (2009). Temperature dependent mechanical behaviour of PVDF: Experiments and numerical modelling. *International Journal of Plasticity*, 25(7):1301–1324.

Lan, Z., Chen, M., Goodman, S., Gimpel, K., Sharma, P., and Soricut, R. (2020). ALBERT: A Lite BERT for Self-supervised Learning of Language Representations. *arXiv:1909.11942 [cs]*.

Larsson, F. and Runesson, K. (2007). RVE computations with error control and adaptivity: The power of duality. *Computational Mechanics*, 39(5):647–661.

Larsson, F., Runesson, K., Saroukhani, S., and Vafadari, R. (2011). Computational homogenization based on a weak format of micro-periodicity for RVE-problems. *Computer Methods in Applied Mechanics and Engineering*, 200(1):11–26.

Latorre, M. and Montáns, F. J. (2018). Experimental data reduction for hyperelasticity. *Computers & Structures*.

Latorre, M., Peña, E., and Montáns, F. (2016). Determination and Finite Element Validation of the WYPIWYG Strain Energy of Superficial Fascia from Experimental Data. *Annals of Biomedical Engineering*, 45.

Lazzeri, A. and Bucknall, C. B. (1993). Dilatational bands in rubber-toughened polymers. *Journal of Materials Science*, 28(24):6799–6808.

Lazzeri, A. and Bucknall, C. B. (1995). Applications of a dilatational yielding model to rubber-toughened polymers. *Polymer*, 36(15):2895–2902.

Le, B. A., Yvonnet, J., and He, Q.-C. (2015). Computational homogenization of nonlinear elastic materials using neural networks. *International Journal for Numerical Methods in Engineering*, 104(12):1061–1084.

Lebensohn, A. R. (2001). N-site modeling of a 3D viscoplastic polycrystal using Fast Fourier Transform. *Acta Materialia*, 49(14):2723–2737.

Lee, E. H. (1969). Elastic-Plastic Deformation at Finite Strains. *Journal of Applied Mechanics*, 36(1):1–6.

Lee, E. H. and Liu, D. T. (1967). Finite-Strain Elastic—Plastic Theory with Application to Plane-Wave Analysis. *Journal of Applied Physics*, 38(1):19–27.

Lee, N.-S. and Bathe, K.-J. (1994). Error indicators and adaptive remeshing in large deformation finite element analysis. *Finite Elements in Analysis and Design*, 16(2):99–139.

Leffers, T. (1979). A Modified Sachs Approach to the Plastic Deformation of Polycrystals as a Realistic Alternative to the Taylor Model. In Haasen, P., Gerold, V., and Kostorz, G., editors, *Strength of Metals and Alloys*, pages 769–774. Pergamon.

Lele, S. P. and Anand, L. (2009). A large-deformation strain-gradient theory for isotropic viscoplastic materials. *International Journal of Plasticity*, 25(3):420–453.

Lemaitre, J. (2013). *A Course on Damage Mechanics*. Springer Science & Business Media.

Leonov, A. I. (1976). Nonequilibrium thermodynamics and rheology of viscoelastic polymer media. *Rheologica Acta*, 15(2):85–98.

Leroy, Y. and Ponte Castañeda, P. (2001). Bounds on the self-consistent approximation for nonlinear media and implications for the second-order method. *Comptes Rendus de l'Académie des Sciences - Series IIB - Mechanics*, 329(8):571–577.

Lesičar, T., Sorić, J., and Tonkovic, Z. (2015a). Large strain, two-scale computational approach using C1 continuity finite element employing a second gradient theory. *Computer Methods in Applied Mechanics and Engineering*, 298.

Lesičar, T., Sorić, J., and Tonkovic, Z. (2017a). On the Scale-Transition in Multiscale Modeling of Ductile Damage. *Key Engineering Materials*, 754:226–229.

Lesičar, T., Tonkovic, Z., and Sorić, J. (2015b). Second-Order Computational Homogenization Approach Using Higher-Order Gradients at Microlevel. *Key Engineering Materials*, 665:181–184.

Lesičar, T., Tonkovic, Z., and Sorić, J. (2017b). Two-Scale Computational Approach Using Strain Gradient Theory at Microlevel. *International Journal of Mechanical Sciences*, 126.

Li, F., Liu, Y., Qu, C.-B., Xiao, H.-M., Hua, Y., Sui, G.-X., and Fu, S.-Y. (2015). Enhanced mechanical properties of short carbon fiber reinforced polyethersulfone composites by graphene oxide coating. *Polymer*, 59:155–165.

Li, H., Kafka, O. L., Gao, J., Yu, C., Nie, Y., Zhang, L., Tajdari, M., Tang, S., Guo, X., Li, G., Tang, S., Cheng, G., and Liu, W. K. (2019). Clustering discretization methods for generation of material performance databases in machine learning and design optimization. *Computational Mechanics*, 64(2):281–305.

Li, J. and Dunn, M. (2001). Variational bounds for the effective moduli of heterogeneous piezoelectric solids. *Philosophical Magazine A: Physics of Condensed Matter, Structure, Defects and Mechanical Properties*, 81:903–926.

Li, X. and Wiberg, N.-E. (1994). A posteriori error estimate by element patch post-processing, adaptive analysis in energy and L2 norms. *Computer and Structures*, 53(4):907–919.

Li, Y., Waas, A. M., and Arruda, E. M. (2011). A closed-form, hierarchical, multi-interphase model for composites—Derivation, verification and application to nanocomposites. *Journal of the Mechanics and Physics of Solids*, 59(1):43–63.

Lippmann, B. A. and Schwinger, J. (1950). Variational Principles for Scattering Processes. I. *Physical Review*, 79(3):469–480.

Liu, L., Li, Z., Jiao, Y., and Li, S. (2017). Maximally dense random packings of cubes and cuboids via a novel inverse packing method. *Soft Matter*, 13(4):748–757.

Liu, L., Yu, Z., Jin, W., Yuan, Y., and Li, S. (2018a). Uniform and decoupled shape effects on the maximally dense random packings of hard superellipsoids. *Powder Technology*, 338:67–78.

Liu, W. K., Karniadakis, G., Tang, S., and Yvonnet, J. (2019a). A computational mechanics special issue on: Data-driven modeling and simulation—theory, methods, and applications. *Computational Mechanics*, 64(2):275–277.

Liu, Z. (2017). *Reduced-Order Homogenization of Heterogeneous Material Systems: From Viscoelasticity to Nonlinear Elasto-Plastic Softening Material*. PhD Thesis, Northwestern University.

Liu, Z., Bessa, M., and Liu, W. K. (2016). Self-consistent clustering analysis: An efficient multi-scale scheme for inelastic heterogeneous materials. *Computer Methods in Applied Mechanics and Engineering*, 306:319–341.

Liu, Z., Fleming, M., and Liu, W. K. (2018b). Microstructural material database for self-consistent clustering analysis of elastoplastic strain softening materials. *Computer Methods in Applied Mechanics and Engineering*, 330:547–577.

Liu, Z. and Wu, C. (2019). Exploring the 3D architectures of deep material network in data-driven multiscale mechanics. *Journal of the Mechanics and Physics of Solids*, 127:20–46.

Liu, Z., Wu, C., and Koishi, M. (2019b). A deep material network for multiscale topology learning and accelerated nonlinear modeling of heterogeneous materials. *Computer Methods in Applied Mechanics and Engineering*, 345:1138–1168.

Liu, Z., Xiao, B., Wang, W., and Ma, Z. (2013). Developing high-performance aluminum matrix composites with directionally aligned carbon nanotubes by combining friction stir processing and subsequent rolling. *Carbon*, 62:35–42.

Lloyd, S. (1982). Least squares quantization in PCM. *IEEE Transactions on Information Theory*, 28(2):129–137.

Lombardo, B. S., Keskkula, H., and Paul, D. R. (1994). Influence of ABS type on morphology and mechanical properties of PC/ABS blends. *Journal of Applied Polymer Science*, 54(11):1697–1720.

Los, W. and Wood, J. (2011). Dealing with Data: Upgrading Infrastructure. *Science*, 331(6024):1515–1516.

Lott, S. F. (2019). *Mastering Object-Oriented Python: Build Powerful Applications with Reusable Code Using OOP Design Patterns and Python 3.7, 2nd Edition*. Packt Publishing Ltd.

Lubachevsky, B. D. and Stillinger, F. H. (1990). Geometric properties of random disk packings. *Journal of Statistical Physics*, 60(5):561–583.

Lubachevsky, B. D., Stillinger, F. H., and Pinson, E. N. (1991). Disks vs. spheres: Contrasting properties of random packings. *Journal of Statistical Physics*, 64(3-4):501–524.

Lucarini, S. and Segurado, J. (2019). An algorithm for stress and mixed control in Galerkin-based FFT homogenization. *International Journal for Numerical Methods in Engineering*, 119(8):797–805.

Luo, H. A. and Weng, G. J. (1987). On Eshelby's inclusion problem in a three-phase spherically concentric solid, and a modification of Mori-Tanaka's method. *Mechanics of Materials*, 6(4):347–361.

Lynch, C. (2008). How do your data grow? *Nature*, 455(7209):28–29.

Ma, X., Shakoor, M., Vasiukov, D., Lomov, S. V., and Park, C. H. (2021). Numerical artifacts of Fast Fourier Transform solvers for elastic problems of multi-phase materials: Their causes and reduction methods. *Computational Mechanics*, 67(6):1661–1683.

Machiels, L., Peraire, J., and Patera, A. T. (2001). A Posteriori Finite-Element Output Bounds for the Incompressible Navier–Stokes Equations: Application to a Natural Convection Problem. *Journal of Computational Physics*, 172(2):401–425.

Maday, Y., Patera, A. T., and Peraire, J. (1999). A general formulation for a posteriori bounds for output functionals of partial differential equations; application to the eigenvalue problem. *Comptes Rendus de l'Académie des Sciences - Series I - Mathematics*, 328(9):823–828.

Madou, K. and Leblond, J.-B. (2012a). A Gurson-type criterion for porous ductile solids containing arbitrary ellipsoidal voids—I: Limit-analysis of some representative cell. *Journal of the Mechanics and Physics of Solids*, 60(5):1020–1036.

Madou, K. and Leblond, J.-B. (2012b). A Gurson-type criterion for porous ductile solids containing arbitrary ellipsoidal voids—II: Determination of yield criterion parameters. *Journal of the Mechanics and Physics of Solids*, 60(5):1037–1058.

Madou, K. and Leblond, J.-B. (2013). Numerical studies of porous ductile materials containing arbitrary ellipsoidal voids – I: Yield surfaces of representative cells. *European Journal of Mechanics - A/Solids*, 42:480–489.

Madou, K., Leblond, J.-B., and Morin, L. (2013). Numerical studies of porous ductile materials containing arbitrary ellipsoidal voids – II: Evolution of the length and orientation of the void axes. *European Journal of Mechanics - A/Solids*, 42:490–507.

Malherbe, C. and Vayatis, N. (2017). Global optimization of Lipschitz functions. In *Proceedings of the 34th International Conference on Machine Learning - Volume 70*, ICML'17, pages 2314–2323, Sydney, NSW, Australia. JMLR.org.

Mandadapu, K. K., Sengupta, A., and Papadopoulos, P. (2012). A homogenization method for thermomechanical continua using extensive physical quantities. *Proceedings of the Royal Society A: Mathematical, Physical and Engineering Sciences*, 468(2142):1696–1715.

Mandel, J. (1966). Contribution théorique à l'étude de l'écrouissage et des lois de l'écoulement plastique. In Görtler, H., editor, *Applied Mechanics*, pages 502–509, Berlin, Heidelberg. Springer.

Matheron, G. (1963). Principles of geostatistics. *Economic Geology*, 58(8):1246–1266.

Matouš, K., Geers, M. G., Kouznetsova, V. G., and Gillman, A. (2017). A review of predictive nonlinear theories for multiscale modeling of heterogeneous materials. *Journal of Computational Physics*, 330:192–220.

Matouš, K., Kulkarni, M. G., and Geubelle, P. H. (2008). Multiscale cohesive failure modeling of heterogeneous adhesives. *Journal of the Mechanics and Physics of Solids*, 56(4):1511–1533.

Matsubara, S., Terada, K., Maeda, R., Kobayashi, T., Murata, M., Sumiyama, T., Furuichi, K., and Nonomura, C. (2020). Viscoelastic-viscoplastic combined constitutive model for glassy amorphous polymers under loading/unloading/no-load states. *Engineering Computations*, 37(5):1703–1735.

McClintock, F. A. (1968). A Criterion for Ductile Fracture by the Growth of Holes. *Journal of Applied Mechanics*, 35(2):363–371.

Mccoy, J. (1981). Macroscopic Response of Continua with Random Microstructures. *Mechanics Today*, 6.

McCrum, N. G., Buckley, C. P., and Bucknall, C. B. (1997). *Principles of Polymer Engineering*. Oxford University Press, Oxford, New York, second edition edition.

McKay, M. D., Beckman, R. J., and Conover, W. J. (1979). A Comparison of Three Methods for Selecting Values of Input Variables in the Analysis of Output from a Computer Code. *Technometrics*, 21(2):239–245.

McLaughlin, R. (1977). A study of the differential scheme for composite materials. *International Journal of Engineering Science*, 15(4):237–244.

Mear, M. E. and Hutchinson, J. W. (1985). Influence of yield surface curvature on flow localization in dilatant plasticity. *Mechanics of Materials*, 4(3):395–407.

Melro, A. R. (2011). *Analytical and Numerical Modelling of Damage and Fracture of Advanced Composites*. PhD Thesis, University of Porto.

Meng, L., Li, S., and Yao, X. (2017). Maximally dense random packings of intersecting spherocylinders with central symmetry. *Powder Technology*, 314:49–58.

Mercer, B. S., Mandadapu, K. K., and Papadopoulos, P. (2015). Novel formulations of microscopic boundary-value problems in continuous multiscale finite element methods. *Computer Methods in Applied Mechanics and Engineering*, 286:268–292.

Mesarovic, S. D. and Padbidri, J. (2005). Minimal kinematic boundary conditions for simulations of disordered microstructures. *Philosophical Magazine*, 85:65–78.

Metropolis, N., Rosenbluth, A. W., Rosenbluth, M. N., Teller, A. H., and Teller, E. (1953). Equation of State Calculations by Fast Computing Machines. *The Journal of Chemical Physics*, 21(6):1087–1092.

Michel, J., Moulinec, H., and Suquet, P. (1999a). Effective properties of composite materials with periodic microstructure: A computational approach. *Computer Methods in Applied Mechanics and Engineering*, 172(1-4):109–143.

Michel, J. C., Lopez-Pamies, O., Ponte Castañeda, P., and Triantafyllidis, N. (2007). Microscopic and macroscopic instabilities in finitely strained porous elastomers. *Journal of the Mechanics and Physics of Solids*, 55(5):900–938.

Michel, J. C., Moulinec, H., and Suquet, P. (1999b). Effective properties of composite materials with periodic microstructure: A computational approach. *Computer Methods in Applied Mechanics and Engineering*, 172(1):109–143.

Michel, J. C., Moulinec, H., and Suquet, P. (2001). A computational scheme for linear and non-linear composites with arbitrary phase contrast. *International Journal for Numerical Methods in Engineering*, 52(12):139–160.

Michel, J. C. and Suquet, P. (2003). Nonuniform transformation field analysis. *International Journal of Solids and Structures*, 40(25):6937–6955.

Miehe, C. (2002). Strain-driven homogenization of inelastic microstructures and composites based on an incremental variational formulation. *International Journal for Numerical Methods in Engineering*, 55(11):1285–1322.

Miehe, C. and Bayreuther, C. G. (2007). On multiscale FE analyses of heterogeneous structures: From homogenization to multigrid solvers. *International Journal for Numerical Methods in Engineering*, 71(10):1135–1180.

Miehe, C. and Dettmar, J. (2004). A framework for micro–macro transitions in periodic particle aggregates of granular materials. *Computer Methods in Applied Mechanics and Engineering*, 193(3):225–256.

Miehe, C., Hofacker, M., Schänzel, L.-M., and Aldakheel, F. (2015a). Phase field modeling of fracture in multi-physics problems. Part II. Coupled brittle-to-ductile failure criteria and crack propagation in thermo-elastic–plastic solids. *Computer Methods in Applied Mechanics and Engineering*, C(294):486–522.

Miehe, C., Hofacker, M., and Welschinger, F. (2010). A phase field model for rate-independent crack propagation: Robust algorithmic implementation based on operator splits. *Computer Methods in Applied Mechanics and Engineering*, 199:2765–2778.

Miehe, C. and Koch, A. (2002). Computational micro-to-macro transitions of discretized microstructures undergoing small strains. *Archive of Applied Mechanics*, 72(4):300–317.

Miehe, C., Schröder, J., and Bayreuther, C. (2002a). On the homogenization analysis of composite materials based on discretized fluctuations on the micro-structure. *Acta Mechanica*, 155(1):1–16.

Miehe, C., Schröder, J., and Becker, M. (2002b). Computational homogenization analysis in finite elasticity: Material and structural instabilities on the micro- and macro-scales of periodic composites and their interaction. *Computer Methods in Applied Mechanics and Engineering*, 191(44):4971–5005.

Miehe, C., Schröder, J., and Schotte, J. (1999). Computational homogenization analysis in finite plasticity Simulation of texture development in polycrystalline materials. *Computer Methods in Applied Mechanics and Engineering*, 171(3):387–418.

Miehe, C., Vallicotti, D., and Teichtmeister, S. (2015b). Homogenization and multiscale stability analysis in finite magneto-electro-elasticity. *GAMM-Mitteilungen*, 38(2):313–343.

Miehe, C., Vallicotti, D., and Teichtmeister, S. (2016). Homogenization and multiscale stability analysis in finite magneto-electro-elasticity. Application to soft matter EE, ME and MEE composites. *Computer Methods in Applied Mechanics and Engineering*, 300:294–346.

Mikdam, A., Makradi, A., Koutsawa, Y., and Belouettar, S. (2013). Microstructure effect on the mechanical properties of heterogeneous composite materials. *Composites Part B: Engineering*, 44(1):714–721.

Miled, B., Doghri, I., and Delannay, L. (2011). Coupled viscoelastic–viscoplastic modeling of homogeneous and isotropic polymers: Numerical algorithm and analytical solutions. *Computer Methods in Applied Mechanics and Engineering*, 200(47):3381–3394.

Miller, M. N. (1969). Bounds for Effective Bulk Modulus of Heterogeneous Materials. *Journal of Mathematical Physics*, 10(11):2005–2013.

Milton, G. W., Phan-Thien, N., and Cottrell, A. H. (1982). New bounds on effective elastic moduli of two-component materials. *Proceedings of the Royal Society of London. A. Mathematical and Physical Sciences*, 380(1779):305–331.

Miranda, H. D. (2015). *Computational Generation and Homogenization of Random Close Packed Materials*. PhD Thesis, University of Porto.

Mirkhalaf, S. M., Andrade Pires, F. M., and Simoes, R. (2016). An elasto-viscoplastic constitutive model for polymers at finite strains: Formulation and computational aspects. *Computers & Structures*, 166:60–74.

Mitchell, T. M. (1997). *Machine Learning*. McGraw-Hill.

Moës, N. and Belytschko, T. (2002). Extended finite element method for cohesive crack growth. *Engineering Fracture Mechanics*, 69(7):813–833.

Moës, N., Cloirec, M., Cartraud, P., and Remacle, J. F. (2003). A computational approach to handle complex microstructure geometries. *Computer Methods in Applied Mechanics and Engineering*, 192(28):3163–3177.

Moës, N., Dolbow, J., and Belytschko, T. (1999). A finite element method for crack growth without remeshing. *International Journal for Numerical Methods in Engineering*, 46(1):131–150.

Moitra, A. (2018). *Algorithmic Aspects of Machine Learning*. Cambridge University Press.

Monchiet, V. and Bonnet, G. (2012a). A polarization-based FFT iterative scheme for computing the effective properties of elastic composites with arbitrary contrast. *International Journal for Numerical Methods in Engineering*, 89(11):1419–1436.

Monchiet, V. and Bonnet, G. (2012b). A polarization-based FFT iterative scheme for computing the effective properties of elastic composites with arbitrary contrast: A Polarization-based FFT Iterative Scheme. *International Journal for Numerical Methods in Engineering*, 89(11):1419–1436.

Moore, J. A., Ma, R., Domel, A. G., and Liu, W. K. (2014). An efficient multiscale model of damping properties for filled elastomers with complex microstructures. *Composites Part B: Engineering*, 62:262–270.

Moorthy, S. and Ghosh, S. (1996). A Model for Analysis of Arbitrary Composite and Porous Microstructures with Voronoi Cell Finite Elements. *International Journal for Numerical Methods in Engineering*, 39(14):2363–2398.

Morelle, X. P., Chevalier, J., Bailly, C., Pardoen, T., and Lani, F. (2017). Mechanical characterization and modeling of the deformation and failure of the highly crosslinked RTM6 epoxy resin. *Mechanics of Time-Dependent Materials*, 21(3):419–454.

Mori, T. and Tanaka, K. (1973). Average stress in matrix and average elastic energy of materials with misfitting inclusions. *Acta Metallurgica*, 21(5):571–574.

Morin, L., Leblond, J.-B., and Benzerga, A. A. (2015a). Coalescence of voids by internal necking: Theoretical estimates and numerical results. *Journal of the Mechanics and Physics of Solids*, 75:140–158.

Morin, L., Leblond, J.-B., and Kondo, D. (2015b). A Gurson-type criterion for plastically anisotropic solids containing arbitrary ellipsoidal voids. *International Journal of Solids and Structures*, 77:86–101.

Morin, L., Madou, K., Leblond, J.-B., and Kondo, D. (2014). A new technique for finite element limit-analysis of Hill materials, with an application to the assessment of criteria for anisotropic plastic porous solids. *International Journal of Engineering Science*, 74:65–79.

Mortazavi, B., Baniassadi, M., Bardon, J., and Ahzi, S. (2013). Modeling of two-phase random composite materials by finite element, Mori–Tanaka and strong contrast methods. *Composites Part B: Engineering*, 45(1):1117–1125.

Mosby, M. and Matouš, K. (2015). Hierarchically parallel coupled finite strain multiscale solver for modeling heterogeneous layers. *International Journal for Numerical Methods in Engineering*, 102(3-4):748–765.

Mosby, M. and Matous, K. (2015). On mechanics and material length scales of failure in heterogeneous interfaces using a finite strain high performance solver. *Modelling and Simulation in Materials Science and Engineering*, 23:085014.

Mosby, M. and Matouš, K. (2016). Computational homogenization at extreme scales. *Extreme Mechanics Letters*, 6:68–74.

Mościński, J., Bargieł, M., Rycerz, Z. A., and Jacobs, P. W. M. (1989). The Force-Biased Algorithm for the Irregular Close Packing of Equal Hard Spheres. *Molecular Simulation*, 3(4):201–212.

Moulinec, H. and Suquet, P. (1994). A fast numerical method for computing the linear and nonlinear mechanical properties of composites. *A fast numerical method for computing the linear and nonlinear mechanical properties of composites*, 318(11):1417–1423.

Moulinec, H. and Suquet, P. (1998). A numerical method for computing the overall response of nonlinear composites with complex microstructure. *Computer Methods in Applied Mechanics and Engineering*, 157(1):69–94.

Moussaddy, H., Therriault, D., and Lévesque, M. (2013). Assessment of existing and introduction of a new and robust efficient definition of the representative volume element. *International Journal of Solids and Structures*, 50(24):3817–3828.

Mulliken, A. (2006). *Mechanics of Amorphous Polymers and Polymer Nanocom- Posites during High Rate Deformation*. PhD Thesis, Massachusetts Institute of Technology.

Mulliken, A. D. and Boyce, M. C. (2006). Mechanics of the rate-dependent elastic–plastic deformation of glassy polymers from low to high strain rates. *International Journal of Solids and Structures*, 43(5):1331–1356.

Mura, T. (1987). *Micromechanics of Defects in Solids*. Springer Science & Business Media.

Nagel, T., Görke, U.-J., Moerman, K. M., and Kolditz, O. (2016). On advantages of the Kelvin mapping in finite element implementations of deformation processes. *Environmental Earth Sciences*, 75(11):937.

Needleman, A. (1987). A Continuum Model for Void Nucleation by Inclusion Debonding. *Journal of Applied Mechanics*, 54(3):525–531.

Nemat-Nasser, S. and Hori, M. (1993). *Micromechanics: Overall Properties of Heterogeneous Materials*. Number v. 37 in North-Holland Series in Applied Mathematics and Mechanics. North-Holland, Amsterdam ; New York.

Nemat-Nasser, S. and Hori, M. (1995). Universal Bounds for Overall Properties of Linear and Nonlinear Heterogeneous Solids. *Journal of Engineering Materials and Technology*, 117(4):412–432.

Nemat-Nasser, S., Iwakuma, T., and Hejazi, M. (1982). On composites with periodic structure. *Mechanics of Materials*, 1(3):239–267.

Nemat-Nasser, S., Yu, N., and Hori, M. (1993). Bounds and estimates of overall moduli of composites with periodic microstructure. *Mechanics of Materials*, 15(3):163–181.

Newland, D. E. (1984). *An Introduction to Random Vibrations and Spectral Analysis*. Longman.

Nezamabadi, S., Yvonnet, J., Zahrouni, H., and Potier-Ferry, M. (2009). A multilevel computational strategy for handling microscopic and macroscopic instabilities. *Computer Methods in Applied Mechanics and Engineering*, 198(27):2099–2110.

Nguyen, N. C. (2008). A multiscale reduced-basis method for parametrized elliptic partial differential equations with multiple scales. *Journal of Computational Physics*, 227(23):9807–9822.

Nguyen, N. C., Patera, A. T., and Peraire, J. (2008). A 'best points' interpolation method for efficient approximation of parametrized functions. *International Journal for Numerical Methods in Engineering*, 73(4):521–543.

Nguyen, T. K., Combe, G., Caillerie, D., and Desrues, J. (2014). FEM × DEM modelling of cohesive granular materials: Numerical homogenisation and multi-scale simulations. *Acta Geophysica*, 62(5):1109–1126.

Nguyen, V. D., Lani, F., Pardoen, T., Morelle, X. P., and Noels, L. (2016). A large strain hyperelastic viscoelastic-viscoplastic-damage constitutive model based on a multi-mechanism non-local damage continuum for amorphous glassy polymers. *International Journal of Solids and Structures*, 96:192–216.

Nguyen, V. P., Lloberas-Valls, O., Stroeven, M., and Sluys, L. J. (2012). Computational homogenization for multiscale crack modeling. Implementational and computational aspects. *International Journal for Numerical Methods in Engineering*, 89(2):192–226.

Nguyen, V. P., Stroeven, M., and Sluys, L. J. (2011). Multiscale continuous and discontinuous modeling of heterogeneous materials: A review on recent developments. *Journal of Multiscale Modelling*, 03(04):229–270.

Nie, Y., Cheng, G., Li, X., Xu, L., and Li, K. (2019). Principle of cluster minimum complementary energy of FEM-cluster-based reduced order method: Fast updating the interaction matrix and predicting effective nonlinear properties of heterogeneous material. *Computational Mechanics*, 64(2):323–349.

Nie, Y., Li, Z., and Cheng, G. (2021). Efficient prediction of the effective nonlinear properties of porous material by FEM-Cluster based Analysis (FCA). *Computer Methods in Applied Mechanics and Engineering*, 383:113921.

Nochetto, R. H., Siebert, K. G., and Veeser, A. (2009a). Theory of adaptive finite element methods: An introduction. In DeVore, R. and Kunoth, A., editors, *Multiscale, Nonlinear and Adaptive Approximation*, pages 409–542, Berlin, Heidelberg. Springer.

Nochetto, R. H., Veeser, A., and Verani, M. (2009b). A safeguarded dual weighted residual method. *IMA Journal of Numerical Analysis*, 29(1):126–140.

Nolan, G. T. and Kavanagh, P. E. (1992). Computer simulation of random packing of hard spheres. *Powder Technology*, 72(2):149–155.

Norris, A. N. (1985). A differential scheme for the effective moduli of composites. *Mechanics of Materials*, 4(1):1–16.

Oden, J. T. and Prudhomme, S. (2001). Goal-oriented error estimation and adaptivity for the finite element method. *Computers & Mathematics with Applications*, 41(5):735–756.

Ogden, R. W. (1974). On the overall moduli of non-linear elastic composite materials. *Journal of the Mechanics and Physics of Solids*, 22(6):541–553.

Ohtsubo, H. and Kitamura, M. (1992). Numerical investigation of element-wise a posteriori error estimation in two and three dimensional elastic problems. *International Journal for Numerical Methods in Engineering*, 34(3):969–977.

Okada, H., Fukui, Y., and Kumazawa, N. (2001). Homogenization method for heterogeneous material based on boundary element method. *Computers & Structures*, 79(20):1987–2007.

Okada, J.-I., Washio, T., and Hisada, T. (2010). Study of efficient homogenization algorithms for nonlinear problems. *Computational Mechanics*, 46:247–258.

Oliver, J., Cervera, M., and Manzoli, O. (1999). Strong discontinuities and continuum plasticity models: The strong discontinuity approach. *International Journal of Plasticity*, 15(3):319–351.

Oliver, J., Simó, J., and Armero, F. (1993). An analysis of strong discontinuities induced by strain-softening in rate-independent inelastic solids. *Computational Mechanics*.

Olson, T. (1994). Improvements on Taylor's upper bound for rigid-plastic composites. *Materials Science and Engineering: A*, 175(1):15–20.

Ortiz, M., Leroy, Y., and Needleman, A. (1987). A finite element method for localized failure analysis. *Computer Methods in Applied Mechanics and Engineering*, 61(2):189–214.

Ortiz, M. and Quigley, J. J. (1991). Adaptive mesh refinement in strain localization problems. *Computer Methods in Applied Mechanics and Engineering*, 90(1):781–804.

Ostoja-Starzewski, M. (1998). Random field models of heterogeneous materials. *International Journal of Solids and Structures*, 35(19):2429–2455.

Ostoja-Starzewski, M. (2006). Material spatial randomness: From statistical to representative volume element. *Probabilistic Engineering Mechanics*, 21(2):112–132.

O'Sullivan, C. and Bray, J. D. (2004). Selecting a suitable time step for discrete element simulations that use the central difference time integration scheme. *Engineering Computations*, 21(2/3/4):278–303.

Özdemir, I., Brekelmans, W. a. M., and Geers, M. G. D. (2008a). Computational homogenization for heat conduction in heterogeneous solids. *International Journal for Numerical Methods in Engineering*, 73(2):185–204.

Özdemir, I., Brekelmans, W. A. M., and Geers, M. G. D. (2008b). FE2 computational homogenization for the thermo-mechanical analysis of heterogeneous solids. *Computer Methods in Applied Mechanics and Engineering*, 198(3):602–613.

Paggi, M. and Reinoso, J. (2017). Revisiting the problem of a crack impinging on an interface:A modeling framework for the interaction between the phase field approach for brittle fracture and the interface cohesive zone model. *Computer Methods in Applied Mechanics and Engineering*, 321:145–172.

Pan, J., Saje, M., and Needleman, A. (1983). Localization of deformation in rate sensitive porous plastic solids. *International Journal of Fracture*, 21(4):261–278.

Papanicolau, G., Bensoussan, A., and Lions, J.-L. (1978). *Asymptotic Analysis for Periodic Structures*. Elsevier.

Paraschivoiu, M., Peraire, J., and Patera, A. T. (1997). A posteriori finite element bounds for linear-functional outputs of elliptic partial differential equations. *Computer Methods in Applied Mechanics and Engineering*, 150(1):289–312.

Parés, N., Bonet, J., Huerta, A., and Peraire, J. (2006). The computation of bounds for linear-functional outputs of weak solutions to the two-dimensional elasticity equations. *Computer Methods in Applied Mechanics and Engineering*, 195(4):406–429.

Parsa, B., Rajasekaran, K., Meier, F., and Banerjee, A. G. (2018). A Hierarchical Bayesian Linear Regression Model with Local Features for Stochastic Dynamics Approximation. *arXiv:1807.03931 [cs, stat]*.

Pastor, M., Peraire, J., and Zienkiewicz, O. C. (1991). Adaptive remeshing for shear band localization problems. *Archive of Applied Mechanics*, 61(1):30–39.

Pathan, M. V., Tagarielli, V. L., Patsias, S., and Baiz-Villafranca, P. M. (2017). A new algorithm to generate representative volume elements of composites with cylindrical or spherical fillers. *Composites Part B: Engineering*, 110:267–278.

Pearson, R. A. and Yee, A. F. (1989). Toughening mechanisms in elastomer-modified epoxies. *Journal of Materials Science*, 24(7):2571–2580.

Pecullan, S., Gibiansky, L. V., and Torquato, S. (1999). Scale effects on the elastic behavior of periodic andhierarchical two-dimensional composites. *Journal of the Mechanics and Physics of Solids*, 47(7):1509–1542.

Pedregosa, F., Varoquaux, G., Gramfort, A., Michel, V., Thirion, B., Grisel, O., Blondel, M., Prettenhofer, P., Weiss, R., Dubourg, V., Vanderplas, J., Passos, A., Cournapeau, D., Brucher, M., Perrot, M., Duchesnay, E., and Louppe, G. (2012). Scikit-learn: Machine Learning in Python. *Journal of Machine Learning Research*, 12.

Peerlings, R. H. J., R. Borst, D., Brekelmans, W. a. M., and J. H.P. Vree, D. (1996). Gradient enhanced damage for quasi-brittle materials. *International Journal for Numerical Methods in Engineering*, 39(19):3391–3403.

Peraire, J. and Patera, A. T. (1999). Asymptotic a posteriori finite element bounds for the outputs of noncoercive problems: The Helmholtz and Burgers equations. *Computer Methods in Applied Mechanics and Engineering*, 171(1):77–86.

Perić, D., de Souza Neto, E., Feijóo, R., Partovi, M., and Molina, A. (2011). On micro-to-macro transitions for multi-scale analysis of non-linear heterogeneous materials: Unified variational basis and finite element implementation. *International Journal for Numerical Methods in Engineering*, 87:149–170.

Perić, D., de Souza Neto, E., Somer, D., and Dettmer, W. (2009). On computational procedures for multiscale analysis of heterogeneous solids: Variational basis and fe implementation. *Computational Plasticity X - Fundamentals and Applications*.

Perić, D., Dutko, M., and Owen, D. R. J. (1998a). An adaptive finite element approach in associated and non-associated plasticity considering localization phenomena. In *Aspects of Adaptive Strategies for Large Deformation Problems at Finite Inelastic Strains*, number 47 in Studies in Applied Mechanics. Elsevier, Amsterdam ; New York.

Perić, D., Dutko, M., and Owen, D. R. J. (1998b). Aspects of adaptive strategies for large deformation problems at finite inelastic strains. In *Aspects of Adaptive Strategies for Large Deformation Problems at Finite Inelastic Strains*, number 47 in Studies in Applied Mechanics, pages 349–363. Elsevier, Amsterdam ; New York.

Perić, D., Hochard, C., Dutko, M., and Owen, D. R. J. (1996). Transfer operators for evolving meshes in small strain elasto-placticity. *Computer Methods in Applied Mechanics and Engineering*, 137(3):331–344.

Perić, D., Owen, D. R. J., and Honnor, M. E. (1992). A model for finite strain elasto-plasticity based on logarithmic strains: Computational issues. *Computer Methods in Applied Mechanics and Engineering*, 94(1):35–61.

Perić, D., Vaz, M., and Owen, D. R. J. (1999). On adaptive strategies for large deformations of elasto-plastic solids at finite strains: Computational issues and industrial applications. *Computer Methods in Applied Mechanics and Engineering*, 176(1):279–312.

Peric, D., Yu, J., and Owen, D. (1994). On error estimates and adaptivity in elastoplastic solids: Applications to the numerical simulation of strain localization in classical and Cosserat continua. *International Journal for Numerical Methods in Engineering*, 37(8):1351–1379.

Perram, J. W. and Wertheim, M. (1985). Statistical mechanics of hard ellipsoids. I. Overlap algorithm and the contact function. *Journal of Computational Physics*, 58(3):409–416.

Pham, K., Kouznetsova, V. G., and Geers, M. G. D. (2013). Transient computational homogenization for heterogeneous materials under dynamic excitation. *Journal of the Mechanics and Physics of Solids*, 61(11):2125–2146.

Phelps, J. H., Abd El-Rahman, A. I., Kunc, V., and Tucker, C. L. (2013). A model for fiber length attrition in injection-molded long-fiber composites. *Composites Part A: Applied Science and Manufacturing*, 51:11–21.

Phillips, D. (2018). *Python 3 Object-Oriented Programming: Build Robust and Maintainable Software with Object-Oriented Design Patterns in Python 3.8, 3rd Edition*. Packt Publishing Ltd.

Picasso, M. (2003). An Anisotropic Error Indicator Based on Zienkiewicz–Zhu Error Estimator: Application to Elliptic and Parabolic Problems. *SIAM Journal on Scientific Computing*, 24(4):1328–1355.

Pierard, O., Friebel, C., and Doghri, I. (2004). Mean-field homogenization of multi-phase thermo-elastic composites: A general framework and its validation. *Composites Science and Technology*, 64(10):1587–1603.

Pietruszczak, S. and Mróz, Z. (1981). Finite element analysis of deformation of strain-softening materials. *International Journal for Numerical Methods in Engineering*, 17:327–334.

Pijaudier-Cabot, G., Bodé, L., and Huerta, A. (1995). Arbitrary Lagrangian–Eulerian finite element analysis of strain localization in transient problems. *International Journal for Numerical Methods in Engineering*, 38(24):4171–4191.

Pijnenburg, K. G. W., Seelig, T., and van der Giessen, E. (2005). Successively refined models for crack tip plasticity in polymer blends. *European Journal of Mechanics - A/Solids*, 24(5):740–756.

Pijnenburg, K. G. W. and Van der Giessen, E. (2001). Macroscopic yield in cavitated polymer blends. *International Journal of Solids and Structures*, 38(20):3575–3598.

Pinho-da-Cruz, J., Oliveira, J. A., and Teixeira-Dias, F. (2009). Asymptotic homogenisation in linear elasticity. Part I: Mathematical formulation and finite element modelling. *Computational Materials Science*, 45(4):1073–1080.

Plews, J. A. and Duarte, C. A. (2015). Bridging multiple structural scales with a generalized finite element method. *International Journal for Numerical Methods in Engineering*, 102(3-4):180–201.

Ponte Castañeda, P. (2002). Second-order homogenization estimates for nonlinear composites incorporating field fluctuations: I—theory. *Journal of the Mechanics and Physics of Solids*, 50(4):737–757.

Ponte Castañeda, P., deBotton, G., and Li, G. (1992). Effective properties of nonlinear inhomogeneous dielectrics. *Physical Review B*, 46(8):4387–4394.

Ponte Castañeda, P., Willis, J. R., and Spencer, A. J. M. (1988). On the overall properties of nonlinearly viscous composites. *Proceedings of the Royal Society of London. A. Mathematical and Physical Sciences*, 416(1850):217–244.

Povirk, G. L. (1995). Incorporation of microstructural information into models of two-phase materials. *Acta Metallurgica et Materialia*, 43(8):3199–3206.

Procházka, P. (2001). Homogenization of linear and of debonding composites using the BEM. *Engineering Analysis with Boundary Elements*, 25(9):753–769.

Prudhomme, S. and Oden, J. T. (1999). On goal-oriented error estimation for elliptic problems: Application to the control of pointwise errors. *Computer Methods in Applied Mechanics and Engineering*, 176(1):313–331.

Prudhomme, S., Oden, J. T., Westermann, T., Bass, J., and Botkin, M. E. (2003). Practical methods for a posteriori error estimation in engineering applications. *International Journal for Numerical Methods in Engineering*, 56(8):1193–1224.

Raabe, D. (1998). *Computational Materials Science: The Simulation of Materials Microstructures and Properties*. Wiley-VCH.

Rachowicz, W., Oden, J. T., and Demkowicz, L. (1989). Toward a universal h-p adaptive finite element strategy part 3. design of h-p meshes. *Computer Methods in Applied Mechanics and Engineering*, 77(1):181–212.

Rahimian, M., Ehsani, N., Parvin, N., and reza Baharvandi, H. (2009). The effect of particle size, sintering temperature and sintering time on the properties of Al–Al2O3 composites, made by powder metallurgy. *Journal of Materials Processing Technology*, 209(14):5387–5393.

Raissi, M., Perdikaris, P., and Karniadakis, G. E. (2017a). Physics Informed Deep Learning (Part I): Data-driven Solutions of Nonlinear Partial Differential Equations. *arXiv:1711.10561 [cs, math, stat]*.

Raissi, M., Perdikaris, P., and Karniadakis, G. E. (2017b). Physics Informed Deep Learning (Part II): Data-driven Discovery of Nonlinear Partial Differential Equations. *arXiv:1711.10566 [cs, math, stat]*.

Rannacher, R. and Suttmeier, F.-T. (1997). A feed-back approach to error control in finite element methods: Application to linear elasticity. *Computational Mechanics*, 19(5):434–446.

Rannacher, R. and Suttmeier, F. T. (1998a). A Posteriori Error Control and Mesh Adaptation for FE models in Elasticity and Elasto-Plasticity. In *Advances in Adaptive Computational Methods in Mechanics*, number 47 in Studies in Applied Mechanics, pages 275–292. Elsevier, Amsterdam ; New York.

Rannacher, R. and Suttmeier, F.-T. (1998b). A posteriori error control in finite element methods via duality techniques: Application to perfect plasticity. *Computational Mechanics*, 21(2):123–133.

Rao, K. R., Kim, D. N., and Hwang, J. J. (2010). *Fast Fourier Transform - Algorithms and Applications*. Signals and Communication Technology. Springer Netherlands.

Reichhardt, T. (1999). It's sink or swim as a tidal wave of data approaches. *Nature*, 399(6736):517–520.

Reis, F. J. P. and Andrade Pires, F. M. (2014). A mortar based approach for the enforcement of periodic boundary conditions on arbitrarily generated meshes. *Computer Methods in Applied Mechanics and Engineering*, 274:168–191.

Reis, F. J. P., Rodrigues Lopes, I. A., Andrade Pires, F. M., and Andrade, F. X. C. (2018). Microscale analysis of heterogeneous ductile materials with nonlocal damage models of integral type. *Computers & Structures*, 201:37–57.

Renard, J. and Marmonier, M. (1987). Etude de l'initiation de l'endommagement dans la Matrice d'un mateáriau Composite par une Meáthode d'homogeánisation. *Aerosp. Sci. Technol*, 6:37–51.

Reuss, A. (1929). Berechnung der Fließgrenze von Mischkristallen auf Grund der Plastizitätsbedingung für Einkristalle . *ZAMM - Journal of Applied Mathematics and Mechanics / Zeitschrift für Angewandte Mathematik und Mechanik*, 9(1):49–58.

Rice, J. R. (1976). The localization of plastic deformation. In *In: W.T. Koiter (Ed.), Theoretical and Applied Mechanics*, pages 207–220. North-Holland Publishing Company.

Rice, J. R. and Tracey, D. M. (1969). On the ductile enlargement of voids in triaxial stress fields$_*$. *Journal of the Mechanics and Physics of Solids*, 17(3):201–217.

Richter, T. (2010). A posteriori error estimation and anisotropy detection with the dual-weighted residual method. *International Journal for Numerical Methods in Fluids*, 62(1):90–118.

Roberts, A. (1997). Statistical reconstruction of three-dimensional porous media from two-dimensional images. *Physical Review E*, 56(3):3203–3212.

Ródenas, J. J., Albelda, J., Tur, M., and Fuenmayor, F. (2017). A hierarchical h-adaptivity methodology based on element subdivision. *Revista UIS Ingenierías*, 16(2):263–280.

Ródenas, J. J., Tur, M., Fuenmayor, F. J., and Vercher, A. (2007). Improvement of the superconvergent patch recovery technique by the use of constraint equations: The SPR-C technique. *International Journal for Numerical Methods in Engineering*, 70(6):705–727.

Rodrigues Lopes, I., Andrade Pires, F., and Reis, F. (2017). A mixed parallel strategy for the solution of coupled multi-scale problems at finite strains. *Computational Mechanics*, 61.

Rodrigues Lopes, I. A. (2019). *Multi-Scale Modelling and Analysis of Multi-Phase Solids Using Second-Order Computational Homogenisation at Finite Strains with Parallel Computing*. PhD Thesis, University of Porto.

Rodríguez, R. (1994). Some remarks on Zienkiewicz-Zhu estimator. *Numerical Methods for Partial Differential Equations*, 10(5):625–635.

Rosen, B. W. and Hashin, Z. (1970). Effective thermal expansion coefficients and specific heats of composite materials. *International Journal of Engineering Science*, 8(2):157–173.

Rosenblatt, F. (1958). The perceptron: A probabilistic model for information storage and organization in the brain. *Psychological Review*, 65(6):386–408.

Rouainia, M. and Perić, D. (1998). A computational model for elasto-viscoplastic solids at finite strain with reference to thin shell applications. *International Journal for Numerical Methods in Engineering*, 42(2):289–311.

Roussette, S., Michel, J. C., and Suquet, P. (2009). Nonuniform transformation field analysis of elastic–viscoplastic composites. *Composites Science and Technology*, 69(1):22–27.

Rudykh, S. and deBotton, G. (2012). Instabilities of Hyperelastic Fiber Composites: Micromechanical Versus Numerical Analyses. *Journal of Elasticity*, 106:123–147.

Rumbaugh, J. (2005). *The Unified Modeling Language Reference Manual*. Pearson Education.

Runge, E. and Gross, E. K. U. (1984). Density-Functional Theory for Time-Dependent Systems. *Physical Review Letters*, 52(12):997–1000.

Sab, K. (1992). On the Homogenization and the Simulation of Random Materials. *Eur. J. Mech, . A/Solids*, pages 585–607.

Sachidanandam, R., Weissman, D., Schmidt, S., Kakol, J., Stein, L., Marth, G., Sherry, S., Mullikin, J., Mortimore, B., and Willey, D. (2001). A map of human genome sequence variation containing 1.42 million single nucleotide polymorphisms. *Nature*, 409:928–933.

Sachs, G. (1929). Zur Ableitung einer Fließbedingung. In Bauer, O., Hansen, M., v. Göler, F., Sachs, G., Schmid, E., Wassermann, G., Sipp, K., Sieglerschmidt, H., Karnop, R., Kuntze, W., Laute, K., Eisenschitz, R., Rabinowitsch, B., Weissenberg, K., Boas, W., and Masima, M., editors, *Mitteilungen der deutschen Materialprüfungsanstalten: Sonderheft IX: Arbeiten aus dem Kaiser Wilhelm-Institut für Metallforschung und demStaatlichen Materialprüfungsamt zu Berlin-Dahlem*, pages 94–97. Springer Berlin Heidelberg, Berlin, Heidelberg.

Saeb, S., Steinmann, P., and Javili, A. (2016). Aspects of Computational Homogenization at Finite Deformations: A Unifying Review From Reuss' to Voigt's Bound. *Applied Mechanics Reviews*, 68(5):050801.

Salnikov, V., Choï, D., and Karamian-Surville, P. (2015). On efficient and reliable stochastic generation of RVEs for analysis of composites within the framework of homogenization. *Computational Mechanics*, 55(1):127–144.

Saltelli, A., Annoni, P., Azzini, I., Campolongo, F., Ratto, M., and Tarantola, S. (2010). Variance based sensitivity analysis of model output. Design and estimator for the total sensitivity index. *Computer Physics Communications*, 181(2):259–270.

Saltelli, A., Ratto, M., Andres, T., Campolongo, F., Cariboni, J., Gatelli, D., Saisana, M., and Tarantola, S. (2008). *Global Sensitivity Analysis: The Primer*. John Wiley & Sons.

Sanchez-Palencia, E. (1974). Comportements local et macroscopique d'un type de milieux physiques heterogenes. *International Journal of Engineering Science*, 12(4):331–351.

Sandström, C., Larsson, F., Runesson, K., and Johansson, H. (2013). A two-scale finite element formulation of Stokes flow in porous media. *Computer Methods in Applied Mechanics and Engineering*, 261-262:96–104.

Santiago, J., Claeys-Bruno, M., and Sergent, M. (2012). Construction of space-filling designs using WSP algorithm for high dimensional spaces. *Chemometrics and Intelligent Laboratory Systems*, 113:26–31.

Scheunemann, L., Balzani, D., Brands, D., and Schröder, J. (2015). Design of 3D statistically similar Representative Volume Elements based on Minkowski functionals. *Mechanics of Materials*, 90:185–201.

Schneider, C. A., Rasband, W. S., and Eliceiri, K. W. (2012). NIH Image to ImageJ: 25 years of image analysis. *Nature Methods*, 9(7):671–675.

Schneider, M. (2019). On the mathematical foundations of the self-consistent clustering analysis for non-linear materials at small strains. *Computer Methods in Applied Mechanics and Engineering*, 354:783–801.

Schneider, M., Wicht, D., and Böhlke, T. (2019). On polarization-based schemes for the FFT-based computational homogenization of inelastic materials. *Computational Mechanics*, 64(4):1073–1095.

Schröder, J. (2009). Derivation of the localization and homogenization conditions for electro-mechanically coupled problems. *Computational Materials Science*, 46(3):595–599.

Schröder, J. (2014). A numerical two-scale homogenization scheme: The FE2-method. In Schröder, J. and Hackl, K., editors, *Plasticity and Beyond: Microstructures, Crystal-Plasticity and Phase Transitions*, CISM International Centre for Mechanical Sciences, pages 1–64. Springer Vienna, Vienna.

Schröder, J. and Keip, M.-A. (2010). A Framework for the Two-Scale Homogenization of Electro-Mechanically Coupled Boundary Value Problems. In Kuczma, M. and Wilmanski, K., editors, *Computer Methods in Mechanics: Lectures of the CMM 2009*, Advanced Structured Materials, pages 311–329. Springer Berlin Heidelberg, Berlin, Heidelberg.

Schröder, J., Labusch, M., and Keip, M.-A. (2016). Algorithmic two-scale transition for magneto-electro-mechanically coupled problems: FE2-scheme: Localization and homogenization. *Computer Methods in Applied Mechanics and Engineering*, 302:253–280.

Sedgewick, R. and Wayne, K. (2011). *Algorithms*. Addison-Wesley Professional.

Seelig, T. and Giessen, E. (2007). Effects of microstructure on crack tip fields and fracture toughness in PC/ABS polymer blends. *International Journal of Fracture*, 145(3):205–222.

Seelig, T. and van der Giessen, E. (2002). Localized plastic deformation in ternary polymer blends. *International Journal of Solids and Structures*, 39(13):3505–3522.

Segurado, J. and Llorca, J. (2002). A numerical approximation to the elastic properties of sphere-reinforced composites. *Journal of the Mechanics and Physics of Solids*, 50(10):2107–2121.

Segurado, J. and LLorca, J. (2006). Computational micromechanics of composites: The effect of particle spatial distribution. *Mechanics of Materials*, 38(8):873–883.

Selvam, J. D., Dinaharan, I., and Rai, R. S. (2021). Matrix and Reinforcement Materials for Metal Matrix Composites. In *Reference Module in Materials Science and Materials Engineering*, page B9780128035818118909. Elsevier.

Senior, A. W., Evans, R., Jumper, J., Kirkpatrick, J., Sifre, L., Green, T., Qin, C., Žídek, A., Nelson, A. W. R., Bridgland, A., Penedones, H., Petersen, S., Simonyan, K., Crossan, S., Kohli, P., Jones, D. T., Silver, D., Kavukcuoglu, K., and Hassabis, D. (2020). Improved protein structure prediction using potentials from deep learning. *Nature*, 577(7792):706–710.

Shahba, A. and Ghosh, S. (2019). Coupled phase field finite element model for crack propagation in elastic polycrystalline microstructures. *International Journal of Fracture*.

Shakoor, M., Kafka, O. L., Yu, C., and Liu, W. K. (2019). Data science for finite strain mechanical science of ductile materials. *Computational Mechanics*, 64(1):33–45.

Shalev-Shwartz, S. and Ben-David, S. (2014). *Understanding Machine Learning: From Theory to Algorithms*. Cambridge University Press, New York, NY, USA, 1 edition edition.

Shan, Z. and Gokhale, A. M. (2002). Representative volume element for non-uniform micro-structure. *Computational Materials Science*, 24(3):361–379.

Sharma, P., Sharma, S., and Khanduja, D. (2015). Production and some properties of Si_3N_4 reinforced aluminium alloy composites. *Journal of Asian Ceramic Societies*, 3(3):352–359.

Shen, F., Kang, G., Lam, Y. C., Liu, Y., and Zhou, K. (2019). Thermo-elastic-viscoplastic-damage model for self-heating and mechanical behavior of thermoplastic polymers. *International Journal of Plasticity*, 121:227–243.

Shen, H. and Brinson, L. C. (2006). A numerical investigation of the effect of boundary conditions and representative volume element size for porous titanium. *Journal of Mechanics of Materials and Structures*, 1(7):1179–1204.

Shirvanimoghaddam, K., Hamim, S. U., Karbalaei Akbari, M., Fakhrhoseini, S. M., Khayyam, H., Pakseresht, A. H., Ghasali, E., Zabet, M., Munir, K. S., Jia, S., Davim, J. P., and Naebe, M. (2017). Carbon fiber reinforced metal matrix composites: Fabrication processes and properties. *Composites Part A: Applied Science and Manufacturing*, 92:70–96.

Shlush, L. I., Zandi, S., Mitchell, A., Chen, W. C., Brandwein, J. M., Gupta, V., Kennedy, J. A., Schimmer, A. D., Schuh, A. C., Yee, K. W., McLeod, J. L., Doedens, M., Medeiros, J. J. F., Marke, R., Kim, H. J., Lee, K., McPherson, J. D., Hudson, T. J., Pan-Leukemia Gene Panel Consortium, T. H., Brown, A. M. K., Yousif, F., Trinh, Q. M., Stein, L. D., Minden, M. D., Wang, J. C. Y., and Dick, J. E. (2014). Identification of pre-leukaemic haematopoietic stem cells in acute leukaemia. *Nature*, 506(7488):328–333.

Shojaei, A. K. and Volgers, P. (2018). A coupled hyperelastic-plastic-continuum damage model for studying cyclic behavior of unfilled engineering polymers. *International Journal of Fatigue*, 107:33–39.

Silver, D., Hubert, T., Schrittwieser, J., Antonoglou, I., Lai, M., Guez, A., Lanctot, M., Sifre, L., Kumaran, D., Graepel, T., Lillicrap, T., Simonyan, K., and Hassabis, D. (2017a). Mastering Chess and Shogi by Self-Play with a General Reinforcement Learning Algorithm. *arXiv:1712.01815 [cs]*.

Silver, D., Schrittwieser, J., Simonyan, K., Antonoglou, I., Huang, A., Guez, A., Hubert, T., Baker, L., Lai, M., Bolton, A., Chen, Y., Lillicrap, T., Hui, F., Sifre, L., van den Driessche, G., Graepel, T., and Hassabis, D. (2017b). Mastering the game of Go without human knowledge. *Nature*, 550(7676):354–359.

Simo, J. C. (1985). On the computational significance of the intermediate configuration and hyperelastic stress relations in finite deformation elastoplasticity. *Mechanics of Materials*, 4(3):439–451.

Simo, J. C. (1987). On a fully three-dimensional finite-strain viscoelastic damage model: Formulation and computational aspects. *Computer Methods in Applied Mechanics and Engineering*, 60(2):153–173.

Simo, J. C. and Hughes, T. J. R. (1998). *Computational Inelasticity*. Interdisciplinary Applied Mathematics. Springer-Verlag, New York.

Simo, J. C., Oliver, J., and Armero, F. (1993). An analysis of strong discontinuities induced by strain-softening in rate-independent inelastic solids. *Computational Mechanics*, 12(5):277–296.

Simo, J. C. and Ortiz, M. (1985). A unified approach to finite deformation elastoplastic analysis based on the use of hyperelastic constitutive equations. *Computer Methods in Applied Mechanics and Engineering*, 49(2):221–245.

Simpson, T. and Lin, D. (2001). Sampling Strategies for Computer Experiments: Design and Analysis. *Int. J. Reliab. Appl.*, 2.

Simpson, T., Poplinski, J., Koch, P. N., and Allen, J. (2001). Metamodels for Computer-based Engineering Design: Survey and recommendations. *Engineering with Computers*, 17(2):129–150.

Smit, R. J. M., Brekelmans, W. A. M., and Meijer, H. E. H. (1998). Prediction of the mechanical behavior of nonlinear heterogeneous systems by multi-level finite element modeling. *Computer Methods in Applied Mechanics and Engineering*, 155(1):181–192.

Sobol, I. M. (1967). On the distribution of points in a cube and the approximate evaluation of integrals. *USSR Computational Mathematics and Mathematical Physics*, 7(4):86–112.

Sobol, I. M. (1976). Uniformly distributed sequences with an additional uniform property. *USSR Computational Mathematics and Mathematical Physics*, 16(5):236–242.

Solinc, U. and Korelc, J. (2015). A simple way to improved formulation of FE2 analysis. *Computational Mechanics*, 56.

Spahn, J., Andrä, H., Kabel, M., and Müller, R. (2014). A multiscale approach for modeling progressive damage of composite materials using fast Fourier transforms. *Computer Methods in Applied Mechanics and Engineering*, 268:871–883.

Sperling, L. H. (2006). *Introduction to Physical Polymer Science*. Wiley, Hoboken, N.J, 4th ed edition.

Spieler, C., Kästner, M., Goldmann, J., Brummund, J., and Ulbricht, V. (2013). XFEM modeling and homogenization of magnetoactive composites. *Acta Mechanica*, 224(11):2453–2469.

Srivastava, V., Chester, S. A., Ames, N. M., and Anand, L. (2010). A thermo-mechanically-coupled large-deformation theory for amorphous polymers in a temperature range which spans their glass transition. *International Journal of Plasticity*, 26(8):1138–1182.

Staum, J. (2009). Better simulation metamodeling: The why, what, and how of stochastic kriging. In *Proceedings of the 2009 Winter Simulation Conference (WSC)*, pages 119–133.

Steenbrink, A. C., Van Der Giessen, E., and Wu, P. D. (1997). Void growth in glassy polymers. *Journal of the Mechanics and Physics of Solids*, 45(3):405–437.

Stein, E., editor (2005). *Adaptive Finite Elements in Linear and Nonlinear Solid and Structural Mechanics*. CISM International Centre for Mechanical Sciences. Springer-Verlag, Wien.

Stein, E., Barthold, F. J., Ohnimus, S., and Schmidt, M. (1998). Adaptive finite elements in elastoplasticity with mechanical error indicators and Neumann-type estimators. In *Advances in Adaptive Computational Methods in Mechanics*, number 47 in Studies in Applied Mechanics, pages 81–99. Elsevier, Amsterdam ; New York.

Steinmann, P. and Willam, K. (1992). Adaptive Techniques for Localization Analysis. *undefined*.

Stupkiewicz, S., Lewandowski, M. J., and Lengiewicz, J. (2014). Micromechanical analysis of friction anisotropy in rough elastic contacts. *International Journal of Solids and Structures*, 51(23):3931–3943.

Suquet, P. (1985). Elements of homogenization for inelastic solid mechanics. *Springer*.

Suquet, P. M. (1993). Overall potentials and extremal surfaces of power law or ideally plastic composites. *Journal of the Mechanics and Physics of Solids*, 41(6):981–1002.

Swaminathan, S. and Ghosh, S. (2006). Statistically Equivalent Representative Volume Elements for Unidirectional Composite Microstructures: Part II - With Interfacial Debonding. *Journal of Composite Materials*, 40.

Swaminathan, S., Ghosh, S., and Pagano, N. (2006). Statistically equivalent representative volume elements for unidirectional composite microstructures: Part I-Without damage. *Journal of Composite Materials*, 40.

Tadmor, E. B., Miller, R. E., and Elliott, R. S. (2012). *Continuum Mechanics and Thermodynamics: From Fundamental Concepts to Governing Equations*. Cambridge University Press, Cambridge, UK ; New York.

Tadmor, E. B., Ortiz, M., and Phillips, R. (1996). Quasicontinuum analysis of defects in solids. *Philosophical Magazine A*, 73(6):1529–1563.

Tahmasebi, P. and Sahimi, M. (2013). Cross-Correlation Function for Accurate Reconstruction of Heterogeneous Media. *Physical Review Letters*, 110(7):078002.

Takano, N., Ohnishi, Y., Zako, M., and Nishiyabu, K. (2000). The formulation of homogenization method applied to large deformation problem for composite materials. *International Journal of Solids and Structures*, 37(44):6517–6535.

Tang, S., Zhang, L., and Liu, W. K. (2018). From virtual clustering analysis to self-consistent clustering analysis: A mathematical study. *Computational Mechanics*, 62(6):1443–1460.

Taylor, G. I. (1938). Plastic Strain in Metals. *Journal of the Institute of Metals*, 62:307–327.

Temizer, İ. (2012). On the asymptotic expansion treatment of two-scale finite thermoelasticity. *International Journal of Engineering Science*, 53:74–84.

Temizer, İ. (2014). Multiscale thermomechanical contact: Computational homogenization with isogeometric analysis. *International Journal for Numerical Methods in Engineering*, 97.

Temizer, İ. and Wriggers, P. (2008). A multiscale contact homogenization technique for the modeling of third bodies in the contact interface. *Computer Methods in Applied Mechanics and Engineering*, 198:377–396.

Temizer, İ. and Wriggers, P. (2011a). An adaptive multiscale resolution strategy for the finite deformation analysis of microheterogeneous structures. *Computer Methods in Applied Mechanics and Engineering*, 200(37):2639–2661.

Temizer, İ. and Wriggers, P. (2011b). Homogenization in finite thermoelasticity. *Journal of the Mechanics and Physics of Solids*, 59(2):344–372.

Temizer, İ., Wu, T., and Wriggers, P. (2013). On the optimality of the window method in computational homogenization. *International Journal of Engineering Science*, 64:66–73.

Temizer, I. and Zohdi, T. I. (2007). A numerical method for homogenization in non-linear elasticity. *Computational Mechanics*, 40(2):281–298.

Terada, K., Hori, M., Kyoya, T., and Kikuchi, N. (2000). Simulation of the multi-scale convergence in computational homogenization approaches. *International Journal of Solids and Structures*, 37(16):2285–2311.

Terada, K. and Kikuchi, N. (1995). Nonlinear homogenization method for practical applications. *American Society of Mechanical Engineers, Applied Mechanics Division, AMD*, 212:1–16.

Terada, K. and Kikuchi, N. (1996). Microstructural Design of Composites Using the Homogenization Method and Digital Images. *Journal of the Society of Materials Science*, 45(6Appendix):65–72.

Terada, K. and Kikuchi, N. (2001). A class of general algorithms for multi-scale analyses of heterogeneous media. *Computer Methods in Applied Mechanics and Engineering*, 190(40):5427–5464.

Terada, K., Kurumatani, M., Ushida, T., and Kikuchi, N. (2010). A method of two-scale thermo-mechanical analysis for porous solids with micro-scale heat transfer. *Computational Mechanics*, 46(2):269–285.

Terada, K., Saiki, I., Matsui, K., and Yamakawa, Y. (2003). Two-scale kinematics and linearization for simultaneous two-scale analysis of periodic heterogeneous solids at finite strain. *Computer Methods in Applied Mechanics and Engineering*, 192(31):3531–3563.

Tervoort, T. (1996). *Constitutive Modelling of Polymer Glasses: Finite, Nonlinear Viscoelastic Behaviour of Polycarbonate*. PhD Thesis, Einhoven University of Technology, The Netherlands.

Tervoort, T., Smit, R., Brekelmans, W., and Govaert, L. (1997). A Constitutive Equation for the Elasto-Viscoplastic Deformation of Glassy Polymers. *Mechanics of Time-Dependent Materials*, 1(3):269–291.

Theodoridis, S. and Koutroumbas, K. (2008). *Pattern Recognition*. Academic Press.

Thomas, S., Grohens, Y., and Jyotishkumar, P., editors (2014). *Characterization of Polymer Blends: Miscibility, Morphology and Interfaces*. Wiley-VCH, Weinheim, Germany, first edition.

Timmermans, P. H. M. (1997). *Evaluation of a Constitutive Model for Solid Polymeric Materials: Model Selection and Parameter Quantification*. PhD thesis, Eindhoven University of Technology.

Toptan, F., Kilicarslan, A., Karaaslan, A., Cigdem, M., and Kerti, I. (2010). Processing and microstructural characterisation of AA 1070 and AA 6063 matrix B4Cp reinforced composites. *Materials & Design*, 31:S87–S91.

Torquato, S. (1991). Random Heterogeneous Media: Microstructure and Improved Bounds on Effective Properties. *Applied Mechanics Reviews*, 44(2):37–76.

Torquato, S. (2013). *Random Heterogeneous Materials: Microstructure and Macroscopic Properties*. Springer Science & Business Media.

Torquato, S. and Jiao, Y. (2009). Dense packings of the Platonic and Archimedean solids. *Nature*, 460(7257):876–879.

Tseng, H.-C., Chang, R.-Y., and Hsu, C.-H. (2018). Numerical predictions of fiber orientation and mechanical properties for injection-molded long-carbon-fiber thermoplastic composites. *Polymer Composites*, 39(10):3726–3739.

Tuckerman, M. (2010). *Statistical Mechanics: Theory and Molecular Simulation*. OUP Oxford.

Turteltaub, S. and Suiker, A. S. J. (2005). Transformation-induced plasticity in ferrous alloys. *Journal of the Mechanics and Physics of Solids*, 53(8):1747–1788.

Turteltaub, S. and Suiker, A. S. J. (2006). A multiscale thermomechanical model for cubic to tetragonal martensitic phase transformations. *International Journal of Solids and Structures*, 43(14):4509–4545.

Tvergaard, V. (1981). Influence of voids on shear band instabilities under plane strain conditions. *International Journal of Fracture*, 17(4):389–407.

Tvergaard, V. (1982). On localization in ductile materials containing spherical voids. *International Journal of Fracture*, 18(4):237–252.

Tvergaard, V. (1987). Effect of yield surface curvature and void nucleation on plastic flow localization. *Journal of the Mechanics and Physics of Solids*, 35(1):43–60.

Tvergaard, V. (1990). Effect of fibre debonding in a whisker-reinforced metal. *Materials Science and Engineering: A*, 125(2):203–213.

Tvergaard, V. and Needleman, A. (1984). Analysis of the cup-cone fracture in a round tensile bar. *Acta Metallurgica*, 32(1):157–169.

Ubertini, F. (2004). Patch recovery based on complementary energy. *International Journal for Numerical Methods in Engineering*, 59(11):1501–1538.

Uchida, M., Kamimura, K., Yoshida, T., and Kaneko, Y. (2022). Viscoelastic-viscoplastic modeling of epoxy based on transient network theory. *International Journal of Plasticity*, 153:103262.

Uchida, M., Wakuda, R., and Kaneko, Y. (2019). Evaluation and modeling of mechanical behaviors of thermosetting polymer under monotonic and cyclic tensile tests. *Polymer*, 174:130–142.

van Breemen, L. C. A., Engels, T. A. P., Klompen, E. T. J., Senden, D. J. A., and Govaert, L. E. (2012). Rate- and temperature-dependent strain softening in solid polymers. *Journal of Polymer Science Part B: Polymer Physics*, 50(24):1757–1771.

van Breemen, L. C. A., Klompen, E. T. J., Govaert, L. E., and Meijer, H. E. H. (2011). Extending the EGP constitutive model for polymer glasses to multiple relaxation times. *Journal of the Mechanics and Physics of Solids*, 59(10):2191–2207.

Van der Giessen, E. and Seelig, T. (2015). Computational modeling of rubber-toughening in amorphous thermoplastic polymers: A review. *International Journal of Fracture*, 196(1-2):207–222.

Van Houtte, P. (1982). On the equivalence of the relaxed Taylor theory and the Bishop-Hill theory for partially constrained plastic deformation of crystals. *Materials Science and Engineering*, 55(1):69–77.

van Melick, H. G. H., Govaert, L. E., and Meijer, H. E. H. (2003a). Localisation phenomena in glassy polymers: Influence of thermal and mechanical history. *Polymer*, 44(12):3579–3591.

van Melick, H. G. H., Govaert, L. E., and Meijer, H. E. H. (2003b). On the origin of strain hardening in glassy polymers. *Polymer*, 44(8):2493–2502.

van Tuijl, R. A., Harnish, C., Matouš, K., Remmers, J. J. C., and Geers, M. G. D. (2019). Wavelet based reduced order models for microstructural analyses. *Computational Mechanics*, 63(3):535–554.

Vaughan, T. and McCarthy, C. (2010). A combined experimental–numerical approach for generating statistically equivalent fibre distributions for high strength laminated composite materials. *Composites Science and Technology*, 70(2):291–297.

Ventelon, L. and Willaime, F. (2010). Generalized stacking-faults and screw-dislocation core-structure in bcc iron: A comparison between ab initio calculations and empirical potentials. *Philosophical Magazine*, 90(7-8):1063–1074.

Verfürth, R. (1994). A posteriori error estimation and adaptive mesh-refinement techniques. *Journal of Computational and Applied Mathematics*, 50(1):67–83.

Verfürth, R. (1998). A Review of A Posteriori Error Estimation Techniques for Elasticity Problems. In *Advances in Adaptive Computational Methods in Mechanics*, number 47 in Studies in Applied Mechanics. Elsevier, Amsterdam ; New York.

Verhoosel, C., Remmers, J., Gutierrez, M., and Borst, R. (2010). Computational homogenization for adhesive and cohesive failure in quasi-brittle solids. *International Journal for Numerical Methods in Engineering*, 83:1155–1179.

Veubeke, B. F. D. (1966). Bending and stretching of plates special models for upper and lower bounds. *undefined*.

Voigt, W. (1889). Ueber die Beziehung zwischen den beiden Elasticitätsconstanten isotroper Körper. *Annalen der Physik*, 274(12):573–587.

Wagner, P., Wriggers, P., Veltmaat, L., Clasen, H., Prange, C., and Wies, B. (2017). Numerical multiscale modelling and experimental validation of low speed rubber friction on rough road surfaces including hysteretic and adhesive effects. *Tribology International*, 111:243–253.

Walpole, L. J. (1966a). On bounds for the overall elastic moduli of inhomogeneous systems—I. *Journal of the Mechanics and Physics of Solids*, 14(3):151–162.

Walpole, L. J. (1966b). On bounds for the overall elastic moduli of inhomogeneous systems—II. *Journal of the Mechanics and Physics of Solids*, 14(5):289–301.

Walpole, L. J. (1969). On the overall elastic moduli of composite materials. *Journal of the Mechanics and Physics of Solids*, 17(4):235–251.

Wang, J., O'Gara, J. F., and Tucker, C. L. (2008). An objective model for slow orientation kinetics in concentrated fiber suspensions: Theory and rheological evidence. *Journal of Rheology*, 52(5):1179–1200.

Wang, J., Peng, L. F., Deng, Y. J., Lai, X. M., Fu, M. W., and Ni, J. (2019a). A finite strain thermodynamically-based constitutive modeling and analysis of viscoelastic-viscoplastic deformation behavior of glassy polymers. *International Journal of Plasticity*, 122:135–163.

Wang, W., Wang, J., and Kim, M.-S. (2001). An algebraic condition for the separation of two ellipsoids. *Computer Aided Geometric Design*, 18(6):531–539.

Wang, X., Gong, J., An, A., Zhang, K., and Nie, Z. (2019b). Random generation of convex granule packing based on weighted Voronoi tessellation and cubic-polynomial-curve fitting. *Computers and Geotechnics*, 113:103088.

Wang, Z., Guo, J., Seppala, J. E., and Nguyen, T. D. (2021). Extending the effective temperature model to the large strain hardening behavior of glassy polymers. *Journal of the Mechanics and Physics of Solids*, 146:104175.

Wasserman, L. (2018). Topological Data Analysis. *Annual Review of Statistics and its Application*, 5(1):501–532.

Weinan, E. (2011). *Principles of Multiscale Modeling*. Cambridge University Press.

Wen, J., Huang, Y., Hwang, K. C., Liu, C., and Li, M. (2005). The modified Gurson model accounting for the void size effect. *International Journal of Plasticity*, 21(2):381–395.

Wiberg, N.-E., Abdulwahab, F., and Ziukas, S. (1994). Enhanced superconvergent patch recovery incorporating equilibrium and boundary conditions. *International Journal for Numerical Methods in Engineering*, 37(20):3417–3440.

Widrow, B. and Hoff, M. E. (1988). Adaptive switching circuits. In Anderson, J. A. and Rosenfeld, E., editors, *Neurocomputing: Foundations of Research*, pages 123–134. MIT Press, Cambridge, MA, USA.

Willis, J. R. (1977). Bounds and self-consistent estimates for the overall properties of anisotropic composites. *Journal of the Mechanics and Physics of Solids*, 25(3):185–202.

Willis, J. R. (1981). Variational and Related Methods for the Overall Properties of Composites. In Yih, C.-S., editor, *Advances in Applied Mechanics*, volume 21, pages 1–78. Elsevier.

Willis, J. R. (1986). Variational Estimates for the Overall Response of an Inhomogeneous Nonlinear Dielectric. In Ericksen, J. L., Kinderlehrer, D., Kohn, R., and Lions, J.-L., editors, *Homogenization and Effective Moduli of Materials and Media*, The IMA Volumes in Mathematics and Its Applications, pages 247–263. Springer New York.

Wongsto, A. and Li, S. (2005). Micromechanical FE analysis of UD fibre-reinforced composites with fibres distributed at random over the transverse cross-section. *Composites Part A: Applied Science and Manufacturing*, 36(9):1246–1266.

Wriggers, P. (2008). *Nonlinear Finite Element Methods*. Springer Science & Business Media.

Wriggers, P. and Simo, J. C. (1990). A general procedure for the direct computation of turning and bifurcation points. *International Journal for Numerical Methods in Engineering*, 30(1):155–176.

Wu, J., Yuan, Y., Gong, H., and Tseng, T.-L. B. (2018). Inferring 3D ellipsoids based on cross-sectional images with applications to porosity control of additive manufacturing. *IISE Transactions*, 50(7):570–583.

Wu, J. J. and Buckley, C. P. (2004). Plastic deformation of glassy polystyrene: A unified model of yield and the role of chain length. *Journal of Polymer Science Part B: Polymer Physics*, 42(11):2027–2040.

Wu, S. (1985). Phase structure and adhesion in polymer blends: A criterion for rubber toughening. *Polymer*, 26(12):1855–1863.

Wu, S., Rupprecht, C., and Vedaldi, A. (2020). Unsupervised Learning of Probably Symmetric Deformable 3D Objects From Images in the Wild. In *2020 IEEE/CVF Conference on Computer Vision and Pattern Recognition (CVPR)*, pages 1–10, Seattle, WA, USA. IEEE.

Wu, Z., Francis, M. F., and Curtin, W. A. (2014). Magnesium interatomic potential for simulating plasticity and fracture phenomena. *Modelling and Simulation in Materials Science and Engineering*, 23(1):015004.

Wulfinghoff, S., Cavaliere, F., and Reese, S. (2017). Model order reduction of nonlinear homogenization problems using a Hashin-Shtrikman type finite element method. *Computer Methods in Applied Mechanics and Engineering*, 330.

Wunderlich, W., Cramer, H., and Steinl, G. (1998). An adaptive finite element approach in associated and non-associated plasticity considering localization phenomena. In *Advances in Adaptive Computational Methods in Mechanics*, number 47 in Studies in Applied Mechanics. Elsevier, Amsterdam ; New York.

Xiao, R. and Nguyen, T. D. (2015). An effective temperature theory for the nonequilibrium behavior of amorphous polymers. *Journal of the Mechanics and Physics of Solids*, 82:62–81.

Xu, H., Li, Y., Brinson, C., and Chen, W. (2014). A Descriptor-Based Design Methodology for Developing Heterogeneous Microstructural Materials System. *Journal of Mechanical Design*, 136(5).

Xu, H., Liu, R., Choudhary, A., and Chen, W. (2015). A Machine Learning-Based Design Representation Method for Designing Heterogeneous Microstructures. *Journal of Mechanical Design*, 137(5).

Yamakov, V., Wolf, D., Phillpot, S., Mukherjee, A., and Gleiter, H. (2002). Dislocation processes in the deformation of nanocrystalline aluminium by molecular-dynamics simulation. *Nature materials*, 1:45–8.

Yan, W., Lian, Y., Yu, C., Kafka, O. L., Liu, Z., Liu, W. K., and Wagner, G. J. (2018a). An integrated process–structure–property modeling framework for additive manufacturing. *Computer Methods in Applied Mechanics and Engineering*, 339:184–204.

Yan, W., Lin, S., Kafka, O. L., Lian, Y., Yu, C., Liu, Z., Yan, J., Wolff, S., Wu, H., Ndip-Agbor, E., Mozaffar, M., Ehmann, K., Cao, J., Wagner, G. J., and Liu, W. K. (2018b). Data-driven multi-scale multi-physics models to derive process–structure–property relationships for additive manufacturing. *Computational Mechanics*, 61(5):521–541.

Yan, W., Lin, S., Kafka, O. L., Yu, C., Liu, Z., Lian, Y., Wolff, S., Cao, J., Wagner, G. J., and Liu, W. K. (2018c). Modeling process-structure-property relationships for additive manufacturing. *Frontiers of Mechanical Engineering*, 13(4):482–492.

Yanase, K. and Ju, J.-W. (2012). Effective Elastic Moduli of Spherical Particle Reinforced Composites Containing Imperfect Interfaces. *International Journal of Damage Mechanics*, 21:97–127.

Yasi, J. A., Nogaret, T., Trinkle, D. R., Qi, Y., Hector, L. G., and Curtin, W. A. (2009). Basal and prism dislocation cores in magnesium: Comparison of first-principles and embedded-atom-potential methods predictions. *Modelling and Simulation in Materials Science and Engineering*, 17(5):055012.

Yee, A. F. and Pearson, R. A. (1986). Toughening mechanisms in elastomer-modified epoxies. *Journal of Materials Science*, 21(7):2462–2474.

Yeong, C. L. Y. and Torquato, S. (1998). Reconstructing random media. *Physical Review E*, 57(1):495–506.

Yu, C., Kafka, O. L., and Liu, W. K. (2019). Self-consistent clustering analysis for multiscale modeling at finite strains. *Computer Methods in Applied Mechanics and Engineering*, 349:339–359.

Yu, C., Kafka, O. L., and Liu, W. K. (2021). Multiresolution clustering analysis for efficient modeling of hierarchical material systems. *Computational Mechanics*, 67(5):1293–1306.

Yu, C., Kang, G., Chen, K., and Lu, F. (2017). A thermo-mechanically coupled nonlinear viscoelastic–viscoplastic cyclic constitutive model for polymeric materials. *Mechanics of Materials*, 105:1–15.

Yu, J., Peric, D., and Owen, D. R. J. (1991). An Assessment of the Cosserat Continuum through the Finite Element Simulation of a Strain Localisation Problem. In Oñate, E., Periaux, J., and Samuelsson, A., editors, *The Finite Element Method in the 1990's: A Book Dedicated to O.C. Zienkiewicz*, pages 321–332. Springer, Berlin, Heidelberg.

Yu, P., Yao, X., Han, Q., Zang, S., and Gu, Y. (2014). A visco-elastoplastic constitutive model for large deformation response of polycarbonate over a wide range of strain rates and temperatures. *Polymer*, 55(25):6577–6593.

Yu, P., Yao, X., Tan, S., and Han, Q. (2016). A Macro-Damaged Viscoelastoplastic Model for Thermomechanical and Rate-Dependent Behavior of Glassy Polymers. *Macromolecular Materials and Engineering*, 301(4):469–485.

Yu, Q. and Fish, J. (2002). Temporal homogenization of viscoelastic and viscoplastic solids subjected to locally periodic loading. *Computational Mechanics*, 29(3):199–211.

Yuan, Y., VanderWerf, K., Shattuck, M. D., and O'Hern, C. S. (2019). Jammed packings of 3D superellipsoids with tunable packing fraction, coordination number, and ordering. *Soft Matter*, 15(47):9751–9761.

Yvonnet, J. (2012). A fast method for solving microstructural problems defined by digital images: A space Lippmann-Schwinger scheme: THE SLS METHOD. *International Journal for Numerical Methods in Engineering*, 92(2):178–205.

Yvonnet, J., Gonzalez, D., and He, Q. C. (2009). Numerically explicit potentials for the homogenization of nonlinear elastic heterogeneous materials. *Computer Methods in Applied Mechanics and Engineering*, 198(33):2723–2737.

Yvonnet, J. and He, Q.-C. (2007). The reduced model multiscale method (R3M) for the non-linear homogenization of hyperelastic media at finite strains. *Journal of Computational Physics*, 223(1):341–368.

Yvonnet, J., Monteiro, E., and He, Q.-C. (2013). Computational homogenization method and reduced database model for hyperelastic heterogeneous structures. *International Journal for Multiscale Computational Engineering*, 11.

Zäh, D. and Miehe, C. (2013). Computational homogenization in dissipative electro-mechanics of functional materials. *Computer Methods in Applied Mechanics and Engineering*, 267:487–510.

Zaïri, F., Naït-Abdelaziz, M., Gloaguen, J. M., and Lefebvre, J. M. (2008). Modelling of the elasto-viscoplastic damage behaviour of glassy polymers. *International Journal of Plasticity*, 24(6):945–965.

Zaïri, F., Naït-Abdelaziz, M., Gloaguen, J. M., and Lefebvre, J. M. (2011). A physically-based constitutive model for anisotropic damage in rubber-toughened glassy polymers during finite deformation. *International Journal of Plasticity*, 27(1):25–51.

Zaïri, F., Naït-Abdelaziz, M., Woznica, K., and Gloaguen, J.-M. (2005). Constitutive equations for the viscoplastic-damage behaviour of a rubber-modified polymer. *European Journal of Mechanics - A/Solids*, 24(1):169–182.

Zeller, R. and Dederichs, P. H. (1973). Elastic Constants of Polycrystals. *physica status solidi (b)*, 55(2):831–842.

Zeman, J., de Geus, T. W. J., Vondřejc, J., Peerlings, R. H. J., and Geers, M. G. D. (2017). A finite element perspective on nonlinear FFT-based micromechanical simulations. *International Journal for Numerical Methods in Engineering*, 111(10):903–926.

Zeman, J., Vondřejc, J., Novák, J., and Marek, I. (2010). Accelerating a FFT-based solver for numerical homogenization of periodic media by conjugate gradients. *Journal of Computational Physics*, 229(21):8065–8071.

Zhang, H. W., Wu, J. K., and Lv, J. (2012). A new multiscale computational method for elasto-plastic analysis of heterogeneous materials. *Computational Mechanics*, 49(2):149–169.

Zhang, H. W., Zhang, S., Bi, J. Y., and Schrefler, B. A. (2007). Thermo-mechanical analysis of periodic multiphase materials by a multiscale asymptotic homogenization approach. *International Journal for Numerical Methods in Engineering*, 69(1):87–113.

Zhang, M., Benítez, J. M., and Montáns, F. J. (2016). Capturing yield surface evolution with a multilinear anisotropic kinematic hardening model. *International Journal of Solids and Structures*, 81:329–336.

Zhang, P. and To, A. C. (2016). Transversely isotropic hyperelastic-viscoplastic model for glassy polymers with application to additive manufactured photopolymers. *International Journal of Plasticity*, 80:56–74.

Zhang, Z. (1996a). Mathematical analysis of Zienkiewicz—Zhu's derivative patch recovery technique. *Numerical Methods for Partial Differential Equations*, 12(4):507–524.

Zhang, Z. (1996b). Ultraconvergence of the Patch Recovery Technique. *Mathematics of Computation*, 65(216):1431–1437.

Zhu, J. Z. (1997). A posteriori error estimation—the relationship between different procedures. *Computer Methods in Applied Mechanics and Engineering*, 150(1):411–422.

Zhu, J. Z., Hinton, E., and Zienkiewicz, O. C. (1993). Mesh enrichment against mesh regeneration using quadrilateral elements. *Communications in Numerical Methods in Engineering*, 9(7).

Zhu, J. Z. and Zhang, Z. (1998). The relationship of some a posteriori error estimators. In *Advances in Adaptive Computational Methods in Mechanics*, number 47 in Studies in Applied Mechanics. Elsevier, Amsterdam ; New York.

Zhu, J. Z. and Zienkiewicz, O. C. (1990). Superconvergence recovery technique and a posteriori error estimators. *International Journal for Numerical Methods in Engineering*, 30(7):1321–1339.

Zhu, Q. and Zhao, Q. (2003). SPR technique and finite element correction. *Numerische Mathematik*, 96(1):185–196.

Zhu, X., Zhang, L., and Tang, S. (2021). Adaptive selection of reference stiffness in virtual clustering analysis. *Computer Methods in Applied Mechanics and Engineering*, 376:113621.

Zi, G. and Belytschko, T. (2003). New crack-tip elements for XFEM and applications to cohesive cracks. *International Journal for Numerical Methods in Engineering*, 57(15):2221–2240.

Zienkiewicz, O. C. (2001). Displacement and equilibrium models in the finite element method by B. Fraeijs de Veubeke, Chapter 9, Pages 145–197 of Stress Analysis, Edited by O. C. Zienkiewicz and G. S. Holister, Published by John Wiley \& Sons, 1965. *International Journal for Numerical Methods in Engineering*, 52(3):287–342.

Zienkiewicz, O. C. and Cormeau, I. C. (1974). Visco-plasticity—plasticity and creep in elastic solids—a unified numerical solution approach. *International Journal for Numerical Methods in Engineering*, 8(4):821–845.

Zienkiewicz, O. C., Huang, M., and Pastor, M. (1995a). Localization problems in plasticity using finite elements with adaptive remeshing. *International Journal for Numerical and Analytical Methods in Geomechanics*, 19(2):127–148.

Zienkiewicz, O. C., Pastor, M., and Huang, M. (1995b). Softening, localisation and adaptive remeshing. Capture of discontinuous solutions. *Computational Mechanics*, 17(1):98–106.

Zienkiewicz, O. C., Taylor, R. L., and Fox, D. (2014). *The Finite Element Method for Solid and Structural Mechanics*. Elsevier/Butterworth-Heinemann, Amsterdam ; Boston, 7th ed edition.

Zienkiewicz, O. C., Taylor, R. L., and Zhu, J. Z. (2013). *The Finite Element Method: Its Basis and Fundamentals*. Elsevier, Butterworth-Heinemann, Amsterdam, seventh edition edition.

Zienkiewicz, O. C. and Wu, J. (1994). Automatic directional refinement in adaptive analysis of compressible flows. *International Journal for Numerical Methods in Engineering*, 37(13):2189–2210.

Zienkiewicz, O. C. and Zhu, J. Z. (1987). A simple error estimator and adaptive procedure for practical engineerng analysis. *International Journal for Numerical Methods in Engineering*, 24(2):337–357.

Zienkiewicz, O. C. and Zhu, J. Z. (1992a). The superconvergent patch recovery and a posteriori error estimates. Part 1: The recovery technique. *International Journal for Numerical Methods in Engineering*, 33(7):1331–1364.

Zienkiewicz, O. C. and Zhu, J. Z. (1992b). The superconvergent patch recovery and a posteriori error estimates. Part 2: Error estimates and adaptivity. *International Journal for Numerical Methods in Engineering*, 33(7):1365–1382.

Zienkiewicz, O. C. and Zhu, J. Z. (1992c). The superconvergent patch recovery (SPR) and adaptive finite element refinement. *Computer Methods in Applied Mechanics and Engineering*, 101(1):207–224.

Zienkiewicz, O. C., Zhu, J. Z., and Gong, N. G. (1989). Effective and practical h–p-version adaptive analysis procedures for the finite element method. *International Journal for Numerical Methods in Engineering*, 28(4):879–891.

Zimmerman, R. W. (1992). Hashin-Shtrikman bounds on the poisson ratio of a composite material. *Mechanics Research Communications*, 19(6):563–569.

Zinchenko, A. Z. (1994). Algorithm for Random Close Packing of Spheres with Periodic Boundary Conditions. *Journal of Computational Physics*, 114(2):298–307.

Appendix A
Notes on Micromechanics

Despite the simplicity of the Self-Consistent Clustering Analysis (Liu et al., 2016), the author believes that the understanding of some its underlying concepts requires a previous background on micromechanics. In this regard, some fundamentals on micromechanics are introduced in the following sections with the hope of providing at least a basic comprehension of such concepts and a deeper insight into the SCA's formulation. For a complete and detailed treatment the reader is referred to the vast amount of literature on this subject, e.g., the well-known books of Toshio Mura (Mura, 1987) and S.Nemat-Nasser and M.Hori (Nemat-Nasser and Hori, 1993) where this Appendix is based on.

A.1 Introduction

Micromechanics encompasses mechanics related to microstructures of materials (Mura, 1987) and one of its main objectives is to express in a systematic and rigorous manner the continuum quantities associated with an infinitesimal material neighborhood in terms of the parameters that characterize the underlying microstructure and properties of the associated microconstituents (Nemat-Nasser and Hori, 1993). Not surprisingly, an essential concept on micromechanics is the already introduced RVE (see Section 2.10), over which suitable boundary-value problems are formulated in order to obtain the continuum constitutive properties of the microscopically heterogeneous material.

As pointed out in Nemat-Nasser and Hori (1993), distinct micromechanical approaches have been followed in the literature on the basis of systematic modeling. Inspired in the pioneering works of (e.g., Hill (1952), Kröner (1953), Kröner (1958), Hashin and Shtrikman (1962b), Hashin and Shtrikman (1962a), Hashin and Shtrikman (1963), Hill (1963), Hill (1964a), Hill (1964b), Hill (1965c), Hill (1965b), Budiansky (1965), Walpole (1966a), Walpole (1966b), Kröner (1977), Willis (1977), Kroner (1978), Willis (1981)), one of such approaches relies heavily on the rigorous analysis of continuum mechanics, namely on the linear theory of elasticity and general averaging techniques, seeking to compute the effective elastic moduli (elasticity and compliance tensors) and associated bounds by estimating local quantities in the RVE in terms of macroscopic boundary conditions. Other well-established approach is of statistical nature, where an RVE is viewed as a member of an essemble of RVE's, from which ensemble averages are estimated and used to represent the corresponding macroscopic constitutive parameters (e.g., Beran (1968), Miller (1969), Beran (1971), Kröner (1971), Batchelor (1974), Hori and Yonezawa (1974), Hori and Yonezawa (1975), Mccoy (1981), Torquato (1991)). In particular, the effective properties are defined in terms of the so called correlation tensors, where the n-point correlation tensor is the probability of finding certain material phases at n different point within an RVE (Nemat-Nasser and Hori, 1993). Without going into further detail, it can be stated that the assumption of ergodicity (see Kröner (1971)), which allows replacing essemble averages with sample averages, may be viewed as the bridge between these two approaches.

A.2 Effective moduli of heterogeneous elastic solids

Consider an heretogeneous RVE of domain $\Omega_{\mu,0}$ and boundary $\partial\Omega_{\mu,0}$ composed by a uniform linearly elastic matrix of domain $\Omega^M_{\mu,0}$ (elasticity and compliance tensors $\mathbf{D}^e$ and $\mathbf{S}^e$) containing n_β uniform linearly elastic inhomogeneities of domain Ω^β_μ (elasticity and compliance tensors $\mathbf{D}^{e,\beta}$ and $\mathbf{S}^{e,\beta}$, $\beta = 1,2,\ldots,n_\beta$) perfectly bonded to the matrix (see Figure A.1)[1]. The effective elasticity and compliance tensors of the heterogeneous RVE are denoted by $\bar{\mathbf{D}}^e$ and $\bar{\mathbf{S}}^e$. The objective is therefore to determine or estimate the effective elastic moduli of the RVE in terms of its heterogeneous microstructure properties.



Figure A.1: Heterogeneous RVE composed by uniform linearly elastic inhomogeneities embedded in a uniform linearly elastic matrix.

A.2.1 Micro-scale boundary conditions

Following Nemat-Nasser and Hori (1993), two particular micro-scale boundary conditions are considered in the following sections, namely uniform boundary tractions and linear boundary displacements. The uniform boundary tractions, $\boldsymbol{t}^0_\mu$, can be expressed in terms of a constant stress tensor, $\boldsymbol{\sigma}^0_\mu$, as

$$\boldsymbol{t}^0_\mu = \boldsymbol{\sigma}^0_\mu \cdot \boldsymbol{n}(\boldsymbol{Y}), \quad \forall \boldsymbol{Y} \in \partial\Omega_{\mu,0}. \tag{A.1}$$

The macroscopic stress tensor can be obtained by homogenization as

$$\boldsymbol{\sigma}(\boldsymbol{X}) = \frac{1}{v_\mu}\int_{\Omega_{\mu,0}} \boldsymbol{\sigma}(\boldsymbol{Y})\,\mathrm{d}v, \tag{A.2}$$

and, noticing the identity $\boldsymbol{\sigma}(\boldsymbol{Y}) = (\mathrm{div}[\boldsymbol{\sigma}(\boldsymbol{Y}) \otimes \boldsymbol{Y}])^T$, straighforward application of the Gauss theorem yields

$$\boldsymbol{\sigma}(\boldsymbol{X}) = \frac{1}{v_\mu}\int_{\partial\Omega_{\mu,0}} \boldsymbol{Y} \otimes \boldsymbol{t}_\mu(\boldsymbol{Y})\,\mathrm{d}a. \tag{A.3}$$

[1] For the treatment of linearly elastic solids containing traction-free defects (microcavities and microcracks), the interested reader is referred to Chapter 2 of Nemat-Nasser and Hori (1993).

Then, by assuming uniform boundary tractions, substitution of Equation (A.1) allows to conclude that

$$\boldsymbol{\sigma}(\boldsymbol{X}) = \left(\frac{1}{v_\mu} \int_{\partial\Omega_{\mu,0}} \boldsymbol{Y} \otimes \boldsymbol{n}(\boldsymbol{Y}) \, \mathrm{d}a \right) \cdot \boldsymbol{\sigma}^0_\mu = \boldsymbol{\sigma}^0_\mu . \tag{A.4}$$

In an complete analogous way, the linear boundary displacements, $\boldsymbol{u}^0_\mu$, can be expressed in terms of a constant strain tensor, $\boldsymbol{\varepsilon}^0_\mu$, as

$$\boldsymbol{u}^0_\mu = \boldsymbol{Y} \cdot \boldsymbol{\varepsilon}^0_\mu , \quad \forall \boldsymbol{Y} \in \partial\Omega_{\mu,0} . \tag{A.5}$$

The macroscopic strain tensor can be obtained by homogenization as

$$\boldsymbol{\varepsilon}(\boldsymbol{X}) = \frac{1}{v_\mu} \int_{\Omega_{\mu,0}} \boldsymbol{\varepsilon}(\boldsymbol{Y}) \, \mathrm{d}v , \tag{A.6}$$

and straighforward application of the Gauss theorem yields

$$\boldsymbol{\varepsilon}(\boldsymbol{X}) = \frac{1}{v_\mu} \int_{\partial\Omega_{\mu,0}} \frac{1}{2} \left(\boldsymbol{u}^0_\mu \otimes \boldsymbol{n}(\boldsymbol{Y}) + \boldsymbol{n}(\boldsymbol{Y}) \otimes \boldsymbol{u}^0_\mu \right) \mathrm{d}a . \tag{A.7}$$

Then, by assuming linear boundary displacements, substitution of Equation (A.5) allows to conclude that

$$\boldsymbol{\varepsilon}(\boldsymbol{X}) = \boldsymbol{\varepsilon}^0_\mu . \tag{A.8}$$

A.2.2 Effective compliance tensor

It is first considered that the RVE is subjected to uniform boundary tractions which, in view of Equation (A.4), is equivalent to impose a macroscopic stress $\boldsymbol{\sigma} = \boldsymbol{\sigma}^0_\mu$. If the RVE was homogeneous, then the stress field would be uniform throughout the entire RVE, $\boldsymbol{\sigma}_\mu(\boldsymbol{Y}) = \boldsymbol{\sigma}^0_\mu$, as well as the corresponding strain field,

$$\boldsymbol{\varepsilon}_\mu(\boldsymbol{Y}) = \mathbf{S}^e : \boldsymbol{\sigma}^0_\mu \equiv \boldsymbol{\varepsilon}^0_\mu , \quad \forall \boldsymbol{Y} \in \Omega_{\mu,0} . \tag{A.9}$$

However, the presence of the inhomogeneities disturbs the uniform strain and stress fields, which can now be defined as

$$\boldsymbol{\sigma}_\mu(\boldsymbol{Y}) = \boldsymbol{\sigma}^0_\mu + \boldsymbol{\sigma}^d_\mu(\boldsymbol{Y}) , \quad \forall \boldsymbol{Y} \in \Omega_{\mu,0} , \tag{A.10}$$

and

$$\boldsymbol{\varepsilon}_\mu(\boldsymbol{Y}) = \boldsymbol{\varepsilon}^0_\mu + \boldsymbol{\varepsilon}^d_\mu(\boldsymbol{Y}) = \begin{cases} \mathbf{S}^{e,\beta} : \left(\boldsymbol{\sigma}^0_\mu + \boldsymbol{\sigma}^d_\mu(\boldsymbol{Y}) \right) , & \forall \boldsymbol{Y} \in \Omega^\beta_{\mu,0} , \\ \mathbf{S}^e : \left(\boldsymbol{\sigma}^0_\mu + \boldsymbol{\sigma}^d_\mu(\boldsymbol{Y}) \right) , & \forall \boldsymbol{Y} \in \Omega^M_{\mu,0} , \end{cases} \tag{A.11}$$

where the superscript d is used to denote the disturbed fields due to the presence of the inhomogeneities.

The macroscopic strain tensor can be obtained by homogenization as

$$\boldsymbol{\varepsilon}(\boldsymbol{X}) = \frac{1}{v_\mu} \int_{\Omega_{\mu,0}} \boldsymbol{\varepsilon}_\mu(\boldsymbol{Y}) \, \mathrm{d}v = \frac{1}{v_\mu} \int_{\Omega_{\mu,0}} \boldsymbol{\varepsilon}^0_\mu + \boldsymbol{\varepsilon}^d_\mu(\boldsymbol{Y}) \, \mathrm{d}v , \tag{A.12}$$

and one seeks to determine the effective compliance tensor, $\bar{\mathbf{S}}^e$, such that

$$\boldsymbol{\varepsilon}(\boldsymbol{X}) = \bar{\mathbf{S}}^e : \boldsymbol{\sigma}(\boldsymbol{X}) = \bar{\mathbf{S}}^e : \boldsymbol{\sigma}_\mu^0 . \tag{A.13}$$

For this purpose it is convenient to split the strain field homogenization as

$$\boldsymbol{\varepsilon}(\boldsymbol{X}) = \frac{1}{v_\mu}\left(\int_{\Omega_{\mu,0}^M} \boldsymbol{\varepsilon}_\mu(\boldsymbol{Y})\, \mathrm{d}v + \sum_{\beta=1}^{n_\beta} \int_{\Omega_{\mu,0}^\beta} \boldsymbol{\varepsilon}_\mu(\boldsymbol{Y})\, \mathrm{d}v \right), \tag{A.14}$$

which can be rewritten as

$$\boldsymbol{\varepsilon}(\boldsymbol{X}) = f_M\, \bar{\boldsymbol{\varepsilon}}^M + \sum_{\beta=1}^{n_\beta} f_\beta\, \bar{\boldsymbol{\varepsilon}}^\beta , \tag{A.15}$$

where $f_M \equiv v_\mu^M / v_\mu$ and $f_\beta \equiv v_\mu^\beta / v_\mu$ are the volume fractions of the matrix and each inhomogeneity respectively, and $\bar{\boldsymbol{\varepsilon}}^M$ and $\bar{\boldsymbol{\varepsilon}}^\beta$ are the homogenized strain fields over the matrix and over each inhomogeneity,

$$\bar{\boldsymbol{\varepsilon}}^M = \frac{1}{v_\mu^M} \int_{\Omega_{\mu,0}^M} \boldsymbol{\varepsilon}_\mu(\boldsymbol{Y})\, \mathrm{d}v , \qquad \bar{\boldsymbol{\varepsilon}}^\beta = \frac{1}{v_\mu^\beta} \int_{\Omega_{\mu,0}^\beta} \boldsymbol{\varepsilon}_\mu(\boldsymbol{Y})\, \mathrm{d}v . \tag{A.16}$$

It is possible to split the stress field in a similar way as

$$\boldsymbol{\sigma}(\boldsymbol{X}) = f_M\, \bar{\boldsymbol{\sigma}}^M + \sum_{\beta=1}^{n_\beta} f_\beta\, \bar{\boldsymbol{\sigma}}^\beta = \boldsymbol{\sigma}_\mu^0 , \tag{A.17}$$

being the homogenized stress fields over the matrix and over each inhomogeneity defined as

$$\bar{\boldsymbol{\sigma}}^M = \frac{1}{v_\mu^M} \int_{\Omega_{\mu,0}^M} \boldsymbol{\sigma}_\mu(\boldsymbol{Y})\, \mathrm{d}v , \qquad \bar{\boldsymbol{\sigma}}^\beta = \frac{1}{v_{\mu,0}^\beta} \int_{\Omega_{\mu,0}^\beta} \boldsymbol{\sigma}_\mu(\boldsymbol{Y})\, \mathrm{d}v . \tag{A.18}$$

Noticing that $\bar{\boldsymbol{\varepsilon}}^M = \mathbf{S}^e : \bar{\boldsymbol{\sigma}}^M$, from Equations (A.13) and (A.15) and it is possible to write

$$\bar{\mathbf{S}}^e : \boldsymbol{\sigma}_\mu^0 = f_M\, \mathbf{S}^e : \bar{\boldsymbol{\sigma}}^M + \sum_{\beta=1}^{n_\beta} f_\beta\, \bar{\boldsymbol{\varepsilon}}^\beta . \tag{A.19}$$

Substitution of $\bar{\boldsymbol{\sigma}}^M$ from Equation (A.17) and simple algebraic manipulations finally yield

$$\left(\bar{\mathbf{S}}^e - \mathbf{S}^e \right) : \boldsymbol{\sigma}_\mu^0 = \sum_{\beta=1}^{n_\beta} f_\beta \left(\mathbf{S}^{e,\beta} - \mathbf{S}^e \right) : \bar{\boldsymbol{\sigma}}^\beta . \tag{A.20}$$

The previous expression defines the effective compliance tensor of the RVE in terms of the average stress of each inhomogeneity. As pointed out in Nemat-Nasser and Hori (1993), it is important to emphasize that it is not necessary to know the stress field within each inhomogeneity, only its average is required to determine the effective compliance tensor of the RVE. Furthermore, the effective compliance tensor defined by Equation (A.20) is exact and valid whether the heterogeneous RVE domain Ω_μ is finite or infinitely extended.

The well-known lower bounds of the effective elastic moduli proposed by Reuss (Reuss, 1929) are obtained by assuming that the average stress in each inhomogeneity is equal to the

macroscopic stress, i.e., $\bar{\boldsymbol{\sigma}}^{\beta} = \boldsymbol{\sigma} = \boldsymbol{\sigma}^0_{\mu}$. Under this assumption, the effective compliance tensor is obtained as

$$\bar{\mathbf{S}}^{e} = \left(1 - \sum_{\beta=1}^{n_\beta} f_\beta\right)\mathbf{S}^{e} + \sum_{\beta=1}^{n_\beta} f_\beta \mathbf{S}^{e,\beta}\,. \tag{A.21}$$

A.2.3 Effective elasticity tensor

It is now considered that the RVE is subjected to linear boundary displacements which, in view of Equation (A.8), is equivalent to impose a macroscopic strain $\boldsymbol{\varepsilon} = \boldsymbol{\varepsilon}^0_{\mu}$. If the RVE was homogeneous, then the strain field would be uniform throughout the entire RVE, $\boldsymbol{\varepsilon}_{\mu}(\boldsymbol{Y}) = \boldsymbol{\varepsilon}^0_{\mu}$, as well as the corresponding stress field,

$$\boldsymbol{\sigma}_{\mu}(\boldsymbol{Y}) = \mathbf{D}^{e} : \boldsymbol{\varepsilon}^0_{\mu} \equiv \boldsymbol{\sigma}^0_{\mu}\,, \quad \forall\, \boldsymbol{Y} \in \Omega_{\mu,0}\,. \tag{A.22}$$

However, the presence of the inhomogeneities disturbs the uniform strain and stress fields, which can now be defined as

$$\boldsymbol{\varepsilon}_{\mu}(\boldsymbol{Y}) = \boldsymbol{\varepsilon}^0_{\mu} + \boldsymbol{\varepsilon}^d_{\mu}(\boldsymbol{Y})\,, \quad \forall\, \boldsymbol{Y} \in \Omega_{\mu,0}\,, \tag{A.23}$$

and

$$\boldsymbol{\sigma}_{\mu}(\boldsymbol{Y}) = \boldsymbol{\sigma}^0_{\mu} + \boldsymbol{\sigma}^d_{\mu}(\boldsymbol{Y}) = \begin{cases} \mathbf{D}^{e,\beta} : \left(\boldsymbol{\varepsilon}^0_{\mu} + \boldsymbol{\varepsilon}^d_{\mu}(\boldsymbol{Y})\right), & \forall\, \boldsymbol{Y} \in \Omega^{\beta}_{\mu,0}\,, \\ \mathbf{D}^{e} : \left(\boldsymbol{\varepsilon}^0_{\mu} + \boldsymbol{\varepsilon}^d_{\mu}(\boldsymbol{Y})\right), & \forall\, \boldsymbol{Y} \in \Omega^{M}_{\mu,0}\,. \end{cases} \tag{A.24}$$

The macroscopic stress tensor can be obtained by homogenization as

$$\boldsymbol{\sigma}(\boldsymbol{X}) = \frac{1}{v_{\mu}} \int_{\Omega_{\mu,0}} \boldsymbol{\sigma}_{\mu}(\boldsymbol{Y})\, \mathrm{d}v = \frac{1}{v_{\mu}} \int_{\Omega_{\mu,0}} \boldsymbol{\sigma}^0_{\mu} + \boldsymbol{\sigma}^d_{\mu}(\boldsymbol{Y})\, \mathrm{d}v\,, \tag{A.25}$$

and one seeks to determine the effective compliance tensor, $\bar{\mathbf{D}}^{e}$, such that

$$\boldsymbol{\sigma}(\boldsymbol{X}) = \bar{\mathbf{D}}^{e} : \boldsymbol{\varepsilon}(\boldsymbol{X}) = \bar{\mathbf{D}}^{e} : \boldsymbol{\varepsilon}^0_{\mu}\,. \tag{A.26}$$

By following an identical procedure to that presented in the previous section, it is possible to define the effective elasticity tensor of the RVE in terms of the average strain of each inhomogeneity as

$$\left(\bar{\mathbf{D}}^{e} - \mathbf{D}^{e}\right) : \boldsymbol{\varepsilon}^0_{\mu} = \sum_{\beta=1}^{n_\beta} f_\beta \left(\mathbf{D}^{e,\beta} - \mathbf{D}^{e}\right) : \bar{\boldsymbol{\varepsilon}}^{\beta}\,. \tag{A.27}$$

Again, it is remarked that it is not necessary to know the strain field within each inhomogeneity, only its average is required to determine the effective elasticity tensor of the RVE. Moreover, the effective elasticity tensor defined by Equation (A.27) is exact and valid whether the heterogeneous RVE domain Ω_{μ} is finite or infinitely extended.

The well-known upper bounds of the effective elastic moduli proposed by Voigt (Voigt, 1889) are obtained by assuming that the average strain in each inhomogeneity is equal to the macroscopic strain, i.e., $\bar{\boldsymbol{\varepsilon}}^{\beta} = \boldsymbol{\varepsilon} = \boldsymbol{\varepsilon}^0_{\mu}$. Under this assumption, the effective elasticity tensor is obtained as

$$\bar{\mathbf{D}}^{e} = \left(1 - \sum_{\beta=1}^{n_\beta} f_\beta\right)\mathbf{D}^{e} + \sum_{\beta=1}^{n_\beta} f_\beta \mathbf{D}^{e,\beta}\,. \tag{A.28}$$

A.3 Theory of eigenstrains

A.3.1 The concept of eigenstrain

The concepts of eigenstrain and eigenstress are of utmost importance in micromechanics. The eigenstrain is a generic name given to inelastic strains which may stem from thermal expansion, phase transformation, plastic deformation or initial strains. However, although the material can be actually subjected to strains of this nature, it is not necessary to attribute the eigenstrain to any specific source. The total strain can therefore be regarded as the sum of the elastic strains and eigenstrains as

$$\boldsymbol{\varepsilon}_\mu(\boldsymbol{Y}) = \boldsymbol{\varepsilon}^e_\mu(\boldsymbol{Y}) + \boldsymbol{\varepsilon}^*_\mu(\boldsymbol{Y}), \tag{A.29}$$

where $\boldsymbol{\varepsilon}^*_\mu(\boldsymbol{Y})$ denotes the eigenstrain field. In turn, the eigenstress can be associated with the self-equilibrated internal stresses (or residual stresses) originated by one or several eigenstrains in a body free from any external body or surface forces. Therefore, the eigenstress field is also not necessarily associated with any specific source and emerges due to the incompatibility of the eigenstrain field (see Mura (1987)).

A.3.2 Eigenstrain problem

Consider a finite homogeneous linearly elastic solid occupying the region $\Omega_{\mu,0}$ of boundary $\partial\Omega_{\mu,0}$, with elasticity tensor $\mathbf{D}^e$. In accordance with Mura (1987), an inclusion is defined as a finite subdomain $\Omega^{\tilde{\beta}}_{\mu,0}$ of the homogeneous solid $\Omega_{\mu,0}$ (thus with elasticity tensor $\mathbf{D}^e$) if an eigenstrain field is prescribed as

$$\boldsymbol{\varepsilon}^*_\mu(\boldsymbol{Y}) = \begin{cases} \boldsymbol{\varepsilon}^*_\mu(\boldsymbol{Y}), & \text{in} \quad \Omega^{\tilde{\beta}}_{\mu,0}, \\ 0, & \text{in} \quad \Omega^M_{\mu,0} \equiv \Omega_{\mu,0} - \Omega^{\tilde{\beta}}_{\mu,0}, \end{cases} \tag{A.30}$$

where $\Omega^M_{\mu,0}$ denotes the matrix surrounding the inclusion $\Omega^{\tilde{\beta}}_{\mu,0}$[2]. The eigenstrain problem consists in finding the displacement field, $u_\mu(\boldsymbol{Y})$, the strain field, $\boldsymbol{\varepsilon}_\mu(\boldsymbol{Y})$, and the stress field, $\sigma_\mu(\boldsymbol{Y})$, when the solid, free from any external body or surface forces[3], is subjected to a given eigenstrain field, $\boldsymbol{\varepsilon}^*_\mu(\boldsymbol{Y})$. The strong equilibrium equations are therefore

$$\begin{cases} \operatorname{div}[\boldsymbol{\sigma}_\mu(\boldsymbol{Y})] = \mathbf{0}, & \forall \boldsymbol{Y} \in \Omega^{\tilde{\beta}}_{\mu,0}, \\ \boldsymbol{\sigma}_\mu(\boldsymbol{Y}) \cdot \boldsymbol{n}(\boldsymbol{Y}) = \mathbf{0}, & \forall \boldsymbol{Y} \in \partial\Omega^{\tilde{\beta}}_{\mu,0}. \end{cases} \tag{A.31}$$

According with the Hooke's Law and using the inditial notation for convenience, the constitutive relation between the stress and the elastic strain is established as

$$\sigma_{\mu,ij}(\boldsymbol{Y}) = \mathsf{D}^e_{ijkl}\,\varepsilon^e_{\mu,kl}(\boldsymbol{Y}), \tag{A.32}$$

or, in view of Equation (A.29), as

$$\sigma_{\mu,ij}(\boldsymbol{Y}) = \mathsf{D}^e_{ijkl}\left(\varepsilon_{\mu,kl}(\boldsymbol{Y}) - \varepsilon^*_{\mu,kl}(\boldsymbol{Y})\right). \tag{A.33}$$

[2] The $(\tilde{\bullet})$ is here employed to emphasize that is only considered one inclusion, being the β kept in order to be consistent with the notation of the previous section.

[3] When the solid is subjected to external body and/or surface forces, the stress field can be obtained by superposition of the (eigen)stress field of the free solid and the stress field of the proper boundary value problem.

Moreover, given that

$$\varepsilon_{\mu,kl} = \frac{1}{2}\left(\frac{\partial u_{\mu,k}}{\partial Y_l} + \frac{\partial u_{\mu,l}}{\partial Y_k}\right), \tag{A.34}$$

and attending to the major and minor simmetries of the elasticity tensor, i.e.,

$$\mathsf{D}^e_{ijkl} = \mathsf{D}^e_{klij} = \mathsf{D}^e_{jikl} = \mathsf{D}^e_{ijlk}, \tag{A.35}$$

it is then possible to write

$$\sigma_{\mu,ij}(\boldsymbol{Y}) = \mathsf{D}^e_{ijkl}\left(\frac{\partial u_{\mu,k}(\boldsymbol{Y})}{\partial Y_l} - \varepsilon^*_{\mu,kl}(\boldsymbol{Y})\right). \tag{A.36}$$

Substitution of the previous constitutive relation in the strong equilibrium equations finally yields

$$\begin{cases} \mathsf{D}^e_{ijkl}\dfrac{\partial^2 u_{\mu,k}(\boldsymbol{y})}{\partial Y_j \partial Y_l} - \mathsf{D}^e_{ijkl}\dfrac{\partial \varepsilon^*_{\mu,kl}(\boldsymbol{Y})}{\partial Y_j} = 0\,, & \forall\, \boldsymbol{Y} \in \Omega^{\tilde{\beta}}_{\mu,0}\,, \\ \mathsf{D}^e_{ijkl}\dfrac{\partial u_{\mu,k}(\boldsymbol{Y})}{\partial Y_l} n_j(\boldsymbol{Y}) = \mathsf{D}^e_{ijkl}\varepsilon^*_{\mu,kl}(\boldsymbol{Y})\, n_j(\boldsymbol{Y})\,, & \forall\, \boldsymbol{Y} \in \partial\Omega^{\tilde{\beta}}_{\mu,0}\,. \end{cases} \tag{A.37}$$

It is instructive to notice that the displacement field caused by a prescribed eigenstrain distribution $\boldsymbol{\varepsilon}^*_\mu(\boldsymbol{Y})$ in a free solid is equivalent to the displacement field obtained by considering the same solid subjected to body and surface forces defined respectively as

$$\boldsymbol{b}_\mu(\boldsymbol{Y}) = -\mathrm{div}\left[\mathbf{D}^e : \boldsymbol{\varepsilon}^*_\mu(\boldsymbol{Y})\right], \quad \boldsymbol{t}_\mu(\boldsymbol{Y}) = \left(\mathbf{D}^e : \boldsymbol{\varepsilon}^*_\mu(\boldsymbol{Y})\right)\cdot \boldsymbol{n}(\boldsymbol{Y})\,. \tag{A.38}$$

A.3.3 Equivalent inclusion method

Consider a finite heterogeneous linearly elastic solid, occupying the region $\Omega_{\mu,0}$ of boundary $\partial\Omega_{\mu,0}$, with a matrix $\Omega^M_{\mu,0} \equiv \Omega_{\mu,0} - \Omega^{\tilde{\beta}}_{\mu,0}$, characterized by a uniform elasticity tensor $\mathbf{D}^e$, and a single inhomogeneity, defined in a finite subdomain $\Omega^{\tilde{\beta}}_{\mu,0}$, with a given uniform elasticity tensor $\mathbf{D}^{e,\beta} \neq \mathbf{D}^e$. Let the solid be subjected to linear surface displacements[4], $\boldsymbol{u}^0_\mu$, on $\partial\Omega_{\mu,0}$, associated with a uniform strain field, $\boldsymbol{\varepsilon}^0_\mu$, as

$$\boldsymbol{u}^0_\mu = \boldsymbol{Y}\cdot\boldsymbol{\varepsilon}^0_\mu, \quad \forall\, \boldsymbol{Y} \in \partial\Omega_{\mu,0}\,. \tag{A.39}$$

If the elastic solid was homogeneous ($\mathbf{D}^{e,\beta} = \mathbf{D}^e$), then the strain field would be uniform throughout the entire volume, $\boldsymbol{\varepsilon}_\mu(\boldsymbol{Y}) = \boldsymbol{\varepsilon}^0_\mu$, as well as the corresponding stress field,

$$\boldsymbol{\sigma}_\mu(\boldsymbol{Y}) = \mathbf{D}^e : \boldsymbol{\varepsilon}^0_\mu = \boldsymbol{\sigma}^0_\mu, \quad \forall\, \boldsymbol{Y} \in \Omega_{\mu,0}\,. \tag{A.40}$$

However, the presence of an inhomogeneity with a different elasticity tensor $\mathbf{D}^{e,\beta}$, i.e., the existence of a material mismatch, disturbs the uniform strain and stress fields, which can now be defined as

[4] The treatment would be similar if were considered uniform boundary tractions, $\boldsymbol{t}^0_\mu$, associated with the uniform stress field, $\boldsymbol{\sigma}^0_\mu$. In this case, the corresponding strain field would be defined as $\boldsymbol{\varepsilon}^0_\mu = \mathbf{S}^e : \boldsymbol{\sigma}^0_\mu$.

$$\boldsymbol{\varepsilon}_{\mu}(\boldsymbol{Y}) = \boldsymbol{\varepsilon}_{\mu}^{0} + \boldsymbol{\varepsilon}_{\mu}^{d}(\boldsymbol{Y}), \quad \forall \boldsymbol{Y} \in \Omega_{\mu,0}, \tag{A.41}$$

and

$$\boldsymbol{\sigma}_{\mu}(\boldsymbol{Y}) = \boldsymbol{\sigma}_{\mu}^{0} + \boldsymbol{\sigma}_{\mu}^{d}(\boldsymbol{Y}) = \begin{cases} \mathbf{D}^{e,\beta} : \left(\boldsymbol{\varepsilon}_{\mu}^{0} + \boldsymbol{\varepsilon}_{\mu}^{d}(\boldsymbol{Y})\right), & \forall \boldsymbol{Y} \in \Omega_{\mu,0}^{\tilde{\beta}}, \\ \mathbf{D}^{e} : \left(\boldsymbol{\varepsilon}_{\mu}^{0} + \boldsymbol{\varepsilon}_{\mu}^{d}(\boldsymbol{Y})\right), & \forall \boldsymbol{Y} \in \Omega_{\mu,0}^{M} \equiv \Omega_{\mu,0} - \Omega_{\mu,0}^{\tilde{\beta}}, \end{cases} \tag{A.42}$$

where the superscript d is used to denote the disturbed fields due to the presence of the inhomogeneity.

A convenient and effective way to to deal with the above consists in formulating an auxiliar problem where is considered an equivalent (fictitious) finite homogeneous linearly elastic solid occupying the same region $\Omega_{\mu,0}$ of boundary $\partial\Omega_{\mu,0}$ with elasticity tensor $\mathbf{D}^{e}$, coincident with the matrix' elasticity tensor of the actual problem. In order to account for the material mismatch ($\mathbf{D}^{e,\beta} \neq \mathbf{D}^{e}$) in the actual problem, a suitable eigenstrain field, $\boldsymbol{\varepsilon}_{\mu}^{*}(\boldsymbol{Y})$, can be prescribed in the region $\Omega_{\mu,0}^{\tilde{\beta}}$ as

$$\boldsymbol{\varepsilon}_{\mu}^{*}(\boldsymbol{Y}) = \begin{cases} \boldsymbol{\varepsilon}_{\mu}^{*}(\boldsymbol{Y}), & \text{in } \Omega_{\mu,0}^{\tilde{\beta}}, \\ 0, & \text{in } \Omega_{\mu,0}^{M} \equiv \Omega_{\mu,0} - \Omega_{\mu,0}^{\tilde{\beta}}, \end{cases} \tag{A.43}$$

such that the equivalent homogeneous solid has exactly the same strain and stress fields as the heterogeneous solid of the actual problem. Notice that the auxiliary problem is in fact an eigenstrain problem superposed with the uniform strain field $\boldsymbol{\varepsilon}_{\mu}^{0}$, i.e.,

$$\boldsymbol{\varepsilon}_{\mu}(\boldsymbol{Y}) = \boldsymbol{\varepsilon}_{\mu}^{0} + \boldsymbol{\varepsilon}_{\mu}^{d}(\boldsymbol{Y}), \quad \forall \boldsymbol{Y} \in \Omega_{\mu,0}, \tag{A.44}$$

and

$$\boldsymbol{\sigma}_{\mu}(\boldsymbol{Y}) = \boldsymbol{\sigma}_{\mu}^{0} + \boldsymbol{\sigma}_{\mu}^{d}(\boldsymbol{Y}) = \begin{cases} \mathbf{D}^{e} : \left(\boldsymbol{\varepsilon}_{\mu}^{0} + \boldsymbol{\varepsilon}_{\mu}^{d}(\boldsymbol{Y}) - \boldsymbol{\varepsilon}_{\mu}^{*}(\boldsymbol{Y})\right), & \forall \boldsymbol{Y} \in \Omega_{\mu,0}^{\tilde{\beta}}, \\ \mathbf{D}^{e} : \left(\boldsymbol{\varepsilon}_{\mu}^{0} + \boldsymbol{\varepsilon}_{\mu}^{d}(\boldsymbol{Y})\right), & \forall \boldsymbol{Y} \in \Omega_{\mu,0}^{M} \equiv \Omega_{\mu,0} - \Omega_{\mu,0}^{\tilde{\beta}}. \end{cases} \tag{A.45}$$

From the comparison of Equations (A.42) and (A.45), the necessary and sufficient condition for the equivalence of the strain and stress fields between both problems is

$$\boldsymbol{\sigma}_{\mu}(\boldsymbol{Y}) = \mathbf{D}^{e,\beta} : \left(\boldsymbol{\varepsilon}_{\mu}^{0} + \boldsymbol{\varepsilon}_{\mu}^{d}(\boldsymbol{Y})\right) = \mathbf{D}^{e} : \left(\boldsymbol{\varepsilon}_{\mu}^{0} + \boldsymbol{\varepsilon}_{\mu}^{d}(\boldsymbol{Y}) - \boldsymbol{\varepsilon}_{\mu}^{*}(\boldsymbol{Y})\right), \quad \forall \boldsymbol{Y} \in \Omega_{\mu,0}^{\tilde{\beta}}, \tag{A.46}$$

which can be rewritten in a more compact way as

$$\boldsymbol{\varepsilon}_{\mu}^{0} + \boldsymbol{\varepsilon}_{\mu}^{d}(\boldsymbol{Y}) = \mathbf{L}^{\beta} : \boldsymbol{\varepsilon}_{\mu}^{*}(\boldsymbol{Y}), \quad \forall \boldsymbol{Y} \in \Omega_{\mu,0}^{\tilde{\beta}}, \tag{A.47}$$

with the constant fourth-order tensor $\mathbf{L}^{\beta}$ defined as

$$\mathbf{L}^{\beta} \equiv \left(\mathbf{D}^{e} - \mathbf{D}^{e,\beta}\right)^{-1} : \mathbf{D}^{e}. \tag{A.48}$$

Since the solution of the eigenstrain problem can be in general obtained in terms of an integral operator acting on $\boldsymbol{\varepsilon}^*_\mu(\boldsymbol{Y})$, the disturbed strain field, $\boldsymbol{\varepsilon}^d_\mu(\boldsymbol{Y})$, can be determined from the solution of the auxiliary equivalent problem as

$$\boldsymbol{\varepsilon}^d_\mu(\boldsymbol{Y}) = \mathbb{F}\left(\boldsymbol{Y}; \boldsymbol{\varepsilon}^*_\mu(\boldsymbol{Y})\right), \quad \forall\, \boldsymbol{Y} \in \Omega_\mu\,. \tag{A.49}$$

Therefore, for a given prescribed uniform strain field, $\boldsymbol{\varepsilon}^0_\mu$, it is possible to determine the suitable eigenstrain field $\boldsymbol{\varepsilon}^*_\mu(\boldsymbol{Y})$ to perform the 'homogenization' of the problem from the consistency condition in Equation (A.47),

$$\mathbf{L}^\beta : \boldsymbol{\varepsilon}^*_\mu(\boldsymbol{Y}) - \mathbb{F}\left(\boldsymbol{Y}; \boldsymbol{\varepsilon}^*_\mu(\boldsymbol{Y})\right) = \boldsymbol{\varepsilon}^0_\mu, \quad \forall\, \boldsymbol{Y} \in \Omega^{\tilde{\beta}}_\mu. \tag{A.50}$$

A.3.4 Eshelby's solution

Eshelby (Eshelby and Peierls, 1957) derived a solution for a particular eigenstrain problem which has played a key role ever since in the micromechanics field. Consider an infinitely extended homogeneous linearly elastic solid with elasticity tensor $\mathbf{D}^e$ and a single ellipsoidal inclusion $\Omega^{\tilde{\beta}}$ with a prescribed uniform eigenstrain field

$$\boldsymbol{\varepsilon}^*_\mu(\boldsymbol{Y}) = \begin{cases} \boldsymbol{\varepsilon}^*_\mu, & \text{in} \quad \Omega^{\tilde{\beta}}_{\mu,0}\,, \\ 0, & \text{elsewhere}\,. \end{cases} \tag{A.51}$$

The detailed derivation of Eshelby's solution can be easily found in the literature (e.g., Mura (1987), Nemat-Nasser and Hori (1993)) and will not be reproduced here. The most important and valuable aspect about his solution is that the strain field, $\boldsymbol{\varepsilon}_\mu(\boldsymbol{Y})$, inside of the ellipsoidal inclusion $\Omega^{\tilde{\beta}}$ is uniform and can be defined as

$$\boldsymbol{\varepsilon}_\mu(\boldsymbol{Y}) = \mathbf{E}^\beta : \boldsymbol{\varepsilon}^*_\mu, \quad \forall\, \boldsymbol{Y} \in \Omega^{\tilde{\beta}}_{\mu,0}\,, \tag{A.52}$$

where $\mathbf{E}^\beta$ denotes the so-called Eshelby's fourth-order tensor. The Eshelby's tensor is completely defined in terms of the aspect ratios of the ellipsoidal inclusion $\Omega^{\tilde{\beta}}_{\mu,0}$ (a_1, a_2 and a_3) and the elastic moduli of the infinitely extended homogeneous solid, exhibiting left and right simmetries such that $\mathsf{E}^\beta_{ijkl} = \mathsf{E}^\beta_{jikl} = \mathsf{E}^\beta_{ijlk}$[5]. The particularization of the Eshelby's tensor for different inclusion geometries (e.g., sphere ($a_1 = a_2 = a_3$), oblate spheroid ($a_1 = a_2 > a_3$), prolate spheroid ($a_1 > a_2 = a_3$, elliptic cylinder ($a_3 \to \infty$), ...) can be found in Mura (1987).

Under the assumptions of Eshelby's eigenstrain problem, one can then explicitly determine the strain and stress fields of an infinitely extended heterogeneous linearly elastic solid with an embedded ellipsoidal inhomogeneity by application of the equivalent inclusion method. In the first place, attending to Equation (A.49), notice that the integral operator $\mathbb{F}(\boldsymbol{Y}; \boldsymbol{\varepsilon}^*_\mu(\boldsymbol{Y}))$ acting on $\boldsymbol{\varepsilon}^*_\mu(\boldsymbol{Y})$ reduces to a tensor operator such that the disturbed strain field, $\boldsymbol{\varepsilon}^d_\mu(\boldsymbol{Y})$, for any point inside the inclusion can be explicitly defined as

$$\boldsymbol{\varepsilon}^d_\mu(\boldsymbol{Y}) = \mathbf{E}^\beta : \boldsymbol{\varepsilon}^*_\mu, \quad \forall\, \boldsymbol{Y} \in \Omega^{\tilde{\beta}}_{\mu,0}\,. \tag{A.53}$$

Substitution of the previous result in the consistency condition (see Equation (A.47)) yields

[5] In general the Eshelby's tensor does not have major simmetry, that is $\mathsf{E}^\beta_{ijkl} \neq \mathsf{E}^\beta_{klij}$.

$$\boldsymbol{\varepsilon}_{\mu}^{*}(\boldsymbol{Y}) = \left(\mathbf{L}^{\beta} - \mathbf{E}^{\beta}\right)^{-1} : \boldsymbol{\varepsilon}_{\mu}^{0}, \quad \forall \boldsymbol{Y} \in \Omega_{\mu,0}^{\tilde{\beta}}, \tag{A.54}$$

which is the uniform eigenstrain field necessary to perform the 'homogenization' of the problem for a given prescribed uniform strain field, $\boldsymbol{\varepsilon}_{\mu}^{0}$.

A.4 Self-Consistent Method

In Section A.2 it is concluded that the effective elasticity and compliance tensors of the heterogeneous RVE can be determined if the average strain and average stress in each inhomogeneity are known (see Equations (A.27) and (A.20)). The theory of eigenstrains introduced in the previous section can now be applied as an effective tool to estimate such quantities.

A.4.1 Self-Consistent assumption

For simplicity of presentation, assume that the RVE inhomogeneities are either ellipsoidal or can be approximated by ellipsoids. In order to estimate the average strain and average stress in a typical inclusion, $\Omega_{\mu,0}^{\tilde{\beta}}$, it is considered an infinitely extended heterogeneous linear elastic solid and a single ellipsoidal inhomogeneity $\Omega_{\mu,0}^{\tilde{\beta}}$. Note that by considering a unique inhomogeneity the interaction effects between the different inclusions in the heterogeneous RVE are being neglected, assumption that renders the usually called dilute distribution of inhomogeneities estimate.

By applying the equivalent inclusion method and consider the suitable 'homogenization' eigenstrain field defined in Equation (A.54), the consistency condition in Equation (A.47) yields the strain field inside the ellipsoidal inhomogeneity as

$$\boldsymbol{\varepsilon}_{\mu}(\boldsymbol{Y}) = \boldsymbol{\varepsilon}_{\mu}^{0} + \boldsymbol{\varepsilon}_{\mu}^{d}(\boldsymbol{Y}) = \mathbf{L}^{\beta} : \left(\mathbf{L}^{\beta} - \mathbf{E}^{\beta}\right)^{-1} : \boldsymbol{\varepsilon}_{\mu}^{0}, \quad \forall \boldsymbol{Y} \in \Omega_{\mu,0}^{\tilde{\beta}}. \tag{A.55}$$

In the so-called Self-Consistent Method, it is considered that the infinitely extended matrix of the heterogeneous linear elastic solid has the yet-unknown effective elastic moduli of the heterogeneous RVE, so that the strain field inside the ellipsoidal inhomogeneity is written instead

$$\boldsymbol{\varepsilon}_{\mu}(\boldsymbol{Y}) = \bar{\mathbf{L}}^{\beta} : \left(\bar{\mathbf{L}}^{\beta} - \bar{\mathbf{E}}^{\beta}\right)^{-1} : \boldsymbol{\varepsilon}_{\mu}^{0}, \quad \forall \boldsymbol{Y} \in \Omega_{\mu,0}^{\tilde{\beta}}, \tag{A.56}$$

where

$$\bar{\mathbf{L}}^{\beta} \equiv \left(\bar{\mathbf{D}}^{e} - \mathbf{D}^{e,\beta}\right)^{-1} : \bar{\mathbf{D}}^{e}, \tag{A.57}$$

and the Eshelby's tensor, $\bar{\mathbf{E}}^{\beta}$, is determined from the effective elastic moduli of the heterogeneous RVE. Given that both $\bar{\mathbf{L}}^{\beta}$ and $\bar{\mathbf{E}}^{\beta}$ are constant tensors and $\boldsymbol{\varepsilon}_{\mu}^{0}$ is a uniform strain

field, then the average strain in the inclusion $\Omega_{\mu,0}^{\tilde{\beta}}$ is

$$\bar{\boldsymbol{\varepsilon}}_{\mu}^{\beta} = \frac{1}{v_{\mu}^{\beta}} \int_{\Omega_{\mu,0}^{\beta}} \bar{\mathbf{L}}^{\beta} : \left(\bar{\mathbf{L}}^{\beta} - \bar{\mathbf{E}}^{\beta} \right)^{-1} : \boldsymbol{\varepsilon}_{\mu}^{0} \, \mathrm{d}v = \bar{\mathbf{L}}^{\beta} : \left(\bar{\mathbf{L}}^{\beta} - \bar{\mathbf{E}}^{\beta} \right)^{-1} : \boldsymbol{\varepsilon}_{\mu}^{0}. \tag{A.58}$$

A.4.2 Effective compliance tensor

For prescribed uniform boundary tractions, $\boldsymbol{t}_{\mu}^{0}$, associated with the macroscopic stress $\boldsymbol{\sigma} = \boldsymbol{\sigma}_{\mu}^{0}$, the average stress in the inclusion $\Omega_{\mu,0}^{\tilde{\beta}}$ is obtained as

$$\bar{\boldsymbol{\sigma}}_{\mu}^{\beta} = \mathbf{D}^{e,\beta} : \bar{\boldsymbol{\varepsilon}}_{\mu}^{\beta} = \mathbf{D}^{e,\beta} : \bar{\mathbf{L}}^{\beta} : \left(\bar{\mathbf{L}}^{\beta} - \bar{\mathbf{E}}^{\beta} \right)^{-1} : \boldsymbol{\varepsilon}_{\mu}^{0}, \tag{A.59}$$

or in terms of the farfield stress $\boldsymbol{\sigma}_{\mu}^{0}$ as[6]

$$\bar{\boldsymbol{\sigma}}_{\mu}^{\beta} = \mathbf{D}^{e,\beta} : \bar{\mathbf{L}}^{\beta} : \left(\bar{\mathbf{L}}^{\beta} - \bar{\mathbf{E}}^{\beta} \right)^{-1} : \bar{\mathbf{S}}^{e} : \boldsymbol{\sigma}_{\mu}^{0}. \tag{A.60}$$

Substitution in Equation (A.20) yields

$$\left(\bar{\mathbf{S}}^{e} - \mathbf{S}^{e} \right) : \boldsymbol{\sigma}_{\mu}^{0} = \left[\sum_{\beta=1}^{n_{\beta}} f_{\beta} \left(\mathbf{S}^{e,\beta} - \mathbf{S}^{e} \right) : \mathbf{D}^{e,\beta} : \bar{\mathbf{L}}^{\beta} : \left(\bar{\mathbf{L}}^{\beta} - \bar{\mathbf{E}}^{\beta} \right)^{-1} : \bar{\mathbf{S}}^{e} \right] : \boldsymbol{\sigma}_{\mu}^{0}, \tag{A.61}$$

and since the relation must hold for any farfield stress, $\boldsymbol{\sigma}_{\mu}^{0}$, it comes

$$\bar{\mathbf{S}}^{e} = \mathbf{S}^{e} + \sum_{\beta=1}^{n_{\beta}} f_{\beta} \left(\mathbf{S}^{e,\beta} - \mathbf{S}^{e} \right) : \mathbf{D}^{e,\beta} : \bar{\mathbf{L}}^{\beta} : \left(\bar{\mathbf{L}}^{\beta} - \bar{\mathbf{E}}^{\beta} \right)^{-1} : \bar{\mathbf{S}}^{e}. \tag{A.62}$$

A.4.3 Effective elasticity tensor

For prescribed linear boundary displacements, $\boldsymbol{u}_{\mu}^{0}$, associated with the macroscopic strain $\boldsymbol{\varepsilon} = \boldsymbol{\varepsilon}_{\mu}^{0}$, the average strain in the inclusion $\Omega_{\mu,0}^{\tilde{\beta}}$ is given by Equation (A.58) and substitution in Equation (A.27) yields

$$\left(\bar{\mathbf{D}}^{e} - \mathbf{D}^{e} \right) : \boldsymbol{\varepsilon}_{\mu}^{0} = \left[\sum_{\beta=1}^{n_{\beta}} f_{\beta} \left(\mathbf{D}^{e,\beta} - \mathbf{D}^{e} \right) : \bar{\mathbf{L}}^{\beta} : \left(\bar{\mathbf{L}}^{\beta} - \bar{\mathbf{E}}^{\beta} \right)^{-1} \right] : \boldsymbol{\varepsilon}_{\mu}^{0}. \tag{A.63}$$

Since the relation must hold for any farfield strain, $\boldsymbol{\varepsilon}_{\mu}^{0}$, it comes

$$\bar{\mathbf{D}}^{e} = \mathbf{D}^{e} + \sum_{\beta=1}^{n_{\beta}} f_{\beta} \left(\mathbf{D}^{e,\beta} - \mathbf{D}^{e} \right) : \bar{\mathbf{L}}^{\beta} : \left(\bar{\mathbf{L}}^{\beta} - \bar{\mathbf{E}}^{\beta} \right)^{-1}. \tag{A.64}$$

[6] Since an infinitely extended linearly elastic solid is considered, the presence of a single inhomogeneity does not affect the effective relations $\boldsymbol{\sigma}_{\mu}^{0} = \bar{\mathbf{D}}^{e} : \boldsymbol{\varepsilon}_{\mu}^{0}$ and $\boldsymbol{\varepsilon}_{\mu}^{0} = \bar{\mathbf{S}}^{e} : \boldsymbol{\sigma}_{\mu}^{0}$ as pointed out in Nemat-Nasser and Hori (1993)

A.4.4 Equivalence between the effective elastic moduli

In order to understand the meaning of the self-consistent assumption, it is instructive to verify what is the relation between the estimated effective elasticity tensor (see Equation (A.27)) and the effective compliance tensor (see Equation (A.20)) of the heterogeneous RVE.

Performing a left and right double contraction of Equation (A.20) by $\mathbf{S}^e$ and $\left(\bar{\mathbf{D}}^e\right)^{-1}$ respectively, one has

$$\mathbf{S}^e : \bar{\mathbf{D}}^e : \left(\bar{\mathbf{D}}^e\right)^{-1} = \mathbf{S}^e : \mathbf{D}^e : \left(\bar{\mathbf{D}}^e\right)^{-1} + \sum_{\beta=1}^{n_\beta} f_\beta \mathbf{S}^e : \left(\mathbf{D}^{e,\beta} - \mathbf{D}^e\right) : \bar{\mathbf{L}}^\beta : \left(\bar{\mathbf{L}}^\beta - \bar{\mathbf{E}}^\beta\right)^{-1} : \left(\bar{\mathbf{D}}^e\right)^{-1}. \tag{A.65}$$

which, since $\left(\mathbf{S}^e\right)^{-1} = \mathbf{D}^e$, can be readily simplified to

$$\mathbf{S}^e = \left(\bar{\mathbf{D}}^e\right)^{-1} + \sum_{\beta=1}^{n_\beta} f_\beta \mathbf{S}^e : \left(\mathbf{D}^{e,\beta} - \mathbf{D}^e\right) : \bar{\mathbf{L}}^\beta : \left(\bar{\mathbf{L}}^\beta - \bar{\mathbf{E}}^\beta\right)^{-1} : \left(\bar{\mathbf{D}}^e\right)^{-1}. \tag{A.66}$$

After substitution of the following identity in the previous expression,

$$\mathbf{S}^e : \left(\mathbf{D}^{e,\beta} - \mathbf{D}^e\right) = -\left(\mathbf{S}^{e,\beta} - \mathbf{S}^e\right) : \mathbf{D}^{e,\beta}, \tag{A.67}$$

a simple algebraic rearrangement finally leads to

$$\left(\bar{\mathbf{D}}^e\right)^{-1} = \mathbf{S}^e + \sum_{\beta=1}^{n_\beta} f_\beta \left(\mathbf{S}^{e,\beta} - \mathbf{S}^e\right) : \mathbf{D}^{e,\beta} : \bar{\mathbf{L}}^\beta : \left(\bar{\mathbf{L}}^\beta - \bar{\mathbf{E}}^\beta\right)^{-1} : \left(\bar{\mathbf{D}}^e\right)^{-1}. \tag{A.68}$$

Comparison of Equations (A.68) and (A.20) shows that

$$\left(\bar{\mathbf{D}}^e\right)^{-1} = \bar{\mathbf{S}}^e, \tag{A.69}$$

and, by performing a similar procedure over the effective elasticity tensor given by Equation (A.27), it is possible to show that

$$\left(\bar{\mathbf{S}}^e\right)^{-1} = \bar{\mathbf{D}}^e. \tag{A.70}$$

It is thus concluded that the estimated effective compliance tensor, $\bar{\mathbf{D}}^e$, for prescribed uniform boundary tractions (associated with the macroscopic stress $\boldsymbol{\sigma} = \boldsymbol{\sigma}^0_\mu$) and the estimated effective elasticity tensor, $\bar{\mathbf{S}}^e$, for prescribed linear displacements (associated with the macroscopic strain $\boldsymbol{\varepsilon} = \boldsymbol{\varepsilon}^0_\mu$) are each other's exact inverse as a consequence of the self-consistent assumption. The Self-Consistent Method yields a unique effective elasticity tensor (or effective compliance tensor) whether a macroscopic stress or a macroscopic strain is regarded prescribed (Nemat-Nasser and Hori, 1993), being the term 'self-consistent' used in the literature to emphasize the existence of this inverse property.

Appendix B
FFT-based Homogenization Basic Scheme (Infinitesimal Strains)

This Appendix provides a concise description of the FFT-based homogenization basic scheme proposed by Moulinec and Suquet (Moulinec and Suquet, 1994) under infinitesimal strains. Besides covering the main formulation aspects, the numerical implementation is conveniently summarized in pseudo-code format. Furthermore, given the application purposes in the context of the clustering-based reduced order models explored in this thesis, only the formulation accounting for linear elastic phases is covered here.

B.1 Problem formulation

Let us assume a heterogeneous RVE of domain Ω_μ and boundary $\partial\Omega_\mu$, with dimensions $(l_{\text{RVE}})_i$, $i = 1,\dots,n_{\text{dim}}$, composed by a given number of perfectly bonded linear elastic phases and characterized by a given material tangent modulus $\mathbf{D}^e(\boldsymbol{Y})$. Following standard first-order homogenization multi-scale kinematic procedures, further assume that a given macro-scale strain, $\boldsymbol{\varepsilon}(\boldsymbol{X})$, is prescribed such that

$$\boldsymbol{\varepsilon}(\boldsymbol{X}) = \frac{1}{v_{\mu,0}} \int_{\Omega_{\mu,0}} \boldsymbol{\varepsilon}_\mu(\boldsymbol{Y}) \, \mathrm{d}v \,, \tag{B.1}$$

where $v_{\mu,0}$ denotes the volume of the RVE in the reference configuration, and that periodic boundary conditions are adopted.

In the absence of body forces, the micro-scale quasi-static equilibrium problem consists of finding the micro-scale strain field that satisfies the strong equilibrium equations

$$\mathrm{div}_0 \left[\boldsymbol{\sigma}_\mu(\boldsymbol{Y})\right] = \mathbf{0} \quad \text{with} \quad \boldsymbol{\sigma}_\mu(\boldsymbol{Y}) = \mathbf{D}^e(\boldsymbol{Y}) : \boldsymbol{\varepsilon}_\mu(\boldsymbol{Y}) \,, \quad \forall \boldsymbol{Y} \in \Omega_{\mu,0} \,. \tag{B.2}$$

As demonstrated in Chapter 4 (see Section 4.2.1), the micro-scale quasi-static equilibrium problem can be formulated as a Lippmann-Schwinger nonlinear integral equilibrium equation. The latter is conveniently recovered here in both frequency and spatial domains as[1]

$$\check{\boldsymbol{\varepsilon}}_\mu(\boldsymbol{\zeta}) = -\check{\boldsymbol{\Phi}}^0(\boldsymbol{\zeta}) : \check{\boldsymbol{\sigma}}^*_\mu(\boldsymbol{\zeta}) \,, \quad \forall \boldsymbol{\zeta} \neq \mathbf{0} \,, \quad \check{\boldsymbol{\varepsilon}}_\mu(\mathbf{0}) = \boldsymbol{\varepsilon}(\boldsymbol{X}) \,, \tag{B.3}$$

and

$$\boldsymbol{\varepsilon}_\mu(\boldsymbol{Y}) = -\int_{\Omega_{\mu,0}} \boldsymbol{\Phi}^0(\boldsymbol{Y} - \boldsymbol{Y}') : \boldsymbol{\sigma}^*_\mu(\boldsymbol{Y}') \, \mathrm{d}v' + \boldsymbol{\varepsilon}(\boldsymbol{X}) \,, \quad \forall \boldsymbol{Y} \in \Omega_{\mu,0} \,, \tag{B.4}$$

[1] Given the assumption of linear elastic constitutive material phases adopted in this Appendix, the explicit consideration of an incremental formulation is ommited.

respectively, where $\boldsymbol{\Phi}^0$ denotes the Green operator associated to the reference micro-scale eigenstress problem and $\boldsymbol{\sigma}^*_\mu$ denotes the stress polarization (or eigenstress) field,

$$\boldsymbol{\sigma}^*_\mu(\boldsymbol{Y}) = \boldsymbol{\sigma}_\mu(\boldsymbol{Y}) - \mathbf{D}^{e,0} : \boldsymbol{\varepsilon}_\mu(\boldsymbol{Y}) \,. \tag{B.5}$$

In their contribution, Moulinec and Suquet (Moulinec and Suquet, 1994) assume an isotropic elastic reference material (see Equation (4.18)) with Lamé parameters (λ^0, μ^0), which renders a closed-form expression of the Green operator in the frequency domain (see Equation (4.21)).

B.2 Spatial discretization

The RVE domain is discretized in a regular grid of $n_\nu = \prod_{i=1}^{n_{\text{dim}}} n_i$ voxels as illustrated in Figure B.1, where n_i denotes the number of voxels in the ith dimension. For instance, in a two-dimensional problem, the spatial coordinates of any sampling point, $\boldsymbol{Y}_{s_1,s_2} \equiv \boldsymbol{Y}(s_1, s_2) \in \Omega_{\mu,0}$, are defined as

$$\boldsymbol{Y}_{s_1,s_2} = \left(\frac{(l_{\text{RVE}})_1}{n_1} s_1, \frac{(l_{\text{RVE}})_1}{n_2} s_2 \right), \quad s_i = 0, 1, \ldots, n_i - 1, \quad i = 1, 2 \,. \tag{B.6}$$

In the frequency domain, obtained by means of a discrete Fourier transform (DFT), each sampling angular frequency is similarly characterized by a wave vector, $\boldsymbol{\zeta}_{s_1,s_2} \equiv \boldsymbol{\zeta}(s_1, s_2)$, defined in a 2D problem as

$$\boldsymbol{\zeta}_{s_1,s_2} = \left(\frac{2\pi}{(l_{\text{RVE}})_1} s_1, \frac{2\pi}{(l_{\text{RVE}})_2} s_2 \right), \quad s_i = 0, 1, \ldots, n_i - 1, \quad i = 1, 2 \,. \tag{B.7}$$

In the three-dimensional case, both spatial coordinates and sampling angular frequencies are defined in a analogous way.



Figure B.1: Spatial discretization of a 2D RVE in a regular grid of 7×7 voxels.

B.3 Fixed point iterative solution

Having performed a suitable discretization of the RVE, Moulinec and Suquet (Moulinec and Suquet, 1994) propose to solve the Lippmann-Schwinger integral equilibrium equation through a simple fixed point iterative procedure. The main idea behind the basic iterative scheme relies on alternating evaluations in both spatial and frequency domains at each iteration: the Lippmann-Schwinger equation is evaluated in the frequency domain, where the Green operator convolution can be efficiently computed, and the constitutive response is evaluated in the spatial domain, where the micro-scale strain field is sought. Although the algorithm is detailed in pseudo-code format in Box B.1, some numerical aspects deserve further comments to allow a proper numerical implementation.

Remark.
A highly efficient computational implementation strategy based on suitable Hadamard (element-wise) operations is proposed in Section 4.6. Despite its overall simplicity, such approach is shown to yield massive speedups in comparison with a naive implementation.

In the first place, regarding the solution of the Lippmann-Schwinger integral equilibrium equation in the frequency domain, Moulinec and Suquet (Moulinec and Suquet, 1994) establish the identity

$$\check{\mathbf{\Phi}}^0(\boldsymbol{\zeta}) : \left(\mathbf{D}^{e,0} : \check{\boldsymbol{\varepsilon}}_\mu(\boldsymbol{\zeta})\right) = \check{\boldsymbol{\varepsilon}}_\mu(\boldsymbol{\zeta}) \,, \tag{B.8}$$

where the left-hand side emerges when the stress polarization field (see Equation (B.5)) is inserted into Equation (B.3). This property allows a simplification of the fixed point iterative solution as it bypasses the need to compute the stress polarization field.

In the second place, as remarked in Moulinec and Suquet (1994) and described in more detail in Michel et al. (2001), the rate of convergence of the algorithm depends drastically on the elastic properties of the reference homogeneous elastic material, λ^0 and μ^0. In order to ensure the best convergence rate of the iterative scheme, Moulinec and Suquet (1994) set the elastic properties as

$$\lambda^0 = \frac{1}{2}\left(\inf_{\boldsymbol{Y}\in\Omega_\mu}[\lambda(\boldsymbol{Y})] + \sup_{\boldsymbol{Y}\in\Omega_\mu}[\lambda(\boldsymbol{Y})]\right), \quad \mu^0 = \frac{1}{2}\left(\inf_{\boldsymbol{Y}\in\Omega_\mu}[\mu(\boldsymbol{Y})] + \sup_{\boldsymbol{Y}\in\Omega_\mu}[\mu(\boldsymbol{Y})]\right), \tag{B.9}$$

where $\inf[\bullet]$ and $\sup[\bullet]$ denote the infimum and supremum.

At last, concerning the evaluation of the iterative convergence, Moulinec and Suquet (Moulinec and Suquet, 1994) propose a discrete error based on the average stress divergence that is computed in the frequency domain as

$$\epsilon = \frac{1}{\left\|\check{\boldsymbol{\sigma}}_\mu(\mathbf{0})\right\|}\sqrt{\frac{1}{n_v}\sum_s^{n_v}\left\|\boldsymbol{\zeta}_s \cdot \check{\boldsymbol{\sigma}}_\mu(\boldsymbol{\zeta}_s)\right\|^2}, \tag{B.10}$$

where n_v is the total number of sampling points, and a convergence tolerance of 1×10^{-4}. Given the computational cost associated with the previous computation, an alternative discrete error is here proposed as

$$\epsilon = \frac{\left\|\boldsymbol{\sigma}_\mu(\boldsymbol{Y}_s)\right\|_{\text{avg}}^{(k)} - \left\|\boldsymbol{\sigma}_\mu(\boldsymbol{Y}_s)\right\|_{\text{avg}}^{(k-1)}}{\left\|\boldsymbol{\sigma}_\mu(\boldsymbol{Y}_s)\right\|_{\text{avg}}^{(k)}}, \tag{B.11}$$

where the average stress norm is defined as

$$\left\|\boldsymbol{\sigma}_\mu(\boldsymbol{Y}_s)\right\|_{\text{avg}}^{(k)} = \frac{1}{n_v}\sum_s^{n_v}\left\|\boldsymbol{\sigma}_\mu(\boldsymbol{Y}_s)\right\|^{(k)}. \tag{B.12}$$

Box B.1: FFT-based homogenization basic scheme (Moulinec and Suquet, 1994) fixed point iterative procedure applied to the solution of the Lippmann-Schwinger integral equilibrium equation associated to a micro-scale quasi-static equilibrium problem. The subscript $(\cdot)_s$ denotes the discrete nature of the sampling points (spatial domain) and angular frequencies (frequency domain).

(i) Initialize iterative counter, $k := 0$

(ii) Set Lamé parameters of reference homogeneous elastic material, $\left(\lambda^0, \mu^0\right)$

(iii) Set initial guess for the micro-scale discrete strain field (spatial domain)

$$\boldsymbol{\varepsilon}_{\mu}^{(0)}(\boldsymbol{Y}_s) = \boldsymbol{\varepsilon}(\boldsymbol{X}), \quad \forall \boldsymbol{Y}_s \in \Omega_{\mu,0}$$

(iv) Compute micro-scale discrete stress field (spatial domain)

$$\boldsymbol{\sigma}_{\mu}^{(k)}(\boldsymbol{Y}_s) = \mathbf{D}^e(\boldsymbol{Y}_s) : \boldsymbol{\varepsilon}_{\mu}^{(k)}(\boldsymbol{Y}_s), \quad \forall \boldsymbol{Y}_s \in \Omega_{\mu,0}$$

(v) Compute micro-scale discrete stress field (frequency domain)

$$\check{\boldsymbol{\sigma}}_{\mu}^{(k)}(\boldsymbol{\zeta}_s) = \mathscr{DFT}\left\{\boldsymbol{\sigma}_{\mu}^{(k)}(\boldsymbol{Y}_s)\right\}$$

(vi) Check for convergence (see Equations (B.10) and (B.11))
if (converged) then

- Exit

else

- Increment iteration counter, $k := k + 1$

(vii) Update micro-scale discrete strain field (frequency domain)

$$\check{\boldsymbol{\varepsilon}}_{\mu}^{(k)}(\boldsymbol{\zeta}_s) = \check{\boldsymbol{\varepsilon}}_{\mu}^{(k-1)}(\boldsymbol{\zeta}_s) - \check{\boldsymbol{\Phi}}^0(\boldsymbol{\zeta}_s) : \check{\boldsymbol{\sigma}}_{\mu}^{(k-1)}(\boldsymbol{\zeta}_s), \quad \forall \boldsymbol{\zeta}_s \neq \mathbf{0}, \quad \check{\boldsymbol{\varepsilon}}_{\mu}^{(k)}(\mathbf{0}) = \boldsymbol{\varepsilon}(\boldsymbol{X})$$

(viii) Compute micro-scale discrete strain field (spatial domain)

$$\boldsymbol{\varepsilon}_{\mu}^{(k)}(\boldsymbol{Y}_s) = \mathscr{DFT}^{-1}\left\{\check{\boldsymbol{\varepsilon}}_{\mu}^{(k)}(\boldsymbol{\zeta}_s)\right\}$$

(ix) Go to step (iv)

Appendix C
Self-Consistent Clustering Analysis (Infinitesimal Strains)

This Appendix includes a comprehensive review of the pioneering clustering-based reduced-order model (CROM) proposed by Liu and coworkers (Liu et al., 2016), the Self-Consistent Clustering Analysis (SCA) method. After providing a global overview of the method, each step of the underlying formulation is thoroughly discussed together with the required details for a suitable numerical implementation. Some numerical examples are also included to demonstrate the performance of the SCA in the solution of a micro-scale quasi-static equilibrium problem.

C.1 Formulation overview

Before diving into the details behind the SCA formulation, it is useful to have a prior overview of the method as schematically illustrated in Figure C.1. The SCA method is a two-stage algorithm. In the offline-stage, which can be understood as a training/learning stage, the high-fidelity representative volume element (RVE)[1] is compressed into a cluster-reduced RVE (CRVE) by means of clustering-based domain decomposition, i.e., a cluster analysis that decomposes the spatial domain into a given number of material clusters (step 2). Aiming to group domain points with similar mechanical behavior, the cluster analysis is performed over a dataset computed from low demanding direct numerical simulations (DNS) of linear elastic micro-scale equilibrium problems under orthogonal loading conditions (step 1). In addition, the so-called cluster interaction tensors must be computed between every pair of clusters (step 3) to conclude the definition of the CRVE. The following online-stage comprises the actual prediction of the material response under a given set of strain and/or stress macro-scale loading constraints. Due to the general material nonlinearity of the clustered Lippmann-Schwinger system of equilibrium equations, the solution can be conveniently solved through a standard Newton-Raphson scheme after proper linearization (step 4). The macro-scale material response can be finally computed by computational homogenization (step 5). Given that the solution accuracy is intrinsically with the model reduction, as well as specific formulation features of the SCA, preliminary assessments against DNS simulations shall be performed through appropriate error metrics.

C.2 Step 1: Linear elastic DNS solutions

Similar to a standard multi-scale model based on computational homogenization, the first requirement consists in generating a high-fidelity RVE that contains the morphological and topological details of the microstructure under analysis (e.g., see Chaper 3). The challenge in the offline-stage is then to reduce the computational cost of the RVE analysis without losing the ability to accurately capture the material mechanical behavior.

[1] The designation of 'high-fidelity' RVE is here employed to describe the RVE associated to a given DNS homogenization method, e.g. FEM or FFT-based homogenization schemes, where all the degrees of freedom resulting from a suitable spatial discretization procedure are accounted for in the solution process.



Figure C.1: Schematic of the Self-Consistent Clustering Analysis (SCA) clustering-based reduced-order model proposed by Liu and coworkers (Liu et al., 2016).

In order to achieve these seemingly incompatible requirements, one can think of grouping points with similar mechanical behavior and treat them in a unified sense – this leads to the concept of material cluster (see Section 4.3.1). Liu and coworkers (Liu et al., 2016) propose to evaluate the mechanical behavior similarity between different points of the domain based on the fourth-order local elastic strain concentration tensor, $\mathbf{H}$,

$$\boldsymbol{\varepsilon}^e_\mu(\boldsymbol{Y}) = \mathbf{H}^e(\boldsymbol{Y}) : \boldsymbol{\varepsilon}^e(\boldsymbol{X}), \quad \forall \boldsymbol{Y} \in \Omega_{\mu,0}, \tag{C.1}$$

establishing the relation between the macro-scale and micro-scale strains at each point of the micro-scale domain. The matricial form of the previous definition shows that $\mathbf{H}^e(\boldsymbol{Y})$ can be determined from the DNS solution of 3 (2D) or 6 (3D) linear elastic micro-scale equilibrium problems under orthogonal loading conditions (e.g., in 2D each column could be found by imposing in turn $\boldsymbol{\varepsilon}^e(\boldsymbol{X}) = [1,0,0]^T$, $\boldsymbol{\varepsilon}^e(\boldsymbol{X}) = [0,1,0]^T$ and $\boldsymbol{\varepsilon}^e(\boldsymbol{X}) = [0,0,1]^T$).

The adoption of such clustering feature yields two important advantages. Firstly, given that only requires the solution of linear elastic micro-scale equilibrium problems[2], the clustering feature dataset can be computed at low computional cost. Secondly, it aggregates data about the material response subject to several loading constraints. This seems a clever way of accounting for the general and distinct loading constraints that may be enforced in the following online-stage, i.e., it is assumed that if two domain points have similar strain concentration tensors, then their behavior will be the same under any loading constraints in the elastic regime. However, it can be argued that linear elastic analyses are not sufficient to characterize the mechanical behavior similarity in the following nonlinear regime involving plasticity, damage and localization phenomena. The answer lies in the main assumption underlying the SCA formulation: given that plastic flow will generally occur in points with equivalent high strain concentrations, it is expected that the mechanical similarity holds in the nonlinear elastoplastic regime.

[2]Given the geometrical and material linearity of the micro-scale equilibrium problem, the orthogonal strain loadings can be enforced in a single loading increment.

Regarding the DNS solution of the micro-scale equilibrium problems under orthogonal strain loadings, one may resort to a first-order homogenization model based on the Finite Element Method (FEM) (see Chapter 2 and Appendix D) or to FFT-based homogenization solvers, such as the FFT-based homogenization basic scheme described in Appendix B. The latter are particularly appealing in this context, as discussed in Section 4.6.

C.3 Step 2: Cluster analysis

With the high-fidelity RVE and the clustering feature dataset at hand, a suitable clustering algorithm must be chosen to perform the clustering-based domain decomposition. Among the extensive amount of clustering algorithms that have been developed and applied to different fields, Liu et al. (2016) selected a particular and well-known centroid-based clustering algorithm named K-means clustering. This unsupervised machine learning clustering technique is able to partition a set of data points into k clusters through two main steps:

1. **Evaluation**. Define the clustering feature based on which similar points are to be grouped and evaluate it at each point of the dataset;

2. **Clustering**. Partition the dataset of points into K clusters such that each cluster contains the points whose clustering feature is closer to the average over that cluster when compared to the average of any other cluster.

In the particular case of interest envisaged here, the clustering feature is the fourth-order elastic strain concentration tensor, $\mathbf{H}^e$, and all the points of the RVE domain are to be grouped into n_c clusters such that cluster I contains the points whose $\mathbf{H}^e$ is closer to the average of cluster I, $\overline{\mathbf{H}}^{e,(I)}$, than to the average of any other cluster $J \neq I$, $\overline{\mathbf{H}}^{e,(J)}$. The technique can be mathematically formulated as a minimization problem as follows:

Problem C.1 | RVE domain decomposition through K-means clustering.

For a given set of strain concentration tensors, $\mathscr{H}$, evaluated at each point of the RVE domain, find n_c sets of points, $\mathscr{S} = \left\{\mathscr{S}^{(1)}, \mathscr{S}^{(2)}, \ldots, \mathscr{S}^{(n_c)}\right\}$, such that the within-cluster least squares sum with respect to the cluster average is minimized as

$$\mathscr{S} = \underset{\mathscr{S}^{(I)}}{\operatorname{argmin}} \sum_{I=1}^{n_\mathrm{c}} \left[\sum_{\boldsymbol{Y} \in \mathscr{S}^{(I)}} \left\| \mathbf{H}^e(\boldsymbol{Y}) - \overline{\mathbf{H}}^{e,(I)} \right\|^2 \right], \tag{C.2}$$

where $\overline{\mathbf{H}}^{e,(I)}$ is the average of all the strain concentration tensors $\mathbf{H}^e(\boldsymbol{Y})$ at the points within the cluster $\mathscr{S}^{(I)}$ and $\|[\bullet]\|$ denotes the Frobenius norm of the matrix $[\bullet]$.

There are several well developed algorithms to solve the previous K-means minimization problem. Among these, Liu et al. (2016) employed the standard Lloyds' algorithm (Lloyd, 1982) that is presented in pseudo-code format in Box C.1 and schematically illustrated in Figure C.2.

Given that each material cluster groups points with similar mechanical behavior, the previous clustering procedure may be applied independently to each material phase of the RVE domain. This approach takes advantage of the a priori knowledge of the problem (material phases) by narrowing the domains where the unsupervised machine learning technique K-means is employed to perform the domain decomposition. In this respect, it is suggested that the number of clusters of the different material phases is set in proportion to the respective volume fractions.



Figure C.2: Schematic of the solution of the K-means clustering minimization problem through the standard Lloyds' algorithm (Lloyd, 1982).

Remark.
The number of cluster n_c is directly related to the achieved degree of data compression of the CRVE model. Given that the analyst can choose the number of clusters to perform the clustering-based domain decomposition, a suitable choice should always contemplate the balance between the model reduction and the accuracy of the CRVE model's mechanical response. In general, an increased number of clusters stores more information about the microstructure details in the offline-stage, leading to more accurate predictions in the online-stage at the expense of an increased computational cost.

C.4 Step 3: Cluster interaction tensors

The final step of the offline-stage consists in the computation of the so-called cluster interaction tensors between every pair of clusters (see Figure C.3). As demonstrated in Section 4.3.2, these fourth-order tensors arise naturally in the derivation of the clustered Lippmann-Schwinger integral equilibrium equation and are defined by Equation (4.79). Following Moulinec and Suquet (Moulinec and Suquet, 1994), the reference homogeneous elastic material is also assumed isotropic and the Green operator is therefore explicitly defined in the frequency domain by Equation (4.21). The choice of the reference material Lamé parameters, (λ^0, μ^0), is discussed in the following section.

Box C.1: Solution of the K-means clustering minimization problem through the standard Lloyds' algorithm (Lloyd, 1982) in order to perform the RVE cluster-based domain decomposition.

(i) Select n_c random points from the RVE domain that define the initial clusters, $\left(\mathscr{S}^{(I)}\right)^{(0)}$, $I = 1,\dots,n_c$, and the set the corresponding averages

(ii) Initialize iterative counter, $k := 1$

(iii) Loop over all the points, characterized by the associated strain concentration tensor, $\mathbf{H}^e(\boldsymbol{Y})$, and assign each point to the cluster I whose average is closer to its value, i.e.,

$$\left\| \mathbf{H}^e(\boldsymbol{Y}) - \left(\overline{\mathbf{H}}^{e,(I)}\right)^{(k)} \right\|^2 \leq \left\| \mathbf{H}^e(\boldsymbol{Y}) - \left(\overline{\mathbf{H}}^{e,(J)}\right)^{(k)} \right\|^2, \quad \forall \boldsymbol{Y} \in \left(\mathscr{S}^{(I)}\right)^{(k)},$$

$$I = 1,2,\dots,n_c, \quad \forall J \in \{1,2,\dots,n_c\}, \quad J \neq I$$

(iv) Check for convergence (clusters remained iteratively unchanged)

if (converged) then

- Convergence to a local optimum[a] is achieved, exit

else

- Increment iteration counter, $k := k+1$

(v) Update the average values of each cluster

$$\left(\overline{\mathbf{H}}^{e,(I)}\right)^{(k)} = \frac{1}{\left(n^{(I)}\right)^{(k)}} \sum_{\boldsymbol{Y} \in \left(\mathscr{S}^{(I)}\right)^{(k)}} \mathbf{H}^e(\boldsymbol{Y}), \tag{C.3}$$

where $\left(n^{(I)}\right)^{(k)}$ is the number of points contained in cluster I

(vi) Go to step (iii)

[a] As pointed out by Liu et al. (2016), the global optimum is not guaranteed in the optimization problem. The algorithm can be run multiple times with different random initializations in order to inspect the optimality of the solution.

Remark.
The convolution over the Jth cluster arising in the definition of the cluster interaction tensors (see Equation (4.79)) can be computed in the discrete frequency domain through efficient FFT algorithms, i.e.,

$$\int_{\Omega_{\mu,0}} \chi^{(J)}(\boldsymbol{Y}')\,\boldsymbol{\Phi}^0(\boldsymbol{Y},\boldsymbol{Y}')\,\mathrm{d}v' = \mathscr{F}^{-1}\left(\check{\chi}^{(J)}(\boldsymbol{\zeta})\,\check{\boldsymbol{\Phi}}^0(\boldsymbol{\zeta})\right). \tag{C.4}$$



Figure C.3: Schematic of the cluster interaction tensors in a cluster-reduced RVE (CRVE) with 3 material clusters.

C.5 Step 4: Clustered Lippmann-Schwinger equilibrium

C.5.1 Micro-scale equilibrium problem

The online-stage of the SCA method consists in the solution of the clustered Lippmann-Schwinger system of equilibrium equations established by Equations (4.87) and (4.88). Due to the general nonlinearity associated to the material clusters constitutive behavior, the solution can be efficiently found through the well-known Newton-Raphson Method (see Section 2.9.5) and the associated quadratic convergence rate.

In order to do so, it is first convenient to set the global residual function defined as

$$\boldsymbol{R}_{m+1} = \begin{bmatrix} \boldsymbol{R}^{(I)}_{m+1} \\ \boldsymbol{R}^{(n_c+1)}_{m+1} \end{bmatrix} = \begin{bmatrix} \boldsymbol{0} \\ \boldsymbol{0} \end{bmatrix}, \qquad \forall I = 1,2,\ldots,n_c\,, \tag{C.5}$$

where the $n_c + 1$ residual functions are defined as

$$\boldsymbol{R}^{(I)}_{m+1} = \Delta\boldsymbol{\varepsilon}^{(I)}_{\mu,m+1} + \sum_{J=1}^{n_c} \mathbf{T}^{(I)(J)} : \left(\Delta\hat{\boldsymbol{\sigma}}^{(J)}_{\mu,m+1} - \mathbf{D}^{e,0} : \Delta\boldsymbol{\varepsilon}^{(J)}_{\mu,m+1}\right) - \Delta\boldsymbol{\varepsilon}^{0}_{\mu,m+1}, \quad \forall I = 1,\ldots,n_c, \tag{C.6}$$

$$\boldsymbol{R}^{(n_c+1)}_{m+1} = \sum_{I=1}^{n_c} f^{(I)}\Delta\boldsymbol{\varepsilon}^{(I)}_{\mu,m+1} - \Delta\boldsymbol{\varepsilon}_{m+1}(\boldsymbol{X}) \quad ; \quad \boldsymbol{R}^{(n_c+1)}_{m+1} = \sum_{I=1}^{n_c} f^{(I)}\Delta\hat{\boldsymbol{\sigma}}^{(I)}_{\mu,m+1} - \Delta\boldsymbol{\sigma}_{m+1}(\boldsymbol{X}). \tag{C.7}$$

Then, each Newton-Raphson iteration (k) consists in finding the solution of the linearized version of Equation (C.5) as

$$\Delta\boldsymbol{\varepsilon}^{(k)}_{\mu,m+1} = \Delta\boldsymbol{\varepsilon}^{(k-1)}_{\mu,m+1} + \delta\Delta\boldsymbol{\varepsilon}^{(k)}_{\mu}, \qquad \delta\Delta\boldsymbol{\varepsilon}^{(k)}_{\mu} = -\mathbf{J}^{-1}\left(\Delta\boldsymbol{\varepsilon}^{(k-1)}_{\mu,m+1}\right)\mathbf{R}\left(\Delta\boldsymbol{\varepsilon}^{(k-1)}_{\mu,m+1}\right), \tag{C.8}$$

where $\Delta\boldsymbol{\varepsilon}_{\mu,m+1}$ is the matricial form of the vector of unknowns defined in Equation (4.88), $\mathbf{R}$ is the vectorial form of the global residual defined in Equation (C.5) and $\mathbf{J}$ is the matricial form of the Jacobian matrix

$$\boldsymbol{J}_{m+1} = \frac{\partial \boldsymbol{R}_{m+1}}{\partial\Delta\boldsymbol{\varepsilon}_{\mu,m+1}} = \begin{bmatrix} \dfrac{\partial \boldsymbol{R}^{(I)}_{m+1}}{\partial\Delta\boldsymbol{\varepsilon}^{(K)}_{\mu,m+1}} & \dfrac{\partial \boldsymbol{R}^{(I)}_{m+1}}{\partial\Delta\boldsymbol{\varepsilon}^{0}_{\mu,m+1}} \\ \dfrac{\partial \boldsymbol{R}^{(n_c+1)}_{m+1}}{\partial\Delta\boldsymbol{\varepsilon}^{(K)}_{\mu,m+1}} & \dfrac{\partial \boldsymbol{R}^{(n_c+1)}_{n+1}}{\partial\Delta\boldsymbol{\varepsilon}^{0}_{\mu,m+1}} \end{bmatrix}, \qquad \forall I, K = 1,\ldots,n_c. \tag{C.9}$$

The solution procedure of a given loading increment $m+1$ of the clustered Lippmann-Schwinger system of equilibrium equations is summarized in pseudo-code format in Box C.2. For the sake of completeness, the linearization of the Lippmann-Schwinger equilibrium residuals and macro-scale constraints residuals is provided in what follows. Attending to the Jacobian matrix established in Equation (C.9), four distinct tensorial derivatives are required to completely define the linearization.

The first derivative can be written in its expanded form as

$$\frac{\partial \boldsymbol{R}^{(I)}_{m+1}}{\partial\Delta\boldsymbol{\varepsilon}^{(K)}_{\mu,m+1}} = \frac{\partial\Delta\boldsymbol{\varepsilon}^{(I)}_{\mu,m+1}}{\partial\Delta\boldsymbol{\varepsilon}^{(K)}_{\mu,m+1}} + \frac{\partial}{\partial\Delta\boldsymbol{\varepsilon}^{(K)}_{\mu,m+1}}\left(\sum_{J=1}^{n_c}\mathbf{T}^{(I)(J)} : \left(\Delta\hat{\boldsymbol{\sigma}}^{(J)}_{\mu,m+1} - \mathbf{D}^{e,0} : \Delta\boldsymbol{\varepsilon}^{(J)}_{\mu,m+1}\right)\right) + \underbrace{\frac{\partial\Delta\boldsymbol{\varepsilon}^{0}_{\mu,m+1}}{\partial\Delta\boldsymbol{\varepsilon}^{(K)}_{\mu,m+1}}}_{0}, \tag{C.10}$$

and applying the differentiation chain rule one gets

$$\frac{\partial \boldsymbol{R}^{(I)}_{m+1}}{\partial\Delta\boldsymbol{\varepsilon}^{(K)}_{\mu,m+1}} = \delta_{(I)(K)}\mathbf{I} + \sum_{J=1}^{n_c}\mathbf{T}^{(I)(J)} : \left(\delta_{(J)(K)}\mathbf{I} : \frac{\partial\Delta\hat{\boldsymbol{\sigma}}^{(K)}_{\mu,m+1}}{\partial\Delta\boldsymbol{\varepsilon}^{(K)}_{\mu,m+1}} - \mathbf{D}^{e,0} : \delta_{(J)(K)}\mathbf{I}\right), \tag{C.11}$$

where $\mathbf{I}$ is the fourth-order identity tensor. Noticing that the material consistent tangent modulus of the Kth cluster is defined as

$$\mathbf{D}^{(K)}_{m+1} = \frac{\partial\Delta\hat{\boldsymbol{\sigma}}^{(K)}_{\mu,m+1}\left(\Delta\boldsymbol{\varepsilon}^{(K)}_{\mu,m+1}, \boldsymbol{\beta}_m\right)}{\partial\Delta\boldsymbol{\varepsilon}^{(K)}_{\mu,m+1}}, \tag{C.12}$$

Box C.2: Solution procedure of a given loading increment $m+1$ of the infinitesimal strains clustered Lippmann-Schwinger system of equilibrium equations through the Newton-Raphon Method.

(i) Initialize iterative counter, $k := 1$

(ii) Set initial guess for incremental strains, $\Delta\varepsilon^{(0)}_{\mu,m+1} = \mathbf{0}$

(iii) Perform the material state update for each cluster

$$\Delta\boldsymbol{\sigma}^{(I)(k-1)}_{\mu,m+1} = \Delta\hat{\boldsymbol{\sigma}}_{\mu,m+1}\left(\Delta\boldsymbol{\varepsilon}^{(I)(k-1)}_{\mu,m+1}, \boldsymbol{\alpha}^{(I)}_{m}\right), \qquad \forall I = 1,2,\ldots,n_{\mathrm{c}}$$

(iv) Compute global residual functions

$$\boldsymbol{R}^{(I)}_{m+1}\left(\Delta\boldsymbol{\varepsilon}^{(k-1)}_{\mu,m+1}\right) = \Delta\boldsymbol{\varepsilon}^{(I)(k-1)}_{\mu,m+1} + \sum_{J=1}^{n_{\mathrm{c}}} \mathbf{T}^{(I)(J)} : \left[\Delta\hat{\boldsymbol{\sigma}}^{(J)(k-1)}_{\mu,m+1} - \mathbf{D}^{e,0} : \Delta\boldsymbol{\varepsilon}^{(J)(k-1)}_{\mu,m+1}\right] - \Delta\boldsymbol{\varepsilon}^{0,(k-1)}_{\mu,m+1},$$

$$\forall I = 1,2,\ldots,n_{\mathrm{c}},$$

$$\boldsymbol{R}^{(n_{\mathrm{c}}+1)}_{m+1}\left(\Delta\boldsymbol{\varepsilon}^{(k-1)}_{\mu,m+1}\right) = \sum_{I=1}^{n_{\mathrm{c}}} f^{(I)}\Delta\boldsymbol{\varepsilon}^{(I)}_{\mu,m+1} - \Delta\boldsymbol{\varepsilon}_{m+1}(\boldsymbol{X});$$

$$\boldsymbol{R}^{(n_{\mathrm{c}}+1)}_{m+1}\left(\Delta\boldsymbol{\sigma}^{(k-1)}_{\mu,m+1}\right) = \sum_{I=1}^{n_{\mathrm{c}}} f^{(I)}\Delta\boldsymbol{\sigma}^{(I)}_{\mu,m+1} - \Delta\boldsymbol{\sigma}_{m+1}(\boldsymbol{X})$$

(v) Check for convergence

if (converged) then

- Update incremental solution, $(\bullet)_{m+1} = (\bullet)^{(k)}_{m+1}$, and exit

(vi) Compute Jacobian matrix

$$\boldsymbol{J}\left(\Delta\varepsilon^{(k-1)}_{\mu,m+1}\right) = \left[\begin{array}{cc} \dfrac{\partial\boldsymbol{R}^{(I)}_{m+1}}{\partial\Delta\boldsymbol{\varepsilon}^{(K)}_{\mu,m+1}} & \dfrac{\partial\boldsymbol{R}^{(I)}_{m+1}}{\partial\Delta\boldsymbol{\varepsilon}^{0}_{\mu,m+1}} \\ \dfrac{\partial\boldsymbol{R}^{(n_{\mathrm{c}}+1)}_{m+1}}{\partial\Delta\boldsymbol{\varepsilon}^{(K)}_{\mu,m+1}} & \dfrac{\partial\boldsymbol{R}^{(n_{\mathrm{c}}+1)}_{m+1}}{\partial\Delta\boldsymbol{\varepsilon}^{0}_{\mu,m+1}} \end{array}\right]_{\left(\Delta\varepsilon^{(k-1)}_{\mu,m+1}\right)}, \qquad \forall I,K = 1,2,\ldots,n_{\mathrm{c}},$$

where the residual derivatives are defined by Equations (C.13), (C.15), (C.18) or (C.21), and (C.22)

(vii) Solve the system of linear equations

$$\delta\Delta\varepsilon^{(k)}_{\mu} = -\mathbf{J}^{-1}\left(\Delta\varepsilon^{(k-1)}_{\mu,m+1}\right)\mathbf{R}\left(\Delta\varepsilon^{(k-1)}_{\mu,m+1}\right)$$

(viii) Update incremental strains

$$\Delta\varepsilon^{(k)}_{\mu,m+1} = \Delta\varepsilon^{(k-1)}_{\mu,m+1} + \delta\Delta\varepsilon^{(k)}_{\mu}$$

(ix) Increment iteration counter, $k := k+1$

(x) Go to step (iii)

it finally results

$$\frac{\partial \boldsymbol{R}^{(I)}_{m+1}}{\partial \Delta \boldsymbol{\varepsilon}^{(K)}_{\mu,m+1}} = \delta_{(I)(K)}\mathbf{I} + \mathbf{T}^{(I)(K)} : \left(\mathbf{D}^{(K)}_{m+1} - \mathbf{D}^{e,0}\right). \tag{C.13}$$

The derivative of the same residual in order to the homogeneous incremental far-field strain is expanded as

$$\frac{\partial \boldsymbol{R}^{(I)}_{m+1}}{\partial \Delta \boldsymbol{\varepsilon}^{0}_{\mu,m+1}} = \underbrace{\frac{\partial \boldsymbol{R}^{(I)}_{m+1}}{\partial \Delta \boldsymbol{\varepsilon}^{0}_{\mu,m+1}} \left(\Delta \boldsymbol{\varepsilon}^{(I)}_{\mu,m+1} + \sum_{J=1}^{n_c} \mathbf{T}^{(I)(J)} : \left(\Delta \hat{\boldsymbol{\sigma}}^{(J)}_{\mu,m+1} - \mathbf{D}^{e,0} : \Delta \boldsymbol{\varepsilon}^{(J)}_{\mu,m+1} \right] \right)}_{0} - \frac{\partial \Delta \boldsymbol{\varepsilon}^{0}_{\mu,m+1}}{\partial \Delta \boldsymbol{\varepsilon}^{0}_{\mu,m+1}}, \tag{C.14}$$

being simply defined as

$$\frac{\partial \boldsymbol{R}^{(I)}_{m+1}}{\partial \Delta \boldsymbol{\varepsilon}^{0}_{\mu,m+1}} = -\mathbf{I}. \tag{C.15}$$

Concerning the macro-scale strain constraint, the third residual derivative yields

$$\frac{\partial \boldsymbol{R}^{(n_c+1)}_{m+1}}{\partial \Delta \boldsymbol{\varepsilon}^{(K)}_{\mu,m+1}} = \frac{\partial}{\partial \Delta \boldsymbol{\varepsilon}^{(K)}_{\mu,m+1}} \left(\sum_{I=1}^{n_c} f^{(I)} \Delta \boldsymbol{\varepsilon}^{(I)}_{\mu,m+1} \right) - \underbrace{\frac{\partial \Delta \boldsymbol{\varepsilon}_{m+1}(\boldsymbol{X})}{\partial \Delta \boldsymbol{\varepsilon}^{(K)}_{\mu,m+1}}}_{0}, \tag{C.16}$$

which can be developed as

$$\frac{\partial \boldsymbol{R}^{(n_c+1)}_{m+1}}{\partial \Delta \boldsymbol{\varepsilon}^{(K)}_{\mu,m+1}} = \sum_{I=1}^{n_c} f^{(I)} \frac{\partial \Delta \boldsymbol{\varepsilon}^{(I)}_{\mu,m+1}}{\partial \Delta \boldsymbol{\varepsilon}^{(K)}_{\mu,m+1}} = \sum_{I=1}^{n_c} f^{(I)} \delta_{(I)(K)} \mathbf{I}, \tag{C.17}$$

and results in

$$\frac{\partial \boldsymbol{R}^{(n_c+1)}_{m+1}}{\partial \Delta \boldsymbol{\varepsilon}^{(K)}_{\mu,m+1}} = f^{(K)} \mathbf{I}. \tag{C.18}$$

In a similar manner, the residual derivative associated with a macro-scale stress constraint is given by

$$\frac{\partial \boldsymbol{R}^{(n_c+1)}_{m+1}}{\partial \Delta \boldsymbol{\varepsilon}^{(K)}_{\mu,m+1}} = \frac{\partial}{\partial \Delta \boldsymbol{\varepsilon}^{(K)}_{\mu,m+1}} \left(\sum_{I=1}^{n_c} f^{(I)} \Delta \hat{\boldsymbol{\sigma}}^{(I)}_{\mu,m+1} \right) - \underbrace{\frac{\partial \Delta \boldsymbol{\sigma}_{m+1}(\boldsymbol{X})}{\partial \Delta \boldsymbol{\varepsilon}^{(K)}_{\mu,m+1}}}_{0}, \tag{C.19}$$

which after application of the differentiation chain rule comes

$$\frac{\partial \boldsymbol{R}^{(n_c+1)}_{m+1}}{\partial \Delta \boldsymbol{\varepsilon}^{(K)}_{\mu,m+1}} = \sum_{I=1}^{n_c} f^{(I)} \frac{\partial \Delta \hat{\boldsymbol{\sigma}}^{(I)}_{\mu,m+1}}{\partial \Delta \boldsymbol{\varepsilon}^{(K)}_{\mu,m+1}} = \sum_{I=1}^{n_c} f^{(I)} \delta_{(I)(K)} \mathbf{I} : \mathbf{D}^{(K)}_{m+1}, \tag{C.20}$$

and results in

$$\frac{\partial \boldsymbol{R}_{m+1}^{(n_c+1)}}{\partial \Delta \boldsymbol{\varepsilon}_{\mu,\,m+1}^{(K)}} = f^{(K)} \mathbf{D}_{m+1}^{(K)}. \tag{C.21}$$

Finally, the fourth and last derivative is null,

$$\frac{\partial \boldsymbol{R}_{m+1}^{(n_c+1)}}{\partial \Delta \boldsymbol{\varepsilon}_{\mu,\,m+1}^{0}} = \mathbf{0}. \tag{C.22}$$

C.5.2 Self-consistent scheme

As discussed in Section 4.3.2, the solution of the clustered Lippmann-Schwinger integral equilibrium equation depends on the reference elastic material Lamé parameters, (λ^0, μ^0), as numerically demonstrated in Liu et al. (2016). Despite not quantifying such dependency from a mathematical point of view, Liu and coworkers (Liu et al., 2016) propose a well-known self-consistent micromechanical approach to find an 'optimal' choice of the reference material Lamé parameters.

Inspired by the self-consistent method of classical micromechanics (see Appendix A), the idea consists in finding, at each instant t_{m+1}, the reference material Lamé parameters, $(\lambda_{m+1}^0, \mu_{m+1}^0)$, that renders the best approximation between the homogeneous tangent modulus of the reference material, $\mathbf{D}_{m+1}^{e,0}(\lambda_{m+1}^0, \mu_{m+1}^0)$, and the CRVE effective tangent modulus (see Equation (C.47)), $\overline{\mathbf{D}}_{m+1}$. Given the linear elastic isotropic nature of the reference homogeneous material, this approach clearly yields a optimization problem that can be stated as follows:

Problem C.2 | Self-consistent optimization problem.

Assuming a reference homogeneous linear elastic isotropic material with the tangent modulus at each loading increment $m+1$ given by $\mathbf{D}_{m+1}^{e,0}(\lambda_{m+1}^0, \mu_{m+1}^0)$, find the two Lamé parameters $(\lambda_{m+1}^0,\ \mu_{m+1}^0)$ such that the difference with respect to the homogenized consistent tangent modulus of the CRVE, $\overline{\mathbf{D}}_{m+1}$, is minimized.

In this context, Liu and coworkers (Liu et al., 2016) propose the so-called regression-based self-consistent scheme. The underlying optimization problem can be mathematically formulated as

Problem C.3 | Regression-based self-consistent scheme optimization problem.

Assuming a reference homogeneous linear elastic isotropic material with the tangent modulus at each loading increment $m+1$ given by $\mathbf{D}_{m+1}^{e,0}(\lambda_{m+1}^0, \mu_{m+1}^0)$, find the two Lamé parameters $(\lambda_{m+1}^0,\ \mu_{m+1}^0)$ such that the difference with respect to the effective tangent modulus of the CRVE, $\overline{\mathbf{D}}_{m+1}$, is minimized as

$$\left\{\lambda_{m+1}^0,\, \mu_{m+1}^0\right\} = \underset{\{\lambda',\,\mu'\}}{\operatorname{argmin}} \left\| \Delta \boldsymbol{\sigma}_{m+1} - \mathbf{D}_{m+1}^{e,0}(\lambda', \mu') : \Delta \boldsymbol{\varepsilon}_{m+1} \right\|^2, \tag{C.23}$$

where $\|[\bullet]\|$ denotes the Frobenius norm of the matrix $[\bullet]$ and the homogenized incremental strain and stress tensors are defined by Equations (4.80) *and* (4.81).

In order to solve the minimization problem, one can define the cost function

$$g(\lambda', \mu') = \left\| \Delta\boldsymbol{\sigma}_{m+1} - \mathbf{D}^{e,0}_{m+1}(\lambda', \mu') : \Delta\boldsymbol{\varepsilon}_{m+1} \right\|^2, \tag{C.24}$$

where $\mathbf{D}^{e,0}_{m+1}$ is the tangent modulus of the reference homogeneous elastic material at the loading increment $m+1$ defined as

$$\mathbf{D}^{e,0}_{m+1}(\lambda^0, \mu^0) = \lambda^0_{m+1} \boldsymbol{I} \otimes \boldsymbol{I} + 2\mu^0_{m+1} \mathbf{I}_s . \tag{C.25}$$

Liu and coworkers (Liu et al., 2016) propose to find the 'optimum' solution $(\lambda^0_{m+1}, \mu^0_{m+1})$ by solving the system of two linear equations defined as

$$\begin{cases} \dfrac{\partial g(\lambda', \mu')}{\partial \lambda'} = 0 , \\ \dfrac{\partial g(\lambda', \mu')}{\partial \mu'} = 0 . \end{cases} \tag{C.26}$$

Denoting the tensorial quantity in Equation (C.24) as $\boldsymbol{A}$ for the sake of compact notation,

$$\boldsymbol{A} = \Delta\boldsymbol{\sigma}_{m+1} - \mathbf{D}^{e,0}_{m+1}(\lambda', \mu') : \Delta\boldsymbol{\varepsilon}_{m+1} , \tag{C.27}$$

and by applying the differentiation chain rule, the derivative of the cost function with respect to λ' is given by

$$\frac{\partial g(\lambda', \mu')}{\partial \lambda'} = \frac{\partial \|\boldsymbol{A}\|^2}{\partial \|\boldsymbol{A}\|} \frac{\partial \|\boldsymbol{A}\|}{\partial \boldsymbol{A}} : \frac{\partial \boldsymbol{A}}{\partial \lambda'} = 2\boldsymbol{A} : \left(- \frac{\partial \mathbf{D}^{e,0}_{m+1}(\lambda', \mu')}{\partial \lambda'} : \Delta\boldsymbol{\varepsilon}_{m+1} \right) . \tag{C.28}$$

Given that

$$\frac{\partial \mathbf{D}^{e,0}_{m+1}(\lambda', \mu')}{\partial \lambda'} = \boldsymbol{I} \otimes \boldsymbol{I} , \tag{C.29}$$

and that

$$(\boldsymbol{I} \otimes \boldsymbol{I}) : \Delta\boldsymbol{\varepsilon}_{m+1} = \mathrm{tr}\left[\Delta\boldsymbol{\varepsilon}_{m+1}\right] \boldsymbol{I} , \tag{C.30}$$

it is possible to write

$$\frac{\partial g(\lambda', \mu')}{\partial \lambda'} = -2\,\mathrm{tr}\left[\Delta\boldsymbol{\varepsilon}_{m+1}\right] \boldsymbol{A} : \boldsymbol{I} = -2\,\mathrm{tr}\left[\Delta\boldsymbol{\varepsilon}_{m+1}\right] \mathrm{tr}\left[\boldsymbol{A}\right] . \tag{C.31}$$

After expanding $\boldsymbol{A}$ and some simple algebraic manipulations, the derivative can be finally written as

$$\frac{\partial g(\lambda', \mu')}{\partial \lambda'} = -2\,\mathrm{tr}\left[\Delta\boldsymbol{\varepsilon}_{m+1}\right] \left(\mathrm{tr}\left[\Delta\boldsymbol{\sigma}_{m+1}\right] - \lambda' \,\mathrm{tr}\left[\boldsymbol{I}\right] \mathrm{tr}\left[\Delta\boldsymbol{\varepsilon}_{m+1}\right] - 2\mu' \,\mathrm{tr}\left[\Delta\boldsymbol{\varepsilon}_{m+1}\right] \right) . \tag{C.32}$$

Concerning the derivative with respect to μ', by following a similar procedure one can write

$$\frac{\partial g(\lambda', \mu')}{\partial \mu'} = \frac{\partial \|\boldsymbol{A}\|^2}{\partial \|\boldsymbol{A}\|} \frac{\partial \|\boldsymbol{A}\|}{\partial \boldsymbol{A}} : \frac{\partial \boldsymbol{A}}{\partial \mu'} = 2\boldsymbol{A} : \left(- \frac{\partial \mathbf{D}^{e,0}_{m+1}(\lambda', \mu')}{\partial \mu'} : \Delta\boldsymbol{\varepsilon}_{m+1} \right) . \tag{C.33}$$

Given that

$$\frac{\partial \mathbf{D}^{e,0}_{m+1}(\lambda', \mu')}{\partial \mu'} = 2\,\mathbf{I}_s , \tag{C.34}$$

and that the infinitesimal strain tensor is symmetric,

$$\mathbf{I}_s : \Delta\boldsymbol{\varepsilon}_{m+1} = \Delta\boldsymbol{\varepsilon}_{m+1}\,, \tag{C.35}$$

it comes

$$\frac{\partial g(\lambda',\mu')}{\partial \mu'} = -4\boldsymbol{A} : \Delta\boldsymbol{\varepsilon}_{m+1}\,. \tag{C.36}$$

After expanding $\boldsymbol{A}$ and performing some algebraic manipulations, the derivative is finally given by

$$\frac{\partial g(\lambda',\mu')}{\partial \mu'} = -4\left(\Delta\boldsymbol{\sigma}_{m+1} : \Delta\boldsymbol{\varepsilon}_{m+1} - \lambda' \operatorname{tr}\left[\Delta\boldsymbol{\varepsilon}_{m+1}\right] \operatorname{tr}\left[\Delta\boldsymbol{\varepsilon}_{m+1}\right] - 2\mu' \Delta\boldsymbol{\varepsilon}_{m+1} : \Delta\boldsymbol{\varepsilon}_{m+1}\right). \tag{C.37}$$

The following system of two linear equations can then be established,

$$\begin{cases} \dfrac{\partial g(\lambda',\mu')}{\partial \lambda'} = -2\operatorname{tr}\left[\Delta\boldsymbol{\varepsilon}_{m+1}\right]\left(\operatorname{tr}\left[\Delta\boldsymbol{\sigma}_{m+1}\right] - \lambda' \operatorname{tr}\left[\boldsymbol{I}\right] \operatorname{tr}\left[\Delta\boldsymbol{\varepsilon}_{m+1}\right] - 2\mu' \operatorname{tr}\left[\Delta\boldsymbol{\varepsilon}_{m+1}\right]\right) = 0\,, \\ \dfrac{\partial g(\lambda',\mu')}{\partial \mu'} = -4\left(\Delta\boldsymbol{\sigma}_{m+1} : \Delta\boldsymbol{\varepsilon}_{m+1} - \lambda' \operatorname{tr}\left[\Delta\boldsymbol{\varepsilon}_{m+1}\right] \operatorname{tr}\left[\Delta\boldsymbol{\varepsilon}_{m+1}\right] - 2\mu' \Delta\boldsymbol{\varepsilon}_{m+1} : \Delta\boldsymbol{\varepsilon}_{m+1}\right) = 0\,, \end{cases} \tag{C.38}$$

and the optimum solution $(\lambda^0_{m+1}, \mu^0_{m+1})$ found as

$$\begin{bmatrix} \lambda^0_{m+1} \\ \mu^0_{m+1} \end{bmatrix} = \begin{bmatrix} \operatorname{tr}\left[\boldsymbol{I}\right] \operatorname{tr}\left[\Delta\boldsymbol{\varepsilon}_{m+1}\right] & 2\operatorname{tr}\left[\Delta\boldsymbol{\varepsilon}_{m+1}\right] \\ \operatorname{tr}\left[\Delta\boldsymbol{\varepsilon}_{m+1}\right]^2 & 2\Delta\boldsymbol{\varepsilon}_{m+1} : \Delta\boldsymbol{\varepsilon}_{m+1} \end{bmatrix}^{-1} \begin{bmatrix} \operatorname{tr}\left[\Delta\boldsymbol{\sigma}_{m+1}\right] \\ \Delta\boldsymbol{\sigma}_{m+1} : \Delta\boldsymbol{\varepsilon}_{m+1} \end{bmatrix}. \tag{C.39}$$

A close inspection of the previous solution reveals two shortcomings of this self-consistent scheme: first, for pure shear loadings ($\operatorname{tr}[\Delta\boldsymbol{\varepsilon}] = \mathbf{0}$) the system of linear equations becomes undetermined and one of the two Lamé parameters must be estimated; and second, for hydrostatic loadings the system of linear equations also becomes undetermined due to the fact that both equations become linearly dependent.

Irrespective of the adopted self-consistent scheme, given that the reference material Lamé parameters are updated at each loading increment, the solution of the clustered Lippmann-Schwinger system of equilibrium equations summarized in Box C.2 must be enriched (see Section 4.3.2). Two important aspects shall be discussed: (1) the efficient update of the Green operator and (2) the coupling between the clustered Lippmann-Schwinger system of equilibrium equations and the regression-based self-consistent scheme.

In the first place, it is convenient to notice that the Green operator (see Equation (4.21)) can be rewritten as

$$\check{\boldsymbol{\Phi}}^0(\boldsymbol{\zeta}) = c_1(\lambda^0,\mu^0)\,\check{\boldsymbol{\Phi}}^0_1(\boldsymbol{\zeta}) + c_2(\lambda^0,\mu^0)\,\check{\boldsymbol{\Phi}}^0_2(\boldsymbol{\zeta})\,, \tag{C.40}$$

where the reference material independent components are defined as

$$(\check{\Phi}^0_1)_{klij}(\boldsymbol{\zeta}) = \frac{1}{\|\boldsymbol{\zeta}\|^2}\left(\delta_{ki}\zeta_j\zeta_l + \delta_{kj}\zeta_i\zeta_l + \delta_{li}\zeta_j\zeta_k + \delta_{lj}\zeta_i\zeta_k\right), \quad (\check{\Phi}^0_2)_{klij}(\boldsymbol{\zeta}) = \frac{\zeta_k\zeta_l\zeta_i\zeta_j}{\|\boldsymbol{\zeta}\|^4}\,, \tag{C.41}$$

and the associated coefficients as

$$c_1(\lambda^0,\mu^0) = \frac{1}{4\mu^0}\,, \quad c_2(\lambda^0,\mu^0) = -\frac{\lambda^0+\mu^0}{\mu^0(\lambda^0+2\mu^0)}\,. \tag{C.42}$$

This means that only the coefficients $c_1(\lambda^0,\mu^0)$ and $c_2(\lambda^0,\mu^0)$ must be recomputed in order to update the cluster interaction tensors, $\mathbf{T}^{(I)(J)}$. In other words, the expensive computation of the fourth-order Green operator components $\check{\mathbf{\Phi}}_1^0(\boldsymbol{\zeta})$ and $\check{\mathbf{\Phi}}_2^0(\boldsymbol{\zeta})$ must be carried out only once in the offline-stage, being these only linearly scaled by the coefficients $c_1(\lambda^0,\mu^0)$ and $c_2(\lambda^0,\mu^0)$ during the online-stage.

In the second place, given the interdependency between the solution of the clustered Lippmann-Schwinger system of equilibrium equations and the solution of the regression-based self-consistent scheme, Liu and coworkers (Liu et al., 2016) adopt a partitioned (or staggered) solution scheme where both problems are iteratively solved as described in Box C.3. The convergence of the self-consistent scheme can be evaluated through the iterative relative change of the reference material Lamé parameters, i.e.,

$$\epsilon_\lambda = \left| \frac{(\lambda^0)^{(k+1)} - (\lambda^0)^{(k)}}{(\lambda^0)^{(k)}} \right|, \qquad \epsilon_\mu = \left| \frac{(\mu^0)^{(k+1)} - (\mu^0)^{(k)}}{(\mu^0)^{(k)}} \right|, \tag{C.43}$$

where k is denoting a iteration of the self-consistent scheme.

Box C.3: Partitioned (or staggered) scheme adopted to solve a given loading increment $m+1$ of the infinitesimal strains clustered Lippmann-Schwinger system of equilibrium equations while updating the reference material Lamé parameters through a self-consistent scheme.

(i) Set initial guess for reference material Lamé parameters, λ^0_{m+1} and μ^0_{m+1}

(ii) Update tangent modulus of the reference homogeneous elastic material

$$\mathbf{D}^{e,0}_{m+1} = \lambda^0_{n+1}\boldsymbol{I}\otimes\boldsymbol{I} + 2\mu^0_{n+1}\mathbf{I}_s$$

(iii) Recompute the cluster interaction tensors by updating the Green operator coefficients

$$\mathbf{T}^{(I)(J)} = \frac{1}{f^{(I)}v_\mu}\int_{\Omega_{\mu,0}}\int_{\Omega_{\mu,0}} \chi^{(I)}(\boldsymbol{Y})\,\chi^{(J)}(\boldsymbol{Y}')\,\mathbf{\Phi}^0(\boldsymbol{Y},\boldsymbol{Y}')\,\mathrm{d}v'\mathrm{d}v,$$

$$\check{\mathbf{\Phi}}^0(\boldsymbol{\zeta}) = c_1(\lambda^0,\mu^0)\,\check{\mathbf{\Phi}}_1^0(\boldsymbol{\zeta}) + c_2(\lambda^0,\mu^0)\,\check{\mathbf{\Phi}}_2^0(\boldsymbol{\zeta})$$

(iv) Solve clustered Lippmann-Schwinger system of equilibrium equations (see Box C.2), without performing the incremental solution update when convergence is achieved

(v) Solve the self-consistent scheme optimization problem (see Problem C.3) and update the reference material Lamé parameters, λ^0_{m+1} and μ^0_{m+1}

(vi) Check for convergence

if (converged) then

- Update incremental solution (see Box C.2), $(\bullet)_{m+1} = (\bullet)^{(k)}_{m+1}$, and exit

else

- Proceed to step (ii)

C.6 Step 5: Macro-scale material response

Once the solution of the clustered Lippmann-Schwinger system of equilibrium equations is found, the macro-scale material response, i.e., the homogenized Cauchy stress tensor, can be computed by computational homogenization as[3]

$$\boldsymbol{\sigma}(\boldsymbol{X}) = \sum_{I=1}^{n_c} f^{(I)} \hat{\boldsymbol{\sigma}}_{\mu}^{(I)} . \tag{C.44}$$

In addition, if the SCA is employed to solve the micro-scale equilibrium problem of an implicit first-order strain-driven hierarchical multi-scale model (see Chapter 2), the solution of a macro-scale Newton-Raphson iteration requires the computation of the homogenized consistent tangent modulus of the CRVE (see Figure 2.4).

In view of the homogeneous far-field strain, $\boldsymbol{\varepsilon}_{\mu}^{0}$, introduced in the Lippmann-Schwinger integral equilibrium equation (see Section 4.3.2), the homogenized consistent tangent modulus of the CRVE at the loading increment $m+1$ is defined as

$$\overline{\mathbf{D}}_{m+1} = \frac{\partial \Delta \boldsymbol{\sigma}_{m+1}(\boldsymbol{X})}{\partial \Delta \boldsymbol{\varepsilon}_{\mu,\, m+1}^{0}} = \frac{\partial}{\partial \Delta \boldsymbol{\varepsilon}_{\mu,\, m+1}^{0}} \left(\sum_{I=1}^{n_c} f^{(I)} \Delta \hat{\boldsymbol{\sigma}}_{\mu,\, m+1}^{(I)} \right). \tag{C.45}$$

Applying the differentiation chain rule and noticing that the material consistent tangent modulus of the Ith cluster is defined as

$$\mathbf{D}_{m+1}^{(I)} = \frac{\partial \Delta \hat{\boldsymbol{\sigma}}_{\mu,\, m+1}^{(I)} \left(\Delta \boldsymbol{\varepsilon}_{\mu,\, m+1}^{(I)}, \boldsymbol{\beta}_m \right)}{\partial \Delta \boldsymbol{\varepsilon}_{\mu,\, m+1}^{(I)}}, \tag{C.46}$$

the CRVE homogenized consistent tangent modulus can be written as

$$\overline{\mathbf{D}}_{m+1} = \sum_{I=1}^{n_c} f^{(I)} \mathbf{D}_{m+1}^{(I)} : \mathbf{H}_{m+1}^{(I)}, \tag{C.47}$$

where $\mathbf{H}_{m+1}^{(I)}$ is the fourth-order strain concentration tensor of the Ith cluster,

$$\Delta \boldsymbol{\varepsilon}_{\mu,\, m+1}^{(I)} = \mathbf{H}_{m+1}^{(I)} : \Delta \boldsymbol{\varepsilon}_{\mu,\, m+1}^{0}, \quad \forall I = 1, 2, \ldots, , n_c \tag{C.48}$$

such that

$$\mathbf{H}_{m+1}^{(I)} = \frac{\partial \Delta \boldsymbol{\varepsilon}_{\mu,\, m+1}^{(I)}}{\partial \Delta \boldsymbol{\varepsilon}_{\mu,\, m+1}^{0}}, \quad \forall I = 1, 2, \ldots, n_c . \tag{C.49}$$

In order to compute $\mathbf{H}_{m+1}^{(I)}$ at the equilibrium state of the Ith cluster, it is possible to state that

$$\mathrm{d}\boldsymbol{R}_{m+1}^{(I)} = \frac{\partial \boldsymbol{R}_{m+1}^{(I)}}{\partial \Delta \boldsymbol{\varepsilon}_{\mu,\, m+1}^{(K)}} : \mathrm{d}\Delta \boldsymbol{\varepsilon}_{\mu,\, m+1}^{(K)} + \frac{\partial \boldsymbol{R}_{m+1}^{(I)}}{\partial \Delta \boldsymbol{\varepsilon}_{\mu,\, m+1}^{0}} : \mathrm{d}\Delta \boldsymbol{\varepsilon}_{\mu,\, m+1}^{0} = \mathbf{0}, \quad \forall I, K = 1, 2, \ldots, n_c , \tag{C.50}$$

[3] The computational homogenization can also be performed at every loading increment m of the micro-scale equilibrium problem with the purpose of extracting the homogenized stress-strain response.

where both $\partial \boldsymbol{R}_{m+1}^{(I)} / \partial \Delta \boldsymbol{\varepsilon}_{\mu,m+1}^{(K)}$ and $\partial \boldsymbol{R}_{m+1}^{(I)} / \partial \Delta \boldsymbol{\varepsilon}_{\mu,m+1}^{0}$ (see Equations (C.13) and (C.15)) are determined at the converged state. By assembling the previous equation for all material clusters $I = 1, 2, \ldots, n_{\mathrm{c}}$ and taking the associated matricial forms, one can readily establish the following system of linear equations,

$$\mathbf{M}\mathbf{S}_{m+1} = -\mathbf{Q}, \tag{C.51}$$

where $\mathbf{M}$ and $\mathbf{Q}$ contain the residual derivatives as

$$\mathbf{M} = \begin{bmatrix} \dfrac{\partial \boldsymbol{R}_{m+1}^{(1)}}{\partial \Delta \boldsymbol{\varepsilon}_{\mu,m+1}^{(1)}} & \cdots & \dfrac{\partial \boldsymbol{R}_{m+1}^{(1)}}{\partial \Delta \boldsymbol{\varepsilon}_{\mu,m+1}^{(n_{\mathrm{c}})}} \\ \vdots & \ddots & \vdots \\ \dfrac{\partial \boldsymbol{R}_{m+1}^{(n_{\mathrm{c}})}}{\partial \Delta \boldsymbol{\varepsilon}_{\mu,m+1}^{(1)}} & \cdots & \dfrac{\partial \boldsymbol{R}_{n+1}^{(n_{\mathrm{c}})}}{\partial \Delta \boldsymbol{\varepsilon}_{\mu,m+1}^{(n_{\mathrm{c}})}} \end{bmatrix}, \quad \mathbf{Q} = \begin{bmatrix} \dfrac{\partial \boldsymbol{R}_{m+1}^{(1)}}{\partial \Delta \boldsymbol{\varepsilon}_{\mu,m+1}^{0}} \\ \vdots \\ \dfrac{\partial \boldsymbol{R}_{m+1}^{(n_{\mathrm{c}})}}{\partial \Delta \boldsymbol{\varepsilon}_{\mu,m+1}^{0}} \end{bmatrix}, \tag{C.52}$$

and $\mathbf{S}_{m+1}$ contains the clusters strain concentration tensors as

$$\mathbf{S}_{m+1} = \begin{bmatrix} \dfrac{\partial \Delta \boldsymbol{\varepsilon}_{\mu,m+1}^{(1)}}{\partial \Delta \boldsymbol{\varepsilon}_{\mu,m+1}^{0}} & \cdots & \dfrac{\partial \Delta \boldsymbol{\varepsilon}_{\mu,m+1}^{(n_{\mathrm{c}})}}{\partial \Delta \boldsymbol{\varepsilon}_{\mu,m+1}^{0}} \end{bmatrix}^{T} \equiv \begin{bmatrix} \mathbf{H}_{m+1}^{(I)} & \cdots & \mathbf{H}_{m+1}^{(n_{\mathrm{c}})} \end{bmatrix}^{T}. \tag{C.53}$$

Given that (see Equation (C.15))

$$\frac{\partial \boldsymbol{R}_{m+1}^{(I)}}{\partial \Delta \boldsymbol{\varepsilon}_{\mu,m+1}^{0}} = -\mathbf{I}, \quad \forall I = 1, 2, \ldots, n_{\mathrm{c}}, \tag{C.54}$$

the solution of the previous system of linear equations shows that the strain concentration tensor of the Ith cluster is computed as

$$\mathbf{H}_{m+1}^{(I)} = \sum_{K=1}^{n_{\mathrm{c}}} \left(\mathbf{M}^{-1} \right)_{(I)(K)}, \quad \forall I = 1, 2, \ldots, n_{\mathrm{c}}. \tag{C.55}$$

C.7 Numerical application

C.7.1 Material characterization and macro-scale loadings

In order to illustrate the performance of the SCA, two types of periodic microstructures are considered following the original paper by Liu and coworkers (Liu et al., 2016):

- **2D microstructure.** Fiber-reinforced composite characterized by unidirectional circular cross-section fibers (phase 2, $f = 30\%$) randomly distributed and embedded in a matrix (phase 1, $f = 70\%$)[4] – see Figure C.4(a);
- **3D microstructure.** Particle-reinforced composite characterized by spherical particles (phase 2, $f = 20\%$) randomly distributed and embedded in a matrix (phase 1, $f = 80\%$) – see Figure C.4(b).

[4] This type of microstructure is suitable to be modeled in plane strain conditions by considering any transversal plane relative to the fibers direction.

The material properties adopted for each material phase are presented in Table C.1. The matrix is assumed elastoplastic with a von Mises associative flow rule and two types of isotropic strain hardening laws are considered, a piecewise linear hardening law and a power hardening law (see Figure C.5).

Remark.
Although the microstructure descriptors (e.g., material phases volume fraction and properties) are identical to the ones reported in Liu et al. (2016), the exact microstructures considered therein cannot be exactly reproduced in terms of spatial topology. Nonetheless, given that the numerical simulations are based on first-order homogenization formulations, a close agreement with the homogenized results reported in Liu et al. (2016) should be obtained.

Table C.1: Constitutive model and properties of fiber-reinforced and particle-reinforced composites' material phases. Notation: Young's Modulus (E), Poisson's ratio (ν), yield stress (σ_y).

Phase	Model	E(MPa)	ν	σ_y(MPa)
Matrix	von Mises (isotropic)	100	0.3	Figure C.5
Fibers/Particles	Elastic (isotropic)	500	0.19	-



(a) (b)

Figure C.4: Biphasic heterogeneous materials microstructures: (a) Fiber-reinforced composite (randomly distributed unidirectional circular cross-section fibers, $f = 30\%$) – 2D RVE; (b) Particle-reinforced composite (randomly distributed spherical particles, $f = 20\%$) – 3D RVE.

Two different sets of macro-scale constraints are enforced in the following sections. First, the two macro-scale strain-stress loading cases reported in Liu et al. (2016) are evaluated, namely[5]:

- uniaxial tension: $\begin{cases} [\varepsilon_{xx}, \varepsilon_{yy}, \varepsilon_{zz}, \varepsilon_{xy}, \varepsilon_{yz}, \varepsilon_{xz}] & = [5.0, -, -, -, -, -] \times 10^{-2}, \\ [\sigma_{xx}, \sigma_{yy}, \sigma_{zz}, \sigma_{xy}, \sigma_{yz}, \sigma_{xz}] & = [-, 0.0, 0.0, 0.0, 0.0, 0.0] \times 10^{-2}, \end{cases}$

[5]The notation '-' denotes that the prescribed component has a different nature between strain and stress.



(a) (b)

Figure C.5: Von Mises elastoplastic matrix isotropic strain hardening: (a) piecewise linear law; (b) power law. Notation: Yield stress (σ_y) and accumulated plastic strain ($\bar{\varepsilon}^p$).

- pure shear: $\begin{cases} [\varepsilon_{xx}, \varepsilon_{yy}, \varepsilon_{zz}, \varepsilon_{xy}, \varepsilon_{yz}, \varepsilon_{xz}] & = [-, -, -, 2.5, 2.5, 2.5] \times 10^{-2}, \\ [\sigma_{xx}, \sigma_{yy}, \sigma_{zz}, \sigma_{xy}, \sigma_{yz}, \sigma_{xz}] & = [0.0, 0.0, 0.0, -, -, -] \times 10^{-2}. \end{cases}$

Second, two macro-scale strain loading cases are considered and defined as

- uniaxial tension: $[\varepsilon_{xx}, \varepsilon_{yy}, \varepsilon_{zz}, \varepsilon_{xy}, \varepsilon_{yz}, \varepsilon_{xz}] = [5.0, 0.0, 0.0, 0.0, 0.0, 0.0] \times 10^{-2}$,
- pure shear: $[\varepsilon_{xx}, \varepsilon_{yy}, \varepsilon_{zz}, \varepsilon_{xy}, \varepsilon_{yz}, \varepsilon_{xz}] = [0.0, 0.0, 0.0, 2.5, 2.5, 2.5] \times 10^{-2}$.

Note that only the in-plane Oxy macro-scale strain and stress components are enforced in the 2D plane strain case. Moreover, all macro-scale loading constraints are prescribed in a total of 200 increments of equal magnitude.

C.7.2 Solution methods and error assessment

Two solution methods are considered in the numerical assessment presented in the following sections: a DNS solution, here adopted as the reference (or 'high-fidelity') solution, and a SCA solution following the original paper (Liu et al., 2016).

Concerning the DNS solution, two types of reference solutions are considered. In a first stage, where macro-scale strain-stress loading cases are enforced, the FEM DNS solution is taken from the SCA paper (Liu et al., 2016). In a second stage, where macro-scale strain loading cases are prescribed, the DNS solution is obtained with a FEM first-order hierarchical multi-scale model based on computational homogenization (see Chapter 2). This solution is carried out with LINKS (Large Strain Implicit Non-linear Analysis of Solids Linking Scales), an implicit multi-scale finite element Fortran code developed by the CM2S research group at the Faculty of Engineering of the University of Porto[6].

[6]Bernardo P. Ferreira is an active member of the CM2S research group, led by F.M. Andrade Pires, and one of the developers of LINKS. This motivated the choice of FEM as the DNS solution, as opposed to the choice of an external FFT-based homogenization solver. Despite the different fundamental basis of the solution, some preliminary studies showed a good agreement between both approaches under elasticity and elastoplasticity for a sufficiently refined mesh.

In turn, the SCA solution is obtained with CRATE (Clustering-based Nonlinear Analyses of Materials), an object-oriented Python program that performs multi-scale nonlinear analyses through clustering-based reduced-order models. The DNS linear elastic analyses required in the offline-stage of SCA are performed with the FFT-based homogenization basic scheme (see Appendix B), also implemented in CRATE. This program has been fully designed and implemented as part of this thesis and is thoroughly described in Chapter 5. Periodic boundary conditions are assumed and the following spatial discretizations are adopted following Liu et al. (2016): $n_v = 600 \times 600$ voxels for the fiber-reinforced composite 2D RVE and $n_v = 64 \times 64 \times 64$ voxels for the particle-reinforced composite 3D RVE[7]. The base clustering of both material phases is performed with the well-known K-Means clustering (standard Lloyds' algorithm) with 10 centroid initializations computed with K-Means++. This algorithm implementation is readily available from Scikit-learn, a Python module integrating a wide range of state-of-the-art machine-learning algorithms for medium-scale supervised and unsupervised problems Pedregosa et al. (2012).

Concerning the error assessment, the relative error, ϵ, is employed to compare the macro-scale homogenized response, being always defined as

$$\epsilon\,(\%) = \left| \frac{a_{\mathrm{SCA}} - a_{\mathrm{DNS}}}{a_{\mathrm{DNS}}} \right| \times 100\,, \tag{C.56}$$

where a denotes the scalar quantity of interest.

At last, unless otherwise stated, all the numerical simulations presented in this section are run with 1 CPU core in a machine with the specifications provided in Table C.2. Nonetheless, some third-party (low-level) packages may perform multi-processor computations at certain operations.

Table C.2: Specifications of the numerical testing machine.

CPU	Model	2× Intel Xeon E5-2650 v4
	Microarchitecture	Broadwell
	Base/Max Frequency	2.20/2.90 GHz
	Num. of cores/threads	24/48 (2 × 12/24)
	L1 Cache	718 KiB (2 × 384 KiB)
	L2 Cache	6 MiB (2 × 3 MiB)
	L3 Cache	60 MiB (2 × 30 MiB)
	Numerical features	SSE3 SSSE3 AVX2
Memory	Capacity	128 GB (8 × 16 GB)
	Specification	DDR4 @ 2400 MHz

[7] Whenever the FEM DNS solution is carried out with LINKS, the compatible regular finite element mesh is generated as described in Appendix D.

C.7.3 Clustering-based domain decomposition

Following the SCA's offline-stage steps described in Sections C.2, C.3 and C.4, both fiber-reinforced and particle-reinforced composites RVEs are compressed into CRVEs as illustrated in Figures C.6 and C.7. The clustering procedure is performed independently for each material phase and the degree of data compression is set proportional to the respective volume fractions. In the case of the fiber-reinforced composite ($f_1 = 70\%$, $f_2 = 30\%$) it is set as $n_{c,1}/n_{c,2} = 2$, while in the particle-reinforced composite ($f_1 = 80\%$, $f_2 = 20\%$) it is set as $n_{c,1}/n_{c,2} = 4$.



Figure C.6: Clustering-based domain decomposition (K-means clustering) of the fiber-reinforced composite RVE for different number of clusters. The ratio between the number of clusters of the matrix phase ($f = 70\%$) and the fiber phase ($f = 30\%$) is set as 2.

C.7.4 Macro-scale strain-stress loading constraints

The homogenized response of both fiber-reinforced and particle-reinforced composites under uniaxial and pure shear strain-stress loading constraints (see Section C.7.1) is presented in Figures C.8-C.11 for a different number of clusters. The relative error with respect to the DNS solution is also shown, being again emphasized that the DNS solution is taken from Liu et al. (2016) for topologically different microstructures and run in a different machine. For these reasons, a comparison between the local fields and between the different solutions computational times is left for the following section.

In the first place, it is possible to conclude that the SCA is able to capture the homogenized nonlinear elastoplastic behavior of both composites with a considerable model compression. Even for the cases with the highest number of clusters ($n_c = 315$), note that the number of degrees of freedom (1.263×10^3 and 1.896×10^3 in the 2D and 3D cases, respectively) is significantly less than in the FEM-based homogenization DNS solution (3.6×10^5 and 2.6×10^5



Figure C.7: Clustering-based domain decomposition (K-means clustering) of the particle-reinforced composite RVE for different number of clusters. The ratio between the number of clusters of the matrix phase ($f = 80\%$) and the particle phase ($f = 20\%$) is set as 4.

finite elements[8] in the 2D and 3D cases, respectively). After the initial linear elastic regime, where the error relative to the DNS solution is generally low, a sudden error spike coincident with the onset of the matrix plastic yielding is observed followed by a decrease to lower error values in the post yielding region. The aforementioned error spike is comprehensible and highlights one of the main limitations of the SCA – the ability to capture localized phenomena. Because the high-fidelity RVE is decomposed in a substantially lower number of finite subdomains (clusters based on the similarity of elastic mechanical response), the CRVE model cannot accurately capture the localized onset of the plastic yielding in these loading cases. As the plastic flow starts to diffuse in the matrix after the initial yielding, the error decreases following the same reasoning.

In the second place, it is clearly seen from the homogenized responses and the associated errors that the SCA predictions' accuracy increases as the number of clusters increases (degree of model reduction decreases). This result is expected since more information about the microstructure details is stored in the offline-stage (more refined clustering-based domain decomposition) and is readily available in the following online-stage to solve the micro-scale equilibrium problem. Of course that an increase in the number of clusters will also lead to an increase of the overall computational cost of the analysis. Nonetheless, this desirable characteristic of the SCA as a reduced-order model allows the analyst to choose a suitable degree of model compression to achieve the desired degree of accuracy – a tradeoff between accuracy and computational cost. Besides, it is truly remarkable that even when considering solely 3 and 5 clusters in the 2D and 3D CRVEs, the accuracy of the homogenized response in

[8] In Liu et al. (2016) it is not specified what type of elements are considered in the DNS FEM analyses. Assuming that standard quadratic elements (QUAD8 and HEXA20) are used due to the elastoplastic behavior, these finite element meshes result in approximatelly 2 million dofs and 3 million dofs, respectively.

the nonlinear elastoplastic regime is relatively reasonable given the massive degree of data compression. This aspect emphasizes the potential of performing a domain decomposition through a clustering procedure based on the local elastic strain concentration tensors.



(a) (b)

Figure C.8: Homogenized response of the fiber-reinforced composite under uniaxial tension strain-stress loading constraints obtained with SCA for a different number of clusters: (a) Homogenized stress; (b) Relative error with respect to the FEM DNS solution. (*) The DNS solution is taken from Liu et al. (2016).

In Tables C.3-C.6, the convergence of the Newton-Raphson iterations in the solution of the clustered Lippmann-Schwinger system of equilibrium equations is presented for the different numerical examples. Without any particular criterion, the (elastoplastic) macro-scale loading increment 100 and the CRVEs decomposed in $n_c = 315$ clusters are selected. Both tables show that the desired Newton-Raphson quadratic convergence rate is achieved in the solution of the clustered Lippmann-Schwinger system of equilibrium equations. This strongly suggests that the associated linearization is properly derived and implemented. In addition, the regression-based self-consistent scheme converged as well (see Equations (C.43)), thus leading to the convergence of the adopted partitioned solution scheme.

C.7.5 Macro-scale strain loading constraints

The homogenized response of both fiber-reinforced and particle-reinforced composites is presented in Figures C.12 and C.15 for a different number of clusters together with the FEM DNS solution obtained with LINKS and the associated relative error. In addition, qualitative comparisons of the local accumulated plastic strain field are illustrated in Figures C.14 and C.17. Concerning the efficiency of the SCA analyses, the computational time of the online-stage is compared against the FEM DNS solution time in Figures C.13 and C.16.

Concerning the homogenized responses of both fiber-reinforced and particle-reinforced composites, most commentaries made in the previous section apply here. Once again, it is clear that the accuracy of the homogenized response as the number of clusters increases, leading to overall errors below 1% for $n_c \gtrapprox 54$. With regard to the underlying local accumulated plastic



Figure C.9: Homogenized response of the fiber-reinforced composite under pure shear strain-stress loading constraints obtained with SCA for a different number of clusters: (a) Homogenized stress; (b) Relative error with respect to the FEM DNS solution. (*) The DNS solution is taken from Liu et al. (2016).

strain fields, both Figures C.14 and C.17 support the previous discussion on the ability of the SCA to capture localized phenomena. While for a low number of clusters the main plastic flow regions are not accurately captured because the domain decomposition is too coarse, these regions are predicted with greater accuracy as the number of clusters increases. Nonetheless, even for the highest number of clusters ($n_c = 315$), it is noticeable that the plastic flow bands are way more diffuse than those predicted in the FEM DNS analysis.

The trade-off between accuracy and computational cost is evidenced in Figures C.13 and C.16, with the SCA online-stage computational time increasing monotonically as the number of clusters increases (notice that the time scale is logarithmic). Together with the relative errors shown in Figures C.12(b) and C.15(b), these plots highlight the balance between accuracy and computational cost that must be made by the analyst. On one side, a lower number of clusters may lead to massive speedups compared with the DNS solution, but the solution may not be sufficiently accurate (accuracy lower bound). On the other side, a high number of clusters may yield highly accurate solutions but at the expense of prohibited computational times (computational cost upper bound). Also, as the computational time of the SCA analysis gets closer to the DNS time and the speedup becomes less significant (≈ 1), the use of the reduced-order model itself loses its meaning. For instance, if the analyst accepts an overall homogenized stress relative error below 1% in these numerical examples, a number of clusters around 50 would be a suitable choice: the fiber-reinforced composite SCA analysis with $n_c = 54$ took approximately 9 minutes while the DNS took almost 7 hours, and the particle-reinforced composite SCA analysis with $n_c = 55$ took around 34 minutes while the DNS took nearly 7 days.



Figure C.10: Homogenized response of the particle-reinforced composite under uniaxial tension strain-stress loading constraints obtained with SCA for a different number of clusters: (a) Homogenized stress; (b) Relative error with respect to the FEM DNS solution. (*) The DNS solution is taken from Liu et al. (2016).



Figure C.11: Homogenized response of the fiber-reinforced composite under pure shear strain-stress loading constraints obtained with SCA for a different number of clusters: (a) Homogenized stress; (b) Relative error with respect to the FEM DNS solution. (*) The DNS solution is taken from Liu et al. (2016).

Table C.3: Convergence table of the fiber-reinforced composite SCA analysis ($n_c = 315$) under uniaxial tension strain-stress loading constraints. Normalized equilibrium residual evolution at the different self-consistent scheme iterations during the macro-scale loading increment 100.

Macro-scale Loading	**Self-consistent Scheme**	**Lippmann-Schwinger Newton-Raphson**	
Increment	Iteration	Iteration	Norm. Eq. Res.
100	1	1	$0.7633 \times 10^{+02}$
		2	$0.9472 \times 10^{+00}$
		3	0.1009×10^{-02}
		4	0.1258×10^{-08}
	2	1	$0.4623 \times 10^{+00}$
		2	0.4344×10^{-05}
		3	0.1126×10^{-11}
	3	1	0.5408×10^{-01}
		2	0.5921×10^{-09}

Table C.4: Convergence table of the fiber-reinforced composite SCA analysis ($n_c = 315$) under pure shear strain-stress loading constraints. Normalized equilibrium residual evolution at the different self-consistent scheme iterations during the macro-scale loading increment 100.

Macro-scale Loading	**Self-consistent Scheme**	**Lippmann-Schwinger Newton-Raphson**	
Increment	Iteration	Iteration	Norm. Eq. Res.
100	1	1	$0.5580 \times 10^{+02}$
		2	$0.2094 \times 10^{+00}$
		3	0.1901×10^{-04}
		4	0.1052×10^{-11}
	2	1	0.5704×10^{-01}
		2	0.2707×10^{-07}

Table C.5: Convergence table of the particle-reinforced composite SCA analysis ($n_c = 315$) under strain-stress uniaxial loading constraints. Normalized equilibrium residual evolution at the different self-consistent scheme iterations during the macro-scale loading increment 100.

Macro-scale Loading	**Self-consistent Scheme**	**Lippmann-Schwinger Newton-Raphson**	
Increment	Iteration	Iteration	Norm. Eq. Res.
100	1	1	$0.7248 \times 10^{+02}$
		2	$0.8168 \times 10^{+00}$
		3	0.5443×10^{-03}
		4	0.3320×10^{-10}
	2	1	0.9874×10^{-01}
		2	0.1038×10^{-07}

Table C.6: Convergence table of the particle-reinforced composite SCA analysis ($n_c = 315$) under strain-stress pure shear loading constraints. Normalized equilibrium residual evolution at the different self-consistent scheme iterations during the macro-scale loading increment 100.

Macro-scale Loading	**Self-consistent Scheme**	**Lippmann-Schwinger Newton-Raphson**	
Increment	Iteration	Iteration	Norm. Eq. Res.
100	1	1	$0.8405 \times 10^{+02}$
		2	$0.4270 \times 10^{+00}$
		3	0.5917×10^{-04}
		4	0.3097×10^{-11}
	2	1	0.2031×10^{-01}
		2	0.4129×10^{-08}



Figure C.12: Homogenized response of the fiber-reinforced composite under uniaxial tension strain loading conditions obtained with SCA for a different number of clusters: (a) Homogenized stress; (b) Relative error with respect to the FEM DNS solution.



Figure C.13: SCA online-stage computational cost in the solution of the fiber-reinforced composite equilibrium problem under uniaxial tension strain loading conditions: (a) Comparison between the computational time of the SCA online-stage and the FEM DNS solution time; (b) Ratio between the computational time of the SCA online-stage and the FEM DNS solution time. The FEM DNS solution is obtained with a solver parallelization of 20 CPU cores.



Figure C.14: Local accumulated plastic strain field of the fiber-reinforced composite under uniaxial strain loading conditions. Comparison between the SCA solution for a different number of clusters and the FEM DNS solution.



Figure C.15: Homogenized response of the particle-reinforced composite under uniaxial tension strain loading conditions obtained with SCA for a different number of clusters: (a) Homogenized stress; (b) Relative error with respect to the FEM DNS solution.



(a) (b)

Figure C.16: SCA online-stage computational cost in the solution of the particle-reinforced composite equilibrium problem under uniaxial tension strain loading conditions: (a) Comparison between the computational time of the SCA online-stage and the FEM DNS solution time; (b) Ratio between the computational time of the SCA online-stage and the FEM DNS solution time. The FEM DNS solution is obtained with a solver parallelization of 20 CPU cores.



Figure C.17: Local accumulated plastic strain field of the particle-reinforced composite under uniaxial strain loading conditions. Comparison between the SCA solution for a different number of clusters and the FEM DNS solution.

Appendix D

Compatible FEM regular mesh and element averaging

In Clustering-based Reduced-Order Models (CROMs) whose solution procedure is partially computed in the discrete frequency domain, such as the Self-Consistent Clustering Analysis (SCA) method (Liu et al., 2016) and the Adaptive SCA (ASCA) (see Chapter 4), the RVE is usually discretized in a regular grid of pixels (2D) or voxels (3D). Given that the Finite Element Method (FEM) is sometimes selected as the direct numerical simulation (DNS) method to establish the reference solution, two essential procedures are required to perform a suitable transfer and/or comparison of data between both types of spatial discretizations: (1) the generation of a compatible regular finite element mesh and (2) a finite element volumetric field averaging. For instance, such circumstances arise when computing the offline-stage DNS solutions with FEM and performing quantitative comparisons between CROMs and FEM micro-scale fields solutions. The adopted procedures are briefly described in this Appendix.

D.1 Generation of compatible FEM regular mesh

The first procedure involves the generation of a finite element mesh compatible with the regular grid of pixels (2D) or voxels (3D). A simple way to achieve this is to convert the pixels (2D) and voxels (3D) into quadrilateral (2D) and brick (3D) finite elements, respectively (see Figure D.1). The suitable order and type of finite elements should be defined according to the problem under analysis.



Figure D.1: Conversion of a regular grid of pixels into a finite element mesh with quadrilateral 8-noded quadratic elements.

D.2 Element volumetric field averaging

The second procedure allows the transfer and/or comparison of data between both types of spatial discretizations. The integrations over the finite element domain are generally performed by means of the Gaussian Quadrature Method and the state variables are computed at a given set of Gauss sampling points. Because each pixel (2D) or voxel (3D) contains only one sampling point, the data from the different Gauss sampling points of the associated finite element must be 'compressed' in some way.

An element volumetric averaging procedure is proposed as follows: for a generic field $a_\mu(\boldsymbol{Y})$ and the local normalized domain Υ of the element, the volumetric average of $a_\mu(\boldsymbol{Y})$ among the Gauss sampling points of each element e is taken as

$$\bar{a}_{e,\mu} = \frac{1}{v_{e,\mu}} \sum_{i=1}^{n_{\text{gp}}} w_i \, a_\mu(\boldsymbol{\xi}_i) \, j(\boldsymbol{\xi}_i) \,, \tag{D.1}$$

where $v_{e,\mu}$ is the volume of the finite element, $\boldsymbol{\xi}_i$ and w_i, $i = 1,2,\ldots,n_{\text{gp}}$, are the positions and weights of the Gauss sampling points in the domain Υ, and $j(\boldsymbol{\xi})$ is the determinant of the mapping $(\boldsymbol{Y} : \Upsilon \rightarrow \Omega^{(e)})$ Jacobian (see Figure D.1).



Figure D.2: Element volumetric averaging as a means to transfer and/or compare data between a finite element mesh and a regular grid of pixels (2D) or voxels (3D).

Appendix E
Overview of Adaptive Finite Element Methods (AFEMs)

This Appendix aims to provide an overview of the main ingredients underlying the so-called Adaptive Finite Element Methods (AFEMs). Although such methods are not directly explored in this document, they provide a suitable background and valuable insights into adaptivity in computational solid mechanics. These are taken as a fundamental inspiration to the development of Adaptive Clustering-based Reduced-Order Models (ACROMs) (see Section 4.4).

E.1 Adaptivity, localization and strain softening

Adaptive methods were first introduced to finite element calculations in the pioneering work of Babuška and Rheinboldt in the late 70s (Babuška and Rheinboldt (1978), Babuška and Rheinboldt (1979)). In the following two decades, a great deal of work has been devoted to this topic in the context of solid mechanics, exploring adaptivity in static and dynamic equilibrium problems, involving infinitesimal and finite strains, and linear and nonlinear elastic and elasto-plastic constitutive behavior (e.g. Ladevèze and Oden (1998), Stein (2005), Zienkiewicz et al. (2013)). Nowadays, it is widely accepted that adaptive procedures are a standard and important tool for practical engineering analyses based on finite element computations (Díez et al. (1998), Zienkiewicz et al. (2013)).

For a large spectrum of applications, given that the quality of finite element solutions is closely tied to the discretization of the structural system (Wunderlich et al., 1998), adaptivity is deemed as an essential tool to obtain numerical solutions with a controlled accuracy (Huerta et al., 1999). The main idea underlying the most common adaptive procedures is simple: after choosing a given measure that describes the quality of the approximated solution over the domain, the spatial discretization (i.e., the finite element mesh) is adaptively refined where the approximate solution is less accurate.

The formal structure of adaptive finite element methods for linear elliptic problems is well understood from both mathematical and practical point of view, forming a solid foundation upon which effective and reliable adaptive techniques have been established (Perić et al., 1998a). In contrast, adaptivity in nonlinear problems involving history path-dependent constitutive behavior and/or finite strains poses greater challenges, namely in the definition of suitable error-related measures and a rigorous mathematical treatment. Besides the fact that convergence can never be guaranteed a priori, the nonuniqueness of the solution may arise and lead to a physically irrelevant solution even if numerical convergence occured (Zienkiewicz et al., 2014). When dealing with such problems, adaptive strategies are even more fundamental, given that a meaningful finite element solution may not be computed without them (Huerta et al., 1999).

In the context of elasto-plastic deformations, the loss of ellipticity of the boundary value problem may be due to several reasons, among which is the development of the so-called strain softening and localization (Rice (1976), Pietruszczak and Mróz (1981), Ortiz and Quigley (1991)). Localization of deformation refers to the emergence of narrow regions or bands in a structure where all further deformation tends to concentrate, in spite of the fact that the external loading follows a monotonic path (De Borst et al., 1993) (see Figure E.1). Once the localization takes

place, large strains may accumulate inside the band without substantially affecting the strains in the surrounding material (Hutchinson and Tvergaard (1980), Ortiz et al. (1987)), the later usually unloading elastically and behaving in a quasi-rigid manner. The localization phenomena are thus associated with displacement (e.g., sliding), strain and stress discontinuities (Zienkiewicz et al., 2014).



Figure E.1: Schematic illustration of problems involving strain softening and localization: (a) Rigid footing placed on an elasto-plastic embankment; (b) Uniaxial compression of plane strain elasto-plastic specimen with two circular openings. Arrows within the material denote (a) plastic flow and (b) plastic slip.

This phenomenon is observed for a wide range of materials (e.g., metals, alloys, polymers, rocks, soils), although the scale of localization, often associated with a 'band width', may differ by some orders of magnitude. Given that it has a detrimental effect on the integrity of the structure, it often acts as a direct precursor to structural failure and fracture mechanisms (De Borst et al., 1993). As noted in Ortiz et al. (1987) and De Borst et al. (1993), it is important to remark that the aforementioned localization occurs as the outcome of the constitutive behavior of the material. From a mechanical point of view, the driving forces behind this phenomena have their source in material instabilities such that the inner product of the stress rate and the strain rate is non-positive[1]. For instance, this particular stability criterion is violated when, in a standard uniaxial traction or compression test, the slope of the true axial strain-stress curve is negative – the so-called strain softening phenomenon (see Figure E.2).

One of the most well-known spurious effects related to the loss of ellipticity in finite element computations is the complete dependence of the approximate solution on the mesh refinement, i.e., the element size. In addition, it is observed that the localization bands exhibit a significant tendency to propagate along the mesh lines. This multitude of solutions is physically unacceptable and is often referred to as mesh sensitivity behavior. Given the importance of such problem in the failure analysis of structures and materials, an extensive body of literature has been and still is devoted to the appropriate treatment of this topic (e.g., Bazant and Mazars (1989), Wriggers and Simo (1990), Simo et al. (1993)). As expected, different approaches have been proposed to accurately solve problems involving strain localization and failure. Among these strategies are (i) the regularization (limit case of viscoplasticity) methods (e.g., Zienkiewicz and Cormeau (1974), De Borst et al. (1993)), (ii) non-local formulations (e.g., Bazant and Lin (1988), Bazant and Pijaudier-Cabot (1988), Reis et al. (2018)), (iii) gradient-enhanced models (e.g., de Borst et al. (1995), Peerlings et al. (1996), Geers et al. (1998),

[1] A discussion on the notion of stability in the context of elastic and inelastic mechanical processes can be found in Hill (1958) and De Borst et al. (1993).



Figure E.2: Strain softening in uniaxial compression of polycarbonate cylindrical specimen.

Kuhl et al. (2000)), (iv) phase-field fracture methods (e.g., Francfort and Marigo (1998), Bourdin et al. (2008), Miehe et al. (2010), Miehe et al. (2015a), Shahba and Ghosh (2019)), (v) concentrated discontinuities approaches (e.g., Oliver et al. (1993), Oliver et al. (1999)), (vi) extended finite element methods (XFEM) (e.g., Moës et al. (1999), Chessa et al. (2002), Moës and Belytschko (2002), Zi and Belytschko (2003)) and (vii) cohesive zone models (e.g., Hillerborg et al. (1976), Needleman (1987), Tvergaard (1990), Paggi and Reinoso (2017)).

Most of the previous strategies can be effectively coupled with adaptive finite element computations, nowadays regarded as a natural approach for the analysis of localization in strain softening materials (e.g., Ortiz et al. (1987), Pastor et al. (1991), Steinmann and Willam (1992), Belytschko and Tabbara (1993), De Borst et al. (1993), Peric et al. (1994), Zienkiewicz et al. (1995b), Zienkiewicz et al. (1995a)). The main reason is that the suitable handling of this phenomenon calls for a very fine mesh in the localization area that is, in general, not known a priori (Huerta et al., 1998).

E.2 Adaptive finite element methodologies

Adaptive finite element methods (AFEMs) have, in general, three main ingredients Huerta et al. (1998): (1) an error estimator or indicator, a measure which is employed to locate where there is a need for mesh refinement/de-refinement; (2) a remeshing criterion, which translates the output of the error analysis into adaptivity necessity and actual mesh parameters (e.g., minimum element size); and (3) a procedure to adapt the spatial interpolation, i.e., an algorithm able to increase or decrease the interpolation in a particular region of the computational domain. A brief overview of these ingredients is provided below, being the interested reader referred to the extensive literature in the topic (e.g., Ladevèze and Oden (1998), Ainsworth and Oden (2000), Stein (2005), Zienkiewicz et al. (2013)).

E.2.1 Error estimators and indicators

Both error estimators and error indicators consist of measures that may be used to assess the error, i.e., the difference between the exact solution and the finite element approximate solution of a given problem. The distinction between the nature of these quantities is described in Huerta et al. (1999) and is here adopted. On the one hand, error estimators approximate a measure

of the actual error in a given norm or behave as equivalent norms. On the other hand, error indicators are quantities that are chosen, in an ad hoc manner, as an indicator of the error, often based on heuristic considerations. However, these terms are sometimes used interchangeably in the literature and, in several cases, proposed error measures exhibit characteristics from both estimators and indicators.

As posed in Ladevèze and Nicolas (1998), in general path- and time-dependent nonlinear material problems, three error sources associated to the problem discretization must be distinguished: (i) the space discretization, associated with the computational domain decomposition and interpolation, (ii) the time discretization, related to the scheme employed to perform the time integration of the rate-dependent constitutive equations, and (iii) the iterative techniques used to solve the discrete nonlinear problem. Due to the path-dependency of the solution, the loading is usually applied in an incremental manner with an iterative linearization, using the Newton-Raphson process in each increment (Boroomand and Zienkiewicz, 1998). In the remainder of this Appendix, focus is given to the spatial discretization error, i.e., it is assumed that a suitable time integration is performed, and that the magnitude of the increments and tolerances of convergence are sufficiently small to make the remainder error sources secundary. This is in consonance with the majority of the literature devoted to the AFEMs.

The so-called a posteriori error estimators are of interest here, given that these extract information about the error of the approximate solution without invoking the often unknown exact solution. Although there are other types, a posteriori estimators may be classified into two major families: recovery-based estimators and residual-based estimators.

Recovery-based estimators were first introduced by Zienkiewicz and Zhu (Zienkiewicz and Zhu, 1987) and, as the name implies, are based on recovery methods. A recovery process denotes an improvement of the approximate solution accuracy by a posteriori treatment of the finite element data. With the recovered solution available, the main idea is to evaluate errors by replacing the exact solution values of quantities (e.g., displacements, strains, stresses), in general unknown, by the recovered values which are more accurate than the direct finite element solution (Zienkiewicz et al., 2013). The so-called Superconvergent Patch Recovery (SPR), proposed by Zienkiewicz and Zhu (Zienkiewicz and Zhu (1992a) Zienkiewicz and Zhu (1992b), Zienkiewicz and Zhu (1992c)) is one of the most successful recovery methods and takes advantage of the superconvergence property of the finite element solutions and/or the availability of optimal sampling points (Zienkiewicz et al., 2013). An extensive body of literature has been devoted to find proofs of mathematical convergence (e.g., Zhang (1996b), Zhang (1996a), Zhu and Zhao (2003)), proposing modifications in the recovery process (e.g., Wiberg et al. (1994), Blacker and Belytschko (1994), Ródenas et al. (2007), Díez et al. (2007), Carey and Carey (2011)), and exploring variants of the patch recovery process (e.g., Li and Wiberg (1994), Ubertini (2004), Benedetti et al. (2006), Huang and Yi (2010)). One of the variants takes the designation of Recovery by Equilibrium of Patches (REP) and has been proposed in Boroomand and Zienkiewicz (1997b) and Boroomand and Zienkiewicz (1997a). The main idea is to replace the generally discontinuous stress field in every element patch by a recovered system which is smooth and continuous. This variant is to some extent similar to that of Ladevèze and coworkers (Ladevèze and Leguillon (1983), Ladevèze et al. (1991)) who sought to establish a fully equilibrating stress field which can replace that of the finite element approximation (Zienkiewicz et al., 2013).

Most of the estimators that do not belong to the previous family fit into the so-called residual-based estimators. In order to estimate the error, these make use of the equilibrium residuals of the finite element approximation, either explicitly or implicitly. The most simple explicit residual-based estimators are based on the equilibrium residuals in the element interior and on the flux discontinuities at the element boundary, the later often named jump discontinuities (e.g., Babuška and Rheinboldt (1978), Kelly et al. (1983), Verfürth (1994),

Ainsworth and Oden (2000)). Some contributions were devoted to evaluate the relationship and equivalence between this type of estimators and the aforementioned recovery-based estimators (e.g., Zhu and Zienkiewicz (1990), Rodríguez (1994), Zhu (1997), Zhu and Zhang (1998), Picasso (2003)). In contrast, implicit residual-based estimators require the solution of an auxiliary boundary value problem for the approximate error, where the residuals of the finite element computation are placed as loadings. Among all the existing implicit residual-based estimators, the equilibrated residual estimator has been shown to be the most robust (Babuška et al. (1994a), Babuška et al. (1994b), Babuška et al. (1997), Zienkiewicz et al. (2013)). This type of estimator was first introduced in Bank and Weiser (1985) and later pursued in Ainsworth and Oden (1993). A key aspect underlying this approach is a proper recovery method, being an approach named recovery by element residuals proposed in Ladevèze and Leguillon (1983) and Kelly (1984), and followed in Ohtsubo and Kitamura (1992).

Other types of estimators involve the analysis of constitutive functionals (e.g., Ladevèze (1985), Ladevèze and Germain (1989), Ladevèze (1996), Gallimard et al. (1996), Ladevèze and Moës (1998)) or general error functionals derived by duality arguments (e.g., Eriksson and Johnson (1988), Johnson and Hansbo (1992), Becker and Rannacher (1997), Rannacher and Suttmeier (1998a)).

Comparisons between the numerical performance of recovery-based and residual-based estimators have been performed in several papers (e.g., Babuška et al. (1994a), Babuška et al. (1994b), Babuška et al. (1997), Carstensen and Alberty (2003)). In order to evaluate the accuracy of different error estimators and compare their robustness for different mesh and element patterns, the so-called effectivity index is defined as the ratio between the finite element approximate solution and the exact solution (Zienkiewicz et al., 2013). For instance, Zienkiewicz and Zhu (Zienkiewicz and Zhu, 1992b) established bounds for the effectivity index for all estimators based on recovery and concluded that if the recovered solution converges at a higher rate than the finite element solution, then asymptotically exact estimation is expected, i.e., an effectivity index of unity in the asymptotic limit. In fact, to be useful in practice, any error estimator should provide a tight bound with an effectivity index close to unity (Zienkiewicz et al., 2013). Another evaluation parameter called robustness index may be also employed to assess the robustness of any particular estimator (Babuška et al., 1997).

Although excellent estimators of errors exist today, much interest resides in demonstrating that these estimators are not only close but they are also bounded (Zienkiewicz et al., 2013). Upper bounds, of course, are mandatory for reliability, i.e., to ensure that the error is below a given tolerance (convergence). Lower bounds on the other hand, are indispensable for efficiency, i.e., to ensure that the required tolerance is achieved with a nearly minimal amount of computational cost (optimality) (Verfürth, 1998). Pioneering efforts in this topic are due to Fraejis de Veubeke (Zienkiewicz (2001), Veubeke (1966)), establishing bounds for the strain energy. Much later the establishment of bounds was revisited in the context of equilibrated residual-based estimators, being upper bounds first derived in Kelly (1984) and Ainsworth et al. (1997). Similar approaches were proposed in Ladevèze and Leguillon (1983), Bank and Weiser (1985) and Babuška et al. (1986), later compiled in Ainsworth and Oden (2000). Upper bounds can also be established for recovery-based estimators by enforcing equilibrium in the recovery procedures (Zienkiewicz et al., 2013), being one of such procedures proposed in Díez et al. (2007). However, most of these methodologies are effective when the basic quantity of interest is a simple one, such as the energy norm of linear problems or the strain energy. Given that defining errors in a pointwise local manner is generally not convenient and ocasionally misleading (e.g., point loads, stress singularities), various 'norms' representing some integral scalar quantity are often introduced to measure the error (Zienkiewicz et al., 2013).

However, different procedures arise when the quantity of interest is of different nature and/or is to be selectively evaluated in a given part of the structure, i.e., developing adaptive strategies by which localized goals of analysis can be solved with specified accuracy. For

instance, when dealing with localization phenomena and problems involving strain softening no global norms can be used effectively, and the energy norm is not in fact 'natural' (Zienkiewicz et al., 2014). Given the importance of such aspects in terms of engineering practicality, much effort is dedicated to discussing possibilities of computing bounds for such quantities of interest (Zienkiewicz et al., 2013). Pioneering work is due to several contributions of Babuška and Miller (Babuška and Miller (1984a), Babuška and Miller (1984b), Babuška and Miller (1984c)) that attempt to extend norms to other quantities of interest. In the late 90s and early 2000s, some authors pursued the same goals, namely Rannacher and coworkers (Becker and Rannacher (1996), Rannacher and Suttmeier (1997), Rannacher and Suttmeier (1998b), Becker and Rannacher (2001)), Oden and Prudhomme (Prudhomme and Oden (1999), Oden and Prudhomme (2001), Prudhomme et al. (2003)), and Patera and coworkers (Paraschivoiu et al. (1997), Peraire and Patera (1999), Maday et al. (1999), Machiels et al. (2001)). These contributions showed that an effective approach to estimate the error in a quantity of interest lies in duality, i.e., the solution of a dual problem on the same mesh as the original problem but with the quantities of interest given as loads (Zienkiewicz et al., 2013). Recent work has been exploring this and other approaches (e.g., Parés et al. (2006), Nochetto et al. (2009b), Ladevèze and Chamoin (2010), Richter (2010), Ainsworth and Rankin (2012)), but more research is needed to develop reliable and computationally efficient error estimates for a quantity of interest (Zienkiewicz et al., 2013).

Attending to their heuristic nature, a great variety of error indicators can be found in the literature and a structured classification similar to the error estimators is not available. Given that the choice of these measures is closely tied with the particular nature of the problem, error indicators are usually quantities that are already available in the finite element computation. For instance, in nonlinear solid mechanics, some common choices are the equivalent plastic strain or its gradient (Huerta et al., 1999). In Ortiz and Quigley (1991) is proposed an error indicator tailored to problems of strain localization and based on the variation of the solution within each element. The adaptive strategy consists of equidistributing the variation of the velocity field over of the elements of the mesh and an heuristic justification for the use of variations as indicators is advanced. A similar approach is proposed in Jin and Wiberg (1990), being the isolines of effective strain used to perform the mesh adaptivity. In the context of thermodynamics with internal variables, error indicators based on a generalized energy norm, the plastic dissipation functional and the rate of plastic work are explored by Perić and coworkers (e.g., Peric et al. (1994), Perić et al. (1998b)). These are found to be an appropriate choice to the adaptive solution of finite strains elastoplastic problems of practical interest. In the same context, Lee and Bathe (1994) propose pointwise error indicators for stresses and plastic strain increments. In order to deal effectively with material failure and the associated high gradients of the state variables, Perić et al. (1999) proposes error indicators based on rate of fracture indicators. From a geometrical point of view, the element aspect ratio or the distortion can be used, an approach that has proven to be effective when dealing with localization phenomena and discontinuities (e.g., Zienkiewicz and Wu (1994), Zienkiewicz et al. (1995a), Zienkiewicz et al. (1995b)). Some methodologies are based on the recognition that in certain directions the unknown function that we are attempting to model exhibits higher gradient or curvatures. A high degree of refinement can be achieved economically in high gradient areas with elongated elements with a suitable orientation (Zienkiewicz et al., 2014) (see Figure E.3). Due to the complexities arising in the error estimation on problems involving path-dependent nonlinear material behavior and, in particular, strain softening localization, several authors proposed various methodologies based on error indicators (e.g., Pastor et al. (1991), Yu et al. (1991), Peric et al. (1994), Pijaudier-Cabot et al. (1995), Stein et al. (1998)).

In Huerta et al. (1999) the advantages and limitations of error estimators and error indicators are summarized as follows. Error estimators provide an objetive and quantitative information about the error, allowing an objective control of the accuracy of the solution. In



Figure E.3: Rigid footing placed on elasto-plastic foundation. Mesh h-refinement and elements aspect ratio based on gradient and curvature of displacement norm.

addition, their definition is not restricted to the specifics of a given problem and so they have a wide range of applicability. On the downside, error estimators must be based on strong and rigorous mathematical foundations that may be cumbersome to derive for complex material behavior and phenomena. Moreover, their evaluation usually involves higher computational costs than error indicators. In turn, error indicators are attractive due to their simplicity and because they are generally based on physical and/or geometrically intuitive considerations that capture the specific features of the problem. These can be computed easily and efficiently, being often already readily available from the finite element solution process. The drawback, of course, is that they are heuristic in nature and only provide relative information about the error, i.e., only point out where the spatial discretization must be refined but no objective control over the solution accuracy. Furthermore, error indicators tend to be problem-dependent and may have to be calibrated.

E.2.2 Adaptive discretization procedures

Several procedures exist to perform the adaptivity of the spatial discretization of finite element solutions, being the main ideas underlying such procedures here highlighted. For a more detailed review of this topic the reader is referred to Zienkiewicz et al. (2013), where several numerical applications are discussed, and references therein.

Generally speaking, adaptivity may involve both refinement and de-refinement in different regions of the spatial domain. Although the procedures are similar in either case, the former has been further explored in the literature. There are essentially two main families of adaptive procedures in finite element computations: h-adaptivity and p-adaptivity.

Adaptivity in h-adaptive procedures is focused on the size of elements in the mesh, keeping the type of elements unchanged. In the regions where a more accurate solution is needed, the element size is decreased in order to enrich the spatial interpolation (mesh refinement). Likewise, in regions where the accuracy is exceeding the prescribed requirements, the element size may be increased to provide maximum economy in reaching the desired accuracy (mesh de-refinement). This family can be further divided into different strategies (see Figure E.4) that can be sorted by degree of adaptivity as follows:

- r-**refinement**. This approach attempts to relocate the nodes' position to obtain an optimal approximation, keeping the total number of nodes constant and the mesh connectivities constant. Nodes tend to be concentrated in the regions where a greater accuracy is most needed, being the mesh coarsened in other regions as a consequence. Despite being easy

to implement and computationally inexpensive, this approach is severely limited in terms of engineering practicality. Given that the number of dof and the mesh topology are fixed from the beginning, the optimal adaptivity is highly dependent on the initial mesh. In fact, it can be argued that such strategy is not a true refinement procedure as a prescribed accuracy cannot generally be reached (Zienkiewicz et al., 2013);

- **Element subdivision**. In terms of mesh refinement this approach is based on the division of existing elements into smaller ones and keeps the original elements boundaries intact. In path-dependent problems this facilitates the mapping of the state variables between different meshes (Wunderlich et al., 1998). Some difficulties may arise related to the placement of the new nodes that define the smaller elements. Cumbersome procedures may be required to deal with hanging nodes that only belong to one of the adjacent elements. Mesh de-refinement is theoretically possible through the fusion of adjacent elements but requires complex data management. Nevertheless, the method of element subdivision can be conveniently implemented and is quite widely used (Zienkiewicz et al., 2013);

- **Mesh regeneration**. This approach emerges as a suitable choice for many practical problems, namely those where the mesh is severely distorted throughout the analysis. As the name implies, mesh regeneration or remeshing consists of building an entirely new mesh where the element's sizes are adapted to fulfill the accuracy requirements. In this case, refinement and de-refinement in different regions of the domain may be simultaneously performed, and the results can be significantly improved. However, the complete mesh generation process can be computationally expensive and it requires a suitable transfer of data between the original and new mesh. For problems involving nonlinear material behavior, and plastic deformation in particular, issues related to the transfer of variables are crucially important for preserving the accuracy, robustness and convergence properties of the finite element solution. These problems are especially acute when dealing with finite strains, since the adaptive procedure must account for frequent substantial changes in geometry during the process (Perić et al. (1996), Perić et al. (1998b)).



Figure E.4: Schematic of the different h-refinement adaptive procedures in the analysis of a elasto-plastic perforated specimen (symmetry conditions) under uniaxial traction.

Adaptivity in p-adaptive procedures is focused on the order of the polynomial that defines each type of element, keeping the elements' size and boundaries unchanged. Therefore, in

the regions where a great accuracy is required, the polynomial order is increased to enrich the spatial interpolation (mesh refinement). Two different strategies may be identified within this family of adaptive procedures: a global one, where the polynomial order is increased uniformly throughout the whole domain; and a local one, in which the polynomial order is increased locally using hierarchical refinement (Zienkiewicz et al., 2013). Although for a given problem dimension the convergence to the true solution is more rapid with p-refinement, procedures may be more computationally expensive and no strategy has been developed that allows the prediction of the best refinement to be used to achieve a prescribed accuracy. In addition, despite being theoretically able to achieve very high accuracy levels, the improvement is heavily dependent on the initial mesh and special treatment is required to deal with hanging nodes that do not match two adjacent elements. For these reasons, p-adaptivity is typically combined with h-adaptivity.

Much work has been put forth in a efficienty coupling between h- and p-adaptive approaches, the so-called hp-adaptivity, where both the size of elements and the order of the associated polynomial are simultaneously changed (e.g., Babuška (1988), Guo and Babuška (1986a), Guo and Babuška (1986b), Demkowicz et al. (1989), Rachowicz et al. (1989), Zienkiewicz et al. (1989)). The suitable combination between the aforementioned error estimators/indicators and the adaptivity procedures described here is discussed in Huerta et al. (1999) to produce effective adaptive strategies for finite element computations.

E.2.3 Remeshing criteria

The remeshing criterion consists of a given strategy that, based on the error assessment, defines when, where and how much should the spatial discretization be adapted through a given procedure. It effectively establishes the bridge between the error estimators/indicators and the adaptive discretization procedure to complete the overall finite element adaptive strategy. Of course that such criterion is closely tied with the objectives to be achieved in a given problem and/or to the solution procedure, and many different approaches may be devised to accomplish the associated goals.

Some common criteria are here described in the context of h-refinement. In such adaptive discretization procedure, the remeshing criterion should provide information about the required element size throughout the mesh to fulfill the prescribed accuracy requirements. In general, at each adaptive stage of the analysis, the mesh generator should receive the specification of the mesh size defined at each nodal point and standard interpolation can be used to find the size of elements. In the regions where the error is not within the prescribed limits, a refinement process must be carried out by decreasing the local element size.

The criteria can be conveniently formulated through a given normalized error estimator or indicator, $\bar{r} = r/r_n$, where r_n is a given normalization measure, and a given limit parameter, θ, such that $\theta \in [0,1]$. In Nochetto et al. (2009a) are described some of the most popular strategies:

- **Maximum strategy**. Every element whose normalized error, $\bar{r}^{(e)}$, is greater than the prescribed limit, θ, is marked for refinement. For instance, the error, r, can be normalized by the maximum value found in the whole mesh, i.e., $r_n = \max_{\forall \Omega^{(e)} \in {}^h\Omega} \left\{ r^{(e)} \right\}$, or an equivalent global measure. The main idea is thus to perform the refinement where a given threshold value of the error is exceeded. A similar strategy can be employed to mark elements for de-refinement by considering a lower limit parameter instead (Belytschko and Tabbara, 1993);

- **Equidistribution strategy**. Similar to the maximum strategy, every element whose normalized error, $\bar{r}^{(e)}$, is greater than the prescribed limit, θ, is marked for refinement. Under determined conditions, it is possible to infer from the so-called Principle of Error Equidistribution that in an 'optimal mesh' the element error is equidistributed by the

elements (e.g., Ortiz and Quigley (1991), Nochetto et al. (2009a)). Therefore, the error, r, is in this case normalized by the average value over the whole mesh, i.e., $r_n = \text{avg}_{\forall \Omega^{(e)} \in {}^h\Omega} \left\{ r^{(e)} \right\}$;

- **Dörfler's strategy**. A group of elements holding the largest errors is marked for refinement if the group's total error normalized by the total mesh error is greater than the prescribed limit, θ.

A simple application of the equidistribution strategy can be found in Zienkiewicz et al. (2013), where the relative energy norm error is adopted as a suitable error estimator. A requirement is posed that the error in any element should be less than a given value when the error is normalized by the average energy norm of the solution. A refinement ratio, defined for each element based on such normalized error estimator, may then be effectively used in an element subdivision or mesh regeneration adaptive procedure. In the later, the element size distribution may be predicted by the asymptotic convergence rate criteria, establishing the relation between the required element size and the refinement ratio, current element size and polynomial order of approximation. Another application example can be found in Zienkiewicz et al. (1995a), where the maximum strategy is adopted and the error in each element is reduced to (or below) a specified value. In this case, an error indicator based on the gradient of the displacement field is employed to deal with strain localization. The minimum element size at each location is then made proportional to a ratio between the maximum gradient found in the whole domain and the local maximum gradient, being the element elongation also adapted from the displacement field curvatures.

In what concerns the general incremental schemes employed to solve nonlinear problems, the required strategy to couple the adaptive procedures with the standard solution cycles may also be considered as part of the remeshing criteria. Although in many papers such strategy is not even explicitly described, a great variety of methodologies can be found in the literature (e.g., Belytschko and Tabbara (1993), Lee and Bathe (1994), Ladevèze and Oden (1998), Nochetto et al. (2009a)).

Appendix F

Hyperelastic-based Constitutive Models through Kinematic Extension

Since the pioneering contributions of Simo and Ortiz (Simo (1985), Simo and Ortiz (1985)), hyperelastic-based formulations of finite plasticity have gained widespread acceptance and been extensively applied in finite strains elastoplastic analyses. Of particular importance to this thesis is a general class of isotropic hyperelastic-based finite strains elastoplastic constitutive models whose computational implementation solely requires a purely kinematic extension of the infinitesimal strains setting. The main hypotheses and key concepts are described in this Appendix, being the interested reader referred to de Souza Neto and coworkers (de Souza Neto et al. (2008) and references therein) where this class of constitutive models is thoroughly discussed[1]. For the sake of completeness, the coupling of such constitutive modeling approach and the finite strains SCA under multiplicative kinematics proposed in Chapter 4 is also detailed.

F.1 Preliminaries

The formulation of isotropic hyperelastic-based finite strains elastoplastic constitutive models is here defined in the spatial configuration, following the formalism of thermodynamics with internal variables and assuming an isothermal evolution. In addition, two aspects should be taken into account. First, the hypothesis of the elastoplastic multiplicative decomposition of the deformation gradient (Lee and Liu (1967), Lee (1969)), mathematically defined as

$$\boldsymbol{F} = \boldsymbol{F}^e \boldsymbol{F}^p \,, \tag{F.1}$$

where $\boldsymbol{F}^e$ and $\boldsymbol{F}^p$ are the elastic and plastic components of the deformation gradient, respectively. This assumption admits the existence of a local unstressed intermediate configuration in a local sense, defined by the plastic deformation gradient $\boldsymbol{F}^p$ or, equivalently, by a purely elastic unloading of the deformed configuration associated to $(\boldsymbol{F}^e)^{-1}$. Second, the adoption of the spatial logarithmic strain tensor as a convenient elastic strain measure, defined as

$$\boldsymbol{\varepsilon}^e = \ln[\boldsymbol{V}^e] = \frac{1}{2}\ln[\boldsymbol{B}^e] \,, \tag{F.2}$$

where $\boldsymbol{B}^e = \boldsymbol{F}^e(\boldsymbol{F}^e)^T$ is the left elastic Cauchy-Green strain tensor.

[1] Several fundamental concepts have also been conveniently introduced in Chapter 2.

F.2 Hyperelastic-based multiplicative elastoplastic models

Three main ingredients suffice to define the general isotropic hyperelastic-based multiplicative elastoplastic constitutive model:

- **Free-energy potential**. Firstly, a general free-energy potential can be defined as $\psi = \psi(\boldsymbol{\varepsilon}^e, \boldsymbol{\alpha})$, where $\boldsymbol{\alpha} \equiv \{\alpha_1, \alpha_2, \ldots, \alpha_k\}$ is the generic set of internal variables. Under isothermal conditions, satisfaction of the Clausius-Duhem inequality in the spatial configuration implies that

$$\boldsymbol{\tau} = \rho_0 \frac{\partial \psi(\boldsymbol{\varepsilon}^e, \boldsymbol{\alpha})}{\partial \boldsymbol{\varepsilon}^e}, \tag{F.3}$$

  where ρ_0 is the material reference density, thus the free-energy potential sets the constitutive law for the Kirchhoff stress tensor. Moreover, the set of thermodynamical forces conjugate to the internal variables, $\boldsymbol{A} \equiv \{A_1, A_2, \ldots, A_k\}$, can be defined as

$$A_i = \rho_0 \frac{\partial \psi(\boldsymbol{\varepsilon}^e, \boldsymbol{\alpha})}{\partial \alpha_i}. \tag{F.4}$$

- **Plastic yield function**. Secondly, a general yield function can be postulated as $\Phi = \Phi(\boldsymbol{\tau}, \boldsymbol{A})$ to define the onset of the plastic flow and, consequently, the set of admissible Kirchhoff stresses as

$$\mathscr{E} = \left\{ \boldsymbol{\tau} \,\middle|\, \Phi(\boldsymbol{\tau}, \boldsymbol{A}) \leq 0 \right\}. \tag{F.5}$$

- **Dissipation potential**. Lastly, a general plastic flow potential can be defined as $\Psi(\boldsymbol{\tau}, \boldsymbol{A})$. from which the plastic flow can be derived. Under plastic isotropic conditions, compatible with a zero plastic spin tensor, $\boldsymbol{W}^p = \boldsymbol{0}$, the evolution of the plastic deformation gradient yields

$$\boldsymbol{L}^p \equiv \dot{\boldsymbol{F}}^p \left(\boldsymbol{F}^p\right)^{-1} = \dot{\gamma} \left(\boldsymbol{R}^e\right)^T \frac{\partial \Psi(\boldsymbol{\tau}, \boldsymbol{A})}{\partial \boldsymbol{\tau}} \boldsymbol{R}^e, \tag{F.6}$$

  where $\boldsymbol{L}^p$ is the plastic velocity gradient, $\dot{\gamma}$ is the plastic multiplier and $\boldsymbol{R}^e$ is the elastic rotation tensor. The plastic flow can also be conveniently defined in terms of the spatial rate of plastic deformation, $\tilde{\boldsymbol{D}}^p \equiv \boldsymbol{R}^e \boldsymbol{D}^p (\boldsymbol{R}^e)^T$, as

$$\tilde{\boldsymbol{D}}^p = \dot{\gamma} \frac{\partial \Psi(\boldsymbol{\tau}, \boldsymbol{A})}{\partial \boldsymbol{\tau}}. \tag{F.7}$$

  In addition, the general evolution of the set of internal variables can be postulated as

$$\dot{\boldsymbol{\alpha}} = -\dot{\gamma} \frac{\partial \Psi(\boldsymbol{\tau}, \boldsymbol{A})}{\partial \boldsymbol{A}}. \tag{F.8}$$

  In both cases, the plastic multiplier must satisfy the constraints

$$\Phi(\boldsymbol{\tau}, \boldsymbol{A}) \leq 0, \qquad \dot{\gamma} \geq 0, \qquad \dot{\gamma} \Phi(\boldsymbol{\tau}, \boldsymbol{A}) = 0, \tag{F.9}$$

  compatible with the set of admissible Kirchhoff stresses (see Equation (F.5)).

Given that in the infinitesimal strains limit, $\boldsymbol{\varepsilon}^e$ and $\tilde{\boldsymbol{D}}^p$ reduce, respectively, to the standard infinitesimal elastic strain tensor and plastic strain rate, the previous finite strains constitutive model framework recovers the same functional format of general isotropic infinitesimal elastoplastic constitutive models. Besides the simplicity from a computational implementation point of view, this finite strains extension preserves important properties of the infinitesimal model such as isochoric plastic deformations, plastic incompressibility and the principle of maximum plastic dissipation under plastic associativity.

F.3 General elastic predictor/return-mapping algorithm

Given the history of the deformation gradient, $\boldsymbol{F}(t)$, over the time domain $t \in [t_0, t_f]$ and the initial values $\boldsymbol{F}^p(t_0)$ (or $\boldsymbol{F}^e(t_0)$) and $\boldsymbol{\alpha}(t_0)$, the Equations (F.6), (F.8) and (F.9) can be recast as a function of time, t, to establish the finite strains elastoplasticity initial value problem.

These differential equations may then be numerically integrated in a fully implicit scheme as follows: (i) the plastic flow rule (Equation (F.6)) is integrated with a backward exponential integrator; (ii) the internal variables evolution law (Equation (F.8)) is integrated with a backward Euler scheme; and (iii) the complementarity constraints (Equation (F.9)) are similarly integrated with a backward Euler scheme. By considering the elastoplastic multiplicative decomposition of the deformation gradient (Equation (F.1)) and the general time increment $[t_n, t_{n+1}]$, where F^e_n and $\boldsymbol{\alpha}_n$ are known, the incremental finite strains elastoplasticity initial value problem comes

$$\begin{cases} \boldsymbol{F}^e_{n+1} = \left(\boldsymbol{F}_\Delta\right)_{n+1} \boldsymbol{F}^e_n (\boldsymbol{R}^e_{n+1})^T \exp\left[-\Delta\gamma_{n+1} \left.\dfrac{\partial \Psi(\boldsymbol{\tau}, \boldsymbol{A})}{\partial \boldsymbol{\tau}}\right|_{n+1}\right] \boldsymbol{R}^e_{n+1} \\ \boldsymbol{\alpha}_{n+1} = \boldsymbol{\alpha}_n - \Delta\gamma_{n+1} \left.\dfrac{\partial \Psi(\boldsymbol{\tau}, \boldsymbol{A})}{\partial \boldsymbol{A}}\right|_{n+1} \end{cases} , \quad \{\boldsymbol{F}^e_{n+1}, \boldsymbol{\alpha}_{n+1}, \Delta\gamma_{n+1}\}, \tag{F.10}$$

subject to the constraints

$$\Phi(\boldsymbol{\tau}_{n+1}, \boldsymbol{A}_{n+1}) \leq 0, \qquad \Delta\gamma_{n+1} \geq 0, \qquad \Delta\gamma_{n+1}\, \Phi(\boldsymbol{\tau}_{n+1}, \boldsymbol{A}_{n+1}) = 0, \tag{F.11}$$

where $\left(\boldsymbol{F}_\Delta\right)_{n+1}$ is the prescribed incremental deformation gradient.

The structure of the previous problem allows the solution through a standard elastic predictor/return-mapping scheme. The elastic trial state assumes a non-dissipative hyperelastic strain increment ($\Delta\gamma_{n+1} = 0$) and is defined as $\{F^{e,\text{trial}}_{n+1}, \alpha^{\text{trial}}_{n+1}\} = \{\left(\boldsymbol{F}_\Delta\right)_{n+1} \boldsymbol{F}^e_n, \boldsymbol{\alpha}_n\}$. If the elastic trial state is plastically admissible, i.e., $\Phi(\boldsymbol{\tau}^{\text{trial}}_{n+1}, \boldsymbol{A}^{\text{trial}}_{n+1}) \leq 0$, then it is accepted as the actual state at t_{n+1}, otherwise the return-mapping system of equations must be solved,

$$\begin{cases} \boldsymbol{F}^e_{n+1} = \boldsymbol{F}^{e,\text{trial}}_{n+1} (\boldsymbol{R}^e_{n+1})^T \exp\left[-\Delta\gamma_{n+1} \left.\dfrac{\partial \Psi(\boldsymbol{\tau}, \boldsymbol{A})}{\partial \boldsymbol{\tau}}\right|_{n+1}\right] \boldsymbol{R}^e_{n+1} \\ \boldsymbol{\alpha}_{n+1} = \boldsymbol{\alpha}_n - \Delta\gamma_{n+1} \left.\dfrac{\partial \Psi(\boldsymbol{\tau}, \boldsymbol{A})}{\partial \boldsymbol{A}}\right|_{n+1} \\ \Phi(\boldsymbol{\tau}_{n+1}, \boldsymbol{A}_{n+1}) = 0 \end{cases} , \quad \{\boldsymbol{F}^e_{n+1}, \boldsymbol{\alpha}_{n+1}, \Delta\gamma_{n+1}\}. \tag{F.12}$$

By adopting the spatial logarithmic strain tensor (see Equation (F.2)) as the primary kinematic unknown, the return-mapping system of equations can be rewritten as

$$\begin{cases} \boldsymbol{\varepsilon}^e_{n+1} = \boldsymbol{\varepsilon}^{e,\text{trial}}_{n+1} - \Delta\gamma_{n+1} \left.\dfrac{\partial \Psi(\boldsymbol{\tau}, \boldsymbol{A})}{\partial \boldsymbol{\tau}}\right|_{n+1} \\ \boldsymbol{\alpha}_{n+1} = \boldsymbol{\alpha}_n - \Delta\gamma_{n+1} \left.\dfrac{\partial \Psi(\boldsymbol{\tau}, \boldsymbol{A})}{\partial \boldsymbol{A}}\right|_{n+1} \\ \Phi(\boldsymbol{\tau}_{n+1}, \boldsymbol{A}_{n+1}) = 0 \end{cases} , \quad \{\boldsymbol{\varepsilon}^e_{n+1}, \boldsymbol{\alpha}_{n+1}, \Delta\gamma_{n+1}\}. \tag{F.13}$$

Besides the considerable simplification in comparison with Equation (F.12), it is clear that the previous state update scheme elegantly recovers the same functional format of the backward elastic predictor/return-mapping algorithms of infinitesimal strains elastoplasticity.

F.4 Finite strains purely kinematical extension

The computational implementation of a general implicit constitutive model involves essentially two main procedures, the state update procedure and the consistent tangent modulus computation.

In view of Equation (F.13), it is remarkable that the finite strains state update procedure only requires additional kinematic pre- and post-processing operations relative to its infinitesimal strains counterpart. The computation of the elastic trial spatial logarithmic strain tensor is obtained as

$$\boldsymbol{\varepsilon}^{e,\text{trial}}_{n+1} = \frac{1}{2}\ln[\boldsymbol{B}^{e,\text{trial}}_{n+1}], \tag{F.14}$$

where the elastic trial left Cauchy-Green strain tensor is computed as

$$\boldsymbol{B}^{e,\text{trial}}_{n+1} \equiv \boldsymbol{F}^{e,\text{trial}}_{n+1}(\boldsymbol{F}^{e,\text{trial}}_{n+1})^T = \left(\boldsymbol{F}_\Delta\right)_{n+1}\boldsymbol{B}^e_n(\boldsymbol{F}_{\Delta,\,n+1})^T. \tag{F.15}$$

Once the infinitesimal strains format elastic predictor/return-mapping system of equations (see Equation (F.13)) is solved for $\boldsymbol{\varepsilon}^e_{n+1}$, $\boldsymbol{\alpha}_{n+1}$, and $\Delta\gamma_{n+1}$, the Kirchhoff stress tensor, $\boldsymbol{\tau}_{n+1}$, is computed by means of Equation (F.3) and the Cauchy stress tensor is also obtained from a purely kinematic operation as

$$\boldsymbol{\sigma}_{n+1} = \frac{1}{\det[\boldsymbol{F}_{n+1}]}\boldsymbol{\tau}_{n+1}. \tag{F.16}$$

Moreover, if the Hencky hyperelastic model is adopted (see Equation (4.161)), i.e., a linear relation between the Kirchhoff stress tensor and the elastic spatial logarithmic strain tensor, the actual functional format and computational implementation of the infinitesimal strains constitutive models are recovered.

Secondly, the general finite strains spatial tangent modulus, $\mathbf{a}$, is defined as (de Souza Neto et al., 2008)

$$\mathsf{a}_{ijkl} = \frac{1}{\det[\boldsymbol{F}]}\frac{\tau_{ij}}{\partial F_{km}}F_{lm} - \sigma_{il}\delta_{jk}, \tag{F.17}$$

where δ_{ij} is the discrete Dirac's delta. With the Kirchhoff stress tensor incremental constitutive function denoted as $\boldsymbol{\tau}_{n+1} = \hat{\boldsymbol{\tau}}(\boldsymbol{F}_{n+1}, \boldsymbol{\alpha}_n)$, it is possible to derive the spatial tangent modulus consistent with the elastic predictor/return-mapping state update as

$$\left(\mathsf{a}_{n+1}\right)_{ijkl} = \frac{1}{2\det[\boldsymbol{F}_{n+1}]}\left[\left(\mathbf{D}:\mathbf{L}:\mathbf{B}\right)_{n+1}\right]_{ijkl} - \left(\sigma_{n+1}\right)_{il}\delta_{jk}, \tag{F.18}$$

where $\mathbf{D} = \partial\hat{\boldsymbol{\tau}}(\boldsymbol{F}_{n+1}, \boldsymbol{\alpha}_n)/\partial\boldsymbol{\varepsilon}^{e,\text{trial}}_{n+1}$, $\mathbf{L}$ is the derivative of the tensor logarithm function[2] evaluated at $\boldsymbol{B}^{e,\text{trial}}_{n+1}$, $\mathbf{L} = \partial\ln[\boldsymbol{B}^{e,\text{trial}}_{n+1}]/\partial\boldsymbol{B}^{e,\text{trial}}_{n+1}$, and $\mathbf{B}$ is a fourth-order tensor defined as

$$\mathsf{B}_{ijkl} = \delta_{ik}(\boldsymbol{B}^{e,\text{trial}}_{n+1})_{jl} + \delta_{jk}(\boldsymbol{B}^{e,\text{trial}}_{n+1})_{il}. \tag{F.19}$$

Aside from the fourth-order tensor $\mathbf{D}$, which has the same functional format as the infinitesimal strains elastoplastic consistent tangent operator, the remainder terms are independent from the particular constitutive model adopted and are exclusively related to finite strains kinematics. Therefore, the computational implementation of the finite strains consistent tangent modulus does also result from a purely kinematic extension of its infinitesimal counterpart.

[2] The computation of isotropic symmetric tensor-valued functions of symmetric tensors is described by de Souza Neto and coworkers (de Souza Neto et al., 2008) (see Appendix A therein).

F.5 Coupling with finite strains SCA

In the finite strains SCA under multiplicative kinematics (see Section 4.7), the micro-scale equilibrium is formulated in the reference configuration and mathematically posed as a clustered Lippmann-Schwinger system of equilibrium equations defined by Equations (4.103) and (4.104). Some operations are required to establish a proper coupling between the just described hyperelastic-based multiplicative elastoplastic models and the finite strains SCA material state update of each cluster (see step (iii) of Box 4.2).

In the first place, it is necessary to compute the elastic trial spatial logarithmic strain tensor, $(\boldsymbol{\varepsilon}^{e,\text{trial}}_{\mu,m+1})^{(I)}$, $I = 1,2,\ldots,n_\text{c}$, according to Equation (F.14). In view of Equation (F.15), the elastic left Cauchy-Green strain tensor, $(\boldsymbol{B}^{e}_{\mu,m})^{(I)}$, can be computed from the known elastic logarithmic strain tensor as

$$(\boldsymbol{B}^{e}_{\mu,m})^{(I)} = \exp\left[2(\boldsymbol{\varepsilon}^{e}_{\mu,m})^{(I)}\right], \tag{F.20}$$

and the incremental deformation gradient tensor computed as

$$\left(\boldsymbol{F}_\Delta\right)^{(I)}_{\mu,m+1} = \boldsymbol{F}^{(I)}_{\mu,m+1}\left(\boldsymbol{F}^{(I)}_{\mu,m}\right)^{-1}, \tag{F.21}$$

where $\boldsymbol{F}^{(I)}_{\mu,m+1}$ is available from the global vector of unknowns (see Equation (4.104)) at each iteration (k) of the Newton-Raphson Method (see step (ix) of Box 4.2). Once the Ith cluster material state update is performed and the Kirchhoff stress tensor (see Equation (F.3)) is known, the first Piola-Kirchhoff stress tensor can be obtained as

$$\boldsymbol{P}^{(I)}_{\mu,m+1} = \boldsymbol{\tau}^{(I)}_{\mu,m+1}\left(\boldsymbol{F}^{(I)}_{\mu,m+1}\right)^{-T}. \tag{F.22}$$

At last, the material consistent tangent modulus of the Ith cluster can be computed from its spatial counterpart (see Equation (F.18)) as

$$\left(\mathsf{A}^{(I)}_{m+1}\right)_{ijkl} = \det\left[\boldsymbol{F}^{(I)}_{\mu,m+1}\right]\left(\mathsf{a}^{(I)}_{m+1}\right)_{ipkq}\left[\left(F^{(I)}_{\mu,m+1}\right)^{-1}\right]_{ql}\left[\left(F^{(I)}_{\mu,m+1}\right)^{-1}\right]_{pj}. \tag{F.23}$$

Page intentionally left blank

Appendix G
Constitutive Model Mathematical Derivations

This Appendix provides convenient mathematical derivations underlying the formulation of the visco-elastic-visco-plastic constitutive model presented in Chapter 6. In particular, it includes the time derivative of the visco-elastic potential, the linearization of the constitutive state update residual, and the consistent tangent modulus arising in a fully implicit computation.

G.1 Time derivative of visco-elastic potential

The visco-elastic potential adopted in the proposed visco-elastic-visco-plastic constitutive model is defined as

$$\psi^{ve} = \frac{1}{2\rho_0}\int_0^t\int_0^t \frac{\partial \boldsymbol{\varepsilon}^e(t^*)}{\partial t^*} : \mathbf{D}^{ve}(2t - t^* - t^\star) : \frac{\partial \boldsymbol{\varepsilon}^e(t^\star)}{\partial t^\star}\,\mathrm{d}t^*\,\mathrm{d}t^\star\,. \tag{G.1}$$

Application of the Leibniz integral rule to the integral with respect to $t^\star$ yields

$$\dot{\psi}^{ve} = \frac{1}{2\rho_0}\int_0^t \frac{\partial \boldsymbol{\varepsilon}^e(t^*)}{\partial t^*} : \mathbf{D}^{ve}(t - t^*) : \frac{\partial \boldsymbol{\varepsilon}^e(t)}{\partial t}\,\mathrm{d}t^* + \frac{1}{2}\int_0^t \frac{\partial}{\partial t}\left(\int_0^t \frac{\partial \boldsymbol{\varepsilon}^e(t^*)}{\partial t^*} : \mathbf{D}^{ve}(2t - t^* - t^\star) : \frac{\partial \boldsymbol{\varepsilon}^e(t)}{\partial t}\,\mathrm{d}t^*\right)\mathrm{d}t^\star\,. \tag{G.2}$$

Using the Leibniz integral rule with respect to t^* in the second-term of the right-hand side leads to

$$\begin{aligned}\dot{\psi}^{ve} = {} & \frac{1}{2\rho_0}\int_0^t \frac{\partial \boldsymbol{\varepsilon}^e(t^*)}{\partial t^*} : \mathbf{D}^{ve}(t - t^*) : \frac{\partial \boldsymbol{\varepsilon}^e(t)}{\partial t}\,\mathrm{d}t^* \\ & + \frac{1}{2\rho_0}\int_0^t \frac{\partial \boldsymbol{\varepsilon}^e(t)}{\partial t} : \mathbf{D}^{ve}(t - t^\star) : \frac{\partial \boldsymbol{\varepsilon}^e(t^\star)}{\partial t^\star}\,\mathrm{d}t^\star \\ & + \frac{1}{2\rho_0}\int_0^t\int_0^t \frac{\partial \boldsymbol{\varepsilon}^e(t^*)}{\partial t^*} : \frac{\partial \mathbf{D}^{ve}(2t - t^* - t^\star)}{\partial t} : \frac{\partial \boldsymbol{\varepsilon}^e(t^\star)}{\partial t^\star}\,\mathrm{d}t^*\,\mathrm{d}t^\star\end{aligned} \tag{G.3}$$

Attending to the similarity between the first two right-hand side terms (t^* and $t^\star$ are both dummy integral variables), and to the major symmetry of the visco-elasticity relaxation tensor, $\mathsf{D}^{ve}_{ijkl} = \mathsf{D}^{ve}_{klij}$, the time derivative of the visco-elastic potential can be finally established as

$$\dot{\psi}^{ve} = \frac{1}{\rho_0}\left(\int_0^t \mathbf{D}^{ve}(t-t^*) : \frac{\partial \boldsymbol{\varepsilon}^e(t^*)}{\partial t^*}\,\mathrm{d}t^*\right) : \dot{\varepsilon}^e + \frac{1}{2\rho_0}\int_0^t\int_0^t \frac{\partial \boldsymbol{\varepsilon}^e(t^*)}{\partial t^*} : \frac{\partial \mathbf{D}^{ve}(2t-t^*-t^\star)}{\partial t} : \frac{\partial \boldsymbol{\varepsilon}^e(t^\star)}{\partial t^\star}\,\mathrm{d}t^*\mathrm{d}t^\star . \quad \text{(G.4)}$$

G.2 Constitutive model linearization

G.2.1 State update residual derivative

Attending to the constitutive state update scalar nonlinear residual function defined as

$$R \equiv \eta_{n+1} - C_1\frac{C_2}{C_3} = 0\,, \quad \text{(G.5)}$$

where C_i, $i = 1,2,3$, are defined by Equations (6.102)-(6.105), application of the differentiation chain rule yields

$$\frac{\partial R}{\partial \eta_{n+1}} = 1 - \frac{\partial C_1}{\partial \eta_{n+1}}\frac{C_2}{C_3} - \frac{\partial C_2}{\partial \eta_{n+1}}\frac{C_1}{C_3} + \frac{\partial C_3}{\partial \eta_{n+1}}\frac{C_1 C_2}{C_3^2}\,, \quad \text{(G.6)}$$

where

$$\frac{\partial C_1}{\partial \eta_{n+1}} = \frac{1}{2}C_1 \exp\left[-\sqrt{\frac{3}{2}}\frac{h}{D_\infty}C_4\right] h\frac{\Delta t}{(\eta_{n+1}+\bar{G}_{n+1}\Delta t)^2}\left\|\boldsymbol{\tau}^{\text{trial}}_{\text{D},d,n+1}\right\|, \quad \text{(G.7)}$$

$$\frac{\partial C_2}{\partial \eta_{n+1}} = \sqrt{\frac{1}{2}}\frac{\bar{G}_{n+1}\Delta t}{(\eta_{n+1}+\bar{G}_{n+1}\Delta t)^2}\left\|\boldsymbol{\tau}^{\text{trial}}_{\text{D},d,n+1}\right\|, \quad \text{(G.8)}$$

$$\frac{\partial C_3}{\partial \eta_{n+1}} = \cosh\left(\frac{1}{\tau^*}\sqrt{\frac{1}{2}}\left(\frac{\eta_{n+1}}{\eta_{n+1}+\bar{G}_{n+1}\Delta t}\right)\left\|\boldsymbol{\tau}^{\text{trial}}_{\text{D},d,n+1}\right\|\right)\frac{1}{\tau^*}\sqrt{\frac{1}{2}}\frac{\bar{G}_{n+1}\Delta t}{(\eta_{n+1}+\bar{G}_{n+1}\Delta t)^2}\left\|\boldsymbol{\tau}^{\text{trial}}_{\text{D},d,n+1}\right\|. \quad \text{(G.9)}$$

G.2.2 Consistent tangent modulus derivatives

The visco-elastic-visco-plastic consistent tangent modulus of the formulated constitutive model can be expressed as

$$\mathbf{D}^{vevp}_{n+1} = \frac{\partial \hat{\boldsymbol{\tau}}}{\partial \boldsymbol{\varepsilon}_{n+1}} = \frac{\partial \boldsymbol{\tau}_{\text{D},n+1}}{\partial \boldsymbol{\varepsilon}_{n+1}} + \frac{\partial \boldsymbol{\tau}_{\text{H},n+1}}{\partial \boldsymbol{\varepsilon}_{n+1}}\,, \quad \text{(G.10)}$$

where $\boldsymbol{\tau}_{\text{D}}$ and $\boldsymbol{\tau}_{\text{H}}$ denote the driving and hardening components of the Kirchhoff stress tensor, respectively. The derivative of the driving component can be conveniently established as

$$\frac{\partial \boldsymbol{\tau}_{\text{D},n+1}}{\partial \boldsymbol{\varepsilon}_{n+1}} = \frac{\partial}{\partial \boldsymbol{\varepsilon}_{n+1}}\left(-p_{\text{D},n+1}\boldsymbol{I}\right) + \frac{\partial}{\partial \boldsymbol{\varepsilon}_{n+1}}\left(\boldsymbol{\tau}_{\text{D},d,n+1}\right), \quad \text{(G.11)}$$

where

$$\frac{\partial}{\partial \boldsymbol{\varepsilon}_{n+1}}\left(-p_{\text{D},n+1}\boldsymbol{I}\right) = K_\infty \boldsymbol{I}\otimes\boldsymbol{I}\,, \quad \text{(G.12)}$$

and

$$\frac{\partial \boldsymbol{\tau}_{\mathrm{D},n+1}}{\partial \boldsymbol{\varepsilon}_{n+1}} = \frac{\Delta t}{(\eta_{n+1}+\bar{G}_{n+1}\Delta t)^2}\,\boldsymbol{\tau}^{\mathrm{trial}}_{\mathrm{D},d,n+1} \otimes \left[\bar{G}_{n+1}\frac{\partial \eta_{n+1}}{\partial \boldsymbol{\varepsilon}_{n+1}} - \eta_{n+1}\frac{\partial \bar{G}_{n+1}}{\partial \boldsymbol{\varepsilon}_{n+1}}\right]$$

$$+ \frac{\eta_{n+1}}{\eta_{n+1}+\bar{G}_{n+1}\Delta t}\left[\sum_{i=1}^{n_{\mathrm{V}}}\left(\boldsymbol{\tau}_{\mathrm{D},i,n}\otimes\frac{\partial \hat{\omega}_{i,n+1}}{\partial \boldsymbol{\varepsilon}_{n+1}}\right) + 2(\boldsymbol{\varepsilon}_{d,n+1}-\boldsymbol{\varepsilon}_{d,n})\otimes\frac{\partial \bar{G}_{n+1}}{\partial \boldsymbol{\varepsilon}_{n+1}} + 2\bar{G}_{n+1}\mathbf{I}_d\right], \quad \text{(G.13)}$$

where $\boldsymbol{I}$ denotes the second-order identity tensor, $\mathbf{I}$ denotes the fourth-order identity tensor, and $\mathbf{I}_d$ denotes the fourth-order deviatoric identity tensor. The derivative of the hardening component comes

$$\frac{\partial \boldsymbol{\tau}_{\mathrm{H},n+1}}{\partial \boldsymbol{\varepsilon}_{n+1}} = H\left[\boldsymbol{\varepsilon}_{d,n+1}\otimes\frac{\partial \bar{\varepsilon}^p_{n+1}}{\partial \boldsymbol{\varepsilon}_{n+1}} + \bar{\varepsilon}^p_{n+1}\mathbf{I}_d\right]. \quad \text{(G.14)}$$

In the first place, at the equilibrium state t_{n+1}, where the constitutive state update residual function is null ($R=0$), it is possible to state that

$$\frac{\mathrm{d}R}{\mathrm{d}\boldsymbol{\varepsilon}_{n+1}} = \frac{\partial R}{\partial \eta_{n+1}}\frac{\partial \eta_{n+1}}{\partial \boldsymbol{\varepsilon}_{n+1}} + \frac{\partial R}{\partial \boldsymbol{\varepsilon}_{n+1}} : \frac{\partial \boldsymbol{\varepsilon}_{n+1}}{\partial \boldsymbol{\varepsilon}_{n+1}} = 0, \quad \text{(G.15)}$$

where $\partial R/\partial \eta_{n+1}$ is the constitutive state update residual derivative (see G.2.1) and the derivative of the viscosity with respect to the total strain can be obtained as

$$\frac{\partial \eta_{n+1}}{\partial \boldsymbol{\varepsilon}_{n+1}} = -\left(\frac{\partial R}{\partial \eta_{n+1}}\right)^{-1}\frac{\partial R}{\mathrm{d}\boldsymbol{\varepsilon}_{n+1}}. \quad \text{(G.16)}$$

Application of the differentiation chain rule yields

$$\frac{\partial R}{\partial \boldsymbol{\varepsilon}_{n+1}} = -\frac{\partial C_1}{\partial \boldsymbol{\varepsilon}_{n+1}}\frac{C_2}{C_3} - \frac{\partial C_2}{\partial \boldsymbol{\varepsilon}_{n+1}}\frac{C_1}{C_3} + \frac{\partial C_3}{\partial \boldsymbol{\varepsilon}_{n+1}}\frac{C_1 C_2}{C_3^2}, \quad \text{(G.17)}$$

and the required derivatives are given by

$$\frac{\partial C_1}{\partial \boldsymbol{\varepsilon}_{n+1}} = C_1\left[-\frac{\mu K_\infty}{\tau^*}\boldsymbol{I} - \frac{1}{2}\,h\exp\left(-\sqrt{\frac{3}{2}}\frac{h}{D_\infty}C_4\right)\right.$$

$$\left.\left[-\frac{\Delta t^2}{(\eta_{n+1}+\bar{G}_{n+1}\Delta t)^2}\left\|\boldsymbol{\tau}^{\mathrm{trial}}_{\mathrm{D},d,n+1}\right\|\frac{\partial \bar{G}_{n+1}}{\partial \boldsymbol{\varepsilon}_{n+1}} + \frac{\Delta t}{\eta_{n+1}+\bar{G}_{n+1}\Delta t}\frac{\partial\left\|\boldsymbol{\tau}^{\mathrm{trial}}_{\mathrm{D},d,n+1}\right\|}{\partial \boldsymbol{\varepsilon}_{n+1}}\right]\right]. \quad \text{(G.18)}$$

$$\frac{\partial C_2}{\partial \boldsymbol{\varepsilon}_{n+1}} = \sqrt{\frac{1}{2}}\left[-\frac{\Delta t}{(\eta_{n+1}+\bar{G}_{n+1}\Delta t)^2}\left\|\boldsymbol{\tau}^{\mathrm{trial}}_{\mathrm{D},d,n+1}\right\|\eta_{n+1}\frac{\partial \bar{G}_{n+1}}{\partial \boldsymbol{\varepsilon}_{n+1}}\right.$$

$$\left.+\frac{\eta_{n+1}}{\eta_{n+1}+\bar{G}_{n+1}\Delta t}\frac{\partial\left\|\boldsymbol{\tau}^{\mathrm{trial}}_{\mathrm{D},d,n+1}\right\|}{\partial \boldsymbol{\varepsilon}_{n+1}}\right] \quad \text{(G.19)}$$

$$\frac{\partial C_3}{\partial \boldsymbol{\varepsilon}_{n+1}} = \sqrt{\frac{1}{2}}\cosh\left(\frac{1}{\tau^*}\sqrt{\frac{1}{2}}\frac{\eta_{n+1}}{\eta_{n+1}+\bar{G}_{n+1}\Delta t}\left\|\boldsymbol{\tau}^{\mathrm{trial}}_{\mathrm{D},d,n+1}\right\|\right)$$

$$\left[-\frac{\Delta t}{(\eta_{n+1}+\bar{G}_{n+1}\Delta t)^2}\left\|\boldsymbol{\tau}^{\mathrm{trial}}_{\mathrm{D},d,n+1}\right\|\eta_{n+1}\frac{\partial \bar{G}_{n+1}}{\partial \boldsymbol{\varepsilon}_{n+1}} + \frac{\eta_{n+1}}{\eta_{n+1}+\bar{G}_{n+1}\Delta t}\frac{\partial\left\|\boldsymbol{\tau}^{\mathrm{trial}}_{\mathrm{D},d,n+1}\right\|}{\partial \boldsymbol{\varepsilon}_{n+1}}\right]. \quad \text{(G.20)}$$

In the second place, the derivative of the norm of the deviatoric trial predictor driving Kirchhoff stress tensor with respect to total strain is obtained as

$$\frac{\partial \left\| \boldsymbol{\tau}^{\text{trial}}_{\text{D},d,n+1} \right\|}{\partial \boldsymbol{\varepsilon}_{n+1}} = \frac{\partial \left\| \boldsymbol{\tau}^{\text{trial}}_{\text{D},d,n+1} \right\|}{\partial \boldsymbol{\tau}^{\text{trial}}_{\text{D},d,n+1}} : \frac{\partial \boldsymbol{\tau}^{\text{trial}}_{\text{D},d,n+1}}{\partial \boldsymbol{\varepsilon}_{n+1}} = \frac{\boldsymbol{\tau}^{\text{trial}}_{\text{D},d,n+1}}{\left\| \boldsymbol{\tau}^{\text{trial}}_{\text{D},d,n+1} \right\|} : \frac{\partial \boldsymbol{\tau}^{\text{trial}}_{\text{D},d,n+1}}{\partial \boldsymbol{\varepsilon}_{n+1}}, \tag{G.21}$$

where

$$\frac{\partial \boldsymbol{\tau}^{\text{trial}}_{\text{D},d,n+1}}{\partial \boldsymbol{\varepsilon}_{n+1}} = \sum_{i=1}^{n_{\text{V}}} \left(\boldsymbol{\tau}_{\text{D},i,n} \otimes \frac{\partial \hat{\omega}_{i,n+1}}{\partial \boldsymbol{\varepsilon}_{n+1}} \right) + 2(\boldsymbol{\varepsilon}_{d,n+1} - \boldsymbol{\varepsilon}_{d,n}) \otimes \frac{\partial \bar{G}_{n+1}}{\partial \boldsymbol{\varepsilon}_{n+1}} + 2\bar{G}_{n+1} \mathbf{I}_d \,. \tag{G.22}$$

In the third place, the derivative of the accumulated plastic strain with respect to total strain yields

$$\frac{\partial \bar{\varepsilon}_{n+1}}{\partial \boldsymbol{\varepsilon}_{n+1}} = \frac{1}{3}\sqrt{\frac{3}{2}} \left[- \frac{\Delta t}{(\eta_{n+1} + \bar{G}_{n+1}\Delta t)^2} \left\| \boldsymbol{\tau}^{\text{trial}}_{\text{D},d,n+1} \right\| \left(\frac{\partial \eta_{n+1}}{\partial \boldsymbol{\varepsilon}_{n+1}} + \frac{\partial \bar{G}_{n+1}}{\partial \boldsymbol{\varepsilon}_{n+1}} \Delta t \right) \right.$$

$$\left. + \frac{\Delta t}{\eta_{n+1} + \bar{G}_{n+1}\Delta t} \frac{\partial \left\| \boldsymbol{\tau}^{\text{trial}}_{\text{D},d,n+1} \right\|}{\partial \boldsymbol{\varepsilon}_{n+1}} \right]. \tag{G.23}$$

At last, it remains to determine the visco-elasticity-related derivatives,

$$\frac{\partial \hat{\omega}_{i,n+1}}{\partial \boldsymbol{\varepsilon}_{n+1}} = \frac{\Delta t}{g^2_{i,n+1}} \exp\left[- \frac{\Delta t}{g_{i,n+1}} \right] \frac{\partial g_{i,n+1}}{\partial \boldsymbol{\varepsilon}_{n+1}}, \tag{G.24}$$

and

$$\frac{\partial \bar{G}_{n+1}}{\partial \boldsymbol{\varepsilon}_{n+1}} = \sum_{i=1}^{n_{\text{V}}} \left[\frac{G_i}{\Delta t} \left(1 - \exp\left[- \frac{\Delta t}{g_{i,n+1}} \right] \right) \frac{\partial g_{i,n+1}}{\partial \boldsymbol{\varepsilon}_{n+1}} - G_i \frac{g_{i,n+1}}{\Delta t} \frac{\partial \hat{\omega}_{i,n+1}}{\partial \boldsymbol{\varepsilon}_{n+1}} \right], \tag{G.25}$$

where

$$\frac{\partial g_{i,n+1}}{\partial \boldsymbol{\varepsilon}_{n+1}} = -g_{T,i}\, \lambda_{g,i}\, (\dot{\varepsilon}^{\text{eq}})^{-(\lambda_{g,i}+1)} \frac{\partial \dot{\varepsilon}^{\text{eq}}_{n+1}}{\partial \boldsymbol{\varepsilon}_{n+1}} \tag{G.26}$$

with

$$\frac{\partial \dot{\varepsilon}^{\text{eq}}_{n+1}}{\partial \boldsymbol{\varepsilon}_{n+1}} = \frac{1}{\Delta t}\sqrt{\frac{2}{3}} \frac{\Delta \boldsymbol{\varepsilon}_{n+1}}{\left\| \boldsymbol{\varepsilon}_{n+1} \right\|}. \tag{G.27}$$

Substitution of the previous results on the Kirchhoff stress tensor derivatives (see Equations (6.116) and (6.117)) completes the closed-form of visco-elastic-visco-plastic consistent tangent modulus.

Appendix H
Constitutive material properties parametric evaluation

The formulated constitutive model accounts for a set of material properties that have a well-defined physical influence on each stage of the intrinsic visco-elastic-visco-plastic material response. To illustrate this distinctive feature, a parametric evaluation is performed through systematic numerical analyses comprising the true stress-true strain uniaxial compressive numerical response of polycarbonate (PC) for $\dot{\varepsilon} = 0.001\,\mathrm{s}^{-1}$ at $T = 25°\mathrm{C}$. The same computational setting described in Section 6.5.1 is adopted here. Without any loss of generality, the material properties calibrated from the uniaxial compression experimental results conducted by Mulliken (Mulliken and Boyce, 2006) are taken as reference (see Table 6.2). The parametric evaluation results are conveniently compiled in Table H.1.

Table H.1: Parametric evaluation of the finite strain visco-elastic-visco-plastic constitutive model's material properties. True stress-true strain uniaxial compressive numerical response of PC for $\dot{\varepsilon} = 0.001\,\mathrm{s}^{-1}$ at $T = 25°\mathrm{C}$. Reference constitutive material properties are provided in Table 6.2.

Category	**Properties**	**Figure**
Elastic	E_∞	H.1
Visco-elastic	G_1, g_1	H.2
Yielding	ΔH, A_0, v^*, μ	H.3
Post-yielding	h, D_∞, H	H.4



Figure H.1: Influence of long-term Young's modulus, E_∞, in the true stress-true strain uniaxial compressive numerical response of PC for $\dot{\varepsilon} = 0.001\,\mathrm{s}^{-1}$ at $T = 25°\mathrm{C}$. Reference constitutive material properties are provided in Table 6.2.



Figure H.2: Influence of visco-elastic properties in the true stress-true strain compressive numerical response of PC for $\dot{\varepsilon} = 0.001\,\mathrm{s}^{-1}$ at $T = 25°\mathrm{C}$: (a) Visco-elastic shear modulus, G_1; (b) Visco-elastic relaxation time, g_1. Reference constitutive material properties are provided in Table 6.2.



Figure H.3: Influence of yielding properties in the true stress-true strain compressive numerical response of PC for $\dot{\varepsilon} = 0.001\,\mathrm{s}^{-1}$ at $T = 25°\mathrm{C}$: (a) Activation energy, ΔH; (b) Fundamental vibration temperature factor, A_0; (c) Shear activation volume, υ^*; (c) Pressure coefficient, μ^*. Reference constitutive material properties are provided in Table 6.2.



Figure H.4: Influence of post-yielding (strain softening and strain hardening) properties in the true stress-true strain compressive numerical response of PC for $\dot{\varepsilon} = 0.001\,\mathrm{s}^{-1}$ at $T = 25°\mathrm{C}$: (a) Softening slope, h; (b) Softening saturation, D_∞; (c) Hardening modulus, H. Reference constitutive material properties are provided in Table 6.2.